

UNCLASSIFIED

AD 410357

DEFENSE DOCUMENTATION CENTER

FOR

SCIENTIFIC AND TECHNICAL INFORMATION

CAMERON STATION, ALEXANDRIA, VIRGINIA



UNCLASSIFIED

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

4-63-4-3

CATALOGED BY DDC 410357
AS AD No. _____

410357

OFFICE OF NAVAL RESEARCH

TECHNICAL REPORT


NO. 5

Contract Nonr-3707(00)

Effect of Impurities on the Electrical Resistivity
Increase During Elongation of Cadmium at 78°K

F. R. Stevenson and H. R. Peiffer

RIAS
7212 Bellona Avenue
Baltimore 12, Maryland



July, 1963

Reproduction in whole or in part is permitted for any
purpose of the United States Government.

Introduction

Observations have been made that the electrical resistivity of metals increases during plastic deformation¹. The increase is associated with changes in the concentration of point, line and planar defects. Further experiments have demonstrated that prior deformation and recovery² as well as impurity concentration³ affect the slope of the resistivity-elongation curves. It is the purpose of this report to present some data obtained on cadmium containing impurities. The influence of lead, magnesium and copper, in particular, are discussed.

Experimental Procedure and Results

Polycrystalline cadmium wire which for most experiments was 1 mm in diameter was obtained in various stages of purity as indicated in Table I. All specimens were annealed in argon one hour at 100°C, cooled, chemically polished as indicated in previous reports⁵, and mounted on the deformation apparatus described elsewhere⁵. Cadmium wires were then resistance welded to the specimen approximately 10 cm apart to serve as potential leads. The total length of specimen was approximately 14 cm. The specimens were deformed in liquid nitrogen and the resistance change was measured potentiometrically as a function of elongation strain as determined by calibrating the cross head movement with a direct measurement of increase of length by means of a traveling microscope. A dummy specimen in the liquid nitrogen served as measure of bath temperature fluctuations. A more detailed description of the experimental technique is available in reference 5.

Assuming constant volume during deformation the fractional resistivity change, $\Delta\rho/\rho_0$, may be calculated from

$$\frac{\Delta\rho}{\rho_0} + 1 = \frac{R}{R_0} \frac{1}{(1+\epsilon)^2}$$

where R_ϵ is the resistance at strain ϵ and R_0 the initial resistance.

The results of the deformation experiments at liquid nitrogen are shown in Figure 1. The closed and open squares represented by curves A and B are data on the same 59 Cd specimen measured while the load was on and after the load was removed, respectively. Part of the difference between A and B can be attributed to the elastic recovery which is estimated to be less than 0.1%. However, the greater part of the difference is undoubtedly due to the presence of the stress and its subsequent effect on the scattering of conduction electrons. It can be seen that both A and B show a linear dependence on strain. The data for cadmium doped with Cu, Pb and Mg also fall on curve B although the cadmium containing Pb shows some deviation. Curve C shows some results for some unpublished data obtained earlier in this laboratory for cadmium of commercial purity. These latter specimens were 5 mm in diameter and their resistance was measured using a Kelvin Double Bridge. Only one point of this data is shown on Figure 1. Other data obtained from this experiment indicate a linear behavior to approximately 13 percent elongation.

Curve C represents the average data of 49 cadmium of data obtained from eighteen different specimens. The deviation from the average value noted on the plot is insignificant.

Discussion

It is interesting to note that the addition of slight amounts of copper has very little influence on the ρ vs ϵ curves over what is observed for high purity cadmium. Additional impurities such as magnesium, at least at a concentration of 1000 ppm, shows no effect. Lead, however, does affect the slope of these curves. At very low concentrations the slope is what is expected for high purity cadmium or cadmium containing some copper and/or magnesium. As the lead concentration increases, however, the slope abruptly drops off and then slowly increases toward the high purity slope as the lead concentration approaches 1000 ppm.

The effect of other impurities such as silicon, iron, silver and aluminum is not very clear. Nevertheless, the 49 cadmium contains all of these elements and does have the lowest ρ vs ϵ slope. Whether it is primarily the lead or these other elements that is influencing this behavior must wait further study.

It is recognized that impurities in copper and other metals influence defect formation such as stacking faults. It can be speculated that the behavior noted in cadmium is associated with twin formation, stacking faults, influence of impurities on preferred orientation and the like. Obviously, a more complete study is necessary to elucidate this phenomenon.

Table I

Emission Spectrograph Analysis of Cadmium Impurities (ppm)

Sample Impurity	69 Cd +1000ppm Pb	69 Cd +1000ppm Mg	69 Cd + 10 ppm Cu	Commercial Cd	49 Cd	59 Cd
Pb	1000	<1	<1	100	3	<1
Mg	<1	1000	<1	<1	10	<1
Si	<1	<1	<1	<1	10	<1
Fe	<1	<1	<1	<1	10	<1
Cu	10	10	10	10	3	<1
Ag	<1	<1	<1	3	10	<1
Al					10	
Total Impurities (Nominal)	1000ppm Pb 10ppm Cu	1000ppm Mg 10ppm Cu	10 ppm Cu	110 ppm	56 ppm	1 ppm

Slope approx.	<3.4	3.4	3.4	1.8	1.2	3.4

