AD647054

(20)

U. S. NAVAL AIR ENGINEERING CENTER

PHILADELPHIA, PENNSYLVANIA

AERONAUTICAL MATERIALS LABORATORY

REPORT NO. NAEC-AML-2536 DATE 5 December 1966

OCEANOGRAPHIC EFFECTS ON PLASTIC ENGINEERING MATERIALS

ASSIGNMENT 12 ~2(1D) UNDER
AIRTASK A32 523 001/200 1/R007 01 01

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DDC
RECEIVED
FEB 23 1967
D

ARCHIVE COPY

NOTICE

Reproduction of this document in any form by other than naval activities is not authorized except by special approval of the Secretary of the Navy or the Chief of Naval Operations as appropriate.

The following Espionage notice can be disregarded unless this document is plainly marked CONFIDENTIAL or SECRET.

This document contains information affecting the national defense of the United States within the meaning of the Espionage Laws, Title 18, U.S.C., Sections 793 and 794. The transmission or the revelation of its contents in any manner to an unauthorized person is prohibited by law.

NAVAL AIR ENGINEERING CENTER
PHILADELPHIA, PENNSYLVANIA 19112

AERONAUTICAL MATERIALS LABORATORY

REPORT NO. NAEC-AML-2536 DATE 5 December 1966

OCEANOGRAPHIC EFFECTS ON PLASTIC ENGINEERING MATERIALS

ASSIGNMENT 12-72(1D) UNDER
AIRTASK A32 523 001/200 1/R007 01 01

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

Prepared by: H. J. Lee
H. J. LEE
Project Engineer

Approved by: E. K. Rishel
E. K. RISHEL, Head
Plastics Branch

C. A. Cassola
C. A. CASSOLA, Superintendent
High Polymer Division

TABLE OF CONTENTS

		PAGE
ABSTRACT		3
I.	INTRODUCTION	4
II.	GENERAL DISCUSSIONS	4
III.	METHODS OF TEST	5
IV.	TEST RESULTS	5
V.	OBSERVATION	6
VI.	CONCLUSIONS	6
VII.	RECOMMENDATIONS	7
VIII.	FUTURE PLANS	7
IX.	APPENDIX A	8
	Table 1 - Mechanical Tests on Oceanographic Specimens	
	Table 2 - Comparison of Room Temperature Mechanical Properties - Control and Exposed Specimens	
	Table 3 - Description of Materials Tested	
X.	APPENDIX B	9
	Figure 1 - Total Assembly - Jig and Twelve Test Specimens Prior to Disassembly for Testing	
	Figure 2 - Jig Disassembled with Specimens Removed	
	Figure 3 - Specimens Removed from Jig Showing Epoxy, Phenolic #3 and Phenolic #2, Respectively	
	Figure 4 - Specimens Removed from Jig Showing Phenolic #1, Acrylic, and Polyester, Respectively	

ABSTRACT

The continuing effort to evaluate oceanographic environment effects on a wide spectrum of plastic engineering materials, reinforced laminates and other plastics, has been in progress. Submersible Test Unit I-2 test panel array, which is discussed, represents one segment of this continuing effort. This panel array was submerged October 1963 for 751 days at a depth of approximately 5,640 feet in the Port Hueneme Pacific Ocean area.

Laboratory studies, after exposure, indicated that, in general, deep sea immersion adversely affected the mechanical properties of most of the materials.

I. INTRODUCTION

A. The study described herein represents one segment of the continuing effort of the Aeronautical Materials Laboratory's endeavor in evaluating deep oceanographic effects on a wide spectrum of polymeric materials. This particular effort is directed principally toward exposures at various depths of the ocean which have been in progress.

B. The principal objective of this portion of the studies is to gather long term engineering data on the relative performance of plastic materials in various ocean environments so that designers of weapon system components will have reliable information on which to base their design of equipment for service under these environments.

II. GENERAL DISCUSSIONS

A. In recent years interest in the ocean depths and the study of new engineering materials that may be utilized at these depths have been increasing. Among these new materials being considered, for such applications as weapon systems, are organic polymers with which this report is concerned.

B. Through the cooperation of the U. S. Naval Civil Engineering Laboratory, Port Hueneme, California, a series of Naval Air Engineering Center - Aeronautical Materials Laboratory specimens are being deep sea exposed at contrasting depths and for various time durations.

C. This report discusses the test panel array (Submersible Test Unit I-2) of commercial plastic reinforced laminates and other plastics, in the relaxed and stressed conditions, which was submerged in October 1963 at a depth of approximately 5,640 feet for 751 days in the Port Hueneme Pacific Ocean area.

D. The selection of material for exposure was based on their presently intended application and the performance data previously submitted by the manufacturer or determined by the Naval Air Engineering Center, Aeronautical Materials Laboratory, Plastics Branch. Appendix A, Table 3, describes these materials.

E. The study of the effects of oceanographic exposure on materials is a problem complicated by the enormously complex environmental variables in the properties of the sea. Among the more important variables are such properties as salinity, temperature, pressure, hydrogen ion concentration, dissolved oxygen,flow currents and types of marine organisms, all of which vary with the depth, site and duration of exposure.

F. However, it is hoped that for any one particular depth and site, the continuous changes in ocean conditions are not so severe as to preclude reproducibility of tests within certain reasonable limits.

III. METHOD OF TESTS

A. Two groups of commercial plastic specimens, low pressure laminates and cured resins, size 5½ inches x 12 inches x 1/8 inch, were mounted in a test jig such that a condition of flexural load of 40-55 pounds total constantly prevailed and below each was mounted a duplicate specimen in the relaxed state (see appendix B, Figures 1 and 2).

B. Each set was held together by phenolic pegs at both ends of the specimens, and all edges in the total assembly were sealed with an epoxy resin, Chrysler Cycleweld C-14, to prevent or hinder deterioration through any weaknesses that may have been incurred during the cutting of each specimen and jig component.

C. For the acrylic specimen, a flexural load of only 12 pounds total was impressed because of the limiting nature of the jig construction.

D. Specimens were submerged to a depth of 5,640 feet for 751 days duration at the Port Hueneme Pacific Ocean area on 2 October 1963 under the following environmental conditions:

Location	33° 44'N, 120° 45'W
Pressure	2482 psi
Salinity	34.59 parts per thousand
Oxygen	2.14 parts per million
Temperature	36.3°F
pH	7.48
Current	less than 0.5 knots
Sediment	green mud to rocks

Specimens were retrieved 22 October 1965.

E. Upon retrieval, the entire assembly was forwarded to the Naval Air Engineering Center in the "as is" condition enclosed in plastic bags. Drying out of the specimens occurred during transit and the interval between disassembly and mechanical testing was such that the curvatures in the stressed specimens were difficultly discernible.

F. Specimen sizes, as cut from the exposed panels, and test procedures for mechanical testing are as detailed in MIL-STD-401A. Values obtained were based on the average of 3 to 6 specimens.

IV. TEST RESULTS

The results of mechanical testing are tabulated in Appendix A, Tables 1 and 2.

V. OBSERVATIONS

A. Specimens on receipt had no apparent surface effects except for a light deposit of what appeared to be marine plant life adhering to the surface of all the specimens and jig in a dendritic pattern. (See Appendix B, Figures 1, 2, 3 and 4.

B. Room temperature mechanical properties tested after exposure indicated the following characteristics:

1. In general, flexural strengths decreased after exposure except for the acrylic and phenolic #3 relaxed specimens which exhibited a slight increase in strength over the control. The values for these specimens demonstrating the increase were based on the average of four specimens. In either case, the fact that the flexural values of three of the four specimens were greater than the average for the respective control, reflects the degree of reliability of the observation.

The values noted for all the stressed specimens indicated that the oceanographic exposure effected loss in flexural strength ranging from 1.5% for phenolic #3 to 12.4% for phenolic #2.

2. Except for phenolic #3 which showed an increase for relaxed and stressed specimens, modulus of elasticity values dropped for all the specimens, relaxed as well as stressed.

3. Tensile strength increases occurred for the polyester and epoxy, both in the relaxed and stressed condition; and for the acrylic in only the stressed state.

4. All specimens incurred loss in compressive strength with those under stress, excepting phenolic #2, exhibiting a lesser degree of loss than those relaxed.

VI. CONCLUSIONS

A. Since this is a continuing effort in evaluating deep sea submergence effects at various depths and for different time durations, note will be made of the oceanographic effects on each individual type of material versus exposure. However, except for the results discussed in each respective report, it is premature at this stage of the effort to justifiably compare the various exposures since there has not been a significant number of them as yet and, additionally, not all of the exposures involve the same types of materials.

B. For this array of specimens deep sea immersion for 751 days adversely affected the mechanical properties of most of the materials.

C. The supposed enhancement of mechanical properties observed after exposure may be explained by the fact that control values were determined much in advance of values for the exposed specimens. During this interval it is possible that gradual postcuring may have occurred before, during, or after exposure to yield the higher strength values and any loss in strength incurred during exposure may be overshadowed by the increase due to this postcure.

VII. RECOMMENDATIONS

A. It is recommended that control specimens be tested, if possible, concurrently with the exposed specimens so as to prevent differences in test data due to any time interval effects such as postcuring.

B. It is also recommended that a significant number of exposures be made testing the same types of materials, providing sufficient coupons of these materials are available.

C. Also recommended is that the time interval between retrieval and laboratory tests be reduced as much as possible to prevent unreliability of results due to recovery or deterioration of mechanical properties during the time interval.

D. Retrieved specimens should be kept immersed in sea water until mechanical tests are initiated.

VIII. FUTURE PLANS

A. The same types of plastic materials as in previous exposures, if available, will be submitted for immersion until a significant number of exposures is obtained.

B. New types of plastic engineering materials will also be studied either concurrently with previous types or separately.

C. Specimens of the same types of materials as in STU 1-4 for shallow water immersion have been prepared and at present await consignment to the appropriate facility.

D. A type of test has been devised and will be applied to determine quantitatively the degree of sea water absorption of exposed specimens. This method of test should not be affected by the drying out of the specimens during the period between retrieval and laboratory testing.

IX. APPENDIX A

MECHANICAL TESTS ON OCEANOGRAPHIC SPECIMENS

Tests[1]	1/8" Acrylic			Polyester			Phenolic 1			Phenolic			Epoxy			Phenolic 3			Phenolic Plates of Jig		
	Control	Exposed A	Exposed B	Control	Exposed A	Exposed B	Control	Exposed A	Exposed B	Control	Exposed A	Exposed B	Control	Exposed A	Exposed B	Control	Exposed A	Exposed B	Exposed A	Exposed B	Exposed C
Room Temperature Flexural Strength (psi)	17,030	17,320	16,645	67,690	64,575	63,535	66,645	61,170	62,085	81,220	72,010	71,170	83,600	72,430	74,495	76,130	76,350	75,000	19,130	19,510	20,215
Modulus of Elasticity (psi)	0.49×10^6	0.47×10^6	0.44×10^6	2.88×10^6	2.83×10^6	2.76×10^6	3.77×10^6	3.65×10^6	3.62×10^6	3.68×10^6	3.37×10^6	3.50×10^6	3.25×10^6	3.09×10^6	3.21×10^6	3.29×10^6	3.55×10^6	3.38×10^6	0.58×10^6	0.59×10^6	0.64×10^6
Tensile Strength (psi)	9,915	8,205	10,375	55,520	55,750	57,625	41,405	39,625	38,670	49,005	40,745	42,580	48,910	39,840	81,000	51,930	44,770	49,970			
Compression Strength (psi)	21,320	16,785	17,145	43,705	33,320	34,085	65,860	43,475	46,805	62,970	50,410	47,210	72,000	43,550	31,795	60,615	48,555	44,660	22,285	24,590	23,035

Table 1

Notes: (1) Tested in accordance with MIL-STD-401A

(2) "A" denotes specimens in the relaxed condition
"B" denotes specimens under flexural stress

COMPARISON OF ROOM TEMPERATURE MECHANICAL PROPERTIES - CONTROL AND EXPOSED SPECIMENS

Oceanographic Specimens	Flexural Strength			Modulus of Elasticity			Tensile Strength			Compressive Strength		
	Relaxed vs Control %	Stressed vs Control %	Stressed vs Relaxed %	Relaxed vs Control %	Stressed vs Control %	Stressed vs Relaxed %	Relaxed vs Control %	Stressed vs Control %	Stressed vs Relaxed %	Relaxed vs Control %	Stressed vs Control %	Stressed vs Relaxed %
1/8" Acrylic	1.6 Gain	2.4 Loss	3.9 Loss	4.4 Loss	11.1 Loss	7.0 Loss	17.3 Loss	4.6 Gain	26.5 Gain	21.3 Loss	19.6 Loss	2.3 Gain
Polyester	4.6 Loss	6.1 Loss	1.6 Loss	1.7 Loss	4.2 Loss	2.5 Loss	0.4 Gain	3.8 Gain	3.4 Gain	23.8 Loss	22.0 Loss	2.3 Gain
Phenolic (1)	8.2 Loss	6.8 Loss	1.0 Gain	3.2 Loss	4.0 Loss	0.8 Loss	4.3 Loss	6.6 Loss	2.4 Loss	34.0 Loss	28.9 Loss	7.7 Gain
Phenolic (2)	11.3 Loss	12.4 Loss	1.2 Loss	8.4 Loss	4.9 Loss	3.9 Gain	16.9 Loss	13.1 Loss	4.5 Gain	19.9 Loss	25.0 Loss	6.4 Loss
Epoxy	13.4 Loss	10.9 Loss	2.9 Gain	4.9 Loss	1.2 Loss	3.9 Gain	22.4 Gain	65.6 Gain	35.4 Gain	39.5 Loss	28.1 Loss	18.9 Gain
Phenolic (3)	2.9 Gain	1.5 Loss	1.8 Loss	7.9 Gain	2.7 Gain	4.8 Loss	4.2 Loss	3.8 Loss	0.4 Gain	19.9 Loss	26.3 Loss	8.0 Loss

Table 2

DESCRIPTION OF MATERIALS TESTED

1.	1/8" Acrylic	EVR-KLEER Type II UVA Cast Optics Corp.
2.	Polyester	Polyester Glass Reinforced Laminate Pleogen 1321 American Petro Chemical Corp.
3.	Phenolic 1	Phenolic Glass Reinforced Laminate Plyophen 98-573 Reichold Chemical Inc.
4.	Phenolic 2	Phenolic Glass Reinforced Laminate Plyophen 98-583 Reichold Chemical Inc.
5.	Phenolic 3	Phenolic Glass Reinforced Laminate EC-200 Evercoat, Chemicals, Inc.
6.	Epoxy	Epoxy Glass Reinforced Laminate Trevarno 161 Coast Manufacturing and Supply Co.
7.	Phenolic Plate	

Table 3

X. APPENDIX B



TOTAL ASSEMBLY - JIG AND TWELVE TEST SPECIMENS
PRIOR TO DISASSEMBLY FOR TESTING

PHOTO NO: CAN-374566(L)-3-66

Figure 1



JIG DISASSEMBLED WITH SPECIMENS REMOVED

PHOTO NO: CAN-374567(L)-3-66

Figure 2



SPECIMENS REMOVED FROM JIG SHOWING
EPOXY, PHENOLIC #3, AND PHENOLIC #2 SPECIMENS RESPECTIVELY

PHOTO NO: CAN-374568(L)-3-56

Figure 3



SPECIMENS REMOVED FROM JIG SHOWING
PHENOLIC #1, ACRYLIC, AND POLYESTER SPECIMENS RESPECTIVELY

PHOTO NO: CAN-374565(L)-3-66

Figure 4

UNCLASSIFIED

Security Classification

DOCUMENT CONTROL DATA - R&D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY *(Corporate author)* Naval Air Engineering Center Aeronautical Materials Laboratory Philadelphia, Pennsylvania 19112	2a. REPORT SECURITY CLASSIFICATION Unclassified 2b. GROUP NA

3. REPORT TITLE

OCEANOGRAPHIC EFFECTS ON PLASTIC ENGINEERING MATERIALS

4. DESCRIPTIVE NOTES *(Type of report and inclusive dates)*

5. AUTHOR(S) *(Last name, first name, initial)*

Lee, Henry J.

6. REPORT DATE 14 November 1966	7a. TOTAL NO. OF PAGES 9	7b. NO. OF REFS
8a. CONTRACT OR GRANT NO. b. PROJECT NO. ASSIGNMENT 12-72(1D) AIRTASK A32 523 001/200 1/R007 c. 01 01 d.	9a. ORIGINATOR'S REPORT NUMBER(S) REPORT NO. NAEC-AML-2536 9b. OTHER REPORT NO(S) *(Any other numbers that may be assigned this report)*	

10. AVAILABILITY/LIMITATION NOTICES

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY Naval Air Systems Command Department of the Navy Washington, D. C. 20360

13. ABSTRACT

The continuing effort to evaluate oceanographic environment effects on a wide spectrum of plastic engineering materials, reinforced laminates and other plastics, has been in progress. Submersible Test Unit I-2 test panel array, which is discussed, represents one segment of this continuing effort. This panel array was submerged October 1963 for 751 days at a depth of approximately 5,640 feet in the Port Hueneme Pacific Ocean area.

Laboratory studies, after exposure, indicated that, in general, deep sea immersion adversely affected the mechanical properties of most of the materials.

DD FORM 1 JAN 64 1473

023558

UNCLASSIFIED

UNCLASSIFIED

Security Classification

14. KEY WORDS	LINK A ROLE	LINK A WT	LINK B ROLE	LINK B WT	LINK C ROLE	LINK C WT
oceanographic						
deep sea						
plastic engineering materials						
reinforced laminates						

INSTRUCTIONS

1. ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization *(corporate author)* issuing the report.

2a. REPORT SECURITY CLASSIFICATION: Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. GROUP: Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. AUTHOR(S): Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. REPORT DATE: Enter the date of the report as day, month, year; or month, year. If more than one date appears on the report, use date of publication.

7a. TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. NUMBER OF REFERENCES: Enter the total number of references cited in the report.

8a. CONTRACT OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. PROJECT NUMBER: Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. ORIGINATOR'S REPORT NUMBER(S): Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. OTHER REPORT NUMBER(S): If the report has been assigned any other report numbers *(either by the originator or by the sponsor)*, also enter this number(s).

10. AVAILABILITY/LIMITATION NOTICES: Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

(1) "Qualified requesters may obtain copies of this report from DDC."

(2) "Foreign announcement and dissemination of this report by DDC is not authorized."

(3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."

(4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."

(5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSORING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring *(paying for)* the research and development. Include address.

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as *(TS)*, *(S)*, *(C)*, or *(U)*.

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.