

MISCELLANEOUS PAPER NO. 6-739

PETROGRAPHIC EXAMINATION OF HARDENED CONCRETE

by

Katharine Mather



September 1965

U. S. Army Engineer Waterways Experiment Station
CORPS OF ENGINEERS

Vicksburg, Mississippi

ARMY-MRC VICKSBURG, MISS

REPRODUCED BY
NATIONAL TECHNICAL
INFORMATION SERVICE
U.S. DEPARTMENT OF COMMERCE
SPRINGFIELD, VA. 22161

70

1

**Best
Available
Copy**

N O T I C E

THIS DOCUMENT HAS BEEN REPRODUCED FROM THE
BEST COPY FURNISHED US BY THE SPONSORING
AGENCY. ALTHOUGH IT IS RECOGNIZED THAT CER-
TAIN PORTIONS ARE ILLEGIBLE, IT IS BEING RE-
LEASED IN THE INTEREST OF MAKING AVAILABLE
AS MUCH INFORMATION AS POSSIBLE.

TAT
W34m
No. 6-739

FOREWORD

ASTM Committee C-9 on Concrete and Concrete Aggregates sponsored the publication in 1955 of ASTM Special Technical Publication No. 169 entitled Significance of Tests and Properties of Concrete and Concrete Aggregates. Part II was concerned with "Tests and Properties of Concrete" and included a paper on "Petrographic Examination - Hardened Concrete" by Mrs. Katharine Mather. In 1964, Committee C-9 undertook the development of a new publication which would replace STP 169 and would deal with tests, properties, and specifications for concrete and concrete aggregates and requested Mrs. Mather to revise her previous paper, to take account of technological progress since the preparation of that paper.

A manuscript was completed and forwarded to the Office, Chief of Engineers, for review and was approved for publication on 19 August 1965. This paper was prepared at the U. S. Army Engineer Waterways Experiment Station under the supervision of Mr. Thomas B. Kennedy, Chief, Concrete Division. Some of the work discussed in the paper was accomplished under the Engineering Studies Program of the Office, Chief of Engineers.

Colonel Alex G. Sutton, Jr., CE, and Colonel John R. Oswalt, Jr., CE, were directors of the Waterways Experiment Station during the preparation of this paper. Mr. J. B. Tiffany was Technical Director.

Petrographic Examination of Hardened Concrete*

Katharine Mather**

Introduction

This paper is intended to show that petrographic examination provides information useful in evaluating hardened concrete; to note the problems inherent in its use; to outline what it involves; to describe the kinds of information that it can produce, and to show how this information can be applied.

The questions that materials testing and evaluation tries to answer are: (a) "How will this material behave in use?" or (b) "Why did this material behave in use in the way it did?" The first question is never unequivocally answered except after-the-fact, by determining how the material did behave in use. The most useful method for developing practical information upon which to make decisions that depend on prediction of probable behavior of materials is the study of why materials behaved in use as they did.

Testers of materials are unable to compress time or to anticipate and reproduce the environment that the material will experience. Generally they use standardized procedures not directly related to the specific environment, or that do not determine the particular properties relevant

*Prepared at request of ASTM Committee C-9 on Concrete and Concrete Aggregates for consideration to replace the paper "Petrographic Examination-Hardened Concrete" by Katharine Mather included in ASTM STP No. 169, 1955, pp 68-80; in a revision of that publication.

**Research Geologist (Engineering Petrography); Chief, Petrography and X-ray Section, Engineering Sciences Branch, Concrete Division, U. S. Army Engineer Waterways Experiment Station, Jackson, Mississippi.

to performance in the specific instance. Thus testing construction materials amounts to obtaining certain kinds of information about certain samples in specified conditions and extrapolating to the conditions of intended use insofar as they can be predicted.

Petrographic examination of hardened concrete is included among the subjects in this volume because it helps to improve the extrapolation from test results to performance in use. It offers direct observational information on what is being tested and what is in the structure, giving another way of appraising the relation between samples and materials in use and judging how similar the two are.

Communication Problems

A petrographic examination of concrete ordinarily begins and ends with a problem of communication between the person who requests the examination (usually an engineer) and the person who makes it (usually a petrographer). Unless the two succeed in producing a clear, mutually understood statement of the problem, they cannot expect a clear, useful answer economically obtained. The engineer who asks for an examination of a particular concrete suspects that the concrete is unusual; the more clearly he defines the peculiarity, the more he directs the petrographer toward the important aspects. The engineer may not be familiar with the techniques that the petrographer may use or with his approach; the petrographer may not realize the engineer's responsibility for decision and action, may not find out all the engineer could tell him about the concrete, and may not realize which petrographic findings are useful and relevant. The petrographer should not expect petrographic results to be taken on faith unless the rationality

of the techniques producing them is demonstrated. Both should remember that the essentials of petrographic examination of concrete are practiced anytime anyone looks intelligently at concrete either in a structure or as a specimen and tries to relate what he can see to the past or future performance of the concrete. On this basis, it is clear that many most useful petrographic examinations are made by inspectors, engineers, chemists, physicists--anyone concerned with the production or use of concrete. No one should hesitate to examine concrete with all available means; all, from novice to expert, should question the indicated conclusions and confirm them in as many ways as possible.

Methods

A recommended practice for petrographic examination of concrete aggregates has been standardized.⁽¹⁾ Techniques of petrographic examination of hardened concrete have been described and discussed.⁽²⁻²⁵⁾ They have not been standardized for several reasons including: the considerable variety of techniques that are used in different laboratories; the wide variety of purposes for which examinations are made; the rapidly increasing uses in the recent past of a variety of instruments and kinds of data clearly applicable in petrographic examination of cement paste and hardened concrete but not yet available in many laboratories in which petrographic examinations of concrete are made.

At present I know of no laboratory where petrographic examinations of concrete are made that is equipped to use all the methods that have yielded useful information, and no one person who has digested the available approaches and developed the ability to choose the particular combination of techniques best suited to each problem encountered. Concretes are more complex than

most rocks used as aggregates; their constituents are less well known; concretes change through time more rapidly than most aggregates. All of these circumstances combine to make each petrographic examination of concrete peculiarly specific and to make the methods harder to generalize and standardize.

Between 1950 and 1955 remarkably rapid advances in knowledge of the calcium silicate hydrates⁽²⁶⁻²⁸⁾ were brought about in part by work sponsored by the Building Research Station. J. D. Bernal and his students, then working at Birkbeck College, and others in the United Kingdom, proceeded by synthesis of compounds, and study of naturally occurring minerals, making use of X-ray crystallographic methods, optical methods, and static dehydration. The interest thus aroused among mineralogists and chemists, especially in the United Kingdom and the Soviet Union, has led to a greatly increased knowledge of natural and synthetic calcium silicate hydrates,⁽²⁹⁾ recently summarized by Taylor^(30,31) and from another approach by Belov and coworkers.⁽³²⁾

In 1955 differential thermal analysis had been usefully applied^(24,25) but not widely investigated. The use of electron microscopy in the study of portland cement hydrates had not advanced very far in the USA, and differences of opinion on proper specimen preparation, and ambiguities in interpretation made it difficult for persons not expert in the field to assess the value and meaning of the results. The potentialities of these methods and others for characterizing calcium silicate hydrates, calcium aluminate hydrates, and other phases in hydrated cement paste could be recognized but most laboratories where petrographic examinations of hardened concrete were made

were not equipped with instruments more sophisticated than the polarizing microscope, and were not yet prepared to relate and to combine the information available from visual observation and light microscopy with that available from X-ray diffraction, differential thermal analysis, and electron microscopy and diffraction.

These newer techniques and the results they yield offered an opportunity to understand in much more detail than previously had been possible the chemical reactions that had gone on in a concrete being examined, because they suggested that it would soon be possible to characterize the hydration products and reaction products more clearly and thus to reconstruct in detail the chemical reactions of normal hydration or of abnormal deterioration, or of both, in the concrete, and to evaluate, with much more certainty than is possible without fairly complete identification of the reaction products, the relative roles of chemical attack and physical attack in producing deterioration. The goal, of relating better established and more familiar techniques in petrographic examination of hardened concrete to the more intimate and detailed insights made possible by the newer techniques, remained to be achieved, and while progress since 1955 is considerable, it is not complete.

Petrographic examination of hardened concrete does not imply that a microscope, or any other particular instrument, necessarily is used; it does imply examination to discover what recognizable constituents are present and how they are arranged in space. Often it implies an evaluation of quality and condition of the concrete--an evaluation sometimes based on quantitative information.

ASTM methods requiring observation of "type of failure and appearance of the concrete" (C 116) and "type of fracture if other than the usual cone" (C 39) implicitly require partial petrographic examination--the part dealing with defects and departure from the norm--but offer no instructions on how to conduct it. Several specifications under the jurisdiction of ASTM Committee C 13 on Concrete Pipe include as one basis for rejection "measurements and inspection" to ascertain whether the product conforms to the specification as to design and freedom from defects (C 14, section 35, C 76, section 27; C 112, section 20; C 361, section 32; C 412, sections 16, 17; C 444, sections 13, 19; C 478, sections 24, 27; C 505, section 26; C 506, sections 26, 29; C 507, sections 26, 29). These provisions for visual inspection and measurements are also requirements for a partial petrographic examination; a person qualified to make the inspection and measurements needs to be familiar with the products specified, because the instructions provided are not detailed. Tables I and II give outlines for examining concrete as a material, but do not refer to dimensions or to quality of formed or finished surfaces.

Purpose and Scope

General

A petrographic examination attempts to answer two general objective questions: "What is the composition?" and "How is it put together?" The first question refers to the recognizable individual constituents present on the scale at which they are considered. The second question refers to structural fabric, that is, the articulation or packing in space of the component elements making up any sort of external form⁽³³⁾ or heterogeneous

solid body. Both questions may be answered on any useful scale by choice of technique or techniques of appropriate resolving power. The resolving power needed differs depending on the specific questions to be answered.

Specific

Step one, in any case, is to define the problem, to find and ask the right questions, those that need to be answered to solve the problem that caused the examination to be requested. These right questions should be answered insofar as they can be in the context, limited as it will be by money, time, instrumentation, and the state of the art. The best petrographic examination is the one that finds the right questions and answers them with maximum economy in minimum time, with a demonstration clear to all concerned that the right questions were answered, with all necessary and no superfluous detail. In practice the approach to the ideal varies depending on the problem, the skill with which the questions are asked, and the skill of the petrographer. One measure of the petrographer's skill is knowing when to stop, either because the problem is adequately solved, or, in some cases, because it has been shown to be insoluble under the circumstances.

Fabric and Composition

Fabric--the packing of component elements in space--is the heterogeneity obvious as one looks at a weathered concrete structure or at a broken or sawed surface of concrete. Fabric includes all of the structural elements, ranging in scale from gross to atomic, and comprises both structure and texture as those terms are used in rock description. The fabric appears on the scale of the lift or course or batch or the structural crack, on the scale of the coarse aggregate, on the scale of the sand grains or the

solid body. Both questions may be answered on any useful scale by choice of technique or techniques of appropriate resolving power. The resolving power needed differs depending on the specific questions to be answered.

Specific

Step one, in any case, is to define the problem, to find and ask the right questions, those that need to be answered to solve the problem that caused the examination to be requested. These right questions should be answered insofar as they can be in the context, limited as it will be by money, time, instrumentation, and the state of the art. The best petrographic examination is the one that finds the right questions and answers them with maximum economy in minimum time, with a demonstration clear to all concerned that the right questions were answered, with all necessary and no superfluous detail. In practice the approach to the ideal varies depending on the problem, the skill with which the questions are asked, and the skill of the petrographer. One measure of the petrographer's skill is knowing when to stop, either because the problem is adequately solved, or, in some cases, because it has been shown to be insoluble under the circumstances.

Fabric and Composition

Fabric--the packing of component elements in space--is the heterogeneity obvious as one looks at a weathered concrete structure or at a broken or sawed surface of concrete. Fabric includes all of the structural elements, ranging in scale from gross to atomic, and comprises both structure and texture as those terms are used in rock description. The fabric appears on the scale of the lot or course or batch or the structural crack, on the scale of the coarse aggregate, on the scale of the sand grains or the

air voids in the mortar or the "microcracks," on the scale of the residual unhydrated cement or the calcium hydroxide crystals, on the scale of the hydrous calcium aluminates and the scale of the poorly crystalline hydrous calcium silicates in the hydrated cement paste, or on the scale of the atomic structure of any crystal forming a part of any of the structural components. Rocks, fabricated metals, and yeast-raised bread are other examples of substances with fabric. The closest naturally occurring analogy among rocks to the fabric of concrete is graywacke conglomerate with abundant matrix. The closest naturally occurring analogue to hardened cement paste is silty clay.

Fabric and composition together define, characterize, and form the basis for descriptive classification of solid multicomponent substances. Composition and fabric are so closely interrelated in concrete that they cannot be clearly separated.

One important decision in a petrographic examination is whether it is the fabric, that is, the gross heterogeneity resulting from the conditions of batching, mixing or consolidation, or the adequacy of air-void system for frost resistance--or the composition, that is, reactions between cement and aggregate, or reactions between a contaminant and cement paste, or between paste and solutions from external sources--that is the factor most likely to have been principally responsible for the condition that led to the request for petrographic examination. Were the construction practices employed suitable for producing concrete capable of giving satisfactory service in the particular environment and exposure? Were the materials that were chosen susceptible to participation in chemical reactions that have

deleterious consequences? Was there a failure to modify the environment for instance by improving the drainage so as to increase the ability of the concrete to survive it? Is the difficulty principally physical or principally chemical? Usually several causes have interacted, but one is probably the originator; if it can be identified, the appropriate techniques are more clearly pointed out.

Investigating composition and fabric provides a specific, unique definition of what is being examined, and lets the petrographer know what he is talking about. The standard tests do not always supply information that permits discrimination between one piece of concrete and another, but direct observation on the relevant scale does. There are n possible concretes all having 2-in. slumps, with air contents of 5 percent, with 4500-psi compressive strength at 28 days, but the No. 2 cylinder in the set of 3 broken on day A in laboratory B is unique, perceptibly and logically, from Nos. 1 and 3, and from all the members of the other possible sets, and its top is different from its bottom as cast. The salient lesson from the study of composition and fabric of concrete is the individuality and uniqueness of each structure or part of a structure, of each specimen, of each thin section; this individual combination of fabric and composition reflects the history and uniquely conditions the future of the concrete. What is investigated at any time is particular concrete, not concrete in general. Each structure and each part of a structure is unique in terms of contents, fabric, history, and exposure.

Comparisons

To say that each structure and specimen is unique does not mean that comparisons are useless or impossible; they are essential, and concretes can

be rationally grouped and usefully compared within classes and between classes, if the basis for the grouping is objective. Each comparison is an abstraction that leaves out of account some characteristics of the things compared, so that it is necessary to bear in mind that the accidentally or deliberately omitted factors may prove to be important. Paste, mortar, or concrete of known proportions, materials, age, and curing history offer the logical basis for comparison and extrapolation; laboratory specimens made to be examined or salvaged just after having been tested for strength provide a good source of such comparative material. Specimens exposed to laboratory air outside the moist room or curing tank for more than a few hours are much less suitable, because specimens that are cracked or that have slender cross-sections sometimes carbonate very rapidly. Specimens exposed to simulated weathering tests, or wetting and drying cycles, or prolonged drying are not to be considered as representative of normally cured or of naturally weathered concretes. Natural weathering differs from part to part of a structure, as well as from climate to climate and subgrade to subgrade.

Interpretation of Observations

Normal Concrete

The most valuable information that can be obtained by petrographic examination of concrete comes from the examination of normal concrete; only by comparison with the range of constituents and fabrics in normal concrete can that which differs from the normal be recognized and its differences specifically defined. Unless it can be demonstrated that the constituents, or the proportions of constituents, or the fabric, depart from those found

in serviceable concrete of the age and class in the region, there is no logical basis for assuming any connection between constituents, or proportions, or fabric, and service behavior. Even when it can be shown that a concrete has a peculiar service record and some unique feature or features not shared by a dozen others of comparable class, age, and provenance, it remains to be seen whether the known unique feature and the peculiar service record are causally connected, or whether both are related to some third or nth factor that is the effective cause of the abnormal behavior.

For this discussion, "normal" constituents and fabrics are defined as those present in serviceable concrete of the class and age in the region. "Serviceable" is used instead of "undeteriorated" because it is possible to tell whether concrete in a structure is serving as it was intended to, but the criteria that distinguish inevitable chemical and physical changes from deterioration in concrete 20 or 50 years old have not been well established.

Class of Concrete

The restriction to concrete of one class is necessary because changes in cement content, water-cement ratio, and maximum size of aggregate large enough to change the class entail such large changes in properties that no close comparison will be significant. If, for example, the criteria for paving concrete are applied to mass concrete, it appears that all mass concrete is very inferior, ^{it} which/is not for the purpose it is intended to serve. Class of concrete is important in the definition as it implies relative homogeneity in mixture proportions, particularly in water-cement ratio, cement factor, and maximum size of aggregate. It is possible by microscopic methods to sort mass concretes that are fairly homogeneous in cement content and water-cement ratio into order of increasing age, or it is possible to sort mass concretes fairly

homogeneous in age in order of increasing cement content. In terms of the ability to sort mass concrete microscopically, fairly homogeneous in cement content and water-cement ratio means a maximum difference in cement content of about 0.5 bags per cu yd, and 0.1 by weight in water-cement ratio.

Age of Concrete

Some restriction on the ages of concretes compared is necessary unless age is the variable being studied. Unless the age is known or unless one has younger and older concretes of otherwise comparable characteristics, so that the age of the unknown may be estimated in relation to the knowns, it may be impossible to judge the significance of observations. For example, in one case calcium sulfoaluminate was found in many voids as far as 5 in. from the outer surfaces of a concrete pavement of high flexural and compressive strength and of unknown age. In other field concrete from the region, calcium sulfoaluminate is commonly present in concrete over five years old made with type I or type III cement, but it is not abundant and is confined to voids near outer surfaces. If the concrete of unknown age is in fact five or seven years old, it differs conspicuously from others of comparable age and class in the region and the difference probably justifies some concern about its future; if it is 15 years old, it is peculiar but the peculiarity is probably of less practical importance.

Provenance of Concrete

Restriction to one region assists rational comparison from several points of view. The aggregates economically available in an area are determined by the regional geology and consequently show some homogeneity of composition resulting from similarity of origin and history. In a particular region, cements and aggregates economically available are used in

making concrete which is exposed to the climate characteristic of the region-- the prevailing temperature range and temperature frequency distribution and the characteristic amount and sequence of precipitation. The extent of a region of comparable concrete may vary from a few square miles to many thousands, depending on variation in: (1) regional geology as it determines quantity and uniformity of aggregate supply; (2) topography--a region of low relief and generally uniform slope such as the Great Plains, or the Atlantic or Gulf Coastal Plain, has widespread, essentially comparable range and distribution of temperature and precipitation, but in a region of high relief and broken slopes, temperature varies considerably with altitude, and precipitation with orientation to prevailing winds, making important differences in exposure over short distances; and (3) patterns of distribution of aggregates and cement from competitive sources.

An additional influence that may appear is a prevailing engineering opinion, in an organization placing concrete in a large area, on what is desirable in mixture proportions or methods of placing or consolidation. In building gravity dams the Corps of Engineers restricts the height of a single lift to 5 to 7-1/2 ft, ⁽³⁴⁾ while the Hydroelectric Power Commission of Ontario has placed gravity dams up to 70 ft high in one continuous operation. ⁽³⁵⁾ The intention in the first case is to minimize heat generation and in the second to eliminate horizontal construction joints. Such differences in emphasis entail differences in mixture proportions, plant, and construction practice that are bound to affect the fabric and character of the concrete. The existence of satisfactory structures built in many different ways underlines the need to define "normal" concrete in objective and restricted terms.

Example

Although the most important kind of petrographic examination of concrete is the examination of normal concrete, usually the concrete that a petrographer is asked to examine has behaved in an unexpected way. Before and during the early stages of the examination, the information on the history and behavior should be considered and the following questions asked:

- (a) What process or processes could produce the described results?
- (b) What observable traces could the process or processes leave in the concrete?
- (c) Would such traces be unique and specific evidence of what is supposed to have happened?

Consider, for example, two 6- by 12-in. cylinders made at a field project during the winter; the 28-day strengths were 885 and 1025 psi, less than 25 percent of the strengths obtained from earlier and later cylinders made, cured, and tested under presumably similar conditions; the resident engineer suspects an overdose of air-entraining agent.

Processes that Could Produce the Results

Several distinct processes were considered that could have produced the observed results. Increasing the air content does reduce the compressive strength; the observed reduction is so drastic, however, as to require an increase in air content of at least 15 percent of air to be a sufficient cause. Mistakes in batching such as too little cement or too much water or damage due to early freezing also could produce the observed results.

Traces that These Processes Could Leave

Excessive air content can be recognized at low magnification, and verified and quantified by comparison with concrete of known air content

and by count. ASTM Recommended Practice C 457 describes procedures for determining parameters of the air-void system. Too little cement can be demonstrated by comparing thin or polished sections from cylinders of normal strength and the same mixture and age, with sections from these cylinders, and finding substantially less cement in the low-strength cylinders. Too much water produces sedimentation even in air-entrained concrete, and may be demonstrated by comparing finely-ground surfaces of axial slices of cylinders of normal strength and those of reduced strength, and finding wider underside separations between paste and aggregate in the cylinders of reduced strength; the result may be inconclusive. More complete demonstration would result from comparing thin sections cut parallel with the placing direction from cylinders of normal strength, of the same mixture and age with sections cut in the same orientation from these cylinders, and finding probably a little less unhydrated cement with a large development of calcium hydroxide rims along the undersides of aggregate in the low strength cylinders.

Freezing before final set may leave imprints of ice crystals recognizable at low magnification.

Unique and Specific Evidence

Lacking the necessary comparative material--cylinders of normal strength and similar age and history from the same mixture--it is very difficult to show petrographically that a large part of the cement was left out or that a large excess of water was put in. By making three sets of specimens from one mixture, one set with normal proportions, one with reduced cement, one with added water, curing all three in standard conditions, breaking part in compression, and sectioning companion specimens, a strong presumption might

be established that one of the two working hypotheses was correct; it would not be conclusive proof. Demonstration that the concrete froze before final set would depend on finding the imprint of the ice crystals. Excessive air content, on the other hand, can be qualitatively and quantitatively demonstrated without ambiguity.

Let us hope that the resident engineer in our example is right, for the other possibilities that suggest themselves would be harder to establish. Examination of broken surfaces, outer surfaces, and sawed slices did show that the air content of the concrete was phenomenally high, around 25 percent (Fig. 1) by comparison with concrete of known air content (Fig. 2). The air content was so high and the thin walls of paste between the air voids so fragile that the low strengths were explained adequately by this evidence alone.

This example illustrates how one goes about asking relevant questions that can be answered by petrographic evidence. The general question in examination of hardened concrete with peculiar behavior is: does this concrete differ significantly from comparable normal concrete, with respect to one or more properties that may be shown to be causally connected with its behavior? The generalized form of the null hypothesis is that the concrete falls within the normal range in respect to/certain property or properties.

Of the four mechanisms considered, three should produce recognizable traces in amounts that can at least be approximated. The freezing-before-final-set hypothesis was poorly defined in effects and their magnitude. The ability to be quantitative and the ability to obtain confirmation by nonmicroscopic means differed in the three hypotheses. Air content is specified in a numerical range, in this case, 4 to 7 percent measured at the mixer.

Brown and Pierson⁽³⁶⁾ have shown and others confirmed that measurements of the air content of freshly mixed concrete and micrometric determinations of the air content of the same concrete allowed to set undisturbed agree very closely. If concrete with 7 percent air were produced and if a generous allowance for field and laboratory error is made, it would still be most surprising to find more than 10 percent air in a supposedly normal cylinder from this project. The low strengths were in the range of strengths of moist-cured foamed neat cement.⁽³⁷⁾ With this background we conclude that unless the low strength cylinders have a total air content above 20 percent, the excessive air hypothesis could not be accepted as an adequate explanation of the strengths. The hypothesis can be quantitatively expressed, and the quantities can be measured in more than one independent way; the magnitudes involved can be distinguished by anyone who can see through a stereoscopic microscope and ask "What relation does the air content of A bear to the air content of C?"

The quantitative aspects of both forms of the batching-mistakes hypothesis are not so well explored and data are less easily verified by independent means. The volume of cement in the original mixture and the volume of calcium hydroxide at a given stage in hydration can be calculated making certain assumptions, which in this example could not be confirmed. However, given comparable cylinders of normal strength, the omitted-cement hypothesis could be checked by comparing sections from the normal concrete with sections from the low-strength concrete to see whether there was a difference between the amounts of unhydrated cement per unit area. If the difference were to provide a satisfactory explanation, it would be fairly large and should be perceptible

to an observer able to recognize unhydrated cement in thin or polished sections. Some petrographers might choose to count a group of 300 to 500 points on a section of each kind, to obtain a result that can be expressed as a number, with the understanding that the sample was not adequate; others would prefer to look at several areas and express the results as "more than..." "less than..." or "no difference recognized." The procedure in checking the extra-water hypothesis is similar, but would concern the development of calcium hydroxide rims along undersides of fine aggregate.

The simple, orderly example just described involves a problem that can be solved without techniques more elaborate than those normally used in several concrete laboratories in this country in 1945. The simplicity and order arise because the concrete examined was two test specimens, and both the history available and the total age of the specimens made it clear--and examination of the concrete adequately confirmed--that no chemical attack on cement paste had taken place, and that reactions between the particular aggregates and cement could not have developed, in the time available, to a degree that could render them significant effects on the strength.

Reconstruction of History of Field Concrete

To pass from consideration of such petrographic examinations as that described in the previous example to the petrographic examination of concrete that has aged and perhaps deteriorated in service, introduces two important new unknowns--time, and the precise environment of the structure. The effects of the passage of relatively short periods of time on the constituents present in several cement pastes of known water-cement ratio

stored under laboratory conditions have been investigated,^(38,43) but anomalies remain⁽⁴⁰⁾ in the results, although both the composition of the pastes and the nature of the environments were known and controlled far more thoroughly than the composition and environment of any field concrete.

Composition

If the changes in composition through time of cement paste in laboratory conditions were known for a representative number of cement compositions and water-cement ratios, effects of both cement-aggregate interactions and of environmental influences would be easier to recognize and could be more usefully interpreted.

Environment

Why do exposed vertical walls of chert-gravel concrete in the vicinity of St. Louis, Missouri, generally have fewer popouts than apparently similar walls in the vicinity of Memphis, Tennessee? The winters are colder in St. Louis, but the mean annual rainfall is lower; and in Memphis a larger proportion of the higher mean annual rainfall occurs in winter. The difference may be that the chert gravel in the Memphis walls is more likely to be critically saturated when it freezes. The Weather Bureau's climatological data for the location is a valuable source of information that can assist in many petrographic examinations of hardened concrete.

The discovery in Mississippi of several highway pavements and associated structures affected by sulfate attack and by combined sulfate and acid attack⁽⁴⁴⁾ emphasizes the need to make use of available information on the composition of foundations and subgrades.

Thus, the examination of samples of field concrete after extended service involves an increase in complexity, a decrease in available information, and

a decrease in the confidence that may be placed in the answer, as compared to examinations of laboratory test specimens of hardened concrete.

It does not belittle the petrographer to admit that he cannot make bricks without straw; neither can the chemist, the physicist, or the engineer; sometimes the petrographer can recover evidence not accessible by other approaches. Several reasons make reconstructions of the history of deteriorated field concrete difficult; in any particular instance it may be important, and impossible in the present state of our knowledge to decide what weight belongs to each.

Deteriorated field concrete that is referred to a laboratory or to a petrographer is almost never concrete that has performed abnormally for one single obvious cause; such simple cases can be and are explained on the spot to the satisfaction of those concerned. The field concrete that is examined by a petrographer is concrete that has worried some responsible person enough to make the effort and expense of sampling and testing appear justified. There is thus a built-in bias in the sampling process. Normally the concrete that a petrographer sees as part of his assigned duties is controversial concrete sent in by organizations with alert conscientious concrete technologists. In practice, this generally means that he sees only the poor concrete produced with better than average control. The worst concrete is rarely sampled and sent to a petrographer; good concrete is rarely controversial.

Furthermore, the older the concrete, the less information is likely to be available about materials, proportions, conditions of placing, and the characteristics that undeteriorated comparable concrete would have. Although one can deduce from the concrete that water-cement ratio was high

or low, and usually that cement factor was high or low or medium, and the general quality of the workmanship, one cannot reconstruct the alkali content of the cement. Aggregate sources, particularly of natural sand and gravel, can be located from their composition--the constituents present and their size distribution are diagnostic of the region and sometimes of the particular source.

Finally, deteriorated field concrete usually shows superimposed traces of several processes, with at least one in an advanced stage. The most advanced process may conceal the evidence of others that were more important in effect. Frequently the most conspicuous process is carbonation of outer surfaces and along the borders of old cracks.

Laboratory test exposures are simplified compared to natural exposures by the exclusion of some factors and the regulation of those retained, and often are "accelerated" by altering some factor so as to remove it from the range possible in nature. Consequently, a laboratory procedure often results in symptoms different from symptoms encountered in a field example of the process the test is intended to simulate.

Samples of field concrete, when examined using light microscopy, frequently are found to contain secondary calcium carbonate near their outer surfaces, along old cracks, and sometimes in the interior. Such calcium carbonate, when examined by optical methods, is generally found to be calcite, rarely aragonite, and almost never vaterite, the form-birefringent spherulitic calcite with interstitial water. Vaterite, however, was found by optical methods to be common on mortar bars that had been tested according to ASTM C 227 and had been found on concrete specimens tested for resistance to

freezing and thawing according to ASTM C 290. The use of X-ray diffraction to examine cement-paste concentrates from field concrete has revealed that vaterite, not recognized by optical methods, is frequently a major constituent of the secondary calcium carbonate,⁽⁴⁵⁾ especially on samples from seawater exposures or from other wet environments. Vaterite is known to persist for several months in laboratory specimens stored in room conditions. The sequence from poorly crystallized vaterite, calcite, and aragonite to well-crystallized calcite in the carbonation of pastes and mortars has been clarified by Cole and Kroone,⁽⁴⁶⁾ and vaterite is now known as a natural mineral.⁽⁴⁷⁾

Accelerated freezing and thawing in water according to ASTM Method C 290 produces a characteristic loss of surface skin and loss of mortar, which is not like the condition of specimens exposed on the mean-tide rack at Eastport, Maine.⁽⁴⁸⁾ Some field concrete deteriorated by natural freezing and thawing develops sets of subparallel cracks normal to the placing direction of the concrete or deteriorated regions parallel to the nearest free surface. These phenomena are not reproduced in accelerated freezing and thawing in water.

Field concrete that has deteriorated primarily because of the alkali-silica reaction usually has much more advanced and conspicuous internal symptoms of this reaction than are found in mortar bars of expansive combinations examined after test according to ASTM Method C. 227. On the other hand, some field concrete regarded as undeteriorated has shown a range of evidence of alkali-silica reaction.

Alkali-carbonate and alkali-silica reactions exist together in varying degrees of development in some concretes⁽¹⁸⁾ and inconspicuous degrees of

reaction may be the only recognizable peculiarities in cases of unsatisfactory service with possibly expensive consequences.⁽⁴⁹⁾ The several alkali-carbonate reactions⁽⁵⁰⁾ include dedolomitization, and rim-forming reactions.^(17, 50,51) The effects of rim-forming reactions are as yet inadequately known, although they appear to reduce strength.

Closure

It was true in 1955 and still is that we do not yet know enough about the hydrous calcium silicates that hold concrete together, the other compounds associated with them, and the varying successions of compounds in laboratory and field hydration of concrete. For instance: hexacalcium aluminate trisulfate hydrate⁽⁵²⁾-- more usually known as "high sulfate sulfoaluminate" or ettringite-- is a normal early hydration product of most cements. It is not stable in the presence of tricalcium aluminate when hydration can continue, and frequently disappears from cement pastes after longer curing. If it is found in a 20-year old concrete, does it indicate some abnormality? Calcium aluminate monocarbonate (or monocarboaluminate)^(15,52) is found in laboratory cement pastes, and in field concrete.^(18,45) In the laboratory it can be produced by accidental carbonation, or by the addition of finely ground calcite to the freshly mixed paste.⁽⁵²⁾ Hadley⁽⁵⁰⁾ recognized it at the interface of dolomitic limestone and cement paste in dedolomitization. What is its effect in field concretes with and without carbonate aggregates?⁽⁵³⁾

The measure of progress, and the results of the use of newer techniques including X-ray diffraction, differential thermal analysis, electron microscopy and electron diffraction are that the questions listed above, and others, are

obvious to me in 1965, although I could not have formulated them in 1955. "Things which are seen"--concrete and mortar-- "were not made of things which do appear"⁽⁵⁴⁾ to the eye and to the light microscope. The use of the newer techniques mentioned, and of the electron probe and infrared spectroscopy, in conjunction with the observing eye and the light microscope, still offers the chance of sorting out the qualitative and quantitative differences in hydration products and in submicroscopic fabric that are related to serviceable and deteriorated concrete.

- (14) _____, Discussion of ^DÅ Grudemo in
Proceedings Fourth International Symposium on the Chemistry of Cement,
National Bureau of Standards Monograph 43, pp 648-655, 1962.
- (15) P. Selignann and N. R. Greening, "New Techniques for Temperature and Humidity Control in X-Ray Diffractometry," Journal of the PCA Research and Development Laboratories, Vol 4, No. 2, pp 2-9, 1962.
- (16) M. Polivka, J. W. Kelly, and C. H. Best, "A Physical Method for Determining the Composition of Hardened Concrete," Am Soc Testing and Mats, STP No. 205, pp 135-152, 1958.
- (17) R. E. Bisque and J. Lemish, "Chemical Characteristics of Some Carbonate Rock Aggregates as Related to Durability of Concrete," Highway Research Board Bulletin 196, pp 29-45, 1958.
- (18) K. Mather, A. D. Buck, and W. I. Luke, "Alkali-Silica and Alkali-Carbonate Reactivity of Some Aggregates from South Dakota, Kansas, and Missouri," Highway Research Board Record No. 45, Nat. Acad. Sci. - Nat. Res. Council Publication 1167, pp 72-109, 1964.
- (19) G. M. Idorn, "Disintegration of Field Concrete," Committee on Alkali Reactions in Concrete, Progress Report N 1, Danish National Inst. of Building Res. and The Academy of Technical Sciences, 39 pp, Copenhagen, 1956.
- (20) E. Poulsen, Preparation of Samples for Microscopic Investigation, Comm. on Alkali Reactions in Concrete, Danish Nat. Inst. of Building Res. and The Acad. of Tech. Sci., Copenhagen, 1958.
Progress Report M1,
46pp.
- (21) G. M. Idorn, Studies of Disintegrated Concrete, Parts I, II, III, IV, Comm. on Alkali Reactions in Concrete, Progress Reports N 2, 3, 4, 5; Danish Nat. Inst. of Building Research and The Acad. of Tech. Sci., Copenhagen, 1961 (I, II); 1964 (III, IV).
- (22) C. M. Hunt, "Infrared Absorption Spectra of Some Compounds in the CaO - SiO₂ - H₂O System," Proceedings Fourth Int. Symp. on the Chem. of Cement, National Bur. of Stds. Monograph 43, pp 297-304, 1962, discussion by R. Roy, pp 304-305, closure by author p 305.
- (23) J. D. Bernal, J. W. Jeffery, and H. F. W. Taylor, "Crystallographic Research on the Hydration of Portland Cement, First Report," Magazine of Concrete Research No. 11, pp 49-54, 1952.

- (24) G. L. Kalousek, "Application of Differential Thermal Analysis in a Study of the System Lime-Silica-Water," Proceedings of the Third International Symposium on the Chemistry of Cement, London, 1952, Cement and Concrete Assn., London, pp 296-311, 1954.
- (25) R. W. Nurse and H. F. W. Taylor, discussion of (23), ibid pp 311 - 318.
- (26) H. F. W. Taylor, "Hydrated Calcium Silicates. Part I Compound Formation at Ordinary Temperatures," Journal Chemical Soc. (London), pp 3682-3690, December 1950.
- _____, "Hydrated Calcium Silicates Part V. The Water Content of Calcium Silicate Hydrate(I)," ibid, pp 163-174, January 1953.
- (27) L. Heller and H. F. W. Taylor, "Hydrated Calcium Silicates. Part II. Hydrothermal Reactions: Lime: Silica Ratio 1:1," Ibid, pp 2397-2401, September 1951.
- _____, "Hydrated Calcium Silicates. Part III. Hydrothermal Reactions of Mixtures of Lime: Silica Molar Ratio 3:2," Ibid, pp 1018-1020, March 1952.
- _____, "Hydrated Calcium Silicates. Part IV. Hydrothermal Reactions: Lime: Silica Ratios 2:1 and 3:1, Ibid, pp 2535-2541, July 1952.
- (28) J. D. Bernal, "The Structures of Cement Hydration Compounds," Proceedings of the Third Int. Sym. on the Chemistry of Cement, London, 1952, Cement and Concrete Assn., London, pp 216-236, 1954; discussion by P. M. deWolff, L. Heller, W. H. Taylor, H. D. Megaw, E. Thilo, A. Grudemo, A. E. Moore, R. H. Bogue, F. M. Lea and author, pp 237-260.
- (29) L. Heller and H. F. W. Taylor, Crystallographic Data for the Calcium Silicates, H. M. Stationery Office, London, 1956.
- (30) H. F. W. Taylor, "The Chemistry of Cement Hydration," in J. E. Burke, Ed., Progress in Ceramic Science, Vol 1, Pergamon Press, New York, pp 89-145, 1961.
- (31) H. F. W. Taylor, ed, The Chemistry of Cements, Vol 1, Academic Press, London; Academic Press, N. Y., pp 167-231, 1964.
- (32) N. V. Belov, et al.: Crystal Chemistry of Large Cation Silicates [Kristallo Khimiya Silicatosov S. Krupnymi Kationami;] Authorized Translation, Consultants Bureau, N. Y., 1963.

- (33) E. B. Knopf, translator, Structural Petrology, Memoir 6, Geol. Soc. America, p 12, 1938 - Translation of B. Sander, Gefügekunde der Gesteine.
- (34) Office of the Chief of Engineers, Engineering and Design, Standard Practice for Concrete, Engineer Manual EM 1110-2-2000, 15 December 1963.
- (35) R. B. Young, Frost-Resistant Concrete, Proceedings Am. Concrete Inst., Vol 36, pp 477-490, 1940.
- (36) L. S. Brown and C. U. Pierson, Linear Traverse Technique for Measurement of Air in Hardened Concrete, Proceedings Am. Conc. Inst. Vol 47, pp 117-123, 1951. T. F. Willis, K. Mather, L. S. Brown, and C. U. Pierson, discussion of (36), ibid. pp 124-1 to 124-7.
- (37) R. C. Valore, Jr., Cellular Concretes Part 2, Proceedings Am. Concrete Inst., Vol 50, p 820, 1954.
- (38) S. Brunauer and D. L. Kantro, "The Hydration of Tricalcium Silicate and Decalcium Silicate from 50°C to 50°C" in H. F. W. Taylor, ed., The Chemistry of Cements, Vol 1, Academic Press, London and New York, pp 287-312, 1964.
- (39) Highway Research Board Committee MC-B6(3), G. L. Kalousek, Chairman, unpublished work.
- (40) G. L. Kalousek, "Analyzing SO₃ - Bearing Phases in Hydrating Cements," Materials Research and Standards, Vol. 5, No. 6, pp 292-304, June 1965.
- (41) K. T. Greene, "Early Hydration Reactions of Portland Cement," Fourth International Symposium on the Chemistry of Cement, Washington, D. C., 1960, National Bureau of Standards Monograph 43, vol 1, pp 359-374, 1962, discussion pp 374-385, by W. C. Hansen, E. T. Carlson, T. C. Powers, A. J. Gaskin, S. A. Greenberg and V. S. Mehra, and author.
- (42) D. L. Kantro, L. E. Copeland, E. R. Anderson, "An X-Ray Diffraction Investigation of Hydrated Portland Cement Pastes," pp 1020-1034, discussion p 1035 by K. Mather and author, Proceedings ASTM, vol. 60, 1960.
- (43) V. S. Ramachandran, R. F. Feldman, and P. S. Sereda, Application of Differential Thermal Analysis in Cement Research," Highway Research Record 62, Publ. 1246 National Academy of Sciences - National Research Council, pp 40-61, 1964.

- (44) F. Lossing, Sulfate Attack on Concrete Pavements in Mississippi, presented Highway Research Board, January 1965, in press.
- (45) K. Mather and R. C. Mielenz, Cooperative Examination of Cores from the McPherson Test Road, Proceedings Highway Research Board, pp 205-216, 1960.
- (46) W. F. Cole and B. Kroone, Nature, British Association no of, Vol 184, p B. A. 57, 1959.
- (47) J. D. C. McConnell, "Vaterite from Ballycraig, Larne, Northern Ireland," Mineralogical Magazine, Vol 32, No. 250, pp 535-544, Sept. 1960.
- (48) T. B. Kennedy and K. Mather, "Correlation Between Laboratory Accelerated Freezing and Thawing and Weathering at Treat Island, Maine," Proceedings American Concrete Institute, Vol 50, pp 141-172, 1953.
- (49) W. I. Luke, "Alkali-Carbonate Reaction in Concrete from Chickamauga Dam Powerhouse," Proceedings ASTM, Vol 64, pp 887-902, 1964.
- (50) D. W. Hadley, "Alkali Reactivity of Dolomitic Carbonate Rocks," Highway Research Record No. 45, National Academy of Sciences - National Research Council Publication 1167, pp 1-19, 1964.
- (51) A. D. Buck, "Investigation of a reaction involving nondolomitic limestone aggregate in concrete," U. S. Army Engineer Waterways Experiment Station, Miscellaneous Paper No. 6-274, June 1965.
- (52) R. Turriziani, "The Calcium Aluminate Hydrates and Related Compounds," in H. F. W. Taylor ed., The Chemistry of Cements, vol 1, pp 233-286, Academic Press, London and New York, 1964.
- (53) P. Seligmann, Discussion in Highway Research Record No. 45, Publication 1167, pp 111-113, 1964.
- (54) Paul, Epistle to the Hebrews, Chapter II, Verse 3.

TABLE I.—OUTLINE FOR EXAMINATION OF CONCRETE WITH EYE AND HAND LENS.

Coarse Aggregate	+ Fine Aggregate	+ Matrix	+ Air	+ Steel
CONSTITUENTS				
<p><i>Maximum dimension, in inches, in the range $\rightarrow d >$</i></p> <p>Type:</p> <ol style="list-style-type: none"> Gravel Crushed stone Mixed 1 and 2 Other (name) Mixed 1 +/or 2 +/or 4 <p>If 1, 2, or 4, homogeneous or heterogeneous</p> <p>Lithologic types</p> <p>Coarse aggregate more than 20, 30, 40, 50 per cent of total</p>	<p>Type:</p> <ol style="list-style-type: none"> Natural sand Manufactured sand Mixed Other Mixed 1 +/or 2 +/or 4 <p>If 1, 2, or 4, homogeneous or heterogeneous</p>	<p>Color, by comparison with National Research Council Rock Color Chart (1948)</p> <p>Color distribution:</p> <ol style="list-style-type: none"> Mottled Even Gradational changes 	<p>More than 3 per cent of total, predominantly in spherical voids</p> <p>Less than 3 per cent of total, abundant nonspherical voids</p> <p>Color differences between voids and mortar?</p>	<p>Type</p> <p>Voids empty, filled, lined, or partly filled</p>
FABRIC				
<p>Shape</p> <p>Distribution</p> <p>Packing</p> <p>Grading (even, uneven, excess, or deficiency of size or sizes)</p> <p>Parallelism of flat sides or long axes of exposed sections, normal to direction of placement +/or parallel to formed and finished surfaces¹</p>	<p>Distribution</p> <p>Particle shape as preferred orientation</p> <p>Grading perceptible</p>	<p>Distribution</p>	<p>Shape</p> <p>Distribution</p> <p>Grading (as perceptible)</p> <p>Parallelism of long axes of irregular voids or sheets of voids: with each other; with flat sides or long axes of coarse aggregate</p>	<p>Voids below horizontal or low-angle reinforcement</p>
CONDITION				
<p>Does it ring when hit lightly with a hammer or does it give a dull, flat sound? Cracks? How distributed? Crack fillings? With cores or sawed specimens: did aggregate tear out in drilling or sawing?</p>				<p>Rusty or clean? Put in rusty or corroded later?</p>

¹ A satisfactory portion of the coarse aggregate has maximum dimensions in the range shown as measured on sawed or broken surfaces. See also sawed or drilled close to and parallel to formed surfaces appear to show local turbulence as a result of spading or rodding close to the form. Sections sawed in the plane of bedding (normal to the direction of placement) are likely to have inconspicuous orientation. Sections broken normal to placement in conventionally placed concrete with normal bond tend to have aggregate knobs abundant on the bottom of the upper piece as cast and sockets abundant on the top of the lower piece as cast.

TABLE II.—OUTLINE EXAMINATION OF CONCRETE WITH A STEREO-MICROSCOPE.

Coarse Aggregate	Aggregate	Matrix	Voids
Lithologic types and mineralogy as perceptible Surface texture Within the piece: grain shape grain size—extreme range observed, mm median within range — to — mm textureless (too fine to resolve) uniform or variable within the piece From piece to piece: intergranular bond porosity and absorption* If concrete breaks through aggregate, through how much of what kind? If boundary voids, along what kind of aggregate? All? All of one kind? More than 50 per cent of one kind? Several kinds?	Types and mineralogy perceptible Structure Distribution	Color Fracture around or through aggregate Contact of matrix with aggregate: close, no opening visible on sawed or broken surface; aggregate not dislodged with fingers or probe; boundary openings—frequent, common, rare width empty filled Cracks present, absent, result of specimen preparation, preceding specimen preparation Fly ash†	Grading Proportion of spherical to nonspherical Nonspherical, ellipsoidal, irregular, disk-shaped Color change from interior surface to matrix Interior surface luster like rest of matrix, dull, shining Linings in voids absent, rare, common, in most, complete, partial, colorless, colored, silky tufts, hexagonal tablets, gel, other Underside voids or sheets of voids uncommon, small, common, abundant


* Pore visible to the naked eye, or at X—, or sucks in water that is dropped on it.

† Dark solid spheres or hollow-centered spheres of glass +/or magnetite recognizable at X 9 on sawed or broken surfaces. Other mineral admixtures with characteristic particles visible at low magnification should be recognizable.

Condition: When it is examined at X 6 to X 10 under good light, the freshly broken surface of a concrete in good physical condition that still retains most of its natural moisture content has a luster that in mineralogical terms is subtranslucent glimmering vitreous.† Thin edges of splinters of the paste transmit light; reflections appear to come from many minute points on the surface, and the quality of luster is like that from broken glass but less intense. Concrete in less good physical condition is more opaque on a freshly broken surface, and the luster is dull, vitreous going toward chalky. A properly cured laboratory specimen from a concrete mixture of normal proportions cured 28 days that has shown normal compressive or flexural strength and that is broken with a hammer and examined on a new break within a week of the time that it finished curing should provide an example of concrete in good physical condition. Under the same conditions of examination, when there is reasonable assurance that the concrete does not contain white portland cement or slag cement, the color of the matrix of concrete in good physical condition is definitely gray or definitely tan, except adjoining old cracks or original surfaces. † E. S. Dana, "Textbook of Mineralogy," John Wiley & Sons, New York, N. Y., 4th Ed., pp. 273-274 (1932). Revised by W. E. Ford.

FIG. 1.—Void Size and Distribution in the Cement Paste Just Inside the Surface Skin, Bottom of Low-Strength Cylinder (X 6).

This is the surface as received, with most of the surface skin rubbed off in handling. The void walls can be broken with a fingernail. The sides of the cylinder show the same condition with finer bubbles in some areas.



Reproduced from
best available copy.

FIG. 2.—This Diamond-Sawed and Ground Slice of Air-Entrained Concrete (X 6) Provides a Comparison with Fig. 1.

The air content of the plastic concrete determined by pressure meter was 5.3 per cent; the air content of this hardened beam by micrometric count was 5.7 per cent. This surface is smoother than the surfaces in the other photograph, but this concrete obviously has less than a third of the air content of the other.