AD-752 030

INVESTIGATION OF THE EFFECTS OF LIQUID OXYGEN ON CHEMICALLY TREATED SURFACES OF ALUMINUM TUBING

M. Perlman, et al

Naval Air Development Center
Warminster, Pennsylvania

16 October 1972

Reproduced From
Best Available Copy

DISTRIBUTED BY:

NTIS

National Technical Information Service
U. S. DEPARTMENT OF COMMERCE
5285 Port Royal Road, Springfield Va. 22151

AD752030

NAVAL AIR DEVELOPMENT CENTER

WARMINSTER, PA 18974

REPORT NO. NADC-72220-[illegible] 16 OCT 1972

INVESTIGATION OF THE EFFECTS OF LIQUID [illegible] ON CHEMICALLY TREATED SURFACES OF ALUMINUM TUBING

PHASE REPORT

AIRTASK A530 5203/00[illegible]/3510[illegible]00002
Work Unit A5311B-40

Approved for public release; distribution unlimited.

Reproduced by
NATIONAL TECHNICAL
INFORMATION SERVICE
U S Department of Commerce
Springfield VA 22151

[redacted]

NOTICE

[illegible] DISCLAIMER - The disposition or instructions [illegible] products [illegible] do not constitute an endorsement by the Government [illegible] any convey or imply [illegible] license or rights [illegible] such products.

A

UNCLASSIFIED

Security Classification

DOCUMENT CONTROL DATA - R & D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

NAVAL AIR DEVELOPMENT CENTER Air Vehicle Technology Dept. (3022) Warminster, Pennsylvania 18974	UNCLASSIFIED 2b. GROUP

3. REPORT TITLE

INVESTIGATION OF THE EFFECTS OF LIQUID OXYGEN ON CHEMICALLY TREATED SURFACES OF ALUMINUM TUBING

4. DESCRIPTIVE NOTES (Type of report and inclusive dates)

PHASE REPORT

5. AUTHOR(S) (First name, middle initial, last name)

J. F. DANOVICH

6. REPORT DATE	7a. TOTAL NO. OF PAGES	7b. NO. OF REFS
16 Oct 72	10	4

8a. CONTRACT OR GRANT NO. b. PROJECT NO. AIRTASK A510 5103/0014/3510000002 Work Unit A5311B-40	9a. ORIGINATOR'S REPORT NUMBER(S) NADC-72201-VT 9b. OTHER REPORT NO(S) (Any other numbers that may be assigned this report)

10. DISTRIBUTION STATEMENT

Approved for public release; distribution unlimited.

11. SUPPLEMENTARY NOTES	12. SPONSORING MILITARY ACTIVITY Naval Air Systems Command Washington, D.C. 20360

13. ABSTRACT

This report describes the effects of liquid oxygen on chemically treated (chromic acid anodized and chromate conversion coated) surfaces of aluminum tubing used in aviators' breathing systems. Tests were conducted to detect residual deposits, gaseous contamination and changes in surface structure.

Details of illustrations in this document may be better studied on microfiche

AD 752030

DD FORM 1473 (PAGE 1) 19

0102-014-6600

UNCLASSIFIED

Security Classification

14 KEY WORDS	LINK A ROLE	LINK A WT	LINK B ROLE	LINK B WT	LINK C ROLE	LINK C WT
Liquid oxygen						
Aluminum tubing						
Chemically treated surfaces						
Infrared Spectrophotometry						
Atomic Absorption Spectroscopy						
Electron Microscopy						

ib

DEPARTMENT OF THE NAVY
NAVAL AIR DEVELOPMENT CENTER
WARMINSTER, PA 18974

AIR VEHICLE TECHNOLOGY DEPARTMENT

REPORT NO. NADC-72201-VT 16 OCT 1972

INVESTIGATION OF THE EFFECTS OF LIQUID OXYGEN ON CHEMICALLY TREATED SURFACES OF ALUMINUM TUBING

PHASE REPORT

AIRTASK A510 5103/0014/3510000002
Work Unit A5311B-40

This report describes the effects of liquid oxygen on chemically treated (chromic acid anodized and chromate conversion coated) surfaces of aluminum tubing used in aviators' breathing systems. Tests were conducted to detect residual deposits, gaseous contamination and changes in surface structure.

Reported by: M. Perlman and John F. Danovich
M. PERLMAN, Physical Science Technician, Materials Synthesis and Characterization Section
J. F. DANOVICH, Research Chemist, Materials Synthesis and Characterization Section

Reviewed by: E. R. Wright
E. R. WRIGHT, Supervisory Chemist, Materials Synthesis and Characterization Section

Approved by: G. K. Holmes
G. K. HOLMES, Head, Materials Protection Branch

F. S. Williams
F. S. WILLIAMS, Superintendent, Aero Materials Laboratory

Approved for public release; distribution unlimited.

1C

INTRODUCTION

Aluminum transfer tubing used in the oxygen breathing system aboard aircraft has been free of chemical coatings as specified in reference (a). Recently an aircraft manufacturer has used chemically treated sections of aluminum tubing in the liquid oxygen system aboard the F-14. Since specific information was not available on the possible effects which liquid oxygen may have on chemically treated aluminum surfaces and the resulting quality of the pilots' breathing oxygen, it was decided to determine if residual deposits, gaseous contaminants and adverse surface structural changes could be anticipated. Atomic absorption, infrared analysis and electron microscopy were used to study the effects of pressurized liquid oxygen flowing through untreated, chromic acid anodized, and chromate conversion coated aluminum tubing.

MATERIALS AND TEST PROCEDURES

Three 1-foot lengths of aluminum tubing, 6061-T6 (MIL-T-7081) HYD ¼ in. I.D. by 1/16 in. thickness with connector fittings, were treated in accordance with the requirements of MIL-C-5541B (reference (b)) so that a chromate conversion coating was obtained on the interior and exterior surfaces of the tubing. Three additional lengths of tubing from the same source as the above stock were treated in accordance with MIL-A-8625C, Type I, (reference (c)) to obtain a chromic acid anodized coating on the interior and exterior surfaces of the tubing. A length of "untreated" aluminum tubing from the same base stock was used as a control.

The sections of chromate conversion coated tubing were then assembled and connected to the outlet valve of a 500 gallon liquid oxygen (LOX) storage tank. The tank was pressurized to approximately 10 lbs. to produce a continuous flow of LOX through the transfer tubing for 10 minutes. The LOX was collected in a 4000 ml. glass beaker.

Upon filling, the beaker was removed and replaced by a Navy G-276 LOX Sampler Cylinder. A LOX sample was collected for analysis of contaminants in the gaseous state by infrared spectrophotometry.

The sections of transfer tubing were then disconnected and immersed in the beaker of collected LOX for one hour, until evaporation was complete. The residue was retained for analysis by atomic absorption spectroscopy.

The same procedures were repeated with the chromic acid anodized tubing and the untreated (control) tubing.

Preceding page blank

ANALYSIS AND RESULTS

1. Chromium by Atomic Absorption Spectroscopy

A measure of the chemical inertness of the chromate conversion and chromic acid anodize coatings would be indicated by resistance of these films to the severe solvent and abrasive action of liquid oxygen under the test conditions. If leaching occurs the presence of chromium in the LOX residues would be expected. The residues, therefore, were transferred from the collection beakers by washings with demineralized water and dilute hydrochloric acid into volumetric flasks for analysis by atomic absorption spectroscopy. Standard solutions of chromium were prepared for calibration. The analytical conditions were as follows:

INSTRUMENT: Perkin-Elmer Model 303
HOLLOW CATHODE LAMP: Chromium
WAVELENGTH: 3579A
FLAME: Air-Acetylene
SENSITIVITY: 0.1 PPM Cr for 1% Absorption

RESULTS:

SAMPLE	% CHROMIUM FOUND
Chromate Conversion Coating	None detected
Chromic Acid Anodize Coating	None detected
Untreated	None detected

2. Gaseous Contaminants by Infrared Spectrophotometry

The samples of LOX collected in Navy G-276 Sampler Cylinders under the conditions of test were analyzed by infrared spectrophotometry for the presence of gaseous contaminants as specified in specification MIL-O-27210C (reference (d)). The presence of unusual infrared absorption bands not normally encountered in specification grade LOX would be indicative of contributions by the chemically treated transfer tubing.

RESULTS OF ANALYSIS: No unusual contaminants were detected.

3. Surface Examination by Electron Microscopy

The following conditions were represented by samples of tubes:

a. Untreated; unexposed
b. Untreated; exposed to LOX
c. Chromic acid anodized; unexposed
d. Chromic acid anodized; exposed to LOX
e. Chromate conversion coating; unexposed
f. Chromate conversion coating; exposed to LOX

These were cut lengthwise and the interior surfaces replicated with two percent solution of collodion. These replicas were then shadowed with chromium followed by vapor deposited carbon. The collodion first replicas were dissolved with acetone and the remaining chromium-carbon replicas were examined in the electron microscope at magnification up to 36,000X, and then photographed at 12,000 magnification. Figure 1 shows electron micrographs of the interior surfaces of the tubings. Photos A and B show the interior surface of the untreated aluminum tubing before and after subjecting to LOX, respectively. No structural differences were observed between the two specimens. Photos C and D show the interior surfaces of the chromic acid anodized tubing before and after subjecting it to LOX. Examination of many areas, even up to 36,000X, gave only minor evidence of a smoothing of some of the asperities on the surface of the tubing subjected to the LOX. These differences are not apparent in photos C and D. Photos E and F show the interior surfaces of the chromium conversion coated tubing before and after subjecting it to LOX. A visible difference was observed in the smoothing effect of oxygen on the roughness of the chromate conversion coating. The change in surface smoothness, however, did not adversely affect the quality of LOX being transferred.

CONCLUSIONS

From the foregoing studies it is concluded that:

1. Liquid oxygen had no detrimental effects on the chemically treated aluminum transfer tubing.

2. The chemically treated tubing did not adversely affect the quality of the breathing oxygen.

3. No advantages in using chemically treated transfer tubing were apparent.

RECOMMENDATIONS

It is recommended that there be no mandatory requirement for use of chemically treated aluminum transfer tubing in the liquid oxygen systems of naval aircraft. Existing systems which use chemically treated tubing, however, may continue to be used effectively.

REFERENCES

(a) Military Specification MIL-D-19326, Installation and Test of Liquid Oxygen Systems in Aircraft

(b) Military Specification MIL-C-5541B, Chemical Conversion Coatings on Aluminum and Aluminum Alloys

(c) Military Specification MIL-A-8625C, Anodic Coatings for Aluminum and Aluminum Alloys

(d) Military Specification MIL-O-27210C(ASG), Oxygen, Aviator's Breathing, Liquid and Gas



BEFORE LIQUID OXYGEN UNTREATED AFTER LIQUID OXYGEN



BEFORE LIQUID OXYGEN CHROMIC ACID ANODIZED AFTER LIQUID OXYGEN



BEFORE LIQUID OXYGEN CHROMIUM CONVERSION COATED AFTER LIQUID OXYGEN

FIGURE 1 ELECTRON MICROGRAPHS OF THE INTERIOR SURFACES

Reproduced from best available copy.