

AD-A026 403

RIA-80-U227

WVT-TR-76015

AD TECHNICAL LIBRARY

USADACS Technical Library  
5 0712 01010891 7

PROJECTILE LUBRICATION BY MELTING ROTATING BANDS

April 1976



BENET WEAPONS LABORATORY  
WATERVLIET ARSENAL  
WATERVLIET, N.Y. 12189

**TECHNICAL REPORT**

AMCMS No. 664617.12.288.0  
DA Project No. 1X664617D340  
Pron No. 72-6-53509-01-72-M7

19970930 089

APPROVED FOR PUBLIC RELEASE: DISTRIBUTION UNLIMITED

DTIC QUALITY INSPECTED 1

#### DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

The use of trade name(s) and/or manufacturer(s) in this report does not constitute an official indorsement or approval.

#### DISPOSITION

Destroy this report when it is no longer needed. Do not return it to the originator.

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER WVT-TR-76015	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Projectile Lubrication by Melting Rotating Bands		5. TYPE OF REPORT & PERIOD COVERED
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) R.S. Montgomery		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS Benet Weapons Laboratory Watervliet Arsenal, Watervliet, N.Y. 12189 SARWV-RT		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS AMCMS No. 664617.12.288.0 Da Proj. No. 1X664617D340 Pron No. 72-6-53509-01-72-M7
11. CONTROLLING OFFICE NAME AND ADDRESS US Army Armament Command Rock Island, Illinois 61201		12. REPORT DATE April 1976
		13. NUMBER OF PAGES 15
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)		
Ammunition	Gun Barrels	Aluminum
Projectiles	Lubrication	Copper
Rotating Band	Friction	Gilding Metal
Melting	Reduction	Iron
Pressure	Liquid Metals	Plastic
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)		
<p>Sliding experiments carried out in the laboratory with a pin-on-disk machine produced appreciably higher coefficients of friction than the actual values measured for projectiles sliding down cannon bores. Although the pin surface melted, the coefficient of friction was at least an order of magnitude higher than expected for liquid film lubrication. The sliders in the laboratory experiments were, of course, much smaller than actual rotating bands and the bearing pressure was limited by distortion of the sliding pin. A recently</p> <p>(SEE REVERSE SIDE)</p>		

20. published theoretical study of lubrication by a melting slider can account for the disparity on this basis.


WVT-TR-76015

AD

PROJECTILE LUBRICATION BY MELTING ROTATING BANDS

R.S. Montgomery

April 1976



**BENET WEAPONS LABORATORY  
WATERVLIET ARSENAL  
WATERVLIET, N.Y. 12189**

**TECHNICAL REPORT**

AMCMS No. 664617.12.288.0

DA Project No. 1X664617D340

Pron No. 72-6-53509-01-72-M7

APPROVED FOR PUBLIC RELEASE: DISTRIBUTION UNLIMITED

TABLE OF CONTENTS

	<u>Page</u>
DISCUSSION	1
REFERENCES	5

APPENDIX

APPENDIX 1 - Estimation of Effective Width of Rotating Bands, $x_2$ .	8
APPENDIX 2 - Calculation of Volumetric Latent Heat, L	10
APPENDIX 3 - Calculation of Maximum Non-Dimensional Load Support, $W^*$ , For Laboratory Experiments With Gilding Metal	12

TABLE

TABLE 1 - 155mm M185 Howitzer Firing Data (From Ref. 2)	6
---	---

FIGURES

FIGURE 1 - 155mm M185 Howitzer Friction Data as a Function of Non-dimensional Speed.	4
FIGURE 2 - Rotating Band Configurations of the Projectiles.	9

## Projectile Lubrication by Melting Rotating Bands

The lowest coefficients of friction for all the metals investigated in the fast-sliding wear study made by the Franklin Institute in the period 1947-1956 (1) were in the range of 0.15 to 0.20. This was despite the fact that the abrupt drop in both the frictions and the wear rates at the same point leaves little doubt that the sliding was lubricated by a molten surface film at the higher sliding velocities and bearing pressures. An appreciably lower coefficient of friction would be expected for hydrodynamic lubrication and the coefficients of friction for actual projectiles sliding down cannon bores are known to be considerably below this value. For example, the values for projectiles fired in the 155mm M185 howitzer were as low as 0.015 after only ten to twenty inches of travel. (2)

It was suspected that this disparity resulted because the laboratory experiments were made using a small slider and relatively low bearing pressures as well as other differences. The laboratory slider was a pin just 0.080 in. in diameter while a rotating band is usually an inch to an inch and a half wide and the laboratory bearing pressures did not exceed 20,000 psi while the average band pressure during engraving is on the order of 50,000 psi. It certainly was not an effect of sliding velocity because the laboratory experiments were made at velocities as high as 1800 fps while the 155mm projectiles in ref. 2 had not reached 400 fps when the coefficient of friction was as low as 0.015. While these factors were suspected to be the causes

of the disparity, the reasons were not clear until the recent publication by Wilson of a theoretical study on lubrication by a melting solid (3). From his analysis, the coefficient of friction is proportional to the square root of the non-dimensional sliding speed, S. This speed is defined as:

$$S \equiv \mu U / x_2 L \quad (1)$$

where:  $\mu$  = liquid viscosity

U = sliding velocity

$x_2$  = length of slider

L = volumetric latent heat

Therefore, the coefficient of friction is inversely proportional to the square root of the length of the slider for any particular sliding velocity. This could account for a portion of the disparity in the coefficients of friction.

In Wilson's study it was also shown that, in the case of a melting slider, the system is not self-sustaining until very high values of non-dimensional bearing pressure. Specifically, the system does not develop its own lubricant supply for complete liquid film lubrication until the non-dimensional bearing pressure,  $W^*$ , is greater than about 0.2.  $W^*$  is defined as:

$$W^* \equiv w / L x_2 \quad (2)$$

where: w = load per unit width

Below this value, the leading edge of the slider would not be lubricated by the liquid metal and, consequently, the coefficient of friction would be much greater. The value of  $W^*$  for the gilding metal bands on the 155mm M107 projectile would be about 0.20 during

engraving for an engraving pressure of 50,000 psi and assuming the latent heats of zinc and copper in the alloy are additive. (See Appendix) It would be 0.19 for the copper bands on the 155mm M483 projectile during engraving for the same pressure. Therefore, in this case, lubrication by surface melting of the rotating bands would be self-sustaining or close to it. On the other hand, the maximum  $W^*$  for copper or gilding metal in the laboratory experiments was only about 0.07. The high coefficients of friction measured in the laboratory pin-on-disk experiments could easily be accounted for by the small slider size and low bearing pressures.

After a short distance of sliding, the coefficient of friction becomes low but not as low as predicted by Wilson. This is apparent from Fig. 1 where the 155mm howitzer friction data from ref. 2 is plotted as a function of non-dimensional speed on Wilson's graph. This may be a result of the complex geometries and bearing pressure patterns of the rotating bands. The bearing pressure at the entering ramp at the leading edge is considerably less and the cannellures, in the grooves of the rifling at least, break the sliding surface into shorter segments. Furthermore, the experimentally measured engraving pressure is an average pressure; the actual bearing pressure is significantly greater at the lands and less in the grooves of the rifling.

It is interesting to note that, from this analysis, the material of the rotating bands has an appreciable effect on the bearing pressure required for the lubrication to be self-sustaining through the volumetric latent heat. While the required bearing pressure is

• M107 PROJECTILE  
 ○ M483 PROJECTILE




Fig. 1 155mm M185 Howitzer Friction Data as a Function of Non-dimensional Speed. The data is from Ref. (2) and the lines of constant non-dimensional bearing pressure,  $W^*$ , from Ref. (3).

about 50,000, 53,000, and 56,000 psi for gilding metal, copper, and iron bands respectively, it would only be about 30,000 psi for aluminum bands. The required bearing pressure would even be less for the plastic band materials. This would have a significant effect on the friction of the bands during the initial engraving process.

### References

- (1) Montgomery, R.S., Friction and Wear at High Sliding Speeds, Watervliet Arsenal Technical Report 75028; WEAR 36, 275-298 (1976)
- (2) Bubb, Gary, Determination of In-bore Resistance Forces, Second International Symposium on Ballistics and Warhead Mechanisms, Daytona, Florida, 8-11 March 1976; Montgomery, R.S., Surface Melting of Rotating Bands, Watervliet Arsenal Technical Report 75060; WEAR To be published
- (3) Wilson, W.R.D., Lubrication by a Melting Solid, Am. Soc. Mech. Engr., Paper No. 75-Lub-26 (1975)

TABLE I

155MM M185 HOWITZER FIRING DATA (FROM REF. 2)

Rd. No.	316	318	319	320	330	331	313	314	315	324
Proj.	M107	M107	M107	M107	M107	M107	M483A1	M483A1	M483A1	M483A1
1.0 in. Travel	U Sx10 <sup>9</sup> 700 1.5 0.42	310 0.68 0.138	510 1.1 0.073	368 0.81 0.126	264 0.58 0.082	298 0.66 0.099	- - -	- - -	- - -	- - -
2.0 in. Travel	U Sx10 <sup>9</sup> - -	- -	- -	- -	- -	- -	912 1.2 0.043	968 1.3 0.032	996 1.3 0.021	892 1.2 0.030
5.0 in. Travel	U Sx10 <sup>9</sup> 2100 4.6 0.027	2080 4.6 0.010	2280 5.0 0.036	2300 5.1 0.034	1800 4.0 0.021	1900 4.2 0.026	2080 2.8 0.022	2140 2.8 0.020	- -	1900 2.5 0.025
10.0 in. Travel	U Sx10 <sup>9</sup> 3200 17.0 0.023	3200 7.0 0.005	3380 7.4 0.027	3340 7.3 0.026	2820 6.2 0.018	2900 6.4 0.021	3100 4.1 0.018	3180 4.2 0.015	- -	2840 3.8 0.019
20.0 in. Travel	U Sx10 <sup>9</sup> 4100 9.0 0.020	4460 9.8 0.008	4600 10 0.021	4600 10 0.021	4040 8.9 0.015	4100 9.0 0.017	4240 5.6 0.014	4320 5.7 0.012	- -	3940 5.2 0.019

337	338	339	340	341	342	345	346	347	360
M483A1									
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-
1096	1008	1120	968	936	932	980	1040	1120	600
1.5	1.3	1.5	1.3	1.2	1.2	1.3	1.4	1.5	8.0
0.032	0.029	0.027	0.027	0.026	0.042	0.035	0.037	0.035	0.055
2260	2160	2280	2460	2400	2400	2420	2500	2560	1680
3.0	2.9	3.0	3.3	3.2	3.2	3.2	3.3	3.4	2.2
0.022	0.020	0.019	0.016	0.013	0.010	0.015	0.011	0.016	0.018
3240	3200	3300	3600	3660	-	3860	3920	3860	2700
4.3	4.3	4.4	4.8	4.9	-	5.1	5.2	5.1	3.6
0.022	0.020	0.019	0.016	0.015	-	0.015	0.009	0.016	0.018
4460	-	-	-	-	-	-	5580	5440	3800
5.9	-	-	-	-	-	-	7.4	7.2	5.1
0.018	-	-	-	-	-	-	0.011	0.016	0.018

## Appendix 1

### Estimation of Effective Width of Rotating Bands, $x_2$ .

#### M107 Projectile

##### Contact with rifling grooves

Assume 50% of cannellure in contact -

Contact begins about 0.26 in. behind leading edge.

Contact length =  $1.00 - 0.26 - 0.05 = 0.69$  in.

##### Contact with rifling lands

Assume all of cannellure in contact -

Contact length = 1.00

##### Av. length of contact

$$\frac{1.00 (0.15) + 0.69 (0.249)}{0.15 + 0.249} = 0.81 \text{ in.}$$

#### M483 Projectile

##### Contact with rifling grooves

Assume 70% of first cannellure in contact and 90% of second cannellure in contact.

Contact begins about 0.26 in. behind leading edge.

Contact length =  $1.49 - 0.07 - 0.01 - 0.26$   
= 1.15 in.


##### Contact with rifling lands

Assume all of cannellure in contact.


Contact length = 1.49 in.

##### Av. length of contact

$$\frac{1.49 (0.15) + 1.15 (0.249)}{0.15 + 0.249} = 1.28 \text{ in.}$$



M483



M107

Fig. 2 Rotating Band Configurations of the Projectiles.

## Appendix 2

### Calculation of Volumetric Latent Heat, L

Heats of Fusion (gcal/g) from Kubaschewski and Alcock,  
Metallurgical Thermochemie (1967)

$$\text{Al} = 92.7 \pm 1.1$$

$$\text{Cu} = 48.8 \pm 1.6$$

$$\text{gilding metal (90 Cu-10Zn)} = 46.6$$

(assuming additive)

$$\text{Fe} = 59.1 \pm 3.6$$

$$\text{Ni} = 69.9 \pm 1.4$$

$$\text{Zn} = 26.6 \pm 0.5$$

Densities (g/cm<sup>3</sup>)

$$\text{Al} = 2.71$$

$$\text{Cu} = 8.91$$

$$\text{gilding metal} = 8.80$$

$$\text{Fe} = 7.86$$

$$\text{Ni} = 8.86$$

$$\text{Zn} = 7.14$$

L = (Heat of Fusion, gcal/g)(Density, g/cm<sup>3</sup>)(3087, ft-lbs/Kcal)(12, in<sup>3</sup>/ft<sup>3</sup>)

$$(1000, \text{gcal/Kcal})(0.06102, \text{in}^3/\text{cm}^3)$$

Volumetric Latent Heat (in-lbs/in<sup>3</sup>)

$$\text{Al} = 152,000$$

$$\text{Cu} = 264,000$$

$$\text{Gilding Metal} = 249,000$$

$$\text{Fe} = 282,000$$

$$\text{Ni} = 376,000$$

$$\text{Zn} = 115,000$$

Calculation of Non-Dimensional Speed, S, For Gilding Metal Bands of

M107 Projectile

Assume viscosity,  $\mu$ , is the same as liquid copper at its melting point. (3.1 centipoises)

$$\begin{aligned} S = \mu^U/x_2L &= \frac{(0.031 \text{ dyne-sec/cm}^2)(2.248 \times 10^{-6} \text{ lb/dyne})(U \text{ in/sec})}{(0.1550 \text{ in}^2/\text{cm}^2)(0.81 \text{ in})(249,000 \text{ in-lbs/in}^3)} \\ &= 2.2 \times 10^{-12} U(\text{in/sec}) \end{aligned}$$

Calculation of Non-Dimensional Speed, S, For Copper Bands of M483

Projectile

$$\begin{aligned} S &= \frac{(0.031)(2.248 \times 10^{-6})(U \text{ in/sec})}{(0.1550)(1.28)(264,000)} \\ &= 1.33 \times 10^{-12} U (\text{in/sec}) \end{aligned}$$

### Appendix 3

#### Calculation of Maximum Non-Dimensional Load Support, $W^*$ , For Laboratory Experiments With Gilding Metal

The slider had a circular contact area of 0.080 in diameter.

$x_2$  was estimated as 0.071 in.

$$\begin{aligned} W^* &= \frac{(\text{max. load})}{(\text{slider Diameter}) Lx_2} = \frac{98.5}{(0.080)(249,000)(0.071)} \\ &= 0.07 \end{aligned}$$

#### Calculation of $W^*$ for Gilding Metal During Engraving of M107 Projectile

$$\begin{aligned} W^* &= \frac{w}{Lx_2} = \frac{\text{bearing pressure}}{L} \\ &= \frac{50,000}{249,000} = 0.20 \end{aligned}$$

#### Calculation of $W^*$ for Copper During Engraving of M483 Projectile

$$W^* = \frac{50,000}{264,000} = 0.19$$

#### Calculation of Bearing Pressure Required for Self-Sustaining Liquid

##### Film Lubrication

$$\frac{W}{x_2} = W^*L$$

$$P = 0.2 L$$

$$\text{Al} = 30,000 \text{ psi}$$

$$\text{Cu} = 53,000 \text{ psi}$$

$$\text{gilding metal} = 50,000 \text{ psi}$$

$$\text{Fe} = 56,000 \text{ psi}$$

$$\text{Ni} = 75,000 \text{ psi}$$

$$\text{Zn} = 23,000 \text{ psi}$$

WATERVLIET ARSENAL INTERNAL DISTRIBUTION LIST

May 1976

	<u>No. of Copies</u>
COMMANDER	1
DIRECTOR, BENET WEAPONS LABORATORY	1
DIRECTOR, DEVELOPMENT ENGINEERING DIRECTORATE	1
ATTN: RD-AT	1
RD-MR	1
RD-PE	1
RD-RM	1
RD-SE	1
RD-SP	1
DIRECTOR, ENGINEERING SUPPORT DIRECTORATE	1
DIRECTOR, RESEARCH DIRECTORATE	2
ATTN: RR-AM	1
RR-C	1
RR-ME	1
RR-PS	1
TECHNICAL LIBRARY	5
TECHNICAL PUBLICATIONS & EDITING BRANCH	2
DIRECTOR, OPERATIONS DIRECTORATE	1
DIRECTOR, PROCUREMENT DIRECTORATE	1
DIRECTOR, PRODUCT ASSURANCE DIRECTORATE	1
PATENT ADVISORS	1

## EXTERNAL DISTRIBUTION LIST

May 1976

1 copy to each

CDR  
US ARMY MAT & DEV READ. COMD  
ATTN: DRCRD  
DRCRD-TC  
DRCRD-W  
5001 EISENHOWER AVE  
ALEXANDRIA, VA 22304

OFC OF THE DIR. OF DEFENSE R&E  
ATTN: ASST DIRECTOR MATERIALS  
THE PENTAGON  
WASHINGTON, D.C. 20315

CDR  
US ARMY TANK-AUTMV COMD  
ATTN: AMDTA-UL  
AMSTA-RKM MAT LAB  
WARREN, MICHIGAN 48090

CDR  
PICATINNY ARSENAL  
ATTN: SARPA-TS-S  
SARPA-VP3 (PLASTICS  
TECH EVAL CEN)  
DOVER, NJ 07801

CDR  
FRANKFORD ARSENAL  
ATTN: SARFA  
PHILADELPHIA, PA 19137

DIRECTOR  
US ARMY BALLISTIC RSCH LABS  
ATTN: AMXBR-LB  
ABERDEEN PROVING GROUND  
MARYLAND 21005

CDR  
US ARMY RSCH OFC (DURHAM)  
BOX CM, DUKE STATION  
ATTN: RDRD-IPL  
DURHAM, NC 27706

CDR  
WEST POINT MIL ACADEMY  
ATTN: CHMN, MECH ENGR DEPT  
WEST POINT, NY 10996

CDR  
US ARMY ARMT COMD  
ATTN: AMSAR-PPW-IR  
AMSAR-RD  
AMSAR-RDG  
ROCK ISLAND, IL 61201

CDR  
US ARMY ARMT COMD  
FLD SVC DIV  
ARMCOM ARMT SYS OFC  
ATTN: AMSAR-ASF  
ROCK ISLAND, IL 61201

CDR  
US ARMY ELCT COMD  
FT MONMOUTH, NJ 07703

CDR  
REDSTONE ARSENAL  
ATTN: AMSMI-RRS  
AMSMI-RSM  
ALABAMA 35809

CDR  
ROCK ISLAND ARSENAL  
ATTN: SARRI-RDD  
ROCK ISLAND, IL 61202

CDR  
US ARMY FGN SCIENCE & TECH CEN  
ATTN: AMXST-SD  
220 7TH STREET N.E.  
CHARLOTTESVILLE, VA 22901

DIRECTOR  
US ARMY PDN EQ. AGENCY  
ATTN: AMXPE-MT  
ROCK ISLAND, IL 61201

CDR  
HQ, US ARMY AVN SCH  
ATTN: OFC OF THE LIBRARIAN  
FT RUCKER, ALABAMA 36362

EXTERNAL DISTRIBUTION LIST (Cont)

1 copy to each

CDR  
US NAVAL WPNS LAB  
CHIEF, MAT SCIENCE DIV  
ATTN: MR. D. MALYEVAC  
DAHLGREN, VA 22448

DIRECTOR  
NAVAL RSCH LAB  
ATTN: DIR. MECH DIV  
WASHINGTON, D.C. 20375

DIRECTOR  
NAVAL RSCH LAB  
CODE 26-27 (DOCU LIB.)  
WASHINGTON, D.C. 20375

NASA SCIENTIFIC & TECH INFO FAC  
PO BOX 8757, ATTN: ACQ BR  
BALTIMORE/WASHINGTON INTL AIRPORT  
MARYLAND 21240

DEFENSE METALS INFO CEN  
BATTELLE INSTITUTE  
505 KING AVE  
COLUMBUS, OHIO 43201

MANUEL E. PRADO / G. STISSER  
LAWRENCE LIVERMORE LAB  
PO BOX 808  
LIVERMORE, CA 94550

DR. ROBERT QUATTRONE  
CHIEF, MAT BR  
US ARMY R&S GROUP, EUR  
BOX 65, FPO N.Y. 09510

2 copies to each

CDR  
US ARMY MOB EQUIP RSCH & DEV COMD  
ATTN: TECH DOCU CEN  
FT BELVOIR, VA 22060

CDR  
US ARMY MAT RSCH AGCY  
ATTN: AMXMR - TECH INFO CEN  
WATERTOWN, MASS 02172

CDR  
WRIGHT-PATTERSON AFB  
ATTN: AFML/MXA  
OHIO 45433

CDR  
REDSTONE ARSENAL  
ATTN: DOCU & TECH INFO BR  
ALABAMA 35809

12 copies

CDR  
DEFENSE DOCU CEN  
ATTN: DDC-TCA  
CAMERON STATION  
ALEXANDRIA, VA 22314

NOTE: PLEASE NOTIFY CDR, WATERVLIET ARSENAL, ATTN: SARWV-RT-TP,  
WATERVLIET, N.Y. 12189, IF ANY CHANGE IS REQUIRED TO THE ABOVE.