

AD-A137 561

EFFECTS OF IODINATION ON THE ELECTRICAL CONDUCTIVITY OF
HYDROGEN BIS(PHTH. .(U) NORTH CAROLINA UNIV AT CHAPEL
HILL DEPT OF CHEMISTRY L W HAAR ET AL. 25 JAN 84 TR-22
N00014-76-C-0816

1/1

UNCLASSIFIED

F/G 20/3


NL

END

FILED

3

DEC



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

12

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 22	2. GOVT ACCESSION NO. AD-A13756	3. RECIPIENT'S CATALOG NUMBER 1
4. TITLE (and Subtitle) Effects of Iodination on the Electrical Conductivity of Hydrogen Bis(Phthalocyaninato) Neodymium(III)		5. TYPE OF REPORT & PERIOD COVERED Technical Report, Interim
6. AUTHOR(s) Leonard W. ter Haar, William E. Hatfield and M. Tsutsui		6. PERFORMING ORG. REPORT NUMBER
7. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry 045A University of North Carolina Chapel Hill, North Carolina 27514		8. CONTRACT OR GRANT NUMBER(s) N00014-76-C-0816
9. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Department of the Navy Arlington, Virginia 22217		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
11. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE January 25, 1984
		13. NUMBER OF PAGES 13
		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release, Distribution Unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report) This document has been approved for public release and sale; its distribution is unlimited.		
18. SUPPLEMENTARY NOTES Prepared for publication in the <u>Journal of Molecular Crystals and Liquid Crystals.</u>		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) electrical conductivity hydrogen bis(phthalocyaninato) neodymium low-dimensional conducting materials iodination thermally activated transport sandwich compound		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Partial oxidation of hydrogen bis(phthalocyaninato) neodymium(III) by molecular iodine dramatically increases electrical conductivity. The results are discussed in terms of structural models.		

DTIC
ELECTE
S FEB 7 1984 D

AD A 1 3 7 5 6 1

DUPLICATE COPY

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A/1	



OFFICE OF NAVAL RESEARCH

Contract N00014-76-C-0816

Task No. NR 053-617

TECHNICAL REPORT NO. 22

EFFECTS OF IODINATION ON THE ELECTRICAL CONDUCTIVITY

OF HYDROGEN BIS(PHTHALOCYANINATO) NEODYMIUM(III)

BY

Leonard W. ter Haar and William E. Hatfield
 Department of Chemistry
 University of North Carolina
 Chapel Hill, NC 27514

M. Tsutsui*
 Department of Chemistry
 Texas A&M
 College Station, TX 77843

Prepared for publication
 in
 JOURNAL MOLECULAR CRYSTALS AND LIQUID CRYSTALS

Reproduction in whole or in part is permitted for any
 purpose of the United States Government.

This document has been approved for public release and
 sale; its distribution is unlimited.

*deceased

EFFECTS OF IODINATION ON THE ELECTRICAL CONDUCTIVITY
OF HYDROGEN BIS(PHTHALOCYANINATO) NEODYMIUM(III)

LEONARD W. ter HAAR and WILLIAM E. HATFIELD
Department of Chemistry, University of North
Carolina, Chapel Hill, N. C. 27514.

M. TSUTSUI*
Department of Chemistry, Texas A&M,
College Station, TX 77843.

Abstract Partial oxidation of hydrogen
bis(phthalocyaninato) neodymium(III) by molecular
iodine dramatically increases electrical
conductivity. The results are discussed in terms of
structural models.

INTRODUCTION

Subscript n

Iodination of metallomacrocycles has been shown to be an effective synthetic approach to low-dimensional conducting materials consisting of partially oxidized molecular stacks.^e The weakness of this approach is that there is little synthetic control over the the small differences in molecular and lattice forces which control the formation of stacks. An improvement to this approach was provided by the ("face-to-face") orientation of macrocycles found in the [M(Pc)O]_n materials.^e In this paper we show that a similar orientational effect exists in the linear chain compound,

* deceased

L.W. ter HAAR, W.E. HATFIELD AND M. TSUTSUI

composed of stacked hydrogen bis(phthalocyaninato) neodymium(III) [bis(Pc)Nd(III)] sandwich molecules.

EXPERIMENTAL

Bis(Pc)Nd(III) was prepared and purified using previously described methods.³ Partial oxidation of bis(Pc)Nd(III) was carried out with molecular iodine to obtain molecular compositions of bis(Pc)Nd(III)I_y with y = 1.3 and 1.8. All materials were air stable during the period of the measurements. A pressure of 10⁷ Pa was used to compress the materials into pellets 5 mm in diameter and typically 0.5 - 1.0 mm thick. The van der Pauw technique⁴ utilizing four probe conductivity measurements was used. The probes were attached to the pellets using silver paste contacts. Room temperature resistivity values were measured for several days to check for any chemical reaction at the electrodes; none was observed. After high temperature measurements (>300 K), room temperature resistivity was checked again to ascertain whether decomposition had occurred; none was observed. Several runs were made on each sample to demonstrate reproducibility. All possible permutations of the voltage and current leads around the four probe network were examined at high and low temperatures to assure legitimate use of the van der Pauw theorem. A typical D. C. current of 10⁻⁵ amps was used for variable temperature data sets. Ohmic behavior was observed for all samples.

RESULTS

Variable temperature resistivity data shown in Figure 1

ELECTRICAL CONDUCTIVITY OF $\text{bis}(\text{Pc})\text{Nd}(\text{III})(\text{I}_3)_x$




Figure 1. Electrical resistivity data for the series $\text{bis}(\text{Pc})\text{Nd}(\text{III})(\text{I}_3)_x$, with best fit lines.

indicate the polycrystalline samples to be thermally activated semiconductors. The data were fit by least-squares techniques to the thermally activated transport model

$$\sigma = \sigma_0 \exp(-\Delta/kT) \quad (1)$$

where σ_0 is the infinite temperature conductivity and Δ is the apparent activation energy. The parameters which describe each of the samples are set out in Table I. The data for $\text{bis}(\text{Pc})\text{Nd}(\text{III})$ are in agreement with previously determined data⁵ (in ambient hydrogen and in air) which had revealed that absorbed oxygen decreased the resistivity values and the activation energies. Exposure of the iodinated complexes to oxygen was not expected to alter the

L.W. ter HAAR, W.E. HATFIELD AND M. TSUTSUI

TABLE I Electrical conductivity parameters for the series bis(Pc)Nd(III)I_y.

y	σ_0 ($\Omega^{-1}\text{cm}^{-1}$)	σ_{RT} ($\Omega^{-1}\text{cm}^{-1}$)	Δ (eV)
0.0(air)	0.24	4.5×10^{-3}	0.103
1.3	0.21	6.4×10^{-2}	0.030
1.8	1.95	0.8×10^{-1}	0.023

conductivity data since further oxidation was unlikely. Partial oxidation of bis(Pc)Nd(III) by iodine dramatically reduces the resistivity and activation energy, as has been observed in the case of other metallomacrocycles.

DISCUSSION

The molecular structure of bis(Pc)Nd(III) has been determined to be that of a sandwich compound⁶ as opposed to the planar M(Pc) units found for first row transition metal compounds. The neodymium ion occupies an eight coordinate central position between two parallel but staggered (45°) phthalocyanine molecules (Figure 2). The eight neodymium-nitrogen bonds range from 2.39 to 2.49 Å. These molecular units pack into the crystal as a chain which has a herring bone motif. Location of the acidic hydrogen in the complex has been very elusive in terms of experimental verification. Nichol森, et. al.,⁷ proposed that the proton was firmly bound to only one of the phthalocyanine rings. To account for spectroscopic properties, Moskalev,

ELECTRICAL CONDUCTIVITY OF $\text{bis}(\text{Pc})\text{Nd}(\text{III})(\text{I}_3)_x$




Figure 2. Sandwich structure of $\text{bis}(\text{Pc})\text{Nd}(\text{III})$.

et. al.,⁸ suggested that the proton bridges $\text{bis}(\text{Pc})\text{Nd}(\text{III})$ units in solution to form $\mu\text{-H}$ dimers, trimers, etc.. Electrochemical studies⁹ of solutions have shown that lanthanide sandwich compounds of the type discussed here show electrochromic properties which can be related to the oxidation state of the phthalocyanine rings. Hence, the presence of the acidic proton is of considerable importance in the redox properties of these systems. X-ray photoelectron spectra⁶ have shown that the eight nitrogens are chemically equivalent. These documented experiments lead to the conclusion that the proton is located between the $\text{bis}(\text{Pc})\text{Nd}(\text{III})$ units in the solid state. Since the packing of the molecular units is similar to that of the β form of CuPc , this results in a "hydrogen bonding" bridged chain (Figure 3) qualitatively similar to the oxo-bridged $\text{M}(\text{Pc})\text{O}$ polymers.

In hydrogen atmosphere, $\text{bis}(\text{Pc})\text{Nd}(\text{III})$ exhibits an activation energy that is 25% of that of CuPc and a room temperature resistivity that is four orders of magnitude smaller than that of CuPc . Measurements on $\text{bis}(\text{Pc})\text{Nd}(\text{III})$




Figure 3. Hydrogen bonded molecules in bis(Pc)Nd(III) forming a linear chain structure.

exposed to ambient air, reveal decreased resistivity and activation energy relative to the same sample kept in a hydrogen atmosphere, presumably because of absorbed oxygen. The electrical conductivity values and activation energies for bis(Pc)Nd(III) are comparable to those of the Si(Pc)O polymer,² and bis(Pc)Nd(III) is a significantly better conductor than other M(Pc) systems. This can be understood in terms of the intermolecular hydrogen bond which promotes charge carrier transfer in a manner similar to that of the oxygen in the Si(Pc)O polymer. The presence of the acidic proton serves to bind the bis(Pc)Nd(III) units more tightly together resulting in shorter intermolecular contacts than

ELECTRICAL CONDUCTIVITY OF $\text{Bis}(\text{Pc})\text{Nd}(\text{III})(\text{I}_3)_x$

those usually observed in $\text{M}(\text{Pc})$ systems. Hence, the increased conductivity and lowered activation energy can be understood in terms of the decreased distance between molecules and the consequential enhanced motion of the charge carriers.

The charge carriers in $\text{bis}(\text{Pc})\text{Nd}(\text{III})$ are mobile within the molecular units, and so we conclude that the conductivity of the system can be improved if the sandwiches are brought closer together. The effect of absorbed oxygen indicates that partial oxidation of the stacks increases the conductivity. Controlled oxidation of $\text{bis}(\text{Pc})\text{Nd}(\text{III})$ by iodine verifies that this model is plausible. Furthermore, on a simple electrostatic basis, it may be seen that the molecular sandwich units repel each other less when they have been partially oxidized. As a consequence, the distance between sandwich units decreases, the interaction between them increases, and a decreased activation energy and improved charge carrier transport results. $\text{Bis}(\text{Pc})\text{Nd}(\text{III})\text{I}_{1.3}$ has nearly the same infinite temperature conductivity as the unoxidized material, but only a slightly larger activation energy than the $y = 1.8$ material. The $y = 1.8$ material has the smallest activation energy, and its infinite temperature conductivity is larger than in the other two samples. These results indicate that the first oxidation level ($y = 1.3$) decreases the activation energy nearly to the minimum value possible in this structure, while oxidation to the $y = 1.8$ level only affects the number and the characteristics of the charge carriers.

It is well known that single crystal conductivities of low dimensional materials are usually two to three orders

L.W. ter HAAR, W.E. HATFIELD AND M. TSUTSUI

of magnitude larger in the molecular stacking direction than in the pressed pellets of the same material. This is simply a consequence of the averaging of the crystallographic directions and interparticle resistance effects. Metallic conductivity behavior in the chain direction can be masked in the powder data due to the insulating behavior perpendicular to the stacking direction. One should compare bis(Pc)Nd(III)I_y powder data to that of a pressed pellet of the molecular metal Ni(Pc)I_{1.0},¹⁰ which has $\sigma_{RT} = 7 \times 10^{-1} \Omega^{-1} \text{cm}^{-1}$ and $\Delta = 0.04$ eV. However, single crystal room temperature conductivities along the stacking direction of Ni(Pc)I_{1.0} are on the order of $6 \times 10^2 \Omega^{-1} \text{cm}^{-1}$ and are metallic according to variable temperature data. This suggests that the conductivity of the bis(Pc)Nd(III)I_y materials may very well be metallic in the chain direction, thus stimulating continued efforts to obtain single crystals. This research was supported in part by the Office of Naval Research.

REFERENCES

1. J. A. Ibers, L. J. Pace, J. Martinsen, B. M. Hoffman, Structure and Bonding, **50**, 1 (1980).
2. K. F. Schoch, Jr., B. R. Kundalkar, T. J. Marks, J. Amer. Chem. Soc., **101**, 7071 (1979).
3. I. S. Kirin, P. N. Moskalev, Y. U. Makashev, Russ. J. Inorg. Chem., **10**, 1065 (1965).
4. L. J. van der Pauw, Philips Tech. Rev., **20**, 220 (1958).
5. M. Yamana, M. Tsutsui, J. S. Ham, J. Chem. Phys., **76**, 2761 (1982).
6. K. Kasuga, M. Tsutsui, R. C. Petterson, K. Tatsumi, N. van Opdenbosch, G. Pepe, E. F. Meyer, Jr., J. Amer. Chem. Soc., **102**, 4835 (1980).
7. M. M. Nicholson, F. P. Pizzarello, J. Electrochem. Soc., **126**, 490 (1979).
8. P. N. Moskaev, G. M. Shapkin, A. N. Darovskikh,

ELECTRICAL CONDUCTIVITY OF $\text{Bis}(\text{Pc})\text{Nd}(\text{III})(\text{I}_3)_x$

- Russ. J. Inorg. Chem., 24, 188 (1979).
9. G. A. Corker, B. Grant, N. J. Clecak, J. Electrochem. Soc., 126, 1339 (1979).
 10. C. J. Schramm, R. P. Scaringe, D. R. Stojakovic, B. M. Hoffman, J. A. Ibers, T. J. Marks, J. Amer. Chem. Soc., 102, 6702 (1980).

TECHNICAL REPORT DISTRIBUTION LIST, 053

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. M. P. Hawthorne Department of Chemistry University of California Los Angeles, California 90024	1	Dr. T. Marks Department of Chemistry Northwestern University Evanston, Illinois 60201	1
Dr. D. B. Brown Department of Chemistry University of Vermont Burlington, Vermont 05401	1	Dr. J. Zuckerman Department of Chemistry University of Oklahoma Norman, Oklahoma 73019	1
Dr. D. Venezky Chemistry Division Naval Research Laboratory Code 6130 Washington, D.C. 20375	1	Professor O. T. Beachley Department of Chemistry State University of New York Buffalo, New York 14214	1
Dr. John E. Jensen Hughes Research Laboratory 3011 Malibu Canyon Road Malibu, California 90265		Professor K. M. Nicholas Department of Chemistry Boston College Chestnut Hill, Massachusetts 02167	1
Dr. A. Cowley Department of Chemistry University of Texas Austin, Texas 78712	1	Professor R. Neilson Department of Chemistry Texas Christian University Fort Worth, Texas 76129	1
Dr. W. Hatfield Department of Chemistry University of North Carolina Chapel Hill, North Carolina 27514	1	Professor M. Newcomb Texas A&M University Department of Chemistry College Station, Texas 77843	1
Dr. M. H. Chisholm Department of Chemistry Indiana University Bloomington, Indiana 47401	1	Professor Richard Eisenberg Department of Chemistry University of Rochester Rochester, New York 14627	1
		Professor R. D. Archer University of Massachusetts Chemistry Department Amherst, Massachusetts 01003	

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 413 800 North Quincy Street Arlington, Virginia 22217	2	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Pasadena Detachment Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Dean William Tolles Naval Postgraduate School Monterey, California 93940	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
U.S. Army Research Office Attn: CRD-AA-IP P. O. Box 12211 Research Triangle Park, N.C. 27709	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Mr. Vincent Schaper DTNSRDC Code 2803 Annapolis, Maryland 21402	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1	Mr. A. M. Anzalone Administrative Librarian PLASTECH/ARRADCOM Bldg 3401 Dover, New Jersey 07801	1

END

FILMED

3-84

DTIC