

A D-R146 378

CHEMICAL DERIVATIZATION OF MICROELECTRODE ARRAYS BY  
OXIDATION OF PYRROLE R. (U) MASSACHUSETTS INST OF TECH  
CAMBRIDGE DEPT OF CHEMISTRY G P KITTLESEN ET AL.


1/1


UNCLASSIFIED

10 SEP 84 TR-2-ONR N00014-84-K-0553

F/G 9/1

NL





COPY RESOLUTION TEST CHART

UNCLASSIFIED

12

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER <b>ONR-TR2</b>	2. GOVT ACCESSION NO. <b>AD-A146378</b>	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) "Chemical Derivatization of Microelectrode Arrays by Oxidation of Pyrrole and N-Methylpyrrole: Fabrication of Molecule-Based Electrode Devices"		5. TYPE OF REPORT & PERIOD COVERED Interim Technical Report
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) Gregg P. Kittlesen, Henry S. White and Mark S. Wrighton		8. CONTRACT OR GRANT NUMBER(s) N00014-84-K-0553
9. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry, Rm. 6-335 Massachusetts Institute of Technology Cambridge, Massachusetts 02139		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS  NR-051-579
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Department of the Navy Arlington, Virginia 22217		12. REPORT DATE September 10, 1984
		13. NUMBER OF PAGES 38
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report)  Approved for public release; reproduction is permitted for any purpose of the United States Government; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)  Distribution of this document is unlimited.		
18. SUPPLEMENTARY NOTES  Prepared for publication in the <u>Journal of the American Chemical Society.</u>		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)  chemical derivatization, microelectrode arrays, molecule-based electrodes, oxidation		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)  See reverse side.		

AD-A146 378

DTIC FILE COPY

DD FORM 1473 1 JAN 73

EDITION OF 1 NOV 65 IS OBSOLETE S/N 0102-014-6601

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

39

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

An array of eight Au microelectrodes, each  $-0.12 \mu\text{m}$  thick,  $3 \mu\text{m}$  wide, and  $140 \mu\text{m}$  long separated from each other by a distance of  $1.4 \mu\text{m}$ , has been fabricated on a  $0.45 \mu\text{m}$  thick  $\text{SiO}_2$  layer grown on a single crystal Si substrate using standard microfabrication techniques. Each electrode can be individually addressed and characterized electrochemically. The individual electrodes can be functionalized with polypyrrole or with poly-N-methylpyrrole by oxidation of pyrrole or N-methylpyrrole, respectively, using conditions similar to those for macroscopic electrodes. The amount of polymer deposited can be controlled and it is possible to electrically "connect" adjacent microelectrodes with deposited polymer. Since the reduced forms of these polymers are insulating and the oxidized forms are electronically conducting it is possible to prepare electronic devices that are analogous to diodes and transistors using adjacent microelectrodes connected with polymer. The current passing between two microelectrodes connected with polymer as a function of potential between them, and when both are fully oxidized to the conducting state of the polymer, allows a measure of the maximum conductivity of the polymer. We find that polypyrrole is about  $10^2$  to  $10^3$  times less resistive than poly-N-methylpyrrole, consistent with previous studies of these two materials. Scanning electron microscopy confirms that polymer can be grown in controlled amounts to selectively connect adjacent microelectrodes.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

OFFICE OF NAVAL RESEARCH

CONTRACT N00014-84-K-0553

Task No. NR 051-579

TECHNICAL REPORT NO. 2

"CHEMICAL DERIVATIZATION OF MICROELECTRODE ARRAYS BY  
OXIDATION OF PYRROLE AND N-METHYLPYRROLE:  
FABRICATION OF MOLECULE-BASED ELECTRODE DEVICES"

by

Gregg P. Kittlesen, Henry S. White, and Mark S. Wrighton

Prepared for Publication

in the

Journal of the American Chemical Society

Department of Chemistry  
Massachusetts Institute of Technology  
Cambridge, Massachusetts 02139

September 10, 1984

BIB  
COPY

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Avail and/or	
Dist	Special

A-1

Reproduction in whole or in part is permitted for  
any purpose of the United States Government.

This document has been approved for public release  
and sale; its distribution is unlimited.

CHEMICAL DERIVATIZATION OF MICROELECTRODE ARRAYS BY OXIDATION OF PYRROLE AND  
N-METHYLPYRROLE: FABRICATION OF MOLECULE-BASED ELECTRONIC DEVICES

Gregg P. Kittlesen, Henry S. White and Mark S. Wrighton\*

Department of Chemistry  
Massachusetts Institute of Technology  
Cambridge, Massachusetts 02139

\*Address correspondence to this author.

Abstract: An array of eight Au microelectrodes, each  $\sim 0.12 \mu\text{m}$  thick,  $3 \mu\text{m}$  wide, and  $140 \mu\text{m}$  long separated from each other by a distance of  $1.4 \mu\text{m}$ , has been fabricated on a  $0.45 \mu\text{m}$  thick  $\text{SiO}_2$  layer grown on a single crystal Si substrate using standard microfabrication techniques. Each electrode can be individually addressed and characterized electrochemically. The individual electrodes can be functionalized with polypyrrole or with poly-N-methylpyrrole by oxidation of pyrrole or N-methylpyrrole, respectively, using conditions similar to those for macroscopic electrodes. The amount of polymer deposited can be controlled and it is possible to electrically "connect" adjacent microelectrodes with deposited polymer. Since the reduced forms of these polymers are insulating and the oxidized forms are electronically conducting it is possible to prepare electronic devices that are analogous to diodes and transistors using adjacent microelectrodes connected with polymer. The current passing between two microelectrodes connected with polymer as a function of potential between them, and when both are fully oxidized to the conducting state of the polymer, allows a measure of the maximum conductivity of the polymer. We find that polypyrrole is about  $10^2$  to  $10^3$  times less resistive than poly-N-methylpyrrole, consistent with previous studies of these two materials. Scanning electron microscopy confirms that polymer can be grown in controlled amounts to selectively connect adjacent microelectrodes.

We wish to report the chemical functionalization of a microelectrode array in a manner that illustrates the fabrication of molecule-based electronic devices having a dimension of  $1.4 \mu\text{m}$ . Our fundamental objective is to illustrate a synthetic methodology that can, in principle, lead to the preparation of aggregate chemical systems that have a specific function. Integration of chemical (and biological) systems with microelectronics seems possible inasmuch as solid state devices now involve crucial dimensions of the same order as large molecular assemblies. A preliminary communication shows that it is possible to fabricate a molecule-based transistor using three derivatized microelectrodes.<sup>1</sup> This paper is a full account of the procedures used to synthesize such devices.

Our work involves the rational chemical functionalization of an array of small (nominally  $2 \mu\text{m}$  wide x  $140 \mu\text{m}$  long x  $0.12 \mu\text{m}$  thick) Au electrodes. The nominal separation between the  $2 \times 100 \mu\text{m}$  Au electrodes is  $2 \mu\text{m}$ . Figure 1 shows a cross-sectional view of the microelectrode array. The particular design is somewhat arbitrary, but the crucial features are that we have several small electrodes, separated by a small dimension, that can be contacted individually. The exact dimensions are not crucial except that we wish to take advantage of the small dimensions to illustrate that certain kinds of materials properties can be probed, that it is possible to independently functionalize closely spaced adjacent electrodes, and that the functionalization of such arrays can be useful in preparing new kinds of devices based on rational molecular chemistry. Some of the unique properties of microelectrodes have recently been reported in the literature.<sup>2-5</sup> Additionally, much relevant work has been done on modification of macroscopic electrodes.<sup>6-10</sup> We note, in particular, that work on so-called bilayer

assemblies comprises part of the basis for diode devices based on redox active polymers.<sup>11</sup> One especially important piece of work is that of Pickup and Murray showing that "diodes" and "triodes" can be prepared using macroscopic electrodes derivatized with a redox polymer coated with a porous metal contact.<sup>12</sup> Also, the 2  $\mu\text{m}$  separation between the microelectrodes of the array represented in Figure 1 should allow studies of some of the polymeric materials used to modify macroscopic electrodes, since polymers of this thickness can pass significant current density in steady state current experiments using modified electrodes.<sup>13</sup>

Our initial work on the microelectrode array shown in Figure 1 concerns the functionalization of the microelectrodes with conducting polymers formed from the oxidation of pyrrole and N-methylpyrrole at the Au surfaces. The formation of electronically conducting polypyrrole and poly-N-methylpyrrole has previously been reported via oxidation of the monomers at macroscopic electrodes.<sup>14</sup> In connection with the present work, the significant facts are that the polymers have very different conductivity in the reduced and oxidized states and that the oxidized states are sufficiently conducting that significant current can pass through a several micron thickness. We seek to show that the individual microelectrodes can be functionalized in a controlled manner with a polymer and that the conductivity properties of the polymers can be exploited to make devices that have a diode characteristic with respect to current-potential behavior. Our work illustrates that it may be possible to make new kinds of electronic devices,<sup>15</sup> including microsensor arrays,<sup>16</sup> based on the functionalization of microelectrodes. For example, our molecule-based transistor<sup>1</sup> is similar to a "chemiresistor"<sup>16</sup> that can be used to detect gases that cause a change in the resistance of a chemical coating between an interdigitated pair of electrodes.

## EXPERIMENTAL SECTION

Fabrication of Microelectrode Arrays. The fabrication of microelectrode arrays was carried out in the M.I.T. Microelectronics Laboratory equipped to prepare the completed device represented by the layout in Figure 2 with the cross-sectional view given in Figure 1. The procedure begins with the design of the array and the preparation of masks to be used in the microfabrication procedure. The microelectrode array was designed using the Computer Aided Design program HPEDIT at a Hewlett Packard Model 2648A graphics terminal on a DEC-20. The design file was translated into Caltech Intermediate Form (CIF). This CIF file was translated to Mann compatible code and written on magnetic tape. Masks for photolithography were made from the file on magnetic tape using a Gyrex Model 1005A Pattern Generator. E-K 5" x 5" x 0.090" Extra Flat high resolution glass emulsion plates were used to make the photolithography masks. The emulsion plates were developed by a dark field process.

p-Si wafers of <100> orientation, 2" diameter, and 0.011" thickness obtained from Wacker were used as substrates upon which to fabricate the microelectrode arrays. The fabrication work was performed in the MIT Microelectronics Lab, a class 100 clean room. The silicon wafers were RCA cleaned in a laminar air flow hood. The wafers were immersed in hot aqueous H<sub>2</sub>O<sub>2</sub> (6% by volume/aqueous NH<sub>3</sub> (14% by volume), briefly etched in HF (diluted 10-1 with deionized water), immersed in hot aqueous H<sub>2</sub>O<sub>2</sub> (6% by volume)/HCl (14% by volume), rinsed in deionized water (>14 MΩ·cm), and spun dry. The cleaned wafers were loaded immediately into an oxidation tube furnace at 1100°C under N<sub>2</sub>. A dry/wet/dry/anneal oxidation cycle was used to grow a thermal oxide 4500 Å thick. Oxide thicknesses were measured using a Gaertner Model L117 ellipsometer and a Nanometrics NanoSpec/AFT. The oxidized wafers were taken immediately to the photolithography stage.

Each oxidized wafer was flood-coated with hexamethyldisilazane and spun at 6000 rpm for 20 sec. One ml of MacDermid Ultramac PR-914 positive photoresist was syringed onto each wafer. The wafer coated with resist was spun for 30 sec at 4000 rpm. The wafer coated with resist was then prebaked 35 min at 90° C.

A GCA Mann 4800 DSW Wafer Stepper was used to expose the photoresist. The Mann uses the 405 nm line of a 350 W Hg arc lamp as a light source. The mask image is reduced 5:1 in the projection printing. An exposure time of 0.85 sec was used. The exposed photoresist was developed 60 sec in MacDermid Ultramac MF-62 diluted 1:1 with deionized water.

A bilayer metallization was performed in a MRC 8620 Sputtering System. Wafers were placed on a quartz plate that was freshly coated with Cr. The wafers were backsputtered 2 min at 50 W forward power in an Ar plasma at 5 mtorr. Cr was sputtered at 50 W forward power to give a layer 200 Å thick. Au was then sputtered at 50 W forward power to give a layer 1000 Å thick. Cr serves as an adhesion layer.

At this point Cr/Au was in contact with the SiO<sub>2</sub> substrate only in the areas that were to form the microelectrodes, leads, and contact pads. The Cr/Au was deposited on photoresist in all other areas. This resist/Cr/Au on the oxide was removed by a lift-off procedure. The metallized wafers were immersed in warm acetone for 75 min. The soft-baked positive photoresist is soluble in acetone. The wafers were briefly sonicated in acetone to remove the metal between microelectrodes and dried. Wafers were then cleaned of residual photoresist in a planar oxygen plasma etching chamber at 200 W forward power in 50 mtorr oxygen for 60 sec.

Individual die (chips) were scribed and separated. The chips were mounted on TO-5 headers with Epoxi-Patch 0151 Clear (Hysol). A Mech-EI Ind. Model NU-827 Au ball ultrasonic wire bonder was used to make wire bonds from

the chip to the T0-5 header. The leads, bonding pads, wire bonds, and header were encapsulated with Epoxi-Patch 0151. The header was connected through a T0-5 socket to external wires. The external wires were encased in a glass tube. The header was sealed at the distal end of the glass tube with heat shrink tubing and Epoxi-Patch 1C white epoxy (Hysol).

Prior to use as a microelectrode array, the array was tested to establish the leakage current between the various electrodes of the array. Arrays characterized as usable have a measured resistance between any two electrodes of greater than  $10^9 \Omega$  in non-aqueous electrolyte solution containing no added electroactive species. In many cases only a fraction of the electrodes of an array were usable. Prior to use in experimentation the microelectrode arrays were tested further in aqueous electrolyte solution containing 0.01 M  $\text{K}_3[\text{Fe}(\text{CN})_6]$  and 0.01 M  $\text{K}_4[\text{Fe}(\text{CN})_6]$  to establish that the microelectrodes give the expected response. In many cases the electrodes were non-functioning as if covered with a layer of insulating material. Typically a negative potential excursion to evolve  $\text{H}_2$  cleaned the Au surface sufficiently to give good electrochemical response to the  $\text{Fe}(\text{CN})_6^{3-/4-}$  redox couple. We have found that  $\text{Cl}^-$ -containing media give rapid corrosion of the devices and have restricted our electrolyte to 0.1 M  $\text{LiClO}_4$  or 0.1 M  $\text{NaClO}_4$  in  $\text{H}_2\text{O}$  solvent or 0.1 M  $[\text{n-Bu}_4\text{N}]\text{ClO}_4$  in  $\text{CH}_3\text{CN}$  solvent. Completed, tested, and cleaned arrays were used in further experiments.

Electrochemical Equipment. Most of the electrochemical experimentation was carried out using a Pine Model RDE 3 bipotentiostat and potential programmer. In cases where two microelectrodes were under active potential control and a third was to be probed, a PAR Model 363 potentiostat/galvanostat was used in

conjunction with the Pine Model RDE 3. All potentials were controlled relative to an aqueous saturated calomel reference electrode (SCE). Typically, electrochemical measurements were carried out under N<sub>2</sub> or Ar at 25°.

Derivatization of Microelectrodes. The Au microelectrodes were functionalized by oxidation of 25-50 mM pyrrole or N-methylpyrrole in CH<sub>3</sub>CN/0.1 M [n-Bu<sub>4</sub>N]ClO<sub>4</sub>. The polypyrrole was deposited at +0.8 V vs. SCE, and the poly-N-methylpyrrole was deposited at +1.2 V vs. SCE, as previously described.<sup>14</sup> The deposition of the polymer can be effected in a controlled manner by removing the array from the derivatization procedure after passing a certain amount of charge. Electrodes were then examined by cyclic voltammetry in CH<sub>3</sub>CN/0.1 M [n-Bu<sub>4</sub>N]ClO<sub>4</sub> to assess the coverage of polymer and to determine whether the polymer coated two or more electrodes resulting in a "connection" between them.

Scanning Electron Microscopy. The microelectrode arrays were examined by electron microscopy using a Cambridge Mark 2A Stereoscan with a resolution of 20 nm. The arrays were first coated with ~200 Å of Au to minimize problems from surface charging.

## RESULTS AND DISCUSSION

Fabrication of Microelectrode Arrays. Figures 1 and 2 represent the design of the microelectrode arrays used in this study. However, the actual devices are somewhat different in certain details as illustrated by the electron micrographs shown in Figure 3. Most importantly, the Au microelectrodes are  $-3 \mu\text{m}$  wide with a spacing of  $-1.4 \mu\text{m}$  between them. The slightly larger electrode width is not consequential, but the smaller spacing between them allows larger currents to pass when the electrodes are "connected" with a covering of polymer, vide infra. Also, note that the outer two microelectrodes of the eight electrode array are thinned as are some of the wires to the contact pads. The separation of the outer electrodes and the immediately adjacent electrode is still  $1.4 \mu\text{m}$ , and we have found no measurable consequence from either the thinned electrode or the thinned connecting wires to the contact pads. The thinned wires are a consequence of difficulties in the metal lift-off procedure but do not affect the performance in the experiments described here. The wider Au wires yielding smaller spacings is also a consequence of the microfabrication procedure and can actually be used to advantage in the study of the charge transport properties of deposited polymers.

A word about yield of useful devices is appropriate. Starting with a 2" diameter Si wafer yields 177 microelectrode arrays after cutting the wafer into individual chips containing the array and its contact pads. It is difficult to cite good yield data with so little in the way of statistics, but it is not uncommon to have one of every two microelectrode arrays that function properly in the test procedure that sorts out usable devices. However, it is not typical to have arrays with eight functioning electrodes for a variety of reasons including broken leads to contact pads, overflow of

epoxy insulation, and incomplete metal lift-off. Low device yield is one of the most frustrating parts of the work described in this paper. Unlike molecular substances, there are no easy methods to "purify" chips. In principle, improvement in usable device yield can be realized with greater attention to details in the microfabrication procedure.

In terms of the microfabrication procedure itself, the most tedious, time consuming and difficult task is the insulation of all exposed metal (contact pads, leads, and bonding wires) except for the eight microelectrodes. The area of desired exposure is approximately  $4 \times 10^{-3} \times 1.5 \times 10^{-2}$  cm to allow electrolyte contact with only the eight exposed electrodes. Presently, the procedure is to use a fast drying epoxy applied with the tip of a syringe needle by hand while observing through an optical microscope at 50X. This procedure works which is its only virtue. Earlier we had attempted to define the microelectrode region with a polyimide, but we found that electrolyte could penetrate and come in contact with connecting wires and even contact pads. Future effort is to be directed towards the development of a procedure for automated, complete insulation of all metal except the microelectrode array itself.

Electrochemical Characterization of Microelectrode Arrays. The microelectrode arrays were typically examined in  $\text{H}_2\text{O}/0.1 \text{ M LiClO}_4/0.01 \text{ M K}_3[\text{Fe}(\text{CN})_6]/0.01 \text{ M K}_4[\text{Fe}(\text{CN})_6]$  to determine the electrochemical response to the  $\text{Fe}(\text{CN})_6^{3-/4-}$  ( $E^\circ = +0.2 \text{ V vs. SCE}$ )<sup>17</sup> redox couple. Linear potential sweep voltammograms of a good microelectrode array are shown in Figure 4. As seen in Figure 4, the linear sweep voltammogram at the 50 mV/s sweep rate shown indicates that the current is limited by diffusion of the  $\text{Fe}(\text{CN})_6^{3-/4-}$  redox couple, and the current-potential curve characteristic of a macroscopic Au

electrode for this redox couple is not seen. This is the behavior expected for electrodes having a sufficiently small dimension. Much of the work on microelectrodes and their current-potential characteristics has concerned planar disks,<sup>1-5</sup> but considerations of other electrode geometries suggest that the smaller dimension (3  $\mu\text{m}$ ) of our rectangular electrodes is the one of consequence in assessing the sweep rate dependence of the current-potential behavior. We will elaborate further on this issue in a separate article.

The current-potential curves in Figure 4 establish that it is possible to prepare an array of electrodes each of which can be contacted individually to give the good response to a solution species. The magnitude of the limiting current, the point of zero current, and the similarity of response from each of the electrodes are the points of importance. The variations in limiting current are likely a consequence of epoxy runover to varying degrees over the microelectrodes. The characterization represented by Figure 4 simply indicates that working electrodes can be fabricated and are expected to be useful in chemical derivatization studies.

Chemical Derivatization of Microelectrodes with Polypyrrole and Poly-N-methylpyrrole. Figure 5 represents the essential objective in functionalizing the microelectrode arrays with polymers derived from pyrrole or N-methylpyrrole. We seek to illustrate that it is possible to electrochemically deposit electroactive polymers on an individual electrode and in variable amounts. Most importantly, we seek to illustrate that it is possible to deposit sufficient amounts of polymer that two or more electrodes can be bridged with the polymer and thereby be "connected" to each other via the polymer. By "connected" we mean connected in the electronic sense; the consequence is that charge can pass from one microelectrode to another via conduction mechanisms

of the polymer. Experiments detailed below establish that we are able to achieve the situation represented by Figure 5.

Au microelectrodes can be functionalized with polypyrrole by oxidation of 25-50 mM pyrrole in CH<sub>3</sub>CN/0.1 M [n-Bu<sub>4</sub>N]ClO<sub>4</sub> as described for macroscopic electrodes<sup>14</sup> and detailed in the Experimental Section. Figure 6 shows the cyclic voltammetry of a polypyrrole modified array in CH<sub>3</sub>CN/0.1 M [n-Bu<sub>4</sub>]ClO<sub>4</sub> containing no added redox active species. Some of the eight microelectrodes were not purposefully functionalized with polypyrrole and show negligible amounts present, based on the lack of a cyclic voltammetry signal characteristic of electrode-confined polymer.<sup>14</sup> Immediately adjacent to electrodes which were not derivatized are electrodes that show cyclic voltammograms characteristic of electrode-confined polypyrrole. The shape of the voltammogram is nearly the same as found for a macroscopic Au electrode derivatized in the same manner. Further, the potential of the oxidation and reduction peaks are as expected for the oxidation and reduction of polypyrrole. Controlled amounts of polypyrrole can be deposited, based on the integration of the charge passed upon cycling the derivatized microelectrodes individually between the negative and positive potential limits. For several of the electrodes the current-potential curves are the same and the integrated charge is large. These electrodes are covered by polypyrrole in such a way that they are connected. Typically, connected electrodes are associated with coverages of  $\sim 10^{-7}$  mol/cm<sup>2</sup>. Addressing one electrode oxidizes and reduces the polymer over all of them. This point will be elaborated fully below, but the important conclusion here is that it is possible to deposit controlled amounts of polypyrrole on a given electrode. This is an especially important point because it establishes the viability of derivatizing adjacent microelectrodes with different polymers, the subject of another article.<sup>18</sup>

In a manner similar to that for polypyrrole, it is possible to derivatize a microelectrode array with poly-N-methylpyrrole. Again, it is possible to derivatize in a controlled fashion and to leave some microelectrodes "naked", some with a small amount of polymer, and some with sufficient polymer to connect two or more microelectrodes. The poly-N-methylpyrrole derivatized electrodes can be characterized by cyclic voltammetry in  $\text{CH}_3\text{CN}/0.1 \text{ M } [\text{n-Bu}_4\text{N}]\text{ClO}_4$  showing the oxidation and reduction of the polymer occurring at a somewhat more positive potential than for polypyrrole, as expected.<sup>14</sup> The deposited polymers can also be observed on the microelectrodes using scanning electron microscopy. Figure 7 illustrates three electrodes of one array having little or no poly-N-methylpyrrole on them and no obvious connection compared to three other microelectrodes on the same array having an amount of polymer sufficient to connect them. For this particular array electrochemical characterization showed that the heavily coated microelectrodes are connected and the lightly coated electrodes simply showed a cyclic voltammogram of a poly-N-methylpyrrole derivatized Au electrode. We do not, however, regard the electron microscopy as an unambiguous indicator of whether the microelectrodes are connected. We rely on the electrical and electrochemical measurements to establish this. The microscopy does reveal considerable unevenness in the coverage of the microelectrodes, perhaps as a consequence of the large ratio of length to distance of separation of the electrodes. We intend to lower this ratio to achieve greater reproducibility and evenness of coverage of the electrodes. The point here is that the long electrodes may have random, irreproducible initiation sites for polymer growth that make uneven connections between adjacent electrodes. In any event, the scanning electron microscopy is in qualitative accord with electrochemical experiments, both in terms of where polymer was supposed to have been deposited and the amounts subsequently measured by cyclic voltammetry in  $\text{CH}_3\text{CN}/0.1 \text{ M } [\text{n-Bu}_4\text{N}]\text{ClO}_4$ .

The electrochemical deposition procedure allows the functionalization of one microelectrode at a time, even at the 1.4  $\mu\text{m}$  spacing employed in the microelectrode array. Both the microscopy and the electrochemical characterization show that there is little spreading of the polymer until sufficient quantities have been deposited that two, or more, microelectrodes are connected. Connection between two electrodes so closely spaced is what makes possible the measurement of some of the properties of the deposited polymers and the fabrication of certain kinds of electronic devices. These issues will be dealt with in the following section.

Molecule-Based Electronic Devices and Polymer Conductivity. The ability to electrically connect two, or more, microelectrodes with a polymer having very different conductivity in two redox levels raises the possibility of making new kinds of electronic devices. For the polypyrrole and the poly-N-methylpyrrole the oxidized materials are electronic conductors and the reduced state is essentially insulating. The conductivity varies by a factor of more than  $10^{10}$ , depending on the redox state of these polymers.<sup>14</sup> We have undertaken experiments that show that these conductivity properties can be measured using heavily coated microelectrode arrays and that the current passing between two connected microelectrodes as a function of the potential between them can vary as for a diode. The threshold potential of the diode and the current-potential curve depend on the polymer.

Figure 8 summarizes the results of an experiment using a microelectrode array where five electrodes are connected using polypyrrole. The experiment is to determine the spatial potential distribution across the polypyrrole-coated microelectrode array when one or two of the electrodes is under active potential control. The entire array is immersed in  $\text{CH}_3\text{CN}/0.1 \text{ M } [\text{n-Bu}_4]\text{ClO}_4$  and a bipotentiostat is used to actively control the potential of one or two microelectrodes against a common reference and counter electrode in the solution.

To establish that the microelectrodes are connected we set the potential of one (electrode #5 in Figure 8a) of the five electrodes at a negative potential,  $-1.0$  V vs. SCE, and one (electrode #2 in Figure 8a) at a variable positive potential and measure the potential of the microelectrodes not under active potential control. As shown in Figure 8a all of the electrodes, except for the one under active control at  $-1.0$  V vs. SCE, are nearly equal to the positive potential applied to electrode #2. A small potential drop ( $\sim 50$  mV) occurs over the  $\sim 9$   $\mu\text{m}$  distance separating electrodes #2 and 4, but the essential finding is that nearly all (up to  $1.8$  V) of the potential drop occurs across a narrow region immediately adjacent to electrode #5 under active potential control at  $-1.0$  V. This result is consistent with the difference in conductivity<sup>14</sup> of the reduced and oxidized state of polypyrrole. The consequence of the extreme difference in conductivity with redox state is that the potential drop can occur across a very small fraction of length of the connecting polymer when one microelectrode is held at a potential where the polymer is reduced and insulating and another is held at a potential where the polymer is oxidized and conducting. Such would not be expected for a polymer having only modest conductivity, as for polymers that exhibit so-called redox conductivity, where a linear change in concentration of redox centers across the thickness spanned by two electrodes at differing potentials would give a potential profile predicted by the Nernst equation.<sup>13b,19</sup> The experiment represented by Figure 8 illustrates part of the value of the microelectrode array in that a polymer film can be probed at small spatial intervals. Figure 8b shows that when only one of the microelectrodes is under active potential control in the positive region all of the electrodes are measured to be at the same potential as would be expected when there is an electrical connection between them. When one of the microelectrodes is driven negative it would be expected that all would ultimately follow, but upon reduction the polymer becomes insulating and the rate of potential following can be expected to be slower.

Figure 9 shows current-potential data which establish that diode behavior from polypyrrole connected microelectrodes does obtain. What is shown is a family of current vs.  $V_{app}$  curves as a function of the the potential,  $V_{set}$ , at which one of the electrodes is fixed relative to the SCE. The current measured is that passing between the two microelectrodes. We have established that the magnitude of the current passing through one microelectrode is identical to that passing through the other microelectrode but opposite in sign. Note that when  $V_{set}$  is sufficiently positive that the current- $V_{app}$  curve is linear over a wide range of  $V_{app}$ ; the resistance of polypyrrole from the slope of such plots is about  $10^3 \Omega$ . When  $V_{set}$  is sufficiently negative, there is a broad range of the current- $V_{app}$  curve where there is insignificant current. Thus, for a value of  $V_{set}$  sufficiently negative, a good diode characteristic can be obtained, Figure 10. The onset of current corresponds closely to the situation where the  $V_{app}$  results in the conversion of the polypyrrole from its reduced and insulating state to its oxidized and strongly conducting state, as would be expected.

It is interesting that we are able to observe steady current densities exceeding  $1 \text{ kA/cm}^2$  for two Au microelectrodes connected by polypyrrole. This current density is calculated using the exposed geometrical area of a Au electrode. The unevenness of the polymer in terms of the coverage and degree of connection between two adjacent Au electrodes makes it difficult to establish the current density in the film. However, the  $1 \text{ kA/cm}^2$  is a lower limit, since the thickness of the polymer is  $\sim 1 \mu\text{m}$ .

Data similar to those shown in Figure 9 for polypyrrole have also been obtained for two microelectrodes connected with poly-N-methylpyrrole. However, the value of  $V_{set}$  necessary to obtain a current that is linear with variation in  $V_{app}$  is more positive than with polypyrrole and the resistance of the poly-N-methylpyrrole is  $10^5$ - $10^6 \Omega$ . Both the higher resistance and the more

positive potential necessary to obtain the conducting regime are consistent with the known differences between the two polymers.<sup>14</sup> Two adjacent microelectrodes connected with poly-N-methylpyrrole can function as a diode also, Figure 10. We see that the threshold potential is greater than for the polypyrrole, consistent with the more positive potential needed to bring the poly-N-methylpyrrole to its maximum conductivity state. The current densities for the diodes represented by the data in Figure 10 are high, and especially so for the polypyrrole device. This is a consequence of the close spacing of the electrodes, coupled with the reasonable conductivity of the polymers. The diode characteristics illustrated in Figure 10 show an impressive direct current-potential relationship. It should be noted, though, that the on-off rate will be determined by chemical reactions of the polymer. The on-off rate for the polypyrrole and poly-N-methylpyrrole devices described here is ~10 s. The curves in Figures 9 and 10 are essentially steady-state (<5 mV/s). Fast sweep rates give fast turn on but slow turn off resulting in large hysteresis in the current-potential curves.

For both the polypyrrole and the poly-N-methylpyrrole we have estimated the actual conductivities of the oxidized polymers from several measurements on independently prepared microelectrode arrays having two or more electrodes connected with the polymer. The values are  $\sim 10^{-2}$  and  $\sim 10^{-4}$ - $10^{-5}$   $\Omega^{-1}\cdot\text{cm}^{-1}$  for the polypyrrole and the poly-N-methylpyrrole, respectively, in fair agreement with the range of conductivities reported in the literature.<sup>14</sup> The relative conductivity of the polypyrrole and poly-N-methylpyrrole is also in accord with what is known about these two polymers. Greater confidence is placed in the relative conductivity of the two polymers, rather than in absolute values, because the dimensions and geometry are not accurately known.

The "diode" devices described here are different from a solid state diode,<sup>20</sup> e.g. a p-n junction or a semiconductor/metal Schottky barrier. The solid state

devices, in addition to having capability of high frequency operation, are two terminal devices. In effect, the molecule-based diodes characterized here are, in fact, triodes where the ability to pass current in only one direction (as for a diode) depends on fixing one of the terminals to a potential,  $V_{set}$ , relative to the SCE. Thus, the solution represents a third terminal. This relationship has been pointed out by Pickup and Murray<sup>12</sup> for a macroscopic diode/triode based on a redox polymer. Work is underway in this laboratory to fabricate a two terminal molecule-based diode by derivatizing adjacent microelectrodes with two different redox polymers such that the two polymers do connect. Dissimilar values of  $E^{\circ}$  for the two connected polymers will allow current to flow in only one direction without the restriction of having active potential control of one of the terminals, as for the devices described here.

In some respects, the diode/triode devices described here resemble solid state transistors<sup>20</sup> where  $V_{set}$  is the analogue of the gate potential,  $V_G$ , and  $V_{app1}$  is the drain potential,  $V_D$ . A difference, of course, is that in the solid state devices the potentials are referenced to ground whereas the potentials for the devices described here are referenced to a reference electrode immersed in the solution. The charge passed associated with movement in  $V_{set}$  from a negative potential where the polymer is insulating to a positive potential where the polymer is conducting can be regarded as the signal (charge) necessary to turn the device "on". The data in Figure 9 for a polypyrrole-based device shows that the device starts to turn on between a  $V_G$  of -0.4 and -0.2 V vs. SCE. This is the analogue of the threshold voltage,  $V_T$ , for a solid state device and corresponds to the potential where polypyrrole becomes conducting. Solid state transistors do not, however, have a diode-like  $V_D$  vs. drain current,  $I_D$ , characteristic. Thus, the molecule-based devices do differ in important ways compared to solid state devices.

In our recent communication<sup>1</sup> we referred to an array of three microelectrodes connected with polypyrrole as a molecule-based transistor. In that device one of the three electrodes was regarded as the gate with the other two being source and drain, but the value of  $V_D$  and  $V_G$  were not referenced to a common point as in the diode/triode described here or a solid state transistor. The value of  $V_G$  was referenced to an SCE. A floating potential was used at the source and drain;  $V_D$  was set with a battery. The value of  $V_T$ , however, was also between -0.4 and -0.2 V vs. SCE, since fundamentally all of the devices described based on polypyrrole or poly-N-methylpyrrole depend on the dramatic change in conductivity in going from the reduced to the oxidized state of the polymer. The rationale for characterizing the derivatized three electrode array with a floating  $V_D$  is to simulate the response of the device to a redox reagent in solution that could be equilibrated with the polymer to turn it "on" or "off". Future effort in this laboratory will include study of the equilibration of molecule-based transistors with solution redox reagents.

## CONCLUSIONS

We have shown that it is possible to fabricate a microelectrode array and to functionalize the individual microelectrodes in a controlled fashion using an electropolymerization procedure. Diodes having a crucial dimension (contact to contact) of 1.4  $\mu\text{m}$  have been demonstrated for two different polymers, polypyrrole and poly-N-methylpyrrole. The diode characteristics depend in a rational way on the polymer used to connect two microelectrodes. This work and our report of a molecule-based transistor establish that synthetic strategies do exist for the integration of chemical and microelectronics systems.<sup>1</sup> The synthetic strategy of electropolymerization has been shown to have wide-spread utility,<sup>6a,7a,c,10b,g,11a,13a,21</sup> and we expect that many of the polymers deposited on macroscopic electrodes can be deposited onto electrodes spaced as closely as 1.4  $\mu\text{m}$ . In principle, the microelectrode arrays functionalized with the conducting polymers employed here could serve as redox sensors, since the conductivity depends on the redox state of the polymer. However, we have not yet made any quantitative measurements in this regard.

## ACKNOWLEDGMENTS

We thank the Defense Advanced Research Projects Agency and the Office of Naval Research for partial support of this research. Support from the M.I.T. Polymer Processing Program and use of the M.I.T. Microelectronics Laboratory in the Center for Materials Science and Engineering are gratefully acknowledged.

REFERENCES

1. White, H.S.; Kittlesen, G.P.; Wrighton, M.S. J. Am. Chem. Soc., 1984, 106, 0000.
2. (a) Wightman, R.M. Anal. Chem., 1981, 53, 1125a-1134a; (b) Howell, J.O.; Wightman, R.M. Anal. Chem., 1984, 56, 524-529; (c) Sutts, K.J.; Dayton, M.A.; Wightman, R.M. Anal. Chem., 1982, 54, 995-998; (d) Candill, W.L.; Howell, J.O.; Wightman, R.M. Anal. Chem., 1982, 54, 2532-2535; (e) Dayton, M.A.; Brown, J.C.; Sutts, K.J.; Wightman, R.M. Anal. Chem., 1980, 52, 946-950; (f) Dayton, M.A.; Ewing, A.G.; Wightman, R.M. Anal. Chem., 1980, 52, 2392-2396.
3. Ponchon, J.-L.; Cespuglio, R.; Gonon, F.; Jouvot, M.; Dujol, J.-F. Anal. Chem., 1979, 51, 1483-1486.
4. Osteryoung, J.; Aoki, K. J. Electroanal. Chem., 1981, 125, 315-320.
5. Robison, R.S.; McCreery, R.L. Anal. Chem., 1981, 53, 997-1001.
6. (a) Murray, R.W. Acc. Chem. Res., 1980, 13, 135-141; (b) Facci, J.; Murray, R.W. J. Electroanal. Chem., 1981, 124, 339-342; (c) Daum, P.; Murray, R.W. J. Electroanal. Chem., 1979, 103, 289-294; (d) Daum, P.; Lenhard, J.R.; Rolison, D.R.; Murray, R.W. J. Am. Chem. Soc., 1980, 102, 4649-4653.
7. (a) Pcerce, P.J.; Bard, A.J. J. Electroanal. Chem., 1980, 97, 112-115; (b) Rubenstein, I.; Bard, A.J. J. Am. Chem. Soc., 1981, 103, 512-515; (c) Abruna, H.D.; Bard, A.J. J. Am. Chem. Soc., 1982, 104, 2641-2645; (d) Henning, T.P.; White, H.S.; Bard, A.J. J. Am. Chem. Soc., 1981, 103, 3937-3941; (e) Daum, P.; Murray, R.W. J. Phys. Chem., 1981, 85, 389-396.
8. (a) Kaufman, F.G.; Schroeder, A.H.; Engler, A.H.; Kramer, S.R.; Chambers, J.B. J. Am. Chem. Soc., 1980, 102, 483-488; (b) Kaufman, F.B.; Engler, E.M. J. Am. Chem. Soc., 1979, 101, 547-549; (c) Lau, A.N.K.; Miller, L.L. J. Am. Chem. Soc., 1983, 105, 5271-5277; (d) Lau, A.N.K.; Miller, L.L.; Zinger, S. J. Am. Chem. Soc., 1983, 105, 5278-5284; (e) Van DeMark, M.R.; Miller, L.L.

- J. Am. Chem. Soc., 1978, 100, 3223-3224; (f) Landrum, H.L.; Salmon, R.T.; Hawkridge, F.M. J. Am. Chem. Soc., 1977, 99, 3154-3158.
9. (a) Tsou, Y.-M.; Anson, F.C. J. Electrochem. Soc., 1984, 131, 595-601; (b) Shigehara, K.; Oyama, N.; Anson, F.C. Inorg. Chem., 1981, 20, 518-522; (c) Shigehara, K.; Oyama, N.; Anson, F.C. J. Am. Chem. Soc., 1981, 103, 2552-2558; (d) Buttry, D.A.; Anson, F.C. J. Am. Chem. Soc., 1983, 105, 685-689; (e) Oyama, N.; Anson, F.C. J. Am. Chem. Soc., 1979, 101, 3450-3456.
10. (a) Harrison, D.J.; Daube, K.; Wrighton, M.S. J. Electroanal. Chem., 1984, 163, 93-115; (b) Dominey, R.N.; Lewis, T.J.; Wrighton, M.S. J. Phys. Chem., 1983, 87, 5345-5354; (c) Wrighton, M.S.; Palazzotto, M.C.; Bocarsly, A.B.; Bolts, J.M.; Fischer, A.B.; Nadjo, L. J. Am. Chem. Soc., 1978, 100, 7264-7271; (d) Bolts, J.M.; Wrighton, M.S. ibid., 1979, 101, 6179-6184; (e) Bocarsly, A.B.; Walton, E.G.; Wrighton, M.S. ibid., 1980, 102, 3390-3398; (f) Calabrese, G.S.; Buchanan, R.M.; Wrighton, M.S. J. Am. Chem. Soc., 1982, 104, 5786-5788; (g) Bookbinder, D.C.; Bruce, J.A.; Dominey, R.N.; Lewis, N.S.; Wrighton, M.S. Proc. Natl. Acad. Sci., USA, 1980, 77, 6280-6284.
11. (a) Pickup, P.G.; Kutner, W.; Leidner, C.R.; Murray, R.W. J. Am. Chem. Soc., 1984, 106, 1991-1998; (b) Abruna, H.D.; Denisevich, P.; Umana, M.; Meyer, T.J.; Murray, R.W. J. Am. Chem. Soc., 1981, 103, 1-5; (c) Denisevich, P.; Willman, K.W.; Murray, R.W. J. Am. Chem. Soc., 1981, 103, 4727-4737.
12. Pickup, P.G.; Murray, R.W. J. Electrochem. Soc., 1984, 131, 833-839.
13. (a) Lewis, T.J.; White, H.S.; Wrighton, M.S. J. Am. Chem. Soc., in press; (b) Pickup, P.G.; Murray, R.W. J. Am. Chem. Soc., 1983, 105, 4510-4514.

14. (a) Kanazawa, K.K.; Diaz, A.F.; Geiss, R.H.; Gill, W.D.; Kwak, J.F.; Logan, J.A.; Rabolt, J.; Street, G.B. J. Chem. Soc., Chem. Commun., 1979, 854-855; (b) Diaz, A. Chemica Scripta, 1981, 17, 145-148; (c) Salmon, M.; Diaz, A.F.; Logan, A.J.; Krounki, M.; Bargon, J. Mol. Cryst. Liq. Cryst., 1982, 83, 265-276; (d) Diaz, A.F.; Martinez, A.; Kanazawa, K.K. J. Electroanal. Chem., 1981, 130, 181-187; (e) Bull, R.A.; Fan, F.-R.F.; Bard, A.J. J. Electrochem. Soc., 1982, 129, 1009-1015.
15. See, for example, the special issue on "Molecular Electronics": IEE Proceedings-I, Solid State and Electron Devices, 1983, 103, 197-263.
16. For a recent overview of sensors that depend on microstructures see: Wohltjen, H. Anal. Chem., 1984, 56, 87A-103A.
17. Sawyer, D.T.; Roberts, J.L. "Experimental Electrochemistry for Chemistry", John Wiley & Sons: New York, 1974.
18. White, H.S.; Kittlesen, G.P.; Wrighton, M.S., to be submitted.
19. Andrieux, C.P.; Saveant, J.M. J. Electroanal. Chem., 1982, 142, 1-30.
20. Sze, S.M. "Physics of Semiconductor Devices", 2nd ed., John Wiley & Sons: New York, 1981.
21. (a) Trouillon, G.; Garnier, F. J. Electroanal. Chem., 1982, 135, 173-178; (b) Noufi, R.; Nozik, A.J.; White, J.; Warren, J. J. Electrochem. Soc., 1982, 129, 2261-2265; (c) Simon, R.A.; Ricco, A.J.; Wrighton, M.S. J. Am. Chem. Soc., 1982, 104, 2031-2034; (d) Bookbinder, D.C.; Wrighton, M.S. J. Electrochem. Soc., 1983, 130, 1080-1087.

FIGURE CAPTIONS

Figure 1. Cross-sectional view of design for an array of Au microelectrodes. The drawing is to scale except for the Si substrate which is 0.011".

Figure 2. Top view of complete layout for microelectrode array represented in Figure 1. The drawing is to scale.

Figure 3. Scanning electron micrographs of a fabricated microelectrode array. The brighter areas in the micrographs are the Au wires and contact pads.

Figure 4. Linear sweep (50 mV/s) voltammograms for six of eight electrodes of a microelectrode array. Two electrodes were not connected. The entire array is immersed in  $\text{H}_2\text{O}/0.1 \text{ M NaClO}_4/0.01 \text{ M K}_3[\text{Fe}(\text{CN})_6]/0.01 \text{ M K}_4[\text{Fe}(\text{CN})_6]$ .

Figure 5. Representation of synthetic objective for a microelectrode array derivatized with polypyrrole. Drawing is to scale.

Figure 6. Cyclic voltammograms (100 mV/s) in  $\text{CH}_3\text{CN}/0.1 \text{ M } [n\text{-Bu}_4\text{N}]\text{ClO}_4$  for a microelectrode array derivatized with polypyrrole. The bottom portion represents the expected situation based on the derivatization procedure and electrochemical response.

Figure 7. Scanning electron micrographs of three microelectrodes on an array lightly coated with poly-N-methylpyrrole (left) and three microelectrodes on the same array heavily coated with poly-N-methylpyrrole (right). Electrochemical measurements show that the left three electrodes are unconnected and the right three are connected.

Figure 8. (a) Potential of five electrodes connected with polypyrrole when one is under active potential control at -1.0 V vs. SCE and one is at a

positive potential where the polypyrrole is expected to be conducting.

(b) Potential of same five electrodes in (a) but only one electrode is under active potential control. In both (a) and (b) the microelectrode array is immersed in  $\text{CH}_3\text{CN}/0.1 \text{ M } [\underline{n}\text{-Bu}_4\text{N}]\text{ClO}_4$ .

Figure 9. Current vs.  $V_{\text{app}}$  curves for two adjacent microelectrodes connected with polypyrrole as a function of  $V_{\text{set}}$  where  $V_{\text{set}}$  is the potential of one of the two electrodes fixed vs. SCE. The potential,  $V_{\text{app}}$ , of the other electrode is varied. The current measured is that between the two microelectrodes.

Figure 10. Comparison of diode characteristic for two microelectrodes connected with (a) polypyrrole and (b) poly-N-methylpyrrole. In (a)  $V_{\text{set}} = -1.0 \text{ V vs. SCE}$  and in (b)  $V_{\text{set}} = -0.6 \text{ V vs. SCE}$ .


# MICROELECTRODE ARRAY



Scale:  $2\mu\text{m}$




Au

SiO<sub>2</sub>


Si Substrate








Au Microelectrode Array  
10 mM  $K_4Fe(CN)_6$  / 10 mM  $K_3Fe(CN)_6$   
 $H_2O$  / 0.1 M NaClO<sub>4</sub>




# ELECTROCHEMICAL DEPOSITION OF AN ELECTRONIC CONDUCTOR


2  $\mu\text{m}$



Au Microelectrode Array  
 $\text{CH}_3\text{CN}/0.1\text{M} [\text{s-Bu}_4\text{N}][\text{ClO}_4]$   
 100 mV/s










Current

Steady State Current Between  
Two Adjacent Gold Microelectrodes  
Connected by Polypyrrole  
 $\text{CH}_3\text{CN}/0.1\text{M}[\text{n-Bu}_4\text{N}]\text{ClO}_4$




Applied Potential, V vs. SCE

(a) Polypyrrole - Based Diode  
 $\text{CH}_3\text{CN}/0.1\text{M} [\text{n-Bu}_4\text{N}] \text{ClO}_4$



(b) Poly - N - Methylpyrrole - Based Diode  
 $\text{CH}_3\text{CN}/0.1\text{M} [\text{n-Bu}_4\text{N}] \text{ClO}_4$



END

FILMED

1984

DTIC