

AD-A261 250



(1)

AEDC-TR-92-23

APPENDIX D, VOL. II



Duct Protection Coating Concept  
Development and Test

Appendix D, Volume II: Test Specimen Fabrication,  
Conditioning, and Testing Documentation

C. David Newlander  
Mission Research Corporation  
Costa Mesa, CA 92626

January 1993

Final Report for February 1992

DTIC  
ELECTED  
FEB 17 1993  
S E D

Approved for public release; distribution is unlimited.

93-02966



ARNOLD ENGINEERING DEVELOPMENT CENTER  
ARNOLD AIR FORCE BASE, TENNESSEE  
AIR FORCE MATERIEL COMMAND  
UNITED STATES AIR FORCE

93 2 16 050 93 2 12 1993

## NOTICES

When U. S. Government drawings, specifications, or other data are used for any purpose other than a definitely related Government procurement operation, the Government thereby incurs no responsibility nor any obligation whatsoever, and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise, or in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Qualified users may obtain copies of this report from the Defense Technical Information Center.

References to named commercial products in this report are not to be considered in any sense as an endorsement of the product by the United States Air Force or the Government.

This report has been reviewed by the Office of Public Affairs (PA) and is releasable to the National Technical Information Service (NTIS). At NTIS, it will be available to the general public, including foreign nations.

## APPROVAL STATEMENT


This report has been reviewed and approved.



PAUL LACASSE, Capt. CF  
Propulsion Division  
Directorate of Technology  
Deputy for Operations

Approved for publication:

FOR THE COMMANDER



KEITH L. KUSHMAN  
Director of Technology  
Deputy for Operations

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188
<p>Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.</p>			
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE <b>January 1993</b>	3. REPORT TYPE AND DATES COVERED <b>Final Report - February 1992</b>	
4. TITLE AND SUBTITLE <b>Duct Protection Coating Concept Development and Test</b>		5. FUNDING NUMBERS <b>F40600-89-0002</b>	
6. AUTHOR(S) <b>C. David Newlander Mission Research Corporation Costa Mesa, CA 92626</b>			
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) <b>Mission Research Corporation 3505 Cadillac Avenue, Building H Costa Mesa, CA 92626</b>		8. PERFORMING ORGANIZATION REPORT NUMBER <b>AEDC-TR-92-23 Appendix D, Vol. II</b>	
9. SPONSORING/MONITORING AGENCY NAMES(S) AND ADDRESS(ES) <b>Arnold Engineering Development Center/DOT Air Force Materiel Command Arnold Air Force Base, TN 37389-9011</b>		10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES <b>Available in Defense Technical Information Center (DTIC).</b>			
12a. DISTRIBUTION/AVAILABILITY STATEMENT <b>Approved for public release; distribution is unlimited.</b>		12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) <b>The overall objective of the program was to develop and test a surface cleaning/preparation and corrosion resistant protective polymer coating for the interior of the AEDC Environment Test Facility ferrous metal air supply ducts. The types of cleaning techniques acceptable to the AEDC were basically limited to chemical approaches. Typically, sand or abrasive blasting is used to produce corrosion-free, clean surfaces for coating steel substrates. These particular techniques are strongly discouraged and basically "outlawed" at the AEDC facilities. Water blasting is an acceptable technique, but requires a high pressure water stream, expensive equipment, and considerable clean up.</b>			
14. SUBJECT TERMS <b>coating steel substrates      polymer coating      supply ducts</b>			15. NUMBER OF PAGES <b>277</b>
			16. PRICE CODE
17. SECURITY CLASSIFICATION OF REPORT <b>UNCLASSIFIED</b>	18. SECURITY CLASSIFICATION OF THIS PAGE <b>UNCLASSIFIED</b>	19. SECURITY CLASSIFICATION OF ABSTRACT <b>UNCLASSIFIED</b>	20. LIMITATION OF ABSTRACT <b>SAME AS REPORT</b>

**MRC-COM-R-92-0315**

**DUCT PROTECTION COATING CONCEPT  
DEVELOPMENT AND TEST**

**CONTRACT: F40600-89-C-0002**

**FINAL TECHNICAL REPORT (CDRL A002)**

**APPENDIX D: TEST SPECIMEN FABRICATION, CONDITIONING,  
AND TESTING DOCUMENTATION.**

**PART II: SETS I Through 28**

**15 February 1992**

**Submitted to:** ✓

**Arnold Engineering Development Center  
Arnold Air Force Station, Tennessee 37389-5000  
ATTN: Captain Paul LaCasse/DOTr  
Dowe Jones/PKP**

**Submitted by:** ✓

**Mission Research Corporation  
Survivable Structures Technologies Division  
3505 Cadillac Avenue, Building H  
Costa Mesa, California 92626  
C. David Newlander, Program Manager**

<b>Accession For</b>	
NTIS	CRA&I <input checked="" type="checkbox"/>
DTIC	TAB <input type="checkbox"/>
Unannounced <input type="checkbox"/>	
Justification .....	
By .....	
Distribution /	
<b>Availability Codes</b>	
<b>Dist</b>	<b>Avail and / or Special</b>
A-1	

**DTIC QUALITY INSPECTED 3**

**MRC Fabrication/Conditioning/Test Form 90-1**

**Set: I      Sample: AS-4**      Comments: o MARB-33    AS-4    Original (Host testing)  
**Materials: MARB-33/ MARB2-33**      o MARB 2    for hot hardness  
     o MARB2-33 + MARB2    for cold hardness  
     o Primer only    Cold non-cracking  
     o wire brushed (lower 1/5th only)

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
07/03/90	Acid clean	-	HCl cleaned
08/01/90	Acid clean	-	Re-clean
08/01/90	Coat	-	Brush coat 4 formula sections
08/01/90	Cure	0	1 hr @ 480 F
08/02/90	1/4 hrs @ -100 F	C	
08/02/90	1 hr @ 250 F	C	
08/02/90	15 hrs @ 130 F	H	
08/03/90	1/4 hrs @ -90 F	C	
08/03/90	1/4 hrs @ 280 F	C	
08/06/90	1 hr @ -100 F	C	
08/07/90	5 hrs @ 140 F	H	
08/10/90	1 hr @ -110 F	C	autocycle
08/10/90	1 hr @ 600 F	C	autocycle

## NRC Fabrication/Conditioning/Test Form 90-1

Set: 1      Sample: AS-4

Comments: Page 2

Materials: MARRB-33/MARRB2-33

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/13/90	1 hr @ -100 F	C	Autocycle
08/14/90	1 hr @ -100 F	C	Altered Autocycle
08/14/90	1/2 hr @ 600 F	C	Altered Autocycle
08/16/90	5 hrs @ 140 F	H	
08/17/90	1/2 hrs @ 20 F	H	
08/17/90	3 hrs @ 130 F	H	
08/20/90	16 hrs @ 160 F	H	
08/21/90	1 hr @ -100 F	C	
08/21/90	16 hrs @ 120 F	H	
08/22/90	1 hr @ -100 F	C	Autocycle
08/22/90	1 hr @ 600 F	C	Autocycle
08/22/90	15 hrs @ 125 F	H	
08/23/90	2 hrs/600 F	0	

Set: I      Sample: AS-4  
Materials: MARB-33/MARB2-33

NRC Fabrication/Conditioning/Test Form 90-1

Comments: Page 3

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/23/90	15 hrs @ 125 F	H	
08/28/90	22 hrs @ 125 F	H	
08/29/90	5 hrs @ 600 F	0	
08/29/90	14 hrs @ 125 F	H	Humid
08/30/90	4 hrs @ 600 F	0	
09/05/90	1 hr @ -100 F	C	Autocycle
09/05/90	16 hrs @ 160 F	H	
09/06/90	3 hrs @ 600 F	0	
09/06/90	15 hrs @ 125 F	H	Humid to dry
09/07/90	1 hr @ -125 F	C	Autocycle
09/07/90	1 hr @ 800 F	C	Manual HIGH heat
09/20/90	Test (Location 1)	A	>1050 No Failure      knock off 35% clean Substrate/ 65% C
09/24/90	3 hrs @ 600 F	0	

## NRC Fabrication/Conditioning/Test Form 90-1

Set: I      Sample: AS-4

Comments: page 4

Materials: MARB-33/MARB2-33

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/24/90	13 hrs @ 120 F	H	
09/25/90	1 hr @ 487 F	0	
09/25/90	16 hrs @ 120 F	H	
09/26/90	3 hrs @ 600 F	0	
09/27/90	40 hrs @ 120 F	H	
09/29/90	Test (Location 2)	A	1050 PSI (90% C; 10% A)
10/01/90	3.5 hrs @ 610 F	0	
10/01/90	16 hrs @ 120 F	H	
10/02/90	1 hr @ -100 F	C	
10/03/90	23 hrs @ 120/150 F	H	
10/04/90	1 hr @ -100 F	C	
10/04/90	1 hr @ 600 F	C	
10/04/90	15 hrs @ 120-160 F	H	


## MRC Fabrication/Conditioning/Test Form 91-1

Page 4

Set-Sample: 22R - AS4      Comments:

Materials: MARB 45

Equip Definitions: See Page 1



Date	Action	Equip	Results/Comments
03/12/91	16 hrs @ 115 F	H	
03/14/91	Test (Location 4)	A	>1000 PSI
03/19/91	3 hrs @ 610 F	O	dry
03/19/91	17 hrs @ 116 F	H	
03/20/91	3 hrs @ 650 F	O	
03/20/91	1 hr @ -100 F	C	
03/20/91	16 hrs @ 140 F	H	
03/21/91	1 hr @ -100 F	C	
03/21/91	1 hr @ 640 F	O	dry oven
03/21/91	16 hrs @ 140 F	H	
03/22/91	1 hr @ -100 F	C	auto
03/22/91	1 hr @ 640 F	O	dry heat
03/22/91	1 hr @ -100 F	C	
03/22/91	43 hrs @ 115 F	H	
03/24/91	1 hr @ -100 F	C	
03/28/91	Test (Location 5)	A	550 PSI (50% C; 50% dolly) cold

## HRC Fabrication/Conditioning/Test Form 90-1

Set: I      Sample: AS-4

Comments: page 5

Materials: MARB-33/ MARB2-33

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/06/90	1 hr @ 487 F	0	
10/08/90	1 hr @ -100 F	C	
10/08/90	1 hr @ 600 F	C	autocycle
10/08/90	20 hrs @ 120 F	H	very humid
10/09/90	1 hr @ -100 F	C	
10/10/90	Test (Location 3 TR)	A	>1000 PSI (85% C; 15% C/I black oxide)
10/10/90	1 hr @ -100 F	C	
10/10/90	8 hrs @ 350 F	0	
10/11/90	18 hrs @ 120 F	H	very humid
10/19/90	65 hrs @ 100 F	H	very humid
10/22/90	24 hrs @ 120/135 F	H	very humid      STOP TESTING
			Top quarter of panel 1s AS4 and very rusty with coating failure
			Conclusion: Do not apply thick brush coats; Increase Aluminum content.      See 22R- ASA 01/15/91


## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 22R - AS4      Comments: Repair Test

Substrate/Preparation: 516/ light rusting

Materials: MARB-45



Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
 H = Humidity Chamber;  
 A = Adhesion Tester; T = Misc Tests

Date	Action	Equip	Results/Comments
Formerly I-AS4 (See form 90-1)	-		Gel clean and tape remove loose MARB
01/15/91	Clean	-	Gel clean 15 minutes
01/16/91	Coat panel	-	Spray coat 3 layers of MARB-45
01/17/91	1 hr @ 487 F	O	Cure slow to temperature
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	>1000 PSI (no failure)
01/30/91	1 hr @ -110 F	C	cold
01/30/91	41 hrs @ 115 F	H	very humid
02/01/91	1 hr @ -110 F	C	autocycle
02/01/91	1 hr @ 600 F	C	autocycle
02/04/91	2.5 hrs @ 600 F	O	dry heat


## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 22R - AS4      Comments: Repair test

Materials: MARB-45

Equip Definitions: See Page 1



Date	Action	Equip	Results/Comments
02/04/91	42 hrs @ 115-150 F	H	very humid
02/06/91	2.5 hrs @ 58 F	O	
02/07/91	3 hrs @ 590 F	O	
02/08/91	1 hr @ -100 F	C	autocycle
02/09/91	1 hr @ -100 F	C	autocycle
02/11/91	1 hr @ -100 F	C	autocycle
02/11/91	2 hrs @ 620 F	O	dry heat
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	autocycle
02/12/91	2 hrs @ 600 F	O	
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 2)	A	800 PSI (90% C, 10% F) some failure
02/22/91	2 hrs @ 590 F	C	dry heat
02/22/91	19 hrs @ 115 F	H	humid
02/25/91	2 hrs @ 600 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 22R - AS4      Comments:

Materials: MARB 45

Equip Definitions: See Page 1

	3
2	4
1	5

Date	Action	Equip	Results/Comments
02/25/91	1 hr @ -100 F	C	autocycle
02/27/91	1 hr @ -100 F	C	autocycle
02/27/91	2 hrs @ 350 F	O	dry
02/28/91	1 hr @ -100 F	C	
02/28/91	2 hrs @ 600 F	O	
02/28/91	18 hrs @ 115 F	H	
03/04/91	Test (Location 3)	A	750 PSI (100% C)
	overlapped previous coating dolly location		
03/04/91	1 hr @ 487 F	O	dry oven
03/04/91	1 hr @ -100 F	C	auto
03/05/91	1 hr @ -100 F	C	auto
03/05/91	1 hr @ 600 F	O	dry heat
03/05/91	16.5 hrs @ 116 F	H	humid
03/08/91	1 hr @ -100 F	C	
03/08/91	2 hrs @ 600 F	O	
03/08/91	64 hrs @ 140 F	H	
03/11/91	1 hr @ -100 F	C	
03/11/91	2 hrs @ 600 F	O	
03/11/91	17 hrs @ 115 F	H	
03/12/91	1 hr @ -100 F	C	
03/12/91	1 hr @ 480 F	O	

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I      Sample: ST-4

Comments:

Materials: 4 Silicones on A516-70 steel  
Acid cleaned

1. 50% solids SR-240

2. Thin SR-240

3. 50% solids MARB Blend

4. Thin MARB Blend

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
07/24/90	Acid clean	-	60% HCL/rinse
07/25/90	Formulate	-	Silicone
07/26/90	Coat	-	Brush
07/26/90	1 hr @ 410 F	0	Bake
07/27/90	Test at 250 F	E	Scratch
07/27/90	1 hr @ 40 F	H	
07/27/90	0.5 hrs @ 10 F	H	
07/27/90	20 hrs @ 130 F	H	
07/29/90	Test	E	Scratch
07/30/90	2 hrs @ -100 F	C	Cracking evident #1 & #3
07/31/90	1 hr @ 480 F	C	
07/31/90	20 hrs @ 130 - 145 F	H	very humid 8 hrs
08/02/90	0.25 hrs @ -100 F	C	

**MRC Fabrication/Conditioning/Test Form 90-1****Set: I      Sample: ST-4**

Comments: page 2

**Materials: Thinning Silicones****Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humdity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/02/90	1 hr @ 250 F	C	
08/02/90	15 hrs @ 130 F	H	
08/03/90	Test	E	Scratch
08/06/90	1 hrs @ -100 F	C	

Blended resins is best; Must be applied thin.

## NRC Fabrication/Conditioning/Test Form 90-1

Set: I      Sample: SB-7

Comments: Testing Blends for microcracking

Materials: 7 Silicone Blends on one A517 panel

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester  
 E = Scratch Tester Balanced Beam

Date	Action	Equip	Results/Comments
07/24/90	Clean	-	60% HCL / rinse
07/25/90	Formulate	-	Silicone Blend formulations:
		1	2    3    4    5    6    7
		SR-240	100    0    17    67    33    50    83    %
		6-2230	0    100    83    33    67    50    17    %
07/25/90	Coating	-	Brushcoat 3.5 mils wet (too thick)
07/25/90	1 hr @ 480 F	0	Bake cure
07/26/90	1 hr @ 410 F	0	Dry heat
07/27/90	Scratch testing @ 250 F	E/0	#2 & #3 Best; #1 & #7 Worst
07/27/90	1 hr @ 40 F	H	
07/27/90	1/2 hrs @ 10 F	H	
07/27/90	20 hrs @ 130 F	H	
07/29/90	Scratch Test	E	

**NRC Fabrication/Conditioning/Test Form 90-1**

Set: I Sample: S8-7

Comments: Page 2

Materials: 7 Silicone Blends

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
07/30/90	2 hrs @ -100 F	C	
07/31/90	1 hr @ 480 F	C	
07/31/90	20 hrs @ 130-145 F	H	8 hrs very humid
08/02/90	1/4 hrs @ -100 F	C	
08/02/90	1 hr @ 250 F	C	
08/02/90	15 hrs @ 130 F	H	Humid
08/03/90	Scratch Test	E	
08/06/90	1 hr @ -100 F	C	Autocycle
08/06/90	1 hr @ 600 F	C	Autocycle
			Best #1/ #4/ #7 #5 is MARB blend

## NRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 1      Comments: Mass weight loss

Materials: Silicone Blend (no filler) used in MARB

Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/03/90	Acid clean	-	Remove mill scale both sides of panel
08/07/90	Acid clean	-	Reclean to remove spot rust
08/11/90	Clean	-	Consultant cleaner both sides 44B-FFPVA
08/11/90	Coat	-	Brush coat Silicone Blend 100% panel 78in <sup>2</sup>
08/12/90	1 hr @ 480 F	0	cure
08/14/90	2 hrs @ 600 F	0	
08/16/90	2 hrs @ 600 F	0	
08/17/90	2 hrs @ 600 F	0	
08/20/90	2 hrs @ 600 F	0	
08/21/90	2 hrs @ 600 F	0	
08/22/90	2 hrs @ 600 F	0	
08/23/90	2 hrs @ 600 F	0	
08/23/90	15 hrs @ 125 F	H	

Set: I-P2      Sample: 1  
Materials: MARB

MRC Fabrication/Conditioning/Test Form 90-1  
Comments: Page 2

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/27/90	6 hrs @ 580 F	0	
08/28/90	22 hrs @ 125 F	H	
08/29/90	5 hrs @ 600 F	0	
08/29/90	14 hrs @ 125 F	H	
08/30/90	4 hrs @ 600 F	0	
09/05/90	1 hr @ -100 F	C	Autocycle
09/05/90	16 hrs @ 125 F	H	
09/06/90	3 hrs @ 600 F	0	
09/06/90	15 hrs @ 125 F	H	Humid to dry
09/07/90	1 hr @ -125 F	C	Autocycle
09/07/90	1 hr @ 800 F	C	Manual HIGH heat Too high heat - failed

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 2      Comments: Mass weight loss

Materials: MARB

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/03/90	Acid clean	-	Remove mill scale both sides of panel
08/07/90	Acid clean	-	Reclean to remove spot rust
08/11/90	Clean	-	Consultant cleaner both sides 44B-FFPVA
08/11/90	Coat	-	Brush coat MARB
08/13/90	1 hr @ 480 F	0	Cure
08/14/90	2 hrs @ 600 F	0	
08/16/90	2 hrs @ 600 F	0	
08/17/90	2 hrs @ 600 F	0	
08/20/90	2 hrs @ 600 F	0	
08/21/90	2 hrs @ 600 F	0	
08/22/90	2 hrs @ 600 F	0	
08/23/90	2 hrs @ 600 F	0	
08/23/90	15 hrs @ 125 F	H	

## MAC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 2

Comments: Page 2

Materials: HARB

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/27/90	6 hrs @ 580 F	0	
08/28/90	22 hrs @ 125 F	H	
08/29/90	5 hrs @ 600 F	0	
08/29/90	14 hrs @ 125 F	H	
08/30/90	4 hrs @ 600 F	0	
09/05/90	1 hr @ -100 F	C	Autocycle
09/05/90	16 hrs @ 125 F	H	
09/06/90	3 hrs @ 600 F	0	
09/06/90	15 hrs @ 125 F	H	Humid to dry
09/07/90	1 hr @ -125 F	C	Autocycle
09/07/90	1 hr @ 800 F	C	Manual HIGH heat
09/11/90	1 hr @ -100 F	C	
09/11/90	1 hr @ 590 F	C	

## MRC Fabrication/Conditioning/Test Form 90-1

Sat: 1-P2      Sample: 2

Comments: page 3

Materials: MARB

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/12/90	1 hr @ -100 F	C	
09/12/90	3 hrs @ 600 F	0	
09/12/90	16 hrs @ 125 F	H	
09/13/90	21 hrs @ 125 F	H	very humid
09/14/90	1 hr @ -100 F	C	
09/18/90	1 hr @ -100 F	C	
09/18/90	1 hr @ 600 F	0	
09/19/90	1 hr @ 15 F	H	
09/19/90	21 hrs @ 15 F	H	
09/20/90	Test (Location 1)	A	600 PSI (100% C/I)
09/24/90	3 hrs @ 600 F	0	
09/24/90	13 hrs @ 120 F	H	
09/25/90	1 hr @ 487 F	0	

NRC Fabrication/Conditioning/Test Form 90-1

Sammlung 2

Comments: page 4

### **Materials: MARB**

**Equipment Definitions:** O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/25/90	16 hrs @ 120 F	H	
09/26/90	3 hrs @ 600 F	0	
09/27/90	40 hrs @ 120 F	H	
09/29/90	Test (Location 2)	A      450 PSI (85% C; 15% A) 1259.6g	Stop testing although coating looks excellent

## HRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 3

Comments: Mass weight loss

Materials: DC 6-2230 Silicone Resin

Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/03/90	Acid clean	-	Remove mill scale both sides of panel
08/07/90	Acid clean	-	Reclean to remove spot rust - Drill hole to hang
08/11/90	Clean	-	Consultant cleaner both sides 44B-FFPVA / weigh
08/11/90	Coat	-	Brush coat Silicone resin 100% of panel 78 in <sup>2</sup>
08/13/90	1 hr @ 480 F	0	Cure
08/14/90	2 hrs @ 600 F	0	
08/16/90	2 hrs @ 600 F	0	
08/17/90	2 hrs @ 600 F	0	
08/20/90	2 hrs @ 600 F	0	
08/21/90	2 hrs @ 600 F	0	
08/22/90	2 hrs @ 600 F	0	
08/23/90	2 hrs @ 600 F	0	
08/23/90	15 hrs @ 125 F	H	

NRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 3

Comments: Page 2

Materials: DC 2230 Silicone Resin

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/27/90	6 hrs @ 580 F	0	
08/28/90	22 hrs @ 125 F	H	
08/29/90	5 hrs @ 600 F	0	
08/29/90	14 hrs @ 125 F	H	
08/30/90	4 hrs @ 600 F	0	
09/05/90	1 hr @ -100 F	C	Autocycle
09/05/90	16 hrs @ 125 F	H	
09/06/90	3 hrs @ 600 F	0	
09/06/90	15 hrs @ 125 F	H	Humid to dry
09/07/90	1 hr @ -125 F	C	Autocycle
09/07/90	1 hr @ 800 F	C	Manual HIGH heat

## NRC Fabrication/Conditioning/Test Form 90-1

Sat: I-P2      Sample: 4      Comments: Mass weight loss

Materials: Sherwin Williams - Silver-Brite  
 Hi-Heat resisting Aluminum paint  
 B59S3

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/03/90	Acid clean	-	Remove mill scale both sides of panel
08/07/90	Acid clean	-	Reclean to remove spot rust; drill hole to hang in oven
08/11/90	Clean	-	Consultant cleaner both sides 44B-FFPVA; weigh
08/11/90	Coat	-	Brush coat SW Silver-Brite B59S3 100% panel 78 in <sup>2</sup>
08/13/90	48 hrs ambient	-	Dry
08/14/90	2 hrs @ 600 F	0	
08/16/90	2 hrs @ 600 F	0	
08/17/90	2 hrs @ 600 F	0	
08/20/90	2 hrs @ 600 F	0	
08/21/90	2 hrs @ 600 F	0	
08/22/90	2 hrs @ 600 F	0	
08/23/90	2 hrs @ 600 F	0	
08/23/90	15 hrs @ 125 F	H	

**MRC Fabrication/Conditioning/Test Form 90-1**

Set: I-P2      Sample: 4

Comments: Page 2

Materials: SW Silver-Brite

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/27/90	6 hrs @ 580 F	0	
03/28/90	22 hrs @ 125 F	H	
08/29/90	5 hrs @ 600 F	0	
08/29/90	14 hrs @ 125 F	H	
08/30/90	4 hrs @ 600 F	0	
09/05/90	1 hr @ -100 F	C	Autocycle
09/05/90	16 hrs @ 125 F	H	
09/06/90	3 hrs @ 600 F	0	
09/06/90	15 hrs @ 125 F	H	Humid to dry
09/07/90	1 hr @ -125 F	C	Autocycle
09/07/90	1 hr @ 800 F	C	Manual HIGH heat
09/11/90	1 hr @ -100 F	C	
09/11/90	1 hr @ 590 F	C	

**MRC Fabrication/Conditioning/Test Form 90-1****Set: 1-P2      Sample: 4****Comments: page 3****Materials: SW Silver Brite****Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester**

Date	Action	Equip	Results/Comments
09/12/90	1 hr @ -100 F	C	
09/12/90	3 hrs @ 600 F	0	
09/12/90	16 hrs @ 125 F	H	
09/13/90	21 hrs @ 125 F	H	<b>very humid</b>
09/14/90	1 hr @ -100 F	C	
09/18/90	1 hr @ -100 F	C	
09/18/90	1 hr @ 600 F	0	
09/19/90	1 hr @ 15 F	H	
09/19/90	21 hrs @ 130 F	H	
09/20/90	Test (Location 1)	A	250 PSI (75% C; 25% I)
09/24/90	3 hrs @ 600 F	0	
09/24/90	13 hrs @ 120 F	H	
09/25/90	1 hr @ 487 F	0	

**MRC Fabrication/Conditioning/Test Form 90-1**

**Set:** I-P2    **Sample:** 4  
**Materials:** SW Silverbrite

**Comments:** page 4

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

<b>Date</b>	<b>Action</b>	<b>Equip</b>	<b>Results/Comments</b>
09/25/90	16 hrs @ 120 F	H	
09/26/90	3 hrs @ 600 F	0	
09/27/90	40 hrs @ 120 F	H	
09/29/90	Test (Location 2)	A	700 PSI (90% C; 10% A) 1268.2g
			Stop testing although coating looks excellent

**MRC Fabrication/Conditioning/Test Form 90-1**

Set: I-21P      Sample: 9001

Comments:

Materials: MARB 2 over MARS 3

**Equip Definitions:** O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
07/16/90	Acid Clean	-	Remove mill scale both sides of panel
07/18/90	Medium rust	H	
08/07/90	Clean	-	Acid clean and wire brush and xylene wipe
08/07/90	Coat	-	Brush MARS 3-33% Thin 2 coats
08/07/90	Coat	-	Brush MARS 2-33% Thin 2 coats      Brush strokes
08/08/90	1 hr @ 480 F	0	Cure slowly heatup
08/10/90	1 hr @ -110 F	C	
08/10/90	1 hr @ 600 F	C	Autocycle
08/13/90	1 hr @ -100 F	C	Cold autocycle
08/14/90	1 hr @ -100 F	C	Cold autocycle
08/14/90	1/2 hr @ 600 F	C	Hot altered autocycle
08/16/90	5 hrs @ 140 F	H	Humid
08/17/90	1/2 hr @ 20 F	H	

**NRC Fabrication/Conditioning/Test Form 90-1****Set: I-21P      Sample: 9001****Comments: Page 2****Materials: MARB 2 over MARS 3****Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester**

Date	Action	Equip	Results/Comments
08/17/90	3 hrs @ 130 F	H	
08/20/90	16 hrs @ 160 F	H	
08/21/90	1 hr @ -100 F	C	Cold
08/21/90	16 hrs @ 120 F	H	
08/22/90	1 hr -100 F	C	Cold
08/22/90	1 hr @ 600 F	C	Hot
			General stroke rusting
08/22/90	15 hrs @ 125 F	H	
08/23/90	1 hr @ -100 F	C	
08/23/90	1 hr @ 600 F	C	
08/23/90	15 hrs @ 125 F	H	
08/28/90	22 hrs @ 125 F	H	
08/29/90	5 hrs @ 600 F	O	
08/29/90	14 hrs @ 125 F	H	

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-21P   Sample: 9001

Comments: Page 3

Materials: MARS 2 over MARS 3

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/30/90	4 hrs @ 600 F	0	
09/05/90	1 hr @ -100 F	C	
09/05/90	16 hrs @ 125 F	H	
09/06/90	3 hrs @ 600 F	0	
09/06/90	15 hrs @ 125 F	H	Humid to dry
09/07/90	1 hr @ -125 F	C	Autocycle
09/07/90	1 hr @ 800 F	C	Manual HIGH heat
09/20/90	Test (Location 1)	A	>1050 PSI No Failure knockoff 85% substrate; 15% C
09/24/90	3 hrs @ 600 F	0	
09/24/90	13 hrs @ 120 F	H	
09/25/90	1 hr @ 487 F	0	
09/25/90	16 hrs @ 120 F	H	
09/26/90	3 hrs @ 600 F	0	

## NRC Fabrication/Conditioning/Test Form 90-1

Set: I-21P      Sample: 9001

Comments: page 4

Materials: MARS 2 over MARS 3

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/27/90	40 hrs @ 120 F	H	
09/29/90	Test (Location 2)	A	700 PSI (100% C)
10/01/90	3.5 hrs @ 610 F	0	
10/01/90	16 hrs @ 120 F	H	
10/02/90	1 hr @ -100 F	C	
10/03/90	23 hrs @ 120/150 F	H	
10/04/90	1 hr @ -100 F	C	
10/04/90	1 hr @ 600 F	C	autocycle
10/04/90	15 hrs @ 120/160 F	H	
10/06/90	1 hr @ 487 F	0	
10/08/90	1 hr @ -100 F	C	
10/08/90	1 hr @ 600 F	C	autocycle
10/09/90	20 hrs @ 120 F	H	very humid

## MAC Fabrication/Conditioning/Test Form 90-1

Set: I-2IP      Sample: 9001

Comments: page 5

Materials: MARS-2 over MARS-3

Equip Definitions: 0 - Oven; C - Heat/Cooling Chamber; H - Humidity Chamber; A - Adhesion Tester

Date	Action	Equip	Results/Comments
10/10/90	Test (Location 3 C)	A	>1000 PSI (80% C; 10% A; 10% F)
10/10/90	1 hr @ -100 F	C	
10/10/90	0 hrs @ 350 F	0	
10/11/90	18 hrs @ 120 F	H	
11/08/90	89 hrs @ 140 F	H	very humid
01/14/91			Sent to NLB for waterblasting

## M&amp;C Fabrication/Conditioning/Test Form 90-1

Set: I-2IP      Sample: 9002

Comments:

Materials: Sheffield #326

**Equip Definitions:** O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
07/16/90	Acid clean	-	Remove mill scale both sides of panel
07/18/90	Medium rusting	H	
08/16/90	Clean	-	Acid clean and consultant clean
08/16/90	Coat	-	Brush coat (thin) air dry 1239.7g
08/17/90	Coat	-	Brush Coat (thin) air dry 1240.2g
08/20/90	1 hr @ 480 F	0	Cure (1.5 hrs slowly)
08/22/90	15 hrs @ 125 F	H	
08/23/90	1 hr @ -100 F	C	Autocycle
08/23/90	1 hr @ 600 F	C	Autocycle
08/23/90	15 hrs @ 125 F	H	
08/28/90	22 hrs @ 125 F	H	
08/29/90	5 hrs @ 600 F	0	
08/29/90	14 hrs @ 125 F	H	

## NMC Fabrication/Conditioning/Test Form 90-1

Set: I-21P      Sample: 9002

Comments: Page 2

Materials: Sheffield #326

Equip Definitions: 0 - Oven; C - Heat/Cooling Chamber; H - Humidity Chamber; A - Adhesion Tester

Date	Action	Equip	Results/Comments
08/30/90	4 hrs @ 600 F	0	
09/05/90	1 hr @ -100 F	C	
09/05/90	16 hrs @ 125 F	H	
09/06/90	3 hrs @ 600 F	0	
09/06/90	15 hrs @ 125 F	H Humid to dry	
09/07/90	1 hr @ -125 F	C Autocycle	
09/07/90	1 hr @ 800 F	C Manual HIGH heat No damage	
09/11/90	1 hr @ -100 F	C autocycle	
09/11/90	1 hr @ 590 F	C altered autocycle	
09/12/90	1 hr @ -100 F	C autocycle	
09/12/90	3 hrs @ 600 F	0	
09/12/90	16 hrs @ 125 F	H	
09/13/90	21 hrs @ 125 F	H	

## NRC Fabrication/Conditioning/Test Form 90-1

Set: I-21P      Sample: 9002

Comments: Page 3

Materials: Sheffield #326

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/11/90	1 hr @ -100 F	C	
09/18/90	1 hr @ -100 F	C	
09/19/90	1 hr @ 600 F	0	
09/19/90	1 hr @ 15 F	H	
09/19/90	21 hrs @ 130 F	H	
09/20/90	Test (Location 1)	A	200 PSI (100% C)
09/24/90	3 hrs @ 600 F	0	
09/24/90	13 hrs @ 120 F	H	
09/25/90	1 hr @ 487 F	0	
09/25/90	16 hrs @ 120 F	H	
09/26/90	3 hrs @ 600 F	0	
09/27/90	40 hrs @ 120 F	H	
09/29/90	Test (Location 2)	A	50 PSI (100% C)

**HRC Fabrication/Conditioning/Test Form 90-1****Set: I-21P****Sample: 9002****Comments: Page 4****Materials: Sheffield #326****Equip Definitions:** O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/01/90	3.5 hrs @ 610 F	O	
10/01/90	16 hrs @ 120 F	H	
10/02/90	1 hr @ -100 F	C	
10/03/90	23 hrs @ 120/150 F	H	
10/04/90	1 hr @ -100 F	C	
10/04/90	1 hrs @ 600 F	C	autocycle
10/04/90	15 hrs @ 120/160 F	H	
10/05/90	1 hr @ 487 F	O	
10/09/90	1 hr @ -100 F	C	
10/09/90	1 hr @ 600 F	C	autocycle
10/09/90	20 hrs @ 120 F	H	very humid
10/10/90	Test (Location 1 C)	A	50 PSI (90% F; 10% C) no test
10/10/90	1 hr @ -100 F	C	

## NRC Fabrication/Conditioning/Test Form 90-1

Set: I-21P    Sample: 9002

Comments: page 5

Materials: Sheffield #326

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/10/90	8 hrs @ 350 F	0	
10/11/90	18 hrs @ 120 F	H	
11/08/90	89 hrs @ 140 F	H	
11/26/90	1 hr @ 450 F	C	
11/26/90	4 hrs @ 600 F	0	
11/27/90	6 hrs @ 600 F	0	
11/27/90	40 hrs @ 140 F	H	very humid
11/29/90	4.5 hrs @ 550 F	0	
11/29/90	20 hrs @ 140 F	H	very humid
12/03/90	Test (Location 4)	A	50 PSI (100% F)
	Events:	21 H; 1 C (800F); 18 O/C (350 to 650F); 11 C (100F) = 51 total	
12/04/90	3 hrs @ 550 F	0	
12/04/90	15 hrs @ 120-160 F	H	dry

## HRC Fabrication/Conditioning/Test Form 90-1

Set: I-21P      Sample: 9002

Comments: page 6

Materials: Sheffield #326

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/05/90	1 hr @ -100 F	C	autocycle
12/05/90	1 hr @ 600 F	C	autocycle
12/05/90	16 hrs @ 120 F	H	
12/06/90	1 hr @ -110 F	C	autocycle
12/06/90	3 hrs @ 560 F	C	autocycle
12/07/90	5 hrs @ 560 F	0	
12/08/90	1 hr @ -110 F	C	autocycle
12/10/90	1 hr @ -110 F	C	autocycle
12/10/90	3 hrs @ 570 F	0	
12/11/90	1 hr @ -110 F	C	autocycle
12/11/90	3 hrs @ 570 F	0	
12/12/90	3 hrs @ 580 F	0	removed @ 225 F
12/12/90	1 hr @ -110 F	C	remove @ 20 F

**NRC Fabrication/Conditioning/Test Form 90-1****Set: I-21P      Sample: 9002****Comments: page 7****Materials: Sheffield # 326****Equip Definitions:** 0 = Open; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

<b>Date</b>	<b>Action</b>	<b>Equip</b>	<b>Results/Comments</b>
12/12/90	18 hrs @ 140 F	H	very humid
12/13/90	5 hrs @ 580 F	0	
12/15/90	30 hrs @ 115/140 F	H	dry
12/15/90	15 hrs @ 120 F	H	humid
12/17/90	3 hrs @ 560 F	0	
12/17/90	32 hrs @ 140 F	H	very humid
12/17/90	12 hrs @ 120 F	H	very humid
12/19/90	3 hrs @ 580 F	0	
12/19/90	1 hr @ -110 F	C	autocycle
01/14/91	Sent for watercleaning @ NLB		

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-21P      Sample: 9003

Comments:

Materials: Sherwin Williams Superbright

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
07/16/90	Acid Clean	-	Remove mill scale both sides of panel
07/16/90	Rust	H	
08/17/90	Clean	-	Acid clean and consultant clean
08/17/90	Coat	-	Brush coat (thin) 1226.3g
08/20/90	1 hr @ 480 F	0	Cure first coat
08/20/90	Coat	-	Brush coat (thin)
08/21/90	Coat	-	Brush coat (thin)
08/22/90	2 hrs @ 600 F	0	Slowly heat-up
08/22/90	15 hrs @ 125	H	
08/23/90	1 hr @ -100 F	C	Cold autocycle
08/23/90	1 hr @ 600 F	C	Hot autocycle
08/23/90	15 hrs @ 125 F	H	
08/28/90	22 hrs @ 125 F	H	

## HRC Fabrication/Conditioning/Test Form 90-1

Set: I-21P      Sample: 9003      Comments: Page 2

Materials: Sherwin Williams Silverbrite

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
08/29/90	5 hrs @ 600 F	0	
08/29/90	14 hrs @ 125 F	H	
08/30/90	4 hrs @ 600 F	0	
09/05/90	1 hr @ -100 F	C	
09/05/90	16 hrs @ 125 F	H	
09/06/90	3 hrs @ 600 F	0	
09/06/90	15 hrs @ 125 F	H	Humid to dry
09/07/90	1 hr @ -125 F	C	Autocycle
09/07/90	1 hr @ 800 F	C	Manual HIGH heat Stop testing

## NRC Fabrication/Conditioning/Test Form 90-1

Set: I-21P      Sample: 9004

Comments: Spray tests

Materials: Red Hot Spraying

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
	old 7104 sample Backside clean		
			1290.9 As cleaned
			1290.0 1st coat
			1291.1 2nd coat
			1291.2 3rd coat
			4th coat
09/12/90	3 hrs @ 600 F	0	
09/12/90	16 hrs @ 125 F	H	
09/13/90	21 hrs @ 125 F	H	
09/20/90	Stop testing		

**NRC Fabrication/Conditioning/Test Form 90-1**

**Set:** I-P2      **Sample:** 9005  
**Comments:**  
**Materials:** Red Hot Spraying

**Comments:**  
**(will scale on back)**

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/06/90	3 hrs @ 600 F	0	
09/06/90	15 hrs @ 125 F	H	
09/07/90	1 hr @ -100 F	C	
09/07/90	1 hr @ 800 F	C	HOT
09/11/90	1 hr @ -100 F	C	
09/11/90	1 hr @ 590 F	C	
09/12/90	1 hr @ -100 F	C	
09/12/90	3 hrs @ 600 F	0	
09/12/90	16 hrs @ 125 F	H	
09/13/90	21 hrs @ 125 F	H	
09/20/90	Test (Location 1)	A	550 PSI (80% C; 20% I)

## HRC Fabrication/Conditioning/Test Form 90-1

Set: 1-P2      Sample: 9005

Comments: page 2

Materials: Red Hot Spraying

(will scale on back)

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/24/90	3 hrs @ 600 F	0	
09/24/90	13 hrs @ 120 F	H	
09/25/90	1 hr @ 487 FF	0	
09/25/90	16 hrs @ 120 F	H	
09/26/90	3 hrs @ 600 F	0	
09/27/90	40 hrs @ 120 F	H	
09/29/90	Test (Location 2)	A	800 PSI (75% C; 10% A; 15% F)
10/01/90	3.5 hrs @ 610 F	0	
10/01/90	16 hrs @ 120 F	H	
10/02/90	1 hr @ -100 F	C	
10/03/90	23 hrs @ 120/150 F	H	
10/04/90	1 hr @ -100 F	C	
10/04/90	1 hr @ 600	C	autocycle

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9005      Comments: Page 3  
Materials: Red Hot Spraying

(mill scale on back)

Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/04/90	15 hrs @ 120/150 F	H	
10/06/90	1 hr @ 487 F	O	
10/08/90	1 hr @ -100 F	C	
10/08/90	1 hr @ 600 F	C	autocycle
10/08/90	20 hrs @ 120 F	H	very humid
10/09/90	1 hr @ -100 F	C	
10/10/90	Test (Location 3 C)	A	600 PSI (90% C; 10% C/I black oxide)
10/10/90	1 hr @ -100 F	C	
10/10/90	8 hrs @ 350 F	O	
10/11/90	18 hrs @ 120 F	H	very humid
			Stop testing

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9007

Comments: A516-70

Materials: MARB-47

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
07/12/90	Acid clean	-	Remove mill scale both sides of panel
07/12/90	16 hrs @ 130 F	H	Rusting panels
07/13/90	2 hrs @ 620 F	0	Aging panel
07/13/90	17 hrs @ 135 F	H	Rusting panel
07/19/90	20 hrs @ 130 F	H	Salt spray rusting
09/07/90	Acid reclean	-	One side
09/07/90	Coat	-	Cloth wipe on MARB
09/07/90	Coat	-	Spray light coat MARB      1227.7g
09/07/10	Coat	-	Spray coat MARB      1227.9g
09/07/90	Coat	-	Spray topcoat MARB      dry wt: 1228.4g
09/10/90	1 hr @ 487 F	0	cure
09/11/90	1 hr @ -100 F	C	
09/11/90	1 hr @ 590 F	C	

## NRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2

Sample: 9007

Comments: page 2

Materials: MARB-47

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/12/90	1 hr @ -100 F	C	
09/12/90	3 hrs @ 600 F	0	
09/12/90	16 hrs @ 125 F	H	
09/13/90	21 hrs @ 125 F	H	Very humid
09/14/90	1 hr @ -100 F	C	
09/18/90	1 hr @ -100 F	C	
09/18/90	1 hr @ 600 F	0	
09/19/90	1 hr @ 15 F	H	
09/19/90	21 hrs @ 130 F	H	
09/20/90	Test (Location 1)	A	600 PSI (100% C/I)
09/24/90	3 hrs @ 600 F	0	
09/24/90	13 hrs @ 120 F	H	
09/25/90	1 hr @ 487 F	0	

## NRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2

Sample: 9007

Comments: page 3

Materials: WAR-B-47

Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/25/90	16 hrs @ 120 F	H	
09/26/90	3 hrs @ 600 F	O	
09/27/90	40 hrs @ 120 F	H	
09/29/90	Test (Location 2)	A	500 PSI (100% C/I)
10/01/90	3.5 hrs @ 610 F	O	
10/01/90	16 hrs @ 120 F	H	
10/02/90	1 hr @ -100 F	C	
10/03/90	23 hrs @ 120/150 F	H	
10/04/90	1 hr @ -100 F	C	
10/04/90	1 hr @ 600 F	C	autocycle
10/04/90	15 hrs @ 120/160 F	H	
10/06/90	1 hr @ 487 F	O	
10/08/90	1 hr @ -100 F	C	

Set: I-P2      Sample: 9007  
Materials: MARB-47

MRC Fabrication/Conditioning/Test Form 90-1

Comments: page 4

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/08/90	1 hr @ 600 F	C	autocycle
10/08/90	20 hrs @ 120 F	H	very humid
10/09/90	1 hr @ -100 F	C	
10/10/90	Test (Location 3 TL)	A	600 PSI (100% C/I) Grey, lots of lint
10/10/90	1 hr @ -100 F	C	
10/10/90	8 hrs @ 350 F	0	
10/11/90	18 hrs @ 120 F	H	
10/19/90	65 hrs @ 100 F	H	very humid
10/22/90	24 hrs @ 120/135 F	H	very humid
11/08/90	89 hrs @ 140 F	H	very humid
11/26/90	1 hr @ 450 F	C	
11/26/90	4 hrs @ 600 F	0	
11/27/90	6 hrs @ 600 F	0	

## HRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9007

Comments: page 5

Materials: MARB-47

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
11/27/90	40 hrs @ 140 F	H	very humid
11/29/90	4.5 hrs @ 550 F	0	
11/29/90	20 hrs @ 140 F	H	very humid
12/03/90	Test (Location 4)	A	950 PSI (100% C/I)
12/04/90	3 hrs @ 550 F	0	
12/04/90	15 hrs @ 120-160 F	H	dry
12/05/90	1 hr @ -100 F	C	
12/05/90	1 hr @ 600 F	C	auto
12/05/90	16 hrs @ 120 F	H	
12/06/90	1 hr @ -110 F	C	auto
12/06/90	3 hrs @ 560 F	0	
12/07/90	5 hrs @ 560 F	0	
12/08/90	1 hr @ -110 F	C	auto

**Set: I-P2      Sample: 9007**  
**Materials: MARB-47**

**NRC Fabrication/Conditioning/Test Form 90-1**

Comments: page 6

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/10/90	1 hr @ -110 F	C	auto
12/10/90	3 hrs @ 570 F	0	
12/11/90	1 hr @ -110 F	C	auto
12/12/90	3 hrs @ 580 F	0	removed at 225 F end before ambient
12/12/90	1 hr @ -110 F	C	removed at 20 F autoclycle close to end
12/12/90	18 hrs @ 140 F	H	very humid
12/13/90	5 hrs @ 580 F	0	
12/15/90	30 hrs @ 115-140	H	dry
12/15/90	15 hrs @ 120 F	H	humid
12/17/90	3 hrs @ 560 F	0	
12/17/90	32 hrs @ 140 F	H	very humid
12/17/90	12 hrs @ 120 F	H	very humid
12/19/90	3 hrs @ 560 F	0	

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9007

Comments: page 7

Materials: MARB-47

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/19/90	1 hr @ -110	C	auto
12/28/90	Test (location 5)	A	1000 PSI (60% C/I; 40 % F) Continued on Test Form 91-1
01/15/91	1 hr @ -110 F	C	auto
01/15/91	1 hr @ 600 F	C	auto
01/15/91	16 hrs @ 118 F	H	
01/16/91	20 hrs @ 120 F	H	very humid
01/17/91	15 hrs @ 120 F	H	
01/18/91	28 hrs @ 120 F	H	
01/19/91	1 hr @ -110 F	C	
01/19/91	1 hr @ 580 F	0	
01/21/91	1 hr @ -100 F	C	
01/21/91	2 hrs @ 600 F	0	
01/22/91	2 hrs @ 610 F	0	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: IP2 - 9007    Comments: See 1990 Testing

Substrate/Preparation: 516/ medium salt pitting

Materials: MARB-47 (cloth wipe and 3 spray coats)

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
 H = Humidity Chamber;  
 A = Adhesion Tester; T = Misc Tests

7

6

Date	Action	Equip	Results/Comments
07/12/90	See 1990 Test Form 90-1		Mill Scale removed both sides
09/07/90	" " "		Coat date; cured: 09/10/90
12/28/90	" " "		3 month testing completed: 65 events
12/28/90	Test (Location 5)	A	1000 PSI (60% C/I; 40% F)
01/15/91	1 hr @ -110 F	C	Cold Autocycle
01/15/91	1 hr @ 600 F	C	Hot Autocycle
01/15/91	16 hrs @ 118 F	H	Humid
01/16/91	1/2 hr @ -95 F	C	Cold (aborted autocycle)
01/16/91	20 hrs @ 120 F	H	very Humid
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot,dry
01/22/91	2 hrs @ 610 F	O	hot,dry
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	very humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 6)	A	900 PSI (20% C/I; 70% F; 10% dolly)

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: IP2 - 9007    Comments: Page 2

Materials: MARB-47

Equip Definitions: See Page 1

Date	Action	Equip	Results/Comments
01/30/91	1 hr @ -110 F	C	cold
01/30/91	41 hrs @ 115 F	H	very humid
02/01/91	1 hr @ -110 F	C	autoclave
02/01/91	1 hr @ 600 F	C	autoclave
02/04/91	2.5 hrs @ 600 F	O	dry heat
02/04/91	42 hrs @ 115/150 F	H	very humid
02/06/91	2.5 hrs @ 580 F	O	dry heat
02/07/91	3 hrs @ 590 F	O	dry heat
02/08/91	1 hr @ -100 F	C	autocycle
02/09/91	1 hr @ -100 F	C	
02/11/91	1 hr @ -100 F	C	autocycle
02/11/91	2 hrs @ 620 F	O	heat
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	autocycle
02/12/91	2 hrs @ 600 F	O	
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	

## NRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: IP2 - 9007      Comments: page 3

Materials: MARB 47

Equip Definitions: See Page 1

7  
6

Date	Action	Equip	Results/Comments
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 7)	A	100 PSI (85% C/I, 15% F)
02/19/91	STOP TESTING		Accelerated testing completed

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9008

Comments:

Materials: MZRB-60

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
07/12/90	Acid clean	-	Remove mill scale both sides of panel
07/12/90	16 hrs @ 130 F	H	Rusting panels
07/13/90	2 hrs @ 620 F	0	Aging panel
07/13/90	17 hrs @ 135 F	H	Rusting panel
07/19/90	20 hrs @ 130 F	H	Salt spray rusting
09/07/90	Acid reclean	-	One side
09/07/90	Coat	-	Cloth wipe on MZRB-60
09/07/90	Coat	-	light coat MZRB-60
09/07/90	Coat	-	Brush coat MZRB-60
09/10/90	1 hr @ 487 F	0	cure
09/11/90	1 hr @ -100 F	C	
09/11/90	1 hr @ 590 F	C	

## NRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9008      Comments: page 2  
 Materials: MZRB-60

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/12/90	1 hr @ -100 F	C	
09/12/90	3 hrs @ 600 F	0	
09/12/90	16 hrs @ 125 F	H	
09/13/90	21 hrs @ 125 F	H	very humid
09/14/90	1 hr @ -100 F	C	
09/18/90	1 hr @ -100 F	C	
09/18/90	1 hr @ 600 F	0	
09/19/90	1 hr @ 15 F	H	
09/19/90	21 hrs @ 130 F	H	
09/20/90	Test (Location 1)	A	>1050 No failure Knockoff 95% Substrate; 5% C
09/24/90	3 hrs @ 600 F	0	
09/24/90	13 hrs @ 120 F	H	
09/25/90	1 hr @ 487 F	0	

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9008

Comments: page 3

Materials: MZRB-60

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/25/90	16 hrs @ 120 F	H	
09/26/90	3 hrs @ 600 F	0	
09/27/90	40 hrs @ 120 F	H	
09/29/90	Test (Location 2)	A	400 PSI (99% C/I; 1% F)
10/01/90	3.5 hrs @ 610 F	0	
10/01/90	16 hrs @ 120 F	H	
10/02/90	1 hr @ -100 F	C	
10/03/90	23 hrs @ 120/150 F	H	
10/04/90	1 hr @ -100 F	C	
10/04/90	1 hr @ 600 F	C	autocycle
10/04/90	15 hrs @ 120/160 F	H	
10/06/90	1 hr @ 487 F	0	
10/08/90	1 hr @ -100 F	C	autocycle

**NRC Fabrication/Conditioning/Test Form 90-1****Set: I-P2      Sample: 9008**

Comments: page 4

**Materials: MZRB-60 Spraying****Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/08/90	1 hr @ 600 F	C	autocycle
10/08/90	20 hrs @ 120 F	H	very humid
10/09/90	1 hr @ -100 F	C	
10/10/90	Test (Location 3 C)	A	>1000 no failure
10/10/90	1 hr @ -100 F	C	
10/10/90	8 hrs @ 350 F	0	
10/11/90	18 hrs @ 120 F	H	very humid
11/08/90	89 hrs @ 140 F	H	
11/26/90	1 hr @ 450 F	C	
11/26/90	4 hrs @ 600 F	0	
11/27/90	6 hrs @ 600 F	0	
11/27/90	40 hrs @ 140 F	H	very humid
11/29/90	4.5 hrs @ 550 F	0	

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9008

Comments: page 5

Materials: MZRB-60

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
11/29/90	20 hrs @ 140 F	H	very humid
12/03/90	Test (Location 4)	A	550 PSI (100% C)
12/04/90	3 hrs @ 550 F	0	
12/04/90	15 hrs @ 120-160 F	H	dry
12/05/90	1 hr @ -100 F	C	
12/05/90	1 hr @ 600 F	C	auto
12/05/90	16 hrs @ 120 F	H	
12/06/90	1 hr @ -110 F	C	auto
12/06/90	3 hrs @ 560 F	0	
12/07/90	5 hrs @ 560 F	0	
12/08/90	1 hr @ -110 F	C	auto
12/10/90	3 hrs @ 570 F	0	
12/11/90	1 hr @ -110 F	C	auto

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9008

Comments: page 6

Materials: MZRB-60

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/11/90	3 hrs @ 570 F	0	
12/12/90	3 hrs @ 580 F	0	removed at 225 F end before ambient
12/12/90	1 hr @ -110 F	C	removed at 20 F autocycle close to end
12/12/90	18 hrs @ 140 F	H	very humid
12/13/90	5 hrs @ 580 F	0	
12/15/90	30 hrs @ 115-140	H	dry
12/15/90	15 hrs @ 120 F	H	humid
12/17/90	3 hrs @ 560 F	0	
12/17/90	32 hrs @ 140 F	H	very humid
12/17/90	12 hrs @ 120 F	H	very humid
12/19/90	3 hrs @ 560 F	0	
12/19/90	1 hr @ -110	C	auto
12/28/90	Test (location 5)	A	400 PSI (95% C; 5% F) STOP TESTING

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9009      Comments:  
 Materials: MARB-47 over MZRB-60

1 2 3 4 5

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
07/12/90	Acid clean	-	Remove mill scale both sides of panel
07/12/90	16 hrs @ 130 F	H	Rusting panels
07/13/90	2 hrs @ 620 F	O	Aging panel
07/13/90	17 hrs @ 135 F	H	Rusting panel
07/19/90	20 hrs @ 130 F	H	Salt spray and severely pit rusting
09/07/90	Acid reclean	-	One side; grind over corner 1226.7g
09/07/90	Coat	-	Cloth wipe on MZRB-60 1227.6g
09/07/90	Coat	-	Spray light coat MARB 1227.7g
09/07/10	Coat	-	Spray coat MARB 1227.9g
09/07/90	Coat	-	Spray topcoat MARB dry wt: 1228.4g
09/10/90	1 hr @ 487 F	0	cure
09/11/90	1 hr @ -100 F	C	
09/11/90	1 hr @ 590 F	C	

Set: 1-P2      Sample: 9009

**NRC Fabrication/Conditioning/Test Form 90-1**

Comments: page 2

Materials: MARB-47 over MZRB-60

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/12/90	1 hr @ -100 F	C	
09/12/90	3 hrs @ 600 F	0	
09/12/90	16 hrs @ 125 F	H	
09/13/90	21 hrs @ 125 F	H	very humid
09/14/90	1 hr @ -100 F	C	
09/18/90	1 hr @ -100 F	C	
09/18/90	1 hr @ 600 F	0	
09/19/90	1 hr @ 15 F	H	
09/19/90	21 hrs @ 130 F	H	
09/20/90	Test (Location 1)	A	1050 PSI (90 % A; 10% F) Lint hairs
09/24/90	3 hrs @ 600 F	0	
09/24/90	13 hrs @ 120 F	H	
09/25/90	1 hr @ 487 F	0	

**NRC Fabrication/Conditioning/Test Form 90-1**

Set: I-P2      Sample: 9009

Comments: page 3

Materials: MARB-47 over NZRB-60

**Equip Definitions:** O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/25/90	16 hrs @ 120 F	H	
09/26/90	3 hrs @ 600 F	O	
09/27/90	40 hrs @ 120 F	H	
09/29/90	Test (Location 3)	A	510 PSI (50% C; 5% C/I)
10/01/90	3.5 hrs @ 610 F	O	
10/01/90	16 hrs @ 120 F	H	
10/02/90	1 hr @ -100 F	C	
10/03/90	23 hrs @ 120/150 F	H	
10/04/90	1 hr @ -100 F	C	
10/04/90	1 hr @ 600 F	C	Autocycle
10/04/90	15 hrs @ 120/160 F	H	
10/06/90	1 hr @ 487 F	O	
10/08/90	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9009

Comments: page 4

Materials: WARB-47 over MZRB-60

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/08/90	1 hr @ 600 F	C	autocycle
10/08/90	20 hrs @ 120 F	H	very humid
10/09/90	1 hr @ -100 F	C	
10/10/90	Test (Location 4 TC)	A	750 PSI (50% C; 50% C/I black)
10/10/90	1 hr @ -100 F	C	
10/10/90	8 hrs @ 350 F	0	to Ken to check black oxide
11/08/90	89 hrs @ 140 F	H	
11/26/90	1 hr @ 450 F	C	
11/26/90	4 hrs @ 600 F	0	
11/27/90	6 hrs @ 600 F	0	
11/27/90	40 hrs @ 140 F	H	very humid
11/29/90	4.5 hrs @ 550 F	0	
11/29/90	20 hrs @ 140 F	H	very humid

## HRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2

Sample: 9009

Materials: MARB-47 over MZRB-60

Comments: page 5

**Equip Definitions:** O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/03/90	Test (Location 2)	A	700 PSI (100% C)
12/04/90	3 hrs @ 550 F	O	
12/04/90	15 hrs @ 120-160 F	H	dry
12/05/90	1 hr @ -100 F	C	
12/05/90	1 hr @ 600 F	C	auto
12/05/90	16 hrs @ 120 F	H	
12/06/90	1 hr @ -110 F	C	auto
12/06/90	3 hrs @ 560 F	O	
12/07/90	5 hrs @ 560 F	O	
12/08/90	1 hr @ -110 F	C	auto
12/10/90	1 hr @ -110 F	C	auto
12/10/90	3 hrs @ 570 F	O	
12/11/90	1 hr @ -110 F	C	auto

**MRC Fabrication/Conditioning/Test Form 90-1****Set: I-P2      Sample: 9009****Comments: page 6****Materials: MARB-47 over NZRB-60****Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester**

Date	Action	Equip	Results/Comments
12/11/90	3 hrs @ 570 F	O	removed at 225 F
12/12/90	3 hrs @ 580 F	O	removed at 225 F end before ambient
12/12/90	1 hr @ -110 F	C	removed at 20 F autoclycle close to end
12/12/90	18 hrs @ 140 F	H	very humid
12/13/90	5 hrs @ 580 F	O	
12/15/90	30 hrs @ 115-140	H	dry
12/15/90	15 hrs @ 120 F	H	humid
12/17/90	3 hrs @ 560 F	O	
12/17/90	32 hrs @ 140 F	H	very humid
12/17/90	12 hrs @ 120 F	H	very humid
12/19/90	3 hrs @ 560 F	O	
12/19/90	1 hr @ -110 F	C	auto
12/28/90	Test (location 5)	A	600 PSI (40% C; 60% F) STOP TESTING

## HRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9010

Comments:

Materials: HARB-47

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
07/13/90	Acid clean	-	Remove mill scale both sides of panel
07/16/90	3 hrs @ 130 F	H	Rusting panels
07/18/90	16 hrs @ 130 F	H	Rusting panels
07/19/90	Salt Spray	-	Spray panels with Sea Salt solution
07/19/90	20 hrs @ 130 F	H	Severe rusting of panels
07/20/90	5 hrs @ 140 F	H	Re-salt spray
07/23/90	8 hrs @ 170 F	H	
07/23/90	4 hrs @ 140 F	H	severe pitting corrosion
09/17/90	Clean (1 hour)	-	Consultant gel
09/24/90	Clean (5 minutes)	-	Flash rust removal with XII-04 very clean
09/24/90	Coat	-	Spray coat 2 thin layers
09/25/90	Coat	-	Spray coat 2 layers
09/25/90	1 hr @ 487 F	0	Slow cure

**MRC Fabrication/Conditioning/Test Form 90-1**

Set: I-P2      Sample: 9010

Comments: Page 2

Materials: MARB-47

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/25/90	16 hrs @ 120 F	H	
09/26/90	3 hrs @ 600 F	0	
09/27/90	40 hrs @ 120 F	H	
09/29/90	Test (Location 1)	A	350 PSI (85% C; 15% F)
10/01/90	3.5 hrs @ 610 F	0	
10/01/90	16 hrs @ 120 F	H	
10/02/90	1 hr @ -100 F	C	
10/03/90	23 hrs @ 120/150 F	H	Excellent condition; rough due to Aluminum globs
10/04/90	1 hr @ -100 F	C	
10/04/90	1 hr @ 600 F	C	
10/06/90	15 hrs @ 120/160 F	H	
10/06/90	1 hr @ 487 F	0	
10/08/90	1 hr @ -120 F	C	

## HRC Fabrication/Conditioning/Test Form 90-1

Set: 1-P2      Sample: 9010

Comments: page 3

Materials: HARB-47

**Equip Definitions:** O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/08/90	1 hr @ 600 F	C	autocycle
10/08/90	20 hrs @ 120 F	H	very humid
10/09/90	1 hr @ -100 F	C	
10/10/90	Test (Location 2 Tl)	A	500 PSI (100% C)
10/10/90	1 hr @ -100 F	C	
10/10/90	8 hrs @ 350 F	O	
10/11/90	18 hrs @ 120 F	H	very humid
10/19/90	65 hrs @ 100 F	H	very humid
10/22/90	24 hrs @ 120/135 F	H	very humid
11/08/90	89 hrs @ 140 F	H	very humid
11/29/90	4.5 hrs @ 550 F	O	
11/29/90	20 hrs @ 140 F	H	very humid
12/03/90	Test (Location 3)	A	650 PSI (100% C)

**MRC Fabrication/Conditioning/Test Form 90-1**

Set: I-P2      Sample: 9010

Comments: page 4

Materials: MARB-47

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/04/90	3 hrs @ 550 F	0	
12/04/90	15 hrs @ 120-160 F	H	dry
12/05/90	1 hr @ -100 F	C	
12/05/90	1 hr @ 600 F	C	autocycle
12/05/90	16 hrs @ 120 F	H	
12/06/90	1 hr @ -110 F	C	autocycle
12/06/90	3 hrs @ 560 F	0	
12/07/90	5 hrs @ 560 F	0	
12/08/90	1 hr @ -110 F	C	autocycle
12/10/90	1 hr @ -110 F	C	autocycle
12/10/90	3 hrs @ 570 F	0	
12/11/90	1 hr @ -110 F	C	autocycle
12/11/90	3 hrs @ 570 F	0	

## NRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9010

Comments: page 5

Materials: MARB-47

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/12/90	3 hrs @ 580 F	0	removed at 225 F
12/12/90	1 hr @ -110 F	C	removed at 20 F autocycle
12/12/90	18 hrs @ 140 F	H	very humid
12/13/90	5 hrs @ 580 F	0	
12/15/90	30 hrs @ 115-140 F	H	dry
12/15/90	15 hrs @ 120 F	H	humid
12/17/90	3 hrs @ 560 F	0	
12/17/90	32 hrs @ 140 F	H	very humid
12/17/90	12 hrs @ 120 F	H	very humid
12/19/90	3 hrs @ 560 F	0	
12/19/90	1 hr @ -110 F	C	autocycle
12/28/90	Test (location 4 & 5)	A	200 & 300 PSI (100% C)
			See 1991 testing on new format

**MRC Fabrication/Conditioning/Test Form 90-1****Set: I-P2      Sample: 9010**

Comments: page 6

**Materials: MARB-47****Equip Definitions:** 0 = Open; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
01/17/91	15 hrs @ 120 F	H	humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle
01/19/91	1 hr @ 580 F	0	dry heat
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	0	dry heat
01/22/91	2 hrs @ 610 F	0	dry heat
01/22/91	1 hr @ -110 F	C	cold autocycle
01/22/91	16 hrs @ 115 F	H	Very humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (location 6)	A	100 PSI (100% C)
	4 spray coats practice and was not intended to be tested		Holds up well
	See 1991 format		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: IP2-9010      Comments: See form 90-1

Substrate/Preparation: 51 /Severe SS pitting

Materials: MARB-47

6

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
 H = Humidity Chamber;  
 A = Adhesion Tester; T = Misc Tests

Date	Action	Equip	Results/Comments
07/13/90	remove mil scale	-	HCL clean both sides
07/23/90	See Test form 90-1	H	Severe SS rust pitting
09/24/90	See Test form 90-1	-	Spray 4 coats
09/25/90	1 hr @ 487 F Cure	O	Slow to temperature
12/28/90	See Test Form 90-1	-	47 events in 3 months
01/15/91	16 hrs @ 118 F	H	humid
01/16/91	1/2 hr @ -95 F	C	
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	very humid
01/23/91	1 hr @ -110 F	C	cold      Poor spray application
01/26/91	Test (Location 6)	A	100 PSI (100% C)
01/30/91	1 hr @ -110 F	C	
01/30/91	41 hrs @ 115 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1

- Page 2

Set-Sample: IP2 - 9010    Comments: page 2

Materials: MARB-47

Equip Definitions: See Page 1

Date	Action	Equip	Results/Comments
02/01/91	1 hr @ -110 F	C	
02/01/91	1 hr @ 600 F	C	
02/04/91	2.5 hrs @ 600 F	O	
02/04/91	42 hrs @ 115-150 F	H	very humid
02/06/91	2.5 hrs @ 580 F	O	
02/07/91	3 hrs @ 590 F	O	
02/08/91	1 hr @ -100 F	C	autocycle
02/09/91	1 hr @ -100 F	C	autocycle
02/11/91	1 hr @ -100 F	C	autocycle
02/11/91	2 hrs @ 620 F	O	
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	
02/12/91	2 hrs @ 600 F	O	
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 7)	A	100 PSI (100% C) Testing completed
03/08/91	Clean off MARB		HCL/ Sander

## NRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9011 - 9013      Comments: Q Panels/ Sprayed

Materials: MARB-47 1 coat, 2 coats, 3 coats

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
09/25/90	Clean	-	Wipe Q-Panels with Xylene
09/25/90	Coat	-	Spray one coat 9011
			Spray two coats 9012
			Spray 3 coats 9013
09/25/90	1 hr @ 487 F	0	Curing slowly
09/25/90	16 hrs @ 120 F	H	
09/26/90	3 hrs @ 600 F	0	
09/26/90	40 hrs @ 120 F	H	
10/01/90	3.5 hrs @ 610 F	0	
10/01/90	16 hrs @ 120 F	H	
10/02/90	1 hr @ -100 F	C	
10/03/90	23 hrs @ 120/150 F	H	
10/04/90	1 hr @ -100 F	C	

## HRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9011;9012;9013      Comments: page 2

Materials: MARB-47 on Q-panels

Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/04/90	1 hr @ 600 F	C	
10/04/90	15 hrs @ 120 F/160 F	H	
10/06/90	1 hr @ 487 F	O	
10/08/90	1 hr @ -100 F	C	
10/08/90	1 hr @ 600 F	C	autocycle
10/08/90	20 hrs @ 120 F	H	very humid
10/10/90	Test (location 1)	A	50 PSI (100% F no test) 9013 only
			Stop Tests

## MRC Fabrication/Conditioning/Test Form 90-1

Set: 21      Sample: 9014

Comments: A-516 steel/Materials: MARB-47

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/04/90	Remove mill scale	-	HCl acid clean both sides
10/04/90	15 hrs @ 120/160 F	H	Light rusting
10/05/90	Clean	-	Consultant gel XIX-01 (5 min)/ Rinse
10/05/90	Coat	-	Spray coat 2 thin layers (small air sprayer)
			Let dry 15 minutes between coats
	Coat	-	Spray coat 3rd coat - 2 passes
10/06/90	Cure 1 hr @ 487 F	0	slow to temperature
10/08/90	1 hr @ -100 F	C	
10/08/90	1 hr @ 600 F	C	autocycle
10/08/90	20 hrs @ 120 F	H	Very humid
10/09/90	1 hr @ -100 F	C	
10/10/90	Test (location 1 fl)	A	>1000 PSI No Failure
10/10/90	1 hr @ -100 F	C	

Set: 21      Sample: 9014

Comments: page 2

Materials: MARB-47

**MRC Fabrication/Conditioning/Test Form 90-1**

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/10/90	8 hrs @ 350 F	0	To Ken to check Black Oxide
11/08/90	89 hrs @ 140 F	H	No rusting
11/26/90	1 hr @ 450 F	C	
11/26/90	4 hrs @ 600 F	0	
11/27/90	6 hrs @ 600 F	0	
11/27/90	40 hrs @ 140 F	H	very humid
11/29/90	4.5 hrs @ 550 F	0	
11/29/90	20 hrs @ 140 F	H	very humid
12/03/90	Test (Location 2)	A	700 PSI (30% C/I; 30% C; 10% F; 30% dolly)
12/04/90	3 hrs @ 550 F	0	
12/04/90	15 hrs @ 120-160 F	H	dry
12/05/90	1 hr @ -100 F	C	
12/05/90	1 hr @ 600 F	C	auto

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-f2      Sample: 9014

Comments: page 3

Materials: MARR-47

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/05/90	16 hrs @ 120 F	H	
12/06/90	1 hr @ -110 F	C auto	
12/06/90	3 hrs @ 560 F	0	
12/07/90	5 hrs @ 560 F	0	
12/08/90	1 hr @ -110 F	C auto	
12/09/90	1 hr @ -110 F	C auto	
12/10/90	3 hrs @ 570 F	0	
12/11/90	1 hr @ -110 F	C auto	
12/11/90	3 hrs @ 570 F	0	
12/12/90	3 hrs @ 580 F	0	removed at 225 F end before ambient
12/12/90	1 hr @ -110 F	C	removed at 20 F autocycle close to end
12/12/90	18 hrs @ 140 F	H	very humid
12/13/90	5 hrs @ 580 F	0	
12/15/90	30 hrs @ 115-140	H	dry

## MRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9014  
 Materials: MARB-47

Comments: page 4

**Equip Definitions:** 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/15/90	15 hrs @ 120 F	H	humid
12/17/90	3 hrs @ 560 F	0	
12/17/90	32 hrs @ 140 F	H	very humid
12/17/90	12 hrs @ 120 F	H	very humid
12/19/90	3 hrs @ 560 F	0	
12/19/90	1 hr @ -110	C	auto
12/28/90	Test (location 3)	A	1000 PSI (60% C/l; 40 % F)

Poor 4 coats spray application; not intended to test; rusting bottom edge

CONTINUED in 1992 format

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 21 - 9014 Comments: See form 90-1

Substrate/Preparation: 516% light rusting

Materials: MARB-47

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
 H = Humidity Chamber;  
 A = Adhesion Tester; T = Misc Tests

	73	5
1		2
8		6
4		

Date	Action	Equip	Results/Comments
10/04/90	Remove mill scale	-	HCL clean both sides
10/05/90	See 1990 test form 90-1		Coat date; 3 spray coats
10/06/90	Cure 1 hr @ 487 F	O	Slow rise to temperature
12/28/90	1990 Test series ended		37 events in two months Edge rust
01/15/91	1 hr @ -110 F	C	autocycle
01/15/91	1 hr @ 600 F	C	autocycle
01/15/91	16 hrs @ 118 F	H	humid
01/16/91	1/2 hr @ -95 F	C	Liq Nitrogen low - aborted autocycle
01/16/91	20 hrs @ 120 F	H	very humid
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry heat
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	autocycle cold Rust appearing - small spots
01/21/91	2 hrs @ 600 F	O	hot dry
01/22/91	2 hrs @ 610 F	O	hot dry
01/22/91	1 hr @ -110 F	C	cold autocycle
01/22/91	16 hrs @ 115 F	H	very humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 4)	A	1000 PSI (70% F; 20% C/I; 10% dolly)

## NRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 21 - 9014 Comments: Page 2

Materials: MARB-47

Equip Definitions: See Page 1

5

6

Date	Action	Equip	Results/Comments
01/30/91	1 hr @ -110 F	C	cold
01/30/91	41 hrs @ 115 F	H	very humid
02/01/91	1 hr @ -110 F	C	autoclave
02/01/91	1 hr @ 600 F	C	autoclave
02/04/91	2.5 hrs @ 600 F	O	dry heat
02/04/91	42 hrs @ 115/150 F	H	very humid
02/06/91	2.5 hrs @ 580 F	O	dry heat
02/07/91	3 hrs @ 590 F	O	dry heat
02/08/91	1 hr @ -100 F	C	autocycle
02/09/91	1 hr @ -100 F	C	
02/11/91	1 hr @ -100 F	C	autocycle
02/11/91	2 hrs @ 620 F	O	heat
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	autocycle
02/12/91	2 hrs @ 600 F	O	
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 21 - 9014 Comments:

Materials: MARB 47

Equip Definitions: See Page 1

5

6

Date	Action	Equip	Results/Comments
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 5)	A	500 PSI (95% C, 2% A, 3% F)
02/22/91	2 hrs @ 590 F	O	
02/22/91	19 hrs @ 115 F	H	humid
02/25/91	2 hrs @ 600 F	O	dry heat
02/25/91	1 hr @ -100 F	C	autocycle
02/27/91	1 hr @ -100 F	C	autocycle
02/27/91	2 hrs @ 350 F	O	dry low heat
02/28/91	1 hr @ -100 F	C	auto
02/28/91	2 hrs @ 600 F	O	dry heat
02/28/91	18 hrs @ 115 F	H	humid
03/04/91	Test (Location 6)	A	>1000 PSI
03/04/91	1 hr @ 487 F	O	dry
03/04/91	1 hr @ -100 F	C	
03/05/91	1 hr @ -100 F	C	
03/05/91	1 hr @ 600 F	O	
03/05/91	16.5 hrs @ 116 F	H	
03/04/91	Test (Location 7)	A	1000 PSI
03/24/91	13 events later	C, A, O	
	Test (Location 8)	A	1000 PSI

**HRC Fabrication/Conditioning/Test Form 90-1****Set: 21      Sample: 9015**

Comments:

**Materials: MZRB-60****Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester**

Date	Action	Equip	Results/Comments
10/01/90	Remove mill scale	-	HCl acid clean both sides
10/01/90	15 hrs @ 120/160 F	H	Light rusting
10/05/90	Clean	-	Consultant gel XIX-01 (5 min)/ Rinse
10/05/90	Coat	-	Spray coat 1 layer (atomizer sprayer) 3 mils wet (too Thick)
			Let dry 15 minutes between coats
	Coat	-	Spray coat 2nd coat - 1 pass
10/06/90	Cure 1 hr @ 487 F	0	slow to temperature (remove coating from .125 inch square)
10/08/90	1 hr @ -100 F	C	
10/08/90	1 hr @ 600 F	C	autocycle
10/08/90	20 hrs @ 120 F	H	Very humid
10/09/90	1 hr @ -100 F	C	
10/10/90	Test (Location 1 TL)	A	>450 PSI (no test 100% F) no bonding to coating
10/10/90	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 90-1

Set: 21      Sample: 9015

Comments: page 2

Materials: MZRB-60

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/10/90	8 hrs @ 350 F	0	
10/11/90	18 hrs @ 120 F	H	
10/19/90	65 hrs @ 100 F	H	very humid
10/22/90	24 hrs @ 120/150 F	H	very humid
11/08/90	89 hrs @ 140 F	H	very humid      no rusting, but cracked where too thin
11/26/90	1 hr @ 450 F	C	
11/26/90	4 hrs @ 600 F	0	
11/27/90	6 hrs @ 600 F	0	
11/27/90	40 hrs @ 140 F	H	very humid
11/29/90	4.5 hrs @ 550 F	0	
11/29/90	20 hrs @ 140 F	H	very humid
12/03/90	Test (Location 2 TR)	A	1050 PSI (85% C; 15% F)
12/04/90	3 hrs @ 550 F	0	

## MRC Fabrication/Conditioning/Test Form 90-1

Set: 21      Sample: 9015

Comments: page 3

Materials: MZRB-60

Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/04/90	15 hrs @ 120-160 F	H	dry
12/05/90	1 hr @ -100 F	C	
12/05/90	1 hr @ 600 F	C	auto
12/05/90	16 hrs @ 120 F	H	
12/06/90	1 hr @ -110 F	C	auto
12/06/90	3 hrs @ 560 F	0	
12/07/90	5 hrs @ 560 F	0	
12/08/90	1 hr @ -110 F	C	auto
12/10/90	1 hr @ -110 F	C	auto
12/10/90	3 hrs @ 570 F	0	
12/11/90	1 hr @ -110 F	C	auto
12/11/90	3 hrs @ 570 F	0	
12/12/90	3 hrs @ 580 F	0	removed at 225 F end before ambient
12/12/90	1 hr @ -110 F	C	removed at 20 F autocycle close to end

## HRC Fabrication/Conditioning/Test Form 90-1

Set: I-P2      Sample: 9015      Comments: page 4

Materials: MZRB-60

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/12/90	18 hrs @ 140 F	H	very humid
12/13/90	5 hrs @ 580 F	0	
12/15/90	30 hrs @ 115-140	H	dry
12/15/90	15 hrs @ 120 F	H	humid
12/17/90	3 hrs @ 560 F	0	
12/17/90	32 hrs @ 140 F	H	very humid
12/17/90	12 hrs @ 120 F	H	very humid
12/19/90	3 hrs @ 560 F	0	
12/19/90	1 hr @ -110	C	auto
12/28/90	Test (location 3)	A	500 PSI (90% C; 10 % F)
01/15/91	1 hr @ -110 F	C	auto
01/15/91	1 hr @ 600 F	C	auto
01/15/91	16 hrs @ 118 F	H	
01/15/91	STOP TESTING		100% mudcracking

## HRC Fabrication/Conditioning/Test Form 90-1

Set: 21      Sample: 9016      Comments:

Materials: MZRB-blend; MZRB-33; MZRB-47; MZRB-60; MZRB-80

Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/04/90	Remove mill scale	-	HCl acid clean both sides
10/04/90	15 hrs @ 120/160 F	H	Light rusting
10/05/90	Clean	-	Consultant gel XIX-01 (5 min)/ Rinse
10/05/90	Coat	-	Brush coat 1 layer as shown above drawing
10/06/90	Cure 1 hr @ 487 F	0	slow to temperature
10/08/90	1 hr @ -100 F	C	
10/08/90	1 hr @ 600 F	C	autocycle
10/08/90	20 hrs @ 120 F	H	Very humid
10/09/90	1 hr @ -100 F	C	
10/10/90	Test (Location 1 TR)	A	-33 1000 PSI (10% F)
10/10/90	Test (Location 2 CL)	A	-47 700 PSI (10% F)
10/10/90	Test (Location 3 CR)	A	-60 >1000 PSI (10% F)
10/10/90	Test (Location 4 BL)	A	-80 700 PSI (10% F)

## NRC Fabrication/Conditioning/Test Form 90-1

Set: 21      Sample: 9016

Comments: page 2

Materials: NZRB Blends; Zinc loadings

Equip Definitions: 0 - Oven; C - Heat/Cooling Chamber; H - Humidity Chamber; A - Adhesion Tester

Date	Action	Equip	Results/Comments
10/10/90	1 hr @ -100 F	C	
10/10/90	8 hrs @ 350 F	0	
10/11/90	18 hrs @ 120 F	H	very humid
10/19/90	65 hrs @ 100 F	H	very humid
10/22/90	24 hrs @ 120/135 F	H	very humid
11/08/90	89 hrs @ 140 F	H	very humid
11/26/90	1 hr @ 450 F	C	
11/26/90	4 hrs @ 600 F	0	
11/27/90	6 hrs @ 600 F	0	
11/27/90	40 hrs @ 140 F	H	very humid
11/29/90	4.5 hrs @ 550 F	0	
11/29/90	20 hrs @ 140 F	H	very humid

## NRC Fabrication/Conditioning/Test Form 90-1

Set: 21      Sample: 9016      Comments: page 3

Materials: MZRB Blends; Zinc loadings

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/03/90	Test (Location 5 TR)	A	>1050 PSI
12/03/90	Test (Location 6 CL)	A	>1050 PSI
12/03/90	Test (Location 7 CR)	A	1050 PSI (50% C; 50% F)
12/03/90	Test (Location 8 BL)	A	1000 PSI (50% C; 50% F)
12/04/90	3 hrs @ 550 F	0	
12/04/90	15 hrs @ 120-160 F	H	dry
12/05/90	1 hr @ -100 F	C	
12/05/90	1 hr @ 600 F	C	auto
12/05/90	16 hrs @ 120 F	H	
12/06/90	1 hr @ -110 F	C	auto
12/06/90	3 hrs @ 560 F	0	
12/07/90	5 hrs @ 560 F	0	
12/08/90	1 hr @ -110 F	C	auto

## WZC Fabrication/Conditioning/Test Form 90-1

Set: 21      Sample: 9016      Comments: page 4

Materials: WZRB Blends; Zinc loadings

Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/10/90	1 hr @ -110 F	C	auto
12/10/90	3 hrs @ 570 F	O	
12/11/90	1 hr @ -110 F	C	auto
12/11/90	3 hrs @ 570 F	O	
12/12/90	3 hrs @ 580 F	O	removed at 225 F end before ambient
12/12/90	1 hr @ -110 F	C	removed at 20 F autocycle close to end
12/12/90	18 hrs @ 140 F	H	very humid
12/13/90	5 hrs @ 580 F	O	
12/15/90	30 hrs @ 115-140	H	dry
12/15/90	15 hrs @ 120 F	H	humid
12/17/90	3 hrs @ 560 F	O	
12/17/90	32 hrs @ 140 F	H	very humid
12/17/90	12 hrs @ 120 F	H	very humid
12/19/90	3 hrs @ 560 F	O	

**NRC Fabrication/Conditioning/Test Form 90-1****Set: 21      Sample: 9016****Comments: page 5****Materials: MZRB Blends; Zinc loadings****Equip Definitions:** O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/19/90	1 hr @ -110	C	auto
12/28/90	Test (Location 9 BMR)	A	400 PSI (90% C/I; 10% F) highest filler
12/28/90	Test (Location 10)	A	200 PSI (50% F; 50% C/I) high filler
	STOP TESTING		

**MRC Fabrication/Conditioning/Test Form 90-1****Set: 21      Sample: 9017      Comments:****Materials: MARB-blend; MARB-15; MARB-33; MARB-47****Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesive Tester**

Date	Action	Equip	Results/Comments
10/04/90	Remove mill scale	-	HCl acid clean both sides
10/04/90	15 hrs @ 120/160 F	H	Light rusting
10/05/90	Clean	-	Consultant gel XIX-01 (5 min)/ Rinse
10/05/90	Coat	-	Brush coat 1 layer
			Let dry 15 minutes between coats
	Coat	-	Brush 2nd coat
10/06/90	Cure 1 hr @ 487 F	0	slow to temperature
10/08/90	1 hr @ -100 F	C	1/2 soaked to center (scratched)
10/08/90	1 hr @ 600 F	C	autocycle o cracking in blend
10/08/90	20 hrs @ 120 F	H	Very humid o Failing on non-soaked side
10/09/90	1 hr @ -100 F	C	o Rusting at cracks, & exposed interface
10/10/90	Test (Location 1 TR)	A	>1000 PSI no failure and under blend      Dolly knocked off
10/10/90	Test (Location 2 CL)	A	>1000 PSI no failure

## MRC Fabrication/Conditioning/Test Form 90-1

Set: 21      Sample: 9017

Comments: page 2

## Materials: MARB variations

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
10/10/90	Test (Location 3 CR)	A	>1000 PSI no failure
10/10/90	Test (Location 4 BL)	A	>1000 PSI no failure
10/10/90	1 hr @ -100 F	C	
10/10/90	8 hrs @ 350 F	0	
10/11/90	18 hrs @ 120 F	H	very humid
10/19/90	65 hrs @ 100 F	H	very humid
10/22/90	24 hrs @ 120/135 F	H	very humid
11/08/90	89 hrs @ 140 F	H	very humid
11/26/90	1 hr @ 450 F	C	
11/26/90	4 hrs @ 600 F	0	
11/27/90	6 hrs @ 600 F	0	
11/27/90	40 hrs @ 140 F	H	very humid
11/29/90	4.5 hrs @ 550 F	0	
11/29/90	20 hrs @ 140 F	H	very humid

## MRC Fabrication/Conditioning/Test Form 90-1

Set: 21      Sample: 9017

Comments: page 3

Materials: MARB Blend; Aluminum filler loadings

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/03/90	Test (Location 5 TL)	A	>1000 PSI resin blend
12/03/90	Test (Location 6 CR)	A	>1050 PSI MARB-15
12/03/90	Test (Location 7 CL)	A	>1000 PSI MARB-33
12/03/90	Test (Location 8 BR)	A	900 PSI (90% C/I; 10% dolly)
12/04/90	3 hrs @ 550 F	0	
12/04/90	15 hrs @ 120-160 F	H	dry
12/05/90	1 hr @ -100 F	C	
12/05/90	1 hr @ 600 F	C	auto
12/05/90	16 hrs @ 120 F	H	
12/06/90	1 hr @ -110 F	C	auto
12/06/90	3 hrs @ 560 F	0	
12/07/90	5 hrs @ 560 F	0	
12/08/90	1 hr @ -110 F	C	auto

## NRC Fabrication/Conditioning/Test Form 90-1

Set: 21      Sample: 9017

Comments: page 4

## Materials: Aluminum loadings

Equip Definitions: 0 = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/10/90	1 hr @ -110 F	C	auto
12/10/90	3 hrs @ 570 F	0	
12/11/90	1 hr @ -110 F	C	auto
12/11/90	3 hrs @ 570 F	0	
12/12/90	3 hrs @ 580 F	0	removed at 225 F end before ambient
12/12/90	1 hr @ -110 F	C	removed at 20 F autocycle close to end
12/12/90	18 hrs @ 140 F	H	very humid
12/13/90	5 hrs @ 580 F	0	
12/15/90	30 hrs @ 115-140	H	dry
12/15/90	15 hrs @ 120 F	H	humid
12/17/90	3 hrs @ 560 F	0	
12/17/90	32 hrs @ 140 F	H	very humid
12/17/90	12 hrs @ 120 F	H	very humid
12/19/90	3 hrs @ 560 F	0	

## HRC Fabrication/Conditioning/Test Form 90-1

Set: 21      Sample: 9017

Comments: page 5

Materials: Aluminum loadings

Equip Definitions: O = Oven; C = Heat/Cooling Chamber; H = Humidity Chamber; A = Adhesion Tester

Date	Action	Equip	Results/Comments
12/19/90	1 hr @ -110	C	auto
12/28/90	Test (Location 9 TMR)	A	>1000 PSI (90% F; 10 % dolly) low filler
12/28/90	Test (Location 10 LML)	A	650 PSI (90% F; 10% C/I) highest filler
			STOP TESTING Conclusions drawn

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 22P - 9100      Comments:

Substrate/Preparation: 516/ light rusting

Materials: MARB-DC45; Blends; MARB-45; MZRB-50

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
H = Humidity Chamber; A = Adhesion

I	3	5	9
-----			
2	10	4	6

Date	Action	Equip	Results/Comments
12/14/90	HCL clean	-	Mill scale removed both sides
01/14/91	Clean	-	Gel clean 15 minutes
01/14/91	Coat panel	-	Brush coat MARB-DC-47;blends;MARB-47;MZRB
01/14/91	1 hr @ 487 F	O	Cure
01/15/91	1 hr @ -110 F	C	cold autocycle
01/15/91	1 hr @ 600 F	C	hot autocycle
01/15/91	16 hrs @ 118 F	H	Humid (MZRB has 100% mudcracking)
01/16/91	1/2 hr @ -95 F	C	Low liquid N <sub>2</sub> (MARB-DC-X1-0409 cracks)
01/16/91	20 hrs @ 120 F	H	very humid
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	1000 PSI (90% F; 8% dolly; 2% C)
01/26/91	Test (Location 2)	A	800 PSI (75% F; 20% C; 5% dolly)

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 22P - 9100    Comments:

Materials: see page 1

Equip Definitions: See Page 1



Date	Action	Equip	Results/Comments
01/30/91	1 hr @ -110 F	C	cold
01/30/91	41 hrs @ 115 F	H	very humid
02/01/91	1 hr @ -110 F	C	autocycle
02/01/91	1 hr @ 600 F	C	autocycle hot
02/04/91	2.5 hrs @ 600 F	O	dry heat
02/04/91	42 hrs @ 115-150 F	H	very humid
02/06/91	2.5 hrs @ 58 F	O	
02/07/91	3 hrs @ 590 F	O	
02/08/91	1 hr @ -100 F	C	autocycle
02/09/91	1 hr @ -100 F	C	autocycle
02/11/91	1 hr @ -100 F	C	autocycle
02/11/91	2 hrs @ 620 F	O	dry heat
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	autocycle
02/12/91	2 hrs @ 600 F	O	
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 22P - 9100      Comments:

Substrate/Preparation: 516/ light rusting

Materials: MARB-DC45; Blends; MARB-45; MZRB-50

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
H = Humidity Chamber; A = Adhesion

1	3	5	9
2	10	4	6

Date	Action	Equip	Results/Comments
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 3)	A	500 PSI (100% C)
02/18/91	Test (Location 4)	A	700 PSI (50% C, 50% F)
02/22/91	2 hrs @ 590 F	O	
02/22/91	19 hrs @ 115 F	H	
02/25/91	2 hr @ 600 F	O	
02/25/91	1 hr @ -100 F	C	autocycle
02/27/91	1 hr @ -100 F	C	autocycle
02/27/91	2 hrs @ 350 F	O	
02/28/91	1 hr @ -100 F	C	auto
02/28/91	2 hrs @ 600 F	O	
02/28/91	18 hrs @ 115 F	H	humid
03/04/91	Test (Location 5)	A	550 PSI (100% C)
03/04/91	Test (Location 6)	A	600 PSI (50% C; 50% F)
03/04/91	1 hr @ 487 F	O	
03/04/91	1 hr @ -100 F	C	
03/05/91	1 hr @ -100 F	H	
03/05/91	1 hr @ 600 F	O	
03/05/91	16.5 hrs @ 116 F	H	
03/08/91	1 hr @ -100 F	C	
03/08/91	2 hrs @ 600 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 4

**Set-Sample:** 22P - 9100    **Comments:****Substrate/Preparation:** 516/ light rusting

1	3	5	9
-----			
2	10	4	6
-----			

**Materials:** MARB-DC45; Blends; MARB-45; MZRB-50**Equip Definitions:** O = Oven; C = Heat/Cooling Chamber;  
H = Humidity Chamber; A = Adhesion

Date	Action	Equip	Results/Comments
03/08/91	64 hrs @ 140 F	H	very humid
03/11/91	1 hr @ -100 F	C	
03/11/91	2 hrs @ 600 F	O	
03/11/91	17 hrs @ 115 F	H	
03/12/91	1 hr @ -100 F	C	
03/12/91	1 hr @ 480 F	O	
03/12/91	16 hrs @ 115 F	H	
03/14/91	Test (Location 7)	A	400 PSI (80% C/I; 18% C; 2% F, dolly)
03/14/91	Test (Location 8)	A	700 PSI (10% C; 40% F; 50% dolly)
03/19/91	3 hrs @ 610 F	O	
03/28/91	Test (Location 9)	A	400 PSI (100% C)
03/28/91	Test (Location 10)	A	825 PSI (20% C/I; 50% F; 30% dolly)

## MRC Fabrication "Conditioning/Test Form 91-1

Page 1

Set-Sample: 22 - 9101 Comments:

Substrate/Preparation: 285/ light rusting

Materials: MARB-45 Dilute

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
H = Humidity Chamber;  
A = Adhesion Tester; T = Misc Tests

1

Date	Action	Equip	Results/Comments
12/14/90	HCL clean	-	Mill scale removed both sides
01/15/91	Clean	-	Gel clean 15 minutes
01/16/91	Coat panel	-	Spray coat 3 layers of MARB-45 dilute
01/17/91	1 hr @ 487 F	O	Cure slow to temperature
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	550 PSI (100% C) Testing stopped
			Some coating failure - Ambient control, compare with 9102 or 9103

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 22 - 9102 Comments:

Substrate/Preparation: 516/ light rusting

Materials: MARB-45 dilute

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
 H = Humidity Chamber;  
 A = Adhesion Tester; T = Misc Tests

1

Date	Action	Equip	Results/Comments
12/14/90	HCL clean	-	Mill scale removed both sides
01/15/91	Clean	-	Gel clean 15 minutes
01/16/91	Coat panel	-	Spray coat 3 layers of MARB-45 dilute
01/17/91	1 hr @ 487 F	O	Cure slow to temperature
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	600 PSI (100% C)
01/30/91	1 hr @ -110 F	C	cold
01/30/91	41 hrs @ 115 F	H	very humid
02/01/91	1 hr @ -110 F	C	autocycle
02/01/91	1 hr @ 600 F	C	autocycle
02/04/91	2.5 hrs @ 600 F	O	dry, heat

**MRC Fabrication/Conditioning/Test Form 91-1**

Page 2

**Set-Sample: 22 - 9102      Comments:**

### **Materials: MARB-45**

**Equip Definitions:** See Page 1

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 22 - 9103 Comments:

Substrate/Preparation: 203/ light rusting

Materials: MARB-45 dilute

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
 H = Humidity Chamber;  
 A = Adhesion Tester; T = Misc Tests

1

Date	Action	Equip	Results/Comments
12/14/90	HCL clean	-	Mill scale removed both sides
01/15/91	Clean	-	Gel clean 15 minutes
01/16/91	Coat panel	-	Spray coat 3 layers of MARB-45 dilute
01/17/91	1 hr @ 487 F	O	Cure slow to temperature
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	500 PSI (15% C/I; 70% C; 15% dolly)
01/30/91	1 hr @ -110 F	C	cold
01/30/91	41 hrs @ 115 F	H	very humid
02/01/91	1 hr @ -110 F	C	autocycle
02/01/91	1 hr @ 600 F	C	autocycle
02/04/91	2.5 hrs @ 600 F	O	dry heat

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 22 - 9103 Comments:

Materials: MARB-45

Equip Definitions: See Page 1



---

---

Date Action Equip Results/Comments

02/04/91 42 hrs @ 115-150 F H very humid

STOP TESTING - poor coating, too dilute; failure at thin spots

---

---

---

---

---

---

---

---

---

---

---

---

---

---

---

---

---

---

---

---

---

---

---

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 22P - 9200      Comments:

Substrate/Preparation: 516/ light rusting

Materials: MARB-40; MARB-DC-40

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
H = Humidity Chamber; A = Adhesion

	3
1	
2	4

Date	Action	Equip	Results/Comments
12/14/90	HCL clean	-	Mill scale removed both sides
01/14/91	Clean	-	Gel clean 15 minutes
01/14/91	Coat panel	-	Brush coat MARB-40; MARB-DC-47
01/14/91	1 hr @ 487 F	O	Cure
01/15/91	1 hr @ -110 F	C	cold autocycle
01/15/91	1 hr @ 600 F	C	hot autocycle
01/15/91	16 hrs @ 118 F	H	Humid
01/16/91	1/2 hr @ -95 F	C	Low liquid N <sub>2</sub>
01/16/91	20 hrs @ 120 F	H	very humid
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	1000 PSI (40% C; 40% F; 20% dolly)
01/26/91	Test (Location 2)	A	1000 PSI (50% C; 40% F; 10% dolly)

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 22P - 9200      Comments:

Materials: see page 1

Equip Definitions: See Page 1

Date	Action	Equip	Results/Comments
01/30/91	1 hr @ -110 F	C	cold
01/30/91	41 hrs @ 115 F	H	very humid
02/01/91	1 hr @ -110 F	C	autocycle
02/01/91	1 hr @ 600 F	C	autocycle hot
02/04/91	2.5 hrs @ 600 F	O	dry heat
02/04/91	42 hrs @ 115-150 F	H	very humid
02/06/91	2.5 hrs @ 58 F	O	
02/07/91	3 hrs @ 590 F	O	
02/08/91	1 hr @ -100 F	C	autocycle
02/09/91	1 hr @ -100 F	C	autocycle
02/11/91	1 hr @ -100 F	C	autocycle
02/11/91	2 hrs @ 620 F	O	dry heat
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	autocycle
02/12/91	2 hrs @ 600 F	O	
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 22P - 9200      Comments:

Materials: see page 1

Equip Definitions: See Page 1

	5
1	3
2	6 4

Date	Action	Equip	Results/Comments
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 3)	A	150 PSI (100% C)
02/18/91	Test (Location 4)	A	100 PSI (100% C)
02/22/91	2 hrs @ 590 F	O	
02/22/91	19 hrs @ 115 F	H	
02/25/91	2 hrs @ 600 F	O	
02/25/91	1 hr @ -100 F	C	
02/27/91	1 hr @ -100 F	C	
02/27/91	2 hrs @ 350 F	O	
02/28/91	1 hr @ -100 F	C	
02/28/91	2 hrs @ 600 F	O	
02/28/91	18 hrs @ 115 F	H	
03/04/91	Test (Location 5)	A	700 PSI (100% C)
03/04/91	Test (Location 6)	A	750 PSI (100% C)

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 22R - 9201    Comments: Repair test on panel 8701

Substrate/Preparation: 516/ remove loose MARB

Materials: MARB-45 dilute

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
 H = Humidity Chamber;  
 A = Adhesion Tester; T = Misc Tests

1

Date	Action	Equip	Results/Comments
	Formerly Panel 8701 (See form 90-1)		Gel clean and tape remove loose MARB
01/15/91	Clean	-	Gel clean 15 minutes
01/16/91	Coat panel	-	Spray coat 3 layers of MARB-45
01/17/91	1 hr @ 487 F	O	Cure slow to temperature
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	300 PSI (60% C/I; 30% C; 10 % A rusty)
<b>STOP TESTING</b>			
03/05/91	coating completely removed with 3M sander stripper		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 22R - 9202    Comments: Repair test on panel 8702

Substrate/Preparation: 516/ remove loose MARB

Materials: MARB-45 dilute

I

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;

Date	Action	Equip	Results/Comments
	Formerly Panel 8702 (See form 90-1)		Gel clean and tape remove loose MARB
01/15/91	Clean	-	Gel clean 15 minutes
01/16/91	Coat panel	-	Spray coat 3 layers of MARB-45
01/17/91	1 hr @ 487 F	O	Cure slow to temperature
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	200 PSI (50% C/I; 50% C alum)
01/30/91	1 hr @ -110 F	C	cold
01/30/91	41 hrs @ 115 F	H	very humid
02/01/91	1 hr @ -110 F	C	autocycle cold
02/01/91	1 hr @ 600 F	C	autocycle hot
02/04/91	2.5 hrs @ 600 F	O	dry heat STOP TESTING - FAILURE
03/05/91	Coating completely removed in 1 minute with 3M sander stripper		


## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 22R - 9203 Comments: Repair test on panel 8603

Substrate/Preparation: 516/ remove loose MARB

Materials: MARB-45 dilute



Equip Definitions: O = Oven; C = Heat/Cooling Chamber;

Date	Action	Equip	Results/Comments
Formerly Panel 8603 (See form 90-1)			Gel clean and tape remove loose MARB
01/15/91	Clean	-	Gel clean 15 minutes
01/16/91	Coat panel	-	Spray coat 3 layers of MARB-45
01/17/91	1 hr @ 487 F	O	Cure slow to temperature
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	100 PSI (100% C/I grey - 1/2% F)
01/30/91	1 hr @ -110 F	C	cold
01/30/91	41 hrs @ 115 F	H	very humid
02/01/91	1 hr @ -110 F	C	autocycle cold
02/01/91	1 hr @ 600 F	C	autocycle hot
02/04/91	2.5 hrs @ 600 F	O	dry heat STOP TESTING - FAILURE
03/05/91	Coating completely removed in 1 minute with 3M sander stripper		


## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set/Sample: 22P - 9300      Comments:

Substrate/Preparation: 516/ light rusting

Materials: MARB-DC-40

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
H = Humidity Chamber; A = Adhesion

Date	Action	Equip	Results/Comments
12/14/90	HCL clean	-	Mill scale removed both sides
01/14/91	Clean	-	Gel clean 15 minutes
01/14/91	Coat panel	-	Brush coat MARB-DC-40
01/14/91	1 hr @ 487 F	O	Cure
01/15/91	1 hr @ -110 F	C	cold autocycle
01/15/91	1 hr @ 600 F	C	hot autocycle
01/15/91	16 hrs @ 118 F	H	Humid
01/16/91	1/2 hr @ -95 F	C	Low liquid N <sub>2</sub>
01/16/91	20 hrs @ 120 F	H	very humid
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	1000 PSI (10% C; 80% F; 10% dolly)

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 22P - 9300      Comments: 

Materials: see page 1

Equip Definitions: See Page 1

Date	Action	Equip	Results/Comments
01/30/91	1 hr @ -110 F	C	cold
01/30/91	41 hrs @ 115 F	H	very humid
02/01/91	1 hr @ -110 F	C	autocycle
02/01/91	1 hr @ 600 F	C	autocycle hot
02/04/91	2.5 hrs @ 600 F	O	dry heat
02/04/91	42 hrs @ 115-150 F	H	very humid
02/06/91	2.5 hrs @ 58 F	O	
02/07/91	3 hrs @ 590 F	O	
02/08/91	1 hr @ -100 F	C	autocycle
02/09/91	1 hr @ -100 F	C	autocycle
02/11/91	1 hr @ -100 F	C	autocycle
02/11/91	2 hrs @ 620 F	O	dry heat
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	autocycle
02/12/91	2 hrs @ 600 F	O	
02/12/91	15 hrs @ 118 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 22P - 9300      Comments:

Materials: see page 1

Equip Definitions: See Page 1

3 2

1

Date	Action	Equip	Results/Comments
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 2)	A	>1000 PSI (no failure)
02/22/91	2 hrs @ 590 F	O	
02/22/91	19 hrs @ 115 F	H	
02/25/91	2 hrs @ 600 F	O	
02/25/91	1 hr @ -100 F	C	
02/27/91	1 hr @ -100 F	C	
02/27/91	2 hrs @ 350 F	O	
02/28/91	1 hr @ -100 F	C	
02/28/91	2 hrs @ 600 F	O	
02/28/91	18 hrs @ 115 F	H	
03/04/91	Test (Location 3)	A	600 PSI (80% C; 20% F)
03/04/91	1 hr @ 487 F	O	
03/04/91	1 hr @ -100 F	C	
03/05/91	1 hr @ -100 F	C	
03/05/91	1 hr @ 600 F	O	
03/05/91	16.5 hrs @ 116 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1


Page 1

Set-Sample: 23 - 9301 Comments:

Substrate/Preparation: 285/ light rusting

Materials: MARB-DC-40

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
 H = Humidity Chamber;  
 A = Adhesion Tester; T = Misc Tests



Date	Action	Equip	Results/Comments
12/14/90	HCL clean	-	Mill scale removed both sides
01/15/91	Clean	-	Gel clean 15 minutes
01/16/91	Coat panel	-	Spray coat 3 layers of MARB-DC-40
01/17/91	1 hr @ 487 F	O	Cure slow to temperature
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	1000 PSI (10% C; 70% F; 20% dolly)
	STOP TESTING - Control ambient panel for 9302-9303 Looks spotty		
02/25/91	one of two panels to CDN for HB salt-spray environment testing		

## MRC Fabrication/Conditioning/Test Form 91-1


Page 1

Set-Sample: 23 - 9302 Comments:

Substrate/Preparation: 516/ light rusting

Materials: MARB-DC-40

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
 H = Humidity Chamber;  
 A = Adhesion Tester; T = Misc Tests



Date	Action	Equip	Results/Comments
12/14/90	HCL clean	-	Mill scale removed both sides
01/15/91	Clean	-	Gel clean 15 minutes
01/16/91	Coat panel	-	Spray coat 3 layers of MARB-DC-40
01/17/91	1 hr @ 487 F	O	Cure slow to temperature
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	1000 PSI (50% C; 50% F; 6% dolly)
01/30/91	1 hr @ -110 F	C	autocycle
01/30/91	41 hrs @ 115 F	H	very humid
02/01/91	1 hr @ -110 F	C	autocycle
02/01/91	1 hr @ 600 F	C	autocycle
02/04/91	2.5 hrs @ 600 F	O	dry heat

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 23 - 9302      Comments: Repair test

Materials: MARB-DC-40

Equip Definitions: See Page 1

2

1

Date	Action	Equip	Results/Comments
02/04/91	42 hrs @ 115-150 F	H	very humid
02/06/91	2.5 hrs @ 58 F	O	
02/07/91	3 hrs @ 590 F	O	
02/08/91	1 hr @ -100 F	C	autocycle
02/09/91	1 hr @ -100 F	C	autocycle
02/11/91	1 hr @ -100 F	C	autocycle
02/11/91	2 hrs @ 620 F	O	dry heat
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	autocycle
02/12/91	2 hrs @ 600 F	O	
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 2)	A	100 PSI (90% C, 10% F)
02/19/91	STOP TESTING		poor results
03/05/91	Coating completely removed in 1 minute with 3M sander stripper		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 23 - 9303 Comments:

Substrate/Preparation: 203/ light rusting

Materials: MARB-DC-40

Equip Definitions: O = Oven; C = Heat/Cooling Chamber;  
 H = Humidity Chamber;  
 A = Adhesion Tester; T = Misc Tests

2
1

Date	Action	Equip	Results/Comments
12/14/90	HCL clean	-	Mill scale removed both sides
01/15/91	Clean	-	Gel clean 15 minutes
01/16/91	Coat panel	-	Spray coat 3 layers of MARB-DC-40
01/17/91	1 hr @ 487 F	O	Cure slow to temperature
01/17/91	15 hrs @ 120 F	H	very humid
01/18/91	28 hrs @ 120 F	H	dry
01/19/91	1 hr @ -110 F	C	autocycle cold
01/19/91	1 hr @ 580 F	O	hot
01/21/91	1 hr @ -100 F	C	cold
01/21/91	2 hrs @ 600 F	O	hot
01/22/91	2 hrs @ 610 F	O	hot
01/22/91	1 hr @ -110 F	C	cold
01/22/91	16 hrs @ 115 F	H	humid
01/23/91	1 hr @ -110 F	C	cold
01/26/91	Test (Location 1)	A	1000 PSI (70% C; 20% F; 10% dolly)
01/30/91	1 hr @ -110 F	C	cold
01/30/91	41 hrs @ 115 F	H	very humid
02/01/91	1 hr @ -110 F	C	autocycle
02/01/91	1 hr @ 600 F	C	autocycle
02/04/91	2.5 hrs @ 600 F	O	dry heat

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 23 - 9303    Comments: Repair test

Materials: MARB-DC-40

Equip Definitions: See Page 1

2

1

Date	Action	Equip	Results/Comments
02/04/91	42 hrs @ 115-150 F	H	very humid
02/06/91	2.5 hrs @ 58 F	O	
02/07/91	3 hrs @ 590 F	O	
02/08/91	1 hr @ -100 F	C	autocycle
02/09/91	1 hr @ -100 F	C	autocycle
02/11/91	1 hr @ -100 F	C	autocycle
02/11/91	2 hrs @ 620 F	O	dry heat
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	autocycle
02/12/91	2 hrs @ 600 F	O	
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 2)	A	50 PSI (85% C/I, 15% F)
02/19/91	STOP TESTING		dark oxide interface, very poor results
03/05/91	Coating completely removed with 3M sander stripper		
03/08/91	Backside rust cleaned off with HCL		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 24 - 9401 Comments:

Materials: MARB 40 (Oct 30, 1990) Substrate: A-203-E

Equip Definitions:

	1	2
--	---	---

Date	Action	Equip	Results/Comments
10/30/90	Acid cleaned		HCL to remove mill scale
01/20/91	Gel cleaned		Corrosion inhibitor study
01/24/91	Gel cleaned		5 minutes, rinsed, dried
01/24/91	Coat		Spray coat right 33%
01/24/91	Coat		Spray coat right 66%
01/24/91	Cure	0	4 hrs air dry, 1 hr @ 450 F slowly
Hold at ambient			
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----
-----	-----	-----	-----

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 24 - 9403 Comments:

Materials: MARB 40 (Oct 30, 1990) Substrate: A-516-70

	1	2
--	---	---

## Equip Definitions:

Date	Action	Equip	Results/Comments
10/30/90	Acid cleaned		HCL to remove mill scale
01/20/91	Gel cleaned		Corrosion inhibitor study
01/24/91	Gel cleaned		5 minutes, rinsed, dried
01/24/91	Coat		Spray coat right 33%
01/24/91	Coat		Spray coat right 66%
01/24/91	Cure	0	4 hrs air dry, 1 hr @ 450 F slowly
02/25/91	Hold at ambient	Gave to CDN	for HB salt-spray environment testing

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 24 - 9405 Comments:

Materials: MARB 40 (Oct 30, 1990) Substrate: A-285-C

## Equip Definitions:

	1	2

Date	Action	Equip	Results/Comments
10/30/90	Acid cleaned		HCL to remove mill scale
01/20/91	Gel cleaned		Corrosion inhibitor study
01/24/91	Gel cleaned		5 minutes, rinsed, dried
01/24/91	Coat		Spray coat right 33%
01/24/91	Coat		Spray coat right 66%
01/24/91	Cure	0	4 hrs air dry, 1 hr @ 450 F slowly
	Hold at ambient		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 24 - 9402 Comments:

Materials: MARB 40 (Oct 30, 1990) Substrate: A-203-E

Equip Definitions:

	1	2

Date	Action	Equip	Results/Comments
10/30/90	Acid cleaned		HCL to remove mill scale
01/20/91	Gel cleaned		Corrosion inhibitor study
01/24/91	Gel cleaned		5 minutes, rinsed, dried
01/24/91	Coat		Spray coat right 33%
01/24/91	Coat		Spray coat right 66%
01/24/91	Cure	O	4 hrs air dry, 1 hr @ 450 F slowly
01/30/91	1 hr @ -110 F	C	
01/30/91	41 hrs @ 115 F	H	
02/01/91	1 hr @ -110 F	C	autocycle
02/01/91	1 hr @ 600 F	C	autocycle
02/04/91	2.5 hrs @ 600 F	O	dry heat
02/04/91	42 hrs @ 115-150 F	H	very humid
02/06/91	2.5 hrs @ 580 F	O	
02/07/91	3 hrs @ 590 F	O	
02/08/91	1 hr @ -100 F	C	
02/09/91	1 hr @ -100 F	C	
02/11/91	1 hr @ -100 F	C	
02/11/91	2 hrs @ 620 F	O	dry heat
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	
02/12/91	2 hrs @ 600 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 24 - 9402      Comments:

Materials: MARB-40

Substrate: A203-E

	1	2
--	---	---

Equip Definitions:

Date	Action	Equip	Results/Comments
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 1)	A	250 PSI (30% C; 70% C/I)
02/18/91	Test (Location 2)	A	100 PSI (50% C; 50% C/I)
	STOP TESTING		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 24 - 9404 Comments:

Materials: MARB 40 (Oct 30, 1990) Substrate: A-516-70

Equip Definitions:

	1	2
	3	6
	5	4

Date	Action	Equip	Results/Comments
10/30/90	Acid cleaned		HCL to remove mill scale
01/20/91	Gel cleaned		Corrosion inhibitor study
01/24/91	Gel cleaned		5 minutes, rinsed, dried
01/24/91	Coat		Spray coat right 33%
01/24/91	Coat		Spray coat right 66%
01/24/91	Cure	O	4 hrs air dry, 1 hr @ 450 F slowly
01/30/91	1 hr @ -110 F	C	
01/30/91	41 hrs @ 115 F	H	
02/01/91	1 hr @ -110 F	C	autocycle
02/01/91	1 hr @ 600 F	C	autocycle
02/04/91	2.5 hrs @ 600 F	O	dry heat
02/04/91	42 hrs @ 115-150 F	H	very humid
02/06/91	2.5 hrs @ 580 F	O	
02/07/91	3 hrs @ 590 F	O	
02/08/91	1 hr @ -100 F	C	
02/09/91	1 hr @ -100 F	C	
02/11/91	1 hr @ -100 F	C	
02/11/91	2 hrs @ 620 F	O	dry heat
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	
02/12/91	2 hrs @ 600 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 24 - 9404 Comments:

Materials: MARB-40 Substrate: A516-70

Equip Definitions:

	1	2
	3	6
	5	4

Date	Action	Equip	Results/Comments
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 1)	A	150 PSI (50% C; 50% C/I)
02/18/91	Test (Location 2)	A	300 PSI (100% C, C/I)
02/22/91	2 hrs @ 590 F	O	
02/22/91	19 hrs @ 115 F	H	
02/25/91	2 hrs @ 600 F	O	
02/25/91	1 hr @ -100 F	C	
02/27/91	1 hr @ -100 F	C	
02/27/91	2 hrs @ 350 F	O	
02/28/91	1 hr @ -100 F	C	
02/28/91	2 hrs @ 600 F	O	
02/28/91	18 hrs @ 115 F	H	
03/04/91	Test (Location 3)	A	620 PSI (60% C/I; 40% C) 1 coat rusting
03/04/91	Test (Location 4)	A	200 PSI (20% F; 80% C/I)
03/04/91	1 hr @ 487 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 24 - 9404 Comments:

Materials: MARB-40

Substrate: A516-70

	1	2
	3	6
	5	4

Equip Definitions:

Date	Action	Equip	Results/Comments
03/04/91	1 hr @ -100 F	C	
03/05/91	1 hr @ -100 F	C	
03/05/91	1 hr @ 600 F	O	
03/05/91	16.5 hrs @ 116 F	H	
03/08/91	1 hr @ -100 F	C	
03/08/91	2 hrs @ 600 F	O	
03/08/91	64 hrs @ 140 F	H	
03/11/91	1 hr @ -100 F	C	
03/11/91	2 hrs @ 600 F	O	
03/11/91	17 hrs @ 115 F	H	
03/12/91	1 hr @ -100 F	C	
03/12/91	1 hr @ 480 F	O	
03/12/91	16 hrs @ 115 F	H	
03/14/91	Test (Location 5)	A	100 PSI (90% C/I; 5% C; 5% F) 1 coat
03/14/91	Test (Location 6)	A	350 PSI (50% dolly) poor test, low pressure
03/19/91	3 hrs @ 610 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 24 - 9406 Comments:

Materials: MARB 40 (Oct 30, 1990) Substrate: A-285

Equip Definitions:

	1	2
--	---	---

Date	Action	Equip	Results/Comments
10/30/90	Acid cleaned		HCL to remove mill scale
01/20/91	Gel cleaned		Corrosion inhibitor study
01/24/91	Gel cleaned		5 minutes, rinsed, dried
01/24/91	Coat		Spray coat right 33%
01/24/91	Coat		Spray coat right 66%
01/24/91	Cure	O	4 hrs air dry, 1 hr @ 450 F slowly
01/30/91	1 hr @ -110 F	C	
01/30/91	41 hrs @ 115 F	H	
02/01/91	1 hr @ -110 F	C	autocycle
02/01/91	1 hr @ 600 F	C	autocycle
02/04/91	2.5 hrs @ 600 F	O	dry heat
02/04/91	42 hrs @ 115-150 F	H	very humid
02/06/91	2.5 hrs @ 580 F	O	
02/07/91	3 hrs @ 590 F	O	
02/08/91	1 hr @ -100 F	C	
02/09/91	1 hr @ -100 F	C	
02/11/91	1 hr @ -100 F	C	
02/11/91	2 hrs @ 620 F	O	dry heat
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	
02/12/91	2 hrs @ 600 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 24 - 9406 Comments:

Materials: MARB-40

Substrate: A285

	1	2
--	---	---

Equip Definitions:

Date	Action	Equip	Results/Comments
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 1)	A	100 PSI (95% C/I; 5% C)
02/18/91	Test (Location 2)	A	150 PSI (48% C; 50% C/I; 2% F)

STOP TESTING

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25A - 9507      Comments:

Materials: Silicone Release DC-1-2531

Equip Definitions:

	5
	2
	6
as	4
is	3 1

Date	Action	Equip	Results/Comments
01/31/91	Acid cleaned		HCL both sides
01/31/91	Gel cleaned		
02/08/91	Gel cleaned		
02/08/91	Coat		Brush coat top half
02/08/91	Coat		Brush coat left half (top right 2 coats)
02/08/91	Cure	O	air dry, 1 hr @ 400 F
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	
02/12/91	2 hrs @ 600 F	O	
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 1)	A	>1000 PSI (1 coat - no failure)
02/18/91	Test (Location 2)	A	1000 PSI (2 coats - 90% C, 9% F, 1% dolly)
02/22/91	2 hrs @ 590 F	O	
02/22/91	19 hrs @ 115 F	H	
02/25/91	2 hrs @ 600 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25A - 9507 Comments:

Materials: Silicone Release Resin

Equip Definitions:

	5
	2
	6
	4
3	1

Date	Action	Equip	Results/Comments
02/25/91	1 hr @ -100 F	C	
02/27/91	1 hr @ -108 F	C	
02/27/91	2 hrs @ 350 F	O	
02/28/91	1 hr @ -100 F	C	
02/28/91	2 hrs @ 600 F	O	
02/28/91	18 hrs @ 115 F	H	
03/04/91	Test (Location 3)	A	>1000 PSI But looks rusty underneath
03/04/91	1 hr @ 487 F	O	
03/04/91	1 hr @ -100 F	C	
03/05/91	1 hr @ -100 F	C	
03/05/91	1 hr @ 600 F	O	
03/05/91	16.5 hrs @ 116 F	H	
03/08/91	1 hr @ -100 F	C	cold auto
03/08/91	2 hrs @ 600 F	O	
03/08/91	64 hrs @ 140 F	H	
03/11/91	1 hr @ -100 F	C	
03/11/91	2 hrs @ 600 F	O	
03/11/91	17 hrs @ 115 F	H	
03/12/91	1 hr @ -100 F	C	
03/12/91	1 hr @ 487 F	O	
03/12/91	16 hrs @ 115 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 25A - 9507      Comments: Silicone Release

03/14/91	Test (Location 4)	A	1000 PSI (60% F; 40% dolly)	1 coat
03/14/91	Test (Location 5)	A	>1000 PSI	2 coats
03/19/91	3 hrs @ 610 F	O		
03/19/91	17 hrs @ 116 F	H		
03/20/91	3 hrs @ 650 F	O		
03/20/91	1 hr @ -100 F	C		
03/20/91	16 hrs @ 140 F	H		
03/21/91	1 hr @ -100 F	C		
03/21/91	1 hr @ 640 F	O		
03/21/91	16 hrs @ 140 F	H		
03/22/91	1 hr @ -100 F	C		
03/22/91	1 hr @ 640 F	O		
03/22/91	1 hr @ -100 F	C		
03/22/91	43 hrs @ 115 F	H		
03/24/91	1 hr @ -100 F	C	46 events (350 hours)	
03/28/91	Test (Location 6)	A	650 PSI (50% C/I; 50% F /dolly)	

STOP TESTING - 100% Rusting Add Zinc or Aluminum in 9508 paint

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25A -9508      Comments:

Materials: A516-70 panel  
 Silicone Release      As is  
                           Aluminum filled

Equip Definitions:

7777	0
1 3	
2 4	

Date	Action	Equip	Results/Comments
03/14/91			
03/19/91	3 hrs @ 610 F	O	
03/19/91	17 hrs @ 116 F	H	
03/20/91	3 hrs @ 650 F	O	
03/20/91	1 hr @ -100 F	C	
03/20/91	16 hrs @ 140 F	H	
03/21/91	1 hr @ -100 F	C	
03/21/91	1 hr @ 640 F	O	
03/21/91	16 hrs @ 140 F	H	
03/22/91	1 hr @ -100 F	C AM	
03/22/91	1 hr @ 640 F	O	
03/22/91	1 hr @ -100 F	C PM	
03/22/91	43 hrs @ 115 F	H	
03/24/91	1 hr @ -100 F	C	
03/25/91	1 hr @ -100 F	C	
03/25/91	17 hrs @ 140 F	H	
03/25/91	1 hr @ 0 F	C	
03/26/91	1 hr @ 700 F	O	Very hot
03/27/91	2 hrs @ 650 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 25A - 9508      Comments: Silicone Release with aluminum / upper  
with zinc (grey)/ lower

03/27/91	1 hr @ -100 F	C
03/28/91	1 hr @ -100 F	C
03/28/91	2 hrs @ 650 F	O
03/29/91	Test (Location 1)	A      800 PSI (50% C, 15% A, 20% F)      0.5 mils
03/29/91	Test (Location 2)	A      600 PSI (80% C/I, 20 % F)      0.55 mils
03/29/91	20 hrs @ 120 F	H
03/30/91	1 hr @ -100 F	C
03/30/91	44 hrs @ 118 F	H
04/01/91	1 hr @ -100 F	C
04/01/91	2 hrs @ 650 F	O
04/01/91	20 hrs @ 120 F	H
04/02/91	1 hr @ -100 F	C
04/02/91	17 hrs @ 120 F	H
04/03/91	1 hr @ -100 F	C
04/03/91	17 hrs @ 120 F	H
04/04/91	1 hr @ -150 F	C
04/04/91	2 hrs @ 650 F	O
04/04/91	20 hrs @ 120 F	H
04/05/91	1 hr @ -100 F	C
04/05/91	1 hr @ 650 F	O
04/06/91	Test (Location 3)	A      >1000 PSI
04/06/91	Test (Location 4)	A      550 PSI (90% C; 10% F)
04/08/91	2 hrs @ 650 F	O
04/08/91	1 hr @ -100 F	C

**MRC Fabrication/Conditioning/Test Form 91-1**

Page 3

**04/08/91 40 hrs @ 120 F H**

04/10/91 1 hr @ -100 F C

04/10/91 2 hrs @ 650 F

04/11/91 4 hrs @ 650 E

04/11/81 14 hrs 0 150 E H

04/13/81 1 hr & 100 E 6

-----  
24/3/21 65 hrs 8.120 E

24/15/21 1 hr 2 102 5

2015 RELEASE UNDER E.O. 14176

2017-126-1-1-2-102-F

-----

-----  
-----

04/17/31 14 m/s & 115°

84/18/91 1 M

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25 - 15 panels Comments: 9510-9524

Materials: Corrosion Inhibitor variation

Equip Definitions:

Date	Action	Equip	Results/Comments
02/10/91	Clean		All panels HCL cleaned of mill scale
02/20/91	Clean		Gel (0291) clean 15 minutes
02/20/91	Rinse		Tap water, do not dry
02/20/91	Rinse		Corrosion inhibitor final rinse, hang
02/21/91	Report		Observations on Test plan sheet
02/21/91	Select -		9510; 9511; 9512; 9514; 9517; 9518; 9520; 9521; & 9522
02/21/91	Reject -		
	9513 SH3 Sharp	1 to 300 Blast	Rust, film, discoloration
	9515 N2 K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	1 to 1 (1/2)	"
	9516 H1 HN-(C <sub>2</sub> H <sub>5</sub> OH) <sub>2</sub>	1 to 0 Normal	"
	9519 E2 NaNO <sub>3</sub> Ed's	1 to 20 Normal	"
	9523 B3 NaNO <sub>3</sub> Brulin	1 to 30 (1/2)	"
	9524 B4 NaNO <sub>3</sub> Brulin	1 to 3.5 (4X)	"
02/21/91	Coat selected panels - See individual sheets.		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25 - 9510 Comments: Control S4

Materials: MARB 4 (as cleaned, force air dried A516-70)

Equip Definitions:

4	0	2
		3
		1

Date	Action	Equip	Results/Comments
02/10/91	Clean		Panel HCL cleaned of mill scale
02/20/91	Clean		Gel (0291) clean 15 minutes
02/20/91	Rinse		Tap water, do not dry
02/20/91	Rinse		Tap water, force air dry, hang on hook
02/21/91	Report		Observations on Test plan sheet - No rusting
02/21/91	Coat		Spray three coats MARB 4
02/21/91	1 hr @ 480 F	O	Cure
02/22/91	2 hrs @ 590 F	O	dry heat
02/22/91	19 hrs @ 115 F	H	humid
02/25/91	2 hrs @ 600 F	O	dry heat
02/25/91	1 hr @ -100 F	C	auto
02/26/91	Test (Location 1)	A	>1000 PSI
02/27/91	1 hr @ -100 F	C	auto
02/27/91	2 hrs @ 350 F	O	dry
02/28/91	1 hr @ -100 F	C	auto
02/28/91	2 hrs @ 600 F	O	dry, hot
02/28/91	18 hrs @ 115 F	H	
03/04/91	Test (Location 2)	A	1000 PSI (100% C)
03/04/91	1 hr @ 487 F	O	
03/04/91	1 hr @ -100 F	C	
03/05/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 25 - 9510 Comments: S-4

03/05/91	1 hr @ 600 F	O
03/05/91	16.5 hrs @ 116 F	H
03/08/91	1 hr @ -100 F	C
03/08/91	2 hrs @ 600 F	O
03/08/91	64 hrs @ 140 F	H
03/11/91	1 hr @ -100 F	C
03/11/91	2 hrs @ 600 F	O
03/11/91	17 hrs @ 115 F	H
03/12/91	1 hr @ -100 F	C
03/12/91	1 hr @ 487 F	O
03/12/91	16 hrs @ 115 F	H
03/13/91	1 hr @ -100 F	C
03/13/91	2 hrs @ 600 F	O
03/13/91	16 hrs @ 140 F	H
03/14/91	1 hr @ -100 F	C
03/14/91	1 hr @ 525 F	C
03/15/91	Test (Location 3)	A 300 PSI (100% C)
03/19/91	3 hrs @ 610 F	O
03/19/91	17 hrs @ 116 F	H
03/20/91	3 hrs @ 650 F	O
03/20/91	1 hr @ -100 F	C
03/20/91	16 hrs @ 140 F	H
03/21/91	1 hr @ -100 F	C
03/21/91	1 hr @ 640 F	O

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 25 - 9510 Comments: S4

03/21/91	16 hrs @ 140 F	H
03/22/91	1 hr @ -100 F	C
03/22/91	1 hr @ 640 F	O
03/22/91	1 hr @ -100 F	C
03/22/91	43 hrs @ 115 F	H
03/24/91	1 hr @ -100 F	C
03/25/91	1 hr @ -100 F	C
03/25/91	17 hrs @ 140 F	H
03/28/91	Test (Location 4)	A 300 PSI (100% C - very rough failure)
STOP TESTING		


## HRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25 - 9511 Comments: SH1

Materials: MARB 4 over Sharp Rust Inhibitor

Equip Definitions:



Date	Action	Equip	Results/Comments
02/10/91	Clean		Panel HCL cleaned of mill scale
02/20/91	Clean		Gel (0291) clean 15 minutes
02/20/91	Rinse		Tap water, do not dry
02/20/91	Rinse		Corrosion inhibitor final rinse, hang
02/21/91	Report		Observations on Test plan sheet
02/21/91	Coat		Spray three coats MARB 4
02/21/91	1 hr @ 480 F	O	Cure
02/22/91	2 hrs @ 590 F	O	dry heat
02/22/91	19 hrs @ 115 F	H	humid
02/25/91	2 hrs @ 600 F	O	dry heat
02/25/91	1 hr @ -100 F	C	auto
02/26/91	Test (Location 1)	A	>1000 PSI
02/27/91	Test (Location 2)	A	>1000 PSI
02/27/91	1 hr @ -100 F	C	auto
02/27/91	2 hrs @ 350 F	O	dry
02/28/91	1 hr @ -100 F	C	auto
02/28/91	2 hrs @ 600 F	O	dry, hot
02/28/91	18 hrs @ 115 F	H	
03/04/91	Test (Location 3)	A	900 PSI (100% C)
03/04/91	1 hr @ 487 F	O	
03/04/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 25 - 9511 Comments: SH-1

03/05/91	1 hr @ -100 F	C
03/05/91	1 hr @ 600 F	O
03/05/91	16.5 hrs @ 116 F	H
03/08/91	1 hr @ -100 F	C
03/08/91	2 hrs @ 600 F	O
03/08/91	64 hrs @ 140 F	H
03/11/91	1 hr @ -100 F	C
03/11/91	2 hrs @ 600 F	O
03/11/91	17 hrs @ 115 F	H
03/12/91	1 hr @ -100 F	C
03/12/91	1 hr @ 487 F	O
03/12/91	16 hrs @ 115 F	H
03/13/91	1 hr @ -100 F	C
03/13/91	2 hrs @ 600 F	O
03/13/91	16 hrs @ 140 F	H
03/14/91	1 hr @ -100 F	C
03/14/91	1 hr @ 525 F	C
03/15/91	Test (Location 4)	A 800 PSI (100% C)
03/19/91	3 hrs @ 610 F	O
03/19/91	17 hrs @ 116 F	H
03/20/91	3 hrs @ 650 F	O
03/20/91	1 hr @ -100 F	C
03/20/91	16 hrs @ 140 F	H
03/21/91	1 hr @ -100 F	C
03/21/91	1 hr @ 640 F	O

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 25 - 9511      Comments: SH-1

03/21/91 16 hrs @ 140 F H  
03/22/91 1 hr @ -100 F C  
03/22/91 1 hr @ 640 F O  
03/22/91 1 hr @ -100 F C  
03/22/91 43 hrs @ 115 F H  
03/24/91 1 hr @ -100 F C  
03/25/91 1 hr @ -100 F C  
03/25/91 17 hrs @ 140 F H  
03/28/91 Test (Location 5) A 250 PSI (100% C)

STOP TESTING

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25 - 9512 Comments: SH2

Materials: MARB 4 over Sharp Rust Inhibitor (normal: 1 to 30)

Equip Definitions:

	0	3
2		1

Date	Action	Equip	Results/Comments
02/10/91	Clean		Panel HCL cleaned of mill scale
02/20/91	Clean		Gel (0291) clean 15 minutes
02/20/91	Rinse		Tap water, do not dry
02/20/91	Rinse		Corrosion inhibitor final rinse, hang
02/21/91	Report		Observations on Test plan sheet
02/21/91	Coat		Spray three coats MARB 4
02/21/91	1 hr @ 480 F	O	Cure
02/22/91	2 hrs @ 590 F	O	dry heat
02/22/91	19 hrs @ 115 F	H	humid
02/25/91	2 hrs @ 600 F	O	dry heat
02/25/91	1 hr @ -100 F	C	auto
02/26/91	Test (Location 1)	A	350 PSI (100% A - I) grey
02/27/91	Test (Location 2)	A	300 PSI (100% C/I) grey
	STOP TESTS		continue with new 9512 (old 9525)
03/13/91	16 hrs @ 140 F	H	
03/14/91	1 hr @ -100 F	C	
03/14/91	1 hr @ 525 F	C	
03/15/91	Test (Location 1)	A	350 PSI (30% C; 20% A; 20% F; 30% dolly)
03/19/91	3 hrs @ 610 F	O	
03/19/91	17 hrs @ 116 F	H	
03/20/91	3 hrs @ 650 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 25 - 9512 Comments: SH2

Materials: MARB 4 over Sharp Rust Inhibitor (normal: 1 to 30)

2	0
2	1

## Equip Definitions:

Date	Action	Equip	Results/Comments
03/20/91	1 hr @ -100 F	C	
03/20/91	16 hrs @ 140 F	H	
03/21/91	1 hr @ -100 F	C	
03/21/91	1 hr @ 640 F	O	
03/21/91	16 hrs @ 140 F	H	
03/22/91	1 hr @ -100 F	C	
03/22/91	1 hr @ 640 F	O	
03/22/91	1 hr @ -100 F	C	PM
03/22/91	43 hrs @ 115 F	H	humid
03/24/91	1 hr @ -100 F	C	
03/25/91	1 hr @ -100 F	C	
03/26/91	Test (Location 2)	A	300 PSI (100% C - C/I and rust)

STOP TESTING

Set-Sample: 26 -9602	Comments:	Page 2
03/22/91 1 hr @ 640 F	O	
03/22/91 1 hr @ -100 F	C PM	
03/22/91 43 hrs @ 115 F	H	
03/24/91 1 hr @ -100 F	C	
03/25/91 1 hr @ -100 F	C	
03/25/91 17 hrs @ 140 F	H very humid	
03/26/91 1 hr @ 0 F	C	
03/26/91 1 hr @ 700 F	O very hot	
03/27/91 2 hrs @ 650 F	O	
03/27/91 1 hr @ -100 F	C	
03/28/91 1 hr @ -100 F	C	
03/28/91 2 hrs @ 650 F	O 50% coating discoloration	
03/29/91 Test (Location 3b)	A 500 PSI (100% C)	1.2 mils
03/29/91 Test (Location 4)	A 300 PSI (100% C/I, C)	1.0 mils
03/29/91 20 hrs @ 120 F	H	
03/30/91 1 hr @ -100 F	C	
03/30/91 44 hrs @ 118 F	H	
04/01/91 1 hr @ -100 F	C	
04/01/91 2 hrs @ 650 F	O	
04/01/91 20 hrs @ 120 F	H	
04/02/91 1 hr @ -100 F	C	
04/02/91 17 hrs @ 120 F	H 1271.0 g	
04/03/91 1 hr @ -100 F	C	
04/03/91 17 hrs @ 120 F	H	
04/04/91 1 hr @ -150 F	C Manual 15 to 8% N <sub>2</sub>	
04/04/91 2 hrs @ 650 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26 - 9602      Comments:

Materials: Sherwin Williams 859S8 Alkyd Silicone

Equip Definitions:

2	o 1 6b
	4
	7
	5
	3b

Date	Action	Equip	Results/Comments
03/06/91	Clean	-	Remove all mill scale with 50% HCL
03/11/91	Clean	-	5 minutes gel, rinse, quick air dry
03/11/91	Coat	S	Spray entire panel
03/12/91	1 hr @ 480 F	O	Bake 1271.05 g
03/12/91	16 hrs @ 115 F	H	Humid
03/13/91	1 hr @ -100 F	C	auto cold
03/13/91	2 hrs @ 600 F	O	hot, dry
03/13/91	16 hrs @ 140 F	H	Humid
03/14/91	1 hr @ -100 F	C	auto
03/14/91	1 hr @ 525 F	C	hot, dry
03/15/91	Test (Location 1)	A	200 PSI (90% A; 10% C)
03/19/91	Test (Location 2)	A	1000 PSI (35% C; 65% C/I/A)
03/19/91	3 hrs @ 610 F	O	1270.8 g
03/19/91	17 hrs @ 116 F	H	
03/20/91	3 hrs @ 650 F	O	
03/20/91	1 hr @ -100 F	C	
03/20/91	16 hrs @ 140 F	H	
03/21/91	1 hr @ -100 F	C	
03/21/91	1 hr @ 640 F	O	
03/21/91	16 hrs @ 140 F	H	
03/22/91	1 hr @ -100 F	C	AM

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25 - 9514 Comments: N1

Materials: MARB 4 over Potassium Chromate ( $K_2Cr_2O_7$ )

Equip Definitions:

5	0	3
2		4
		1

Date	Action	Equip	Results/Comments
02/10/91	Clean		Panel HCL cleaned of mill scale
02/20/91	Clean		Gel (0291) clean 15 minutes
02/20/91	Rinse		Tap water, do not dry
02/20/91	Rinse		Corrosion inhibitor final rinse, hang
02/21/91	Report		Observations on Test plan sheet
02/21/91	Coat		Spray three coats MARB 4
02/21/91	1 hr @ 480 F	O	Cure
02/22/91	2 hrs @ 590 F	O	dry heat
02/22/91	19 hrs @ 115 F	H	humid
02/25/91	2 hrs @ 600 F	O	dry heat
02/25/91	1 hr @ -100 F	C	auto
02/26/91	Test (Location 1)	A	975 PSI (100% C)
02/27/91	Test (Location 2)	A	550 PSI (100% C)
02/27/91	1 hr @ -100 F	C	auto
02/27/91	2 hrs @ 350 F	O	dry
02/28/91	1 hr @ -100 F	C	auto
02/28/91	2 hrs @ 600 F	O	dry, hot
02/28/91	18 hrs @ 115 F	H	
03/04/91	Test (Location 3)	A	300 PSI (100% C) spotty
03/04/91	1 hr @ 487 F	O	
03/04/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 25 - 9514 Comments: N1

03/05/91	1 hr @ -100 F	C
03/05/91	1 hr @ 600 F	O
03/05/91	16.5 hrs @ 116 F	H
03/08/91	1 hr @ -100 F	C
03/08/91	2 hrs @ 600 F	O
03/08/91	64 hrs @ 140 F	H
03/11/91	1 hr @ -100 F	C
03/11/91	2 hrs @ 600 F	O
03/11/91	17 hrs @ 115 F	H
03/12/91	1 hr @ -100 F	C
03/12/91	1 hr @ 487 F	O
03/12/91	16 hrs @ 115 F	H
03/13/91	1 hr @ -100 F	C
03/13/91	2 hrs @ 600 F	O
03/13/91	16 hrs @ 140 F	H
03/14/91	1 hr @ -100 F	C
03/14/91	1 hr @ 525 F	C
03/15/91	Test (Location 4)	A 500 PSI (95% C; 5% F)
03/19/91	3 hrs @ 610 F	O
03/19/91	17 hrs @ 116 F	H
03/20/91	3 hrs @ 650 F	O
03/20/91	1 hr @ -100 F	C
03/20/91	16 hrs @ 140 F	H
03/21/91	1 hr @ -100 F	C
03/21/91	1 hr @ 640 F	O

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 25 - 9514      Comments: N1

03/21/91	16 hrs @ 140 F	H
03/22/91	1 hr @ -100 F	C
03/22/91	1 hr @ 640 F	O
03/22/91	1 hr @ -100 F	C
03/22/91	43 hrs @ 115 F	H
03/24/91	1 hr @ -100 F	C
03/25/91	1 hr @ -100 F	C
03/25/91	17 hrs @ 140 F	H
03/28/91	Test (Location 5)	A      150 PSI (100 % C)

STOP TESTING

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25 - 9517 Comments: H2

Materials: MARB 4 over HN- ( $C_2H_5OH$ )<sub>2</sub>

Equip Definitions:

5	0	3
2		1

Date	Action	Equip	Results/Comments
02/10/91	Clean		Panel HCL cleaned of mill scale
02/20/91	Clean		Gel (0291) clean 15 minutes
02/20/91	Rinse		Tap water, do not dry
02/20/91	Rinse		Corrosion inhibitor final rinse, hang
02/21/91	Report		Observations on Test plan sheet
02/21/91	Coat		Spray three coats MARB 4
02/21/91	1 hr @ 480 F	O	Cure
02/22/91	2 hrs @ 590 F	O	dry heat
02/22/91	19 hrs @ 115 F	H	humid
02/25/91	2 hrs @ 600 F	O	dry heat
02/25/91	1 hr @ -100 F	C	auto
02/26/91	Test (Location 1)	A	>1000 PSI
02/27/91	Test (Location 2)	A	>1000 PSI
02/27/91	1 hr @ -100 F	C	auto
02/27/91	2 hrs @ 350 F	O	dry
02/28/91	1 hr @ -100 F	C	auto
02/28/91	2 hrs @ 600 F	O	dry, hot
02/28/91	18 hrs @ 115 F	H	
03/04/91	Test (Location 3)	A	>1000 PSI
03/04/91	1 hr @ 487 F	O	
03/04/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 25 - 9517 Comments: H-2

03/05/91	1 hr @ -100 F	C
03/05/91	1 hr @ 600 F	O
03/05/91	16.5 hrs @ 116 F	H
03/08/91	1 hr @ -100 F	C
03/08/91	2 hrs @ 600 F	O
03/08/91	64 hrs @ 140 F	H
03/11/91	1 hr @ -100 F	C auto
03/11/91	2 hrs @ 600 F	O
03/11/91	17 hrs @ 115 F	H
03/12/91	1 hr @ -100 F	C
03/12/91	1 hr @ 487 F	O
03/12/91	16 hrs @ 115 F	H
03/13/91	1 hr @ -100 F	C
03/13/91	2 hrs @ 600 F	O
03/13/91	16 hrs @ 140 F	H
03/14/91	1 hr @ -100 F	C
03/14/91	1 hr @ 525 F	C
03/15/91	Test (Location 4)	A 300 PSI (50% C; 50% F)
03/19/91	3 hrs @ 610 F	O
03/19/91	17 hrs @ 116 F	H
03/20/91	3 hrs @ 650 F	O
03/20/91	1 hr @ -100 F	C
03/20/91	16 hrs @ 140 F	H
03/21/91	1 hr @ -100 F	C
03/21/91	1 hr @ 640 F	O

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 25 - 9517 Comments: H2

03/21/91	16 hrs @ 140 F	H
03/22/91	1 hr @ -100 F	C
03/22/91	1 hr @ 640 F	O
03/22/91	1 hr @ -100 F	C
03/22/91	43 hrs @ 115 F	H
03/24/91	1 hr @ -100 F	C
03/25/91	1 hr @ -100 F	C
03/25/91	17 hrs @ 140 F	H
03/28/91	Test (Location 5)	300 PSI (100% C)

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25 - 9518 Comments: E1

Materials: MARB 4 over Sodium Nitrite (1/2 Ed's formulation MB)

Equip Definitions:

	0
2	1

Date	Action	Equip	Results/Comments
02/10/91	Clean		Panel HCL cleaned of mill scale
02/20/91	Clean		Gel (0291) clean 15 minutes
02/20/91	Rinse		Tap water, do not dry
02/20/91	Rinse		Corrosion inhibitor final rinse, hang
02/21/91	Report		Observations on Test plan sheet
02/21/91	Coat		Spray three coats MARB 4
02/21/91	1 hr @ 480 F	O	Cure
02/22/91	2 hrs @ 590 F	O	dry heat
02/22/91	19 hrs @ 115 F	H	humid
02/25/91	2 hrs @ 600 F	O	dry heat
02/25/91	1 hr @ -100 F	C	auto
02/26/91	Test (Location 1)	A	400 PSI (100% A)
02/27/91	Test (Location 2)	A	150 PSI (90% C/I; 10% C)


## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25 - 9520 Comments: E4

Materials: MARB 4 over Sodium Nitrite (Ed's Formulation MB)

Equip Definitions:



Date	Action	Equip	Results/Comments
02/10/91	Clean		Panel HCL cleaned of mill scale
02/20/91	Clean		Gel (0291) clean 15 minutes
02/20/91	Rinse		Tap water, do not dry
02/20/91	Rinse		Corrosion inhibitor final rinse, hang
02/21/91	Report		Observations on Test plan sheet
02/21/91	Coat		Spray three coats MARB 4
02/21/91	1 hr @ 480 F	O	Cure
02/22/91	2 hrs @ 590 F	O	dry heat
02/22/91	19 hrs @ 115 F	H	humid
02/25/91	2 hrs @ 600 F	O	dry heat
02/25/91	1 hr @ -100 F	C	auto
02/26/91	Test (Location 1)	A	250 PSI (100% A-I) grey
	STOP TESTING		


**MRC Fabrication/Conditioning/Test Form 91-1**

Page 1

Set-Sample: 25 - 9521 Comments: B1

### **Materials: MARB 4 over Sodium Nitrite (Brulin's)**

## **Equip Definitions:**



Date	Action	Equip	Results/Comments
02/10/91	Clean		Panel HCL cleaned of mill scale
02/20/91	Clean		Gel (0291) clean 15 minutes
02/20/91	Rinse		Tap water, do not dry
02/20/91	Rinse		Corrosion inhibitor final rinse, hang
02/21/91	Report		Observations on Test plan sheet
02/21/91	Coat		Spray three coats MARB 4
02/21/91	1 hr @ 480 F	O	Cure
02/22/91	2 hrs @ 590 F	O	dry heat
02/22/91	19 hrs @ 115 F	H	humid
02/25/91	2 hrs @ 600 F	O	dry heat
02/25/91	1 hr @ -100 F	C	auto
02/26/91	Test (Location 1)	A	450 PSI (40% A; 50% C; 10% F)
STOP TESTING			

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25 - 9522 Comments: B2

Materials: MARB 4 over Sodium Nitrite (Brulin's)

Equip Definitions:

0
1

Date	Action	Equip	Results/Comments
02/10/91	Clean		Panel HCL cleaned of mill scale
02/20/91	Clean	Gel (0291)	clean 15 minutes
02/20/91	Rinse		Tap water, do not dry
02/20/91	Rinse		Corrosion inhibitor final rinse, hang
02/21/91	Report		Observations on Test plan sheet
02/21/91	Coat		Spray three coats MARB 4
02/21/91	1 hr @ 480 F	O	Cure
02/22/91	2 hrs @ 590 F	O	dry heat
02/22/91	19 hrs @ 115 F	H	humid
02/25/91	2 hrs @ 600 F	O	dry heat
02/25/91	1 hr @ -100 F	C	auto
02/26/91	Test (Location 1)	A	300 PSI (50% A; 50% C) rust, copper specks
	STOP TESTING		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25A - 9507    Comments:

Materials: Silicone Release DC-1-2531

Equip Definitions:

		5
		2
		6
as		4
is	3	1

Date	Action	Equip	Results/Comments
01/31/91	Acid cleaned		HCL both sides
01/31/91	Gel cleaned		
02/08/91	Gel cleaned		
02/08/91	Coat		Brush coat top half
02/08/91	Coat		Brush coat left half (top right 2 coats)
02/08/91	Cure	O	air dry, 1 hr @ 400 F
02/11/91	16 hrs @ 115 F	H	
02/12/91	1 hr @ -100 F	C	
02/12/91	2 hrs @ 600 F	O	
02/12/91	18 hrs @ 115 F	H	
02/13/91	1 hr @ -100 F	C	
02/13/91	15 hrs @ 118 F	H	
02/14/91	1 hr @ -100 F	C	
02/14/91	2 hrs @ 590 F	O	
02/14/91	16 hrs @ 120 F	H	
02/15/91	0.5 hrs @ -40 F	C	
02/18/91	Test (Location 1)	A	>1000 PSI (1 coat - no failure)
02/18/91	Test (Location 2)	A	1000 PSI (2 coats - 90% C, 9% F, 1% dolly)
02/22/91	2 hrs @ 590 F	O	
02/22/91	19 hrs @ 115 F	H	
02/25/91	2 hrs @ 600 F	O	


## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25A - 9507 Comments:

Materials: Silicone Release Resin

Equip Definitions:



Date	Action	Equip	Results/Comments
02/25/91	1 hr @ -100 F	C	
02/27/91	1 hr @ -108 F	C	
02/27/91	2 hrs @ 350 F	O	
02/28/91	1 hr @ -100 F	C	
02/28/91	2 hrs @ 600 F	O	
02/28/91	18 hrs @ 115 F	H	
03/04/91	Test (Location 3)	A	>1000 PSI But looks rusty underneath
03/04/91	1 hr @ 487 F	O	
03/04/91	1 hr @ -100 F	C	
03/05/91	1 hr @ -100 F	C	
03/05/91	1 hr @ 600 F	O	
03/05/91	16.5 hrs @ 116 F	H	
03/08/91	1 hr @ -100 F	C	cold auto
03/08/91	2 hrs @ 600 F	O	
03/08/91	64 hrs @ 140 F	H	
03/11/91	1 hr @ -100 F	C	
03/11/91	2 hrs @ 600 F	O	
03/11/91	17 hrs @ 115 F	H	
03/12/91	1 hr @ -100 F	C	
03/12/91	1 hr @ 487 F	O	
03/12/91	16 hrs @ 115 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 25A - 9507      Comments: Silicone Release

03/14/91	Test (Location 4)	A	1000 PSI (60% F; 40% dolly)	1 coat
03/14/91	Test (Location 5)	A	>1000 PSI	2 coats
03/19/91	3 hrs @ 610 F	O		
03/19/91	17 hrs @ 116 F	H		
03/20/91	3 hrs @ 650 F	O		
03/20/91	1 hr @ -100 F	C		
03/20/91	16 hrs @ 140 F	H		
03/21/91	1 hr @ -100 F	C		
03/21/91	1 hr @ 640 F	O		
03/21/91	16 hrs @ 140 F	H		
03/22/91	1 hr @ -100 F	C		
03/22/91	1 hr @ 640 F	O		
03/22/91	1 hr @ -100 F	C		
03/22/91	43 hrs @ 115 F	H		
03/24/91	1 hr @ -100 F	C	46 events (350 hours)	
03/28/91	Test (Location 6)	A	650 PSI (50% C/I; 50% F /dolly)	

STOP TESTING - 100% Rusting Add Zinc or Aluminum in 9508 paint

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 25A -9508      Comments:

A516-70 panel  
 Materials: Silicone Release      As is  
                                         Aluminum filled

Equip Definitions:

777	0
1	3
2	4

Date	Action	Equip	Results/Comments
03/14/91			
03/19/91	3 hrs @ 610 F	O	
03/19/91	17 hrs @ 116 F	H	
03/20/91	3 hrs @ 650 F	O	
03/20/91	1 hr @ -100 F	C	
03/20/91	16 hrs @ 140 F	H	
03/21/91	1 hr @ -100 F	C	
03/21/91	1 hr @ 640 F	O	
03/21/91	16 hrs @ 140 F	H	
03/22/91	1 hr @ -100 F	C AM	
03/22/91	1 hr @ 640 F	O	
03/22/91	1 hr @ -100 F	C PM	
03/22/91	43 hrs @ 115 F	H	
03/24/91	1 hr @ -100 F	C	
03/25/91	1 hr @ -100 F	C	
03/25/91	17 hrs @ 140 F	H	
03/25/91	1 hr @ 0 F	C	
03/26/91	1 hr @ 700 F	O	Very hot
03/27/91	2 hrs @ 650 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

**Set-Sample: 25A - 9508      Comments: Silicone Release with aluminum / upper  
with zinc (grey)/ lower**

03/27/91	1 hr @ -100 F	C
03/28/91	1 hr @ -100 F	C
03/28/91	2 hrs @ 650 F	O
03/29/91	Test (Location 1)	A      800 PSI (50% C, 15% A, 20% F)      0.5 mils
03/29/91	Test (Location 2)	A      600 PSI (80% C/I, 20 % F)      0.55 mils
03/29/91	20 hrs @ 120 F	H
03/30/91	1 hr @ -100 F	C
03/30/91	44 hrs @ 118 F	H
04/01/91	1 hr @ -100 F	C
04/01/91	2 hrs @ 650 F	O
04/01/91	20 hrs @ 120 F	H
04/02/91	1 hr @ -100 F	C
04/02/91	17 hrs @ 120 F	H
04/03/91	1 hr @ -100 F	C
04/03/91	17 hrs @ 120 F	H
04/04/91	1 hr @ -150 F	C
04/04/91	2 hrs @ 650 F	O
04/04/91	20 hrs @ 120 F	H
04/05/91	1 hr @ -100 F	C
04/05/91	1 hr @ 650 F	O
04/06/91	Test (Location 3)	A      >1000 PSI
04/06/91	Test (Location 4)	A      550 PSI (90% C; 10% F)
04/08/91	2 hrs @ 650 F	O
04/08/91	1 hr @ -100 F	C

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 25A - 9508    Comments: Silicone Release with aluminum / upper  
with zinc (grey)/ lower

04/08/91	40 hrs @ 120 F	H
04/10/91	1 hr @ -100 F	C
04/10/91	2 hrs @ 650 F	O
04/11/91	4 hrs @ 650 F	O
04/11/91	14 hrs @ 150 F	H
04/12/91	1 hr @ -100 F	C
04/12/91	65 hrs @ 120 F	H
04/15/91	1 hr @ -100 F	C
04/15/91	40 hrs @ 115 F	H
04/17/91	1 hr @ -100 F	C
04/17/91	1 hr @ -100 F	C
04/17/91	2 hrs @ 650 F	O
04/17/91	14 hrs @ 115 F	H
04/18/91	1 hr @ -100 F	C

Stopped events

-----  
-----  
-----  
-----  
-----  
-----  
-----  
-----  
-----  
-----  
-----

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26 -9601      Comments:

A516-70 panel  
 Materials: Sherwin Williams B59S3 Silicone paint

Equip Definitions:

o	6b
2	1
3b	4
	5

Date	Action	Equip	Results/Comments
03/06/91	Clean	-	Remove all mill scale with 50% HCL
03/11/91	Clean	-	5 minutes gel, rinse, quick air dry
03/11/91	Coat	S	Spray entire panel
03/12/91	1 hr @ 480 F	O	Bake
			1244.2 g
03/12/91	16 hrs @ 115 F	H	Humid
03/13/91	1 hr @ -100 F	C	auto cold
03/13/91	2 hrs @ 600 F	O	hot, dry
03/13/91	16 hrs @ 140 F	H	Humid
03/14/91	1 hr @ -100 F	C	auto
03/14/91	1 hr @ 525 F	C	manual
03/15/91	Test (Location 1)	A	550 PSI (100% dolly)
03/19/91	Test (Location 2)	A	>1000 PSI No Failure
03/19/91	3 hrs @ 610 F	O	hot, dry
			1244.1 g
03/19/91	17 hrs @ 116 F	H	humid
03/20/91	3 hrs @ 650 F	O	hot, dry
03/20/91	1 hr @ -100 F	C	
03/20/91	16 hrs @ 140 F	H	
03/21/91	1 hr @ -100 F	C	
03/21/91	1 hr @ 640 F	O	
03/21/91	16 hrs @ 140 F	H	
03/22/91	1 hr @ -100 F	C	AM

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26 -9601      Comments:

A516-70 panel  
 Materials: Sherwin Williams B59S3 Silicone paint

Equip Definitions:

2	0	6b
	1	
	3b	
	4	
	5	

Date	Action	Equip	Results/Comments
03/22/91	1 hr @ 640 F	O	
03/22/91	1 hr @ -100 F	C	PM
03/22/91	43 hrs @ 115 F	H	
03/24/91	1 hr @ -100 F	C	
03/25/91	1 hr @ -100 F	C	
03/25/91	17 hrs @ 140 F	H	very humid
03/26/91	1 hr @ 0 F	C	
03/26/91	1 hr @ 700 F	O	very hot
03/27/91	2 hrs @ 650 F	O	
03/27/91	1 hr @ -100 F	C	
03/28/91	1 hr @ -100 F	C	rusting where thin; flaking where thick
03/28/91	2 hrs @ 650 F	O	very rusty, 85% coating failure
03/29/91	Test (Location 3b)	A	450 PSI (90% C, 5% F, 5% A) rust 0.8 mils
03/29/91	Test (Location 4)	A	400 PSI (100% C/I, C) 0.4 mils
03/29/91	20 hrs @ 120 F	H	
03/30/91	1 hr @ -100 F	C	
03/30/91	44 hrs @ 118 F	H	
04/01/91	1 hr @ -100 F	C	
04/01/91	2 hrs @ 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 26 -9601      Comments:

04/02/91 17 hrs @ 120 F H 1244.3 g

04/03/91 1 hr @ -100 F C

04/03/91 17 hrs @ 120 F H

04/04/91 1 hr @ -150 F C Manual 15 to 8% N<sub>2</sub>

04/04/91 2 hrs @ 650 F O

04/04/91 20 hrs @ 120 F H

04/05/91 1 hr @ -100 F C

04/05/91 1 hr @ 650 F O

04/06/91 Test (Location 5) A 800 PSI (100% C) rust and oxide

04/08/91 2 hrs @ 650 F O

04/08/91 1 hr @ -100 F C

04/08/91 40 hrs @ 120 F H

04/10/91 1 hr @ -100 F C

04/10/91 2 hrs @ 650 F O

04/11/91 4 hrs @ 650 F O

04/11/91 14 hrs @ 150 F H

04/12/91 1 hrs @ -100 F C

04/12/91 65 hrs @ 120 F H

04/15/91 1 hr @ -100 F C 95% visual failure

04/17/91 Test (Location 6b) A 800 PSI (80% C/I; 20% C-10% rust)

STOP TESTING /REPORT GENERATED 1244.5g 52 events (-150 to 700°F)

Do not continue testing 05/06/91 0.3g wt gain

Set-Sample: 26 -9602      Comments:      Page 3

04/04/91 20 hrs @ 120 F      H

04/05/91 1 hr @ -100 F      C

04/05/91 1 hr @ 650 F      O

04/06/91 Test (Location 5)      A      900 PSI (100% C) mostly clean

04/08/91 2 hrs @ 650 F      O

04/08/91 1 hr @ -100 F      C

04/08/91 40 hrs @ 120 F      H

04/10/91 1 hr @ -100 F      C

04/10/91 2 hrs @ 650 F      O

04/11/91 4 hrs @ 650 F      O

04/11/91 14 hrs @ 150 F      H

04/12/91 1 hrs @ -100 F      C

04/12/91 65 hrs @ 120 F      H

04/15/91 1 hr @ -100 F      C      25% visual failure

04/17/91 Test (Location 6)      A      700 PSI (90% C; 10% F)

STOP TESTING /REPORT GENERATED 1271.0 g 52 events (-150 to 700oF)

Continue Testing to 90% failure      0.05 g wt loss

05/06/91 17 hrs @ 120 F      H

05/07/91 12 hr @ -100 F      C

05/07/91 3 hrs @ 650 F      O

05/07/91 15 hrs @ 120 F      H

05/08/91 1 hr @ -100 F      C

05/08/91 3 hrs @ 690 F      O

05/09/91 1 hr @ -100 F      C

05/09/91 87 hrs @ 124 F      H

05/13/91 1 hr @ -100 F      C

Set-Sample: 26 -9602      Comments:      Page 4

05/13/91 2 hrs @ 650 F      O

05/15/91 1 hr @ -100 F      C

05/15/91 1 hr @ 600 F      C

05/16/91 1 hr @ -100 F      C

05/17/91 1 hr @ -100 F      C

05/17/91 1 hr @ 600 F      C

05/17/91 20 hrs @ 120 F      H

05/17/91 46 hrs @ 120-140 F      H

05/21/91 1 hr @ -100 F      C

05/22/91 3 hrs @ 650 F      O

05/24/91 4 hrs @ 680 F      O

05/28/91 5 hrs @ 650 F      O

05/28/91 16 hrs @ 120 F      H

05/29/91 4 hrs @ 650 F      O

05/29/91 1 hr @ -100 F      C

05/30/91 1 hr @ -100 F      C

05/30/91 3 hrs @ 630 F      O

05/30/91 17 hrs @ 120 F      H

05/31/91 1 hr @ -100 F      C

06/03/91 3 hrs @ 650 F      O

06/03/91 22 hrs @ 140 F      H

06/04/91 66 hrs @ 120 F      H

06/12/91 5 hrs @ 600 F      O

06/13/91 4 hrs @ 600 F      O

06/13/91 1 hr @ -120 F      C      manual

06/13/91 40 hrs @ 120 F      H

Set-Sample: 26 -9602		Comments:	Page 5
06/15/91	2 hrs @ 600 F	0	
06/17/91	2 hrs @ 650 F	0	
06/17/91	1 hr @ -100 F	C	
06/17/91	18 hrs @ 120 F	H	
06/18/91	5 hrs @ 650 F	0	92 events (-150 to 700 F) 30% failure
07/08/91	Test (Location 7)	A	550 PSI (60% C/I; 40% F)

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26 - 9603 Comments:

Materials: Sheffield # 392 siliconized

Equip Definitions:

0	6b
2	3b
4	1
7	
	5

Date	Action	Equip	Results/Comments
03/06/91	Clean	-	Remove all mill scale with 50% HCL
03/11/91	Clean	-	5 minutes gel, rinse, quick air dry
03/11/91	Coat	S	Spray entire panel
03/12/91	1 hr @ 480 F	O	Bake 1257.4 g
03/12/91	16 hrs @ 115 F	H	Humid
03/13/91	1 hr @ -100 F	C	auto cold
03/13/91	2 hrs @ 600 F	O	hot, dry
03/13/91	16 hrs @ 140 F	H	Humid
03/14/91	1 hr @ -100 F	C	auto
03/14/91	1 hr @ 525 F	C	manual
03/15/91	Test (Location 1)	A	700 PSI (70% A; 30% F)
03/19/91	Test (Location 2)	A	1000 PSI (100% A)
03/19/91	3 hrs @ 610 F	O	1257.3 g
03/19/91	17 hrs @ 116 F	H	
03/20/91	3 hrs @ 650 F	O	
03/20/91	1 hr @ -100 F	C	
03/20/91	16 hrs @ 140 F	H	
03/21/91	1 hr @ -100 F	C	
03/21/91	1 hr @ 640 F	O	
03/21/91	16 hrs @ 140 F	H	
03/21/91	1 hr @ -100 F	C	AM

Set-Sample: 26 -9603      Comments:      Page 2

03/22/91	1 hr @ 640 F	O	
03/22/91	1 hr @ -100 F	C	PM
03/22/91	43 hrs @ 115 F	H	
03/24/91	1 hr @ -100 F	C	
03/25/91	1 hr @ -100 F	C	
03/25/91	17 hrs @ 140 F	H	very humid
03/26/91	1 hr @ 0 F	C	
03/26/91	1 hr @ 700 F	O	very hot
03/27/91	2 hrs @ 650 F	O	
03/27/91	1 hr @ -100 F	C	
03/28/91	1 hr @ -100 F	C	
03/28/91	2 hrs @ 650 F	O	30% fail; some rust
03/29/91	Test (Location 3b)	A	500 PSI (100% C)      0.6 mils
03/29/91	Test (Location 4)	A	500 PSI (100% C)      0.8 mils
03/29/91	20 hrs @ 120 F	H	
03/30/91	1 hr @ -100 F	C	
03/30/91	44 hrs @ 118 F	H	
04/01/91	1 hr @ -100 F	C	
04/01/91	2 hrs @ 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	1 hr @ -100 F	C	
04/02/91	17 hrs @ 120 F	H	1257.4 g
04/03/91	1 hr @ -100 F	C	
04/03/91	17 hrs @ 120 F	H	
04/04/91	1 hr @ -150 F	C	Manual 15 to 8% N <sub>2</sub>
04/04/91	2 hrs @ 650 F	O	

Set-Sample: 26 -9603      Comments:      Page 3

04/04/91 20 hrs @ 120 F      H

04/05/91 1 hr @ -100 F      C

04/05/91 1 hr @ 650 F      H

04/06/91 Test (Location 5)      A      400 PSI (100% C) clean, some A

04/08/91 2 hrs @ 650 F      O

04/08/91 1 hr @ -100 F      C

04/08/91 40 hrs @ 120 F      H

04/10/91 1 hr @ -100 F      C

04/10/91 2 hrs @ 650 F      O

04/11/91 4 hrs @ 650 F      O

04/11/91 14 hrs @ 150 F      H

04/12/91 1 hrs @ -100 F      C

04/12/91 65 hrs @ 120 F      H

04/15/91 1 hr @ -100 F      C      40% visual failure

04/17/91 Test (Location 6b)      A      500 PSI (100% C/F)

STOP TESTING /REPORT GENERATED 52 events (-150 to 700 F)

05/06/91                          1257.3 g 0.1 g wt gain

05/06/91 17 hrs @ 120 F      H

05/07/91 12 hr @ -100 F      C

05/07/91 3 hrs @ 650 F      O

05/07/91 15 hrs @ 120 F      H

05/08/91 1 hr @ -100 F      C

05/08/91 3 hrs @ 690 F      O

05/09/91 1 hr @ -100 F      C

05/09/91 87 hrs @ 124 F      H

05/13/91 1 hr @ -100 F      C

Set-Sample: 26 -9603      Comments:      Page 4

05/13/91	2 hrs @ 650 F	O
05/15/91	1 hr @ -100 F	C
05/15/91	1 hr @ 600 F	C
05/16/91	1 hr @ -100 F	C
05/17/91	1 hr @ -100 F	C
05/17/91	1 hr @ 600 F	C
05/17/91	20 hrs @ 120 F	H
05/18/91	46 hrs @ 120-140 F	H
05/21/91	1 hr @ -100 F	C
05/22/91	3 hrs @ 650 F	O
05/24/91	4 hrs @ 680 F	O
05/28/91	5 hrs @ 650 F	O
05/28/91	16 hrs @ 120 F	H
05/29/91	4 hrs @ 650 F	O
05/29/91	1 hr @ -100 F	C
05/30/91	1 hr @ -100 F	C
05/30/91	3 hrs @ 630 F	O
05/30/91	17 hrs @ 120 F	H
05/31/91	1 hr @ -100 F	C
06/03/91	3 hrs @ 650 F	O
06/03/91	22 hrs @ 140 F	H
06/04/91	66 hrs @ 120 F	H
06/12/91	5 hrs @ 600 F	O
06/13/91	4 hrs @ 600 F	O
06/13/91	1 hr @ -120 F	C
06/13/91	40 hrs @ 120 F	H

Set-Sample: 26 -9603      Comments:      Page 5

06/15/91	2 hrs @ 600 F	0		
06/17/91	2 hrs @ 650 F	0		
06/17/91	1 hr @ -100 F	C		
06/17/91	18 hrs @ 120 F	H		
06/18/91	5 hrs @ 650 F	0	92 events (-150 to 700 F)	30% failure
07/08/91	Test (Location 7)	A	550 PSI (85% C; 15% F)	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26 - 9604 Comments: poor spraying

Materials: MARB-4 Old Lot:October 1990 A285 steel

Equip Definitions: 1 side brushed over

:	0	6b
2:	4	1
		3b
		5

Date	Action	Equip	Results/Comments
03/06/91	Clean	-	Remove all mill scale with 50% HCL
03/12/91	Clean	-	5 minutes gel, rinse, quick air dry
03/12/91	Coat	S	Spray entire panel - clumpy, poor uniform
03/12/91	1 hr @ 480 F	O	Cure 1271.0 g
03/12/91	16 hrs @ 115 F	H	Humid
03/13/91	1 hr @ -100 F	C	auto cold
03/13/91	2 hrs @ 600 F	O	hot, dry
03/13/91	16 hrs @ 140 F	H	Humid
03/14/91	1 hr @ -100 F	C	auto
03/14/91	1 hr @ 520 F	C	manual
03/15/91	Test (Location 1)	A	100 PSI (90% A; 10% F)
03/19/91	Test (Location 2)	A	1000 PSI (50% F; 50% C/I/A) flaky
03/19/91	3 hrs @ 610 F	O	1270.8 g
03/19/91	17 hrs @ 116 F	H	
03/20/91	3 hrs @ 650 F	O	
03/20/91	1 hr @ -100 F	C	
03/20/91	16 hrs @ 140 F	H	
03/21/91	1 hr @ -100 F	C	
03/21/91	1 hr @ 640 F	O	
03/21/91	16 hrs @ 140 F	H	
03/22/91	1 hr @ -100 F	C	AM

Set-Sample:	26 -9604	Comments:	Page 2
03/22/91	1 hr @ 640 F	O	
03/22/91	1 hr @ -100 F	C PM	
03/22/91	43 hrs @ 115 F	H	
03/24/91	1 hr @ -100 F	C	
03/25/91	1 hr @ -100 F	C	
03/25/91	17 hrs @ 140 F	H very humid	
03/26/91	1 hr @ 0 F	C	
03/26/91	1 hr @ 700 F	O very hot	
03/27/91	2 hrs @ 650 F	O	
03/27/91	1 hr @ -100 F	C	
03/28/91	1 hr @ -100 F	C	
03/28/91	2 hrs @ 650 F	O 50% failure brush side; 10% fail back	
03/29/91	Test (Location 3b)	A 750 PSI (70% C; 25% F; 5% dolly) 2.3 mils	
03/29/91	Test (Location 4)	A 600 PSI (100% C) 1.05 mils	
03/29/91	20 hrs @ 120 F	H	
03/30/91	1 hr @ -100 F	C	
03/30/91	44 hrs @ 118 F	H	
04/01/91	1 hr @ -100 F	C	
04/01/91	2 hrs @ 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	1 hr @ -100 F	C	
04/02/91	17 hrs @ 120 F	H 1270.7 g	
04/03/91	1 hr @ -100 F	C	
04/03/91	17 hrs @ 120 F	H	
04/04/91	1 hr @ -150 F	C Manual 15 to 8% N <sub>2</sub>	
04/04/91	2 hrs @ 650 F	O	

Set-Sample: 26 -9604 . Comments: Page 3

04/04/91 20 hrs @ 120 F H

04/05/91 1 hr @ -100 F C

04/05/91 1 hr @ 650 F O

04/06/91 Test (Location 5) A >1000 PSI

04/08/91 2 hrs @ 650 F O

04/08/91 1 hr @ -100 F C

04/08/91 40 hrs @ 120 F H

04/10/91 1 hr @ -100 F C

04/10/91 2 hrs @ 650 F O

04/11/91 4 hrs @ 650 F O

04/11/91 14 hrs @ 150 F H

04/12/91 1 hrs @ -100 F C

04/12/91 65 hrs @ 120 F H

04/15/91 1 hr @ -100 F C 5% visual failure

04/17/91 Test (Location 6) A 600 PSI (100 % C) 1270.6g

STOP TESTING /REPORT GENERATED 52 events (-150 to 700 F)

05/06/91 continued testing 0.4 to 0.2 g wt loss

05/06/91 17 hrs @ 120 F H

05/07/91 12 hr @ -100 F C

05/07/91 3 hrs @ 650 F O

05/07/91 15 hrs @ 120 F H

05/08/91 1 hr @ -100 F C

05/08/91 3 hrs @ 690 F O

05/09/91 1 hr @ -100 F C

05/09/91 87 hrs @ 124 F H

05/13/91 1 hr @ -100 F C

Set-Sample: 26 -9604      Comments:      Page 4

05/13/91 2 hrs @ 650 F O

05/15/91 1 hr @ -100 F C

05/15/91 1 hr @ 600 F C

05/16/91 1 hr @ -100 F C

05/17/91 1 hr @ -100 F C

05/17/91 1 hr @ 600 F C

05/17/91 20 hrs @ 120 F H

05/17/91 46 hrs @ 120-140 F H

05/21/91 1 hr @ -100 F C

05/22/91 3 hrs @ 650 F O

05/24/91 4 hrs @ 680 F O

05/28/91 5 hrs @ 650 F O

05/28/91 16 hrs @ 120 F H

05/29/91 4 hrs @ 650 F O

05/29/91 1 hr @ -100 F C

05/30/91 1 hr @ -100 F C

05/30/91 3 hrs @ 630 F O

05/30/91 17 hrs @ 120 F H

05/31/91 1 hr @ -100 F C

06/03/91 3 hrs @ 650 F O

06/03/91 22 hrs @ 140 F H

06/04/91 66 hrs @ 120 F H

06/12/91 5 hrs @ 600 F O

06/13/91 4 hrs @ 600 F O

06/13/91 1 hr @ -120 F C manual

06/13/91 40 hrs @ 120 F H



## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26 - 9605 Comments:

Materials: MARB-4 New Lot

Equip Definitions:

2	0	6b
	4	1
		3b
		5

Date	Action	Equip	Results/Comments
03/06/91	Clean	-	Remove all mill scale with 50% HCL
03/12/91	Clean	-	5 minutes gel, rinse, quick air dry
03/12/91	Coat	S	Spray entire panel
03/12/91	1 hr @ 480 F	O	Cure Good hard coating 1281.6 g
03/12/91	16 hrs @ 115 F	H	Humid
03/13/91	1 hr @ -100 F	C	auto cold
03/13/91	2 hrs @ 600 F	O	hot, dry
03/13/91	16 hrs @ 140 F	H	Humid
03/14/91	1 hr @ -100 F	C	auto
03/14/91	1 hr @ 520 F	C	manual
03/15/91	Test (Location 1)	A	500 PSI (90% dolly; 10% F)
03/19/91	Test (Location 2)	A	1000 PSI (80% dolly; 20% F)
03/19/91	3 hrs @ 610 F	O	1281.6 g
03/19/91	17 hrs @ 116 F	H	
03/20/91	3 hrs @ 650 F	O	
03/20/91	1 hrs @ -100 F	C	
03/20/91	16 hrs @ 140 F	H	
03/21/91	1 hr @ -100 F	C	
03/21/91	1 hr @ 640 F	O	
03/21/91	16 hrs @ 140 F	H	
03/22/91	1 hr @ -100 F	C	AM

Set-Sample: 26 -9605		Comments:	Page 2
03/22/91	1 hr @ 640 F	O	
03/22/91	1 hr @ -100 F	C	PM
03/22/91	43 hrs @ 115 F	H	
03/24/91	1 hr @ -100 F	C	
03/25/91	1 hr @ -100 F	C	
03/25/91	17 hrs @ 140 F	H	very humid
03/26/91	1 hr @ 0 F	C	
03/26/91	1 hr @ 700 F	O	very hot
03/27/91	2 hrs @ 650 F	O	
03/27/91	1 hr @ -100 F	C	
03/28/91	1 hr @ -100 F	C	
03/28/91	2 hrs @ 650 F	O	10% coating fail, no rust
03/29/91	Test (Location 3b)	A	500 PSI (60% F; 40% C) 1.1 mils
03/29/91	Test (Location 4)	A	600 PSI (100% C/I, C) 0.85 mils
03/29/91	20 hrs @ 120 F	H	
03/30/91	1 hr @ -100 F	C	
03/30/91	44 hrs @ 118 F	H	
04/01/91	1 hr @ -100 F	C	
04/01/91	2 hrs @ 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	1 hr @ -100 F	C	
04/02/91	17 hrs @ 120 F	H	1281.5 g
04/03/91	1 hr @ -100 F	C	
04/03/91	17 hrs @ 120 F	H	
04/04/91	1 hr @ -150 F	C	Manual 15 to 8% N <sub>2</sub>
04/04/91	2 hrs 650 F	O	

Set-Sample: 26 -9605      Comments:      Page 3

04/04/91 20 hrs @ 120 F      H

04/05/91 1 hr @ -100 F      C

04/05/91 1 hr @ 650 F      O

04/06/91 Test (Location 5) A      >1000 PSI

04/08/91 2 hrs @ 650 F      O

04/08/91 1 hr @ -100 F      C

04/08/91 40 hrs @ 120 F      H

04/10/91 1 hr @ -100 F      C

04/10/91 2 hrs @ 650 F      O

04/11/91 4 hrs @ 650 F      O

04/11/91 14 hrs @ 150 F      H

04/12/91 1 hrs @ -100 F      C

04/12/91 65 hrs @ 120 F      H

04/15/91 1 hr @ -100 F      C      1% visual failure

04/17/91 Test (Location 6) A      900 PSI (100% C)

STOP TESTING /REPORT GENERATED      1281.4g 52 events (-150 to 700 F)

05/06/91 Continue testing to failure      0.35 g wt gain

05/06/91 17 hrs @ 120 F      H

05/07/91 12 hr @ -100 F      C

05/07/91 3 hrs @ 650 F      O

05/07/91 15 hrs @ 120 F      H

05/08/91 1 hr @ -100 F      C

05/08/91 3 hrs @ 690 F      O

05/09/91 1 hr @ -100 F      C

05/09/91 87 hrs @ 124 F      H

05/13/91 1 hr @ -100 F      C

Set-Sample:	26 -9605	Comments:	Page 4
05/13/91	2 hrs @ 650 F	O	
05/15/91	1 hr @ -100 F	C	
05/15/91	1 hr @ 600 F	C	
05/16/91	1 hr @ -100 F	C	
05/17/91	1 hr @ -100 F	C	
05/17/91	1 hr @ 600 F	C	
05/17/91	20 hrs @ 120 F	H	
05/17/91	46 hrs @ 120-140 F	H	
05/21/91	1 hr @ -100 F	C	
05/22/91	3 hrs @ 650 F	O	
05/24/91	4 hrs @ 680 F	O	
05/28/91	5 hrs @ 650 F	O	
05/28/91	16 hrs @ 120 F	H	
05/29/91	4 hrs @ 650 F	O	
05/29/91	1 hr @ -100 F	C	
05/30/91	1 hr @ -100 F	C	
05/30/91	3 hrs @ 630 F	O	
05/30/91	17 hrs @ 120 F	H	
05/31/91	1 hr @ -100 F	C	
06/03/91	3 hrs @ 650 F	O	
06/03/91	22 hrs @ 140 F	H	
06/04/91	66 hrs @ 120 F	H	
06/12/91	5 hrs @ 600 F	O	
06/13/91	4 hrs @ 600 F	O	
06/13/91	1 hr @ -120 F	C manual	
06/13/91	40 hrs @ 120 F	H	

Set-Sample: 26 -9605	Comments:	Page 5
06/15/91 2 hrs @ 600 F	0	
06/17/91 2 hrs @ 650 F	0	
06/17/91 1 hr @ -100 F	C	
06/17/91 18 hrs @ 120 F	H	
06/18/91 5 hrs @ 650 F	0	92 events (-150 to 700 F) 5% failure
07/08/91 Test (Location 7)	A	850 PSI (90 % C; 10% F)

SEE SET26.OLD for 9601 and 9606; SET26.AMB for Ambient testing

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26 - 9606 Comments:

Materials: Sherwin Williams Spray Aluminum

Equip Definitions:

	o	6b
2	4	1
3b		

5

Date	Action	Equip	Results/Comments
03/06/91	Clean	-	Remove all mill scale with 50% HCL
03/11/91	Clean	-	5 minutes gel, rinse, quick air dry
03/11/91	Coat	S	Spray entire panel
03/12/91	1 hr @ 480 F	O	Bake 1284.15 g
03/12/91	16 hrs @ 115 F	H	Humid
03/13/91	1 hr @ -100 F	C	auto cold
03/13/91	2 hrs @ 600 F	O	hot, dry
03/13/91	16 hrs @ 140 F	H	Humid
03/14/91	1 hr @ -100 F	C	auto
03/14/91	1 hr @ 520 F	C	manual
03/15/91	Test (Location 1)	A	100 PSI (70% C; 30% A)
03/19/91	Test (Location 2)	A	550 PSI (85% C; 4% A; 1% dolly)
03/19/91	3 hrs @ 610 F	O	1284.0 g
03/19/91	17 hrs @ 116 F	H	
03/20/91	3 hrs @ 650 F	O	
03/20/91	1 hr @ -100 F	C	
03/20/91	16 hrs @ 140 F	H	
03/21/91	1 hr @ -100 F	C	
03/21/91	1 hr @ 640 F	O	
03/21/91	16 hrs @ 140 F	H	
03/22/91	1 hr @ -100 F	C	AM

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26 -9606      Comments:

AS16-70 panel  
Materials: Sherwin Williams Spray Aluminum

Equip Definitions:

	o	6b
2	4	1
3b		
	5	

Date	Action	Equip	Results/Comments
03/22/91	1 hr @ 640 F	O	
03/22/91	1 hr @ -100 F	C	PM
03/22/91	43 hrs @ 115 F	H	
03/24/91	1 hr @ -100 F	C	
03/25/91	1 hr @ -100 F	C	
03/25/91	17 hrs @ 140 F	H	very humid
03/26/91	1 hr @ 0 F	C	
03/26/91	1 hr @ 700 F	O	very hot
03/27/91	2 hrs @ 650 F	O	
03/27/91	1 hr @ -100 F	C	
03/28/91	1 hr @ -100 F	C	
03/28/91	2 hrs @ 650 F	O	90% fail; alot of rust
03/29/91	Test (Location 3b)	A	950 PSI (50% C; 20% A; 30% F,D) 0.4 mils
03/29/91	Test (Location 4)	A	600 PSI (60% C/I,C; 40% A) 0.9 mils
03/29/91	20 hrs @ 120 F	H	
03/30/91	1 hr @ -100 F	C	
03/30/91	44 hrs @ 118 F	H	
04/01/91	1 hr @ -100 F	C	
04/01/91	2 hrs @ 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 26 -9606      Comments:

04/02/91 17 hrs @ 120 F H 1284.3 g

04/03/91 1 hr @ -100 F C

04/03/91 17 hrs @ 120 F H

04/04/91 1 hr @ -150 F C Manual 15 to 8% N<sub>2</sub>

04/04/91 2 hrs @ 650 F O

04/04/91 20 hrs @ 120 F H

04/05/91 1 hr @ -100 F C

04/05/91 1 hr @ 650 F O

04/06/91 Test (Location 5) A 900 PSI (20% D; 60% F; 20% C)

04/08/91 2 hrs @ 650 F O

04/08/91 1 hr @ -100 F C

04/08/91 40 hrs @ 120 F H

04/10/91 1 hr @ -100 F C

04/10/91 2 hrs @ 650 F O

04/11/91 4 hrs @ 650 F O

04/11/91 14 hrs @ 150 F H

04/12/91 1 hrs @ -100 F C

04/12/91 65 hrs @ 120 F H

04/15/91 1 hr @ -100 F C 90% visual failure

04/17/91 Test (Location 6) A 650 PSI (80% C; 10% F; 10% A/rust)

STOP TESTING /REPORT GENERATED

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26 -9601A      Comments:

A516-70 panel  
Materials: Sherwin Williams 859S3 Silicone paint

Equip Definitions:

1	4	0
	2	
		3B

Date	Action	Equip	Results/Comments
03/06/91	Clean	-	Remove all mill scale with 50% HCL
03/11/91	Clean	-	5 minutes gel, rinse, quick air dry
03/11/91	Coat	S	Spray entire panel
<b>Ambient drying</b>			
03/19/91	Test (Location 1)	A	100 PSI (100% C) near Epoxy
04/15/91	Test (Location 2)	A	100 PSI (100% C)
	Hardness	B	600g medium scrape
04/15/91	1 hr @ 487 F	O	1 month late cure
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ -100 F	C	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	
04/19/91	1 hr @ -100 F	C	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr @ -100 F	C	
04/20/91	2 hrs @ 650 F	O	
04/20/91	44 hrs @ 118 F	H	


## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26 -9601A      Comments: See pg 1

A516-70 panel  
Materials: SW 859S3

Equip Definitions:



Date	Action	Equip	Results/Comments
04/22/91	1 hr @ -100 F	C	
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	1 hr @ -100 F	C	
04/23/91	3 hrs @ 780 F	O	very hot
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	1 hr @ -100 F	C	
04/24/91	4 hrs @ 650 F	O	
04/25/91	1 hr @ -100 F	C	
04/25/91	3 hrs @ 630 F	O	
04/27/91	Test (Location 38)	A	>800 no failure General rusting
04/29/91	1 hr @ -100 F	C	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	wet panels before exposure
04/30/91	1 hr @ 480 F	O	
04/30/91	1 hr @ -100 F	C	
04/30/91	17 hrs @ 118 F	O	
05/01/91	1 hr @ -100 F	C	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 26 -9601A      Comments:

05/03/91 3 hrs @ 690 F O

05/03/91 64 hrs @ 120 F H

05/06/91 3 hrs @ 690 F O

05/06/91 1 hr @ -100 F C

05/06/91 17 hrs @ 120 F H

05/07/91 1 hr @ -100 F C

05/07/91 3 hrs @ 650 F O

05/07/91 15 hrs @ 120 F H

05/08/91 1 hr @ -100 F C

05/08/91 3 hrs @ 690 F O

05/09/91 1 hr @ -100 F C

05/09/91 87 hrs @ 124 F H

05/13/91 1 hr @ -100 F C

05/13/91 2 hrs @ 650 F O

05/15/91 1 hr @ -100 F C autocycle

05/15/91 1 hr @ 600 F C autocycle

05/16/91 1 hr @ -100 F C

05/17/91 1 hr @ -100 F C autocycle

05/17/91 1 hr @ 600 F C autocycle

05/17/91 20 hrs @ 120 F H

05/18/91 46 hrs @ 120-140 F H

05/21/91 1 hr @ -100 F C

05/22/91 3 hrs @ 650 F O

05/24/91 4 hrs @ 680 F O

## MRC Fabrication/Conditioning/Test Form 91-1

Page 4

Set-Sample: 26 -9601A      Comments:

A516-70 panel  
Materials: Sherwin Williams B59S3 Silicone paint

Equip Definitions:

	0
1	4
2	
3	B

Date	Action	Equip	Results/Comments
05/28/91	5 hrs @ 650 F	O	
05/28/91	16 hrs @ 120 F	H	
05/29/91	4 hrs @ 650 F	O	
05/29/91	1 hr @ -100 F	C	
05/30/91	1 hr @ -100 F	C	
05/30/91	3 hrs @ 630 F	O	
05/30/91	17 hrs @ 120 F	H	
05/31/91	1 hr @ -100 F	C	
06/03/91	3 hrs @ 650 F	O	
06/05/91	22 hrs @ 140 F	H	
06/06/91	66 hrs @ 120 F	H	
06/12/91	5 hrs @ 600 F	O	
06/13/91	4 hrs @ 600 F	O	
06/13/91	1 hr @ -120 F	C	manual
06/13/91	40 hrs @ 120 F	H	
06/15/91	2 hrs @ 600 F	O	
06/17/91	2 hrs @ 650 F	O	
06/17/91	1 hr @ -100 F	C	
06/17/91	18 hrs @ 120 F	H	
06/18/91	5 hrs @ 650 F	O	Pictures 76 events (-150 to 790 F)
07/08/91	Test (Location 4)	A	>1000 PSI      90% RUSTING

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26 -9602A      Comments:

A516-70 panel  
 Materials: Sherwin Williams 859S8 Silicone paint

	0
1	2
	3

Equip Definitions:

Date	Action	Equip	Results/Comments
03/06/91	Clean	-	Remove all mill scale with 50% HCL
03/11/91	Clean	-	5 minutes gel, rinse, quick air dry
03/11/91	Coat	S	Spray entire panel
<b>Ambient drying</b>			
03/19/91	Test (Location 1)	A	100 PSI (100% C) near Epoxy
04/15/91	Test (Location 2)	A	100 PSI (100% C)
	Hardness	B	600g medium scrape
04/15/91	1 hr @ 487 F	O	1 month late cure
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ -100 F	C	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	
04/19/91	1 hr @ -100 F	C	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr @ -100 F	C	
04/20/91	2 hrs @ 650 F	O	
04/20/91	44 hrs @ 118 F	H	


## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26 -9602A      Comments:

Materials: A516-70 panel  
SW 859S8

Equip Definitions:



Date	Action	Equip	Results/Comments
04/22/91	1 hr @ -100 F	C	
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	1 hr @ -100 F	C	
04/23/91	3 hrs @ 780 F	O	very hot
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	1 hr @ -100 F	C	
04/24/91	4 hrs @ 650 F	O	
04/25/91	1 hr @ -100 F	C	
04/25/91	3 hrs @ 630 F	O	
04/27/91	Test (Location 3)	A	>800 no failure Little rusting
04/29/91	1 hr @ -100 F	C	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	wet panels before exposure
04/30/91	1 hr @ 480 F	O	
04/30/91	1 hr @ -100 F	C	
04/30/91	17 hrs @ 118 F	O	
05/01/91	1 hr @ -100 F	C	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	

Set-Sample: 26 -9602A      Comments:

Page 3

05/03/91 3 hrs @ 690 F O

05/03/91 64 hrs @ 120 F H

05/06/91 3 hrs @ 690 F O

05/06/91 1 hr @ -100 F C

05/06/91 17 hrs @ 120 F H

05/07/91 1 hr @ -100 F C

05/07/91 3 hrs @ 650 F O

05/07/91 15 hrs @ 120 F H

05/08/91 1 hr @ -100 F C

05/08/91 3 hrs @ 690 F O

05/09/91 1 hr @ -100 F C

05/09/91 87 hrs @ 124 F H

05/13/91 1 hr @ -100 F C

05/13/91 2 hrs @ 650 F O

05/15/91 1 hr @ -100 F C autocycle

05/15/91 1 hr @ 600 F C autocycle

05/16/91 1 hr @ -100 F C

05/17/91 1 hr @ -100 F C autocycle

05/17/91 1 hr @ 600 F C autocycle

05/17/91 20 hrs @ 120 F H

05/18/91 46 hrs @ 120-140 F H

05/21/91 1 hr @ -100 F C

05/22/91 3 hrs @ 650 F O

05/24/91 4 hrs @ 680 F O


## MRC Fabrication/Conditioning/Test Form 91-1

Page 4


Set-Sample: 26 -9602A      Comments:

A516-70 panel  
 Materials: Sherwin Williams B59S8 Silicone paint

Equip Definitions:



Date	Action	Equip	Results/Comments
05/28/91	5 hrs @ 650 F	O	
05/28/91	16 hrs @ 120 F	H	
05/29/91	4 hrs @ 650 F	O	
05/29/91	1 hr @ -100 F	C	
05/30/91	1 hr @ -100 F	C	
05/30/91	3 hrs @ 630 F	O	
05/30/91	17 hrs @ 120 F	H	
05/31/91	1 hr @ -100 F	C	
06/03/91	3 hrs @ 650 F	O	
06/05/91	22 hrs @ 140 F	H	
06/06/91	66 hrs @ 120 F	H	
06/12/91	5 hrs @ 600 F	O	
06/13/91	4 hrs @ 600 F	O	
06/13/91	1 hr @ -120 F	C	manual
06/13/91	40 hrs @ 120 F	H	
06/15/91	2 hrs @ 600 F	O	
06/17/91	2 hrs @ 650 F	O	
06/17/91	1 hr @ -100 F	C	
06/17/91	18 hrs @ 120 F	H	
06/18/91	5 hrs @ 650 F	O	Pictures 76 events (-150 to 790 F)
07/08/91	Test (Location 4)	A	>1000 PSI      10% RUSTING




## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26 -9603A      Comments: Mar 6 - Jul 8

A516-70 panel  
 Materials: Sheffield #392 siliconized

Equip Definitions:



Date	Action	Equip	Results/Comments
03/06/91	Clean	-	Remove all mill scale with 50% HCL
03/11/91	Clean	-	5 minutes gel, rinse, quick air dry
03/11/91	Coat	S	Spray entire panel
<b>Ambient drying</b>			
03/19/91	Test (Location 1)	A	100 PSI (100% C)
04/15/91	Test (Location 2)	A	100 PSI (100% C)
Hardness			
04/15/91	1 hr @ 487 F	O	1 month late cure
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ -100 F	C	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	
04/19/91	1 hr @ -100 F	C	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr @ -100 F	C	
04/20/91	2 hrs @ 650 F	O	
04/20/91	44 hrs @ 118 F	H	

Set-Sample: 26 -9603A		Comments:	Page 2
04/22/91	1 hr @ -100 F	C	
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	1 hr @ -100 F	C	
04/23/91	3 hrs @ 780 F	O	very hot
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	1 hr @ -100 F	C	
04/24/91	4 hrs @ 650 F	O	
04/25/91	1 hr @ -100 F	C	
04/25/91	3 hrs @ 630 F	O	
04/27/91	Test (Location 3b)	A	>800 no failure General rusting
04/29/91	1 hr @ -100 F	C	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	wet panels before exposure
04/30/91	1 hr @ 480 F	O	
04/30/91	1 hr @ -100 F	C	
04/30/91	17 hrs @ 118 F	O	
05/01/91	1 hr @ -100 F	C	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	
05/03/91	3 hrs @ 690 F	O	
05/03/91	64 hrs @ 120 F	H	
05/06/91	3 hrs @ 690 F	O	
05/06/91	1 hr @ -100 F	C	
05/06/91	17 hrs @ 120 F	H	

Set-Sample: 26 -9603A      Comments:      Page 3

05/07/91 1 hr @ -100 F C

05/07/91 3 hrs @ 650 F O

05/07/91 15 hrs @ 120 F H

05/08/91 1 hr @ -100 F C

05/08/91 3 hrs @ 690 F O

05/09/91 1 hr @ -100 F C

05/09/91 87 hrs @ 124 F H

05/13/91 1 hr @ -100 F C

05/13/91 2 hrs @ 650 F O

05/15/91 1 hr @ -100 F C autocycle

05/15/91 1 hr @ 600 F C autocycle

05/16/91 1 hr @ -100 F C

05/17/91 1 hr @ -100 F C autocycle

05/17/91 1 hr @ 600 F C autocycle

05/17/91 20 hrs @ 120 F H

05/18/91 46 hrs @ 120-140 F H

05/21/91 1 hr @ -100 F C

05/22/91 3 hrs @ 650 F O

05/24/91 4 hrs @ 680 F O

05/28/91 5 hrs @ 650 F O

05/28/91 16 hrs @ 120 F H

05/29/91 4 hrs @ 650 F O

05/29/91 1 hr @ -100 F C

05/30/91 1 hr @ -100 F C

05/30/91 3 hrs @ 630 F O

05/30/91 17 hrs @ 120 F H

Set-Sample: 26 -9603A      Comments:

Page 4

05/31/91	1 hr @ -100 F	C
06/03/91	3 hrs @ 650 F	O
06/03/91	22 hrs @ 140 F	H
06/04/91	66 hrs @ 120 F	H
06/12/91	5 hrs @ 600 F	O
06/13/91	4 hrs @ 600 F	O
06/13/91	1 hr @ -120 F	C manual
06/13/91	40 hrs @ 120 F	H
06/15/91	2 hrs @ 600 F	O
06/17/91	2 hrs @ 650 F	O
06/17/91	1 hr @ -100 F	C
06/17/91	18 hrs @ 120 F	H
06/18/91	5 hrs @ 650 F	O
		76 events (-150 to 790 F)
07/08/91	Test (Location 4)	A
		250 PSI (90% C; 10% F)      20% rusting

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26 -9604A      Comments:

Materials: Old MARB 4  
A516-70 panel

	0	4
1	2	
	3	

Equip Definitions:

Date	Action	Equip	Results/Comments
03/06/91	Clean	-	Remove all mill scale with 50% HCL
03/11/91	Clean	-	5 minutes gel, rinse, quick air dry
03/11/91	Coat	S	Spray entire panel
<hr/> <b>Ambient dry</b> <hr/>			
03/19/91	Test (Location 1)	A	100 PSI (100% C) near F
04/15/91	Test (Location 2)	A	150 PSI (100% C)
	Hardness	B	600g medium scrape
04/15/91	1 hr @ 487 F	O	1 month late cure
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ -100 F	C	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	
04/19/91	1 hr @ -100 F	C	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr @ -100 F	C	
04/20/91	2 hrs @ 650 F	O	
04/20/91	44 hrs @ 118 F	H	

Set-Sample: 26 -9604A      Comments:      Page 2

04/22/91 1 hr @ -100 F      C

04/22/91 1 hr @ 650 F      O

04/22/91 15 hrs @ 115 F      H

04/23/91 1 hr @ -100 F      C

04/23/91 3 hrs @ 780 F      O      very hot

04/23/91 17 hrs @ 118 F      H      very humid

04/24/91 1 hr @ -100 F      C

04/24/91 4 hrs @ 650 F      O

04/25/91 1 hr @ -100 F      C

04/25/91 3 hrs @ 630 F      O      Poor coating; aluminum specks protruding

04/27/91 Test (Location 3)      A      >900 no failure      General rusting

04/29/91 1 hr @ -100 F      C

04/29/91 3 hrs @ 650 F      O

04/29/91 16 hrs @ 118 F      H      wet panels before exposure

04/30/91 1 hr @ 490 F      O

04/30/91 1 hr @ -100 F      C

04/30/91 17 hrs @ 118 F      O

05/01/91 1 hr @ -100 F      C

05/01/91 3 hrs @ 790 F      O      HOT

05/02/91 3 hrs @ 750 F      O      HOT

05/02/91 18 hrs @ 117 F      H

05/03/91 3 hrs @ 690 F      O

05/03/91 64 hrs @ 120 F      H

05/06/91 3 hrs @ 690 F      O

05/06/91 1 hr @ -100 F      C

05/06/91 17 hrs @ 120 F      H

Set-Sample: 26 -9604A		Comments:	Page 3
05/07/91	1 hr @ -100 F	C	
05/07/91	3 hrs @ 650 F	O	
05/07/91	15 hrs @ 120 F	H	
05/08/91	1 hr @ -100 F	C	
05/08/91	3 hrs @ 690 F	O	
05/09/91	1 hr @ -100 F	C	
05/09/91	87 hrs @ 124 F	H	
05/13/91	1 hr @ -100 F	C	
05/13/91	2 hrs @ 650 F	O	
05/15/91	1 hr @ -100 F	C	autocycle
05/15/91	1 hr @ 600 F	C	autocycle
05/16/91	1 hr @ -100 F	C	
05/17/91	1 hr @ -100 F	C	autocycle
05/17/91	1 hr @ 600 F	C	autocycle
05/17/91	20 hrs @ 120 F	H	
05/18/91	46 hrs @ 120-140 F	H	
05/21/91	1 hr @ -100 F	C	
05/22/91	3 hrs @ 650 F	O	
05/24/91	4 hrs @ 680 F	O	
05/28/91	5 hrs @ 650 F	O	
05/28/91	16 hrs @ 120 F	H	
05/29/91	4 hrs @ 650 F	O	
05/29/91	1 hr @ -100 F	C	
05/30/91	1 hr @ -100 F	C	
05/30/91	3 hrs @ 630 F	O	
05/30/91	17 hrs @ 120 F	H	

Set-Sample: 26 -9604A      Comments:      Page 4

05/31/91 1 hr @ -100 F      C  
06/03/91 3 hrs @ 650 F      O  
06/03/91 22 hrs @ 140 F      H  
06/04/91 66 hrs @ 120 F      H  
06/12/91 5 hrs @ 600 F      O  
06/13/91 4 hrs @ 600 F      O  
06/13/91 1 hr @ -120 F      C      manual  
06/13/91 40 hrs @ 120 F      H  
06/15/91 2 hrs @ 600 F      O  
06/17/91 2 hrs @ 650 F      O  
06/17/91 1 hr @ -100 F      C  
06/17/91 18 hrs @ 120 F      H  
06/18/91 5 hrs @ 650 F      O      76 events (-150 F to 790 F)  
07/08/91 Test (Location 4)      A      >1000 PSI      No failure      10% rusting


## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26 -9605A      Comments:

A516-70 panel  
Materials: MARB 4

Equip Definitions:



Date	Action	Equip	Results/Comments
03/06/91	Clean	-	Remove all mill scale with 50% HCL
03/11/91	Clean	-	5 minutes gel, rinse, quick air dry
03/11/91	Coat	S	Spray entire panel
<b>Ambient drying</b>			
03/19/91	Test (Location 1)	A	250 PSI (100% C)
04/15/91	Test (Location 2)	A	150 PSI (100% C)
Hardness			
04/15/91	1 hr @ 487 F	O	1 month late cure
04/15/91	40 hrs @ 115 F	H	
04/17/991	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ -100 F	C	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	
04/19/91	1 hr @ -100 F	C	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr @ -100 F	C	
04/20/91	2 hrs @ 650 F	O	
04/20/91	44 hrs @ 118 F	H	

Set-Sample: 26 -9605A      Comments:      Page 2

04/22/91 1 hr @ -100 F      C

04/22/91 1 hr @ 650 F      O

04/22/91 15 hrs @ 115 F      H

04/23/91 1 hr @ -100 F      C

04/23/91 3 hrs @ 780 F      O      very hot

04/23/91 17 hrs @ 118 F      H      very humid

04/24/91 1 hr @ -100 F      C

04/24/91 4 hrs @ 650 F      O

04/25/91 1 hr @ -100 F      C

04/25/91 3 hrs @ 630 F      O

04/27/91 Test (Location 3)      A      >800 (98% C)      No rusting

04/29/91 1 hr @ -100 F      C

04/29/91 3 hrs @ 650 F      O

04/29/91 16 hrs @ 118 F      H      wet panels before exposure

04/30/91 1 hr @ 480 F      O

04/30/91 1 hr @ -100 F      C

04/30/91 17 hrs @ 118 F      O

05/01/91 1 hr @ -100 F      C

05/01/91 3 hrs @ 790 F      O      HOT

05/02/91 3 hrs @ 750 F      O      HOT

05/02/91 18 hrs @ 117 F      H

05/03/91 3 hrs @ 690 F      O

05/03/91 64 hrs @ 120 F      H

05/06/91 3 hrs @ 690 F      O

05/06/91 1 hr @ -100 F      C

05/06/91 17 hrs @ 120 F      H

Set-Sample: 26 -9605A		Comments:	Page 3
05/07/91	1 hr @ -100 F	C	
05/07/91	3 hrs @ 650 F	O	
05/07/91	15 hrs @ 120 F	H	
05/08/91	1 hr @ -100 F	C	
05/08/91	3 hrs @ 690 F	O	
05/09/91	1 hr @ -100 F	C	
05/09/91	87 hrs @ 124 F	H	
05/13/91	1 hr @ -100 F	C	
05/13/91	2 hrs @ 650 F	O	
05/15/91	1 hr @ -100 F	C	autocycle
05/15/91	1 hr @ 600 F	C	autocycle
05/16/91	1 hr @ -100 F	C	
05/17/91	1 hr @ -100 F	C	autocycle
05/17/91	1 hr @ 600 F	C	autocycle
05/17/91	20 hrs @ 120 F	H	
05/18/91	46 hrs @ 120-140 F	H	
05/21/91	1 hr @ -100 F	C	
05/22/91	3 hrs @ 650 F	O	
05/24/91	4 hrs @ 680 F	O	
05/28/91	5 hrs @ 650 F	O	
05/28/91	16 hrs @ 120 F	H	
05/29/91	4 hrs @ 650 F	O	
05/29/91	1 hr @ -100 F	C	
05/30/91	1 hr @ -100 F	C	
05/30/91	3 hrs @ 630 F	O	
05/30/91	17 hrs @ 120 F	H	

Set-Sample: 26 -9605A      Comments:      Page 4

---

05/31/91 1 hr @ -100 F      C

---

06/03/91 3 hrs @ 650 F      O

---

06/03/91 22 hrs @ 140 F      H

---

06/04/91 66 hrs @ 120 F      H

---

06/12/91 5 hrs @ 600 F      O

---

06/13/91 4 hrs @ 600 F      O

---

06/13/91 1 hr @ -120 F      C      manual

---

06/13/91 40 hrs @ 120 F      H

---

06/15/91 2 hrs @ 600 F      O

---

06/17/91 2 hrs @ 650 F      O

---

06/17/91 1 hr @ -100 F      C

---

06/17/91 18 hrs @ 120 F      H

---

06/18/91 5 hrs @ 650 F      O      76 events (-150 to 790 F)

---

07/08/91 Test (Location 4)      A      >1000 PSI      2% rusting

---

---

---

---

---

---

---

---

---

---

---

---

---

---

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26 -9606A      Comments:

A516-70 panel  
Materials: Sherwin Williams Spray Paint

1	4	0
2		
		38

Equip Definitions:

Date	Action	Equip	Results/Comments
03/06/91	Clean	-	Remove all mill scale with 50% HCL
03/11/91	Clean	-	5 minutes gel, rinse, quick air dry
03/11/91	Coat	S	Spray entire panel
<b>Ambient drying</b>			
03/19/91	Test (Location 1)	A	200 PSI (100% C)
04/15/91	Test (Location 2)	A	200 PSI (100% C)
	Hardness	B	600g medium scrape
04/15/91	1 hr @ 487 F	O	1 month late cure
04/15/91	40 hrs @ 115 F	H	
04/17/991	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ -100 F	C	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	
04/19/91	1 hr @ -100 F	C	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr @ -100 F	C	
04/20/91	2 hrs @ 650 F	O	
04/20/91	44 hrs @ 118 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26 -9606A      Comments:

A516-70 panel  
Materials: SW paint spray

Equip Definitions:

	0
1	2
	3

Date	Action	Equip	Results/Comments
04/22/91	1 hr @ -100 F	C	
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	1 hr @ -100 F	C	
04/23/91	3 hrs @ 780 F	O	very hot
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	1 hr @ -100 F	C	
04/24/91	4 hrs @ 650 F	O	
04/25/91	1 hr @ -100 F	C	
04/25/91	3 hrs @ 630 F	O	
04/27/91	Test (Location 3B)	A	>900 no failure General rusting
04/29/91	1 hr @ -100 F	C	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	wet panels before exposure
04/30/91	1 hr @ 480 F	O	
04/30/91	1 hr @ -100 F	C	
04/30/91	17 hrs @ 118 F	O	
05/01/91	1 hr @ -100 F	C	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	

Set-Sample: 26 -9606A      Comments:

Page 3

05/03/91 3 hrs @ 690 F O  
05/03/91 64 hrs @ 120 F H  
05/06/91 3 hrs @ 690 F O  
05/06/91 1 hr @ -100 F C  
05/06/91 17 hrs @ 120 F H  
05/07/91 1 hr @ -100 F C  
05/07/91 3 hrs @ 650 F O  
05/07/91 15 hrs @ 120 F H  
05/08/91 1 hr @ -100 F C  
05/08/91 3 hrs @ 690 F O  
05/09/91 1 hr @ -100 F C  
05/09/91 87 hrs @ 124 F H  
05/13/91 1 hr @ -100 F C  
05/13/91 2 hrs @ 650 F O  
05/15/91 1 hr @ -100 F C autocycle  
05/15/91 1 hr @ 600 F C autocycle  
05/16/91 1 hr @ -100 F C  
05/17/91 1 hr @ -100 F C autocycle  
05/17/91 1 hr @ 600 F C autocycle  
05/17/91 20 hrs @ 120 F H  
05/18/91 46 hrs @ 120-140 F H  
05/21/91 1 hr @ -100 F C  
05/22/91 3 hrs @ 650 F O  
05/24/91 4 hrs @ 680 F O

## MRC Fabrication/Conditioning/Test Form 91-1

Page 4

Set-Sample: 26 -9606A      Comments:

A516-70 panel  
Materials: Sherwin Williams Spray Paint

	0
I	2
	3

Equip Definitions:

Date	Action	Equip	Results/Comments
05/28/91	5 hrs @ 650 F	O	
05/28/91	16 hrs @ 120 F	H	
05/29/91	4 hrs @ 650 F	O	
05/29/91	1 hr @ -100 F	C	
05/30/91	1 hr @ -100 F	C	
05/30/91	3 hrs @ 630 F	O	
05/30/91	17 hrs @ 120 F	H	
05/31/91	1 hr @ -100 F	C	
06/03/91	3 hrs @ 650 F	O	
06/03/91	22 hrs @ 140 F	H	
06/04/91	66 hrs @ 120 F	H	
06/12/91	5 hrs @ 600 F	O	
06/13/91	4 hrs @ 600 F	O	
06/13/91	1 hr @ -120 F	C	manual
06/13/91	40 hrs @ 120 F	H	
06/15/91	2 hrs @ 600 F	O	
06/17/91	2 hrs @ 650 F	O	
06/17/91	1 hr @ -100 F	C	
06/17/91	18 hrs @ 120 F	H	
06/18/91	5 hrs @ 650 F	O	76 events (-150 to 790 F) 80% rusting
07/01/91	Test (Location 4)	A	900 PSI (48% C; 48% C/I; 2% rust; 2% F)

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26A - 9607    Comments: MAZRB

mils

0.9

1	4
3	
2	

Materials: MARB-4 with ZINC

0.63

Equip Definitions:

0.55

Date	Action	Equip	Results/Comments
03/24/91	MEK wipe	-	Clean sander-stripper prepared panel
03/24/91	Coat	-	Brush on MAZRB
03/24/91	1 hr @ 487 F	O	Cure
03/25/91	1 hr @ -100 F	C	
03/25/91	17 hrs @ 140 F	H	
03/26/91	1 hr @ -100 F	C	
03/26/91	1 hr @ 700 F	O	Very hot, dry
03/27/91	2 hrs @ 650 F	O	
03/27/91	1 hr @ -100 F	C	
03/28/91	1 hr @ -100 F	C	
03/28/91	2 hr @ 650 F	O	
03/29/91	Test (Location 1)	A	>1050 PSI Excellent condition 0.88 mils
03/29/91	20 hrs @ 120 F	H	
03/30/91	1 hr @ -100 F	C	
03/30/91	44 hrs @ 118 F	H	
04/01/91	1 hr @ -100 F	C	
04/01/91	2 hrs @ 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	1 hr @ -100 F	C	
04/02/91	17 hrs @ 120 F	H	1275.9 g (wet & dry)
04/03/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26A - 9607    Comments:    Steel

Materials: MAZRB

Equip Definitions:

1	4
3	
2	

Date	Action	Equip	Results/Comments
04/03/91	17 hrs @ 120 F	H	
04/04/91	1 hr @ -150 F	C	manual
04/04/91	2 hrs @ 650 F	O	
04/04/91	20 hrs @ 120 F	H	
04/05/91	1 hr @ -100 F	C	
04/05/91	1 hr @ 650 F	O	
04/06/91	Test (Location 2)	A	600 PSI (60% d; 40% F/C)
04/06/91	41 hrs @ 120 F	H	
04/08/91	2 hrs @ 650 F	O	
04/08/91	1 hr @ -100 F	C	
04/08/91	40 hrs @ 120 F	H	
04/10/91	1 hr @ -100 F	C	
04/10/91	2 hrs @ 650 F	O	
04/11/91	4 hrs @ 650 F	O	
04/11/91	14 hrs @ 150 F	H	
04/12/91	1 hr @ -100 F	C	
04/12/91	65 hrs @ 120 F	H	
04/15/91	1 hr @ -100 F	C	
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 26A - 9607 Comments: MAZRB

Materials: MARB-4 with ZINC

Equip Definitions:

1	4
3	
2	

Date	Action	Equip	Results/Comments
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ -100 F	C	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	
04/19/91	1 hr @ -100 F	C	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr @ -100 F	C	
04/20/91	2 hrs @ 650 F	O	
04/20/91	44 hrs @ 118 F	H	
04/22/91	1 hr @ -100 F	C	
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	1 hr @ -100 F	C	
04/23/91	3 hrs @ 780 F	O	very hot
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	1 hr @ -100 F	C	
04/24/91	4 hrs @ 650 F	O	
04/25/91	1 hr @ -100 F	C	
04/25/91	3 hrs @ 630 F	O	Excellent condition except where thick at top
04/27/91	Test (Location 3)	A	500 PSI (100% C) edge rust/cracking top

## MRC Fabrication/Conditioning/Test Form 91-1

Page 4

Set-Sample: 26A - 9607    Comments: MAZRB

mils

0.9

1 4

Materials: MARB-4 with ZINC

0.63

3

Equip Definitions:

0.55

2

Date	Action	Equip	Results/Comments
04/29/91	1 hr @ -100 F	C	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	
04/30/91	1 hr @ 480 F	O	
04/30/91	1 hr @ -100 F	C	
04/30/91	17 hrs @ 118 F	H	
05/01/91	1 hr @ -100 F	C	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	
05/03/91	3 hrs @ 690 F	O	
05/03/91	64 hrs @ 120 F	H	
05/06/91	3 hrs @ 690 F	O	
05/06/91	1 hr @ -100 F	C	
05/06/91	17 hrs @ 120 F	H	
06/07/91	1 hr @ -100 F	C	
05/07/91	3 hrs @ 650 F	O	
05/07/91	15 hrs @ 120 F	H	
05/08/91	1 hr @ -100 F	C	
05/08/91	3 hrs @ 690 F	O	
05/09/91	1 hr @ -100 F	C	


## MRC Fabrication/Conditioning/Test Form 91-1

Page 5

Set-Sample: 26A - 9607      Comments: A516 Steel

Materials: MAZRB

Equip Definitions:



Date	Action	Equip	Results/Comments
05/09/91	87 hrs @ 124 F	H	
05/13/91	1 hr @ -100 F	C	
05/13/91	2 hrs @ 650 F	O	
05/15/91	1 hr @ -100 F	C	
05/15/91	1 hr @ 600 F	C	
05/16/91	1 hr @ -100 F	C	
05/17/91	1 hr @ -100 F	C	
05/17/91	1 hr @ 600 F	C	
05/17/91	20 hrs @ 120 F	H	
05/18/91	46 hrs @ 120-140 F	H	
05/21/91	1 hr @ -100 F	C	
05/22/91	3 hrs @ 650 F	O	
05/24/91	4 hrs @ 680 F	O	
05/28/91	5 hrs @ 650 F	O	
05/28/91	16 hrs @ 120 F	O	
05/29/91	4 hrs @ 650 F	O	
05/29/91	1 hr @ -100 F	C	
05/30/91	1 hr @ -100 F	C	
05/30/91	3 hrs @ 630 F	O	
05/30/91	17 hrs @ 120 F	H	
05/31/91	1 hr @ -100 F	C	


## MRC Fabrication/Conditioning/Test Form 91-1

Page 6

Set-Sample: 26A - 9607    Comments:    Steel

Materials: MAZRB

Equip Definitions:



Date	Action	Equip	Results/Comments
06/03/91	3 hrs @ 650 F	O	
06/03/91	22 hrs @ 140 F	H	
06/04/91	66 hrs @ 120 F	H	
06/12/91	5 hrs @ 600 F	O	
06/13/91	4 hrs @ 600 F	O	
06/13/91	1 hr @ -120 F	C	manual
06/13/91	40 hrs @ 120 F	H	
06/15/91	2 hrs @ 600 F	O	
06/17/91	2 hrs @ 650 F	O	
06/17/91	1 hr @ -100 F	C	
06/17/91	18 hrs @ 120 F	H	
06/18/91	5 hrs @ 650 F	O	0.5-0.7 mils
06/20/91	Pictures	101 events (-150 to 790 F)	Excellent Condition
07/08/91	Test (Location 4)	A	950 PSI (100% C) 0.5% F

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26A - 9608 Comments: MAZRB

mils

0.45

1

4

Materials: MARB with Zinc and Aluminum

0.45

3

Equip Definitions:

0.37

2

Date	Action	Equip	Results/Comments
03/24/91	MEK wipe	-	Clean sander-stripper prepared panel
03/24/91	Coat	-	Brush on MAZRB
03/24/91	1 hr @ 487 F	O	Cure
03/25/91	1 hr @ -100 F	C	
03/25/91	17 hrs @ 140 F	H	
03/26/91	1 hr @ -100 F	C	
03/26/91	1 hr @ 700 F	O	Very hot, dry
03/27/91	2 hrs @ 650 F	O	
03/27/91	1 hr @ -100 F	C	
03/28/91	1 hr @ -100 F	C	
03/28/91	2 hrs @ 650 F	O	
03/29/91	Test (Location 1)	A	>1050 PSI Excellent condition 0.8 mils
03/29/91	22 hrs @ 125 F	H	
03/30/91	1 hr @ -100 F	C	
03/30/91	44 hrs @ 118 F	H	
04/01/91	1 hr @ -100 F	C	
04/01/91	2 hrs @ 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	1 hr @ -100 F	C	
04/02/91	17 hrs @ 120 F	H	1279.8 g (1279.7 g dry)
04/03/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26A - 9608 Comments: Steel

Materials: MAZRB

Equip Definitions:

1	4
	3
	2

Date	Action	Equip	Results/Comments
04/03/91	17 hrs @ 120 F	H	
04/04/91	1 hr @ -150 F	C	manual
04/04/91	2 hrs @ 650 F	O	
04/04/91	20 hrs @ 120 F	H	
04/05/91	1 hr @ -100 F	C	
04/05/91	1 hr @ 650 F	O	
04/06/91	Test (Location 2)	A	600 PSI (60% d; 40% F/C)
04/06/91	41 hrs @ 120 F	H	
04/08/91	2 hrs @ 650 F	O	
04/08/91	1 hr @ -100 F	C	
04/08/91	40 hrs @ 120 F	H	
04/10/91	1 hr @ -100 F	C	
04/10/91	2 hrs @ 650 F	O	
04/11/91	4 hrs @ 650 F	O	
04/11/91	14 hrs @ 150 F	H	
04/12/91	1 hr @ -100 F	C	
04/12/91	65 hrs @ 120 F	H	
04/15/91	1 hr @ -100 F	C	
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 26A - 9608      Comments: MAZRB

Materials: MARB-4 with ZINC

Equip Definitions:

1	4
	3
	2

Date	Action	Equip	Results/Comments
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ -100 F	C	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	
04/19/91	1 hr @ -100 F	C	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr @ -100 F	C	
04/20/91	2 hrs @ 650 F	O	
04/20/91	44 hrs @ 118 F	H	
04/22/91	1 hr @ -100 F	C	
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	1 hr @ -100 F	C	
04/23/91	3 hrs @ 780 F	O	very hot
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	1 hr @ -100 F	C	
04/24/91	4 hrs @ 650 F	O	
04/25/91	1 hr @ -100 F	C	
04/25/91	3 hrs @ 630 F	O	Event 56      some edge rusting
04/29/91	Test (Location 3)	A	>800 PSI (99% C)    some edge rust

## MRC Fabrication/Conditioning/Test Form 91-1

Page 4

Set-Sample: 26A - 9608 Comments: MAZRB

	mils		
	0.45	1	4
			3
	0.45		2
	0.37		

Materials: MARB with Zinc and Aluminum

Equip Definitions:

Date	Action	Equip	Results/Comments
04/29/91	1 hr @ -100 F	C	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	
04/30/91	1 hr @ 480 F	O	
04/30/91	1 hr @ -100 F	C	
04/30/91	17 hrs @ 118 F	H	
05/01/91	1 hr @ -100 F	C	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	
05/03/91	3 hrs @ 690 F	O	
05/03/91	64 hrs @ 120 F	H	
05/06/91	3 hrs @ 690 F	O	
05/06/91	1 hr @ -100 F	C	
05/06/91	17 hrs @ 120 F	H	
06/07/91	1 hr @ -100 F	C	
05/07/91	3 hrs @ 650 F	O	
05/07/91	15 hrs @ 120 F	H	
05/08/91	1 hr @ -100 F	C	
05/08/91	3 hrs @ 690 F	O	
05/09/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 5

Set-Sample: 26A - 9608    Comments: MAZRB

Materials: MARB-4 with ZINC

Equip Definitions:

1	5
	3
	2

Date	Action	Equip	Results/Comments
05/09/91	87 hrs @ 124 F	H	
05/13/91	1 hr @ -100 F	C	
05/13/91	2 hrs @ 650 F	O	
05/15/91	1 hr @ -100 F	C	
05/15/91	1 hr @ 600 F	C	
05/16/91	1 hr @ -100 F	C	
05/17/91	1 hr @ -100 F	C	
05/17/91	1 hr @ 600 F	C	
05/17/91	20 hrs @ 120 F	H	
05/18/91	46 hrs @ 120-140 F	H	
05/21/91	1 hr @ -100 F	C	
05/22/91	3 hrs @ 650 F	O	
05/24/91	4 hrs @ 680 F	O	
05/28/91	5 hrs @ 650 F	O	
05/28/91	16 hrs @ 120 F	O	
05/29/91	4 hrs @ 650 F	O	
05/29/91	1 hr @ -100 F	C	
05/30/91	1 hr @ -100 F	C	
05/30/91	3 hrs @ 630 F	O	
05/30/91	17 hrs @ 120 F	H	
05/31/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 6

Set-Sample: 26A - 9608    Comments: MAZRB

Materials: MARB-4 with ZINC

Equip Definitions:

1	4
	3
	2

Date	Action	Equip	Results/Comments
06/03/91	3 hrs @ 650 F	O	
06/03/91	22 hrs @ 140 F	H	
06/04/91	66 hrs @ 120 F	H	
06/12/91	5 hrs @ 600 F	O	
06/13/91	4 hrs @ 600 F	O	
06/13/91	1 hr @ -120 F	C	manual
06/13/91	40 hrs @ 120 F	H	
06/15/91	2 hrs @ 600 F	O	
06/17/91	2 hrs @ 650 F	O	
06/17/91	1 hr @ -100 F	C	
06/17/91	18 hrs @ 120 F	H	
06/18/91	5 hrs @ 650 F	O	0.6 mils
06/20/91	Pictures	101 events (-150 to 790 F)	Excellent condition, very clean
07/08/91	Test (Location 4)	A	950 PSI (100% C) 0.5% F
			Some rusting on edges and thin coated area

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 268 - 9611    Comments: MAZRB 1-4 coats

mils

0.5

Materials: MARB-4 with ZINC

-----

Equip Definitions:

0.70

4      2

0.75

5      3

-----

1.00

1

-----

Date	Action	Equip	Results/Comments
04/04/91	Clean	-	Clean sander-stripper prepared panel
04/04/91	Clean	-	No rust evident under coating/ repair
		-	formerly 9525/9512 SH
04/04/91	Clean	-	Tape remove and MEK wipe
04/04/91	Coat		(1/2 hr dry between the brush coats 1, 2, 3, and 4)
04/04/91	Dry	-	Ambient dry overnight 18 hours
04/05/91	1 hr @ 480 F (250 C)	0	slow cure
04/05/91	1 hr @ 650 F	0	
04/06/91	Test (Location 1)	A	550 PSI (100% C) (1 coat)
04/06/91	Test (Location 2)	A	>1000 PSI no failure (3 coats)
04/06/91	41 hrs @ 120 F	H	
04/08/91	2 hrs @ 650 F	0	
04/08/91	1 hr @ -100 F	C	
04/08/91	40 hrs @ 120 F	H	
04/10/91	1 hr @ -100 F	C	
04/10/91	2 hrs @ 650 F	0	
04/11/91	4 hrs @ 650 F	0	
04/11/91	14 hrs @ 150 F	H	
04/12/91	1 hr @ -100 F	C	
04/12/91	65 hrs @ 120 F	H	
04/15/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 268 - 9611    Comments:

Materials: MAZRB 1-4 coats

Equip Definitions:

Date	Action	Equip	Results/Comments
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ -100 F	C	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	
04/19/91	1 hr @ -100 F	C	
04/19/91	1 hrs @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr @ -100 F	C	
04/20/91	2 hrs @ 650 F	O	
04/20/91	44 hrs @ 118 F	H	
04/22/91	1 hr @ -100 F	C	
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	1 hr @ -100 F	C	
04/23/91	3 hrs @ 780 F	O	very HOT
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	1 hr @ -100 F	C	
04/24/91	4 hrs @ 650 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 268 - 9611    Comments: MAZRB

Materials: MARB-4 with ZINC 1-4 coats

Equip Definitions:



Date	Action	Equip	Results/Comments
04/25/91	1 hr @ -100 F	C	
04/25/91	3 hrs @ 630 F	O	
04/29/91	Test (Location 3)	A	>900 PSI (90% C; 10% A) Clean, rough
04/29/91	Test (Location 4)	A	>900 PSI no failure
04/29/91	1 hr @ -100 F	C	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	
04/30/91	1 hr @ 480 F	O	
04/30/91	1 hrs @ -100 F	C	
04/30/91	17 hrs @ 118 F	H	
05/01/91	1 hr @ -100 F	C	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	
05/03/91	3 hrs @ 690 F	O	
05/03/91	64 hrs @ 120 F	H	
05/06/91	3 hrs @ 690 F	O	
05/06/91	1 hr @ -100 F	C	
05/06/91	17 hrs @ 120 F	H	
06/07/91	1 hr @ -100 F	C	
05/07/91	3 hrs @ 650 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 4

Set-Sample: 26B - 9611    Comments: MAZRB

Materials: MARB-4 with ZINC 1-4 coats

Equip Definitions:

Date	Action	Equip	Results/Comments
05/07/91	15 hrs @ 120 F	H	
05/08/91	1 hr @ -100 F	C	
05/08/91	3 hrs @ 690 F	O	
05/09/91	1 hr @ -100 F	C	
05/09/91	87 hrs @ 124 F	H	
05/13/91	1 hr @ -100 F	C	
05/13/91	2 hrs @ 650 F	O	
05/15/91	1 hr @ -100 F	C	
05/15/91	1 hr @ 600 F	C	
05/16/91	1 hr @ -100 F	C	
05/17/91	1 hr @ -100 F	C	
05/17/91	1 hr @ 600 F	C	
05/17/91	20 hrs @ 120 F	H	
05/18/91	46 hrs @ 120-140 F	H	
05/21/91	1 hr @ -100 F	C	
05/22/91	3 hrs @ 650 F	O	
05/24/91	4 hrs @ 680 F	O	
05/28/91	5 hrs @ 650 F	O	
05/28/91	16 hrs @ 120 F	O	
05/29/91	4 hrs @ 650 F	O	
05/29/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 5

Set-Sample: 268 - 9611      Comments: MAZRB

Materials: MARB-4 with ZINC 1-4 coats

Equip Definitions:

Date	Action	Equip	Results/Comments
05/30/91	1 hr @ -100 F	C	
05/30/91	3 hrs @ 630 F	O	
05/30/91	17 hrs @ 120 F	H	
05/31/91	1 hr @ -100 F	C	
06/03/91	3 hrs @ 650 F	O	
06/03/91	22 hrs @ 140 F	H	
06/04/91	66 hrs @ 120 F	H	
06/12/91	5 hrs @ 600 F	O	
06/13/91	4 hrs @ 600 F	O	
06/13/91	1 hr @ -120 F	C	manual
06/13/91	40 hrs @ 120 F	H	
06/15/91	2 hrs @ 600 F	O	
06/17/91	2 hrs @ 650 F	O	
06/17/91	1 hr @ -100 F	C	
06/17/91	18 hrs @ 120 F	H	
06/18/91	5 hrs @ 650 F	O	
06/20/91	Pictures      88 events (-120 to 790 F)		Excellent condition
07/08/91	Test (Location 5)	A	250 PSI (85% C; 15% C/I) No rust

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26B - 9612    Comments: MAZRB 1-4 coats

mils

0.5

4

Materials: MARB-4 with ZINC

0.70

1

Equip Definitions:

0.75

2

-----

5

-----

3

Date	Action	Equip	Results/Comments
04/04/91	Clean	-	Clean sander-stripper prepared panel
04/04/91	Clean	-	No rust evident under coating/ repair formerly 9525/9512 SH
04/04/91	Clean	-	Tape remove and MEK wipe
04/04/91	Coat		(1/2 hr dry between the brush coats 1, 2, 3, and 4)
04/04/91	Dry	-	Ambient dry overnight 18 hours
04/05/91	1 hr @ 480 F (250 C)	0	slow cure
04/05/91	1 hr @ 650 F	0	
04/06/91	Test (Location 1)	A	550 PSI (100% C) (2 coats)
04/06/91	Test (Location 2)	A	>1000 PSI no failure (3 coats)
04/06/91	41 hrs @ 120 F	H	
04/08/91	2 hrs @ 650 F	0	
04/08/91	1 hr @ -100 F	C	
04/08/91	40 hrs @ 120 F	H	
04/10/91	1 hr @ -100 F	C	
04/10/91	2 hrs @ 650 F	0	
04/11/91	4 hrs @ 650 F	0	
04/11/91	14 hrs @ 150 F	H	
04/12/91	1 hr @ -100 F	C	
04/12/91	65 hrs @ 120 F	H	
04/15/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26B - 9612      Comments:

Materials: MAZRB with Zinc

Equip Definitions:

Date	Action	Equip	Results/Comments
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ -100 F	C	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	
04/19/91	1 hr @ -100 F	C	
04/19/91	1 hrs @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr @ -100 F	C	
04/20/91	2 hrs @ 650 F	O	
04/20/91	44 hrs @ 118 F	H	
04/22/91	1 hr @ -100 F	C	
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	1 hr @ -100 F	C	
04/23/91	3 hrs @ 780 F	O	very HOT
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	1 hr @ -100 F	C	
04/24/91	4 hrs @ 650 F	O	


## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 26B - 9612    Comments: MAZRB

Materials: MARB-4 with ZINC

Equip Definitions:



Date	Action	Equip	Results/Comments
04/25/91	1 hr @ -100 F	C	
04/25/91	3 hrs @ 630 F	O	
04/29/91	Test (Location 3)	A	>900 PSI (90% C; 10% A) Clean, rough
04/29/91	Test (Location 4)	A	>900 PSI no failure
04/29/91	1 hr @ -100 F	C	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	
04/30/91	1 hr @ 480 F	O	
04/30/91	1 hrs @ -100 F	C	
04/30/91	17 hrs @ 118 F	H	
05/01/91	1 hr @ -100 F	C	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	
05/03/91	3 hrs @ 690 F	O	
05/03/91	64 hrs @ 120 F	H	
05/06/91	3 hrs @ 690 F	O	
05/06/91	1 hr @ -100 F	C	
05/06/91	17 hrs @ 120 F	H	
06/07/91	1 hr @ -100 F	C	
05/07/91	3 hrs @ 650 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 4

Set-Sample: 26B - 9612    Comments: MAZRB

Materials: MARB-4 with ZINC

Equip Definitions:

Date	Action	Equip	Results/Comments
05/07/91	15 hrs @ 120 F	H	
05/08/91	1 hr @ -100 F	C	
05/08/91	3 hrs @ 690 F	O	
05/09/91	1 hr @ -100 F	C	
05/09/91	87 hrs @ 124 F	H	
05/13/91	1 hr @ -100 F	C	
05/13/91	2 hrs @ 650 F	O	
05/15/91	1 hr @ -100 F	C	
05/15/91	1 hr @ 600 F	C	
05/16/91	1 hr @ -100 F	C	
05/17/91	1 hr @ -100 F	C	
05/17/91	1 hr @ 600 F	C	
05/17/91	20 hrs @ 120 F	H	
05/18/91	46 hrs @ 120-140 F	H	
05/21/91	1 hr @ -100 F	C	
05/22/91	3 hrs @ 650 F	O	
05/24/91	4 hrs @ 680 F	O	
05/28/91	5 hrs @ 650 F	O	
05/28/91	16 hrs @ 120 F	O	
05/29/91	4 hrs @ 650 F	O	
05/29/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 5

Set-Sample: 268 - 9612    Comments: MAZRB

Materials: MARB-4 with ZINC

## Equip Definitions:

Date	Action	Equip	Results/Comments
05/30/91	1 hr @ -100 F	C	
05/30/91	3 hrs @ 630 F	O	
05/30/91	17 hrs @ 120 F	H	
05/31/91	1 hr @ -100 F	C	
06/03/91	3 hrs @ 650 F	O	
06/03/91	22 hrs @ 140 F	H	
06/04/91	66 hrs @ 120 F	H	
06/12/91	5 hrs @ 600 F	O	
06/13/91	4 hrs @ 600 F	O	
06/13/91	1 hr @ -120 F	C	manual
06/13/91	40 hs @ 120 F	H	
06/15/91	2 hrs @ 600 F	O	
06/17/91	2 hrs @ 650 F	O	
06/17/91	1 hr @ -100 F	C	
06/17/91	18 hrs @ 120 F	H	
06/18/91	5 hrs @ 650 F	O	
06/20/91	Pictures	88 events (-120 to 790 F)	Excellent condition
07/08/91	Test (Location 5)	A	300 PSI (90% C; 8% C; 2% Rust)

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26B - 9613    Comments: MAZRB 1-4 coats

mils

0.5

1

Materials: MARB-4 with ZINC

0.70

2

5

Equip Definitions:

0.75

3

1.00

4

Date	Action	Equip	Results/Comments
04/04/91	Clean	-	Clean sander-stripper prepared panel
04/04/91	Clean	-	No rust evident under coating/ repair
		-	formerly 9525/9512 SH
04/04/91	Clean	-	Tape remove and MEK wipe
04/04/91	Coat		(1/2 hr dry between the brush coats 1, 2, 3, and 4)
04/04/91	Dry	-	Ambient dry overnight 18 hours
04/05/91	1 hr @ 480 F (250 C)	0	slow cure
04/05/91	1 hr @ 650 F	0	
04/06/91	Test (Location 1)	A	550 PSI (100% C) (1 coats)
04/06/91	Test (Location 2)	A	>1000 PSI no failure (2 coats)
04/06/91	41 hrs @ 120 F	H	
04/08/91	2 hrs @ 650 F	0	
04/08/91	1 hr @ -100 F	C	
04/08/91	40 hrs @ 120 F	H	
04/10/91	1 hr @ -100 F	C	
04/10/91	2 hrs @ 650 F	0	
04/11/91	4 hrs @ 650 F	0	
04/11/91	14 hrs @ 150 F	H	
04/12/91	1 hr @ -100 F	C	
04/12/91	65 hrs @ 120 F	H	
04/15/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 268 - 9613    Comments:

Materials: MAZRB 1-4 coats

Equip Definitions:



Date	Action	Equip	Results/Comments
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ -100 F	C	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	
04/19/91	1 hr @ -100 F	C	
04/19/91	1 hrs @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr @ -100 F	C	
04/20/91	2 hrs @ 650 F	O	
04/20/91	44 hrs @ 118 F	H	
04/22/91	1 hr @ -100 F	C	
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	1 hr @ -100 F	C	
04/23/91	3 hrs @ 780 F	O	very HOT
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	1 hr @ -100 F	C	
04/24/91	4 hrs @ 650 F	O	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 3

Set-Sample: 268 - 9613      Comments: MAZRB

Materials: MARB-4 with ZINC 1-4 coats

Equip Definitions:

3
4

Date	Action	Equip	Results/Comments	
04/25/91	1 hr @ -100 F	C		
04/25/91	3 hrs @ 630 F	O		
04/29/91	Test (Location 3)	A	>900 PSI (90% C; 10% A)	Clean, rough
04/29/91	Test (Location 4)	A	>900 PSI no failure	4 coats
04/29/91	1 hr @ -100 F	C		
04/29/91	3 hrs @ 650 F	O		
04/29/91	16 hrs @ 118 F	H		
04/30/91	1 hr @ 480 F	O		
04/30/91	1 hrs @ -100 F	C		
04/30/91	17 hrs @ 118 F	H		
05/01/91	1 hr @ -100 F	C		
05/01/91	3 hrs @ 790 F	O	HOT	
05/02/91	3 hrs @ 750 F	O	HOT	
05/02/91	18 hrs @ 117 F	H		
05/03/91	3 hrs @ 690 F	O		
05/03/91	64 hrs @ 120 F	H		
05/06/91	3 hrs @ 690 F	O		
05/06/91	1 hr @ -100 F	C		
05/06/91	17 hrs @ 120 F	H		
06/07/91	1 hr @ -100 F	C		
05/07/91	3 hrs @ 650 F	O		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 4

Set-Sample: 26B - 9613    Comments: MAZRB

Materials: MARB-4 with ZINC 1-4 coats

Equip Definitions:

Date	Action	Equip	Results/Comments
05/07/91	15 hrs @ 120 F	H	
05/08/91	1 hr @ -100 F	C	
05/08/91	3 hrs @ 690 F	O	
05/09/91	1 hr @ -100 F	C	
05/09/91	87 hrs @ 124 F	H	
05/13/91	1 hr @ -100 F	C	
05/13/91	2 hrs @ 650 F	O	
05/15/91	1 hr @ -100 F	C	
05/15/91	1 hr @ 600 F	C	
05/16/91	1 hr @ -100 F	C	
05/17/91	1 hr @ -100 F	C	
05/17/91	1 hr @ 600 F	C	
05/17/91	20 hrs @ 120 F	H	
05/18/91	46 hrs @ 120-140 F	H	
05/21/91	1 hr @ -100 F	C	
05/22/91	3 hrs @ 650 F	O	
05/24/91	4 hrs @ 680 F	O	
05/28/91	5 hrs @ 650 F	O	
05/28/91	16 hrs @ 120 F	O	
05/29/91	4 hrs @ 650 F	O	
05/29/91	1 hr @ -100 F	C	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 5

Set-Sample: 26B - 9613    Comments: MAZRB

Materials: MARB-4 with ZINC 1-4 coats

Equip Definitions:

	1
2	5
	3
	4

Date	Action	Equip	Results/Comments
05/30/91	1 hr @ -100 F	C	
05/30/91	3 hrs @ 630 F	O	
05/30/91	17 hrs @ 120 F	H	
05/31/91	1 hr @ -100 F	C	
06/03/91	3 hrs @ 650 F	O	
06/03/91	22 hrs @ 140 F	H	
06/04/91	66 hrs @ 120 F	H	
06/12/91	5 hrs @ 600 F	O	
06/13/91	4 hrs @ 600 F	O	
06/13/91	1 hr @ -120 F	C	manual
06/13/91	40 hrs @ 120 F	H	
06/15/91	2 hrs @ 600 F	O	
06/17/91	2 hrs @ 650 F	O	
06/17/91	1 hr @ -100 F	C	
06/17/91	18 hrs @ 120 F	H	
06/18/91	5 hrs @ 650 F	O	
06/20/91	Pictures	88 events (-120 to 790 F)	Excellent condition
07/08/91	Test (Location 5)	A	550 PSI (90% C/I; 8% C; 2% rust) 2 coats

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26R - 9621 Comments: A-203 steel Rusting

Materials: No coating - for rusting and gel temperature tests

Equip Definitions:



Date	Action	Equip	Results/Comments
03/25/91	MEK wash	-	Removes grease from mill-scale
03/25/91	Aqua regia clean	-	Acid remove mill scale both sides 100%
04/04/91	20 hrs @ 120 F	H	
04/05/91	65 hrs @ 120 F	H	
04/08/91	2 hrs @ 650 F	O	
04/08/91	1 hr @ -100 F	C	
04/08/91	40 hrs @ 120 F	H	
04/10/91	1 hr @ -100 F	C	
04/10/91	2 hrs @ 650 F	O	
04/11/91	4 hrs @ 650 F	O	HOT
04/11/91	14 hrs @ 150 F	H	
04/12/91	1 hr @ -100 F	C	
04/12/91	65 hrs @ 120 F	H	
04/15/91	1 hr @ -100 F	C	
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ 750 F	O	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	


## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26R - 9621 Comments: A-203 steel Rusting

Materials:

Equip Definitions:



Date	Action	Equip	Results/Comments
04/19/91	2 hr @ 700 F	O	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr 700 F	O	
04/20/91	2 hrs @ 650 F	O	24 events
04/20/91	44 hrs @ 118 F	H	
04/22/91	1 hr @ 790 F	O	very hot
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	3 hrs @ 780 F	O	very hot
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	4 hrs @ 650 F	O	
04/25/91	3 hrs @ 630 F	O	32 events
04/29/91	2 hrs @ 250 F	O	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	wet panels before exposure
04/30/91	1 hr @ 480 F	O	
04/30/91	17 hrs @ 118 F	H	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	

Set-Sample: 26R - 9621      Comments: A-203 rusting      Page 3

Date	Action	Equip	Results/comments
05/03/91	3 hrs @ 690 F	O	
05/03/91	64 hrs 120 F	H	
05/06/91	3 hrs @ 690 F	O	
05/06/91	17 hrs @ 120 F	H	44 events (-100 to 790 F) moderate rust
06/05/91	Cut into 9 pieces (2x2) for gel temperature tests		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26R - 9622    Comments: A-203 steel Rusting

Materials: No coating - for rusting and gel cleaning

## Equip Definitions:



Date	Action	Equip	Results/Comments
03/25/91	MEK wash	-	Removes grease from mill-scale
03/25/91	Aqua regia clean	-	Acid remove mill scale both sides 100%
04/04/91	20 hrs @ 120 F	H	
04/05/91	65 hrs @ 120 F	H	
04/08/91	2 hrs @ 650 F	O	
04/08/91	1 hr @ -100 F	C	
04/08/91	40 hrs @ 120 F	H	
04/10/91	1 hr @ -100 F	C	
04/10/91	2 hrs @ 650 F	O	
04/11/91	4 hrs @ 650 F	O	HOT
04/11/91	14 hrs @ 150 F	H	
04/12/91	1 hr @ -100 F	C	
04/12/91	65 hrs @ 120 F	H	
04/15/91	1 hr @ -100 F	C	
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ 750 F	O	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26R - 9622    Comments: A-203 steel Rusting

## Materials:

## Equip Definitions:

Date	Action	Equip	Results/Comments
04/19/91	2 hr @ 700 F	O	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr 790 F	O	
04/20/91	2 hrs @ 650 F	O	24 events
04/20/91	44 hrs @ 118 F	H	
04/22/91	1 hr @ 790 F	O	very hot
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	3 hrs @ 780 F	O	very hot
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	4 hrs @ 650 F	O	
04/25/91	3 hrs @ 630 F	O	32 events
04/29/91	2 hrs @ 250 F	O	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	wet panels before exposure
04/30/91	1 hr @ 480 F	O	
04/30/91	17 hrs @ 118 F	H	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	

Set-Sample: 26R - 9622      Comments: A-203 rusting      Page 3

Date	Action	Equip	Results/comments
05/03/91	3 hrs @ 690 F	O	
05/03/91	64 hrs 120 F	H	
05/06/91	3 hrs @ 690 F	O	
05/06/91	17 hrs @ 120 F	H	44 events (-100 to 790 F) moderate rust
06/05/91	Cut into 9 pieces (2x2) for gel temperature tests		


## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26R - 9623    Comments: A-203 steel Rusting

Materials: No coating

Equip Definitions:



Date	Action	Equip	Results/Comments
03/25/91	MEK wash	-	Removes grease from mill-scale
03/25/91	Aqua regia clean	-	Acid remove mill scale both sides 100%
04/04/91	20 hrs @ 120 F	H	
04/05/91	65 hrs @ 120 F	H	
04/08/91	2 hrs @ 650 F	O	
04/08/91	1 hr @ -100 F	C	
04/08/91	40 hrs @ 120 F	H	
04/10/91	1 hr @ -100 F	C	
04/10/91	2 hrs @ 650 F	O	
04/11/91	4 hrs @ 650 F	O	HOT
04/11/91	14 hrs @ 150 F	H	
04/12/91	1 hr @ -100 F	C	
04/12/91	65 hrs @ 120 F	H	
04/15/91	1 hr @ -100 F	C	
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ 750 F	O	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	


## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26R - 9623    Comments: A-203 steel Rusting

Materials:

Equip Definitions:



Date	Action	Equip	Results/Comments
04/19/91	2 hr @ 700 F	O	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr 700 F	O	
04/20/91	2 hrs @ 650 F	O	24 events
04/20/91	44 hrs @ 118 F	H	
04/22/91	1 hr @ 790 F	O	very hot
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	3 hrs @ 780 F	O	very hot
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	4 hrs @ 650 F	O	
04/25/91	3 hrs @ 630 F	O	32 events
04/29/91	2 hrs @ 250 F	O	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	wet panels before exposure
04/30/91	1 hr @ 480 F	O	
04/30/91	17 hrs @ 118 F	H	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
5/02/91	18 hrs @ 117 F	H	

Set-Sample: 26R - 9621      Comments: A-203 rusting      Page 3

Date	Action	Equip	Results/comments
05/03/91	3 hrs @ 690 F	O	
05/03/91	64 hrs 120 F	H	
05/06/91	3 hrs @ 690 F	O	
05/06/91	17 hrs @ 120 F	H	44 events (-100 to 790 F) moderate rust
06/05/91	Cut into 9 pieces (2x2) for gel temperature tests		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26R - 9624    Comments: A-203 steel Rusting

Materials: No coating

Equip Definitions:



Date	Action	Equip	Results/Comments
03/25/91	MEK wash	-	Removes grease from mill-scale
03/25/91	Aqua regia clean	-	Acid remove mill scale both sides 100%
04/04/91	20 hrs @ 120 F	H	
04/05/91	65 hrs @ 120 F	H	
04/08/91	2 hrs @ 650 F	O	
04/08/91	1 hr @ -100 F	C	
04/08/91	40 hrs @ 120 F	H	
04/10/91	1 hr @ -100 F	C	
04/10/91	2 hrs @ 650 F	O	
04/11/91	4 hrs @ 650 F	O	HOT
04/11/91	14 hrs @ 150 F	H	
04/12/91	1 hr @ -100 F	C	
04/12/91	65 hrs @ 120 F	H	
04/15/91	1 hr @ -100 F	C	
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ 750 F	O	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26R - 9624    Comments: A-203 steel Rusting

## Materials:

## Equip Definitions:

Date	Action	Equip	Results/Comments
04/19/91	2 hr @ 700 F	O	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr 700 F	O	
04/20/91	2 hrs @ 650 F	O	24 events
04/20/91	44 hrs @ 118 F	H	
04/22/91	1 hr @ 790 F	O	very hot
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	3 hrs @ 780 F	O	very hot
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	4 hrs @ 650 F	O	
04/25/91	3 hrs @ 630 F	O	32 events
04/29/91	2 hrs @ 250 F	O	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	wet panels before exposure
04/30/91	1 hr @ 480 F	O	
04/30/91	17 hrs @ 118 F	H	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	



Set-Sample: 26R - 9624

Comments: A-203 rusting

Page 3

Date	Action	Equip	Results/comments
05/03/91	3 hrs @ 690 F	O	
05/03/91	64 hrs 120 F	H	
05/06/91	3 hrs @ 690 F	O	
05/06/91	17 hrs @ 120 F	H	44 events (-100 to 790 F) moderate rust
06/05/91	Cut into 9 pieces (2x2) for gel temperature tests		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26R - 9625 Comments: A-203 steel Rusting

Materials: No coating

Equip Definitions:

Date	Action	Equip	Results/Comments
03/25/91	MEK wash	-	Removes grease from mill-scale
03/25/91	Aqua regia clean	-	Acid remove mill scale both sides 100%
04/04/91	20 hrs @ 120 F	H	
04/05/91	65 hrs @ 120 F	H	
04/08/91	2 hrs @ 650 F	O	
04/08/91	1 hr @ -100 F	C	
04/08/91	40 hrs @ 120 F	H	
04/10/91	1 hr @ -100 F	C	
04/10/91	2 hrs @ 650 F	O	
04/11/91	4 hrs @ 650 F	O	HOT
04/11/91	14 hrs @ 150 F	H	
04/12/91	1 hr @ -100 F	C	
04/12/91	65 hrs @ 120 F	H	
04/15/91	1 hr @ -100 F	C	
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ 750 F	O	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26R - 9625    Comments: A-203 steel Rusting

Materials:

Equip Definitions:

Date	Action	Equip	Results/Comments
04/19/91	2 hr @ 700 F	O	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr 700 F	O	
04/20/91	2 hrs @ 650 F	O	24 events
04/20/91	44 hrs @ 118 F	H	
04/22/91	1 hr @ 790 F	O	very hot
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	3 hrs @ 780 F	O	very hot
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	4 hrs @ 650 F	O	
04/25/91	3 hrs @ 630 F	O	32 events
04/29/91	2 hrs @ 250 F	O	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	wet panels before exposure
04/30/91	1 hr @ 480 F	O	
04/30/91	17 hrs @ 118 F	H	
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	

Set-Sample: 26R - 9625      Comments: A-203 rusting      Page 3

Date	Action	Equip	Results/comments
05/03/91	3 hrs @ 690 F	O	
05/03/91	64 hrs 120 F	H	
05/06/91	3 hrs @ 690 F	O	
05/06/91	17 hrs @ 120 F	H	44 events (-100 to 790 F) moderate rust
06/05/91	Cut into 9 pieces (2x2) for gel temperature tests		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 26R - 9626 Comments: A-203 steel Rusting

Materials: No coating

Equip Definitions:



Date	Action	Equip	Results/Comments
03/25/91	MEK wash	-	Removes grease from mill-scale
03/25/91	Aqua regia clean	-	Acid remove mill scale both sides 100%
04/04/91	20 hrs @ 120 F	H	
04/05/91	65 hrs @ 120 F	H	
04/08/91	2 hrs @ 650 F	O	
04/08/91	1 hr @ -100 F	C	
04/08/91	40 hrs @ 120 F	H	
04/10/91	1 hr @ -100 F	C	
04/10/91	2 hrs @ 650 F	O	
04/11/91	4 hrs @ 650 F	O	HOT
04/11/91	14 hrs @ 150 F	H	
04/12/91	1 hr @ -100 F	C	
04/12/91	65 hrs @ 120 F	H	
04/15/91	1 hr @ -100 F	C	
04/15/91	40 hrs @ 115 F	H	
04/17/91	1 hr @ -100 F	C	
04/17/91	2 hrs @ 650 F	O	
04/17/91	14 hrs @ 115 F	H	
04/18/91	1 hr @ 750 F	O	
04/18/91	2 hrs @ 650 F	O	
04/18/91	17 hrs @ 120 F	H	


## MRC Fabrication/Conditioning/Test Form 91-1

Page 2

Set-Sample: 26R - 9626    Comments: A-203 steel Rusting

## Materials:

## Equip Definitions:



Date	Action	Equip	Results/Comments
04/19/91	2 hr @ 700 F	O	
04/19/91	1 hr @ 620 F	O	
04/19/91	18 hrs @ 120 F	H	
04/20/91	1 hr 700 F	O	
04/20/91	2 hrs @ 650 F	O	24 events
04/20/91	44 hrs @ 118 F	H	
04/22/91	1 hr @ 790 F	O	very hot
04/22/91	1 hr @ 650 F	O	
04/22/91	15 hrs @ 115 F	H	
04/23/91	3 hrs @ 780 F	O	very hot
04/23/91	17 hrs @ 118 F	H	very humid
04/24/91	1 hrs @ 650 F	O	
04/25/91	3 hrs @ 630 F	O	32 events
04/29/91	2 hrs @ 250 F	O	
04/29/91	3 hrs @ 650 F	O	
04/29/91	16 hrs @ 118 F	H	wet panels before exposure
04/30/91	1 hr @ 480 F	O	
04/30/91	Gel Cleaning	-	1/3 panel mostly cleaned in 2 hrs
05/01/91	3 hrs @ 790 F	O	HOT
05/02/91	3 hrs @ 750 F	O	HOT
05/02/91	18 hrs @ 117 F	H	

Set-Sample: 26R - 9626      Comments: A-203 rusting      Page 3

Date	Action	Equip	Results/comments
05/03/91	3 hrs @ 690 F	O	
05/03/91	64 hrs 120 F	H	
05/06/91	3 hrs @ 690 F	O	
05/06/91	17 hrs @ 120 F	H	44 events (-100 to 790 F) moderate rust
06/05/91	Cut into 9 pieces (2x2) for gel temperature tests		


## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 27 - 9701 Comments: A-203 steel

## Materials:

## Equip Definitions:



Date	Action	Equip	Results/Comments	L	R
03/25/91	MEK wash	-	Removes grease from mill-scale		
03/25/91	17 hrs @ 140 F	H	Rusting Panels		
03/26/91	23 hrs @ 140 F	H			
03/27/91	2 hrs @ 650 F	O			
03/27/91	17 hrs @ 138 F	H			
03/28/91	2 hrs @ 650 F	O			
03/28/91	21 hrs @ 120 F	H			
03/29/91	20 hrs @ 120 F	H			
03/30/91	44 hrs @ 118 F	H			
04/01/91	2 hrs @ 700 F	O	HOT		
04/01/91	2 hrs 650 F	O			
04/01/91	20 hrs @ 120 F	H			
04/02/91	2 hrs @ 750 F	O	HOT	1210.8 g	12 events
PANEL SENT TO INGERSOLL-RAND					
05/14/91	See pictures			1208.9 g returned	
	R (center)	40 ipm	35,000 PSI	Some mill-scale flakes remaining	
	L	40 ipm	47,000 PSI	Some mill-scale flakes remaining	

## MRC Fabrication/Conditioning/Test Form 91-1


Page 1

Set-Sample: 27 - 9702 Comments: A-203 steel

6

Materials:

Equip Definitions:



Date	Action	Equip	Results/Comments
03/25/91	MEK wash	-	Removes grease from mill-scale
03/25/91	17 hrs @ 140 F	H	Rusting Panels
03/26/91	23 hrs @ 140 F	H	
03/27/91	2 hrs @ 650 F	O	
03/27/91	17 hrs @ 138 F	H	
03/28/91	2 hrs @ 650 F	O	
03/28/91	21 hrs @ 120 F	H	
03/29/91	20 hrs @ 120 F	H	
03/30/91	44 hrs @ 118 F	H	
04/01/91	2 hrs @ 700 F	O	HOT
04/01/91	2 hrs 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	2 hrs @ 750 F	O	HOT 1254.7 g 12 events
<hr/> PANEL SENT TO INGERSOLL-RAND <hr/>			
05/14/91	See pictures		1252.7 g returned
	R (Center)	60 ipm	47,000 PSI mill-scale removed
	L	60 ipm	35,000 PSI some scale removed


## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 27 - 9703 Comments: A-203 steel

8

Materials:



Equip Definitions:

Date	Action	Equip	Results/Comments
03/25/91	MEK wash	-	Removes grease from mill-scale
03/25/91	17 hrs @ 140 F	H	Rusting Panels
03/26/91	23 hrs @ 140 F	H	
03/27/91	2 hrs @ 650 F	O	
03/27/91	17 hrs @ 138 F	H	
03/28/91	2 hrs @ 650 F	O	
03/28/91	21 hrs @ 120 F	H	
03/29/91	20 hrs @ 120 F	H	
03/30/91	44 hrs @ 118 F	H	
04/01/91	2 hrs @ 700 F	O	HOT
04/01/91	2 hrs 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	2 hrs @ 750 F	O	HOT 1221.6 g 12 events

PANEL SENT TO INGERSOLL-RAND

05/14/91	See pictures	1218.8 g
front	7 top	40 ipm 47,000 PSI
	center	40 ipm 35,000 PSI
backside	8 upper	20 ipm 47,000 PSI Some scale removed
	bottom	40 ipm 47,000 PSI Some scale removed

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 27 - 9711 Comments: A-203 steel

Materials:

Equip Definitions:

Date	Action	Equip	Results/Comments
03/25/91	Gel cleaned 1 hr	-	Removes rust from mill-scale each side
03/25/91	17 hrs @ 140 F	H	Rusting Panels
03/26/91	2 hrs @ 650 F	O	
03/26/91	19 hrs @ 140 F	H	
03/27/91	2 hrs @ 650 F	O	
03/27/91	17 hrs @ 138 F	H	
03/28/91	2 hrs @ 650 F	O	
03/28/91	21 hrs @ 120 F	H	
03/29/91	20 hrs @ 120 F	H	
03/30/91	44 hrs @ 118 F	H	
04/01/91	2 hrs @ 700 F	O	HOT
04/01/91	2 hrs 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	2 hrs @ 750 F	O	HOT 1213.7 g 12 events
05/26/91	All rust removed at I-R		

## CONCLUSIONS:

Only partial removal of mill-scale is accomplished at 35,000 PSI. Even at 47,000 PSI the mill-scale is not completely removed at speeds above 20 ipm. Speeds above 40 ipm leave rough grey colored marks. 40 ipm with 48,000 PSI is the best choice to clean off heavy rust (no mill-scale) as well as MARB coating removal.

No variations in orifice diameter or R.P.M. were done.

**MRC Fabrication/Conditioning/Test Form 91-1**

Page 1

Set-Sample: 27 - 9712 Comments: A-203 steel

## **Materials:**

## **Equip Definitions:**

Date	Action	Equip	Results/Comments
03/25/91	Gel cleaned 1 hr	-	Removes rust from mill-scale each side
03/25/91	17 hrs @ 140 F	H	Rusting Panels
03/26/91	2 hrs @ 650 F	O	
03/26/91	19 hrs @ 140 F	H	
03/27/91	2 hrs @ 650 F	O	
03/27/91	17 hrs @ 138 F	H	
03/28/91	2 hrs @ 650 F	O	
03/28/91	21 hrs @ 120 F	H	
03/29/91	20 hrs @ 120 F	H	
03/30/91	44 hrs @ 118 F	H	
04/01/91	2 hrs @ 700 F	O	HOT
04/01/91	2 hrs 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	2 hrs @ 750 F	O	HOT 1234.2 g 12 events
PANEL SENT TO INGERSOLL-RAND			
05/16/91	All rust removed at I-R		


## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 27 - 9713    Comments: A-203 steel

Materials:

Equip Definitions:



Date	Action	Equip	Results/Comments
03/25/91	Gel cleaned 1 hr	-	Removes rust from mill-scale each side
03/25/91	17 hrs @ 140 F	H	Rusting Panels
03/26/91	2 hrs @ 650 F	O	
03/26/91	19 hrs @ 140 F	H	
03/27/91	2 hrs @ 650 F	O	
03/27/91	17 hrs @ 138 F	H	
03/28/91	2 hrs @ 650 F	O	
03/28/91	21 hrs @ 120 F	H	
03/29/91	20 hrs @ 120 F	H	
03/30/91	44 hrs @ 118 F	H	
04/01/91	2 hrs @ 700 F	O	HOT
04/01/91	2 hrs 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	2 hrs @ 750 F	O	HOT              1254.6 g 12 events
PANEL SENT TO INGERSOLL-RAND			
05/16/91	All rust removed at I-R		

## MRC Fabrication/Conditioning/Test Form 91-1


Page 1

Set-Sample: 27 - 9721 Comments: A203 Steel

2

Materials:

Equip Definitions:



Date	Action	Equip	Results/Comments
03/22/91	Acid clean	-	Aqua regia clean to remove mill-scale
03/25/91	17 hrs @ 140 F	H	Rusting Panels
03/26/91	23 hrs @ 140 F	H	
03/27/91	2 hrs @ 650 F	O	
03/27/91	17 hrs @ 138 F	H	
03/28/91	2 hrs @ 650 F	O	
03/28/91	21 hrs @ 120 F	H	
03/29/91	20 hrs @ 120 F	H	
03/30/91	44 hrs @ 118 F	H	
04/01/91	2 hrs @ 700 F	O	HOT
04/01/91	2 hrs 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	2 hrs @ 750 F	O	HOT 1251.0 g 12 events
PANEL SENT TO INGERSOLL-RAND			
05/14/91	See pictures		1250.8 g
	Center	60 ipm	47,000 PSI
	Bottom	60 ipm	35,000 PSI
05/20/91	Gel cleaned for MARB ambient hardness tests (Set 28)		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 27 - 9722 Comments: A203 Steel

3

Materials:

Equip Definitions:

Date	Action	Equip	Results/Comments
03/22/91	Acid clean	-	Aqua regia clean to remove mill-scale
03/25/91	17 hrs @ 140 F	H	Rusting Panels
03/26/91	23 hrs @ 140 F	H	
03/27/91	2 hrs @ 650 F	O	
03/27/91	17 hrs @ 138 F	H	
03/28/91	2 hrs @ 650 F	O	
03/28/91	21 hrs @ 120 F	H	
03/29/91	20 hrs @ 120 F	H	
03/30/91	44 hrs @ 118 F	H	
04/01/91	2 hrs @ 700 F	O	HOT
04/01/91	2 hrs 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	2 hrs @ 750 F	O	HOT 1246.7 g 12 events
PANEL SENT TO INGERSOLL-RAND			
05/14/91	See pictures		1246.3 g
	Upper 40 ipm	35,000 PSI	
	Bottom 40 ipm	47,000 PSI	Best rust cleaning
05/20/91	Gel cleaned for MARB ambient hardness tests (Set 28)		

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 27 - 9723 Comments: A203 Steel

4

Materials:

Equip Definitions:

777	0
-----	-----
-----	-----
-----	-----

Date	Action	Equip	Results/Comments
03/22/91	Acid clean	-	Aqua regia clean to remove mill-scale
03/25/91	17 hrs @ 140 F	H	Rusting Panels
03/26/91	23 hrs @ 140 F	H	
03/27/91	2 hrs @ 650 F	O	
03/27/91	17 hrs @ 138 F	H	
03/28/91	2 hrs @ 650 F	O	
03/28/91	21 hrs @ 120 F	H	
03/29/91	20 hrs @ 120 F	H	
03/30/91	44 hrs @ 118 F	H	
04/01/91	2 hrs @ 700 F	O	HOT
04/01/91	2 hrs 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	2 hrs @ 750 F	O	HOT 1226.9 g 12 events
PANEL SENT TO INGERSOLL-RAND			
05/14/91	See pictures		1226.6 g
	upper 100 ipm	35,000 PSI	very rough marks ))))))
	bottom 100 ipm	47,000 PSI	very rough marks ))))))
05/20/91	Gel cleaned for MARB ambient hardness tests (Set 28)		

## MRC Fabrication/Conditioning/Test Form 91-1


Page 1

Set-Sample: 27 - 9731 Comments: A203 Steel

1

Materials:

Equip Definitions:



Date	Action	Equip	Results/Comments
/91	Acid clean	-	Aqua regia clean to remove mill-scale

Formerly Panel 9103

03/25/91	17 hrs @ 140 F	H	Rusting Panels
03/26/91	23 hrs @ 140 F	H	
03/27/91	2 hrs @ 650 F	O	
03/27/91	17 hrs @ 138 F	H	
03/28/91	2 hrs @ 650 F	O	
03/28/91	21 hrs @ 120 F	H	
03/29/91	20 hrs @ 120 F	H	
03/30/91	44 hrs @ 118 F	H	
04/01/91	2 hrs @ 700 F	O	HOT
04/01/91	2 hrs 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	2 hrs @ 750 F	O	HOT 1192.4 g 12 events
PANEL SENT TO INGERSOLL-RAND			1191.9 g returned
upper	40 ipm	47,000 PSI	Best MARB removal
center	40 ipm	35,000 PSI	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 27 - 9733 Comments: A203 Steel

Materials:

Equip Definitions:



Date	Action	Equip	Results/Comments
03/22/91	Acid clean	-	Aqua regia clean to remove mill-scale
<hr/> <hr/> <hr/>			
Formerly panel 9401			
<hr/> <hr/> <hr/>			
03/25/91	17 hrs @ 140 F	H	Rusting Panels
03/26/91	23 hrs @ 140 F	H	
03/27/91	2 hrs @ 650 F	O	
03/27/91	17 hrs @ 138 F	H	
03/28/91	2 hrs @ 650 F	O	
03/28/91	21 hrs @ 120 F	H	
03/29/91	20 hrs @ 120 F	H	
03/30/91	44 hrs @ 118 F	H	
04/01/91	2 hrs @ 700 F	O	HOT
04/01/91	2 hrs 650 F	O	
04/01/91	20 hrs @ 120 F	H	
04/02/91	2 hrs @ 750 F	O	HOT
			1200.8 g 12 events
PANEL SENT TO INGERSOLL-RAND			
05/16/91	Total rust removal by water blast		
<hr/> <hr/> <hr/>			

**MRC Fabrication/Conditioning/Test Form 91-1**

Page 1

Set-Sample: 28 - 9800      Comments: A-203 steel

Materials: KEN'S MARB 20 + clay

## **Equip Definitions:**

Date	Action	Equip	Results/Comments
05/22/91	Clean	-	Gel clean thoroughly I/R panel
05/22/91	Coat	-	Brush coat with Ken's mixture of MARB
05/22/91	Cure	-	Ambient curing
05/27/91	Thickness	M	0.6 mils (0.25-1.1)
Panel looks good but cures slowly at lab temperatures as tested daily			
for scratch hardness for a month. In addition, Aluminum can be wiped			
off the surface even 8 months later, although the coating is hard.			

**MRC Fabrication/Conditioning/Test Form 91-1**

Page 1

Set-Sample: 28 - 9801      Comments: A-203 steel

## Materials: MARB4

### **Equip Definitions:**

Date	Action	Equip	Results/Comments
05/22/91	Clean	-	Gel clean thoroughly I,R panel
05/22/91	Coat	-	Brush coat with Ken's mixture of MARB
05/22/91	Cure	-	Ambient curing
05/27/91	Thickness	M	0.6 mils (0.25-1.1)
			Panel looks good but cures slowly at lab temperatures as tested daily for scratch hardness for a month. In addition, Aluminum can be wiped off the surface even 8 months later, although the coating is hard.

**MRC Fabrication/Conditioning/Test Form 91-1**

Page 1

Set-Sample: 28 - 9802 Comments: A-203 steel

### **Materials: MARB4 + Spangle**

## **Equip Definitions:**

**MRC Fabrication/Conditioning/Test Form 91-1**

Page 1

Set-Sample: 28 - 9803 Comments: A-203 steel

Materials: MARB-4 + clay

### **Equip Definitions:**


## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 28 - 9804 Comments: A-203 steel

Materials: MARB4 with Spangle

Equip Definitions:



Date	Action	Equip	Results/Comments	
05/22/91	clean		Thoroughly gel clean I/R panel (leftside)	uncoated
05/30/91	coat		Brush coat MARB4/spangle	
05/30/91	1 hr @ 485 F	O	cure	
05/30/91	17 hrs @ 120 F	H		
05/31/91	1 hr @ -100 F	C		
06/03/91	3 hrs @ 650 F	O		
06/03/91	22 hrs @ 140 F	H		
06/04/91	66 hrs @ 120 F	H		
06/12/91	5 hrs @ 600 F	O		
06/13/91	4 hrs @ 600 F	O		
06/13/91	1 hr @ -120 F	C	manual	
06/13/91	40 hrs @ 120 F	H		
06/15/91	2 hrs @ 600 F	O		
06/17/91	2 hrs @ 650 F	O		
06/17/91	1 hr @ -100 F	C		
06/17/91	18 hrs @ 120 F	H		
06/18/91	5 hrs @ 650 F	O		
06/20/91	Pictures over I/R cleaned paint		15 events (-120 to 650 F)	
07/08/91	Test (Location 1)	A	300 PSI (100% cohesive)	
			Coating in very good condition	

## MRC Fabrication/Conditioning/Test Form 91-1

Page 1

Set-Sample: 28 - 9805 Comments: A-203 steel

Materials: MARB4 with Spangle

Equip Definitions:

		F
:	:	A
l	:	I
		L
I/R	I/R	mill
:	:	:

Date	Action	Equip	Results/Comments
			Ingersol-rand panel
05/30/91	clean		Gel clean entire panel
05/30/91	coat		Spraycoat MARB4 with spangle (top only)
05/30/91	1 hr @ 485 F	O	cure
05/30/91	17 hrs @ 120 F	H	
05/31/91	1 hr @ -100 F	C	
06/03/91	3 hrs @ 650 F	O	
06/03/91	22 hrs @ 140 F	H	
06/04/91	66 hrs @ 120 F	H	
06/12/91	5 hrs @ 600 F	O	
06/13/91	4 hrs @ 600 F	O	
06/13/91	1 hr @ -120 F	C	manual
06/13/91	40 hrs @ 120 F	H	
06/15/91	2 hrs @ 600 F	O	
06/17/91	2 hrs @ 650 F	O	
06/17/91	1 hr @ -100 F	C	
06/17/91	18 hrs @ 120 F	H	
06/18/91	5 hrs @ 650 F	O	
06/20/91	Pictures	15 events (-120 to 650 F)	Flaking over mill scale, left
07/08/91	Test (Location 1)	A	550 PSI (100% C) over I/R cleaned