

SELF-ASSEMBLED MONOLAYER OF ENGINEERED ORGANIC MOLECULES FOR MOLECULAR ELECTRONICS

Govind Mallick, Anubhav Srivastava, Sarah Lastella and Shashi P. Karna
Army Research Laboratory
Weapons and Materials Research Directorate,
ATTN: AMSRD-ARL-WM-BD
Aberdeen Proving Grounds, MD 21005-5069

Qingdon Zheng and Paras N. Prasad
Institute for Lasers, Photonics, and Biophotonics
The University at Buffalo
450 Natural Science and Mathematics Complex
Buffalo, NY 14260

Alma E Wickenden and Madan Dubey
US Army Research Laboratory
Sensors and Electron Devices Directorate
ATTN: AMSRD-ARL-SE-RL
2800 Powder Mill Road
Adelphi, MD 20783

ABSTRACT

A series of molecules for applications in molecular electronics were modeled, synthesized, and self-assembled on a thin Au film on lightly doped Si. The atomic force microscopy of the assembled molecules exhibits uniform distribution.

molecules at the Au surface in the “hollow” spaces has also been reported by other authors.³ Details of the modeling, synthesis, SAM preparation, and characterization of the electrical and surface properties will be presented in a later paper.

SUMMARY

A challenge in realizing molecular-scale devices is the lack of appropriate molecular architecture and controlled assembly of molecules on a solid substrate. Self-assembled monolayers provide a uniform hierarchical structure for developing molecular-scale electronic and sensor devices.^{1,2} As a part of our joint efforts to develop materials, assembly techniques, and understanding of the basic device physics, we have modeled a series of molecular structures by quantum mechanical calculations. The related structures have been synthesized and self-assembled on thin Au films on Si substrates. One of the structures shown in Figure 1, exhibited excellent self-assembly properties at a concentration of 1.135×10^{-3} M in tetrahydrofuran (THF) solution. The self-assembled monolayers (SAM) exhibited reproducible uniformity, as shown in the atomic force microscope (AFM) image (Figure 2). Lower concentrations did not exhibit this self-assembly property under identical conditions. Analysis of the AFM image suggests that the molecules prefer to attach in the (hollow) space surrounded by three Au atoms. This preferential binding of organic




Figure 1. *Ab initio* optimized geometry and energy (ϵ) for highest occupied (HO) and lowest unoccupied (LU) molecular orbitals

Report Documentation Page

*Form Approved
OMB No. 0704-0188*

Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

1. REPORT DATE 00 DEC 2004	2. REPORT TYPE N/A	3. DATES COVERED -			
4. TITLE AND SUBTITLE Self-Assembled Monolayer Of Engineered Organic Molecules For Molecular Electronics		5a. CONTRACT NUMBER			
		5b. GRANT NUMBER			
		5c. PROGRAM ELEMENT NUMBER			
6. AUTHOR(S)		5d. PROJECT NUMBER			
		5e. TASK NUMBER			
		5f. WORK UNIT NUMBER			
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Army Research Laboratory Weapons and Materials Research Directorate, ATTN: AMSRD-ARL-WM-BD Aberdeen Proving Grounds, MD 21005-5069 Institute for Lasers, Photonics, and Biophotonics The University at Buffalo 450 Natural Science and Mathematics Complex Buffalo, NY 14260		8. PERFORMING ORGANIZATION REPORT NUMBER			
		10. SPONSOR/MONITOR'S ACRONYM(S)			
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)		11. SPONSOR/MONITOR'S REPORT NUMBER(S)			
		12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release, distribution unlimited			
13. SUPPLEMENTARY NOTES See also ADM001736, Proceedings for the Army Science Conference (24th) Held on 29 November - 2 December 2005 in Orlando, Florida. , The original document contains color images.					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 2	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			





Figure 2: (a) 2-D AFM $1 \times 1 \mu\text{m}^2$ image of ME3 SAM on Au film. White dots represent the molecules attached at the Au surface. (b) 3-D AFM image of (a). The vertical

peaks correspond to the assembled molecular bundles, having an average height of ~ 2 nm.

REFERENCES

- ¹M. A. Ratner and J. Jortner, in *Molecular Electronics*, Eds. J. Jortner and M. Ratner (Blackwell Science Ltd, London, UK, 1997), p. 5-28.
- ²K. S. Kwok and J. C. Ellenbogen, *Materials Today*, pp. 28-37, February 2002.
- ³R. S. Sahoo and A. Patnaik, *J. Colloid Interface Sci.* **268**, 43 (2003)