



AFRL-RX-WP-TP-2010-4150

**FUNCTIONALLY GRADED MATERIALS BY LASER
METAL DEPOSITION (PREPRINT)**

Syamala R. Pulugurtha, Joseph Newkirk, and Frank Liou

University of Missouri-Rolla

Hsin-Nan Chou

Boeing Research & Technology

MARCH 2010

Approved for public release; distribution unlimited.

See additional restrictions described on inside pages

STINFO COPY

**AIR FORCE RESEARCH LABORATORY
MATERIALS AND MANUFACTURING DIRECTORATE
WRIGHT-PATTERSON AIR FORCE BASE, OH 45433-7750
AIR FORCE MATERIEL COMMAND
UNITED STATES AIR FORCE**

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. **PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.**

1. REPORT DATE (DD-MM-YY) March 2010	2. REPORT TYPE Technical Paper Preprint	3. DATES COVERED (From - To) 01 March 2010 – 01 March 2010
--	---	--

4. TITLE AND SUBTITLE FUNCTIONALLY GRADED MATERIALS BY LASER METAL DEPOSITION (PREPRINT)	5a. CONTRACT NUMBER FA8650-04-C-5704
	5b. GRANT NUMBER
	5c. PROGRAM ELEMENT NUMBER 78011F

6. AUTHOR(S) Syamala R. Pulugurtha, Joseph Newkirk, and Frank Liou (Missouri University-Rolla) Hsin-Nan Chou (Boeing Research & Technology)	5d. PROJECT NUMBER 2865
	5e. TASK NUMBER 25
	5f. WORK UNIT NUMBER 25100000

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) University of Missouri-Rolla Missouri University of Science & Technology 1870 Miner Circle Rolla, MO 65409-0970	Boeing Research & Technology	8. PERFORMING ORGANIZATION REPORT NUMBER
---	------------------------------	---

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Air Force Research Laboratory Materials and Manufacturing Directorate Wright-Patterson Air Force Base, OH 45433-7750 Air Force Materiel Command United States Air Force	10. SPONSORING/MONITORING AGENCY ACRONYM(S) AFRL/RXLMP
	11. SPONSORING/MONITORING AGENCY REPORT NUMBER(S) AFRL-RX-WP-TP-2010-4150

12. DISTRIBUTION/AVAILABILITY STATEMENT
Approved for public release; distribution unlimited.

13. SUPPLEMENTARY NOTES
Technical paper for general release. PAO Case Number: 88ABW-2009-3786; Clearance Date: 28 Aug 2009. Paper contains color.

This work was funded in whole or in part by Department of the Air Force Contract FA8650-04-C-5704. The U.S. Government has for itself and others acting on its behalf a paid-up, nonexclusive, irrevocable worldwide license to use, modify, reproduce, release, perform, display, or disclose the work by or on behalf of the U.S. Government.

14. ABSTRACT
Fabrication of functionally graded materials (FGMs) by laser metal deposition (LMD) has the potential to offer solutions to key engineering problems over the traditional metalworking techniques. But the issues that need to be addressed while building FGMs are intermixing in the layers and cracking due to the residual stresses. This paper is to present the study of the effect of process parameters (laser power and travel speed) on the degree of dilution between the substrate (or, previous layer) and powder material for few metallurgical systems.

15. SUBJECT TERMS
LMD, FGMs, intermixing, cracking, dilution

16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT: SAR	18. NUMBER OF PAGES 38	19a. NAME OF RESPONSIBLE PERSON (Monitor) Todd J. Turner
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			

Functionally Graded Materials by Laser Metal Deposition

¹Syamala R Pulugurtha, ¹Joseph Newkirk, ²Frank Liou, and Hsin-Nan Chou³

¹Department of Materials Science & Engineering, Missouri University of Science & Technology

²Department of Mechanical Engineering, Missouri University of Science & Technology

³Boeing Research & Technology

Abstract

Fabrication of functionally graded materials (FGMs) by laser metal deposition (LMD) has the potential to offer solutions to key engineering problems over the traditional metal-working techniques. But the issues that need to be addressed while building FGMs are intermixing in the layers and cracking due to the residual stresses. This paper is to present the study of the effect of process parameters (laser power and travel speed) on the degree of dilution between the substrate (or, previous layer) and powder material for few metallurgical systems.

Keywords: LMD, FGMs, intermixing, cracking, dilution

Introduction

FGMs for industrial-related applications have been a subject of research for quite some time now, because of their ability to offer unique solution to the engineering problems over conventional materials and traditional composites. Among the various processing methods that are available, FGMs by LMD using solid free form fabrication route for obtaining bulk near net shape metallic components has been a promising technology. Its main advantage is the capability to control composition and properties within a fabricated

structure by either pre-blending or combining different elemental powders using multiple powder feeder systems at the laser focal zone, which enables to tailor properties suited for specific engineering applications. This technology is ideal in producing functional prototypes and structural parts in smaller quantities and cost-effective [1, 2, 3].

Functionally grading dissimilar/incompatible metals (i.e. 100% A to 100% B) is qualitatively different from dissimilar/compatible systems [4] for the following reasons: (1) different thermo-physical properties, (2) composition becomes a parameter that can vary across the melt pool, and (3) nucleation of phases assumes importance, especially when inter-metallic compounds are present in the phase diagram. Although a lot of studies have been conducted on Ti-based systems by laser alloying, cladding, laser-rapid forming (LRF), etc. like Ti-N [5,6,7]; Ti-C-N [8], Ti-Al [9]; SiCp-Ti6Al4V [10]; TiC-Ti6Al4V and TiC+NiCrBSi –Ti6Al4V [11]; Ti-xV, Ti-xMo [12], a very limited literature is available on Ti based alloy/Ni FGMs [13], or Ti based alloy/ Fe FGMs. The dissimilar systems such as Ni-Ti have following features: (a) different thermo-physical properties, for example, thermal diffusivity of Ni is roughly three times that of Ti at room temperature and density of liquid Ni is twice that of liquid Ti, and this significantly influences heat transfer. (b) There are three inter-metallic phases (IMPs) in the system which can form from the liquid through invariant reactions. Lin *et al* [13] successfully deposited a FGM having a continuous gradient from 100% Ti to 60% Rene88DT superalloy by LRF. They investigated the phase evolution during solidification and attributed the hardness of the graded material to be dependent on the amount and morphology of the phases: Ti₂Ni, TiNi, and α + Ti₂Ni eutectoid. Most of the previous studies were focused on understanding the solidification behavior and phase evolution in

multi-component systems, but the issues like intermixing in the layers, cracking due to thermal and residual stresses have not been dealt with. With this in mind, the present work focuses on the effect of process parameters like laser power and travel speed on intermixing in the layers, and the pre-treatment (i.e. substrate heating) of the substrate to try counter cracking issues.

Experimental

Our LAMP system (Fig. 1(a)) consists of a 1 kW diode laser (Nuvonyx ISL-1000M, 808 nm, spot size 2.5 mm), a five-axis numerical control working table, and a powder feeder with co-axial nozzle was used to fabricate the graded materials. The experiments were conducted in an argon-gas environment to prevent the melt pool from oxidizing and oxide contamination from occurring during processing. The powder stream from the hopper was directly injected using argon gas into the molten pool through the laser nozzle. The metal powder was melted and subsequently re-solidified to form the clad layer (Fig. 1(b)). The typical size of the powders was in the range of 100-45 microns. The nominal composition of Fe-82 wt% V (powder-1) and Inconel-625 (powder-2) powders are listed in Table 1. The substrate materials used for the experiment were cold rolled 1 in. thick Ti6Al4V and SS316L. The substrates were cleaned prior to deposition using ethyl alcohol to remove any dirt or grease on the surface.

The as-deposited material was sectioned parallel to the compositional gradient for microscopy studies; for X-ray diffraction (XRD) analysis, the perpendicular section was utilized. The composition along the gradient direction was characterized using scanning electron microscopy (SEM): Hitachi S570 equipped with a Si-drift energy dispersive X-

ray (EDS) analysis facility. The identification of phases was achieved using X-Ray Diffraction (XRD) (Philips Xpert X-ray diffractometer), and micro-hardness of the deposits was measured using Struers (model: Duramin) .

Results and Discussion

Composition and Phase Analysis

In order to understand the effect of residual heat on inter-mixing/cracking with change of laser power on each deposited layer, a simpler experiment was designed by changing the power (Ramp up & Down) every 0.9th inch on a single layer track; parameters listed in Table 2. In case of powder-1, cracks were observed on both the substrates for all the processing parameters. The Fe-V equilibrium phase diagram (Fig. 2(a)) shows σ -phase is more likely to form in austenitic steels when there is ferrite retained from high temperature operation. Also, V is a ferrite stabilizer and forms brittle σ -phase (needle like structure) under processing conditions. XRD phase analysis results further corroborates the presence of only BCC-Fe 2θ peaks in powder-1 deposit on SS316L, as shown in Fig. 3. The combination of brittle phases and residual stresses probably may have caused cracking in the powder-1 deposit on SS316L for all the processing parameters.

Figure 2b shows the equilibrium phase diagram of Ni-Ti alloy. The three most important IMPs in the phase diagram are Ti_2Ni , $TiNi_3$, and $TiNi$, which can contribute to cracking, while Ti-Cr and Ti-Mo form solid solutions over the entire composition range

with no IMPs. Attempts to deposit powder-2 on Ti6Al4V substrate resulted in cracks due to residual stresses at all the processing parameters, while no cracks were observed when deposited on SS316L, an example shown in Fig. 4. A similar work carried out by Domack *et al* [14] showed macroscopic cracking in powder blends containing 40-60 percent Inconel 718 on Ti6Al4V substrate when produced by LMD. But Ni-based powders have been previously proven to bond well with steel in plasma-spraying, co-extrusion technique, or LMD [13,15] as there is no sigma/brittle phases present in the Fe-Ni equilibrium phase-diagram Fig. 2(c).

X-map results for powder-2 on Ti6Al4V and SS316L substrate show self-grading in the melt pool for both the set of experiments, as an example shown in Fig. 5. Elements like Al (-substrate) and Cr (-deposit) did not diffuse into one another, whereas Mo is uniformly distributed in the melt pool. The composition data in Table 3 shows that the laser power does not play a very significant role in controlling the inter-mixing in the melt pool. While that still holds true, laser power did result in segregation in the deposit. The deposit showed two discrete regions: (a) plume, and (b) non-plume. Plume- region consists of mixture of Ti+Ni, with higher weight percentage of Ti, while non-plume region has higher weight percentage of Ni. In general, Ni-Ti have relatively large negative enthalpy of mixing which results in the generation of additional heat in a very localized form in the melt pool, and hence aids the process of inter-mixing [16]. But segregation in the melt pool has shown that though inter-mixing was initiated, it remained incomplete during the deposition process at lower laser power levels. At higher powers, the dilution zone is wide with more inter-mixing. Also, enthalpy of mixing results in formation of a much localized heat source in the melt pool, and can either raise or lower

its temperature. If rate of solidification is considered to be the temperature difference between melt pool and the surrounding substrate material. A higher temperature of the melt pool from exothermic mixing will result in higher solidification rate. Figure 6 shows composition data from EDS analysis plotted on the Ni-Ti equilibrium phase diagram: the plume –zone with higher wt% Ti falls in the lower melting point regions (obviously will solidify the last) compared to the non-plume zones. Also, the density of liquid Ti is very low compared to that of liquid Ni (twice that of liq. Ti) and therefore, the plume zone tries to move to the top along the solidification direction (Fig. 5). Because of the steeper slope of the liquidus NiTi line compared to that of Ti_2Ni , the driving force for NiTi formation will exceed that of Ti_2Ni . Therefore, NiTi will nucleate first (non-plume zone) from the liquid and Ti_2Ni will most likely form heterogeneously on it through peritectic reaction (plume zone) [17]. Since the composition data lies close to the TiNi and Ti_2Ni line compounds, it is safe enough to say that the possible cracking in the deposits is due to IMPs. In case of powder-2 on SS316L, we see only a small amount of Fe present in the deposit and no signs of cracks (Fig. 7 & Table 3). Because Fe-Ni are simple liquids with no interaction between them (Refer Phase Diagrams).

A multi-layered deposition of powder-1 on Ti6Al4V substrate was performed to study the effect of laser power on intermixing/cracking. Table 4 lists the process parameters. The X- maps in Fig. 8 at 455 and 677 W show some amount of un-melted powder-1 particles at surface of the deposit. The composition analysis (Table 5) shows self-grading in the melt pool, although the four layers are not distinct. But all the deposits showed cracks either due to residual stresses or formation of IMPs. Ti-V forms good

solid solution with no brittle phases, but Fe-xTi has two stable IMPs (FeTi and Fe₂Ti), and can contribute to brittle failure (Fig. 2(d)).

Inter-mixing and cracking in the layers for dissimilar materials are both inter-dependant problems. In order to obtain a defect free structure (cracks, pores, or bonding defects) the substrates were pre-heated to 540 °C on a hot plate and maintained at that temperature during the entire deposition process. Table 6 shows the process parameters of powder-2 deposit on (with/without pre-heat) Ti6Al4V substrates. The results show that a pre-heat temperature of 540°C is not sufficient enough to eliminate the cracks formed in the deposits, an example shown in Fig. 9. Kelbassa *et al* [18] showed that a pre-heating temperature between 650-700 °C was required to obtain a defect free single LMD tracks for γ -TiAl deposit on Ti6Al4V and γ -TiAl substrates. A suitable pre-heating guaranteeing a defect free LMD result is still under investigation. Also, the X-maps (Fig. 12) show that at 300 W for with/without substrate pre-heating there is significant amount of un-melted powder particles observed at the surface, and this was also true at 600 W without pre-heating for all the parameters. Though exothermic enthalpy of mixing does contribute additional heat to the melt pool, the melting efficiency is strongly affected by processing parameters and material thermo-physical properties [19]. A dimensionless-parameter model was previously used to estimate the melting efficiency for the LENS deposits. Equation [1] defines melting efficiency as ratio of energy required for melting ($A\Delta H_m$, per unit length) to actual absorbed energy ($h_a P/S$, per unit length).

$$h_m = Ch/Ry = SA\Delta H_m/h_a P \quad [1]$$

$$Ch = S^2 A/\alpha^2$$

$$Ry = h_a P S/\alpha^2 \Delta H_m$$

Where S is the heat-source travel speed, A is the total deposit cross-section, ΔH_m is the melting enthalpy, h_a is the laser energy efficiency (which is assumed to be 40 pct [du pont], α is the thermal diffusivity of the substrate [20], and P is the laser power. For materials with dissimilar thermo-physical properties [powder-2 (2.67 J/mm^3) onto Ti6Al4V (13 J/mm^3) substrate], an average value of melting enthalpy between the two was used, 7.8 J/mm^3 [19]. From the plot between Ch and Ry (Fig. 11(a)), melting efficiency can be determined solely from the dimensionless parameter Ry , for the material used in this study given by the following Equation [2]:

$$h_m = 0.1629 - (0.853/Ry) \quad [2]$$

At constant speed, the measured melting efficiency is slightly higher than that of the calculated value, Fig. 11(b). This discrepancy in the data can be attributed to the additional heat generated in the melt pool for dissimilar metals with exothermic enthalpy of mixing. The figure also shows how melting efficiency increases with the increase in the laser input power. It is previously reported that the calculated maximum melting efficiency for a moving point heat source in a 3D case is about 0.37 [20]. Also, Du pont *et al* [19] reported that increase in travel speed increases the melting efficiency as conduction can be neglected. In this case (Fig. 11(c)), the data contradicts the previously reported studies, which still need to be explained. Pre-heating the substrates to 540°C before and during the deposition enhanced the inter-mixing in the melt pool for all the process parameters, as shown in Fig. 10. A significant amount of self-grading can be seen in the melt pool, as shown in Table 7. Geometric dilution ' D ' which is measured between the melted substrate and deposited powder is given by

$$D = A_s / (A_s + A_p) \quad [3]$$

Where A_s is the cross-sectional area of melted substrate and A_p is the cross-sectional area of deposited powder. The dilution increased with the increase in travel speed (Fig. 11(d)) as less power is delivered to the melt pool, resulting in decrease in deposit cross-sectional area. Also, dilution is affected by the melting efficiency. As the laser power is increased, more energy is available for melting the underlying substrate and incoming powder. Dilution was also observed to increase with substrate heating.

Microhardness

Hardness was measured along the samples (Fig. 12(a,b)) and through the samples (Fig. 12(c)). An average hardness value of 890 ± 10 HV₁₀₀ for powder-2 on Ti6Al4V substrate and 236 ± 10 HV₁₀₀ on SS316L substrate was obtained. A high hardness value in the former case may be due to the presence of brittle IMPs. The deposits were also tested at higher loads to study their performance. A small crack initiated in powder-2 on Ti6Al4V substrate at a load of 9.81 N (@ 5 s), while multiple cracks originated at 19.6N (@ 5 s). In case of powder-2 on SS316L, higher loads produced bigger indents indicating that the deposit is ductile/soft. Hardness as a function of depth for powder-1 on Ti6Al4V substrate at 1 N load, for 5 secs is shown in Fig. 12(c). The profile can be divided into three distinct regions: clad, dilution and heat affected zones (HAZ). The hardness of the dilution zone initially shown to increase and after which dropped to value equal to HAZ. Such a sharp transition in hardness values can be potential reasons for cracks either due to residual stresses or IMPs.

Summary

Inter-mixing and cracking are inter-related problems which need to be addressed while building FGMs with dissimilar materials. An optimized window of processing parameters like laser power, travel speed and powder feed rate is yet to be determined to obtain a successful FGM. Inconel-625 deposits showed macro-cracks due to combined effect of IMPs and residual stresses on Ti6Al4V substrates, while no cracks were observed on SS316L substrates. The possible IMPs present in the deposits were NiTi and NiTi₂. Intermixing and cracking was also observed on multi-layered (MLs) deposits of Fe-82wt%V on Ti6Al4V substrates. An attempt to counter the cracking issue in dissimilar materials by substrate treatment to 540°C did not solve the problem either. Substrate heating prior and during the deposition enhanced inter-mixing in the melt-pool. The geometric dilution (D) increased with increase in laser power, travel speed and substrate heating. Future work would involve optimization of parameters for these systems to reduce inter-mixing and cracking in the deposits, building MLs thin –walls and develop a simulation-model to study the melt-pool dynamics.

Acknowledgement

This research was supported by a grant from the U.S. Air Force Research Laboratory contract # FA8650-04-C-5704. Support from Missouri S&T Intelligent Systems Center is also greatly appreciated.

References

1. G. K. Lewis, U. E. Schlienger, *Materials and Design*, 21 (2000), p417.
2. S. M. Kelly, S. L. Kampe, *Metallurgical and Materials Transaction A*, 35A (2004), p1861.
3. P.A. Kobryn, E.H. Moore, S.L. Semiatin, *Scripta Materialia*, 43 (2000) p299.
4. G.P. Dinda, A.K. Dasgupta, J. Mazumder, *Materials Science and Engineering A* 509 (2009), p98.
5. M. Grenier, D. Dube, A. Adnot, M. Fiset, *Wear*, 210 (1997), p127.
6. V.M. Weerasinghe, D.R.F. West, J. de Damborenea, *J. Material. Process. Technol.*, 58 (1996), p79.
7. X. Chen, G. Wu, R. Wang, W. Guo, J. Yang, S. Cao, Y. Wang, W. Han, *Surf. Coat. Technol.*, 201 (2007), p4843.
8. L. Covelli, F. Pierdominici, I. Smurov, S. Tosto, *Surf. Coat. Technol.*, 78 (1996), p196.
9. J.H. Abboud, R.D. Rawlings, D.R.F. West, *Mater. Sci. Technol.*, 10 (1994), p414.
10. Y.T. Pei, V. Ocelik, J.Th.M. De Hosson, *Acta Materialia*, 50 (2002), p2035.
11. R.L. Sun, D.Z. Yang, L.X. Guo, S.L. Dong, *Surf. Coat. Technol.*, 132 (2000), p251.
12. P.C. Collins, R. Banerjee, H.L. Fraser, *Scripta Materialia*, 48 (2003), p1445.
13. X. Lin, T.M. Yue, H.O. Yang, W.D. Huang, *Acta Materialia*, 54 (2006), p1901.
14. M S Domack, J M Baughman, *Rapid Prototyping Journal*, 11 (2005), p41.
15. F. J. Kahleen, A. V. Klitzing, A. Kar, *J. of Laser Applications*, 12 (2000), p205
16. K. I. Schwendner, R. Banerjee, P. C. Collins, C. A. Brice, H. L. Fraser, *Scripta Materialia*, 45 (2001), p1123.
17. S. Chatterjee, T.A. Abinandanan, K. Chattopadhyay, *J. of Materials Science*, 41 (2006), p643.
18. I. Kelbassa, A. Welsheit, K. Wissenbach, V. Hermes, *Proc. of the 2nd Pacific International Conference on Applications of Lasers and Optics*, 2006, p208.
19. R. R. Unocic, J. N. Du. Pont, *Metallurgical and Materials Transactions B*, 34B (2003), p439.
20. M. Van Elsen, M. Baelmans, P. Mercelis, J. P. Kruth, *International Journal of Heat and Mass Transfer*, 50 (2007), p 4872.

List of Tables

1. The chemical composition (wt%) of the powders
2. Laser processing parameters for different power profiles
3. Composition analysis of powder-2 on Ti6Al4V and SS316L substrates for Ramp-up power profile
4. Parameters for laser deposition of powder-1 on Ti6Al4V substrate
5. Shows the composition data of powder-1 deposits at different laser power levels
6. Experimental parameters for deposition of powder-2 on Ti6Al4V substrate
7. Shows the composition data of powder-2 on Ti6Al4V substrate at different laser power levels

List of Figures

1. (a) LAMP system (fig. shows repair welding); (b) Schematic of the deposition process
2. Equilibrium phase diagrams: (a) Fe-V; (b) Ni-Ti; (c) Fe-Ni; (d) Fe-Ti
3. XRD phase analysis of powder-1 deposit on SS316L
4. Macrostructure of powder-2 deposit at 1000 W on (a) Ti6Al4V (shows macro-cracks); (b) SS316L substrate
5. Shows X-mapping images of RAMP UP power profile of powder-2 on Ti6Al4V substrate at (a) 1000 W, (b) 600W, (c) 300 W
6. Ni-Ti equilibrium phase diagram
7. Shows X-mapping images of RAMP UP power profile of powder-2 on SS316L at (a) 1000 W, and (b) 300 W
8. Shows X-images of powder-1 on Ti6Al4V substrate at (a) 455 W, (b) 535 W, (c) 677 W
9. Macro-cracks in powder-2 on Ti6Al4V substrate, 600 W, 10 ipm, substrate heating @ 540°C
10. X-maps of powder-2 deposit on Ti6Al4V substrate under different process parameters: SH = substrate heating, NSH = no substrate heating
11. (a) Plot between Ch Vs Ry ; (b) melting efficiency at constant speed; (c) melting efficiency at constant power; (d) dilution
12. Microhardness indents using different loads indicated for powder-2 on (a) Ti6Al4V, (b) SS316L substrates; (c) hardness as a function of depth for powder-1 on Ti6Al4V

Table 1: The chemical composition (wt%) of the powders

<i>Type of Powder</i>	<i>Composition (wt%)</i>
Powder-1: Fe-82 wt% V	V (82), Al (0.68), Si (0.9), C (0.07), S (0.01), P (0.02), Fe (18)
Powder-2: Inconel-625	Ni (58), Cr (20-23), Mo (8-10), Nb+Ta (3.15-4.15), Fe (5)

Table 2: Processing parameters for different power profiles, * Ti6Al4V and SS316L substrates, powder-1 & 2

Exp. Type	Power, W	Trvl. Spd., ipm	Pwd. Feed Rt., g/min
Ramp-Up	300, 387.5, 475, 562.5, 650, 737.5, 825, 912.5, 1000	10	5
Ramp-Down	1000, 912.5, 825, 737.5, 650, 562.5, 475, 387.5, 300		

Table 3: Composition analysis of powder-2 on Ti6Al4V and SS316L substrates for Ramp-up power profile *(wt % of V, Cr, Al, & Mo has not been reported in this table)

Exp. Type	Substrate	Power, W	Region	Reg. Type	Composition (wt%)		
					Ti	Ni	Fe
Ramp-up	Ti64	300	1	Substrate	93.41		0.1
			2	Dilution	54.63	32.5	1.01
			3	Deposit	16.36	60.2	
		650	1	Substrate	92.37		0.26
			2	Dilution	59.2	29.6	0.92
					42.62	40	1.09
			4	Deposit	27.25	48	2.5
		1000	1	Substrate	93.47		0.26
			2	Dilution	58.59	27	0.77
					40.83	1.77	38.9
			4	Deposit	20.27	55.8	0.99
		SS316L	300	1	Substrate		7.38
	2			Dilution		39.4	36.1
	3			Deposit		67.5	3.48
	1000		1	Substrate		6.99	74.2
			2	Dilution		23.2	66.5
3			Deposit		65.9	5.54	

Table 4: Parameters for laser deposition of powder-1 on Ti6Al4V substrate

Laser Power, W	Travel Speed, ipm	Powder Feed Rate, g/min
455	20	3
535		
677		

Table 5: Shows the composition data of powder-1 on Ti6Al4V substrate at different laser power levels

Laser Power	Composition wt%			
	Ti	Fe	Al	V
677 W				
Substrate	89.45	0.18	6.82	3.55
Deposit-Bottom	36.51	12.83	3.72	46.95
Deposit-Middle	28.57	8.53	5.14	57.76
Deposit-Top	25.67	10.52	4.58	59.23
535 W				
Substrate	86.28	0.08	10.13	3.51
Deposit-Bottom	35.23	5.86	6.51	52.39
Deposit-Middle	20.24	8.49	5.07	66.2
Deposit-Top	13.67	9.3	4.4	72.63
455 W				
Substrate	88.66	0.35	7.32	3.66
Deposit-Bottom	27.63	11.07	3.62	57.66
Deposit-Middle	11.47	14.31	3.59	70.62
Deposit-Top	6.21	15.04	1.97	76.78

Table 6: Experimental parameters for deposition of powder-2 on Ti6Al4V substrate

Exp. No	Power, W	Travel Speed, ipm	Powder Feed Rate, g/min	Pre-heating, °C
1	300	10,20,30,40	5	540
2	600			
3	1000			

Table 7: Shows the composition data of powder-2 on Ti6Al4V substrate at different laser power levels *(wt % of V, Cr, Al, & Mo has not been reported in this table; shows composition for selected travel speeds; Composition of the substrate is Ti (92.57), V (3.95), Al (2.98); Sub□ Reg. 1 □ Reg. 2, etc.)

Power, W	Trvl. Speed, ipm	Substrate heat, °C	Region	Ni	Ti
300	10	nil	1	52.41	29.88
			2	48.85	37.35
			3	70.3	6.19
		540	1	20.65	70.49
			2	35.64	55.44
			3	44.94	42.53
	20	540	4	67.71	9.03
			1	23.65	68.29
			2	45.65	44.08
		nil	3	52.82	29.85
			4	77.33	0.06
			1	24.35	66.85
600	10	nil	2	49.22	34.52
			3	48.85	35.38
			4	61.15	17.03
			5	63.04	14.98
			6	62.93	14.95
			1	26.85	60.08
	20	nil	2	32.21	52.32
			3	32.16	52.18
			4	30.38	54.55
			5	30.48	54.32
			1	20.65	70.49
			2	35.64	55.44
	10	540	3	44.94	42.53
			4	67.71	9.03
			1	33.94	52.54
			2	40.45	41.84
			3	45.35	35.76
			4	46	35.15
	20	540	5	47.19	33.26
			6	47.68	32.58
			1	24.67	64.75

			2	40.54	43.81	
			3	46.82	36.01	
			4	34.66	47.69	
			1	26.85	60.03	
			2	32.21	52.32	
			3	32.16	52.18	
	20			4	30.38	54.55
				5	30.48	54.32
				1	24.64	63.34
	10	575		2	40.87	42.53
				3	44.07	38.72
				4	43.4	39.39
				5	43.04	39.97
				6	43.04	39.71




Fig. 1: (a) LAMP system (fig. shows repair welding); (b) Schematic of the deposition process.

(Source: <http://www.emeraldinsight.com/fig/1560130405005.png>)




Fig. 2: Equilibrium phase diagrams: (a) Fe-V; (b) Ni-Ti; (c) Fe-Ni; (d) Fe-Ti (Source: www.calphad.com/graphs)




Fig. 3: XRD phase analysis of powder-1 deposit on SS316L. The image shows BCC-Fe peaks in the powder-1 deposit on SS316L substrate.





Fig. 4: Macrostructure of powder-2 deposit at 1000 W on (a) Ti6Al4V (shows macro-cracks); (b) SS316L (no macro-cracks) substrate.





Fig.5: Shows X-mapping images of RAMP UP power profile of powder-2 on Ti6Al4V substrate at (a) 1000 W, (b) 600W, (c) 300 W. Due to incomplete inter-mixing, the melt pool is divided into plume and non-plume regions.




Fig. 6: Ni-Ti equilibrium phase diagram.




Fig. 7: Shows X-mapping images of RAMP UP power profile of powder-2 on SS316L at (a) 1000 W, and (b) 300 W. There is no inter-mixing in the melt pool.




Fig. 8: Shows X-images of powder-1 on Ti6Al4V substrate at (a) 455 W, (b) 535 W, (c) 677 W. The four-layers are not distinguishable and cracks penetrated through the entire deposit.





Fig. 9: Macro-cracks in powder-2 on Ti6Al4V substrate, 600 W, 10 ipm, substrate heating @ 540°C.






Fig. 10: X-maps of powder-2 deposit on Ti6Al4V substrate under different process parameters: SH = substrate heating, NSH = no substrate heating. Substrate heating increased the dilution zone size.







Fig. 11: (a) Plot between Ch Vs Ry ; (b) melting efficiency at constant speed; (c) melting efficiency at constant power; (d) dilution.





Fig. 12: Microhardness indents using different loads indicated for powder-2 on (a) Ti6Al4V, (b) SS316L substrates; (c) hardness as a function of depth for powder-1 on Ti6Al4V.