

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Washington Headquarters Service, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188) Washington, DC 20503.

PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

1. REPORT DATE (DD-MM-YYYY) 1 Apr 05		2. REPORT TYPE Final Technical Report		3. DATES COVERED (From - To) 1 Apr 05-31 Mar 08	
4. TITLE AND SUBTITLE Molecular Design of Multilayer Composites From Carbon Nanotubes				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER FA9550-05-1-0143	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Prof. Nicholas A. Kotov				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Prof. Nicholas A. Kotov University O Michigan Department Of Materials Sciences and Engineering Ann Arbor, MI 48109				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) USAF/AFRL AFOSR 875 North Randolph Street Arlington VA 22203				10. SPONSOR/MONITOR'S ACRONYM(S) AFOSR	
				11. SPONSORING/MONITORING AGENCY REPORT NUMBER AFRL-OSR-VA-TR-2013-0911	
12. DISTRIBUTION AVAILABILITY STATEMENT  Distribution Statement A: Approved for public release. Distribution is unlimited.					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT The Air Force will require aerospace vehicles and weapon systems with performance superior to those of any potential adversary. Conductive nano-reinforcements offer an excellent potential for further improvement of structural performance and lightening protection of polymer composites used in numerous Air Force systems. Success in the proposed research will lead to scalable, low-cost method of producing SWNT/polymer composites thereby overcoming current obstacle to high volume loading of nanoreinforcement due to processing problems. Moreover, the research will lay a foundation for broader technology for multifunctional composite structures.					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT Unclassified	18. NUMBER OF PAGES 11	19a. NAME OF RESPONSIBLE PERSON Dr. Les Lee
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			19b. TELEPHONE NUMBER (Include area code) (703)

**Program Title:** Molecular Design Of Multilayer Composites From Carbon Nanotubes

**PI:** Prof. Nicholas A. Kotov, University of Michigan, Department of Chemical Engineering, Ann Arbor, MI, 48109

**Co-PI:** Prof. John Kieffer, University of Michigan, Department of Materials Science and Engineering, Ann Arbor, MI, 48109

**Contact information:** Nicholas A. Kotov,  
Tel: 734-763-8768,  
Fax: 734-764-7453,  
E-mail: [kotov@umich.edu](mailto:kotov@umich.edu)

**Program Name:** Mechanics of Multifunctional Materials & Microsystems,  
Project Manager Dr. Les Lee

**Final Report for 2005-2008**

### **1. Brief Description of the program and Research Approach**

Previous generation of single wall carbon nanotubes (SWNT) composites suffer from poor connectivity with, and non-uniform distribution within, a polymer matrix resulting in structural defects. These defects are responsible for the mechanical failures of SWNT-polymer composites and the lower-than-expected mechanical performance. A new processing approach, based on sequential layering of chemically-modified nanotubes and polyelectrolytes, also known as layer-by-layer assembly (LBL) can greatly diminish the phase segregation and make SWNT composite highly homogeneous. Recent results<sup>1</sup> indicate that the tensile strength of these materials is several times higher than that of SWNT composites made via mixing; it approaches values typical for hard ceramics but the material itself is significantly lighter, which makes it one of the promising candidates for aviation applications especially for unmanned aerial vehicles (UAVs).

### **2. Major Goals and Objectives.**

Our goal is to produce material with record properties using novel methods of SWNT orientation control and on-line assessment of mechanical properties of the composites. In addition to high structural uniformity provided by LBL, strengthening of bonding between graphene sheet and polymer matrix is to be achieved through optimization of chemical interactions of SWNT with surrounding polymer. As well, it was proposed that the orientation of the individual SWNT fibers by magnetic field will result in significant improvement of strength. Unlike any other preparation methods, LBL makes possible production of highly nano- and micro-scale optimized materials from SWNTs.

These composites are expected to have unique mechanical properties with order-of-magnitude performance improvements.

### **3. Significant Accomplishments**

20130919 108

1. The fundamental problem with formation of SWNT composites with high loading (70%), nanoscale uniformity, and complete exfoliation of SWNTs was resolved. No surfactants or wetting agents destroying interfacial transfer stress transfer were applied.

2. The record composites were made from SWNT stabilized by poly(styrenesulfonate) coupled with poly(vinylalcohol) by optimization of preparation conditions. The strengths obtained exceed **650 MPa**, which is an absolute record for *non-fibrous* SWNT composites. The Young's modulus exceeded **50 GPa**.

3. Mapping of the mechanical properties in respect to the
- (a) oxidation state of SWNTs
  - (b) cross-linking modality;
  - (c) SWNT loading


was carried out (Table 1). Optimum position is likely located between 55 and 70% of SWNT loading.

4. The scale-up issues were addressed in this stage of the proposal. We developed several approaches that will enable large scale and 5-30 times faster manufacturing of the LBL composites than traditional LBL: (1) dewetting method and (2) exponential growth LBL; (3) spin-assisted LBL; and (4) Large scale LBL deposition (Figure 1).




**Figure 1.** Large scale LBL deposition system, "The Big Dipper".

5. Method of consolidation of the LBL films in the hierarchical composites was developed (Figure 2). We observed **strengthening** of the composites as the total volume increases as opposed to decrease of the strength according to the classical  $\sigma^2 A = \text{const}$  expression. This is one of the first actual examples of **hierarchical composites**.



**Figure 2.** Consolidated LBL films.



**Figure 3.** Conductive glass from SWNTs

6. We continued improving the conductivity of the LBL films of SWNT. The new method of detection of the damage in the airframe had been developed. New wireless sensors had been developed. Conductivity as high as  $5 \cdot 10^4$  S/cm was obtained. The best surface conduction was 80 Ohm per square for 80% transparency. Method of preparation of conductive glass from SWNT with tough flexible coating was found.

7. The same methods of LBL assembly developed for SWNT were applied to clays. The strongest clay composite with  $\sigma=450$  MPa and  $Y=106$  GPa was obtained. It was found that it has the ideal stress transfer even for high loadings, which is a critical fundamental discovery.

8. Method of improving fuel cell efficiency with free-standing LBL films was found.

**Table 1** Comparison table of ultimate tensile strength ( $\sigma_{ult}$ ), stiffness ( $E$ ), toughness ( $K$ ), strain ( $\epsilon$ ), and CNT loading for LBL composites and other materials.

Samples (estimated CNT loading)	Cross-linkage	$\sigma_{ult}$ (MPa)	E (GPa)	K (J/g)	$\epsilon$ (%)
[PVA/SWNT <sub>-COOH</sub> (15.8) +PSS] LBL (70%)	GA	391.5±36.8	13.2±2.4	42.8±10.5	18±4
	Heat	359.9±41.5	15.1±2.8	41.4±7.4	18±3
	-	257.2±24.6	11.9±2.5	13.8±3.8	11±1
PVA/SWNT <sub>-COOH</sub> (7.9) +PSS] LBL (60%)	GA	504.5±67.3	15.6±3.8	121.2±19.2	39±3
	Heat	452.6±30.1	23.0±2.4	47.9±16.9	16±4
	-	224.5±15.1	11.6±2.0	26.9±10.5	19±7
[PVA/SWNT <sub>-COOH</sub> (0) +PSS] LBL (47%)	GA	233.4±25.7	11.3±2.0	11.3±5.0	8±3
	Heat	262.57±2.1	10.9±0.8	12.8±1.5	8±1
	-	196.6±30.2	14.2±1.7	5.8±3.8	6±2
[PVA/Clay] LBL <sup>6</sup>	GA	400±40	106±11	~ 0.5	0.3±0.04
PVA <sup>6</sup>	-	40±4	1.7±0.2	~ 7.7	35±4
High performance CNT fiber <sup>36</sup> (100%)	-	8800	357	121	~8
SWNT Nylon composite fiber <sup>55</sup> (0.5%)	-	109	0.79	146	350
Kevlar fiber <sup>84</sup>	-	3600	90	33	5
Spider silk <sup>84</sup>	-	1150±200	7.9±1.8	165±30	39
Aluminum alloy (7075-T6)	-	572	71.7	29	11

**People Involved:**

**Students:** Bong Sup Shim, Ken Loh, Jian Zhu, Christine Andres

**Post-docs:** Kevine Critchley.

**Future Plans:**

Preparation of large scale samples.

Manufacturing large scale samples.

Preparations parts for UAVs.

**Funding Profile:** (Give the fiscal year funding for your program to the nearest thousand dollars. For those years with no funding list it as zero. Only give the funding totals for the current AFOSR program.)

<b>FY04</b>	<b>FY05</b>	<b>FY06</b>	<b>FY07</b>	<b>FY08</b>	<b>FY09</b>	<b>FY10</b>
0K	76K	119K	123K	0K	0K	0K

**References:** (List one or two relevant publications resulting from the AFOSR funded work. If the AFOSR funded effort is new, please list one or two relevant references from your earlier work.)

Podsiadlo P., Kaushik A. K., Arruda E. M., Waas A. M., Shim B. S., Xu J., Nandivada H., Pumplun B. G., Lahann J., Ramamoorthy A., Kotov N. A., Ultrastrong and Stiff Layered Polymer Nanocomposites, *Science*, 2007, 318, 80-83.

Michel M., Taylor A., Sekol R, Podsiadlo P., Kotov N. A. Thompson L.; High Performance, Nanostructured Membrane Electrode Assemblies for Fuel Cells Made by Layer-By-Layer Assembly of Carbon Nanocolloids, *Advanced Materials*, 2007, 19(22), 3859.

Bong Sup Shim, Zhiyong Tang, Matthew P. Morabito, Nicholas A. Kotov, Integration of conductivity, transparency and mechanical strength in highly homogeneous LBL Composites of SWNT, *Chemistry of Materials*, 2007, 19(23), 5467-5474.

Shim, B. S., Podsiadlo P., Lilly D., Agarwal A., Tang Z., Ho S., Ingle P., Patterson D., Lu W., Kotov N. A., Nanostructured Thin Films made by Dewetting Method Of Layer-By-Layer Assembly, *Nano Letters* 2007, 7(11), 3266-3273.

Loh, K. J.; Lynch, J. P.; Shim, B. S.; Kotov, N. An Optimization of Multilayer Carbon Nanotube-Polymer Composite Strain Sensors, *Journal of Intelligent Material Systems and Structures*, 2007, in press.

Podsiadlo, Paul; Sui, Lang; Elkasabi, Yaseen; Burgardt, Peter; Lee, Jaebeom; Miryala, Ashwini; Kusumaatmaja, Winardi; Carman, Mary R.; Shtein, Max; Kieffer, John; Lahann, Joerg; Kotov, Nicholas A.. Layer-by-Layer Assembled Films of Cellulose Nanowires with Antireflective Properties. *Langmuir* 2007, 23(15), 7901-7906.

Paul Podsiadlo, Zhiyong Tang, Bong Sup Shim, Nicholas A. Kotov, Counterintuitive Effect of Molecular Strength and Role of Molecular Rigidity on Mechanical Properties of Layer-By-Layer Assembled Nanocomposites, *Nano Letters*, 2007, 7(5), 1224-1231

P. Podsiadlo, Z. Liu, D. Paterson, P. B. Messersmith, N. A. Kotov, Fusion of Seashell Nacre and Marine Bioadhesive Analogs: High-Strength Nanocomposite by Layer-by-Layer Assembly of Clay and L-3,4-Dihydroxyphenylalanine Polymer, *Advanced Materials*, 2007, 19(7), 949-955.

Loh, K. J.; Kim, J.; Lynch, J. P.; Kam, N. W. S. Kotov, N. A. Multifunctional Layer-by-Layer Carbon Nanotube-Polyelectrolyte Thin Films for Strain and Corrosion Sensing, *Smart Mater. Struct.* 16 2007, 429-438