

UNCLASSIFIED

Defense Technical Information Center  
Compilation Part Notice

ADP011642

TITLE: Nonlinear Properties of Carbon Nanotubes in a Strong Electric Field

DISTRIBUTION: Approved for public release, distribution unlimited

This paper is part of the following report:

TITLE: International Conference on Electromagnetics of Complex Media [8th], Held in Lisbon, Portugal on 27-29 September 2000. Bianisotropics 2000

To order the complete compilation report, use: ADA398724

The component part is provided here to allow users access to individually authored sections of proceedings, annals, symposia, etc. However, the component should be considered within the context of the overall compilation report and not as a stand-alone technical report.

The following component part numbers comprise the compilation report:

ADP011588 thru ADP011680

UNCLASSIFIED

# Nonlinear Properties of Carbon Nanotubes in a Strong Electric Field

A. S. Maksimenko and G. Ya. Slepyan

Institute for Nuclear Problems, Belarus State University,  
Bobruiskaya str. 11, Minsk, 220050, Belarus  
Fax: + 375-17-226 5124; email: antonmx@inp.minsk.by

## Abstract

A theoretical model and computations of the I-V characteristics of both doped and undoped long carbon nanotubes in a strong axial dc-fields at room temperatures have been presented. Negative differential conductivity has been predicted. It has been shown that  $|dI/dV|$  for metal carbon nanotubes in the region of the negative differential conductivity significantly exceeds corresponding values for semiconducting ones. The predicted effect makes possible the design of wave-generating nanotube-based diodes for submillimeter and infrared ranges.

## 1. Introduction

Since the discovery by Iijima of carbon nanotubes (CNs), a great deal of interest has been focused on these quasi-one-dimensional monomolecular structures because of their unique physical properties (mechanical, electrical, optical, etc.) and the rapid experimental progress in the controlled preparation. Processes of electron transport in strong external fields when nonlinear effects are constitutive are of a great interest for potential applications in nanoelectronics and for experimental diagnostic of CN themselves.

The current-voltage (I-V) characteristics for tunnelling electrons in individual single-wall CNs at low temperatures were measured in Refs.[1, 2]. At such temperatures  $k_B T \ll \mathcal{E}_c, \Delta\mathcal{E}$  and conduction occurs through well separated discrete electron states; here  $k_B$  is the Boltzmann constant,  $T$  is the temperature,  $\mathcal{E}_c$  is charging energy,  $\Delta\mathcal{E} = \pi\hbar v_F/L$  is the energy level spacing with  $v_F$  as the Fermi speed and  $L$  as the CN length. At the above condition the current is produced by the electrons tunneling through CN in the presence of the Coulomb blockade induced by the long-ranged (unscreened) Coulomb interaction.

Current instability in CNs is of great interest. The instability appears due to the negative differential conductivity (NDC) in I-V curves of CNs. Nonlinear coherent transport through doped nanotube junctions was considered in Ref.[3]. It was also shown the possibility of NDC for tunnelling electrons. In Ref.[4] a theoretical phenomenological analysis of the I-V characteristics of undoped CNs at room temperatures, when  $k_B T > \mathcal{E}_c, \Delta\mathcal{E}$ . The current was produced by free charge carriers (quasiparticles) which are  $\pi$ -electrons moving in the field of the crystalline lattice. The nonlinearity of the I-V characteristic appears due to the nonlinear properties of the quasiparticle gas. The *negative differential conductivity* region with  $dI/dV < 0$  in CNs was predicted in a certain range of the field strength.

## 2. Theory

This report extends Ref.[4] for the case of doped CNs. Let us consider an doped single-wall zigzag CN ( $m,0$ ) exposed to a homogeneous axial dc-field  $E_z$ ,  $E_z = V/L$ , where  $V$  is the voltage

between the CN ends. We shall apply the semi-classical approximation considering the motion of  $\pi$ -electrons as a classical motion of free quasi-particles with dispersion law extracted from the quantum theory in the tight-binding approximation [5].

The motion of quasi-particles in an external axial electric dc-field is described by the Boltzmann kinetic equation

$$eE_z \frac{\partial f(\mathbf{p})}{\partial p_z} = -\frac{1}{\tau} [f(\mathbf{p}) - F(\mathbf{p})], \quad (1)$$

where  $e$  is the electron charge,  $F(\mathbf{p})$  is the equilibrium Fermi distribution function and  $\tau$  is the relaxation time. The relaxation term of the equation (1) describes the electron-phonon scattering [6, 7], electron-electron collisions etc.

Utilizing the method originally developed in the theory of quantum semiconductor superlattices [8] we can construct an exact solution of kinetic equation (1) without assuming the electric field to be weak. First, note that the distribution function  $f(\mathbf{p})$  is periodic in  $p_z$  with period  $2\pi/a$ ,  $a = 3b/2\hbar$ ,  $b = 1, 42\text{\AA}$ . Then, taking into account the transverse quantization, the distribution function can be presented by:

$$f(\mathbf{p}) = \Delta p_\phi \sum_{s=1}^m \delta(p_\phi - s\Delta p_\phi) \sum_{r \neq 0} f_{rs} e^{iar p_z}, \quad (2)$$

where  $f_{rs}$  are coefficients to be found,  $\delta(x)$  is the Dirac delta-function,  $\Delta p_\phi = \pi\sqrt{3}/am$ . The equilibrium distribution function  $F(\mathbf{p})$  can be expanded in the analogous series with the coefficients as follows

$$F_{rs} = \frac{a}{4\pi} \int_0^{2\pi/a} \left[ \frac{e^{-iar p_z}}{1 + \exp\{(\mathcal{E}_s(p_z) - \mu)/k_B T\}} - \frac{e^{-iar p_z}}{1 + \exp\{(-\mathcal{E}_s(p_z) - \mu)/k_B T\}} \right] dp_z. \quad (3)$$

In this equation first term describes the contribution of conduction band and the second one of valence band. Here  $\mu$  is a chemical potential of CN. It describes doping ( $\mu=0$  for undoped CNs [4]).  $\mu$  can be varied within wide range of values. Accordingly to [3]  $\mu \sim 0.3$  eV for doping by Au substrate,  $-0.5$  eV  $< \mu < 0.5$  eV for doping by typical alkali and halogen atoms. For the KC<sub>8</sub> doped CNs  $\mu \sim 2.0$  eV [9]. Substitution of both expansions into Eq. (1) gives  $f_{rs} = F_{rs}/(1 + i\tau r\Omega)$ , where  $\Omega = aeE_z$  is the Stark frequency.

The surface current density is defined by

$$j_z(E_z) = -\frac{8e\gamma_0}{\sqrt{3}\hbar b m} \sum_{r=1}^{\infty} \frac{r^2 \Omega \tau}{1 + (r\Omega\tau)^2} \sum_{s=1}^m F_{rs} \mathcal{E}_{rs}. \quad (4)$$

Here  $\gamma_0 \sim 3.0$  eV is the overlapping integral. This equation states the basis for the evaluation of I-V characteristics. As it has been stated above, the quasi-particles motion is described classically. Thus, both interband transitions and quantum-mechanical corrections to the intraband motion are left out of account in this model. This imposes the limitation on the external electric field strength:  $|E_z| < \gamma_0/2eR$ .

The Coulomb electron-electron interaction has been also left out of account in our approach. The role of this mechanism as applied to CNs was considered in a number of papers, see [10] for example. It has been established that the short-range electron-electron interaction, typical for CN arrays ('ropes'), have only a weak effects at high temperatures.

### 3. Numerical Results

The I-V characteristics obtained via numerical calculation of Eq.(4) are presented in Fig.1 and Fig. 2 for metal ( $m = 3q$ ,  $q$  is an integer) and Fig. 3 and Fig. 4 for semiconducting ( $m \neq 3q$ ) zigzag CNs.




Fig. 1 Undoped metal zigzag CNs.  
 $T=287,5^{\circ}\text{K}$ ,  $\tau=3 \cdot 10^{-12}$ .




Fig. 2 Doped zigzag CNs with  $m=3q$  ( $q$  is an integer).  
 $\mu=0.2$  eV,  $T=287,5^{\circ}\text{K}$ ,  $\tau=3 \cdot 10^{-12}$ .

The figures show the linear dependence of  $j_z$  on  $E_z$  at weak strengths of the external field both for doped and undoped CNs; it corresponds to the region of ohmic conductivity. As  $E_z$  increases, the value  $\partial j_z / \partial E_z$  growth smaller and at  $E_z = E_z^{(max)}$  the current density reaches the maximum value  $j_z^{max}$ . Further increase of  $E_z$  results in the decrease of  $j_z$ . Thus, predicted in [4] the region with the negative differential conductivity ( $\partial j_z / \partial E_z < 0$ ), in the I-V characteristics of undoped CNs can be also observed in the case of doped CNs.

Fig.1 and Fig. 3 demonstrate that  $E_z^{(max)}$  depends on neither number  $m$  nor the conductivity type (metal or semiconductor), whereas,  $j_z^{max}$  shows the different dependencies on  $m$  for undoped metal and semiconducting CNs. For metal CNs,  $j_z^{max}$  decreases with  $m$  while it increases for semiconducting ones. As  $m \rightarrow \infty$ ,  $j_z^{max}$  for metal and semiconducting CNs tends to the same limit from opposite sides. Generally, at large  $m$ , the I-V characteristics of different CNs are coming close and in the limit case  $m \rightarrow \infty$  they reduce to I-V characteristic of the plane graphite monolayer. It should be noted that the metal CNs exhibit much larger NDC as compared to semiconducting ones. Fig. 2 shows that the doping of metal CNs makes  $J_z^{max}$  some times larger. Doping of semiconducting CNs with small  $m$  does not lead to noticeable changes but as  $m$  increases, current through doped semiconducting CNs increases and values of current density become one order with ones for conducting undoped CNs (Fig. 4).

#### 4. Conclusion

In Summary, we have predicted the NDC effect in both doped and undoped CNs, which is expected to be observable in sufficiently long CNs at room temperatures. I-V curves are expected to be effectively controlled due to doping.

#### Acknowledgement

The research is partially supported through INTAS under project 97-2018 and BMBF under project WEI-001-98.




Fig. 3. Undoped semiconducting zigzag CNs.  
 $T=287,5^{\circ}\text{K}$ ,  $\tau=3 \cdot 10^{-12}$ .




Fig. 4. Doped zigzag CNs with  $m=3q+1$  ( $q$  is an integer).  
 $\mu=0.2$  eV,  $T=287,5^{\circ}\text{K}$ ,  $\tau=3 \cdot 10^{-12}$ .

## References

- [1] S. J. Tans *et al.*, "Individual single-wall carbon nanotubes as quantum wires," *Nature*, London, vol. 386, pp. 474-480, 1997.
- [2] A. Bezryadin *et al.*, "Multiprobe transport experiments on individual single-wall carbon nanotubes," *Phys. Rev. Lett.*, vol. 80, pp. 4036-4039, May 1998.
- [3] A. A. Farajian, K. Estarjani, and Y. Kawazoe, "Nonlinear coherent transport through doped nanotube junctions," *Phys. Rev. Lett.*, vol. 82, pp. 5084-5087, June 1999.
- [4] A. S. Maksimenko and G. Ya. Slepyan, "Negative differential conductivity in carbon nanotubes," *Phys. Rev. Lett.*, vol. 84, pp. 362-365, January 2000.
- [5] M. F. Lin and K. W.-K. Shung, "Magnetization of graphene tubules," *Phys. Rev. B*, vol. 52, pp. 8423-8438, September 1995.
- [6] R. A. Jishi, M. S. Dresselhaus, and G. Dresselhaus, "Electron-phonon coupling and electrical conductivity of fullerene nanotubes," *Phys. Rev. B*, vol. 48, pp. 11385-11389, October 1993.
- [7] C. L. Kane and E. J. Mele, "Size, shape, and low energy electronic structure of carbon nanotubes," *Phys. Rev. Lett.*, vol. 78, pp. 1932-1935, March 1997.
- [8] F. G. Bass and A.A. Bulgakov, *Kinetic and Electrodynamical Phenomena in Classical and Quantum Semiconductor Superlattices*. New York: Nova, 1997.
- [9] Y.-K. Kwon, S. Saito and D. Tomaneck, "Effect of intertube coupling on the electronic structure of carbon nanotube ropes," *Phys. Rev. B*, vol. 58, pp. R13314-R13317, November 1998.
- [10] Yu. A. Krotov, D.-H. Lee, and S. G. Louie, "Low energy properties of (n,n) carbon nanotubes," *Phys. Rev. Lett.*, vol. 78, pp. 4245-4248, June 1997.