AD-753 709

ENGINEERING DESIGN DATA FOR ALUMINUM ALLOY 7475 IN THE T761 AND T61 CONDITION

Russell R. Cervay

Dayton University

Prepared for:

Air Force Materials Laboratory

September 1972

DISTRIBUTED BY:

NTIS

National Technical Information Service
U. S. DEPARTMENT OF COMMERCE
5285 Port Royal Road, Springfield Va. 22151

AFML-TR-72-173

AD753709

ENGINEERING DESIGN DATA FOR ALUMINUM ALLOY 7475 IN THE T761 AND T61 CONDITION

RUSSELL R. CERVAY

UNIVERSITY OF DAYTON
RESEARCH INSTITUTE

TECHNICAL REPORT AFML-TR-72-173

SEPTEMBER 1972

Approved for public release; distribution unlimited.

NATIONAL TECHNICAL
INFORMATION SERVICE

AIR FORCE MATERIALS LABORATORY
AIR FORCE SYSTEMS COMMAND
WRIGHT-PATTERSON AIR FORCE BASE, OHIO

27

NOTICES

When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

A

Copies of this report should not be returned unless otherwise required by security considerations, contractual obligations, or notice on a special document.

AIR FORCE/56780/8 November 1972 - 300

ENGINEERING DESIGN DATA FOR ALUMINUM ALLOY 7475 IN THE T761 AND T61 CONDITION

RUSSELL R. CERVAY

Approved for public release; distribution unlimited.

ic

FOREWORD

This report was prepared by the University of Dayton Research Institute (UDRI), Dayton, Ohio. The work was performed under USAF Contract No. F33615-71-C-1054. The contract was initiated under Project No. 7381, "Materials Applications," Task No. 738106, "Engineering and Design Data," and administered by the Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio, Mr. David C. Watson, AFML/LAE, Project Engineer.

All (or many) of the items compared in this report were commercial items that were not developed or manufactured to meet Government specifications, to withstand the tests to which they were subjected, or to operate as applied during this study. Any failure to meet the objectives of this study is no reflection on any of the commercial items discussed herein or on any manufacturer.

The author would like to acknowledge that testing performed for this program was accomplished by Messrs. Cambron, Eblin, and Maxwell of the UDRI.

The report covers work conducted from April 1971 to February 1972. The contractor's report number if UDRI-TR-72-25.

The report was submitted by the author in April 1972.

This technical report has been reviewed and is approved.

A. OLEVITCH
Chief, Materials Engineering Branch
Materials Support Division

TABLE OF CONTENTS

Section		Page
I	INTRODUCTION	1
II	PROGRAM OUTLINE AND PROCEDURES	2
III	RESULTS AND DISCUSSION	7
IV	CONCLUSIONS	18
V	REFERENCES	19

Preceding page blank

Unclassified
Security Classification

DOCUMENT CONTROL DATA - R&D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1. ORIGINATING ACTIVITY *(Corporate author)*
University of Dayton Research Institute
300 College Park Avenue
Dayton, Ohio 45409

2a. REPORT SECURITY CLASSIFICATION
Unclassified

2b. GROUP

3. REPORT TITLE
ENGINEERING DESIGN DATA FOR ALUMINUM ALLOY 7475 IN THE T761 AND T61 CONDITION

4. DESCRIPTIVE NOTES *(Type of report and inclusive dates)*
Technical Report

5. AUTHOR(S) *(Last name, first name, initial)*
Cervay, Russell R.

6. REPORT DATE
September 1972

7a. TOTAL NO. OF PAGES
~~19~~ 27

7b. NO. OF REFS
3

8a. CONTRACT OR GRANT NO.
F33615-71-C-1054

b. PROJECT NO.
7381

c.
Task No. 738106

d.

9a. ORIGINATOR'S REPORT NUMBER(S)
UDRI-TR-72-25

9b. OTHER REPORT NO(S) *(Any other numbers that may be assigned this report)*
AFML-TR-72-173

10. AVAILABILITY/LIMITATION NOTICES
Approved for public release;distribution is unlimited.

11. SUPPLEMENTARY NOTES

12. SPONSORING MILITARY ACTIVITY
Air Force Materials Laboratory
Air Force Systems Command
Wright-Patterson AFB, Ohio 45433

13. ABSTRACT

Tensile, exfoliation, fatigue, and fatigue crack growth properties were determined for a new aluminum sheet alloy, 7475, in two heat treated conditions, T761 and T61. The tensile properties of the T61 sheet were superior to those for the T761 sheet. The fatigue crack growth properties were the same from heat treatment to heat treatment and were unaffected by crack orientation in the plate. Conventional notched and unnotched fatigue data showed in the 7475 alloy had superior fatigue resistance compared to presently-in-use aluminum alloys. The exfoliation properties of the T761 sheet were slightly superior to those of the T61 heat treatment.

DD FORM 1 JAN 64 1473

Unclassified
Security Classification

Unclassified
Security Classification

14 KEY WORDS	LINK A ROLE	LINK A WT	LINK B ROLE	LINK B WT	LINK C ROLE	LINK C WT
Aluminum						
Tensile						
Exfoliation						
Fatigue						
Crack Growth						
Design Data						

INSTRUCTIONS

1. ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization *(corporate author)* issuing the report.

2a. REPORT SECURITY CLASSIFICATION: Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. GROUP: Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. AUTHOR(S): Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. REPORT DATE: Enter the date of the report as day, month, year; or month, year. If more than one date appears on the report, use date of publication.

7a. TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. NUMBER OF REFERENCES: Enter the total number of references cited in the report.

8a. CONTRACT OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. PROJECT NUMBER: Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. ORIGINATOR'S REPORT NUMBER(S): Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. OTHER REPORT NUMBER(S): If the report has been assigned any other report numbers *(either by the originator or by the sponsor)*, also enter this number(s).

10. AVAILABILITY/LIMITATION NOTICES: Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

(1) "Qualified requesters may obtain copies of this report from DDC."

(2) "Foreign announcement and dissemination of this report by DDC is not authorized."

(3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."

(4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."

(5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSORING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring *(paying for)* the research and development. Include address.

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as *(TS)*, *(S)*, *(C)*, or *(U)*.

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.

ib

*U.S.Government Printing Office: 1972 — 759-487/188

Unclassified
Security Classification

LIST OF FIGURES

Figure		Page
1	Tension Specimen	3
2	Compact Tension Crack Growth Specimen	4
3	Smooth Fatigue Specimen	5
4	Notched Fatigue Specimen	6
5	Yield Strength Versus Temperature for Aluminum Alloy 7475	10
6	Ultimate Strength Versus Temperature for Aluminum Alloy 7475	11
7	Elongation Versus Temperature for Aluminum Alloy 7475	12
8	Crack Growth Rate Versus Stress Intensity Range for Aluminum Alloy 7475	13
9	Notched Fatigue Test Results for Aluminum Alloy 7475	14
10	Smooth Fatigue Test Results for Aluminum Alloy 7475	15
11	Exfoliation Samples Rolled Surfaces After 1200-Hour Exposure	16
12	Beveled Edge of Exfoliation Samples After 1200-Hour Exposure	17

LIST OF TABLES

Table		Page
I	Tensile Properties of 7475-T761 and T61 Aluminum Alloy Sheet	8

SECTION I

INTRODUCTION

This program was initiated to develop engineering design data for the new aluminum sheet alloy, 7475, in two different heat treatments: T61 and T761. The aluminum sheet alloy is represented by Alcoa (Aluminum Company of America) as being one of the promising new aerospace alloys. Initial testing indicates that the material's fracture toughness and resistance to fatigue crack propagation are superior to aluminum alloy 7075-T6. The material, with its higher strength than currently-in-use aluminum alloys, will afford a lighter structure and/or increased structural life.

SECTION II

PROGRAM OUTLINE AND PROCEDURES

Two sheets of the material, 0.090 inches thick, were provided by Alcoa for the program. The sheets were of different heat treatments: T61 and T761.

The material properties that were investigated in this program were: (a) tensile, (b) fatigue crack growth, (c) fatigue (notched and smooth), and (d) exfoliation.

Tensile testing was performed at -65°F, 200°F, and room temperature in both the longitudinal (L) and transverse (T) directions. The data was obtained using conventional tensile specimens and procedures (see Figure 1).

Room temperature fatigue crack growth testing was performed with the crack oriented in both the longitudinal and transverse directions. A compact tension specimen was used for the cyclic crack growth testing (see Figure 2). Because of the thinness of the sample, doublers were used to prevent the samples from buckling.

An S-N curve was generated for both notched and smooth specimens in the longitudinal and transverse orientation (see Figures 3 and 4). All of the fatigue testing was performed in a room temperature laboratory environment.

The exfoliation testing was accomplished with rectangular samples with the edges beveled at a 45 degree angle. The exposure was for 1200 hours in an environmental chamber maintained at 120°F and 100 percent relative humidity.



Figure 1. Tension Specimen



Figure 2. Compact Tension Crack Growth Specimen



Figure 3. Smooth Fatigue Specimen



Figure 4. Notched Fatigue Specimen

SECTION III

RESULTS AND DISCUSSION

The results of the tensile tests are presented in Table I and Figures 5 through 7. The tensile properties are, in general, comparable to aluminum alloys 7075-T76, 7075-T651, and 2024-T851 (References 1-3). The T61 heat treatment had superior strength to the T761 heat treatment.

The cyclic crack growth test results are presented in Figure 8. There was no noticeable difference in crack growth rate with a change in specimen orientation. Any apparent difference caused by a change in heat treatment was fictitious, as all data was within a small scatter band.

The fatigue test results are presented in Figures 9 and 10. There is a great deal of scatter in the fatigue data for both the notched and smooth specimen configurations. The alloy appears to have superior fatigue properties when compared to aluminum alloys 7075 and 2024 (References 1-3). Due to the great scatter in the test data, there is no conclusive evidence that either of the two heat treatments is superior in fatigue.

On the rolled surfaces of the exfoliation samples, the degree of staining is approximately the same for the two heat treatments involved in the program (see Figure 11). However, the beveled edges of the T61 heat treated specimen are pitted (see Figure 12). The edges of the T761 sample were not affected by the environment to which they were exposed. In general, the aluminum alloy stood up very well to the corrosive environment.

TABLE I

Tensile Properties of 7475-T761 and T61 Aluminum Alloy Sheet
(0.090 inch thick)

Specimen	Heat Treatment	Temperature °F	Direction	Ultimate Strength ksi	Yield Strength ksi	Elongation in 2 in. G.L. %	Reduction of Area %
TR2	T761	-65	Longitudinal	76.5	65.8	12.3	29.2
TR5		-65		76.5	66.0	13.8	18.6
TR8		-65		76.3	66.0	12.3	29.8
TR1		R.T.		70.6	62.8	13.5	23.8
TR4		R.T.		70.0	61.8	13.2	28.0
TR7		R.T.		70.0	61.9	13.5	28.0
TR3		200		59.8	57.8	19.2	31.1
TR6		200		60.8	58.6	14.4	27.7
TR9		200		60.8	59.0	14.9	33.2
TT2	T761	-65	Transverse	77.4	65.7	12.0	30.5
TT5		-65		76.8	64.1	13.7	29.2
TT8		-65		76.2	63.9	13.6	30.1
TT1		R.T.		71.6	62.2	13.2	31.8
TT4		R.T.		70.9	61.4	13.8	20.5
TT7		R.T.		70.6	60.7	12.8	28.3
TT3		200		61.0	57.2	17.0	35.0
TT6		200		59.8	56.2	15.3	36.0
TT9		200		59.6	55.8	17.5	33.7
TR2	T61	-65	Longitudinal	83.5	78.4	13.4	31.4
TR5		-65		83.0	77.7	13.7	30.2
TR8		-65		82.7	77.7	11.9	28.3
TR1		R.T.		78.5	74.0	13.4	26.5
TR4		R.T.		78.6	73.9	14.1	29.7

TABLE I (Continued)

Specimen	Heat Treatment	Temperature °F	Direction	Ultimate Strength ksi	Yield Strength ksi	Elongation in 2 in. G.L. %	Reduction of Area %
TR7	T61	R.T.	Longitudinal	78.3	73.7	12.5	23.9
TR3		200		70.1	69.4	15.7	36.6
TR6		200		70.2	69.5	17.7	33.2
TR9		200		70.2	69.5	18.2	32.1
TT2	T61	-65	Transverse	84.1	78.3	12.8	23.9
TT5		-65		84.3	76.4	12.7	25.2
TT8		-65		84.2	76.5	11.8	23.9
TT1		R.T.		79.8	71.3	14.1	29.2
TT4		R.T.		78.7	74.4	13.5	30.3
TT7		R.T.		78.9	71.1	12.6	27.1
TT3		200		70.9	66.4	15.9	35.4
TT6		200		70.2	66.7	16.4	33.0
TT9		200		70.3	66.6	13.1	33.3



Figure 5. Yield Strength Versus Temperature for Aluminum Alloy 7475



Figure 6. Ultimate Strength Versus Temperature for Aluminum Alloy 7475



Figure 7. Elongation Versus Temperature for Aluminum Alloy 7475



Figure 8. Crack Growth Rate Versus Stress Intensity Range for Aluminum Alloy 7475



Figure 9. Notched Fatigue Test Results for Aluminum Alloy 7475



Figure 10. Smooth Fatigue Test Results for Aluminum Alloy 7475

Reproduced from best available copy.



Figure 11. Exfoliation Samples Rolled Surfaces After 1200-Hour Exposure

Reproduced from best available copy.



Figure 12. Beveled Edge of Exfoliation Samples After 1200-Hour Exposure

SECTION IV

CONCLUSIONS

1. The T61 heat treatment for aluminum alloy 7475 has superior tensile strength with no sacrifice in ductility when compared to the T761 heat treatment material.

2. The fatigue crack growth rate of aluminum alloy 7475 is comparable to other aluminum alloys.

3. There is no noticeable variation in crack growth rate between the two heat treatments or with a change in crack orientation.

4. The alloy 7475 is superior in fatigue to other currently-in-use aluminum alloys.

5. The test material showed good exfoliation resistance with the T761 heat treatment slightly superior to the T61.

SECTION V

REFERENCES

1. Alcoa Aerospace Technical Information Bulletin, Series 71, Number 6.

2. Alcoa Aerospace Technical Information Bulletin, Series 69, Number 4.

3. Tensile, Fracture Toughness, and Fatigue Properties of 2024-T851, University of Dayton Research Institute, UDRI-DR-71-05, June 1971.