AD-A118 801 CENTER FOR INFORMATION AND NUMERICAL DATA ANALYSIS AN--ETC F/G 7/2
ABSORPTION COEFFICIENT OF ALKALI HALIDES. PART I.(U)
MAR 79 H H LI F49620-76-C-0105
UNCLASSIFIED CINDAS-54 AFOSR-TR-82-0687 NL

1 of 3
AD
A118801

CINDAS

AFOSR-TR- 82-0687

CINDAS

AD A118801

THERMOPHYSICAL PROPERTIES RESEARCH CENTER
ELECTRONIC PROPERTIES INFORMATION CENTER
THERMOPHYSICAL AND ELECTRONIC PROPERTIES INFORMATION ANALYSIS CENTER
UNDERGROUND EXCAVATION AND ROCK PROPERTIES INFORMATION CENTER

ABSORPTION COEFFICIENT OF ALKALI HALIDES (PART I)

By

H. H. LI

DTIC
ELECTE
SEP 2 1982
S D
H

CINDAS-REPORT 54

March 1979

Copy available to DTIC does not permit fully legible reproduction

Approved for public release; distribution unlimited.

Prepared for

AIR FORCE OFFICE OF SCIENTIFIC RESEARCH
Department of the Air Force
Bolling Air Force Base
Washington, D.C. 20332

DTIC FILE COPY

CENTER FOR INFORMATION AND NUMERICAL DATA ANALYSIS AND SYNTHESIS
PURDUE UNIVERSITY
PURDUE INDUSTRIAL RESEARCH PARK
2595 YEAGER ROAD
WEST LAFAYETTE, INDIANA 47906

82 09 01 029

DISCLAIMER NOTICE

THIS DOCUMENT IS BEST QUALITY PRACTICABLE. THE COPY FURNISHED TO DTIC CONTAINED A SIGNIFICANT NUMBER OF PAGES WHICH DO NOT REPRODUCE LEGIBLY.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER AFOSR-TR- 82-0687	2. GOVT ACCESSION NO. AD-A118 801	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) ABSORPTION COEFFICIENT OF ALKALI HALIDES (PART I)		5. TYPE OF REPORT & PERIOD COVERED INTERIM 1 MAY 78 - 30 APR 79
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) H H LI		8. CONTRACT OR GRANT NUMBER(s) F49620-76-C-0105
9. PERFORMING ORGANIZATION NAME AND ADDRESS PURDUE UNIVERSITY 2595 YEAGER RD WAST LAFAYETTE, IN 47906		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS 2308/A1 61102F
11. CONTROLLING OFFICE NAME AND ADDRESS AIR FORCE OFFICE OF SCIENTIFIC RESEARCH/NA BOLLING AIR FORCE BASE, DC 20332		12. REPORT DATE MARCH 1979
		13. NUMBER OF PAGES 262
14. MONITORING AGENCY NAME & ADDRESS(if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE

16. DISTRIBUTION STATEMENT (of this Report)

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)

18. SUPPLEMENTARY NOTES

19. KEY WORDS (Continue on reverse side if necessary and identify by block number)

ABSORPTION COEFFICIENT
OPTICAL CONSTANTS
ALKALI HALIDES

20. ABSTRACT (Continue on reverse side if necessary and identify by block number)

Data on absorption coefficients of alkali halides were complied and analyzed. The bulk of available data were concentrated to the absorption edges of the main transparent region and were for the seven materials LiF, NaF, NaCl, KCl, KBr, KI, and CsI. Although the intrinsic absorption can be calculated by using the exponential dependence of absorption coefficient on frequency, discrepancies occur in the region where absorption is extremely low. At low absorption levels, extrinsic absorptions due to impurities and surface contamination domin-

DD FORM 1 JAN 73 1473 EDITION OF 1 NOV 65 IS OBSOLETE

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

82 09 01 029

ate the intrinsic absorption by factors ranging from fractions to factors by ten. Experience has shown that extrinsic contributions can be reduced through improved crystal preparation. Another possible reason for the discrepancies may be the limit of instrument sensitivity. The results of this work on the alkali halides are given in two separate reports. Presented in this report are essentially the up-to-date owledge of available data and the recommended room-temperature values of sorption coefficient in the laser wavelength and multiphonon absorption rep . In the second report, results on the data analysis and theoretical dies for the temperature dependence of absorption coefficient will be given

ABSORPTION COEFFICIENT OF ALKALI HALIDES (PART I)

By

H. H. LI

CINDAS REPORT 54

March 1979

Prepared for

AIR FORCE OFFICE OF SCIENTIFIC RESEARCH
Department of the Air Force
Bolling Air Force Base
Washington, D.C. 20332

AIR FORCE OFFICE OF SCIENTIFIC RESEARCH (AFSC)
NOTICE OF TRANSMITTAL TO DTIC
This technical report has been reviewed and is
approved for public release IAW AFR 190-12.
Distribution is unlimited.
MATTHEW J. KERPER
Chief, Technical Information Division

CENTER FOR INFORMATION AND NUMERICAL DATA
ANALYSIS AND SYNTHESIS
Purdue Industrial Research Park
2595 Yeager Road
West Lafayette, Indiana 47906

ABSTRACT

Experimental data on the absorption coefficient of alkali halides were searched, compiled, and analyzed. It was found that the bulk of available data were concentrated to the absorption edges of the main transparent region and were for the seven materials LiF, NaF, NaCl, KCl, KBr, KI, and CsI. Although the intrinsic absorption can be calculated by using the exponential dependence of absorption coefficient on frequency which is formulated on the basis of available data, discrepancies occur in the region where absorption is extremely low, as observed at the wavelengths of interest to laser technology. At low absorption levels, extrinsic absorptions due to impurities and surface contamination dominate the intrinsic absorption by factors ranging from fractions to factors by ten. Experience has shown that extrinsic contributions can be reduced through improved crystal growing and surface polishing techniques. Another possible reason for the discrepancies may be the limit of instrument sensitivity, since absorption coefficient lower than 7×10^{-6} cm^{-1} cannot be detected with certainty.

The results of this work on the alkali halides are given in two separate reports. Presented in this report are essentially the up-to-date knowledge of available data and the recommended room-temperature values of absorption coefficient in the laser wavelength and multiphonon absorption region. In the second report, results on the data analysis and theoretical studies for the temperature dependence of absorption coefficient will be given.

Accession For
NTIS GRA&I
DTIC TAB
Unannounced
Justification
By
Distribution/
Availability Codes
Dist | Avail and/or Special
A

DTIC COPY INSPECTED

Key Words: absorption coefficient, optical constants, alkali halides.

TABLE OF CONTENTS

	Page
LIST OF TABLES	vii
LIST OF FIGURES	xi
LIST OF SYMBOLS	xv
1. INTRODUCTION	1
2. BACKGROUND ON THEORETICAL CONSIDERATIONS AND METHODS OF MEASUREMENT	7
3. NUMERICAL DATA	17
Presentation of Data	17
3.1. Lithium Fluoride, LiF	21
3.2. Sodium Fluoride, NaF	69
3.3. Sodium Chloride, NaCl	97
3.4. Potassium Chloride, KCl	127
3.5. Potassium Bromide, KBr	159
3.6. Potassium Iodide, KI	189
3.7. Cesium Iodide, CsI	215
4. SUMMARY OF RESULTS AND RECOMMENDATIONS	235
5. REFERENCES	241
APPENDIX	255

PRECEDING PAGE B

LIST OF TABLES

		Page
1.	Some Physical Properties of Alkali Halides	4
2.	Available Parameters for Dispersion Equations of Alkali Halides at Room Temperature	15
3.	Summary of Measurements on the Absorption Coefficient of Lithium Fluoride (Wavenumber Dependence)	30
4.	Experimental Data on the Absorption Coefficient of Lithium Fluoride (Wavenumber Dependence)	35
5.	Summary of Measurements on the Absorption Coefficient of Lithium Fluoride (Temperature Dependence)	43
6.	Experimental Data on the Absorption Coefficient of Lithium Fluoride (Temperature Dependence)	44
7.	Summary of Measurements on the Reflectivity of Lithium Fluoride	46
8.	Experimental Data on the Reflectivity of Lithium Fluoride	49
9.	Summary of Measurements on the Transmission of Lithium Fluoride	58
10.	Experimental Data on the Transmission of Lithium Fluoride	61
11.	Peak Positions (λ_{max}) in μm and Half-Widths (W) in eV for the F, R, M, and N Absorption Bands in Lithium Fluoride	66
12.	Recommended Values on Absorption Coefficient of Lithium Fluoride in IR Region at 300 K	67
13.	Summary of Measurements on the Absorption Coefficient of Sodium Fluoride (Wavenumber Dependence)	77
14.	Experimental Data on the Absorption Coefficient of Sodium Fluoride (Wavenumber Dependence)	78
15.	Summary of Measurements on the Absorption Coefficient of Sodium Fluoride (Temperature Dependence)	81
16.	Experimental Data on the Absorption Coefficient of Sodium Fluoride (Temperature Dependence)	82
17.	Summary of Measurements on the Reflectivity of Sodium Fluoride	85
18.	Experimental Data on the Reflectivity of Sodium Fluoride	87
19.	Summary of Measurements on the Transmission of Sodium Fluoride	93
20.	Experimental Data on the Transmission of Sodium Fluoride	94

PRECEDING PAGE BLANK NOT FILMED

21. Peak Positions (λ_{max}) in μm and Half-Widths (W) in eV for the F, R, M, and N Absorption Bands in Sodium Fluoride 95

22. Recommended Values on Absorption Coefficient of Sodium Fluoride in IR Region at 300 K 96

23. Summary of Measurements on the Absorption Coefficient of Sodium Chloride (Wavenumber Dependence) 105

24. Experimental Data on the Absorption Coefficient of Sodium Chloride (Wavenumber Dependence) 109

25. Summary of Measurements on the Absorption Coefficient of Sodium Chloride (Temperature Dependence) 115

26. Experimental Data on the Absorption Coefficient of Sodium Chloride (Temperature Dependence) 116

27. Summary of Measurements on the Reflectivity of Sodium Chloride . . 118

28. Experimental Data on the Reflectivity of Sodium Chloride 119

29. Summary of Measurements on the Transmission of Sodium Chloride . . 121

30. Experimental Data on the Transmission of Sodium Chloride 122

31. Peak Positions (λ_{max}) in μm and Half-Widths (W) in eV for the F, R, M, and N Absorption Bands in Sodium Chloride 124

32. Recommended Values on Absorption Coefficient of Sodium Chloride in IR Region at 300 K 125

33. Summary of Measurements on the Absorption Coefficient of Potassium Chloride (Wavenumber Dependence) 137

34. Experimental Data on the Absorption Coefficient of Potassium Chloride (Wavenumber Dependence) 141

35. Summary of Measurements on the Absorption Coefficient of Potassium Chloride (Temperature Dependence) 147

36. Experimental Data on the Absrotpion Coefficient of Potassium Chloride (Temperature Dependence) 148

37. Summary of Measurements on the Reflectivity of Potassium Chloride 150

38. Experimental Data on the Reflectivity of Potassium Chloride . . . 151

39. Summary of Measurements on the Transmission of Potassium Chloride 155

40. Experimental Data on the Transmission of Potassium Chloride . . . 156

41. Peak Positions (λ_{max}) in μm and Half-Widths (W) in eV for the F, R, M, and N Absorption Bands in Potassium Chloride 157

42. Recommended Values on Absorption Coefficient of Potassium Chloride in IR Region at 300 K 158

43. Summary of Measurements on the Absorption Coefficient of Potassium Bromide (Wavenumber Dependence) 167

44. Experimental Data on the Absorption Coefficient of Potassium Bromide (Wavenumber Dependence) 171

45. Summary of Measurements on the Absorption Coefficient of Potassium Bromide (Temperature Dependence) 176

46. Experimental Data on the Absorption Coefficient of Potassium Bromide (Temperature Dependence) 177

47. Summary of Measurements on the Reflectivity of Potassium Bromide 179

48. Experimental Data on the Reflectivity of Potassium Bromide . . . 180

49. Summary of Measurements on the Transmission of Potassium Bromide 184

50. Experimental Data on the Transmission of Potassium Bromide . . . 185

51. Peak Positions (λ_{max}) in μm and Half-Widths (W) in eV for the F, R, M, and N Absorption Bands in Potassium Bromide 186

52. Recommended Values on Absorption Coefficient of Potassium Bromide in IR Region at 300 K 187

53. Summary of Measurements on the Absorption Coefficient of Potassium Iodide (Wavenumber Dependence) 195

54. Experimental Data on the Absorption Coefficient of Potassium Iodide (Wavenumber Dependence) 197

55. Summary of Measurement on the Absorption Coefficient of Potassium Iodide (Temperature Dependence) 201

56. Experimental Data on the Absorption Coefficient of Potassium Iodide (Temperature Dependence) 202

57. Summary of Measurements on the Reflectivity of Potassium Iodide 204

58. Experimental Data on the Reflectivity of Potassium Iodide 206

59. Summary of Measurements on the Transmission of Potassium Iodide 211

60. Experimental Data on the Transmission of Potassium Iodide 212

61. Peak Positions (λ_{max}) in μm and Half-Widths (W) in eV for the F, R, M, and N Absorption Bands in Potassium Iodide 213

62. Recommended Values on Absorption Coefficient of Potassium Iodide in IR Region at 300 K 214

63. Summary of Measurements on the Absorption Coefficient of Cesium Iodide (Wavenumber Dependence) 220

64. Experimental Data on the Absorption Coefficient of Cesium Iodide (Wavenumber Dependence) 222

65. Summary of Measurements on the Absorption Coefficient of Cesium Iodide (Temperature Dependence) 226

66. Experimental Data on the Absorption Coefficient of Cesium Iodide (Temperature Dependence) 227

67. Summary of Measurements on the Reflectivity of Cesium Iodide . . . 229

68. Experimental Data on the Reflectivity of Cesium Iodide 230

69. Summary of Measurements on the Transmission of Cesium Iodide . . . 232

70. Experimental Data on the Transmission of Cesium Iodide 233

71. Peak Positions (λ_{max}) in μm and Half-Widths (W) in eV for the F, R, M, and N Absorption Bands in Cesium Iodide 234

LIST OF FIGURES

		Page
1.	Typical Absorption Spectrum of an Alkali-Halide Crystal	2
2.	Schematic Absorption Spectrum of an Alkali Halide in Semilogarithismic Scale	13
3.	Absorption Coefficient of Lithium Fluoride (Wavenumber Dependence)	27
4.	Absorption Coefficient of Lithium Fluoride in the Urbach Tail Region	28
5.	Absorption Coefficient of Lithium Fluoride in the Multiphonon Region	29
6.	Absorption Coefficient of Lithium Fluoride (Temperature Dependence)	42
7.	Reflectivity of Lithium Fluoride	45
8.	Transmission of Lithium Fluoride	57
9.	Absorption Coefficient of Sodium Fluoride (Wavenumber Dependence)	74
10.	Absorption Coefficient of Soidum Fluoride in the Urbach Tail Region	75
11.	Absorption Coefficient of Sodium Fluoride in the Multiphonon Region	76
12.	Absorption Coefficient of Sodium Fluoride (Temperature Dependence)	80
13.	Reflectivity of Sodium Fluoride	84
14.	Transmission of Sodium Fluoride	92
15.	Absorption Coefficient of Sodium Chloride (Wavenumber Dependence)	102
16.	Absorption Coefficient of Sodium Chloride in the Urbach Tail Region	103
17.	Absorption Coefficient of Sodium Chloride in the Multiphonon Region	104
18.	Absorption Coefficient of Sodium Chloride (Temperature Dependence)	114
19.	Reflectivity of Sodium Chloride	117
20.	Transmission of Sodium Chloride	120

21. Absorption Coefficient of Potassium Chloride (Wavenumber Dependence) 134

22. Absorption Coefficient of Potassium Chloride in the Urbach Tail Region 135

23. Absorption Coefficient of Potassium Chloride in the Multiphonon Region 136

24. Absorption Coefficient of Potassium Chloride (Temperature Dependence) 146

25. Reflectivity of Potassium Chloride 149

26. Transmission of Potassium Chloride 154

27. Absorption Coefficient of Potassium Bromide (Wavenumber Dependence) 164

28. Absorption Coefficient of Potassium Bromdie in the Urbach Tail Region 165

29. Absorption Coefficient of Potassium Bromide in the Multiphonon Region 166

30. Absorption Coefficient of Potassium Bromide (Temperature Dependence) 175

31. Reflectivity of Potassium Bromide 178

32. Transmission of Potassium Bromide 183

33. Absorption Coefficient of Potassium Iodide (Wavenumber Dependence) 192

34. Absorption Coefficient of Potassium Iodide in the Urbach Tail Region 193

35. Absorption Coefficient of Potassium Iodide in the Multiphonon Region 194

36. Absorption Coefficient of Potassium Iodide (Temperature Dependence) 200

37. Reflectivity of Potassium Iodide 203

38. Transmission of Potassium Iodide 210

39. Absorption Coefficient of Cesium Iodide (Wavenumber Dependence). . 217

40. Absorption Coefficient of Cesium Iodide in the Urbach Tail Region 218

41. Absorption Coefficient of Cesium Iodide in the Multiphonon Region 219

42. Absorption Coefficient of Cesium Iodide (Temperature Dependence) . 225

43. Reflectivity of Cesium Iodide 228

44. Transmission of Cesium Iodide 231

45. Semi-Log Plot of ν_o of Alkali Halides as a Function of 1/M . . . 237

Appendix
Figures

A1. Absorption Coefficient of Lithium Fluoride in vuv Region 256

A2. Absorption Coefficient of Sodium Fluoride in vuv Region 257

A3. Absorption Coefficient of Sodium Chloride in vuv Region 258

A4. Absorption Coefficient of Potassium Chloride in vuv Region . . . 259

A5. Absorption Coefficient of Potassium Bromide in vuv Region 260

A6. Absorption Coefficient of Potassium Iodide in vuv Region 261

A7. Absorption Coefficient of Cesium Iodide in vuv Region 262

LIST OF SYMBOLS

A	constant
B	constant
c	constant
C	constant; calorimetric method
d	thickness of specimen
E	energy in units of eV
E_o	constant
E_a	energy absorbed
E_T	energy transmitted
f	frequency of radiation
h	Plank constant
k	Boltzmann constant
L	length of specimen
n	refractive index
R	apparent reflectivity; reflection method
R_∞	reflectivity at normal incidence without contribution from multiple internal reflection
$\bar{R}$	complex reflectivity
S_i	strengths of the ith oscillator
t	thickness of specimen
T	temperature; trnamission method
Z	transmission and reflection method

Greek Symbols

α	absorption coefficient in units of cm^{-1}
α_o	constant
γ	phase angle

PRECEDING PAGE B

γ_i	damping factor of the ith oscillator
ε	complex dielectric constant
ε_1	real part of complex dielectric constant
ε_2	imaginary part of complex dielectric constant
θ	phase angle
κ	absorption index
λ	wavelength in units of μm
ν	wavenumber in units of cm^{-1}
σ	absorption per surface
σ_s	steepness parameter in Urbach relations
σ_{so}	constant
τ	transmission
τ_∞	transmission at normal incidence without contribution from multiple internal reflection
ψ	phase change upon reflection
ω	frequency of radiation
ω_i	frequency of the ith oscillator

1. INTRODUCTION

The purpose of this work is to present and review the available data and information on the absorption coefficient of alkali halides, to critically evaluate, analyze, and synthesize the data, and to make recommendations for the most probable values of the absorption coefficient. The investigation covers the widest possible wavelength and temperature ranges and is based on the purest samples of alkali halides.

The need for ultraviolet and infrared photographic and detecting devices and the development of high-energy lasers and their associated applications have resulted in requirements for a wide variety of highly transparent optical components, such as windows, lenses, and polarizers. In selecting materials of practical importance, one is concerned with the transparent region which covers various lines of interest. For a given crystal, the width of the main transparent region is governed by two factors. On the short wavelength side, transmission is restricted by electronic excitation, and for long wavelengths by molecular vibrations and rotations. The width of the transparent spectral range increases as the energy for electronic excitation is increased and that for molecular vibrations decreased. Theoretical and experimental studies on the ionic crystals indicate that crytslas having small ions with strong bonding have a wide ultraviolet transparency; this is true for alkali halides. In Figure 1, a schematic view of the absorption spectrum of a typical alkali halide crystal is shown. At the right ($\sim$40 μm) are seen the absorption peaks associated with optical phonons while nearer to the left ($\sim$0.15 μm) are seen the absorption peaks associated with excitons. It is seen that the transparent region of alkali halides covers a spectral range that is suitable to most practical applications.

The alkali halides are typical ionic compounds and their physical properties are in general well understood. The majority of the alkali halides crystallize in the rock salt structure in which each cation (alkali metal ion) is surrounded by six nearest neighbor anions (halogen ions), and each anion by six nearest neighbor cations. The cations and anions are each situated on the points of separate face-centered cubic lattices, and these two lattices are interleaved with each other. This type of crystal is called the β-form. A few of the alkali halides normally crystallize in a slightly different arrangement,



Figure 1. Typical Absorption Spectrum of an Alkali-Halide Crystal

typified by the room-temperature structure of cesium chloride. In this structure, each cation is surrounded by eight nearest neighbor anions and conversely. The cations and anions in this structure may be considered to occupy, respectively, the points of two inter-penetrating simple cubic lattices. This type of crystal is called the α-form. A few physical properties of alkali halide crystals are listed in Table 1.

The applications of high-power infrared lasers, which are now being developed at a rapid rate, are largely limited by the lack of suitable transparent optical materials. As a result, much of the high-power laser research is directed toward finding adequate high-temperature window and dome materials in the wavelength region of 2 to 6 μm and near 10.6 μm. The alkali halides have large transmission ranges from the ultraviolet to the infrared and are available in large sizes and high purity. They are excellent materials for photochemists who are interested in ultraviolet transparency and for laser scientists who are considered with infrared transmission. In spite of their intrinsic physical weaknesses, they are considered good window materials and are recommended by the National Materials Advisory Board [1]. Efforts are being made to improve their mechanical strength and thermal endurance without altering their optical properties.

Among the various optical properties, those of practical importance are refractive index and absorption coefficient. The latter is especially important in the application of high-energy lasers because many unfavorable effects, which are not observed at low energy level, are developed at high power levels. No matter how low the absorption is, the effect is objectionable at high-energy levels. As a natural consequence, the magnitude of absorption coefficient is the key parameter in selecting the laser window materials.

Over the past years extensive theoretical and experimental investigations have been conducted in an effort to determine the absorption property for optical materials and to identify the mechanisms influencing the absorption. As a result, numerous measurements and calculations have been reported. However, the available information is dispersed through the literature chronologically as well as geographically. A concise and comprehensive literature survey, data compilation, and analysis is still not available. Yet the overall profile of the available data and predictions of most probable values are indispensible for scientific research and engineering applications. Because of this reason,

TABLE 1. SOME PHYSICAL PROPERTIES OF ALKALI HALIDES

Material	Structure[a]	Space Group[a]	Density[a] ($g\ cm^{-3}$)	Melting[c] Point (K)	Energy[d] Gap (ev)	Solubility[b] in Water at 298 K ($10^2\ g\ cm^{-3}$)	Molecular Weight[c]	Linear[a] Exp. Coef. at 293 K ($10^{-6}\ K^{-1}$)	Thermal[e] Conductivity at 293 K ($W\ m^{-1}\ K^{-1}$)	Specific[c] Heat at 298 K ($cal\ mole^{-1}\ K^{-1}$)	Transmission[e] Region (μm)	Young's[e] Modulus ($10^{10}\ N\ m^{-2}$)	Hardness[e] (Kr top Nat.)
LiF	Cubic(NaCl)	Fm3m	2.601	1121.3	13.1	0.27	25.9374	33.2		9.994	0.12-9.0	6.481	102-113
LiCl	Cubic(NaCl)	Fm3m	2.06_8	883 ± 2	~10	63.7	42.397	43.8		11.479			
LiBr	Cubic(NaCl)	Fm3m	3.46_4	823	~ 8.5	145.0	86.848	49.8		11.692			
LiI	Cubic(NaCl)	Fm3m	4.06_1	742	≥ 5.9	165.0	133.8434	59.4		11.970			
NaF	Cubic(NaCl)	Fm3m	2.79	1269 ± 2	10.5	4.22	41.9882	31.7		11.198	0.19-15.0		
NaCl	Cubic	Fm3m	2.16_4	1073.5 ± 1.0	8.97	35.7	58.448	39.7	6.4	12.072	0.21-26.0	3.999	19.2
NaBr	Cubic(NaCl)	Fm3m	3.210	1020	7.7	116.0	102.907	42.3		12.285			
NaI	Cubic(NaCl)	Fm3m	3.665	933	≥ 5.8	184.0	149.901	45.5		12.482			
KF	Cubic(NaCl)	Fm3m	2.505	1131	10.9	92.3	58.1004	34.8		11.707			
KCl	Cubic(NaCl)	Fm3m	1.9917	1044	8.5	34.7	74.555	37.1	7.0	12.258	0.21-30.0	2.965	9.3
KBr	Cubic(NaCl)	Fm3m	2.754	1007	7.6	53.48	119.011	38.7	5.0	12.500	0.25-40.0	2.689	7.0
KI	Cubic(NaCl)	Fm3m	3.114	954	6.2	127.5	166.0064	40.8	3.1	12.614	0.25-45.0	2.151	
RbF	Cubic(NaCl)	Fm3m	2.88	1033	10.4	130.6	104.47	27.5					
RbCl	Cubic(NaCl)	Fm3m	2.76	958	8.3	77.0	120.92	36.0					
RbBr	Cubic(NaCl)	Fm3m	3.35	955	7.7	98.0	165.38	37.5					
RbI	Cubic(NaCl)	Fm3m	3.55	915	5.63	152.0	212.37	41.5					
CsF	Cubic(NaCl)	Fm3m	3.55_3	976	10.0	367.0	151.9034	32.0		12.420			
CsCl	Cubic	Pm3m	3.938	tr. 743	≥ 8.0								
CsCl(β)	Cubic(NaCl)	Fm3m	3.54(calc.)	918	≥ 7.5	162.22	168.358	46.3		12.534			
CsBr	Cubic(CsCl)	Pm3m	4.43_3	909	7.0-8.0	124.3	212.81	47.4	0.94		0.3 -55.0	1.586	19.5
CsI	Cubic(CsCl)	Pm3m	4.51	894	≥ 6.3	44.0	259.81	49.0	1.2		0.25-80.0	0.530	

[a] Information is taken from American Institute of Physics Handbook, 3rd Edition, Ref. [2], except the linear expansion coefficients of six materials; those of KF, RbF are from Ref. [3], while those of RbCl, RbBr, RbI, and CsF are from Ref. [4].

[b] Values are from Handbook of Chemistry and Physics, Ref. [5].

[c] Values are from JANAF Thermochemical Tables, Ref. [6].

[d] Values are obtained from Ref. [2, 7].

[e] Values are obtained from Handbook of Military infrared Technology, Ref. [8].

the present work was initiated. Inherent in the character of this work is the fact that we have drawn most heavily upon the scientific literature and feel a debt of gratitude to the authors whose results have been used.

Although all of the alkali halides are, in principle, good optical materials, some of them, however, are intrinsically unsuitable for ordinary applications. They are either physically inadequate or chemically unstable. As a result, available data on the optical constants are concentrate to the following seven materials: LiF, NaF, NaCl, KCl, KBr, KI, and CsI, which are being presented in this work.

Results of the present work are given in two separate reports, Part I and Part II. The first report constitutes essentially the reporting of current status of available data. Material is comprehensively compiled and displayed so that one can see at a glance the spectral distribution of available data and the variation of data with respect to temperature and frequency. In addition, efforts are made to generate recommended values of absorption coefficient for the laser wavelengths and the multiphonon region. The result is an expression that relates the molecular weight of the crystal and a key parameter in an equation that predicts the intrinsic absorption coefficient. Details of this finding is discussed in the section of the report entitled "Summary of Results and Recommendations." In the second report, which will be submitted later, efforts on data analysis and theoretical studies are discussed. It has been experimentally observed in alkali halide crystals, that the exponential dependence of absorption coefficient on frequency holds in the multiphonon region as well as in the Urbach tail region. Furthermore, a power law seems to be generally valid in relating the absorption coefficient with temperature in the temperature region >200 K. All of these features are clearly displayed in the first report. It can be seen that analytical expressions similar to those for the Urbach tail can be formulated for the multiphonon region.

2. BACKGROUND ON THEORETICAL CONSIDERATIONS AND METHODS OF MEASUREMENT

The study of the propagation of light through matter, particularly solids, comprises one of the important and interesting branches of optics. The many and varied optical phenomena exhibited by solids include selective absorption, dispersion, double refraction, polarization effects, and electro-optical and magneto-optical effects. Many of the optical properties of solids can be understood on the basis of classical electromagnetic theory.

The macroscopic electromagnetic state of solids, at a given site, is described by four quantities:

(i) The volume density of electric charge
(ii) The volume density of electric dipoles, called the polarization
(iii) The volume density of magnetic dipoles, called the magnetization
(iv) The electric current per unit area, called the current density

All of these quantities are considered to be macroscopically averaged in order to smooth out the microscopic variations due to the atomic makeup of matter. They are related to the macroscopically averaged electric and magnetic fields by the well known Maxwell equations [9].

Detailed discussion of Maxwell's equations is beyond the intended scope of the present work. What we should bear in mind is that the general solution of Maxwell's equations is a wave function for electric or magnetic field. In the treatment of the interaction of light and matter, the light is considered as an oscillating electric field that engulfs the constituent molecules of matter. Each of the molecules may be considered to be a charged simple harmonic oscillator. When these constituent oscillators are driven by the engulfing electric field of light they become excited by that field and emit Huygens-like spherical wavelets. In the early development of the theory of propagation of light in matter, there was no practical alternative to treating the matter as a collection of charged harmonic oscillators subject, perhaps, to damping forces. The modern developments in the theory of matter and its interaction with radiation, have shown that this simple model has broad utility, and that it can be employed in the discussion of optical constants.

The theory of the optical properties of single crystals is well known and has been extensively reviewed. Hence, in this section, rather than discuss the derivation of the theory in detail, we will instead simply define

PRECEDING PAGE B

theoretical constants, their inter-relationship, and how they appear in expressions for experimentally measurable quantities such as transmission, reflectivity, refractive index, and absorption coefficient.

The response of a nonmagnetic solid with isotropic or cubic symmetry to incident electromagnetic radiation can be generally described in terms of two optical constants, which are related to each other through dispersion relations. These two optical constants can consist of either the refractive index n and the extinction coefficient κ, or ε_1 and ε_2, which are respectively the real and imaginary part of the complex dielectric constant ε. These two pairs of constants are related as follows:

$$\varepsilon = \varepsilon_1 + i\varepsilon_2 + (n + i\kappa)^2 = (n^2 - \kappa^2) + 2in\kappa \tag{1}$$

Let R_∞ be the reflectivity at normal incidence of a solid of sufficient thickness so that there is negligible reflection from the rear surface of the solid and τ_∞ be the corresponding transmission at normal incidence, then R_∞ can be expressed in terms of n and κ as follows:

$$R_\infty = \frac{(n - n')^2 + \kappa^2}{(n + n')^2 + \kappa^2} \tag{2}$$

Generally, the solid is either in air or in a vacuum, where $n' \cong 1$. Therefore, Eq. (2) becomes

$$R_\infty = \frac{(n - 1)^2 + \kappa^2}{(n + 1)^2 + \kappa^2} \tag{3}$$

Similarly, τ_∞ can be expressed as

$$\tau_\infty = \{(1 - R_\infty)^2 + 4R_\infty \sin^2 \Psi\}\, e^{-\alpha t} \tag{4}$$

where

α = absorption coefficient = $4\pi\kappa/\lambda$

λ = wavelength of incident radiation

t = thickness of the sample

$\Psi = \tan^{-1} [2\kappa/(n^2 + \kappa^2 - 1)]$

If $n >> \kappa$, Eq. (4) becomes

$$\tau_\infty \cong (1 - R_\infty)^2\, e^{-\alpha t} \tag{5}$$

Equation (5) is commonly used to determine the absorption coefficient directly by observing the decay of incident light with the thickness of sample.

As we mentioned earlier, the above equations are valid only if the reflection from the rear surface of the solid is negligible. For thin samples, where the reflection from the rear surface cannot be neglected, then the expressions for apparent reflectivity and transmission are:

$$R = \frac{R_\infty \left[(1-e^{-\alpha t})^2 + 4e^{-\alpha t} \sin^2 \gamma\right]}{(1-R_\infty e^{-\alpha t})^2 + 4R_\infty e^{-\alpha t} \sin^2 (\Psi+\gamma)} \tag{6}$$

$$\tau = \frac{e^{-\alpha t} \left[(1-R_\infty)^2 + 4R_\infty \sin^2 \Psi\right]}{(1-R_\infty e^{-\alpha t})^2 + 4R_\infty e^{-\alpha t} \sin^2 (\Psi+\gamma)} \tag{7}$$

where

$\gamma = \frac{2\pi n t}{\lambda}$ (n is an integer),

t = thickness of a thin sample,

R = apparent reflectivity,

τ = apparent transmission.

The second term in the denominator in Eqs. (6) and (7) is an interference term. If no interference fringes are observed because of thickness variation, we then average over γ and obtain:

$$R = \frac{R_\infty (1-e^{-2\alpha t})}{1 - R_\infty^2 e^{-2\alpha t}} \tag{8}$$

$$\tau = \frac{\left[(1-R_\infty)^2 + 4R_\infty \sin^2 \Psi\right] e^{-\alpha t}}{1 - R_\infty^2 e^{-2\alpha t}} \tag{9}$$

It appears that if we know R_∞ and either n or κ, the remaining one can be calculated from this relation. But this usage is only limited to the transparent region where direct measurement of n can be made. It is obvious that the key roles in this method rest on τ and R which are usually difficult to measure accurately because of influencing surface conditions, such as flatness, aging, oxide layers, adsorbed gas, etc. Errors of 1 to 5% in the resulting absorption coefficient are typical. However, this method is self-contained at a given wavelength, and it does not require additional data at other wavelengths or other properties.

Beyond the transparent region, in the high absorption regions, where neither n nor κ are observable, one has to rely on the reflection spectrum from which the optical constants can be derived by the Kramers-Kronig analysis or by the multiple-oscillator fit based on the Lorentz theory [10].

The Kramers-Kronig relations are derived from the dispersion relation in that the phase angle $\theta(\omega)$ of the complex reflectivity, $\bar{R}(\omega)$, is evaluated based on the observed reflection spectrum

$$\bar{R}(\omega) = R(\omega)e^{i\theta(\omega)} \tag{10}$$

$$\theta(\omega) = \frac{\omega}{\pi} P \int_0^\infty \frac{[\ell n R(\omega') - \ell n R(\omega)]}{\omega^2 - \omega'^2} d\omega' \tag{11}$$

where ω is the frequency of radiation and P is the principal value of the Cauchy integral. Based on the amplitude $R(\omega)$, and phase angle of the reflectivity, the refractive index and absorption index can be calculated according to the following equations:

$$n(\omega) = \frac{1 - R(\omega)}{1 + R(\omega) - 2\sqrt{R(\omega)}\cos\theta(\omega)} \tag{12}$$

and

$$\kappa(\omega) = \frac{2\sqrt{R(\omega)}\ \sin\theta(\omega)}{1 + R(\omega) - 2\sqrt{R(\omega)}\cos\theta(\omega)} \tag{13}$$

In principle, the calculation of θ requires a complete reflection spectrum with frequency ranging from zero to infinity. In practice, however, since R is measured only in a limited range of frequencies, errors are inevitable in the calculation of θ and hence in n and κ. These errors arise from the extrapolation of $R(\omega)$ beyond the range of measurements. The typical errors in the resulting n and κ are 5 to 10%, or more.

In the Lorentz theory, the refractive index and absorption index are related to the oscillator frequencies, ω_i, the oscillator strengths, S_i, and the damping factors, γ_i, by the expressions

$$n^2 - \kappa^2 = \varepsilon_\infty + \sum_i \frac{S_i\ [1 - (\omega/\omega_i)^2]}{[1 - (\omega/\omega_i)^2]^2 + \gamma_i^2\ (\omega/\omega_i)^2} \tag{14}$$

$$2n\kappa = \sum_i \frac{S_i \gamma_i \ (\omega/\omega_i)}{[1 - (\omega/\omega_i)^2]^2 + \gamma_i^2 \ (\omega/\omega_i)^2} \tag{15}$$

where ε_∞ is the optical dielectric constant. The resulting n and κ have to satisfy the observed reflectivity by the relation

$$R(\omega) = \left| \frac{n(\omega) - 1 + i\kappa(\omega)}{n(\omega) + 1 + i\kappa(\omega)} \right|^2 \tag{16}$$

It is clear that this approach requires the knowledge of the oscillator frequencies which in general is not complete because of experimental difficulties. This leaves us no choice but to use only the observed predominant ones. Nevertheless, this method, similar to the Kramers-Kronig analysis, yields good approximations to the properties under consideration.

Precise determination for small absorption coefficients, in the order of 10^{-3} cm^{-1} or lower, was considered impossible until the laser source became available. As the bulk absorption becomes smaller than surface losses, uncovering the former requires amplification of the absorption effect which in turn requires high-level energy input to the sample. The two commonly used methods are laser calorimetry [11] and the differential technique [12].

In the laser calorimetric method, the absorbed energy is measured in the form of heat. It can be shown that the total absorption is related to the absorbed energy, E_a, by

$$\alpha L + 2\sigma = \frac{E_a}{E_T} \left(\frac{2n}{1 + n^2} \right) \tag{17}$$

provided $\alpha L < 1$. Here, L is the sample length through which a laser beam passes and σ is the loss per unit surface area. E_a can be calculated using the specific heat and mass of the sample and the measured temperature rise. The transmitted energy can be determined using a black body and its temperature rise. In order to separate the bulk and surface absorptions, the total absorption of a series of samples of different thickness, cut from the same piece of material and polished in the same way must be measured. A plot of total absorption versus sample thickness will give a straight line with slope α and intercept 2σ. This method yields very accurate results and is used to measure absorption as low as 10^{-5} cm^{-1}.

In the differential technique, a dual-beam spectrometer is the basic apparatus and the transmissions and thicknesses of a thick sample (τ_s and d_s) and a reference sample (τ_r and d_r) are measured. An optical wedge is added to the reference beam and its transverse position is so adjusted as to balance the transmitted intensity of the sample beam. The transmission of the wedge, τ_w, is then measured. The relation of the three measured transmissions is, therefore

$$\tau_r \times \tau_w = \tau_s \tag{18}$$

hence, by using Eq. (9)

$$\tau_w = e^{-\alpha\Delta d} \left(\frac{1 - R^2 e^{-2\alpha d_r}}{1 - R^2 e^{-2\alpha d_s}} \right) \tag{19}$$

where $\Delta d = d_s - d_r$, and

$$R = \left(\frac{n-1}{n+1} \right)^2 \tag{20}$$

The accuracy of this method depends on the accuracies of the refractive index and transmission, respectively. While the former can be determined with high accuracy, accuracies of the latter depend on the instrument utilized. An uncertainty of ±1% or greater is in general expected. This imposes a limit, on the order of 1×10^{-3} cm^{-1}, to the lowest absorption coefficient that can be measured by this method.

The typical absorption spectrum of an alkali halide is shown in Figure 1. If we plot the absorption coefficients versus frequency on a semi-log scale, we obtain the absorption spectrum as shown in Figure 2. Behavior of the absorption coefficients in the multiphonon and Urbach regions, respectively, suggests an exponential relation between absorption coefficient and frequency, i.e., $\alpha = \alpha_0 e^{c\nu}$, where α_0 and c are constants. In the transparent region, absorption coefficients of a pure crystal are usually low. If reflectivity can be accurately measured, absorption coefficient can be determined using Eq. (3).

It should be noted that Eq. (3) does not apply to crystals with impurities and defects which are characterized by the emergence, in the transparent region, of a number of absorption bands, the so-called "color centers." The



Figure 2. Schematic Absorption Spectrum of an Alkali Halide in Semilogarithismic Scale

well known ones are the F, R, M, and N absorption bands. Absorption coefficients at these bands vary considerably with temperature, radiation, and time. However, at wavelengths other than these bands, differences in n are negligibly small between samples, and Eq. (3) is valid. The importance of n in relating other optical quantities is self-revealed. Essential parameters for formulae of refractive indices of pure crystals are given in Table 2.

TABLE 2. AVAILABLE PARAMETERS FOR DISPERSION EQUATIONS OF ALKALI HALIDES AT ROOM TEMPERATURE

Material	ϵ_0 [a]	ϵ_∞ [b]	Ultraviolet Absorption Peaks[c] (μm) λ_i	Infrared Absorption Peaks: Wavelength λ_I (μm)	Oscillator Strength ϵ_I	Damping Factor γ_I (μm)
LiF	9.01	1.93		32.79, 19.88	6.80, 0.11	1.967, 3.578
LiCl	11.86	2.75	0.130, 0.143	49.26		
LiBr	13.23	3.16	0.156, 0.162, 0.173	57.80		
LiI	11.03	3.80	0.120, 0.140, 0.167, 0.176, 0.183, 0.197, 0.212	70.42		
NaF	5.072	1.174	0.117	40.57		
NaCl	5.90	2.33	0.050 0.100 0.128 0.158	60.98, 40.50, 120.34	3.2001, 0.0900, 0.331	2.281, 5.730, 198.39
NaBr	6.396	2.60	0.125, 0.145, 0.176, 0.188	74.63		
NaI	7.28	3.01	0.122, 0.141, 0.170, 0.187, 0.228	86.21		
KF	5.50	1.85	0.126	51.55		
KCl	4.85	2.17	0.131, 0.162	70.42		
KBr	4.90	2.36	0.146, 0.173, 0.187	87.72, 60.61	2.4881, 0.1885	4.561, 13.910
KI	5.09	2.65	0.129, 0.175, 0.187, 0.219	98.01, 69.44	2.1363, 0.2765	8.235, 20.832
RbF	6.48	1.93	0.115, 0.132	63.29		
RbCl	4.92	2.18	0.138, 0.166	85.81		
RbBr	4.86	2.34	0.123, 0.146, 0.155, 0.178, 0.191	114.29		
RbI	4.94	2.58	0.120, 0.131, 0.156, 0.179, 0.187, 0.223	132.45		
CsF	8.08	2.16	0.110, 0.118, 0.136	78.74		
CsCl	6.95	2.63	0.119, 0.137, 0.145, 0.162	100.50, 80.00	4.0212, 0.2513	7.538, 26.600
CsBr	6.38	2.78	0.120, 0.146, 0.160, 0.173, 0.187	126.05, 97.09	3.5688, 0.1131	8.163, 15.531
CsI	6.31	3.02	0.130, 0.147, 0.163, 0.177, 0.185, 0.206, 0.218	161.29, 117.65	3.2673, 0.0628	11.290, 17.648

[a] Static dielectric constant data are from Ref. [13, 14, 15, 16, 17].

[b] High-frequency dielectric constant data are from Ref. [13, 16, 18].

[c] The ultraviolet absorption peaks are measured by Hilsch and Pohl [19] Schneider and O'Bryan [20] and Ramachandran [21].

[d] The order of ϵ_I's and γ_I's corresponds to the order of the λ_I's. Data sources: see Ref. [13, 16]; for LiF see Ref. [22]; for NaCl see Ref. [23]; for KBr see Ref. [24] for KI see Ref. [25], for CsCl, CsBr, and CsI see Ref. [26].

3. NUMERICAL DATA

Presentation of Data

Data in the open literature are reported in various units. Absorptions are given in units of cm^{-1}, or as extinction index, optical density, or normalized values. Energy is presented in terms of wavelength, wavenumber, frequency, or electron volt. In the present work, the absorption coefficient is consistently reported in units of cm^{-1} and the energy in units of wavenumber, cm^{-1}. All of absorption data were converted, when necessary, to these uniform set of units. However, in the case of reflectivity and transmission data, the energy unit is in wavelength, μm, as conventionally accepted. Although we have surveyed the absorption coefficient in the vacuum ultraviolet (vuv) region and a number of data sets have been collected, no attempt was made to analyze the spectrum in the vuv region as it is beyond the scope of this work. However, it was felt desirable to see the complete spectrum of absorption coefficient. For this reason the vuv absorption spectra are given in the Appendix.

A number of figures and tables summarize the information and data. The conventions used in this presentation, and specific comments on the interpretation and use of data are given below. Each sub-section in this section gives all the information and data for a given material. The sub-sections are arranged in the following order:

3.1 Lithium Fluoride, LiF
3.2 Sodium Fluoride, NaF
3.3 Sodium Chloride, NaCl
3.4 Potassium Chloride, KCl
3.5 Potassium Bromide, KBr
3.6 Potassium Iodide, KI
3.7 Cesium Iodide, CsI

Presented in each sub-section are information and data in the following order:

a. A text describing and discussing the data, analysis, and recommendations. With the thought that in general a reader will only concern himself with a specific substance, it was felt highly desirable to include in each sub-section important information even if it should constitute a repetition of some of the subject matter found in other sections or sub-sections.

PRECEDING PAGE BLANK

b. A figure of experimental absorption coefficient (wavenumber dependence). For the purpose of showing the details in each of the multiphonon and Urbach tail regions, additional figures are included for visual clarity.

c. A summary table of measurements on the absorption coefficient (wavenumber dependence). An extract of pertinent information for each data set is given in this table.

d. A table of experimental data on the absorption coefficient (wavenumber dependence). The original data reported in this table are converted to the adopted set of units. The order of magnitude of absorption coefficient varies over a wide range, from 10^{-6} cm^{-1} to 10^{6} cm^{-1}, and that of wavenumber varies from 10 cm^{-1} to 10^{5} cm^{-1}. Therefore, it is convenient to present the data in powers of ten. In this table, the numerical value 1.259E±n stands for $1.259 \cdot 10^{\pm n}$.

e. A figure of experimental absorption coefficients (temperature dependence).

f. A summary table of measurements on the absorption coefficient (temperature dependence).

g. A table of experimental data on the absorption coefficient (temperature dependence).

h. A figure of experimental reflectivity.

i. A summary table of measurements on the reflectivity

j. A table of experimental data on the reflectivity.

k. A figure of experimental transmission.

l. A summary table of measurements on the transmission.

m. A table of experimental data on the transmission.

n. A table of peak positions and the corresponding *half-widths of the* well known F, R, M, and N absorption bands.

o. A table of recommended values on the absorption coefficient in the infrared wavelength region. It is rather difficult to give recommendations in this region since most of the data are still in a provisional status, as evidenced by new claims of the discovery of lower values obtained through improvements in sample preparation and experimental

techniques. As a result, in our tables of recommended values, we give the lower limits predicted by the theoretical relations, the lowest available values, or the most probable range of values for a randomly selected sample.

In figures containing experimental data, if data sets are distinguishable, the data sets are labeled by appropriate legends and denoted by the numbers corresponding to those assigned in the corresponding tables on the summary of measurements and experimental data. The tables on the summary of measurements give for each set of data the following information: the reference number, author's name (or names), year of publication, wavelength range covered by the data, temperature range, the description and characterization of the specimen, and information on measurement conditions contained in the original paper.

There are a number of experimental methods used for absorption coefficient determinations. Listed below are the four most commonly used ones and their corresponding code symbols used in the tables:

C - calorimetric method

Z - transmission and refraction method

T - transmission method

R - reflection method

The methods listed above are arranged in the order of their inherent accuracies. The calorimetric method is by far the most accurate method in the determination of the absorption coefficient. It is used for measuring very low absorptions with the lowest attainable level, in the order of 10^{-5} cm^{-1}. Absorption coefficients determined by the second method are usually reliable if the multiple internal reflection and transmission are accounted for. The transmission method is the most popular one used for absorption measurements because of its simplicity. The reflection method is the least accurate method, since errors of 5 to 10% or more are typical. It should be noted that neither the second nor the third method is suitable for absorption coefficient lower than 0.001 cm^{-1} as their sensitivities are considerably reduced at low absorption levels.

Wavelength and wavenumber are two equivalent units to describe the spectral dependence of a property. The conversion table given below should prove convenient.

WAVENUMBER VS WAVELENGTH EQUIVALENTS

Wavenumber, cm^{-1}	Wavelength, μm
100,000	0.1
10,000	1.0
9,434	1.06
5,000	2.0
3,571.4	2.8
3,333.3	3.0
2,631.6	3.8
2,500	4.0
2,000	5.0
1,886.8	5.3
1,666.7	6.0
1,428.6	7.0
1,250	8.0
1,111.1	9.0
1,052.6	9.5
1,000	10.0
943.4	10.6
909.1	11.0

3.1. Lithium Fluoride, LiF

Lithium fluoride has long been of practical interest to spectroscopy because of its attractive optical properties. Its large electronic band gap places its useful transmission limit near 0.11 μm, further into the vacuum ultraviolet region than any other known material. It is, therefore, a useful substrate for absorption studies on thin films of other materials and has long been used as such. In the range of 0.25-4.5 μm the dispersion is low and transmission is high. Less transmission and higher dispersion are found in the low ultraviolet and the infrared. In the low ultraviolet, optical components must be made very thin in order to obtain maximum transmission. Selected specimens of lithium fluoride, in moderately thin pieces, may be expected to transmit several percent of the light down to wavelengths as short as 0.11 μm. Impurities in the crystal, poor polish, and layers of foreign material on the surface may reduce the transmission in the Schumann region down to a negligible quantity. In the infrared, transmission begins to fall off rapidly at 7 μm, and a prism is useful to 5 μm.

Optically speaking, lithium fluoride closely resembles calcium fluoride. However, lithium fluoride is preferable to calcium fluoride for use in prismatic form because of its much greater dispersion in the infrared and greater transparency in the extreme ultraviolet.

Unlike the other alkali halides, lithium fluoride is practically insoluble, and advantage is taken of this fact in the purification of the salt. High purity single crystals of lithium fluoride up to more than 5 inches in diameter and 4 kg in weight are commercially available and are suitable for making optical components in various sizes.

Measurements of the refractive index of lithium fluoride date back to 1927. The existing data cover a spectral range from 0.00236 to 600 μm and at 2000 μm. Based on the optical behavior of the material and the experimental techniques, these data fall quite naturally into two categories: the transparent region ($\sim$0.11 to $\sim$9.0 μm) and the absorption regions ($<$0.11 and $>$9.0 μm). For the high transparency region, since large sizes of LiF are easily obtained, the deviation method is commonly used with the sample in prismatic form. This method was adopted by a number of researchers: Gyulai [27], Schneider [28],

Hohls [29], Harting [30], Durie [31], and Tilton and Plyler [32]. The deviation method, though the oldest, is often considered as the most accurate; less accurate data can be obtained by the interference method. Due to the high absorption in the low uv and near IR at the end of transparent region, the deviation method and interferometry cannot be used. Refractive indices are obtained either by measuring transmission of thin films or by theoretical analysis of the reflection spectra from the bulk material.

Li [33] reduced the experimentally measured data then available to a common temperature of 293 K and after careful analysis generated a Sellmeier type formula representing the refractive index of LiF at 293 K in the spectral region from 0.10 to 11.0 μm,

$$n = 1 + \frac{0.92549\ \lambda^2}{\lambda^2 - (0.07376)^2} + \frac{6.96747\ \lambda^2}{\lambda^2 - (32.79)^2} \tag{21}$$

where λ is in units of μm.

Investigations of absorption coefficient for practical applications are generally classified into three wavelength regions: the ultraviolet and the infrared limits of transparent regions, and the transparent regions. In the ultraviolet limit, the motivation of the researches was to investigate the exciton states in the crystal and to determine the Urbach-rule parameters at the absorption edge.

Kato [34] determined absorption coefficients in the wavelength range from 0.09 to 0.19 μm by applying the Kramers-Kronig relation to the observed reflection spectra of bulk crystal. The peak position of the fundamental band was determined to be at 0.0976 ± 0.0008 μm where the corresponding absorption coefficient was found to be $2.2 \pm 0.1 \times 10^6\ cm^{-1}$. In the investigation of the effects of hydrolysis on the absorption coefficient, crystals grown in air were studied. It was found that absorption near 2.8 μm was due to the vibration of O-H bond and in addition it gave a broader absorption at the tail of the fundamental band. Roessler and Walker [35] reported absorption index in the wavelength region from 0.0443 to 0.248 μm. The absorption coefficient was derived from the near normal reflection spectra of freshly cleaved crystal by Kramers-Kronig analysis. Since any defects or surface contamination tend to decrease the sharpness of uv reflectance structure, the reflection spectra from surfaces showing highest reflectance at structure peaks were selected for their analysis to assure minimum surface contamination and defects.

Schneider [28] determined absorption coefficient (in the wavelength region from 0.11 to 0.16 μm) directly through measurements of transmissions of plate specimens of various thickness. The crystals used are believed to be of high purity and quality polished, as evidenced by higher transmission at short wavelength, 0.11 μm. It was noted that the main factor of decreased transmission was due to the deposits as a result of chemical reaction of the surface with moisture.

Görlich et al. [36] investigated crystals grown by both of the Bridgman and Kyropoulos methods. Absorption spectra in the wavelength range from 0.20 to 0.79 μm were measured for both crystals. Although impurity contents and concentrations had no spectroscopically detectable difference, the crystal grown in air showed much higher absorption coefficients in the region 0.2 to 0.4 μm than that grown in vacuum, particularly steeply rising toward 0.2 μm. In addition, absorption bands in the range between 2.6 to 2.8 μm were observed in air grown crystals but not in vacuum grown ones. This observation is consistent with the results of Kato [34], the extinction of crystals grown in air is chiefly composed of the scattering of light by the microscopic irregularities of the crystalline structure and of the absorption of the additionally incorporated OH^- or oxygen ions. Gyulai [27] reported absorption coefficients in the region between 0.18 and 0.40 μm for a crystal grown by the Kyropoulos method. Owing to the differences in impurity contents and defects, the absorption spectrum showed different profile from that of Görlich et al. [36]. However, both reported weak selective absorption bands between 0.25 and 0.30 μm where the F center is located. Tomiki and Miyata [37] measured absorption coefficients in the Urbach tail region at four temperatures, from 300 to 573 K. They found the tail at 300 K was extrinsic. Based on the data at three higher temperatures, it was possible to find the following parameters:

$E_o = 13.00$ eV,
$\alpha_o = 1.0 \times 10^{10}$ cm^{-1},
$hf = 0.23$ meV,

and

$\sigma_{so} = 0.70$,

for the equations representing the intrinsic absorption in the tail region:

$$\alpha(E,T) = \alpha_o e^{-\sigma_s(T)(E_o-E)/kT} \tag{22}$$

and

$$\sigma_s = \sigma_{so} \frac{2kT}{hf} \tanh \frac{hf}{2kT}$$

Measurements of absorption coefficient for the infrared region were made for the purpose of studying the optically active lattice vibrations and fundamental resonant frequencies. On the short wavelength side of the fundamental absorption band, multiphonon absorption, in which a photon is absorbed and two or more phonons are generated, can occur and lead to absorption coefficients that range from 10^{-3} cm^{-1} to 10^{2} cm^{-1}, depending on the number of phonons generated.

Jasperse et al. [22] made self-consistent measurements of the infrared reflectivity for a wide temperature range from 7.5 to 1060 K. The absorption index was computed by using a two-resonance damped oscillator model. Through the classical pole-fit procedures, by assuming the optical dielectric constant to be temperature independent, they were able to establish the temperature dependence of the resonant frequencies, the damping factors, and the oscillator strengths.

Barker [38] studied the multiphonon infrared absorption by samples of crystalline and molten LiF at temperatures between 300 and 1160 K (melting temperature 1115 K). It was found that the absorption behavior of the molten salt could be closely predicted from the absorption behavior of the solid as if there was no phase transition occurring. The observed relatively small change during the phase transition from solid to liquid implies that at least the high frequency limit of the vibrational spectra are approximately the same in the solid and liquid phases close to the melting point. However, at temperatures from 10-30 K higher than the melting point, the absorption coefficient decreased noticeably and the static dielectric constant changed from 10.76 to 7.84 [39].

Kachare et al. [40] determined the absorption coefficient by a Kramers-Kronig analysis of the reflection spectra. The reflection spectra were measured accurately, particularly in the difficult minimum reflection region. It was concluded that the classic dispersion analysis could not provide reliable values of optical constants for highly anharmonic crystals while the KK analysis could, but required reliable reflectivity data.

Deutsch [12], using a differential technique with a dual beam spectrometer, measured the absorption coefficient for the wavelength range from 4.3 to 7.0 μm at room temperature. It was found that these data could be represented by an exponential relation as:

$$\alpha = \alpha_o \exp(-\nu/\nu_o) \tag{23}$$

where α_o = 21,317 cm^{-1} and ν_o = 153.2 cm^{-1}, according to Deutsch. Klier [41] reported the absorption index in the wavelength range between 5.4 and 14.7 μm. Hohl [29] also reported the absorption index in the range between 4.5 and 15.7 μm. Hohl's values agreed with Klier's in general except that Hohl's measurements showed distinct structure features in the wavelength region beyond 13 μm. In the region from 5 to 11 μm the results of Hohl and Klier agree well with Deutsch's exponential relation, Eq. (23).

Owens [42] measured absorption coefficient at three wavelengths in the millimeter-wave region. Combined with the measurements of other investigations, Owens observed that the extinction coefficient decreased with increasing wavelength and approached a constant value of about 1×10^{-4} *below 1 GHz*. The origin of this constant background loss, which appeared to be independent of temperature, is unknown. It may be due to imperfections in the crystal. Stolen and Dransfeld [43] measured absorption at a wavelength 320 μm between 200 and 425 K. It was found that the absorption increases as a quadratic function of temperature.

Figures 3 to 6 are plots of the available data. The pertinent information of each data source and the corresponding original values are given in Tables 3 to 6. In addition, available information and data on the reflectivity and transmission are also presented in a similar manner (in Figures 7 and 8 and Tables 7 to 10) for completeness and comparison. For the visible and near visible regions, Table 11 gives the spectral positions of the well-known color centers. Noticeable absorptions are likely to occur at these centers when the crystal is exposed to ultraviolet or x-ray radiation.

Recommended values given in Table 12 were calculated according to Eq. (23). In the range between 4.37 and 7 μm, these values are supported by the measurements of Deutsch. It appears that LiF has a high intrinsic absorption coefficient in this region. However, if Eq. (23) holds in the range below 3.9 μm, we can see the intrinsic absorption coefficients in this region are lower than

10^{-4} cm^{-1}. There is an absorption band in the range between 2.6 to 2.8 μm which owes its origin to the inclusion of hydroxyl ions. This absorption band is diminished in vacuum grown crystals. It should be noted that the values in the column "intrinsic" are the lowest limits that one can obtain for ideal samples. In practice, the observed values are generally higher than the limiting values. Unless values appear in the column "observed," the limiting values should be considered as guidelines for estimation and investigation.

Although it was not the aim of this investigation to compile and evaluate the absorption data in the vacuum ultraviolet region, this was done to provide the users a total picture of the available absorption data. The plot of selected curves in this region is given in the Appendix of this report.



Figure 3. Absorption Coefficient of Lithium Fluoride (Wavenumber Dependence)



Figure 4. Absorption Coefficient of Lithium Fluoride in the Urbach Tail Region



Figure 5. Absorption Coefficient of Lithium Fluoride in the Multiphonon Region

TABLE 3. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Wavenumber Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	22	Jasperse, J.R., Kahan, A., Plendl, J.N., and Mitras, S.	1966	R	100-588	7.5	High purity; single crystal; hand polished until optically flat to about 1/2 wavelength of the mean sodium D lines; annealed in a vacuum furnace for two days at a temperature of about 3/4 of the melting temperature of the crystal; near normal (averaged about 11 degrees) reflectivities in the spectral range from 12.5 to 50 μm determined by comparing spectral reflectances from the sample and from an aluminized mirror with reflectivity in the spectral region under consideration; reflectivity data were checked several times for different samples and for several cycles of heating and cooling and reproduced to within ±1 to ±2%; the reflection spectra were analyzed by means of a two-resonant damped-oscillater model; absorption coefficients were calculated from the resulting equations.
2	22	Jasperse, J.R., et al.	1966	R	100-588	85	Same as above.
3	22	Jasperse, J.R., et al.	1966	R	100-588	295	Same as above.
4	22	Jasperse, J.R., et al.	1966	R	100-588	420	Same as above.
5	22	Jasperse, J.R., et al.	1966	R	100-588	605	Same as above.
6	22	Jasperse, J.R., et al.	1966	R	100-588	840	Same as above.
7	22	Jasperse, J.R., et al.	1966	R	100-588	1060	Same as above.
8	34	Kato, R.	1961	R	9.6×10^{4}-1.1×10^{5}	298	High purity; single crystal; freshly cleaved specimens; near normal (15 degrees incident angle) reflectivity obtained; Kramers-Kronig relations applied to derive the optical constants n and k from the reflectivity; data extracted from a figure.
9	34	Kato, R.	1961	R	6.4×10^{4}-9.6×10^{4}	298	Same as above but only for details at the tail of fundamental band; absorption-coefficient data extracted from a figure.
10	34	Kato, R.	1961	R	5.2×10^{4}-8.0×10^{4}	298	Similar to above; absorption-coefficient data extracted from a figure.
11	36	Görlich, P., Karras, H., and Kötitz, G.	1963	T	1.89×10^{4}-4.84×10^{4}	390	Single crystal; grown by the Kyropoulos (in air) method; impurities of Al, Ca, Cr, Cu, Na, Mg, Mn, Si, and Pb with concentrations estimated to be between 10^{-4}-10^{-5}%; unspecified specimen configurations; absorption spectrum obtained and absorption coefficients determined; absorption coefficient data extracted from a figure.
12	36	Görlich, P., et al.	1963	T	2.68×10^{4}-4.72×10^{4}	390	Similar to above except for crystal grown by the Bridgman (in vacuum) method.

TABLE 3. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Wavenumber Dependence) (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
13	36	Görlich, P., Karras, H., and Kötitz, G.	1963	T	3.54×10^{3}-3.87×10^{3}	300	Similar to above for crystal grown by the Kyropoulos (in air) method and measured for infrared region where the crystal grown by the Bridgman (in vacuum) showing no absorption.
14	27	Gyulai, Z.	1927	T	3.2×10^{4}-5.4×10^{4}	293	Single crystal; grown by the Kyropoulos method; plate specimen of 1.4 mm thick; absorption coefficient determined by Szakula for the author; data extracted from a figure; temperature not specified, 293 K assumed.
15	29	Hohls, H.W.	1936	T	6.34×10^{2}-2.23×10^{3}	293	Crystal; grown by the Kyropoulos method; 14 plate specimens of thicknesses from 0.008 cm to 10.53 cm; absorption coefficients directly determined; data extracted from a figure; temperature not specified, 293 K assumed.
16	28	Schneider, E.G.	1936	T	6.25×10^{4}-8.90×10^{4}	293	High purity; single crystal; grown by the Bridgman method; plate specimens of thickness from 0.5 to 25.0 cm; absorption coefficients directly determined; data extracted from a figure.
17	44	Eldridge, J.E.	1972	T	1.8×10^{2}-3.0×10^{2}	10	High purity; single crystal; obtained from the Harshaw Chemical Co.; plate specimens with thicknesses of 0.07, 0.1 and 0.8 cm and mechanically polished; spectral transmitted intensities measured; absorption coefficients determined with the aid of refractive index calculated from a dispersion formula; absorption-coefficient data extracted from a figure; estimated uncertainty about 10% except at long wavelength end where 100% uncertainty estimated.
18	35	Roessler, D.M. and Walker, W.C.	1967	R	9.47×10^{4}-2.02×10^{5}	300	Single crystal; obtained from the Harshaw Chemical Co.; freshly cleaved specimens; absorption coefficients determined from a Kramers-Kronig analysis of experimentally determined near normal reflection spectra; data extracted from a table.
19	41	Klier, M.	1958	R	6.79×10^{2}-1.83×10^{3}	77	Crystal; absorption-coefficient data deduced from reflectance and transmittance measurements on specimens of various thicknesses; data extracted from a figure.
20	41	Klier, M.	1958	R	7.71×10^{2}-1.83×10^{3}	195	Same as above.
21	41	Klier, M.	1958	R	7.03×10^{2}-1.82×10^{3}	293	Same as above.
22	41	Klier, M.	1958	R	7.28×10^{2}-1.83×10^{3}	573	Same as above.
23	41	Klier, M.	1958	Z	28.7-191	77	Crystal; plate specimen; absorption coefficients deduced from transmittance measurements and estimated reflectivity; reflectivity estimated by assuming n = 3.07 for the whole wavelength range; data extracted from a figure; estimated uncertainty about 5 to 10%.
24	41	Klier, M.	1958	R	29-191	293	Same as above.

TABLE 3. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Wavenumber Dependence) (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
25	41	Klier, M.	1958	R	29-193	573	Same as above.
26	38	Barker, A.J.	1972	R	1.19×10^{3}-1.95×10^{3}	300	Synthetic crystal; high purity; highly polished specimen of 1-2 mm thick; absorption coefficients deduced from measurements of reflectivity obtained using the obscured-mirror technique; absorption-coefficient data extracted from a figure.
27	38	Barker, A.J.	1972	R	1.34×10^{3}-2.05×10^{3}	705	Similar to above but at a higher temperature.
28	38	Barker, A.J.	1972	R	1.39×10^{3}-2.1×10^{3}	855	Similar to above but at a higher temperature.
29	38	Barker, A.J.	1972	R	1.43×10^{3}-2.35×10^{3}	975	Similar to above but at a higher temperature.
30	38	Barker, A.J.	1972	R	1.59×10^{3}-2.4×10^{3}	1160	Molten LiF specimen of 1-2 mm thick; reflectivity measurements carried out in a large inert gas atmosphere; absorption coefficients deduced from reflection spectra; absorption-coefficient data extracted from a figure; melting temperature of LiF is 1115K.
31	12	Deutsch, T.F.	1973	D	1.44×10^{3}-2.31×10^{3}	300	Single crystal; obtained from Harshaw Chemical Co.; specimen of 2.5 cm diameter and 2.5 cm long; differential technique used to determine absorption-coefficient data extracted from a figure.
32	42	Owens, J.	1968	L	2.53×10^{-1}-3.4	298	Single crystals; obtained from the Harshaw Chemical Co.; cylinder shaped specimen; filled resonant cavity method used for measuring dielectric constant and loss tangent; absorption coefficient then determined; data extracted from a figure.
33	39	Mead, D.	1974	R	1.0×10^{2}-7.3×10^{3}	1175	LiF melt; high purity; obtained from BDH Ltd.; near normal reflection spectrum obtained; absorption coefficient obtained by the Kramers-Kronig and classical oscillator analysis; data extracted from a smooth curve.
34	40	Kachare, A., Soriaga, M., and Underwood, G.	1974	R	7.71×10^{2}-1.16×10^{3}	300	Single crystal; polished and annealed; near normal reflection spectrum obtained; absorption coefficient deduced from reflection spectrum by the Kramers-Kronig analysis; data extracted from a figure.
35	40	Kachare, A., et al.	1974	R	7.1×10^{2}-1.2×10^{3}	80	Similar to above but at a lower temperature.
36	40	Kachare, A., et al.	1974	R	7.19×10^{2}-1.15×10^{3}	20	Similar to above but at a lower temperature.
37	45	Eldridge, J.E.	1972	T	75-178	63	Natural LiF crystals obtained from the Harshaw Chemical Co.; specimens of 1 x 2.5 cm with thicknesses varying from 0.02 to 0.1 cm; mechanically polished; absorption coefficients obtained from transmission measurements; data extracted from a figure.

TABLE 3. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Wavenumber Dependence) (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
38	45	Eldridge, J.E.	1972	I	70-292	77	Same as above.
39	45	Eldridge, J.E.	1972	I	29-149	300	Same as above.
40	46	Heilmann, G.	1958	R	277-667	293	Single crystal; absorption coefficients determined from the reflectivity measurements from the polarized light at 20° and 70° incident angle; data extracted from a figure.
41	46	Heilmann, G.	1958	R	277-623	573	Same as above.
42	46	Heilmann, G.	1958	R	277-667	873	Same as above.
43	47	Genzel, L. and Klier, M.	1956	T	8.6-147	298	LiF crystal; plate specimens of 145 μm, 725 μm and 4.1 mm thick; absorption coefficients determined based on transmission measurements; data extracted from a figure.
44	48	Fröhlich, D.	1962	R	264-431	300.0	Thin evaporated film specimens of 2 to 5 μm thick; absorption coefficients determined from reflectivity measurements; data extracted from a figure.
45	49	Fröhlich, D.	1964	R	271-357	70	Single crystals; thin plate specimens; absorption coefficients determined from reflectivity measurements; data extracted from a figure.
46	49	Fröhlich, D.	1964	R	263-362	200	Same as above.
47	49	Fröhlich, D.	1964	R	263-364	300	Same as above.
48	50	Seger, G. and Genzel, L.	1962	T	10-33	298	Single crystals; plate specimens of 3, 6, 15, and 30 μm thick; absorption determined from transmission measurements; data extracted from a figure.
49	37	Tomiki, T. and Miyata, T.	1969	Z	9.1×10^{4}-9.8×10^{4}	298.5	Single crystal; ultraviolet quality from the Harshaw Chemical Co.; freshly cleaved specimens for absorption coefficient below 100 cm^{-1}; specimens for higher absorption prepared in high vacuum by melting the flakes of crystals between two plates of glassy carbon and pressed; reflection and transmission spectra obtained and absorption coefficient determined; data extracted from a figure.
50	37	Tomiki, T. and Miyata, T.	1969	Z	8.6×10^{4}-9.4×10^{4}	437	Same as above.
51	37	Tomiki, T. and Miyata, T.	1969	Z	8.5×10^{4}-9.3×10^{4}	510	Same as above.
52	37	Tomiki, T. and Miyata, T.	1969	Z	8.5×10^{4}-9.2×10^{4}	573	Same as above.

TABLE 3. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Wavenumber Dependence) (*continued*)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
53	37	Tomiki, T. and Miyata, T.	1969	Z	$5.3x10^4$-$9.7x10^4$	300	*Above specimen* except aged for two weeks.
54	37	Tomiki, T. and Miyata, T.	1969	Z	$7.9x10^4$-$9.8x10^4$	300	Similar to above except sample aged for one week.

TABLE 4. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Wavenumber Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

ν	α	ν	α	ν	α	ν	α	ν	α	ν	α
DATA SET 1 T = 7.5		DATA SET 2 T = 85.3		DATA SET 3 T = 235.0		DATA SET 4 T = 420.0		DATA SET 5 T = 565.0		DATA SET 6 T = 340.3	
5.882E+2	6.475E+3	5.882E+2	6.412E+3	5.882E+2	6.855E+3	5.882E+2	7.053E+3	5.882E+2	6.892E+3	5.882E+2	6.956E+3
5.263E+2	8.795E+3	5.263E+2	8.863E+3	5.263E+2	9.015E+3	5.263E+2	9.226E+3	5.263E+2	9.155E+3	5.263E+2	9.594E+3
4.762E+2	1.027E+4	4.762E+2	9.933E+3	4.762E+2	9.712E+3	4.762E+2	9.775E+3	4.762E+2	9.772E+3	4.762E+2	9.859E+3
4.348E+2	1.235E+4	4.348E+2	1.197E+4	4.348E+2	1.152E+4	4.348E+2	1.135E+4	4.348E+2	1.085E+4	4.348E+2	1.037E+4
4.167E+2	1.351E+4	4.167E+2	1.331E+4	4.167E+2	1.254E+4	4.167E+2	1.231E+4	4.167E+2	1.181E+4	4.167E+2	1.136E+4
4.000E+2	1.438E+4	4.000E+2	1.438E+4	4.000E+2	1.364E+4	4.000E+2	1.332E+4	4.000E+2	1.250E+4	4.000E+2	1.153E+4
3.846E+2	1.634E+4	3.846E+2	1.538E+4	3.846E+2	1.487E+4	3.846E+2	1.442E+4	3.846E+2	1.346E+4	3.846E+2	1.243E+4
3.704E+2	1.697E+4	3.704E+2	1.754E+4	3.704E+2	1.630E+4	3.704E+2	1.566E+4	3.704E+2	1.442E+4	3.704E+2	1.285E+4
3.571E+2	2.[illegible]E+4	3.571E+2	2.[illegible]E+4	3.571E+2	1.815E+4	3.571E+2	1.711E+4	3.571E+2	1.546E+4	3.571E+2	1.355E+4
3.448E+2	2.537E+4	3.448E+2	2.343E+4	3.448E+2	2.033E+4	3.448E+2	1.885E+4	3.448E+2	1.659E+4	3.448E+2	1.415E+4
3.390E+2	2.939E+4	3.390E+2	2.534E+4	3.390E+2	2.177E+4	3.390E+2	1.987E+4	3.390E+2	1.717E+4	3.390E+2	1.446E+4
3.333E+2	3.477E+4	3.333E+2	2.932E+4	3.333E+2	2.347E+4	3.333E+2	2.160E+4	3.333E+2	1.774E+4	3.333E+2	1.475E+4
3.279E+2	3.877E+4	3.279E+2	3.432E+4	3.300E+2	2.460E+4	3.300E+2	2.273E+4	3.300E+2	1.814E+4	3.300E+2	1.492E+4
3.279E+2	4.494E+4	3.226E+2	4.246E+4	3.279E+2	2.553E+4	3.279E+2	2.223E+4	3.279E+2	1.838E+4	3.279E+2	1.500E+4
3.257E+2	5.137E+4	3.226E+2	4.692E+4	3.257E+2	2.647E+4	3.257E+2	2.275E+4	3.257E+2	1.861E+4	3.257E+2	1.512E+4
3.226E+2	5.[illegible]E+4	3.175E+2	5.167E+4	3.236E+2	2.748E+4	3.236E+2	2.327E+4	3.236E+2	1.883E+4	3.236E+2	1.522E+4
3.226E+2	6.345E+4	3.175E+2	5.318E+4	3.226E+2	2.800E+4	3.226E+2	2.354E+4	3.226E+2	1.894E+4	3.226E+2	1.529E+4
3.225E+2	7.753E+4	3.100E+2	5.281E+4	3.215E+2	2.854E+4	3.215E+2	2.381E+4	3.215E+2	1.905E+4	3.215E+2	1.529E+4
3.225E+2	7.822E+4	3.055E+2	4.939E+4	3.205E+2	2.909E+4	3.205E+2	2.405E+4	3.205E+2	1.915E+4	3.205E+2	1.533E+4
3.195E+2	9.721E+4	3.055E+2	4.270E+4	3.195E+2	2.965E+4	3.195E+2	2.431E+4	3.195E+2	1.925E+4	3.195E+2	1.537E+4
3.185E+2	3.299E+4	3.035E+2	3.472E+4	3.185E+2	3.021E+4	3.185E+2	2.455E+4	3.185E+2	1.934E+4	3.185E+2	1.540E+4
3.175E+2	2.497E+4	3.025E+2	2.762E+4	3.175E+2	3.076E+4	3.175E+2	2.479E+4	3.175E+2	1.943E+4	3.175E+2	1.543E+4
3.165E+2	1.363E+4	3.025E+2	2.092E+4	3.165E+2	3.129E+4	3.165E+2	2.501E+4	3.165E+2	1.951E+4	3.165E+2	1.546E+4
3.155E+2	9.453E+3	3.077E+2	9.473E+3	3.155E+2	3.175E+4	3.155E+2	2.521E+4	3.155E+2	1.958E+4	3.155E+2	1.549E+4
3.135E+2	5.033E+3	3.035E+2	4.760E+3	3.135E+2	3.259E+4	3.135E+2	2.555E+4	3.135E+2	1.971E+4	3.135E+2	1.553E+4
3.115E+2	3.835E+3	2.935E+2	2.963E+3	3.115E+2	3.293E+4	3.115E+2	2.570E+4	3.115E+2	1.979E+4	3.115E+2	1.557E+4
3.095E+2	2.361E+3	2.945E+2	2.033E+3	3.095E+2	3.243E+4	3.096E+2	2.579E+4	3.096E+2	1.984E+4	3.095E+2	1.553E+4
3.077E+2	2.199E+3	2.999E+2	1.532E+3	3.077E+2	3.099E+4	3.077E+2	2.558E+4	3.077E+2	1.943E+4	3.077E+2	1.558E+4
3.030E+2	1.323E+3	2.997E+2	1.269E+3	3.030E+2	2.323E+4	3.030E+2	2.378E+4	3.030E+2	1.852E+4	3.030E+2	1.522E+4
2.899E+2	9.039E+2	2.703E+2	5.774E+2	2.899E+2	6.314E+3	2.899E+2	1.234E+4	2.899E+2	1.581E+4	2.899E+2	1.435E+4
2.703E+2	2.377E+2	2.500E+2	3.142E+2	2.703E+2	2.130E+3	2.703E+2	4.[illegible]27E+3	2.703E+2	7.741E+3	2.703E+2	1.008E+4
2.500E+2	1.257E+2	2.222E+2	1.398E+2	2.500E+2	9.912E+2	2.500E+2	1.363E+3	2.500E+2	3.052E+3	2.500E+2	6.200E+3
2.222E+2	5.945E+1	2.000E+2	1.065E+2	2.222E+2	4.591E+2	2.222E+2	8.389E+2	2.222E+2	1.613E+3	2.222E+2	2.955E+3
2.000E+2	5.027E+1	1.429E+2	3.594E+1	2.000E+2	2.767E+2	2.000E+2	4.981E+2	2.000E+2	9.415E+2	2.000E+2	1.736E+3
1.667E+2	2.094E+1	1.000E+2	1.257E+1	1.667E+2	1.399E+2	1.667E+2	2.434E+2	1.667E+2	4.559E+2	1.667E+2	8.330E+2
				1.000E+2	3.468E+1	1.000E+2	6.057E+1	1.000E+2	1.398E+2	1.000E+2	1.949E+2

TABLE 4. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 7	
T = 100.0	
5.682E+2	5.817E+3
5.263E+2	7.857E+3
4.702E+2	9.302E+3
4.344E+2	1.[illegible]E+4
4.107E+2	1.[illegible]E+4
4.000E+2	1.531E+4
3.840E+2	1.637E+4
3.764E+2	1.143E+4
3.672E+2	1.132E+4
3.448E+2	1.222E+4
3.3[illegible]E+2	1.241E+4
3.333E+2	1.255E+4
3.3[illegible]E+2	1.255E+4
3.279E+2	1.272E+4
3.257E+2	1.275E+4
3.235E+2	1.251E+4
3.226E+2	1.232E+4
3.219E+2	1.234E+4
3.209E+2	1.255E+4
3.195E+2	1.245E+4
3.145E+2	1.291E+4
3.175E+2	1.272E+4
3.1[illegible]E+2	1.293E+4
3.159E+2	1.294E+4
3.13[illegible]E+2	1.293E+4
3.115E+2	1.293E+4
3.092E+2	1.293E+4
3.077E+2	1.293E+4
3.036E+2	1.293E+4
2.889E+2	1.257E+4
2.703E+2	1.035E+4
2.500E+2	7.917E+3
2.222E+2	4.343E+3
2.03[illegible]E+2	2.629E+3
1.867E+2	1.273E+3
1.600E+2	2.956E+2

ν	α
DATA SET 8	
T = 298.0	
1.094E+5	3.312E+5
1.092E+5	3.099E+5
1.082E+5	5.445E+5
1.073E+5	8.223E+5
1.068E+5	1.018E+6
1.059E+5	1.263E+6
1.043E+5	1.403E+6
1.045E+5	1.542E+6
1.041E+5	1.714E+6
1.031E+5	1.839E+6
1.031E+5	2.181E+6
1.028E+5	2.161E+6
1.026E+5	2.231E+6
1.019E+5	2.152E+6
1.017E+5	2.032E+6
1.013E+5	1.521E+6
1.011E+5	9.347E+5
9.327E+4	6.487E+5
9.603E+4	4.214E+5
9.782E+4	2.951E+5
9.877E+4	1.581E+5
9.613E+4	8.456E+4
DATA SET 9	
T = 298.0	
9.573E+4	3.035E+1
9.610E+4	1.495E+1
9.403E+4	9.900E+0
9.419E+4	6.301E+1
9.347E+4	4.400E+1
9.189E+4	2.801E+0
9.[illegible]E+4	2.200E+0
8.971E+4	2.200E+0
8.095E+4	1.801E+0
8.5[illegible]E+4	1.700E+0
8.347E+4	1.500E+0
8.121E+4	1.200E+0
7.815E+4	1.300E+0

ν	α
DATA SET 9(CONT.)	
7.403E+4	5.000E-1
7.089E+4	6.000E-1
6.806E+4	3.600E-1
6.403E+4	2.600E-1
DATA SET 10	
T = 293.0	
8.048E+4	6.400E+1
7.855E+4	4.880E+1
7.685E+4	3.430E+1
7.565E+4	2.440E+1
7.470E+4	1.710E+1
7.355E+4	1.260E+1
7.153E+4	7.500E+0
6.961E+4	5.300E+0
6.839E+4	4.000E+0
6.728E+4	3.000E+0
6.645E+4	2.400E+0
6.470E+4	2.000E+0
6.323E+4	1.700E+0
6.065E+4	1.300E+0
5.815E+4	1.300E+0
5.569E+4	1.100E+0
5.403E+4	1.000E+0
5.250E+4	1.000E+0
DATA SET 11	
T = 390.0	
4.831E+4	5.000E-1
4.765E+4	4.510E-1
4.587E+4	3.560E-1
4.336E+4	2.920E-1
4.107E+4	2.440E-1
4.000E+4	2.170E-1
3.840E+4	2.020E-1
3.522E+4	1.770E-1
3.269E+4	1.550E-1
3.155E+4	1.220E-1

ν	α
DATA SET 11(CONT.)	
3.022E+4	1.000E-1
2.937E+4	8.000E-2
2.589E+4	6.900E-2
2.703E+4	5.500E-2
2.597E+4	4.400E-2
2.469E+4	3.100E-2
2.331E+4	2.300E-2
2.212E+4	1.700E-2
2.175E+4	1.200E-2
1.972E+4	9.000E-3
1.890E+4	7.000E-3
DATA SET 12	
T = 390.0	
4.717E+4	2.110E-2
4.292E+4	1.240E-2
4.115E+4	1.500E-2
3.717E+4	8.300E-3
3.333E+4	4.000E-3
2.950E+4	1.700E-3
2.681E+4	8.000E-4
DATA SET 13	
T = 300.0	
3.652E+3	4.000E-3
3.845E+3	7.000E-3
3.833E+3	1.000E-2
3.824E+3	1.400E-2
3.814E+3	1.900E-2
3.807E+3	2.500E-2
3.795E+3	3.300E-2
3.795E+3	4.900E-2
3.779E+3	6.100E-2
3.774E+3	7.600E-2
3.768E+3	9.700E-2
3.764E+3	1.230E-1
3.759E+3	1.540E-1

ν	α
DATA SET 13(CONT.)	
3.757E+3	1.730E-1
3.754E+3	2.050E-1
3.748E+3	2.570E-1
3.747E+3	2.990E-1
3.738E+3	3.820E-1
3.736E+3	3.930E-1
3.731E+3	3.840E-1
3.727E+3	3.520E-1
3.720E+3	2.600E-1
3.716E+3	2.060E-1
3.711E+3	1.680E-1
3.709E+3	1.360E-1
3.695E+3	1.090E-1
3.686E+3	9.400E-2
3.681E+3	7.400E-2
3.676E+3	8.300E-2
3.672E+3	9.500E-2
3.670E+3	8.000E-2
3.660E+3	6.100E-2
3.660E+3	4.400E-2
3.659E+3	4.000E-2
3.655E+3	4.000E-2
3.647E+3	4.000E-2
3.643E+3	5.700E-2
3.640E+3	5.700E-2
3.635E+3	5.000E-2
3.630E+3	5.400E-2
3.626E+3	8.000E-2
3.623E+3	9.700E-2
3.619E+3	1.050E-1
3.618E+3	9.700E-2
3.611E+3	6.000E-2
3.609E+3	3.300E-2
3.604E+3	2.400E-2
3.598E+3	2.400E-2
3.593E+3	1.600E-2
3.589E+3	1.600E-2
3.582E+3	2.400E-2
3.578E+3	2.400E-2
3.571E+3	1.700E-2

ν	α
DATA SET 13(CONT.)	
3.563E+3	1.330E-2
3.550E+3	6.600E-3
3.539E+3	2.800E-3
DATA SET 14	
T = 293.0	
5.348E+4	3.451E+0
5.255E+4	2.447E+0
5.025E+4	1.810E+0
4.920E+4	1.555E+0
4.879E+4	1.449E+0
4.739E+4	1.391E+0
4.673E+4	1.191E+0
4.500E+4	8.410E-1
4.444E+4	5.570E-1
4.314E+4	6.300E-2
4.200E+4	5.300E-2
4.032E+4	2.190E-1
3.937E+4	3.170E-1
3.748E+4	3.470E-1
3.717E+4	3.330E-1
3.595E+4	1.930E-1
3.571E+4	1.600E-1
3.500E+4	6.800E-2
3.400E+4	9.000E-3
DATA SET 15	
T = 293.0	
2.000E+3	3.700E-2
1.814E+3	1.950E-1
1.667E+3	4.400E-1
1.535E+3	9.900E-1
1.429E+3	2.000E+0
1.333E+3	4.100E+0
1.250E+3	7.300E+0
1.176E+3	9.500E+0
1.111E+3	1.200E+1
1.053E+3	1.950E+1

TABLE 4. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 15(CONT.)	
1.6.0E+3	3.370E+1
9.524E+2	4.450E+1
9.091E+2	6.210E+1
8.696E+2	9.000E+1
8.452E+2	1.292E+2
8.333E+2	1.450E+2
8.244E+2	1.965E+2
8.183E+2	1.924E+2
8.000E+2	2.200E+2
7.952E+2	2.255E+2
7.899E+2	2.251E+2
7.800E+2	2.323E+2
7.[illegible]E+2	2.372E+2
7.746E+2	2.391E+2
7.699E+2	2.325E+2
7.694E+2	2.300E+2
7.039E+2	2.291E+2
7.593E+2	2.194E+2
7.547E+2	2.097E+2
7.5[illegible]E+2	2.075E+2
7.453E+2	2.075E+2
7.407E+2	2.087E+2
7.360E+2	2.147E+2
7.241E+2	2.449E+2
7.143E+2	3.000E+2
6.897E+2	4.000E+2
6.667E+2	1.760E+3
1.452E+2	3.000E+3
6.349E+2	4.200E+3
DATA SET 16	
T = 293.0	
9.897E+4	2.320E+0
9.703E+4	1.950E+0
9.518E+4	1.510E+0
8.340E+4	1.130E+0
8.172E+4	9.900E-1
8.0[illegible]E+4	8.300E-1
7.862E+4	5.000E-1

ν	α
DATA SET 16(CONT.)	
7.698E+4	4.400E-1
7.553E+4	3.700E-1
7.424E+4	3.000E-1
7.153E+4	2.500E-1
6.900E+4	2.100E-1
6.007E+4	1.800E-1
6.400E+4	1.300E-1
6.250E+4	8.000E-2
DATA SET 17	
T = 100.0	
2.994E+2	1.420E+1
2.945E+2	8.037E+0
2.919E+2	4.345E+0
2.900E+2	3.341E+0
2.883E+2	2.553E+0
2.809E+2	1.955E+0
2.834E+2	1.445E+0
2.803E+2	1.043E+0
2.774E+2	7.935E-1
2.737E+2	5.997E-1
2.700E+2	4.677E-1
2.656E+2	3.594E-1
2.600E+2	2.681E-1
2.559E+2	2.334E-1
2.525E+2	1.941E-1
2.447E+2	1.577E-1
2.394E+2	1.330E-1
2.320E+2	1.120E-1
2.254E+2	9.479E-2
2.192E+2	7.620E-2
2.075E+2	6.252E-2
1.999E+2	5.572E-2
1.990E+2	4.742E-2
1.813E+2	4.131E-2

ν	α
DATA SET 18	
T = 300.0	
9.476E+4	1.191E+4
9.677E+4	1.338E+5
9.839E+4	2.644E+5
9.919E+4	4.213E+5
9.759E+4	5.865E+5
1.008E+5	1.482E+6
1.016E+5	2.425E+6
1.020E+5	2.667E+6
1.024E+5	2.819E+6
1.028E+5	2.843E+6
1.032E+5	2.763E+6
1.036E+5	2.631E+6
1.040E+5	2.484E+6
1.044E+5	2.323E+6
1.048E+5	2.121E+6
1.052E+5	2.023E+6
1.056E+5	1.898E+6
1.060E+5	1.772E+6
1.065E+5	1.645E+6
1.069E+5	1.477E+6
1.073E+5	1.361E+6
1.077E+5	1.245E+6
1.081E+5	1.141E+6
1.085E+5	1.036E+6
1.089E+5	9.460E+5
1.093E+5	7.964E+5
1.097E+5	6.891E+5
1.101E+5	5.948E+5
1.105E+5	5.831E+5
1.109E+5	6.410E+5
1.113E+5	7.272E+5
1.117E+5	7.860E+5
1.121E+5	8.311E+5
1.125E+5	8.705E+5
1.129E+5	9.084E+5
1.137E+5	9.717E+5
1.145E+5	1.022E+6
1.153E+5	1.043E+6
1.161E+5	1.065E+6

ν	α
DATA SET 18(CONT.)	
1.169E+5	1.087E+6
1.177E+5	1.095E+6
1.185E+5	1.367E+6
1.202E+5	1.472E+6
1.218E+5	1.541E+6
1.234E+5	9.458E+5
1.254E+5	9.268E+5
1.266E+5	8.274E+5
1.274E+5	7.520E+5
1.282E+5	6.768E+5
1.294E+5	6.046E+5
1.293E+5	6.363E+5
1.306E+5	6.403E+5
1.323E+5	6.648E+5
1.363E+5	8.[illegible]5E+5
1.395E+5	8.941E+5
1.403E+5	9.169E+5
1.411E+5	9.399E+5
1.419E+5	9.275E+5
1.427E+5	9.327E+5
1.435E+5	8.756E+5
1.476E+5	8.345E+5
1.434E+5	8.255E+5
1.492E+5	8.249E+5
1.503E+5	8.294E+5
1.532E+5	9.456E+5
1.873E+5	1.047E+6
1.613E+5	1.170E+6
1.693E+5	1.350E+6
1.694E+5	1.554E+6
1.726E+5	1.735E+6
1.742E+5	1.939E+6
1.759E+5	1.944E+6
1.774E+5	2.073E+6
1.754E+5	2.115E+6
1.806E+5	2.066E+6
1.823E+5	1.993E+6
1.839E+5	1.872E+6
1.847E+5	1.810E+6
1.851E+5	1.768E+6

ν	α
DATA SET 18(CONT.)	
1.855E+5	1.725E+6
1.859E+5	1.682E+6
1.863E+5	1.639E+6
1.871E+5	1.552E+6
1.879E+5	1.464E+6
1.887E+5	1.399E+6
1.903E+5	1.339E+6
1.911E+5	1.261E+6
1.935E+5	1.022E+6
1.976E+5	7.697E+5
2.016E+5	5.827E+5
DATA SET 19	
T = 77.0	
1.825E+3	3.600E-2
1.748E+3	6.393E-2
1.681E+3	1.016E-1
1.612E+3	1.353E-1
1.543E+3	3.426E-1
1.513E+3	4.316E-1
1.488E+3	4.712E-1
1.460E+3	6.045E-1
1.449E+3	9.288E-1
1.364E+3	1.347E+0
1.318E+3	2.143E+0
1.297E+3	2.595E+0
1.277E+3	3.217E+0
1.252E+3	3.773E+0
1.235E+3	4.352E+0
1.215E+3	4.784E+0
1.200E+3	5.085E+0
1.179E+3	5.258E+0
1.144E+3	5.492E+0
1.131E+3	5.736E+0
1.122E+3	5.747E+0
1.099E+3	6.112E+0
1.071E+3	7.428E+0
1.029E+3	1.147E+1
9.785E+2	1.967E+1

ν	α
DATA SET 19(CONT.)	
9.542E+2	2.346E+1
9.32[illegible]E+2	2.447E+1
9.13[illegible]E+2	2.85[illegible]E+1
8.921E+2	3.627E+1
8.721E+2	4.302E+1
8.52[illegible]E+2	5.027E+1
8.347E+2	7.456E+1
8.194E+2	9.784E+1
8.032E+2	1.238E+2
7.800E+2	1.395E+2
7.710E+2	1.493E+2
7.447E+2	1.390E+2
7.289E+2	1.432E+2
7.148E+2	1.575E+2
7.027E+2	1.770E+2
6.900E+2	2.046E+2
6.793E+2	2.417E+2
DATA SET 20	
T = 293.0	
1.829E+3	5.756E-2
1.790E+3	5.017E-2
1.675E+3	1.532E-1
1.603E+3	2.475E-1
1.943E+3	4.140E-1
1.493E+3	6.2[illegible]E-1
1.439E+3	9.446E-1
1.389E+3	1.425E+0
1.370E+3	1.6[illegible]2E+0
1.34[illegible]E+3	2.2[illegible]E+0
1.319E+3	2.556E+0
1.297E+3	3.2[illegible]E+0
1.277E+3	4.[illegible]5E+0
1.253E+3	5.299E+0
1.215E+3	5.762E+0
1.179E+3	6.499E+0
1.147E+3	7.256E+0
1.120E+3	7.495E+0
1.093E+3	8.556E+0

TABLE 4. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 20(CONT.)	
1.656E+3	1.1[illegible]E+1
1.[illegible]30E+3	1.[illegible]26E+1
1.[illegible]03E+3	1.833E+1
9.766E+2	2.523E+1
9.560E+2	3.0[illegible]0E+1
9.116E+2	4.230E+1
8.718E+2	6.3[illegible]4E+1
8.354E+2	9.688E+1
8.153E+2	1.240E+2
8.019E+2	1.511E+2
7.97[illegible]E+2	1.751E+2
7.71[illegible]E+2	1.863E+2
DATA SET 21	
T = 293.0	
1.916E+3	8.223E-2
1.740E+3	1.3[illegible]0E-1
1.697E+3	2.124E-1
1.6[illegible]5E+3	3.823E-1
1.543E+3	6.[illegible]1E-1
1.5[illegible]8E+3	8.427E-1
1.4[illegible]6E+3	9.889E-1
1.4[illegible]0E+3	1.1[illegible]E+0
1.438E+3	1.477E+0
1.4[illegible]0E+3	1.7[illegible]E+0
1.349E+3	2.141E+0
1.306E+3	2.92[illegible]E+0
1.333E+3	2.9[illegible]E+0
1.321E+3	3.421E+0
1.3[illegible]E+3	4.[illegible]7E+0
1.2[illegible]E+3	4.77[illegible]E+0
1.229E+3	6.495E+0
1.211E+3	7.[illegible]5E+0
1.1[illegible]E+3	7.779E+0
1.15[illegible]E+3	8.7[illegible]E+0
1.1[illegible]E+3	9.190E+0
1.12[illegible]E+3	9.927E+0
1.[illegible]93E+3	1.13[illegible]E+1
9.99[illegible]E+2	2.392E+1
9.533E+2	4.022E+1
9.32[illegible]E+2	4.749E+1
9.091E+2	5.073E+1
8.9[illegible]9E+2	6.956E+1
8.090E+2	8.327E+1
8.525E+2	1.044E+2
8.3[illegible]0E+2	1.193E+2
8.183E+2	1.528E+2
8.[illegible]19E+2	1.842E+2
7.302E+2	2.085E+2
7.564E+2	2.399E+2
7.410E+2	2.365E+2
7.283E+2	2.387E+2
7.140E+2	2.474E+2
7.032E+2	2.681E+2
DATA SET 22	
T = 573.0	
1.813E+3	2.458E-1
1.795E+3	4.167E-1
1.073E+3	6.798E-1
1.0[illegible]2E+3	1.[illegible]91E+0
1.5[illegible]0E+3	1.[illegible]62E+0
1.441E+3	2.[illegible]9[illegible]E+0
1.441E+3	3.[illegible]8E+0
1.291E+3	4.193E+0
1.335E+3	5.72[illegible]E+0
1.2[illegible]9E+3	7.420E+0
1.259E+3	9.219E+0
1.22[illegible]E+3	1.21[illegible]E+1
1.1[illegible]9E+3	1.767E+1
1.[illegible]96E+3	2.415E+1
1.[illegible]312E+3	3.471E+1
3.735E+2	5.294E+1
4.32[illegible]E+2	7.03[illegible]E+1
5.921E+2	1.137E+2
6.72[illegible]E+2	1.374E+2
3.35[illegible]E+2	1.693E+2
8.019E+2	2.367E+2
7.716E+2	3.425E+2
7.559E+2	3.887E+2
7.283E+2	4.737E+2
DATA SET 23	
T = 77.0	
1.9[illegible]5E+2	2.410E+1
1.566E+2	1.723E+1
1.233E+2	1.133E+1
9.5[illegible]6E+1	8.734E+0
7.178E+1	1.859E+0
2.871E+1	1.167E-1
DATA SET 24	
T = 293.0	
1.910E+2	2.179E+2
1.589E+2	1.63[illegible]E+2
1.227E+2	1.167E+2
9.[illegible]61E+1	8.714E+1
7.228E+1	2.49[illegible]E+1
2.9[illegible]4E+1	2.467E+0
DATA SET 25	
T = 573.0	
1.932E+2	6.629E+2
1.[illegible]89E+2	5.131E+2
1.233E+2	3.717E+2
9.594E+1	2.892E+2
7.201E+1	9.599E+1
2.921E+1	1.189E+1
DATA SET 26	
T = 30[illegible].0	
1.945E+3	9.[illegible]0E-2
1.944E+3	1.2[illegible]8E-1
1.744E+3	2.400E-1
1.643E+3	5.2[illegible]6E-1
1.5[illegible]5E+3	1.[illegible]8[illegible]E+0
1.447E+3	1.85[illegible]E+0
1.395E+3	2.53[illegible]E+0
1.346E+3	3.68[illegible]E+0
1.292E+3	5.66[illegible]E+0
1.24[illegible]E+3	7.89[illegible]E+0
1.191E+3	9.96[illegible]E+0
DATA SET 27	
T = 7.5.0	
2.542E+3	1.6[illegible]6E-1
1.9[illegible]5E+3	3.[illegible]E-1
1.844E+3	5.4[illegible]E-1
1.742E+3	9.7[illegible]E-1
1.644E+3	1.78[illegible]E+0
1.597E+3	2.36[illegible]E+0
1.544E+3	3.27[illegible]E+0
1.492E+3	4.26[illegible]E+0
1.44[illegible]E+3	5.59[illegible]E+0
1.389E+3	7.27[illegible]E+0
1.341E+3	9.58[illegible]E+0
DATA SET 28	
T = 835.0	
2.093E+3	1.90[illegible]E-1
1.944E+3	3.30[illegible]E-1
1.894E+3	6.2[illegible]E-1
1.795E+3	1.1[illegible]E+0
1.743E+3	1.45[illegible]E+0
1.694E+3	1.92[illegible]E+0
1.642E+3	2.52[illegible]E+0
1.593E+3	3.31[illegible]E+0
1.542E+3	4.35[illegible]E+0
1.492E+3	5.75[illegible]E+0
1.44[illegible]E+3	7.51[illegible]E+0
1.393E+3	9.72[illegible]E+0
DATA SET 29	
T = 975.0	
2.345E+3	1.0[illegible]0E-1
2.245E+3	1.3[illegible]E-1
2.142E+3	2.0[illegible]E-1
2.042E+3	3.9[illegible]E-1
1.943E+3	7.1[illegible]E-1
1.843E+3	1.17[illegible]E+0
1.743E+3	2.0[illegible]E+0
1.7[illegible]E+3	2.62[illegible]E+0
1.644E+3	3.37[illegible]E+0
1.592E+3	4.37[illegible]E+0
1.543E+3	5.0[illegible]E+0
1.490E+3	7.36[illegible]E+0
1.434E+3	9.560E+0
DATA SET 30	
T = 1160.0	
2.400E+3	1.50[illegible]E-1
2.294E+3	2.20[illegible]E-1
2.193E+3	4.0[illegible]E-1
2.094E+3	7.1[illegible]E-1
1.992E+3	1.24[illegible]E+0
1.892E+3	1.91[illegible]E+0
1.845E+3	2.47[illegible]E+0
1.798E+3	3.2[illegible]E+0
1.743E+3	4.20[illegible]E+0
1.697E+3	5.5[illegible]E+0
1.639E+3	7.18[illegible]E+0
1.591E+3	9.020E+0
DATA SET 31	
T = 36[illegible].0	
2.304E+3	5.90[illegible]E-3
2.203E+3	1.15[illegible]E-2
2.101E+3	2.18[illegible]E-2
2.0[illegible]4E+3	4.23[illegible]E-2
1.949E+3	6.24[illegible]E-2
1.901E+3	8.2[illegible]E-2
1.855E+3	1.143E-1
1.80[illegible]E+3	1.7[illegible]E-1
1.752E+3	2.46[illegible]E-1
1.7[illegible]E+3	3.4[illegible]E-1
1.659E+3	5.07[illegible]E-1
1.605E+3	7.[illegible]3E-1
1.55[illegible]E+3	9.397E-1
1.497E+3	1.30[illegible]E+0
1.449E+3	1.574E+0
DATA SET 32	
T = 298.0	
3.4[illegible]E+0	2.754E-4
8.75[illegible]E-1	6.516E-4
2.935E-1	1.24[illegible]E-3
DATA SET 33	
T = 1275.0	
7.27[illegible]E+2	2.832E+3
6.87[illegible]E+2	3.453E+3
6.5[illegible]E+2	4.1[illegible]E+3
6.[illegible]1E+2	5.[illegible]E+3
5.7[illegible]E+2	5.653E+3
5.4[illegible]E+2	6.24[illegible]E+3
4.8[illegible]E+2	6.997E+3
4.620E+2	7.625E+3
4.37[illegible]E+2	8.97[illegible]E+3
4.18[illegible]E+2	8.77[illegible]E+3
3.3[illegible]E+2	8.3[illegible]E+3
3.57[illegible]E+2	8.[illegible]E+3
3.44[illegible]E+2	9.620E+3
3.24[illegible]E+2	9.13[illegible]E+3
2.9[illegible]E+2	4.373E+3
2.57[illegible]E+2	3.955E+3
2.09[illegible]E+2	2.935E+3
2.11[illegible]E+2	2.5[illegible]E+3
1.9[illegible]E+2	1.673E+3
1.365E+2	1.111E+3

TABLE 4. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 33(CONT.)	
1.300E+2	5.905E+2
DATA SET 34	
T = 300.0	
1.100E+3	8.749E+0
1.139E+3	8.593E+0
1.161E+3	4.151E+0
1.001E+3	9.333E+0
1.000E+3	9.149E+0
9.910E+2	2.491E+1
9.910E+2	4.227E+1
9.910E+2	4.990E+1
9.210E+2	9.324E+1
9.110E+2	6.947E+1
8.900E+2	8.847E+1
8.390E+2	1.924E+2
8.000E+2	1.710E+2
8.000E+2	1.917E+2
8.100E+2	2.117E+2
8.100E+2	2.023E+2
7.900E+2	2.049E+2
7.810E+2	2.001E+2
7.710E+2	2.170E+2
7.710E+2	2.319E+2
DATA SET 35	
T = 60.0	
1.192E+3	1.344E+1
1.150E+3	1.279E+1
1.076E+3	1.749E+1
1.039E+3	1.910E+1
9.190E+2	2.095E+1
9.910E+2	9.349E+1
9.390E+2	9.433E+1
8.200E+2	1.170E+2
7.990E+2	1.494E+2
7.780E+2	1.974E+2
7.590E+2	2.360E+2

ν	α
DATA SET 36(CONT.)	
7.390E+2	1.328E+2
7.290E+2	1.470E+2
7.190E+2	1.984E+2
DATA SET 36	
T = 20.0	
1.150E+3	5.781E+0
1.082E+3	5.439E+0
1.073E+3	6.740E+0
1.044E+3	1.095E+1
1.030E+3	1.046E+1
1.022E+3	1.793E+1
1.007E+3	2.273E+1
1.002E+3	2.392E+1
9.892E+2	2.113E+1
9.820E+2	2.096E+1
9.710E+2	2.350E+1
9.190E+2	3.655E+1
8.990E+2	4.580E+1
8.790E+2	5.493E+1
8.600E+2	6.000E+1
7.900E+2	1.425E+2
7.830E+2	1.457E+2
7.830E+2	1.495E+2
7.700E+2	1.535E+2
7.590E+2	1.363E+2
7.590E+2	1.183E+2
7.530E+2	1.164E+2
7.410E+2	1.235E+2
7.320E+2	1.372E+2
7.240E+2	1.492E+2
7.190E+2	1.590E+2
DATA SET 37	
T = 63.0	
0.750E+2	0.971E+0
0.783E+2	0.249E+1
0.803E+2	0.243E+1

ν	α
DATA SET 37(CONT.)	
0.844E+2	0.221E+1
0.926E+2	0.225E+1
0.980E+2	0.244E+1
0.103E+3	0.272E+1
0.103E+3	0.263E+1
0.113E+3	0.455E+1
0.124E+3	0.349E+1
0.133E+3	0.373E+1
0.139E+3	0.398E+1
0.140E+3	0.391E+1
0.159E+3	0.512E+1
0.163E+3	0.504E+1
0.167E+3	0.604E+1
0.170E+3	0.660E+1
0.178E+3	0.666E+1
DATA SET 38	
T = 77.0	
0.098E+2	0.971E+0
0.735E+2	0.207E+1
0.761E+2	0.415E+1
0.787E+2	0.659E+1
0.828E+2	0.724E+1
0.869E+2	0.683E+1
0.970E+2	0.019E+1
0.110E+3	0.691E+1
0.116E+3	0.714E+1
0.121E+3	0.764E+1
0.135E+3	0.955E+1
0.140E+3	0.793E+1
0.147E+3	0.977E+1
0.156E+3	0.900E+1
0.163E+3	0.110E+2
0.181E+3	0.130E+2
0.197E+3	0.165E+2
0.222E+3	0.231E+2
0.239E+3	0.275E+2
0.250E+3	0.307E+2
0.257E+3	0.351E+2

ν	α
DATA SET 38(CONT.)	
0.268E+3	0.402E+2
0.276E+3	0.494E+2
0.284E+3	0.017E+2
0.287E+3	0.734E+2
0.292E+3	0.833E+2
DATA SET 39	
T = 300.0	
0.280E+2	0.835E+0
0.273E+2	0.985E+0
0.299E+2	0.140E+1
0.300E+2	0.484E+1
0.422E+2	0.457E+1
0.514E+2	0.889E+1
0.593E+2	0.192E+2
0.676E+2	0.297E+2
0.725E+2	0.332E+2
0.759E+2	0.054E+2
0.814E+2	0.990E+2
0.804E+2	0.105E+3
0.913E+2	0.121E+3
0.959E+2	0.116E+3
0.107E+3	0.116E+3
0.111E+3	0.121E+3
0.115E+3	0.126E+3
0.120E+3	0.123E+3
0.134E+3	0.125E+3
0.149E+3	0.125E+3
DATA SET 40	
T = 293.0	
0.607E+2	2.078E+3
0.254E+2	5.359E+3
5.889E+2	6.741E+3
5.504E+2	5.264E+3
5.273E+2	1.116E+4
5.011E+2	9.741E+3
4.773E+2	9.945E+3

ν	α
DATA SET 40(CONT.)	
4.546E+2	8.849E+3
4.350E+2	1.073E+4
4.240E+2	1.030E+4
3.843E+2	1.135E+4
3.694E+2	1.284E+4
3.572E+2	1.294E+4
3.436E+2	1.552E+4
3.329E+2	1.709E+4
3.211E+2	1.990E+4
3.117E+2	2.197E+4
3.019E+2	2.763E+4
2.940E+2	1.553E+4
2.950E+2	9.257E+3
2.773E+2	7.740E+3
DATA SET 41	
T = 573.0	
6.232E+2	6.260E+3
5.547E+2	9.814E+3
5.273E+2	1.002E+4
4.997E+2	1.041E+4
4.701E+2	1.042E+4
4.557E+2	1.061E+4
4.334E+2	1.135E+4
4.170E+2	1.243E+4
3.999E+2	1.305E+4
3.843E+2	1.442E+4
3.710E+2	1.585E+4
3.504E+2	1.654E+4
3.442E+2	1.698E+4
3.317E+2	1.715E+4
3.222E+2	1.845E+4
3.102E+2	1.944E+4
3.024E+2	1.932E+4
2.943E+2	1.879E+4
2.830E+2	1.887E+4
2.857E+2	1.559E+4
2.778E+2	1.334E+4

ν	α
DATA SET 42	
T = 673.0	
6.005E+2	4.150E+3
6.079E+2	7.170E+3
5.933E+2	8.369E+3
5.947E+2	6.054E+3
5.242E+2	8.372E+3
4.997E+2	8.946E+3
4.761E+2	8.982E+3
4.534E+2	9.299E+3
4.334E+2	9.640E+3
4.206E+2	1.070E+4
3.935E+2	1.009E+4
3.943E+2	1.024E+4
3.724E+2	1.156E+4
3.584E+2	1.255E+4
3.435E+2	1.337E+4
3.284E+2	1.395E+4
3.222E+2	1.359E+4
3.127E+2	1.354E+4
3.024E+2	1.695E+4
2.945E+2	1.137E+4
2.856E+2	1.124E+4
2.773E+2	9.507E+3
DATA SET 43	
T = 293.0	
1.477E+2	2.543E+2
1.312E+2	2.292E+2
1.230E+2	2.123E+2
1.100E+2	2.036E+2
1.112E+2	2.915E+2
1.087E+2	1.995E+2
1.000E+2	1.631E+2
9.624E+1	1.643E+2
8.929E+1	1.492E+2
8.433E+1	1.333E+2
7.813E+1	1.227E+2
7.407E+1	7.193E+1
6.979E+1	4.588E+1

TABLE 4. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 43(CONT.)	
6.933E+1	4.593E+1
6.662E+1	3.497E+1
5.436E+1	3.192E+1
4.762E+1	2.209E+1
4.196E+1	1.062E+1
3.663E+1	7.371E+0
3.395E+1	5.011E+1
3.444E+1	4.512E+0
3.297E+1	4.116E+0
2.894E+1	3.741E+0
3.031E+1	3.023E+0
3.115E+1	3.533E+0
2.771E+1	3.415E+0
2.646E+1	3.3[illegible]E+0
2.571E+1	3.747E+0
2.462E+1	4.077E+0
2.393E+1	3.371E+0
2.217E+1	3.272E+0
2.123E+1	2.9[illegible]E+0
2.092E+1	2.592E+0
2.102E+1	2.494E+0
2.066E+1	2.956E+0
1.972E+1	2.702E+0
1.946E+1	2.702E+0
1.847E+1	2.522E+0
1.825E+1	2.624E+0
1.778E+1	2.711E+0
1.727E+1	2.471E+0
1.727E+1	2.3[illegible]E+0
1.675E+1	2.1[illegible]E+0
1.651E+1	2.0[illegible]E+0
1.534E+1	2.197E+0
1.498E+1	2.319E+0
1.445E+1	2.191E+0
1.342E+1	2.199E+0
1.304E+1	2.0[illegible]E+0
1.260E+1	1.751E+0
1.193E+1	1.759E+0
1.175E+1	1.901E+0
1.157E+1	2.243E+0

ν	α
DATA SET 43(CONT.)	
1.124E+1	2.273E+0
1.091E+1	2.112E+0
1.044E+1	2.112E+0
1.023E+1	1.931E+0
1.001E+1	1.784E+0
9.524E+0	1.424E+0
9.731E+0	1.350E+0
9.174E+0	1.234E+0
9.009E+0	1.143E+0
8.021E+0	6.676E-1
DATA SET 44	
T = 300.0	
4.312E+2	1.202E+4
4.092E+2	1.399E+4
3.831E+2	1.574E+4
3.621E+2	1.749E+4
3.039E+2	1.919E+4
3.472E+2	2.247E+4
3.373E+2	2.441E+4
3.311E+2	2.621E+4
3.203E+2	3.097E+4
3.035E+2	3.479E+4
3.196E+2	3.481E+4
3.080E+2	3.328E+4
3.054E+2	3.044E+4
3.031E+2	2.495E+4
3.022E+2	2.223E+4
2.995E+2	1.912E+4
2.857E+2	7.699E+3
2.717E+2	4.883E+3
2.639E+2	3.579E+3
DATA SET 45	
T = 700.0	
3.971E+2	1.712E+4
3.699E+2	1.983E+4
3.446E+2	2.279E+4

ν	α
DATA SET 45(CONT.)	
3.378E+2	2.420E+4
3.333E+2	2.589E+4
3.279E+2	2.802E+4
3.236E+2	3.273E+4
3.165E+2	3.845E+4
3.115E+2	3.699E+4
3.077E+2	2.417E+4
3.036E+2	1.359E+4
2.994E+2	1.035E+4
2.942E+2	6.948E+3
2.907E+2	4.420E+3
2.865E+2	2.845E+3
2.780E+2	1.120E+3
2.721E+2	5.449E+2
DATA SET 46	
T = 600.0	
3.623E+2	1.598E+4
3.999E+2	1.690E+4
3.437E+2	1.784E+4
3.306E+2	1.969E+4
3.393E+2	2.258E+4
3.322E+2	2.465E+4
3.279E+2	2.606E+4
3.225E+2	2.911E+4
3.155E+2	3.406E+4
3.135E+2	3.549E+4
3.077E+2	3.028E+4
3.036E+2	1.440E+4
2.976E+2	1.447E+4
2.933E+2	8.107E+3
2.899E+2	5.699E+3
2.865E+2	3.781E+3
2.774E+2	1.955E+3
2.716E+2	1.153E+3
2.632E+2	7.937E+2

ν	α
DATA SET 47	
T = 300.0	
3.636E+2	1.608E+4
3.571E+2	1.795E+4
3.509E+2	1.922E+4
3.449E+2	2.176E+4
3.390E+2	2.326E+4
3.344E+2	2.569E+4
3.279E+2	2.752E+4
3.226E+2	3.032E+4
3.165E+2	3.054E+4
3.125E+2	3.444E+4
3.077E+2	3.269E+4
3.046E+2	2.036E+4
2.985E+2	1.922E+4
2.950E+2	1.431E+4
2.899E+2	8.808E+3
2.857E+2	5.662E+3
2.786E+2	2.695E+3
2.716E+2	1.703E+3
2.632E+2	1.157E+3
DATA SET 48	
T = 298.0	
3.334E+1	5.153E+0
2.829E+1	3.430E+0
2.229E+1	1.965E+0
1.400E+1	7.669E-1
1.706E+1	4.074E-1
DATA SET 49	
T = 298.5	
9.120E+4	5.571E-1
9.224E+4	5.844E-1
9.323E+4	7.316E-1
9.386E+4	1.046E+0
9.446E+4	1.760E+0
9.506E+4	4.496E+0
9.556E+4	9.796E+0

ν	α
DATA SET 49(CONT.)	
9.603E+4	1.250E+1
9.612E+4	3.472E+1
9.690E+4	4.430E+1
9.802E+4	1.120E+2
9.892E+4	1.820E+2
9.802E+4	2.320E+2
9.790E+4	9.050E+2
DATA SET 50	
T = 437.0	
8.602E+4	3.610E-1
8.722E+4	3.600E-1
8.862E+4	5.440E-1
8.940E+4	6.110E-1
9.300E+4	8.160E-1
9.440E+4	9.910E-1
9.350E+4	1.140E+0
9.360E+4	1.320E+0
9.130E+4	2.480E+0
9.170E+4	4.660E+0
9.220E+4	1.010E+1
9.262E+4	1.990E+1
9.280E+4	2.730E+1
9.320E+4	5.240E+1
9.340E+4	8.100E+1
9.380E+4	1.520E+2
9.420E+4	2.850E+2
9.440E+4	4.003E+2
DATA SET 51	
T = 510.0	
8.500E+4	3.990E-1
8.600E+4	3.980E-1
8.720E+4	4.820E-1
8.820E+4	6.790E-1
8.890E+4	1.270E+0
8.940E+4	2.620E+0
9.000E+4	5.150E+0

ν	α
DATA SET 51(CONT.)	
9.030E+4	7.950E+0
9.050E+4	1.120E+1
9.070E+4	2.730E+1
9.130E+4	2.800E+1
9.270E+4	5.020E+1
9.210E+4	1.140E+2
9.200E+4	2.040E+2
9.260E+4	3.190E+2
9.320E+4	5.030E+2
DATA SET 52	
T = 573.0	
8.500E+4	4.690E-1
8.600E+4	6.220E-1
8.720E+4	1.030E+0
8.800E+4	3.940E+0
8.840E+4	1.090E+1
8.930E+4	2.180E+1
9.000E+4	5.000E+1
9.060E+4	9.780E+1
9.130E+4	2.350E+2
9.170E+4	4.420E+2
DATA SET 53	
T = 300.0	
9.710E+4	2.140E+2
9.050E+4	1.170E+2
9.030E+4	3.590E+1
9.000E+4	1.390E+1
9.510E+4	4.340E+0
9.470E+4	3.080E+0
9.410E+4	2.060E+0
9.330E+4	2.012E+0
9.340E+4	1.920E+0
9.280E+4	1.040E+0
9.210E+4	1.920E+0
9.240E+4	1.700E+0
9.010E+4	1.760E+0

TABLE 4. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Wavenumber Dependence) (continued)

ν	α	ν	α	ν	α
DATA SET 53(CONT.)		DATA SET 53(CONT.)		DATA SET 54 T = 300.0	
8.970E+4	1.840E+0	6.720E+4	5.320E-1		
8.[illegible]E+4	1.690E+0	6.680E+4	4.670E-1	7.950E+4	6.940E-1
8.920E+4	1.550E+0	6.660E+4	4.480E-1	8.070E+4	7.560E-1
8.910E+4	1.600E+0	6.640E+4	4.880E-1	8.140E+4	7.560E-1
8.840E+4	1.550E+0	6.590E+4	4.110E-1	8.240E+4	7.890E-1
8.800E+4	1.550E+0	6.560E+4	3.770E-1	8.400E+4	8.240E-1
8.740E+4	1.550E+0	6.520E+4	3.300E-1	8.520E+4	8.600E-1
8.710E+4	1.550E+0	6.480E+4	3.320E-1	8.610E+4	8.600E-1
8.620E+4	1.550E+0	6.470E+4	2.920E-1	8.730E+4	8.600E-1
8.590E+4	1.550E+0	6.410E+4	2.570E-1	8.900E+4	8.610E-1
8.540E+4	1.490E+0	6.380E+4	2.570E-1	8.970E+4	9.370E-1
8.520E+4	1.490E+0	6.360E+4	2.360E-1	9.040E+4	9.370E-1
8.490E+4	1.360E+0	6.350E+4	2.160E-1	9.140E+4	9.370E-1
8.400E+4	1.420E+0	6.310E+4	1.670E-1	9.220E+4	9.790E-1
8.350E+4	1.490E+0	6.290E+4	1.900E-1	9.260E+4	1.020E+0
8.300E+4	1.400E+0	6.290E+4	1.900E-1	9.330E+4	1.160E+0
8.240E+4	1.490E+0	6.260E+4	1.930E-1	9.350E+4	1.440E+0
8.140E+4	1.420E+0	6.260E+4	1.900E-1	9.450E+4	2.030E+0
8.070E+4	1.350E+0	6.280E+4	1.900E-1	9.470E+4	2.630E+0
8.020E+4	1.300E+0	6.260E+4	1.900E-1	9.500E+4	5.020E+0
7.960E+4	1.360E+0	6.240E+4	1.670E-1	9.560E+4	8.420E+0
7.890E+4	1.310E+0	6.220E+4	1.750E-1	9.760E+4	5.240E+2
7.800E+4	1.350E+0	6.220E+4	1.530E-1		
7.770E+4	1.250E+0	6.190E+4	1.900E-1		
7.700E+4	1.250E+0	6.170E+4	1.670E-1		
7.620E+4	1.150E+0	6.140E+4	1.530E-1		
7.560E+4	1.100E+0	6.120E+4	1.410E-1		
7.500E+4	1.060E+0	6.110E+4	1.670E-1		
7.430E+4	1.010E+0	6.080E+4	1.750E-1		
7.400E+4	1.020E+0	6.040E+4	1.750E-1		
7.330E+4	9.600E-1	5.960E+4	1.750E-1		
7.260E+4	9.230E-1	5.880E+4	1.410E-1		
7.150E+4	1.060E+0	5.830E+4	1.190E-1		
7.130E+4	8.510E-1	5.740E+4	1.240E-1		
7.070E+4	8.100E-1	5.690E+4	1.240E-1		
6.990E+4	7.820E-1	5.620E+4	1.040E-1		
6.950E+4	7.820E-1	5.550E+4	1.040E-1		
6.930E+4	7.170E-1	5.500E+4	1.240E-1		
6.840E+4	6.590E-1	5.320E+4	1.090E-1		
6.810E+4	6.040E-2	5.260E+4	1.090E-1		



Figure 6. Absorption Coefficient of Lithium Fluoride (Temperature Dependence)

TABLE 5. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Temperature Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	43	Stolen, R. and Dransfeld, K.	1965	T	31.25	2-413	Single crystals; obtained from the Harshaw Chemical Co. and Isomet Corp.; cylindrical specimen of diameter 2.5 cm, and of varying thickness between 0.1 and 2.5 cm; absorption coefficients directly determined; data extracted from a figure.
2	41	Klier, M.	1958	Z	192.3	77-561	Crystal; plate specimen; absorption coefficients deduced from transmittance measurements and estimated reflectivity; reflectivity estimated by assuming n = 3.07 for the wavelength and in the entire temperature range; data extracted from a figure; estimated uncertainty about 5 to 10%.
3	41	Klier, M.	1958	Z	157.7	77-536	Same as above.
4	41	Klier, M.	1958	Z	122.7	77-552	Same as above.
5	41	Klier, M.	1958	Z	95.24	77-553	Same as above.
6	41	Klier, M.	1958	Z	71.43	77-571	Same as above.
7	41	Klier, M.	1958	Z	28.57	120-555	Same as above.

TABLE 6. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE (Temperature Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

DATA SET 1
ν = 3.125E+1

T	α
211.6	4.734E+2
226.4	6.[illegible]E+2
246.[illegible]	7.[illegible]E+2
279.[illegible]	9.7[illegible]E+2
[illegible]	1.[illegible]E+3
317.[illegible]	1.[illegible]E+3
331.0	1.21[illegible]E+3
369.0	1.433E+3
413.[illegible]	1.815E+3

DATA SET 2
ν = 1.928E+2

T	α
76.9	2.347E+1
85.5	3.277E+1
116.2	4.331E+1
152.4	7.5[illegible]E+1
216.3	1.251E+2
252.1	2.139E+2
347.5	2.715E+2
394.5	3.032E+2
401.3	4.09[illegible]E+2
517.6	5.323E+2
561.[illegible]	6.327E+2

DATA SET 3
ν = 1.577E+2

T	α
76.9	1.035E+1
90.8	2.301E+1
116.1	3.075E+1
155.2	5.849E+1
217.3	9.91[illegible]E+1
249.7	1.911E+2
331.9	2.[illegible]24E+2
380.2	2.582E+2
439.5	3.343E+2
479.7	3.643E+2
535.8	4.387E+2

DATA SET 4
ν = 1.227E+2

T	α
76.9	1.067E+1
93.0	1.824E+1
132.4	2.534E+1
157.4	3.49[illegible]E+1
194.5	4.519E+1
2[illegible]9.4	6.855E+1
289.7	1.14[illegible]E+2
366.4	1.591E+2
451.9	2.265E+2
51[illegible].5	3.[illegible]24E+2
552.[illegible]	3.35[illegible]E+2

DATA SET 5
ν = 9.524E+1

T	α
76.9	7.085E+0
82.2	9.311E+0
88.5	1.135E+1
9[illegible]	1.355E+1
1[illegible].7	1.399E+1
1[illegible]3.6	1.048E+1
122.7	1.771E+1
137.4	2.467E+1
207.9	3.443E+1
2[illegible]3.7	5.[illegible]94E+1
224.0	5.956E+1
249.5	6.53[illegible]E+1
265.5	7.692E+1
328.9	1.122E+2
394.5	1.452E+2
431.5	1.750E+2
49[illegible].9	2.183E+2
553.4	2.455E+2

DATA SET 6
ν = 7.143E+1

T	α
76.9	1.651E+0
82.2	2.130E+0

DATA SET 6(CONT.)

T	α
87.7	2.893E+0
97.3	3.393E+0
116.2	3.537E+0
149.6	3.967E+0
122.2	5.314E+0
132.1	5.727E+0
179.1	8.419E+0
197.7	1.257E+1
219.8	1.174E+1
235.0	1.359E+1
263.6	1.889E+1
276.7	2.193E+1
289.1	2.595E+1
330.4	3.549E+1
377.6	4.113E+1
414.0	5.762E+1
511.2	6.999E+1
571.5	1.016E+2

DATA SET 7
ν = 2.857E+1

T	α
119.9	2.585E-1
128.5	3.231E-1
1[illegible]1.4	5.852E-1
19[illegible].7	9.155E-1
199.9	1.099E+0
218.8	1.407E+0
229.6	1.501E+0
291.7	2.291E+0
375.8	5.188E+0
405.5	5.547E+0
444.6	6.014E+0
473.2	7.[illegible]1E+0
515.2	8.159E+0
554.6	1.07[illegible]E+1



Figure 7. Reflectivity of Lithium Fluoride

TABLE 7. SUMMARY OF MEASUREMENTS ON THE REFLECTIVITY OF LITHIUM FLUORIDE

Data Set No	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	22	Jasperse, J.R., Kahan, A., Plendl, J.N., and Mitra, S.S.	1966	R	12.5-40.0	7.5	High purity; single crystal; hand polished until optically flat to about 1/2 wavelength of the mean sodium D lines; annealed in a vacuum furnace for 2 days at a temperature of about 3/4 of the melting temperature of the crystal; near normal reflectivity determined with aluminized mirror reference; reflectivity data checked several times for different samples and for several cycles of heating and cooling and reproduced to within ±1 to ±2%; data extracted from a figure.
2	22	Jasperse, J.R. et al.	1966	R	12.5-44.0	85	Same as above.
3	22	Jasperse, J.R. et al.	1966	R	12.8-45.3	295	Same as above except sample temperatures measured with chrome-alumel thermocouple accurate to within ±2% of the absolute value.
4	22	Jasperse, J.R. et al.	1966	R	14.2-46.0	420	Same as above.
5	22	Jasperse, J.R. et al.	1966	R	13.9-45.3	605	Same as above.
6	22	Jasperse, J.R. et al.	1966	R	13.4-46.0	840	Same as above except sample temperatures measured with an optical pyrometer accurate to within ±2% of the absolute value.
7	22	Jasperse, J.R. et al.	1966	R	13.9-45.3	1060	Same as above.
8	34	Kato, R.	1961	R	0.086-50.183	283	High purity; single crystal; freshly cleaved specimens; near normal (15° incident angle) reflectivities determined from the intensity ratios of the reflected light to the incident light; uncertainties in the reflectivities about 5% in the wavelength region below 0.095 μm and about 1% above 0.095 μm; data extracted from a figure.
9	34	Kato, R.	1961	R	0.087-0.198	283	Same as above except the crystal grown in air in order to see the effects of hydrolysis on the reflectivities.
10	29	Hohls, H.W.	1936	R	12.0-55.4	293	Crystal; grown by the Kyropoulos method; specimen configuration and surface condition unspecified; normal reflectivity determined by using a freshly vacuum coated silver mirror as reference standard; data extracted from a figure; estimated uncertainty about ±10%; temperature was not given, 293 K assumed.
11	35	Roessler, D.M. and Walker, W.C.	1967	R	0.045-0.105	300	Single crystal; obtained from the Harshaw Chemical Co.; specimens cleaved in air and exposed to low humidity atmosphere for about 2 minutes before transferred to vacuum system of reflectometer; near normal reflectivities obtained over a long period of measurements; no contamination from the use of an oil diffusion pump and no damage due to operations of radiation source observed; data extracted from a figure; estimated uncertainty about 5%.
12	41	Klier, M.	1958	R	13.4-26.0	77	Crystal; specimen with top surface highly polished; reflection spectrum measured and determined with respect to a reference mirror made of German V_2A steel; data extracted from a figure.
13	41	Klier, M.	1958	R	13.5-25.0	293	Same as above.

TABLE 7. SUMMARY OF MEASUREMENTS ON THE REFLECTIVITY OF LITHIUM FLUORIDE (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
14	41	Klier, M.	1958	R	14-25.4	573	Same as above.
15	51	Gottlieb, M.	1960	R	14.5-36.0	300	Li^7F crystals obtained by reaction of Li (97.7% pure Li^7), H_2O and HF; vacuum evaporated film (10 μm thick) onto a natural crystal of LiF; heated to 523 K then cooled; data extracted from a figure.
16	51	Gottlieb, M.	1960	R	14.5-36.0	300	Same as above except material obtained from a chemical reactor of $LiCO_2$ (99.9% pure Li^6) with HF.
17	52	Johnson, B.K.	1941	R	0.134-0.164	298	Single crystal; polished surface; back surface ground; measurements made in vacuum; data extracted from a table.
18	53	Sulzbach, F. and Turner, A.F.	1966	R	8.0-36.9	298	Thin film; evaporated in vacuum onto a glass substrate at 528 K; reflectivity measurements made at 298 K using spectrophotometer; data extracted from a figure.
19	53	Sulzbach, F. and Turner, A.F.	1966	R	10.9-36.9	298	Same as above except film was deposited onto glass at 423 K.
20	53	Sulzbach, F. and Turner, A.F.	1966	R	10.6-34.5	298	Crystal; polished surface; data extracted from a figure.
21	54	McCarthy, D.E.	1963	R	2.0-50.0	298	Synthetic crystal; 5 mm thick; polished to flatness of seven fringes on both sides; 30° reflectivity measured; aluminum mirror reference standard; data extracted from a curve.
22	55	Stephan, G., Lemonnier, J., and Robin, G.	1967	R	0.0306-0.103	298	Cleaved; 20° spectral reflectivity measured in vacuum; data extracted from a figure.
23	55	Stephan, G. et al.	1967	R	0.0306-0.103	298	Same as above except for 60° reflectivity.
24	55	Stephan, G. et al.	1967	R	0.37-0.10	298	Polished; 20° reflectivity measured in vacuum; data extracted from a curve.
25	56	Martin, T.P. and Turner, A.F.	1966	R	14.5-28.1	298	Thin film evaporated onto glass substrate in vacuum; temperature of substrate 308 K; near normal reflectivity measured; data extracted from a curve.
26	56	Martin, T.P. and Turner, A.F.	1966	R	14.6-36.0	298	Same as above except substrate temperature 373 K.
27	56	Martin, T.P. and Turner, A.F.	1966	R	14.4-36.0	298	Same as above except substrate temperature 423 K.
28	56	Martin, T.P. and Turner, A.F.	1966	R	14.5-36.0	298	Same as above except substrate temperature 523 K.
29	56	Martin, T.P. and Turner, A.F.	1966	R	16.9-36.0	298	Same as above except substrate temperature 573 K.

TABLE 7. SUMMARY OF MEASUREMENTS ON THE REFLECTIVITY OF LITHIUM FLUORIDE (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
30	56	Martin, T.P. and Turner, A.F.	1966	R	13.7-35.7	298	Single crystal; normal reflectivity measured; data extracted from a figure.
31	57	Rao, K.K., Moravec, T.J., Rife, J.C., and Dexter, R.N.	1975	R	0.041-0.104	100	Single crystal; obtained from the Harshaw Chemical Co.; cleaved specimen of 1 cm diameter and 3 mm thick; specimen kept in vacuum during measurements; near normal reflectivity obtained; data extracted from a curve.
32	58	Schaefer, J.C. and Hill, E.R.	1965	R	2.5-34.8	300	Single crystal from the Harshaw Chemical Co.; geometry not specified; General Electric and Perkin Elmer spectrophotometers used; data extracted from smooth curve.
33	59	Gottlieb, M.	1960	R	15.9-34.7	135	Single crystal from Harshaw Chemical Co.; polished with water compound, normal reflectance measured in vacuum with aluminum mirror reference standard; data extracted from a curve.
34	59	Gottlieb, M.	1960	R	16.5-29.7	210	Same as above.
35	59	Gottlieb, M.	1960	R	11.14-64.11	300	Same as above.
36	59	Gottlieb, M.	1960	R	16.5-28.3	355	Same as above.
37	59	Gottlieb, M.	1960	R	2.0-14.1	300	Same as above.
38	60	Turner, A.F., Chang, L., and Martin, T.R.	1965	R	14-39	293	Polished single crystal; near normal reflectivity measured with aluminum mirror for reference; data extracted from a figure.
39	61	Nakagawa, I.	1971	R	14.7-47.7	293	Single crystal; near normal reflectivity measurements made in a vacuum; data extracted from a curve.
40	37	Tomiki, T. and Miyata, T.	1969	R	0.095-50.155	293	Single crystal; obtained from the Harshaw Chemical Co.; freshly cleaved; normal reflectivity measured in vacuum; data extracted from a curve.
41	40	Machare, A., Soriaga, M.P., and Andermann, G.	1974	R	8.69-50.0	300	Single crystal; well polished and carefully annealed specimens; near normal reflectivity obtained; in the long-wavelength-shoulder region, random error about 2-2.5%; in the high reflectance region, random error about 0.5%; in the low-wavelength-shoulder, random error about 1.5%; data extracted from a table.
42	40	Machare, A. et al.	1974	R	8.69-50.0	80	Same as above.
43	40	Machare, A. et al.	1974	R	8.69-50.0	20	Same as above.

TABLE 8. EXPERIMENTAL DATA ON THE REFLECTIVITY OF LITHIUM FLUORIDE

[Wavelength, λ, μm; Temperature, T, K; Reflectivity, ρ]

λ	ρ
DATA SET 1	
T = 7.5	
12.50	0.11
13.33	0.13
13.33	0.14
13.71	0.06
13.91	0.09
14.08	0.13
14.28	0.19
14.51	0.28
14.64	0.43
14.79	0.61
15.02	0.71
15.35	0.77
15.62	0.79
15.34	0.81
16.12	0.81
16.35	0.82
16.63	0.83
16.92	0.82
17.24	0.82
17.51	0.81
17.79	0.81
18.14	0.80
18.48	0.79
18.83	0.78
19.56	0.67
19.92	0.65
20.32	0.49
20.74	0.90
21.18	0.92
21.64	0.93
22.22	0.94
22.57	0.95
23.14	0.95
23.54	0.96
24.27	0.97
24.47	0.97
25.51	0.97
26.24	0.98
26.95	0.98

λ	ρ
DATA SET 1(CONT.)	
27.62	0.98
28.46	0.97
29.23	0.96
30.12	0.88
31.05	0.80
32.05	0.69
33.22	0.60
34.36	0.52
35.58	0.47
36.96	0.43
38.31	0.40
39.08	0.38
DATA SET 2	
T = 85.0	
12.50	0.12
13.31	0.13
13.49	0.13
13.90	0.14
13.88	0.13
14.06	0.12
14.26	0.17
14.47	0.23
14.79	0.52
15.03	0.67
15.36	0.73
15.64	0.76
15.84	0.78
16.12	0.81
16.39	0.81
16.60	0.82
16.94	0.81
17.24	0.81
17.54	0.80
17.85	0.80
18.18	0.80
18.51	0.79
18.86	0.77
19.23	0.75

λ	ρ
DATA SET 2(CONT.)	
19.64	0.76
20.00	0.80
20.40	0.83
20.83	0.86
21.27	0.88
21.73	0.90
22.22	0.91
22.72	0.92
23.25	0.93
23.85	0.94
24.50	0.94
25.06	0.95
25.70	0.95
26.38	0.95
27.10	0.95
27.85	0.95
28.65	0.95
29.58	0.93
30.48	0.90
31.44	0.82
32.36	0.72
33.55	0.61
34.60	0.53
35.97	0.47
37.31	0.44
38.61	0.41
40.32	0.38
42.01	0.36
43.85	0.34
DATA SET 3	
T = 295.0	
12.82	0.01
13.33	0.02
13.53	0.03
13.71	0.04
13.88	0.07
14.08	0.12
14.31	0.17

λ	ρ
DATA SET 3(CONT.)	
14.49	0.22
14.72	0.31
14.94	0.44
15.15	0.55
15.38	0.65
15.60	0.69
15.84	0.72
16.10	0.74
16.36	0.76
16.66	0.76
16.94	0.76
17.21	0.76
17.51	0.76
17.82	0.75
18.14	0.74
18.48	0.73
18.83	0.72
19.15	0.70
19.56	0.69
19.96	0.69
20.32	0.70
20.79	0.75
21.14	0.78
21.69	0.80
22.12	0.83
22.67	0.86
23.14	0.87
23.69	0.87
24.27	0.88
24.87	0.89
25.57	0.90
26.17	0.90
26.88	0.90
27.62	0.90
28.40	0.89
29.23	0.89
30.12	0.89
31.05	0.85
32.05	0.81
33.22	0.71

λ	ρ
DATA SET 3(CONT.)	
34.24	0.57
35.58	0.52
36.96	0.47
38.46	0.43
39.84	0.40
41.49	0.37
43.29	0.35
45.24	0.33
DATA SET 4	
T = 420.0	
14.26	0.16
14.49	0.21
14.70	0.30
14.92	0.41
15.12	0.51
15.36	0.59
15.60	0.64
15.84	0.68
16.10	0.70
16.39	0.71
16.66	0.72
16.94	0.72
17.24	0.72
17.54	0.71
17.85	0.71
18.18	0.70
18.55	0.69
18.96	0.68
19.23	0.67
19.60	0.65
20.00	0.65
20.40	0.66
20.83	0.68
21.27	0.71
21.69	0.74
22.22	0.76
22.72	0.79
23.31	0.80

λ	ρ
DATA SET 4(CONT.)	
23.80	0.82
24.44	0.84
25.00	0.84
25.71	0.85
26.45	0.85
27.10	0.84
27.93	0.84
28.65	0.83
29.49	0.83
30.48	0.82
31.34	0.81
32.46	0.77
33.55	0.69
34.72	0.60
35.97	0.52
37.31	0.48
38.61	0.44
40.32	0.40
42.01	0.37
44.05	0.35
45.87	0.34
DATA SET 5	
T = 665.0	
13.89	0.05
14.08	0.08
14.28	0.12
14.49	0.14
14.71	0.19
14.92	0.27
15.15	0.36
15.38	0.46
15.62	0.52
15.84	0.57
16.10	0.60
16.36	0.63
16.63	0.64
16.94	0.65
17.24	0.66

TABLE 8. EXPERIMENTAL DATA ON THE REFLECTIVITY OF LITHIUM FLUORIDE (continued)

λ	ρ
DATA SET 5(CONT.)	
17.54	0.65
17.82	0.65
18.19	0.66
18.51	0.65
18.83	0.65
19.19	0.64
19.55	0.63
19.95	0.63
20.35	0.63
20.79	0.63
21.23	0.64
21.69	0.64
22.12	0.67
22.67	0.69
23.24	0.71
23.63	0.73
24.33	0.75
24.87	0.76
25.57	0.77
26.24	0.77
26.95	0.77
27.62	0.77
28.46	0.77
29.23	0.77
30.12	0.75
31.05	0.75
32.15	0.73
33.22	0.71
34.24	0.65
35.59	0.59
36.92	0.53
38.31	0.48
39.84	0.44
41.49	0.41
43.29	0.38
45.24	0.36
DATA SET 6	
T = 840.0	
13.49	0.02
13.90	0.04
14.30	0.06
14.28	0.08
14.47	0.10
14.70	0.12
14.95	0.16
15.15	0.23
15.38	0.29
15.62	0.36
15.87	0.41
16.12	0.47
16.39	0.51
16.66	0.53
16.94	0.55
17.27	0.56
17.57	0.58
17.85	0.59
18.18	0.61
18.55	0.59
18.93	0.59
19.26	0.59
19.60	0.60
20.04	0.59
20.44	0.59
20.87	0.60
21.27	0.60
21.73	0.66
22.27	0.61
22.77	0.61
23.31	0.62
23.53	0.63
24.53	0.64
25.12	0.66
25.73	0.67
26.45	0.68
27.17	0.68
27.93	0.68
28.73	0.68
DATA SET 6(CONT.)	
29.49	0.68
30.48	0.67
31.54	0.67
32.46	0.65
33.55	0.64
34.84	0.62
35.97	0.58
37.31	0.55
38.75	0.51
40.32	0.47
42.01	0.43
43.85	0.41
45.87	0.38
DATA SET 7	
T = 1660.0	
13.92	0.34
14.30	0.6
14.74	0.09
14.97	0.11
15.17	0.14
15.40	0.19
15.64	0.23
15.89	0.28
16.12	0.34
16.42	0.37
16.69	0.40
16.97	0.44
17.24	0.46
17.57	0.47
17.85	0.49
18.14	0.51
18.51	0.52
18.86	0.52
19.23	0.53
19.60	0.53
20.00	0.54
20.40	0.54
20.83	0.55
DATA SET 7(CONT.)	
21.23	0.55
21.73	0.55
22.17	0.56
22.72	0.56
23.25	0.57
23.75	0.57
24.33	0.57
24.87	0.58
25.57	0.58
26.31	0.58
26.95	0.59
27.70	0.59
28.49	0.60
29.32	0.61
30.21	0.61
31.15	0.60
32.25	0.60
33.22	0.59
34.36	0.58
35.58	0.56
36.90	0.54
38.46	0.52
39.84	0.50
41.32	0.48
43.29	0.45
45.24	0.42
DATA SET 8	
T = 283.0	
0.1861	0.020
0.1872	0.026
0.1885	0.020
0.0898	0.017
0.0906	0.017
0.0913	0.050
0.0918	0.088
0.0926	0.142
0.0936	0.181
0.0938	0.237
DATA SET 8(CONT.)	
0.0947	0.238
0.0949	0.320
0.0953	0.338
0.0958	0.349
0.0963	0.347
0.0968	0.352
0.0973	0.349
0.0977	0.344
0.0981	0.329
0.0984	0.312
0.0984	0.293
0.0989	0.259
0.0994	0.223
0.0998	0.202
0.1004	0.182
0.1009	0.167
0.1015	0.153
0.1023	0.137
0.1028	0.130
0.1035	0.125
0.1040	0.119
0.1050	0.124
0.1055	0.132
0.1064	0.139
0.1069	0.141
0.1073	0.137
0.1077	0.139
0.1088	0.134
0.1094	0.132
0.1109	0.127
0.1117	0.127
0.1127	0.122
0.1138	0.115
0.1147	0.117
0.1156	0.114
0.1165	0.108
0.1178	0.148
0.1195	0.102
0.1203	0.102
0.1214	0.096
DATA SET 8(CONT.)	
0.1227	0.099
0.1238	0.093
0.1258	0.089
0.1275	0.089
0.1287	0.085
0.1303	0.083
0.1320	0.083
0.1347	0.080
0.1374	0.079
0.1411	0.079
0.1440	0.077
0.1479	0.075
0.1524	0.075
0.1550	0.072
0.1585	0.071
0.1627	0.070
0.1677	0.068
0.1776	0.066
0.1866	0.063
DATA SET 9	
T = 283.0	
0.0870	0.017
0.0851	0.014
0.0836	0.006
0.0857	0.013
0.0899	0.021
0.0921	0.030
0.0911	0.079
0.0911	0.084
0.0915	0.114
0.0924	0.149
0.0926	0.160
0.0926	0.173
0.0930	0.193
0.0935	0.195
0.0935	0.224
0.0941	0.257
0.0945	0.275

TABLE 8. EXPERIMENTAL DATA ON THE REFLECTIVITY OF LITHIUM FLUORIDE (continued)

λ	ρ	λ	ρ	λ	ρ	λ	ρ	λ	ρ	λ	ρ
DATA SET 9(CONT.)		DATA SET 9(CONT.)		DATA SET 10(CONT.)		DATA SET 10(CONT.)		DATA SET 11(CONT.)		DATA SET 11(CONT.)	
0.0945	0.272	0.1249	0.049	12.50	0.0179	46.02	0.278	0.0045	0.052	0.0345	0.334
0.0952	0.278	0.1311	0.049	12.88	0.0270	48.19	0.265	0.0057	0.053	0.1011	0.287
0.0959	0.284	0.1316	0.050	13.18	0.0429	51.46	0.252	0.0068	0.046	0.1111	0.278
0.0951	0.281	0.1330	0.051	13.45	0.0619	55.33	0.252	0.0076	0.043	0.1211	0.269
0.0955	0.253	0.1342	0.054	13.74	0.0920			0.0083	0.045	0.1411	0.263
0.0972	0.252	0.1355	0.055	14.02	0.134	DATA SET 11		0.0091	0.054	0.1629	0.204
0.0974	0.235	0.1379	0.059	14.19	0.175	T = 300.0		0.0073	0.055	0.1732	0.189
0.0983	0.228	0.1388	0.061	14.32	0.237			0.0072	0.060	0.1045	0.175
0.0994	0.195	0.1402	0.061	14.75	0.478	0.0452	0.626	0.0726	0.064	0.1043	0.150
0.0998	0.170	0.1423	0.062	15.10	0.600	0.0458	0.635	0.0710	0.055		
0.0996	0.156	0.1422	0.061	15.41	0.706	0.0465	0.656	0.0718	0.059	DATA SET 12	
0.1003	0.129	0.1436	0.064	15.52	0.731	0.0469	0.665	0.0730	0.052	T = 77.0	
0.1015	0.121	0.1445	0.067	15.73	0.748	0.0472	0.682	0.0763	0.036		
0.1019	0.115	0.1462	0.067	15.99	0.763	0.0480	0.689	0.0771	0.035	13.49	0.013
0.1023	0.110	0.1477	0.071	16.33	0.773	0.0480	0.699	0.0771	0.035	13.96	0.007
0.1029	0.101	0.1488	0.073	16.63	0.778	0.0496	0.132	0.0786	0.037	14.94	0.230
0.1035	0.097	0.1513	0.074	17.37	0.779	0.0492	0.144	0.0730	0.039	15.45	0.532
0.1039	0.091	0.1529	0.078	18.23	0.763	0.0494	0.137	0.0814	0.033	15.97	0.316
0.1047	0.088	0.1530	0.078	19.67	0.710	0.0494	0.148	0.0824	0.093	16.97	0.362
0.1053	0.084	0.1540	0.081	19.99	0.711	0.0504	0.198	0.0822	0.096	18.00	0.342
0.1063	0.082	0.1551	0.081	20.27	0.719	0.0512	0.195	0.0830	0.105	18.96	0.319
0.1073	0.080	0.1575	0.083	20.65	0.746	0.0512	0.211	0.0835	0.113	20.00	0.791
0.1092	0.077	0.1593	0.083	21.28	0.803	0.0525	0.248	0.0845	0.104	20.99	0.871
0.1091	0.077	0.1606	0.081	21.77	0.828	0.0525	0.263	0.0854	0.110	22.00	0.904
0.1103	0.073	0.1607	0.079	22.54	0.852	0.0533	0.291	0.0862	0.096	22.96	0.951
0.1110	0.072	0.1646	0.079	23.38	0.835	0.0538	0.297	0.0873	0.103	23.97	0.933
0.1124	0.068	0.1666	0.076	24.26	0.901	0.0549	0.277	0.0882	0.092	24.96	0.920
0.1135	0.068	0.1694	0.076	25.35	0.912	0.0551	0.257	0.0890	0.093	26.00	0.928
0.1143	0.064	0.1710	0.072	26.85	0.912	0.0562	0.260	0.0893	0.079		
0.1154	0.064	0.1734	0.072	28.11	0.896	0.0575	0.136	0.0905	0.043	DATA SET 13	
0.1167	0.062	0.1771	0.069	29.12	0.873	0.0575	0.126	0.0911	0.045	T = 293.0	
0.1165	0.058	0.1810	0.067	30.42	0.831	0.0583	0.129	0.0919	0.079		
0.1194	0.058	0.1804	0.065	32.66	0.776	0.0584	0.112	0.0925	0.183	13.91	0.004
0.1208	0.056	0.1919	0.064	33.34	0.732	0.0605	0.053	0.0933	0.278	14.30	0.033
0.1222	0.055	0.1977	0.062	34.51	0.676	0.0605	0.068	0.0943	0.208	14.47	0.034
0.1234	0.056			37.75	0.467	0.0616	0.076	0.0943	0.274	14.95	0.205
0.1243	0.057	DATA SET 10		38.90	0.404	0.0627	0.071	0.0962	0.337	15.45	0.495
0.1248	0.055	T = 293.0		40.17	0.361	0.0638	0.065	0.0962	0.405	15.97	0.758
0.1265	0.054			42.07	0.321	0.0641	0.056	0.0977	0.429	16.46	0.836
0.1278	0.051	12.05	0.0110	44.05	0.295	0.0645	0.058	0.0984	0.422	16.99	0.820

TABLE 8. EXPERIMENTAL DATA ON THE REFLECTIVITY OF LITHIUM FLUORIDE (continued)

DATA SET 13(CONT.)

λ	ρ
17.44	0.833
17.97	0.818
18.47	0.806
18.96	0.785
19.47	0.769
19.97	0.754
20.45	0.747
21.98	0.784
21.45	0.822
21.96	0.842
22.45	0.839
22.93	0.832
23.44	0.874
24.44	0.875
24.95	0.880

DATA SET 14
T = 573.0

λ	ρ
14.00	0.027
14.51	0.058
14.95	0.160
15.46	0.469
15.97	0.603
16.45	0.731
16.96	0.765
17.48	0.736
17.97	0.772
18.50	0.772
18.93	0.766
19.46	0.740
19.98	0.719
20.46	0.717
20.96	0.712
21.44	0.746
21.95	0.730
22.45	0.781
22.94	0.814
23.44	0.815
23.94	0.815

DATA SET 14(CONT.)

λ	ρ
24.44	0.831
24.93	0.794
25.42	0.794

DATA SET 15
T = 300.0

λ	ρ
14.5	0.24
15.0	0.53
15.5	0.60
17.0	0.70
18.0	0.66
19.0	0.65
20.0	0.70
22.0	0.80
25.0	0.83
28.0	0.81
31.0	0.76
33.0	0.66
34.0	0.58
35.0	0.50
36.0	0.48

DATA SET 16
T = 300.0

λ	ρ
14.5	0.10
15.0	0.50
16.0	0.60
18.0	0.62
19.0	0.66
20.0	0.70
25.0	0.82
28.0	0.80
30.0	0.76
32.0	0.64
34.0	0.48
36.0	0.34

DATA SET 17
T = 298.0

λ	ρ
0.1347	0.05
0.1438	0.05
0.1570	0.04
0.1640	0.02

DATA SET 18
T = 298.0

λ	ρ
8.0	0.016
12.7	0.074
14.1	0.344
14.5	0.484
14.9	0.499
15.7	0.678
16.1	0.710
17.0	0.718
18.0	0.711
19.0	0.686
20.0	0.671
20.6	0.741
22.0	0.771
22.9	0.842
24.5	0.827
25.8	0.806
26.8	0.871
27.7	0.874
29.4	0.858
31.0	0.815
32.9	0.751
33.5	0.737
33.9	0.644
34.9	0.523
36.9	0.474

DATA SET 19
T = 298.0

λ	ρ
13.5	0.068
14.5	0.327

DATA SET 19(CONT.)

λ	ρ
15.4	0.436
16.0	0.477
17.1	0.549
18.1	0.549
19.0	0.508
20.0	0.506
21.0	0.528
22.0	0.562
23.9	0.608
25.0	0.610
26.1	0.629
27.1	0.630
28.1	0.621
29.0	0.616
30.0	0.607
31.9	0.596
32.9	0.572
32.9	0.536
33.9	0.491
36.6	0.398
36.9	0.359

DATA SET 20
T = 298.0

λ	ρ
10.6	0.068
12.0	0.019
12.7	0.033
13.1	0.064
13.6	0.113
13.9	0.191
14.4	0.369
15.0	0.663
15.4	0.719
16.0	0.773
16.0	0.792
17.1	0.795
17.9	0.787
18.6	0.766
19.3	0.733

DATA SET 20(CONT.)

λ	ρ
13.9	0.725
20.5	0.743
21.3	0.794
22.0	0.847
22.9	0.880
23.8	0.898
25.0	0.933
27.4	0.931
29.5	0.884
30.7	0.864
31.8	0.804
32.4	0.750
33.1	0.687
34.5	0.591

DATA SET 21
T = 298.0

λ	ρ
2.00	0.058
4.90	0.048
13.7	0.054
14.1	0.139
14.1	0.487
15.4	0.625
16.8	0.642
18.4	0.593
21.3	0.712
23.8	0.799
26.8	0.841
29.9	0.802
33.3	0.594
35.1	0.435
39.5	0.373
42.0	0.292
43.8	0.249
45.6	0.242
46.3	0.181
47.7	0.133
53.0	0.152

DATA SET 22
T = 298.0

λ	ρ
0.0306	0.002
0.0372	0.013
0.0458	0.066
0.0561	0.101
0.0544	0.140
0.0592	0.051
0.0620	0.057
0.0711	0.048
0.0747	0.043
0.0776	0.059
0.0832	0.080
0.0914	0.069
0.0943	0.149
0.0973	0.224
0.100	0.100
0.103	0.100

DATA SET 23
T = 298.0

λ	ρ
0.0366	0.078
0.0370	0.100
0.0447	0.224
0.0545	0.312
0.0549	0.252
0.0579	0.201
0.0620	0.149
0.0711	0.124
0.0762	0.136
0.0839	0.162
0.0909	0.141
0.0936	0.171
0.0946	0.210
0.0906	0.274
0.103	0.155

TABLE 8. EXPERIMENTAL DATA ON THE REFLECTIVITY OF LITHIUM FLUORIDE (continued)

DATA SET 24
T = 298.0

λ	ρ
0.0972	0.013
0.0947	0.018
0.0921	0.036
0.0537	0.048
0.0554	0.07
0.0509	0.01
0.0504	0.07
0.0511	0.17
0.0525	0.12
0.0[illegible]	0.16
0.0748	0.11
0.0749	0.16
0.0324	0.4
0.0441	0.24
0.0[illegible]	0.62
0.0[illegible]	0.19
0.0[illegible]	0.23
0.0[illegible]	0.02
0.0962	0.183
0.0971	0.034
0.0[illegible]	0.179

DATA SET 25
T = 298.0

λ	ρ
14.8	0.335
15.0	0.300
15.7	0.335
16.0	0.337
16.7	0.360
18.1	0.300
19.9	0.383
20.4	0.40
20.8	0.427
21.3	0.45
22.1	0.494
22.9	0.522
23.3	0.559
24.5	0.583

DATA SET 25(CONT.)

λ	ρ
25.0	0.618
26.5	0.636
27.6	0.647
29.1	0.647
30.0	0.632
31.0	0.612
32.4	0.590
33.1	0.57[illegible]
33.9	0.543
34.0	0.513
35.2	0.492
36.0	0.454

DATA SET 26
T = 298.0

λ	ρ
14.4	0.392
14.7	0.417
15.2	0.442
15.7	0.458
16.3	0.482
17.3	0.492
18.2	0.492
19.0	0.434
19.6	0.473
20.1	0.473
20.6	0.431
21.2	0.523
22.1	0.556
23.3	0.593
24.3	0.621
25.0	0.669
26.9	0.721
28.0	0.756
29.2	0.772
31.4	0.772
32.5	0.752
32.5	0.724
33.0	0.679
33.0	0.632

DATA SET 26(CONT

λ	ρ
34.4	0.581
35.2	0.536
35.9	0.519

DATA SET 27
T = 298.0

λ	ρ
14.5	0.420
14.8	0.501
15.0	0.543
15.4	0.587
15.9	0.628
16.4	0.653

DATA SET 28(CONT.)

λ	ρ
17.1	0.658
18.2	0.660
19.3	0.647
20.1	0.627
20.3	0.620
21.5	0.675
22.0	0.714
23.4	0.744
24.3	0.777
25.2	0.796
26.1	0.815
27.6	0.829
28.1	0.837

DATA SET 29
T = 298.0

λ	ρ
16.9	0.678
18.5	0.691
18.5	0.691
19.0	0.679
19.6	0.640
20.3	0.645
22.2	0.721
23.1	0.761
24.4	0.794
25.0	0.827
26.0	0.843
27.9	0.858
29.2	0.853
30.2	0.841
31.9	0.823
32.5	0.806
32.4	0.758
33.3	0.704
34.3	0.653
35.0	0.623
36.6	0.592

DATA SET 30
T = 298.0

λ	ρ
13.7	0.614
14.8	0.625
15.8	0.742
17.7	0.757
18.7	0.697
21.8	0.836
23.5	0.873
25.8	0.895
26.0	0.885
28.7	0.858
29.0	0.781
33.9	0.591
35.7	0.549

DATA SET 31
T = 298.0

λ	ρ
0.0413	0.014
0.0423	0.026
0.0435	0.010
0.0444	0.021
0.0461	0.021
0.0462	0.050
0.0470	0.057
0.0490	0.194
0.0514	0.221
0.0521	0.277
0.0549	0.340
0.0832	0.302
0.0930	0.344
0.0545	0.282
0.0993	0.197
0.0909	0.143
0.0970	0.137
0.0049	0.044
0.0659	0.04[illegible]
0.0740	0.043
0.0692	0.05[illegible]
0.0740	0.052

DATA SET 31(CONT.)

λ	ρ
0.0729	0.042
0.0760	0.026
0.0775	0.023
0.0[illegible]	0.072
0.0815	0.089
0.0820	0.090
0.0845	0.06
0.0[illegible]	0.04
0.0[illegible]	0.03
0.0[illegible]	0.033
0.0953	0.022
0.0934	0.002
0.1000	0.270
0.1020	0.095
0.1042	0.027

DATA SET 32
T = 300.0

λ	ρ
2.54	0.084
2.57	0.092
2.59	0.093
2.67	0.093
2.63	0.066
2.70	0.063
2.82	0.06
2.84	0.088
2.95	0.098
2.97	0.066
3.05	0.06
3.07	0.095
3.0[illegible]	0.06
3.12	0.099
3.16	0.055
3.17	0.06
3.35	0.055
3.42	0.09
3.[illegible]	0.09
3.24	0.081
3.44	0.337

TABLE 9. EXPERIMENTAL DATA ON THE DEHYDRATION OF LITHIUM BORATE (continued)

DATA SET 32(CONT.)

X	C
5.06	0.52
5.82	0.56
6.00	0.63
6.03	0.63
6.24	0.64
6.99	0.69
7.22	0.72
7.83	0.76
8.32	0.79
10.02	0.87
12.59	0.89
13.27	0.96
13.40	0.97
13.79	0.73
13.96	0.80
14.00	0.87
14.25	0.90
14.47	0.92
14.72	0.89
14.94	0.92
15.25	0.94
15.40	0.777
15.77	0.795
15.77	0.819
16.25	0.833
16.59	0.845
17.32	0.832
18.72	0.834
19.23	0.779
19.72	0.791
20.00	0.792
20.40	0.829
20.00	0.833
21.09	0.840
22.53	0.835
23.00	0.837
23.07	0.836
23.64	0.842
25.22	0.832
25.93	0.844

DATA SET 32(CONT.)

X	C
25.97	0.834
29.32	0.865
30.21	0.853
31.53	0.825
31.53	0.830
31.25	0.846
31.74	0.817
32.35	0.817
33.33	0.824
34.22	0.759
35.00	0.7[illegible]
35.38	0.877

DATA SET 33
T = 335.0

X	C
16.42	0.715
16.33	0.709
16.92	0.813
17.24	0.829
17.79	0.826
18.34	0.739
18.48	0.797
20.24	0.822
20.43	0.852
23.20	0.844
25.04	0.807
28.12	0.845
29.07	0.825
32.79	0.797
34.72	0.807

DATA SET 34
T = 220.0

X	C
16.50	0.752
16.30	0.765
17.30	0.769
17.95	0.780
18.40	0.776

DATA SET 34(CONT.)

X	C
19.15	0.760
19.83	0.770
20.01	0.793
23.00	0.859
23.47	0.900
24.67	0.923
25.57	0.923
26.73	0.929
27.02	0.932
29.87	0.857

DATA SET 35
T = 330.0

X	C
11.13	0.004
12.01	0.007
12.19	0.007
12.92	0.015
13.64	0.059
13.53	0.091
14.13	0.132
15.36	0.238
15.57	0.394
15.72	0.507
15.97	0.659
16.33	0.720
16.81	0.751
17.03	0.766
17.61	0.771
17.93	0.781
18.51	0.743
19.15	0.735
19.34	0.723
19.84	0.715
20.12	0.716
20.44	0.725
21.7[illegible]	0.734
22.92	0.793
21.32	0.776
21.88	0.622

DATA SET 35(CONT.)

X	C
23.67	0.560
23.00	0.669
24.33	0.826
25.00	0.893
25.97	0.890
26.38	0.805
27.35	0.375
28.57	0.361
29.55	0.356
30.48	0.311
30.25	0.794
31.94	0.765
32.06	0.727
34.02	0.554
35.33	0.566
35.36	0.440
36.63	0.427
36.70	0.396
37.31	0.375
37.59	0.329
38.31	0.317
38.75	0.300
[illegible]	0.289
42.00	0.265
47.16	0.248
50.90	0.241
54.64	0.244
57.80	0.236
64.16	0.236

DATA SET 36
T = 355.0

X	C
16.44	0.724
16.77	0.742
17.39	0.748
17.88	0.743
18.41	0.725
19.31	0.695
19.42	0.689

DATA SET 36(CONT.)

X	C
19.94	0.650
20.66	0.693
21.30	0.707
22.22	0.745
23.47	0.655
24.27	0.699
25.57	0.480
27.16	0.653
29.24	0.328

DATA SET 37
T = 360.0

X	C
2.06	0.036
2.72	0.030
3.93	0.054
4.76	0.055
5.40	0.042
6.13	0.030
6.81	0.029
7.27	0.024
7.99	0.024
8.25	0.030
8.77	0.009
9.21	0.007
9.67	0.031
11.13	0.008
11.61	0.010
11.29	0.024
11.87	0.033
12.12	0.035
12.30	0.039
12.75	0.036
13.36	0.043
13.19	0.050
13.47	0.060
14.02	0.249

DATA SET 38
T = 293.0

X	C
14.00	0.77
14.63	0.765
14.8	0.764
15.4	0.773
15.9	0.752
17.00	0.749
17.9	0.703
18.3	0.741
19.3	0.720
20.5	0.706
21.5	0.524
23.00	0.500
23.9	0.465
24.9	0.317
25.00	0.430
27.00	0.424
27.9	0.425
28.00	0.9[illegible]
29.9	0.474
30.9	0.443
32.9	0.734
34.00	0.059
34.9	0.050
35.00	0.054
36.1	0.076
39.0	0.033

DATA SET 39
T = 293.0

X	C
14.72	0.74
15.25	0.473
15.35	0.553
15.02	0.05
15.44	0.054
16.33	0.041
16.39	0.695
17.07	0.697
18.22	0.632

TABLE 8. EXPERIMENTAL DATA ON THE REFLECTIVITY OF LITHIUM FLUORIDE (continued)

λ	ρ
DATA SET 39(CONT.)	
18.58	0.665
19.23	0.643
19.56	0.627
19.76	0.615
20.24	0.630
21.14	0.738
22.02	0.75[illegible]
23.2[illegible]	0.739
24.02	0.722
25.97	0.747
27.17	0.751
28.69	0.753
29.75	0.751
31.95	0.717
31.84	0.773
32.75	0.694
33.75	0.[illegible]7
34.[illegible]	0.655
35.84	0.5[illegible]
37.03	0.453
38.75	0.415
40.41	0.389
43.66	0.374
45.45	0.368
47.61	0.353
DATA SET 40	
T = 293.0	
0.0[illegible]3	0.2103
0.0904	0.2908
0.0971	0.3.94
0.0950	0.2943
0.0931	0.2460
0.1002	0.1315
0.1016	0.1357
0.1025	0.1229
0.1038	0.1065
0.1048	0.1115
0.1061	0.0953

λ	ρ
DATA SET 40(CONT.)	
0.1065	0.0840
0.1072	0.0782
0.1079	0.0782
0.1084	0.0736
0.1095	0.0723
0.1108	0.0713
0.1117	0.0710
0.1125	0.0[illegible]3
0.1140	0.0624
0.1162	0.0605
0.1170	0.0578
0.1192	0.0578
0.1216	0.0557
0.1232	0.0546
0.1246	0.0526
0.1250	0.0508
0.1261	0.0509
0.1334	0.0482
0.1364	0.0465
0.1402	0.0485
0.1426	0.0447
0.1447	0.0445
0.1506	0.0426
0.1527	0.0426
0.1530	0.0401
0.1540	0.0414
0.1544	0.0414
0.1550	0.0395
DATA SET 41	
T = 300.0	
8.69	0.006
8.77	0.006
8.84	0.006
8.92	0.005
9.00	0.005
9.09	0.005
9.17	0.004
9.25	0.004

λ	ρ
DATA SET 41(CONT.)	
9.34	0.034
9.43	0.034
9.52	0.003
9.61	0.003
9.71	0.003
9.80	0.002
9.90	0.002
10.00	0.002
10.10	0.002
10.20	0.001
10.30	0.001
11.76	0.001
11.93	0.002
12.04	0.003
12.19	0.004
12.34	0.005
12.50	0.007
12.65	0.010
12.82	0.013
12.98	0.017
13.15	0.021
13.33	0.027
13.51	0.035
13.69	0.044
13.88	0.065
14.08	0.091
14.28	0.126
14.49	0.182
14.70	0.290
14.92	0.446
15.15	0.600
15.38	0.684
15.62	0.718
15.87	0.741
16.12	0.758
16.39	0.768
16.66	0.772
16.94	0.772
17.24	0.768
17.54	0.761

λ	ρ
DATA SET 41(CONT.)	
17.85	0.752
18.18	0.742
18.51	0.732
18.86	0.721
19.23	0.711
19.60	0.700
20.00	0.688
21.41	0.765
21.83	0.740
21.87	0.776
21.93	0.798
22.22	0.825
22.72	0.851
23.25	0.870
23.80	0.885
24.39	0.894
25.00	0.900
25.64	0.912
26.31	0.912
27.02	0.902
27.77	0.902
28.57	0.902
29.41	0.902
30.30	0.896
31.25	0.882
32.25	0.835
33.33	0.732
34.48	0.624
35.71	0.544
37.03	0.492
38.46	0.477
40.00	0.426
41.66	0.414
43.47	0.384
45.45	0.368
47.61	0.355
50.00	0.342

λ	ρ
DATA SET 42	
T = 600.0	
8.69	0.000
8.77	0.000
8.84	0.000
8.92	0.005
9.00	0.005
9.09	0.005
9.17	0.004
9.25	0.004
9.34	0.004
9.43	0.004
9.52	0.003
9.61	0.003
9.71	0.003
9.80	0.002
9.90	0.002
10.00	0.002
10.10	0.001
10.20	0.001
11.9[illegible]	0.001
11.76	0.001
11.9[illegible]	0.002
12.04	0.003
12.19	0.004
12.34	0.005
12.50	0.007
12.65	0.010
12.82	0.013
12.98	0.017
13.15	0.021
13.33	0.027
13.51	0.035
13.69	0.044
13.88	0.065
14.08	0.091
14.28	0.126
14.49	0.182
14.70	0.290
14.92	0.446
15.15	0.600
15.38	0.684
15.62	0.718
15.87	0.741
16.12	0.758
16.39	0.768
16.66	0.772
16.94	0.772
17.24	0.768
17.54	0.761

λ	ρ
DATA SET 42(CONT.)	
15.39	0.758
15.62	0.763
15.87	0.759
16.12	0.812
16.39	0.823
16.66	0.824
16.94	0.823
17.24	0.818
17.54	0.[illegible]
17.85	0.796
18.18	788
18.51	0.781
18.86	0.772
19.23	0.762
19.60	0.76[illegible]
20.00	0.7[illegible]
20.41	0.7[illegible]
20.83	0.739
21.27	0.737
21.73	0.737
22.22	0.734
22.72	0.7[illegible]
23.25	0.736
23.80	0.740
24.39	0.749
25.00	0.754
25.64	0.756
26.31	0.756
27.02	0.756
27.77	0.754
28.57	0.752
29.41	0.745
30.30	0.726
31.25	0.732
32.25	0.731
33.33	0.730
34.48	0.728
35.71	0.7[illegible]
37.03	0.4[illegible]
38.46	0.4[illegible]

TABLE 8. EXPERIMENTAL DATA ON THE REFLECTIVITY OF LITHIUM FLUORIDE (continued)

λ	ρ	λ	ρ	λ	ρ
DATA SET 42 (CONT.)		DATA SET 43 (CONT.)		DATA SET 43 (CONT.)	
40.00	0.378	13.51	0.642	29.41	0.966
41.66	0.352	13.69	0.655	30.30	0.942
43.47	0.352	13.88	0.675	31.25	0.898
45.45	0.342	14.08	0.696	32.25	0.796
47.61	0.332	14.23	0.137	33.33	0.615
50.00	0.322	14.49	0.209	34.48	0.534
		14.70	0.234	35.71	0.475
DATA SET 43		14.92	0.524	37.03	0.426
T = 23.0		15.15	0.717	38.46	0.398
		15.38	0.766	40.00	0.374
8.69	0.036	15.62	0.791	41.66	0.357
8.77	0.036	15.87	0.806	43.47	0.343
8.84	0.035	16.12	0.822	45.45	0.335
8.92	0.035	16.39	0.833	47.61	0.326
9.00	0.035	16.66	0.836	50.00	0.326
9.09	0.035	16.94	0.832		
9.17	0.034	17.24	0.825		
9.25	0.034	17.54	0.817		
9.34	0.034	17.85	0.808		
9.43	0.033	18.18	0.801		
9.52	0.033	18.51	0.793		
9.61	0.033	18.86	0.784		
9.70	0.033	19.23	0.774		
9.80	0.032	19.60	0.766		
9.90	0.032	20.00	0.818		
10.00	0.032	20.41	0.858		
10.10	0.031	20.83	0.882		
10.20	0.031	21.27	0.902		
10.30	0.031	21.73	0.919		
10.75	0.031	22.22	0.933		
11.90	0.032	22.72	0.945		
12.00	0.033	23.25	0.955		
12.19	0.034	23.80	0.963		
12.34	0.035	24.39	0.969		
12.50	0.037	25.00	0.972		
12.65	0.040	25.64	0.975		
12.76	0.044	26.31	0.976		
12.93	0.049	27.02	0.977		
13.15	0.124	27.77	0.977		
13.33	0.232	28.57	0.975		



Figure 8. Transmission of Lithium Fluoride

TABLE 9. SUMMARY OF MEASUREMENTS ON THE TRANSMISSION OF LITHIUM FLUORIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	34	Kato, R.	1961	T	1.8-11.0	283	High purity; single crystal; freshly cleaved specimens with thicknesses unspecified; data extracted from a curve.
2	34	Kato, R.	1961	T	1.9-11.0	283	Similar to above except crystal grown in air in order to see the effects of hydrolysis on the transmittances; transmission spectrum shows an absorption near 2.8 μm due to the vibration of O-H bond.
3	41	Klier, M.	1958	T	4.5-8.0	77	Crystal; thin specimen of 6153 μm thick; transmittance spectrum measured; data extracted from a figure.
4	41	Klier, M.	1958	T	4.5-8.0	195	Same as above.
5	41	Klier, M.	1958	T	4.5-8.0	293	Same as above.
6	41	Klier, M.	1958	T	4.5-8.0	573	Same as above.
7	41	Klier, M.	1958	T	6.0-9.50	77	Same as above except for specimen of 2021 μm thick.
8	41	Klier, M.	1958	T	5.5-9.32	195	Same as above.
9	41	Klier, M.	1958	T	5.5-9.12	293	Same as above.
10	41	Klier, M.	1958	T	5.5-58.1	573	Same as above.
11	41	Klier, M.	1958	T	6.0-10.3	77	Same as above except for specimen of 726 μm thick.
12	41	Klier, M.	1958	T	6.6-10.3	195	Same as above.
13	41	Klier, M.	1958	T	6.0-10.3	293	Same as above.
14	41	Klier, M.	1958	T	6.0-9.7	573	Same as above.
15	41	Klier, M.	1958	T	75-14.2	77	Same as above except for specimen of 145 μm thick.
16	41	Klier, M.	1958	T	7.5-13.2	195	Same as above.
17	41	Klier, M.	1958	T	7.5-12.7	293	Same as above.
18	41	Klier, M.	1958	T	7.4-12.2	573	Same as above.
19	41	Klier, M.	1958	T	10.9-15.3	77	Same as above except for specimen of 60.1 μm thick.
20	41	Klier, M.	1958	T	10.9-14.5	195	Same as above.
21	41	Klier, M.	1958	T	10.9-13.8	293	Same as above.
22	54	McCarthy, D.E.	1963	T	2-50	298	Synthetic crystal; 5 mm thick; polished to flatness of seven fringes on both sides; data extracted from a curve.

TABLE 9. SUMMARY OF MEASUREMENTS ON THE TRANSMISSION OF LITHIUM FLUORIDE (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
23	62	Davis, R.J.	1966	T	0.104-0.205	298	Single crystal; freshly cleaved; 1.3 mm thick; measured in vacuum; data extracted from a curve.
24	62	Davis, R.J.	1966	T	0.104-0.205	298	The above specimen measured after 20 months storage in a chemical desiccator.
25	62	Davis, R.J.	1966	T	0.104-0.205	298	The above specimen measured after 2 minutes of ultrasonic cleaning in absolute ethyl alcohol.
26	62	Davis, R.J.	1966	T	0.104-0.205	298	Polished; 2.0 mm thick; measured in vacuum; data extracted from curve.
27	62	Davis, R.J.	1966	T	0.104-0.205	298	The above specimen measured after 11 months storage in uncontrolled environment (humidity never exceeding 95 K).
28	62	Davis, R.J.	1966	T	0.104-0.205	298	The above specimen measured after 2 minutes of ultrasonic cleaning in absolute ethyl alcohol.
29	63	Jones, D.A., Jones, R.V., and Stevenson, R.W.	1952	T	5.00-7.19	298	Single crystal; reflection losses eliminated and transmission adjusted to standard thickness of 1 cm; data extracted from a smooth curve.
30	64	Laufer, A.H., Pirog, I.A., and Moneby, J.R.	1965	T	0.104-0.145	299	Single crystal; obtained from Harshaw Chemical Co.; freshly cleaved specimen; 1.5 mm thick; stored and measured in vacuum; data extracted from a curve.
31	64	Laufer, A.H. et al.	1965	T	0.105-0.145	336	Above specimen and conditions.
32	64	Laufer, A.H. et al.	1965	T	0.106-0.119	374	Above specimen and conditions.
33	64	Laufer, A.H. et al.	1965	T	0.107-0.109	407	Above specimen and conditions.
34	65	Heath, D.F. and Sacher, P.A.	1966	T	0.105-0.300	298	Synthetic crystal; obtained from Harshaw Chemical Co.; optically polished specimen of 2.09 mm thick; measured in vacuum; data extracted from a curve.
35	66	McCubbin, T.K. and Sinton, W.M.	1950	T	109-486	298	Specimen of 1 mm thick; data extracted from a curve.
36	67	Bolot, G.	1965	T	0.105-0.350	298	Pure LiF, 0.82 mm thick; data extracted from a curve.
37	68	Linsteadt, G.	1964	T	1.0-10.5	50	Single crystal; specimens of 1.02 mm thick and 1.27 cm in diameter; data extracted from a curve.
38	68	Linsteadt, G.	1964	T	1.0-10.5	85	Similar to above.
39	68	Linsteadt, G.	1964	T	1.0-10.5	300	Similar to above.
40	37	Toriki, T. and Miyata, T.	1969	T	0.104-0.193	298	Single crystal; obtained from Harshaw Chemical Co.; freshly cleaved specimen of 0.221 cm thick; measurements made in a vacuum; data extracted from a curve.

TABLE 9. SUMMARY OF MEASUREMENTS ON THE TRANSMISSION OF LITHIUM FLUORIDE (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
41	37	Tomiki, T. and Miyata, T.	1969	T	0.104-0.210	298	Above conditions except for specimen of 0.200 cm thick.
42	39	Mead, D.	1974	T	43.8-438.6	6.2	Single crystal from BHD Ltd.; hand polished specimen of 1.2 mm thick; data extracted from a curve.
43	39	Mead, D.	1974	T	76.1-448.5	99.7	Above specimen and conditions.
44	39	Mead, D.	1974	T	133.5-535.0	290	Above specimen and conditions.

TABLE 10. EXPERIMENTAL DATA ON THE TRANSMISSION OF LITHIUM FLUORIDE

[Wavelength, λ, μm; Temperature, T, K; Transmission, τ]

λ	τ
DATA SET 1	
T = 283.0	
1.88	0.899
2.19	0.929
2.58	0.922
3.02	0.934
3.67	0.943
4.33	0.951
5.13	0.951
5.66	0.937
6.05	0.921
6.71	0.930
7.07	0.852
7.43	0.829
7.71	0.733
7.82	0.696
8.04	0.631
8.28	0.598
8.56	0.55[illegible]
8.81	0.513
9.01	0.473
9.23	0.407
9.56	0.314
9.73	0.254
10.01	0.171
10.17	0.128
10.27	0.104
10.49	0.090
10.81	0.075
10.87	0.057
DATA SET 2	
T = 283.0	
1.92	0.941
2.07	0.945
2.53	0.951
2.64	0.920
2.67	0.795
2.73	0.691
2.76	0.675
DATA SET 2(CONT.)	
2.83	0.689
2.86	0.826
2.89	0.847
3.25	0.864
4.03	0.874
4.43	0.874
4.83	0.857
5.02	0.872
5.38	0.871
5.72	0.848
6.03	0.846
6.32	0.735
6.52	0.695
6.78	0.658
6.91	0.609
7.07	0.554
7.26	0.474
7.42	0.304
7.57	0.236
7.74	0.228
7.93	0.182
8.03	0.141
8.24	0.106
8.43	0.075
8.91	0.060
9.43	0.044
10.07	0.036
10.73	0.036
DATA SET 3	
T = 77.0	
4.51	0.961
4.74	0.961
4.93	0.961
5.25	0.958
5.52	0.949
5.75	0.936
6.02	0.914
6.25	0.869
DATA SET 3(CONT.)	
6.34	0.840
6.45	0.803
6.59	0.748
6.73	0.723
6.86	0.677
6.98	0.624
7.10	0.572
7.22	0.516
7.35	0.467
7.47	0.417
7.60	0.356
7.72	0.231
7.84	0.215
8.00	0.171
DATA SET 4	
T = 195.0	
5.50	0.937
5.75	0.911
5.98	0.882
6.19	0.836
6.33	0.799
6.45	0.754
6.58	0.713
6.70	0.671
6.83	0.616
6.96	0.555
7.09	0.496
7.20	0.443
7.32	0.389
7.46	0.326
7.56	0.272
7.70	0.218
7.84	0.169
DATA SET 5	
T = 233.0	
4.51	0.949
DATA SET 5(CONT.)	
4.74	0.943
4.99	0.937
5.25	0.926
5.49	0.917
5.72	0.886
5.97	0.847
6.24	0.769
6.45	0.605
6.59	0.612
6.72	0.560
6.85	0.494
6.99	0.414
7.12	0.352
7.21	0.296
7.32	0.250
7.44	0.203
7.57	0.150
7.74	0.118
DATA SET 6	
T = 573.0	
4.51	0.925
4.74	0.915
4.99	0.911
5.25	0.872
5.53	0.826
5.78	0.743
5.98	0.641
6.24	0.547
6.34	0.432
6.44	0.377
6.58	0.313
6.72	0.265
6.84	0.199
6.98	0.153
7.11	0.111
7.19	0.076
DATA SET 7	
T = 77.0	
6.03	0.945
6.26	0.926
6.45	0.895
6.74	0.852
6.98	0.814
7.07	0.790
7.22	0.775
7.34	0.750
7.47	0.717
7.60	0.680
7.69	0.620
7.83	0.547
7.97	0.499
8.07	0.450
8.17	0.412
8.32	0.393
8.45	0.371
8.56	0.355
8.70	0.341
8.81	0.330
8.95	0.322
9.09	0.319
9.20	0.320
9.32	0.275
9.47	0.237
DATA SET 8	
T = 195.0	
6.03	0.920
6.28	0.895
6.57	0.854
6.83	0.801
7.07	0.739
7.32	0.677
7.58	0.603
7.83	0.484
8.09	0.363
8.34	0.310
DATA SET 8(CONT.)	
8.63	0.252
8.97	0.218
9.12	0.168
9.32	0.135
DATA SET 9	
T = 293.0	
5.54	0.944
5.73	0.929
6.03	0.913
6.20	0.893
6.37	0.868
6.53	0.759
7.07	0.692
7.32	0.624
7.55	0.529
7.83	0.421
8.09	0.307
8.34	0.221
8.63	0.175
8.87	0.135
9.12	0.103
DATA SET 10	
T = 573.0	
5.54	0.919
5.73	0.887
6.07	0.831
6.28	0.772
6.57	0.691
6.83	0.590
7.07	0.470
7.32	0.376
7.58	0.269
7.83	0.188
8.09	0.146

TABLE 10. EXPERIMENTAL DATA ON THE TRANSMISSION OF LITHIUM FLUORIDE (continued)

λ	τ
DATA SET 11	
T = 77.0	
6.03	0.909
6.54	0.851
6.89	0.925
7.50	0.871
7.75	0.915
8.13	0.757
8.23	0.736
8.50	0.835
8.76	0.672
8.96	0.554
9.24	0.510
9.45	0.592
9.65	0.452
9.95	0.343
10.23	0.252
DATA SET 12	
T = 195.0	
6.05	0.926
7.15	0.931
7.39	0.851
7.64	0.734
7.87	0.742
8.15	0.684
8.41	0.832
8.65	0.624
8.91	0.596
9.16	0.555
9.39	0.477
9.67	0.353
9.95	0.280
10.24	0.185
DATA SET 13	
T = 293.0	
6.03	0.941
6.63	0.915
7.15	0.855
7.39	0.828
7.64	0.754
7.87	0.692
8.15	0.623
8.41	0.500
8.65	0.513
8.91	0.483
9.16	0.438
9.39	0.381
9.67	0.289
9.95	0.298
10.21	0.143
DATA SET 14	
T = 573.0	
6.03	0.919
6.63	0.856
6.88	0.826
7.21	0.748
7.37	0.686
7.63	0.609
7.90	0.534
8.15	0.442
8.41	0.358
8.65	0.278
8.91	0.226
9.16	0.156
9.38	0.117
9.67	0.081
DATA SET 15	
T = 77.0	
7.51	0.955
7.73	0.942
8.03	0.927
8.27	0.914
8.52	0.905
8.72	0.915
8.98	0.905
9.24	0.902
9.46	0.879
9.73	0.844
9.97	0.795
10.21	0.746
10.46	0.719
10.74	0.695
10.96	0.659
11.21	0.596
11.46	0.527
11.71	0.447
11.95	0.345
12.21	0.254
12.46	0.167
12.72	0.131
12.96	0.126
13.22	0.133
13.49	0.142
13.71	0.129
13.94	0.102
14.21	0.063
DATA SET 16	
T = 195.0	
7.51	0.935
7.79	0.922
8.03	0.908
8.27	0.912
8.56	0.887
8.87	0.876
9.13	0.876
9.34	0.859
9.57	0.824
9.82	0.768
10.07	0.719
10.38	0.655
10.65	0.610
10.88	0.509
11.13	0.507
11.65	0.347
12.18	0.181
12.74	0.094
13.27	0.055
DATA SET 17	
T = 293.0	
7.51	0.911
7.75	0.896
8.02	0.879
8.28	0.866
8.56	0.862
8.89	0.852
9.09	0.830
9.30	0.812
9.59	0.765
9.83	0.713
10.08	0.643
10.34	0.584
10.64	0.526
10.88	0.461
11.14	0.396
11.37	0.330
11.65	0.252
11.89	0.186
12.13	0.117
12.41	0.076
12.72	0.044
DATA SET 18	
T = 573.0	
7.49	0.894
7.74	0.872
7.99	0.853
8.24	0.827
8.57	0.790
8.84	0.753
9.08	0.722
9.59	0.613
10.07	0.510
10.63	0.366
11.14	0.225
11.69	0.119
12.13	0.055
DATA SET 19	
T = 77.0	
10.97	0.770
11.26	0.754
11.47	0.719
11.74	0.683
11.95	0.611
12.19	0.531
12.48	0.463
12.67	0.422
12.94	0.372
13.22	0.372
13.46	0.390
13.75	0.380
13.98	0.351
14.22	0.337
14.45	0.265
14.70	0.293
14.93	0.121
15.23	0.071
DATA SET 20	
T = 195.0	
10.97	0.754
11.26	0.674
11.47	0.621
11.74	0.573
11.95	0.507
12.19	0.437
12.48	0.360
12.74	0.277
12.94	0.244
13.22	0.227
13.46	0.227
13.75	0.227
13.98	0.216
14.22	0.177
14.45	0.132
DATA SET 21	
T = 293.0	
10.97	0.591
11.26	0.475
11.47	0.424
11.74	0.374
11.95	0.315
12.19	0.255
12.48	0.205
12.67	0.148
12.94	0.110
13.22	0.088
13.46	0.074
13.75	0.057
DATA SET 22	
T = 573.0	
2.00	0.936
3.80	0.944
5.00	0.903
6.60	0.629
8.30	0.232
DATA SET 23	
T = 293.0	
0.106	0.229
0.149	0.388

TABLE 10. EXPERIMENTAL DATA ON THE TRANSMISSION OF LITHIUM FLUORIDE (continued)

λ	τ
DATA SET 23(CONT.)	
0.113	0.451
0.122	0.526
0.128	0.596
0.137	0.656
0.142	0.721
0.145	0.762
0.154	0.823
0.165	0.868
0.186	0.934
0.205	0.952
DATA SET 24	
T = 298.0	
0.109	0.137
0.111	0.177
0.112	0.217
0.115	0.264
0.119	0.304
0.122	0.373
0.123	0.413
0.124	0.456
0.125	0.499
0.145	0.531
0.151	0.624
0.157	0.7[illegible]
0.162	0.774
0.165	0.804
0.172	0.824
0.173	0.827
0.178	0.853
0.185	0.865
DATA SET 25	
T = 298.0	
0.105	0.143
0.107	0.200
0.109	0.230
0.112	0.413
DATA SET 25(CONT.)	
0.115	0.501
0.120	0.572
0.125	0.637
0.129	0.658
0.133	0.664
0.143	0.772
0.153	0.837
0.162	0.873
0.182	0.887
0.205	0.884
DATA SET 26	
T = 298.0	
0.107	0.172
0.111	0.236
0.116	0.311
0.120	0.368
0.135	0.419
0.142	0.494
0.151	0.537
0.160	0.673
0.169	0.696
0.173	0.699
0.183	0.735
0.192	0.747
0.205	0.807
DATA SET 27	
T = 298.0	
0.107	0.066
0.117	0.136
0.131	0.178
0.1[illegible]	0.208
0.144	0.251
0.149	0.327
0.153	0.437
0.156	0.503
0.160	0.545
DATA SET 27(CONT.)	
0.166	0.585
0.185	0.718
0.192	0.731
0.200	0.777
0.205	0.805
DATA SET 28	
T = 298.0	
0.107	0.141
0.113	0.269
0.133	0.306
0.141	0.417
0.151	0.544
0.159	0.637
0.165	0.682
0.173	0.701
0.183	0.733
0.194	0.759
0.205	0.835
DATA SET 29	
T = 298.0	
5.40	0.975
5.29	0.943
5.53	0.836
5.73	0.818
5.92	0.713
6.26	0.486
6.60	0.348
6.95	0.174
7.19	0.114
DATA SET 30	
T = 299.0	
0.104	0.076
0.105	0.290
0.106	0.370
DATA SET 30(CONT.)	
0.107	0.404
0.109	0.459
0.119	0.663
0.127	0.778
0.134	0.859
0.140	0.906
0.145	0.937
DATA SET 31	
T = 336.0	
0.100	0.019
0.107	0.309
0.108	0.428
0.109	0.462
0.116	0.627
0.121	0.730
0.129	0.846
0.136	0.915
0.142	0.962
0.145	0.974
DATA SET 32	
T = 374.0	
0.106	0.035
0.108	0.365
0.109	0.487
0.111	0.560
0.117	0.678
0.119	0.725
DATA SET 33	
T = 407.0	
0.107	0.486
0.109	0.432
DATA SET 34	
T = 298.0	
0.105	0.191
0.106	0.349
0.107	0.415
0.108	0.45[illegible]
0.109	0.475
0.111	0.509
0.112	0.523
0.113	0.537
0.114	0.534
0.115	0.55[illegible]
0.116	0.5[illegible]
0.117	0.55[illegible]
0.118	0.569
0.119	0.594
0.120	0.597
0.122	0.595
0.123	0.595
0.125	0.613
0.126	0.6[illegible]
0.127	0.612
0.128	0.620
0.129	0.624
0.132	0.610
0.134	0.635
0.136	0.645
0.139	0.601
0.14[illegible]	0.662
0.143	0.701
0.146	0.727
0.148	0.737
0.149	0.765
0.152	0.810
0.155	0.826
0.157	0.831
0.160	0.857
0.162	0.853
0.164	0.864
0.166	0.870
0.167	0.865
DATA SET 34(CONT.)	
0.168	0.865
0.170	0.861
0.172	0.891
0.175	0.872
0.178	0.875
0.179	0.877
0.179	0.873
0.179	0.872
0.200	0.879
0.209	0.885
0.210	0.893
0.215	0.9[illegible]
0.225	0.907
0.225	0.915
0.230	0.918
0.235	0.916
0.[illegible]	0.9[illegible]
0.245	0.927
0.250	0.92[illegible]
0.255	0.9[illegible]
0.260	0.927
0.265	0.932
0.270	0.928
0.275	0.924
0.28[illegible]	0.928
0.289	0.934
0.290	0.927
0.299	0.933
0.310	0.926
DATA SET 35	
T = 298.0	
1[illegible].0	0.04
1[illegible]	0.[illegible]5
1[illegible]	0.[illegible]5
250.0	0.[illegible]8
294.0	0.51
345.0	0.53
394.0	0.53

TABLE 10. EXPERIMENTAL DATA ON THE TRANSMISSION OF LITHIUM FLUORIDE (continued)

λ	τ
DATA SET 35(CONT.)	
4.65	0.55
4.80	0.55
DATA SET 36	
T = 295.0	
0.100	0.157
0.105	0.224
0.109	0.339
0.112	0.507
0.115	0.624
0.117	0.681
0.120	0.726
0.123	0.755
0.127	0.781
0.133	0.822
0.137	0.850
0.145	0.878
0.155	0.922
0.175	0.929
0.200	0.941
0.237	0.949
0.283	0.954
0.350	0.960
DATA SET 37	
T = 50.0	
1.00	0.935
3.01	0.935
4.37	0.955
5.37	0.955
5.85	0.953
6.41	0.917
6.73	0.844
6.93	0.800
7.09	0.833
7.28	0.794

λ	τ
DATA SET 37(CONT.)	
7.33	0.746
7.51	0.680
7.62	0.628
7.71	0.588
7.81	0.553
7.97	0.527
8.13	0.526
8.37	0.516
8.62	0.492
8.83	0.476
8.97	0.455
9.08	0.437
9.19	0.394
9.34	0.328
9.54	0.235
9.68	0.167
9.84	0.121
10.01	0.084
10.20	0.048
DATA SET 38	
T = 65.0	
1.00	0.935
3.61	0.935
4.37	0.951
4.85	0.956
5.37	0.956
5.85	0.949
6.12	0.939
6.41	0.917
6.73	0.864
6.93	0.860
7.09	0.738
7.25	0.794
7.36	0.746
7.51	0.650
7.62	0.628
7.71	0.588
7.81	0.553

λ	τ
DATA SET 38(CONT.)	
7.97	0.527
8.13	0.520
8.37	0.504
8.62	0.436
8.83	0.473
8.97	0.455
9.08	0.437
9.19	0.394
9.34	0.328
9.54	0.239
9.68	0.167
9.84	0.121
10.01	0.084
10.20	0.048
DATA SET 39	
T = 300.0	
1.00	0.935
3.01	0.935
4.37	0.950
5.33	0.953
5.85	0.943
5.92	0.925
6.35	0.873
6.60	0.844
6.39	0.800
7.02	0.710
7.43	0.620
7.65	0.526
7.83	0.494
8.09	0.400
8.07	0.333
8.24	0.225
9.33	0.186
9.55	0.129
9.81	0.088
10.02	0.053
10.24	0.035

λ	τ
DATA SET 40	
T = 293.0	
0.1042	0.008
0.1044	0.024
0.1045	0.057
0.1047	0.121
0.1050	0.240
0.1053	0.347
0.1054	0.384
0.1057	0.442
0.1060	0.468
0.1065	0.491
0.1071	0.512
0.1077	0.525
0.1084	0.534
0.1092	0.545
0.1105	0.551
0.1116	0.550
0.1122	0.562
0.1130	0.571
0.1143	0.577
0.1158	0.588
0.1172	0.602
0.1191	0.624
0.1200	0.639
0.1209	0.655
0.1208	0.674
0.1283	0.722
0.1448	0.772
0.1521	0.838
0.1569	0.873
0.1591	0.884
0.1612	0.896
0.1625	0.891
0.1638	0.889
0.1646	0.885
0.1660	0.883
0.1668	0.881
0.1687	0.884
0.1708	0.891
0.1734	0.896

λ	τ
DATA SET 40(CONT.)	
0.1771	0.897
0.1928	0.898
DATA SET 41	
T = 298.0	
0.1042	0.048
0.1044	0.124
0.1045	0.257
0.1047	0.417
0.1050	0.537
0.1052	0.236
0.1054	0.243
0.1056	0.315
0.1058	0.325
0.1063	0.342
0.1072	0.357
0.1081	0.371
0.1091	[illegible]
0.1101	0.381
0.1112	0.391
0.1158	0.413
0.1164	0.413
0.1225	0.440
0.1232	0.442
0.1246	0.445
0.1260	0.442
0.1282	[illegible]
0.1287	0.446
0.1291	0.445
0.1316	0.452
0.1334	0.453
0.1352	0.457
0.1373	0.462
0.1391	0.466
0.1409	0.474
0.1425	0.483
0.1435	0.493
0.1452	0.503
0.1462	0.523

λ	τ
DATA SET 41(CONT.)	
0.1472	0.539
0.1550	0.675
0.1579	0.716
0.1583	0.731
0.1603	0.749
0.1671	0.761
0.1765	0.777
0.1823	0.791
0.1988	0.803
0.2141	0.814
DATA SET 42	
T = 0.2	
43.6	0.153
50.1	0.284
53.6	0.291
54.0	0.301
55.7	0.344
60.5	0.357
75.0	0.443
75.9	0.467
82.1	0.494
87.7	0.500
94.3	0.512
100.9	0.524
120.7	0.523
134.4	0.541
184.5	0.549
193.3	0.544
214.4	0.546
231.4	[illegible]
438.5	0.577
DATA SET 43	
T = 99.7	
70.1	0.013
78.0	0.014
81.4	0.017

TABLE 10. EXPERIMENTAL DATA ON THE TRANSMISSION OF LITHIUM FLUORIDE (continued)

λ	τ
DATA SET 43 (CONT.)	
86.2	0.022
90.1	0.026
95.9	0.029
102.3	0.029
109.0	0.024
114.2	0.021
119.1	0.021
124.2	0.029
126.9	0.042
129.1	0.096
132.3	0.150
135.5	0.259
138.1	0.440
144.4	0.453
159.4	0.470
165.0	0.476
185.1	0.484
215.3	0.493
258.3	0.515
312.5	0.534
37[illegible]	0.543
446.4	0.563
DATA SET 44	
T = 29.0	
132.5	0.013
140.5	0.013
150.4	0.012
161.2	0.019
176.5	0.057
205.3	0.112
23[illegible].5	0.157
253.4	0.219
305.3	0.278
374.5	0.358
534.7	0.498

TABLE 11. PEAK POSITIONS (λ_{max}) IN μm AND HALF-WIDTHS (W) IN eV FOR THE F, R, M, AND N ABSORPTION BANDS IN LITHIUM FLUORIDE*

Interionic dist., d (Å)	Temp.	F band		R_1 band	R_2 band	M band		N bands
		λ_{max}	W	λ_{max}	λ_{max}	λ_{max}	W	λ_{max}
2.01	RT	(0.254)†		(0.295)	(0.320)	(0.416)		
		0.245	0.74	0.306	0.376	0.444		N_1: 0.520
		0.248	0.76	0.308	0.378	0.445		N_2: 0.540
		0.249	0.7	0.310	0.380	0.447		
		0.250		0.313		0.450		
		0.257		0.316				
	NT	0.242	0.47					
	HT	0.243	0.58					
			0.43					

* Values were taken from Ref. [69].

† Values given in parentheses are calculated from the Ivey relations [70].

F band $\lambda_{max} = 703\ d^{1.84}$ for NaCl structure, $\lambda_{max} = 251\ d^{2.5}$ for CsCl structure.

R_1 band $\lambda_{max} = 816\ d^{1.84}$

R_2 band $\lambda_{max} = 884\ d^{1.84}$

M band $\lambda_{max} = 1400\ d^{1.56}$

TABLE 12. RECOMMENDED VALUES ON ABSORPTION COEFFICIENT OF LITHIUM FLUORIDE IN IR REGION AT 300 K

ν, cm^{-1}	λ, μm	Absorption Coefficient, cm^{-1}	
		Intrinsic*	Observed† (Selected)
1.100E+03	9.09	1.6E+1	
1.191E+03	8.40	8.9E+0	9.9E+0
1.240E+03	8.06	6.5E+0	7.8E+0
1.292E+03	7.74	4.6E+0	5.6E+0
1.346E+03	7.43	3.2E+0	3.6E+0
1.395E+03	7.17	2.3E+0	2.5E+0
1.449E+03	6.90	1.6E+0	1.5E+0
1.497E+03	6.68	1.2E+0	1.3E+0
1.550E+03	6.45	8.6E-1	9.3E-1
1.605E+03	6.23	6.0E-1	7.0E-1
1.658E+03	6.03	4.2E-1	5.0E-1
1.701E+03	5.88	3.2E-1	3.4E-1
1.751E+03	5.71	2.3E-1	2.4E-1
1.802E+03	5.55	1.6E-1	1.7E-1
1.857E+03	5.39	1.1E-1	1.1E-1
1.887E+03	5.30	9.5E-2	
1.901E+03	5.26	8.7E-2	8.2E-2
1.949E+03	5.13	6.3E-2	6.2E-2
2.004E+03	4.99	4.4E-2	4.2E-2
2.101E+03	4.76	2.3E-2	2.1E-2
2.203E+03	4.54	1.2E-2	1.1E-2
2.304E+03	4.34	6.2E-3	5.9E-3
2.400E+03	4.17	3.3E-3	
2.500E+03	4.00	1.7E-3	
2.600E+03	3.85	9.0E-4	
2.632E+03	3.80	7.3E-4	
2.700E+03	3.70	4.7E-4	
2.800E+03	3.57	2.4E-4	
2.900E+03	3.45	1.2E-4	
3.000E+03	3.33	6.6E-5	
3.704E+03	2.70	6.7E-7	

*Intrinsic values were calculated according to Eq. (23) with uncertainties about ±10%.

†Values in this column are the total absorption coefficient which are either lowest reported or those used to define the constants in Eq. (23). Uncertainties of these values are about ±10%.

3.2. Sodium Fluoride, NaF

Sodium fluoride is less hygroscopic than the other alkali halides, with the exception of lithium fluoride. It is transparent over the same range of wavelengths as calcium fluoride, a wider range than that of lithium fluoride. It is deficient in its mechanical properties, but it has some uses in cases where a particularly low refractive index is desired. It can be easily evaporated as a thin film and can be used as reflection-reducing coating.

Available data on the refractive index of NaF are not abundant, mainly because of its mechanical weakness. The ultraviolet absorption region was investigated by Sano [71], the transparent region by Hohls [29], Harting [30], Kublitzky [72], and Spangenberg [73], and the infrared region by Randall [74]. Zarzyski and Naudin [75] obtained n for molten NaF for the Hg green line at a temperature of 1273 K.

Li [33], in 1976, reduced the then available experimental data on the refractive index to a common temperature of 293 K and after careful evaluation and analysis adopted a Sellmeier type dispersion equation to calculate the refractive index at 293 K in the wavelength range 0.15-17.0 μm:

$$n = 1.41572 + \frac{0.32785\ \lambda^2}{\lambda^2 - (0.117)^2} + \frac{3.18248\ \lambda^2}{\lambda^2 - (40.57)^2} \qquad (24)$$

where λ is in units of μm.

Investigations of absorption coefficient for practical applications are generally classified into three wavelength regions: the ultraviolet and the infrared limits of transparency, and the transparent regions. In the ultraviolet region, the purposes of the studies were to investigate the exciton states in the crystal and to determine the Urbach-rule parameters.

Tomiki and Miyata [37] performed reflectivity and absorption measurements in the intrinsic wavelength region of cleaved NaF samples to clarify the thermal and spectral dependences of absorptions in the tail region. Effects induced by the ultraviolet radiation were observed. Sizable changes in transmission and reflectivity were observed during the course of uv exposure, suggesting the specimen underwent some kind of damage by the radiation. For this reason, experiments were conducted on freshly cleaved specimens. The absorption spectra of a Harshaw NaF plate of optical quality, displayed broad absorptions

PRECEDING PAGE B

around 0.14 μm due to impurities. However, it showed an exponential absorption tail in the highest energy end of the spectrum, 0.125-0.127 μm, where absorption coefficients were higher than 50 cm^{-1}. Since the tail spectra of intrinsic exciton lines as well as of impurity-induced exciton lines equally obey the Urbach rule, the fact alone that a given tail obeys the Urbach rule does not always constitute in itself a criterion with which the tail can be judged as intrinsic or extrinsic. As evidenced by the broad absorption band around 0.14 μm, the observed tail of this specimen can be regarded as an impurity absorption tail. Sano [71] also investigated the Harshaw NaF single crystals at 78 and 300 K in the spectral region 0.104 to 0.21 μm. Results similar to that of Tomiki and Miyata were observed; namely, broad and prominent impurity absorptions followed by the extrinsic exponential tail. The dependence of the experimental band tail on temperature was compared with the theoretical curves for the intrinsic Urbach tails:

$$\alpha = \alpha_o \exp[-\sigma_s(T)(E_o-E)/kT] \tag{25}$$

and

$$\sigma_s(T) = \sigma_{so} \frac{2kT}{hf} \tanh \frac{hf}{2kT}$$

The constants, E_o and α_o, are the coordinates of the theoretical cross-over point. Sano estimated cross-over point for intrinsic Urbach tail at (10.70 eV, 10^{10} cm^{-1}), σ_{so} = 0.69 and hf = 16.5 meV. Chemically purified and zone refined NaF single crystals were prepared and measured by Földvari et al. [76] in the vacuum uv region at temperatures 100 K, 190 K, and 298 K. The reduction of concentration of OH^-, Cl^-, and Br^- impurities, through the purification process, resulted in the low absorption in the region of 0.13 to 0.16 μm. The specimens were placed behind the exist slit of the optical system in order to avoid the irradiation effects. Their experimental results indicated a theoretical cross-over point at (10.70 eV, 10^9 cm^{-1}) in agreement with Sano's estimation. As the extrapolated experimental absorption curves directed towards a common cross-over point, even at low temperatures, they concluded that the absorption is intrinsic.

Tomiki et al. [77] reported absorption coefficients of NaF at 29 K on the lower energy side of the lowest-energy exciton peak. In this spectral region, absorption rises with increasing energy first exponentially and subsequently non-exponentially forming the lower energy branch of the asymmetric

Lorentzian shape of the main peak. This feature owes its origin to the fluorine ion.

In the laser wavelength region, Harrington and Hass [78] investigated the temperature dependence of multiphonon absorption at 10.6 μm from room temperature to 1110 K for NaF samples using transmission measurements with a laser and power meter. All measurements were carried out inside a stabilized oven on samples polished mechanically, followed by chemical polishing. It was observed that the absorption coefficient increases monotonically and smoothly with temperature and appeared nearly as a straight line on logarithmic scale, as anticipated for the near-intrinsic abosrption of the crystal. Since the absorption levels of NaF at 10.6 μm are in the order of 1 cm^{-1}, it is sufficiently high to be ascribed to intrinsic behavior.

Pohl and Meier [79] studied the absorption at the wavelengths 9.3 μm (1020 cm^{-1}) and 10.6 μm (943.4 cm^{-1}) in the temperature range from 4 to 400 K on two samples of different purity. One was grown by standard techniques, with exposure to air, the other was grown in an argon atmosphere. Thus the main difference between the two samples was the concentrations of oxygen-containing impurities, whose effects on the absorption coefficient were revealed by an almost temperature independent amount of 0.25 cm^{-1} higher at 10.6 μm and by 0.30 cm^{-1} at 9.3 μm. Being about of the same order of magnitude as the total absorption, the impurity induced absorption masks the intrinsic temperature dependence of the impure sample in the low temperature region. In the high temperature region, however, the discrepancies between the two samples became less significant as the total absorption is considerably higher than the impurity absorption. As a consequence, data from both of the samples agreed reasonably well with the results of Harrington and Hass [78] which are slightly larger by an almost constant difference of $\Delta\alpha = 0.09$ cm^{-1} than those of the second sample. Similarly, at 9.3 μm, Klier's results [41] are in line with the above mentioned data. At both wavelengths, three distinct temperature dependencies can be clearly observed: (i) a constant low-temperature absorption in the region $T \lesssim 150$ K, indicating negligible occupation of phonon levels, (ii) the increase of absorption in the region >150 indicating phonon population rising, (iii) eventual compliance to the power-law, increasing at $T > T_{Debye}$.

The infrared multiphonon spectrum of many ionic crystals is characterized by a uniform, almost exponential, decay of absorption with frequency. A key

to the experimental identification of the various multiphonon processes is the temperature dependence of the absorption. The larger the number of phonons participating, the steeper the increase of absorption with temperature. McNelly and Pohl [80], in an attempt to split the exponential wing of the restrahlen band of NaF into the component phonon absorptions, systematically measured absorption coefficients in the range 6.67 to 16.67 μm and 100 to 850 K. Extremely pure samples, which were believed to be intrinsic as evidenced by the very small absorption at high frequencies, were employed. Although their studies were able to separate the resultant absorption spectrum into component phonons, the observed absorption spectrum does not indicate distinct peaks.

Figures 9 to 12 represent the available data. The pertinent information on each data set and the corresponding original values are given in Tables 13 to 16. In addition, for completeness and comparison, available information and data on the reflectivity and transmission are also presented in the same manner (in Figures 13 and 14 and Tables 17 to 20). For the visible and near visible regions, Table 21 gives the spectral positions of the well-known color centers. Noticeable absorptions are likely to occur at these centers when the crystal is exposed to ultraviolet, x-ray, or high energy radiation. However, these absorption bands may disappear at high temperatures or by appropriate radiation exposure, as a result of the so-called "thermal and optical bleaching."

In the multiphonon absorption region (shown in Figure 11), the absorption coefficients vary linearly with wavenumber in the semi-log plot indicating an exponential relation

$$\alpha = \alpha_o e^{-\nu/\nu_o} \tag{26}$$

In this region, Hohls [29] measured absorption coefficient of NaF for the spectral range from 7.5 to 24.0 μm at room temperature. Klier [41] reported his results on NaF in the range 7.9 to 19.1 μm at temperatures 79 K, 293 K, and 573 K. When compared with Hohl's results, a close agreement is observed. However, we found that their results were not adequate to define the constants in Eq. (26). It was based on the results of McNelly and Pohl [80], the constants were found to be $\nu_o = 79.5\ cm^{-1}$ and $\alpha_o = 6.1053 \times 10^4\ cm^{-1}$. Details of this finding are given in the section entitled "Summary of Results and Recommendations."

The recommended values given in Table 22 were calculated according to Eq. (26). It appears that NaF has high intrinsic absorption at 10.6 μm. However, if Eq. (26) holds in the region <5 μm, the intrinsic absorption there is lower than 10^{-4} cm. However, like most optical crystals, one expects to observe an absorption band in the range between 2.6 to 2.8 μm due to the hydroxyl ions in the crystal. This absorption band can be eliminated through improved crystal growing techniques. It should be noted that the values in the column "intrinsic" are the lowest limits that one can obtain for ideal samples. In practice, the observed values are generally higher than the limiting values at low absorption levels. Unless values are reported in the "observed" column, the limiting values are considered as guidelines for estimation and investigation.

Although it was not the intent of this work to compile and evaluate the absorption data in the vacuum ultraviolet region, for the purpose of providing the reader with a total picture of the available absorption data, a plot of the available data in this region is given in the Appendix of this report.



Figure 9. Absorption Coefficient of Sodium Fluoride (Wavenumber Dependence)



Figure 10. Absorption Coefficient of Sodium Fluoride in the Urbach Tail Region



Figure 11. Absorption Coefficient of Sodium Fluoride in the Multiphonon Region

TABLE 13. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF SODIUM FLUORIDE (Wavenumber Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	29	Hohls, H.W.	1936	T	$41.6x10^2$-$1.34x10^3$	293	Crystal; grown by the Kyropoulos method; 14 plate specimens of thicknesses from 0.024 to 10.62 mm; absorption coefficients determined from transmission measurements; data extracted from a figure; temperature not specified, 293 K assumed.
2	41	Klier, M.	1958	R	$5.24x10^2$-$1.06x10^3$	77	Crystal; absorption-coefficient data deduced from reflectivity and transmittance measurements on specimens of various thicknesses; data extracted from a figure.
3	41	Klier, M.	1958	R	$5.7x10^2$-$1.12x10^3$	293	Same as above.
4	41	Klier, M.	1958	R	$6.06x10^2$-$1.26x10^3$	573	Same as above.
5	76	Földvari, I., Yoslka, K., and Raksanyi, K.	1974	R	$6.46x10^4$-$7.94x10^4$	298	Pure single crystals; chemically purified and zone refined; freshly cleaved specimens of 0.2-6 mm thick; absorption coefficient data extracted from a figure.
6	76	Földvari, I., et al.	1974	R	$6.46x10^4$-$8.1x10^4$	190	Above specimen and conditions except at a lower temperature.
7	76	Földvari, I., et al.	1974	R	$6.46x10^4$-$8.3x10^4$	100	Above specimen and conditions except at a lower temperature.
8	71	Sano, R.	1969	R	$7.66x10^4$-$8.7x10^4$	78	Single crystal; obtained from the Harshaw Chemical Co., cleaved specimens of 10 mm x 15 mm x 0.17-2.50 mm, approximately; a thinner specimen of 0.08 mm thickness used for absorption measurement in the range of absorption coefficient as high as 10^2 cm^{-1} - 5 x 10^3 cm^{-1}; data extracted from a figure.
9	71	Sano, R.	1969	R	$5.0x10^4$-$8.7x10^4$	295	Similar to above except at a high temperature.
10	77	Tomiki, T., Miyata, T., and Tsukamoto, H.	1974	R	$8.53x10^4$-$8.62x10^4$	29	Single crystals obtained from the Harshaw Chemical Co.; absorption coefficients deduced from reflection spectrum; data extracted from a curve.
11	81	Beck, H. and Pohl, D.W.	1975	T	$6.5x10$ -$1.1x10^3$	100	Single crystal of extreme purity; no indication of any extrinsic absorption; specimens of 54.98 mm and 3.82 mm thick; absorption measured by means of infrared spectrophotometer; data extracted from a figure.
12	37	Tomiki, T. and Miyata, T.	1969	Z	$5.2x10^4$-$8.0x10^4$	300	Single crystal; ultraviolet quality from the Harshaw Chemical Co.; freshly cleaved specimens for absorption coefficient below 100 cm^{-1}; specimens for higher absorption prepared in high vacuum by melting the flakes of crystals between two plates of glassy carbon and pressed; reflection and transmission spectra obtained and absorption coefficients determined; data extracted from a figure.

TABLE 14. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF SODIUM FLUORIDE (Wavenumber Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

ν	α
DATA SET 1	
T = 293.0	
1.333E+2	9.000E-2
1.250E+3	1.700E-1
1.176E+3	2.500E-1
1.111E+3	3.200E-1
1.053E+3	4.300E-1
1.000E+3	5.400E-1
9.524E+2	7.700E-1
9.091E+2	1.100E+0
8.696E+2	1.400E+0
8.333E+2	2.200E+0
8.000E+2	3.000E+0
7.692E+2	4.500E+0
7.407E+2	5.600E+0
7.143E+2	7.100E+0
6.897E+2	8.000E+0
6.667E+2	1.100E+1
6.452E+2	1.300E+1
6.250E+2	1.700E+1
6.061E+2	2.400E+1
5.882E+2	3.000E+1
5.714E+2	3.700E+1
5.556E+2	4.200E+1
5.405E+2	4.900E+1
5.263E+2	5.700E+1
5.128E+2	6.400E+1
5.000E+2	7.000E+1
4.878E+2	7.600E+1
4.762E+2	8.300E+1
4.651E+2	9.000E+1
4.545E+2	9.700E+1
4.444E+2	1.100E+2
4.348E+2	1.200E+2
4.255E+2	1.300E+2
4.167E+2	1.400E+2
DATA SET 2	
T = 77.0	
1.193E+3	1.000E-1
1.003E+3	3.100E-1
9.524E+2	5.400E-1
9.090E+2	7.700E-1
8.696E+2	1.000E+0
8.333E+2	1.400E+0
8.000E+2	1.800E+0
7.692E+2	2.400E+0
7.407E+2	3.000E+0
7.143E+2	3.700E+0
6.897E+2	4.200E+0
6.667E+2	4.900E+0
6.452E+2	5.600E+0
6.250E+2	6.300E+0
6.061E+2	7.000E+0
5.882E+2	7.700E+0
5.714E+2	8.400E+0
5.556E+2	9.100E+0
5.405E+2	9.800E+0
5.263E+2	1.060E+1
5.128E+2	1.130E+1
5.000E+2	1.200E+1
4.878E+2	1.270E+1
4.762E+2	1.340E+1
4.651E+2	1.410E+1
4.545E+2	1.480E+1
4.444E+2	1.550E+1
4.348E+2	1.620E+1
4.255E+2	1.690E+1
4.167E+2	1.760E+1
DATA SET 3	
T = 293.0	
1.114E+3	1.000E-1
1.056E+3	1.190E-1
9.990E+2	5.210E-1
9.524E+2	1.000E+0
9.091E+2	1.500E+0
8.696E+2	2.000E+0
8.333E+2	2.500E+0
8.000E+2	3.000E+0
7.692E+2	3.500E+0
7.407E+2	4.000E+0
7.143E+2	4.500E+0
6.897E+2	5.000E+0
6.667E+2	5.500E+0
6.452E+2	6.000E+0
6.250E+2	6.500E+0
6.061E+2	7.000E+0
5.882E+2	7.500E+0
5.714E+2	8.000E+0
5.556E+2	8.500E+0
5.405E+2	9.000E+0
5.263E+2	9.500E+0
5.128E+2	1.000E+1
5.000E+2	1.050E+1
4.878E+2	1.100E+1
4.762E+2	1.150E+1
4.651E+2	1.200E+1
4.545E+2	1.250E+1
4.444E+2	1.300E+1
4.348E+2	1.350E+1
4.255E+2	1.400E+1
4.167E+2	1.450E+1
DATA SET 4	
T = 573.0	
1.250E+3	1.537E-1
1.183E+3	2.491E-1
1.116E+3	4.279E-1
1.057E+3	7.367E-1
1.000E+3	1.123E+0
9.551E+2	1.664E+0
9.337E+2	2.116E+0
9.116E+2	2.529E+0
8.913E+2	3.123E+0
8.511E+2	4.253E+0
8.032E+2	6.669E+0
7.711E+2	8.559E+0
7.419E+2	1.157E+1
7.149E+2	1.518E+1
6.911E+2	1.883E+1
6.034E+2	2.456E+1
6.408E+2	3.049E+1
6.258E+2	3.799E+1
6.158E+2	4.659E+1
DATA SET 5	
T = 298.0	
7.937E+4	4.660E+1
7.893E+4	2.811E+1
7.862E+4	1.590E+1
7.843E+4	1.030E+1
7.812E+4	8.100E+0
7.716E+4	6.600E+0
7.634E+4	5.900E+0
7.536E+4	5.200E+0
7.446E+4	4.900E+0
7.299E+4	3.900E+0
7.148E+4	3.300E+0
6.994E+4	2.800E+0
6.849E+4	2.300E+0
6.724E+4	2.300E+0
6.579E+4	1.800E+0
6.464E+4	1.800E+0
DATA SET 6	
T = 198.0	
8.697E+4	3.650E+1
8.658E+4	1.070E+1
8.619E+4	1.250E+1
8.000E+4	9.900E+0
7.962E+4	9.700E+0
7.899E+4	8.000E+0
7.716E+4	6.600E+0
7.034E+4	5.900E+0
7.536E+4	5.200E+0
7.440E+4	4.900E+0
7.299E+4	3.900E+0
7.148E+4	3.300E+0
6.998E+4	2.600E+0
6.849E+4	2.300E+0
6.721E+4	2.300E+0
6.579E+4	1.800E+0
6.464E+4	1.800E+0
DATA SET 7	
T = 100.0	
8.271E+4	2.590E+1
8.244E+4	1.330E+1
8.210E+4	1.490E+1
8.177E+4	9.800E+0
8.130E+4	9.400E+0
8.110E+4	8.700E+0
8.313E+4	7.400E+0
7.843E+4	6.700E+0
7.634E+4	5.900E+0
7.536E+4	5.200E+0
7.446E+4	4.800E+0
7.299E+4	3.900E+0
7.145E+4	3.300E+0
6.994E+4	2.600E+0
6.849E+4	2.300E+0
6.721E+4	2.300E+0
6.579E+4	1.800E+0
6.464E+4	1.800E+0
DATA SET 8	
T = 79.0	
8.095E+4	1.520E+6
8.683E+4	1.699E+6
8.658E+4	2.032E+6
8.641E+4	2.179E+6
8.621E+4	2.410E+6
8.610E+4	2.240E+6
8.585E+4	2.523E+6
8.548E+4	2.159E+6
8.531E+4	1.112E+6
8.513E+4	4.656E+5
8.510E+4	2.650E+5
8.482E+4	3.890E+4
8.291E+4	3.802E+2
8.281E+4	3.420E+2
8.243E+4	2.291E+2
8.227E+4	1.329E+2
8.200E+4	1.300E+2
8.170E+4	5.817E+1
8.123E+4	7.079E+1
8.068E+4	5.445E+1
8.023E+4	4.808E+1
7.972E+4	4.246E+1
7.923E+4	3.733E+1
7.880E+4	3.505E+1
7.827E+4	3.296E+1
7.788E+4	3.034E+1
7.771E+4	2.951E+1
7.748E+4	2.655E+1
7.661E+4	2.228E+1
DATA SET 9	
T = 295.0	
8.694E+4	8.995E+5
8.650E+4	1.019E+6
8.635E+4	1.041E+6
8.617E+4	1.132E+6
8.035E+4	1.146E+6
8.554E+4	1.219E+6
8.569E+4	1.272E+6
8.544E+4	1.337E+6
8.529E+4	1.400E+6
8.514E+4	1.415E+6
8.500E+4	1.507E+6
8.482E+4	1.543E+6
8.466E+4	1.549E+6
8.452E+4	1.629E+6
8.437E+4	1.622E+6
8.416E+4	1.622E+6
8.403E+4	1.585E+6
8.391E+4	1.549E+6
8.375E+4	1.426E+6

TABLE 14. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF SODIUM *FLUORIDE* (Wavenumber Dependence) (continued)

ν	α
DATA SET 9(CONT.)	
6.543E+4	9.3[illegible]E+5
6.327E+4	5.2[illegible]E+5
6.235E+4	4.743E+5
6.2[illegible]E+4	2.977E+5
6.2[illegible]E+4	5.6[illegible]3E+4
7.4[illegible]E+4	6.[illegible]E+2
7.9[illegible]E+4	7.4[illegible]E+2
7.921E+4	1.932E+2
7.9[illegible]E+4	1.4[illegible]E+2
7.8[illegible]E+4	3.790E+1
7.825E+4	4.553E+1
7.7[illegible]E+4	4.[illegible]E+1
7.785E+4	4.5[illegible]E+1
7.771E+4	3.327E+1
7.740E+4	3.119E+1
7.727E+4	2.5[illegible]E+1
7.7[illegible]E+4	2.067E+1
7.651E+4	2.476E+1
7.556E+4	1.794E+1
7.4[illegible]E+4	1.6[illegible]E+1
7.3[illegible]E+4	1.0[illegible]7E+1
7.3[illegible]E+4	1.935E+1
7.1[illegible]E+4	1.343E+1
7.129E+4	1.3[illegible]E+1
6.992E+4	1.[illegible]E+1
6.927E+4	8.7[illegible]E+0
6.[illegible]E+4	7.[illegible]7E+0
6.739E+4	5.5[illegible]E+0
6.6[illegible]E+4	4.3[illegible]E+0
6.531E+4	3.2[illegible]E+0
6.470E+4	2.355E+0
6.345E+4	1.963E+0
5.294E+4	1.3[illegible]E+0
6.219E+4	1.4[illegible]E+0
6.1[illegible]E+4	7.[illegible]5E+0
6.473E+4	7.055E-1
6.73E+4	6.9[illegible]E-1
6.1[illegible]E+4	6.982E-1
5.971E+4	6.137E-1
5.819E+4	5.834E-1

ν	α
DATA SET 9(CONT.)	
5.75[illegible]E+4	5.152E-1
5.645E+4	4.466E-1
5.532E+4	3.548E-1
5.470E+4	2.888E-1
5.387E+4	2.[illegible]E-1
5.319E+4	2.7[illegible]E-1
5.2[illegible]E+4	2.399E-1
5.121E+4	2.365E-1
5.[illegible]81E+4	2.259E-1
5.[illegible]41E+4	1.819E-1
5.[illegible]24E+4	2.[illegible]60E-1
DATA SET 10	
T = 29.[illegible]	
8.621E+4	3.939E+6
8.6[illegible]6E+4	4.[illegible]9E+6
8.[illegible]4E+4	3.930E+6
8.[illegible]1E+4	3.894E+6
8.[illegible]1E+4	3.882E+6
8.992E+4	3.9[illegible]E+6
8.941E+4	3.956E+6
8.976E+4	3.467E+6
8.[illegible]8E+4	2.965E+6
8.945E+4	2.175E+6
8.5[illegible]E+4	3.908E+5
DATA SET 11	
T = 1[illegible]	
6.920E+2	4.86[illegible]E+0
6.9[illegible]E+2	3.795E+0
7.[illegible]E+2	2.691E+0
7.0[illegible]E+2	2.14[illegible]E+0
7.99[illegible]E+2	1.[illegible]E+0
8.25[illegible]E+2	1.[illegible]E+0
8.[illegible]E+2	7.11E-1
9.0[illegible]E+2	5.3[illegible]E-1
9.0[illegible]E+2	4.58E-1
9.22[illegible]E+2	2.51[illegible]E-1

ν	α
DATA SET 11(CONT.)	
9.64[illegible]E+2	1.38[illegible]E-1
9.94[illegible]E+2	9.77[illegible]E-2
1.04[illegible]E+3	6.7[illegible]E-2
1.08[illegible]E+3	4.7[illegible]E-2
DATA SET 12	
T = 293.5	
5.250E+4	1.473E-1
5.3[illegible]E+4	1.9[illegible]E-1
5.33[illegible]E+4	2.0[illegible]E-1
5.43[illegible]E+4	2.3[illegible]E-1
5.56[illegible]E+4	2.46[illegible]E-1
5.55[illegible]E+4	3.32[illegible]E-1
5.7[illegible]E+4	3.46[illegible]E-1
5.85[illegible]E+4	4.8[illegible]E-1
5.99[illegible]E+4	6.[illegible]E-1
6.[illegible]E+4	8.5[illegible]E-1
6.1[illegible]E+4	7.49[illegible]E-1
6.13[illegible]E+4	8.92[illegible]E-1
6.23[illegible]E+4	9.28[illegible]E-1
6.26[illegible]E+4	1.1[illegible]E+0
6.32[illegible]E+4	1.31[illegible]E+0
6.37[illegible]E+4	1.69[illegible]E+1
6.42[illegible]E+4	2.19[illegible]E+0
6.49[illegible]E+4	2.71[illegible]E+0
6.54[illegible]E+4	3.98[illegible]E+0
6.72[illegible]E+4	6.35[illegible]E+0
6.81[illegible]E+4	8.25[illegible]E+0
6.86[illegible]E+4	9.79[illegible]E+0
6.91[illegible]E+4	1.21[illegible]E+1
6.95[illegible]E+4	1.21[illegible]E+1
6.98[illegible]E+4	1.32[illegible]E+1
7.07[illegible]E+4	1.5[illegible]E+1
7.13[illegible]E+4	1.86[illegible]E+1
7.17[illegible]E+4	1.86[illegible]E+1
7.2[illegible]E+4	1.78[illegible]E+1
7.25[illegible]E+4	1.94[illegible]E+1
7.29[illegible]E+4	1.94[illegible]E+1
7.35[illegible]E+4	1.94[illegible]E+1

ν	α
DATA SET 12(CONT.)	
7.43[illegible]E+4	2.12[illegible]E+1
7.49[illegible]E+4	2.31[illegible]E+1
7.56[illegible]E+4	2.31[illegible]E+1
7.62[illegible]E+4	2.31[illegible]E+1
7.6[illegible]E+4	2.41[illegible]E+1
7.76[illegible]E+4	2.86[illegible]E+1
7.81[illegible]E+4	3.69[illegible]E+1
7.82[illegible]E+4	4.38[illegible]E+1
7.83[illegible]E+4	5.2[illegible]E+1
7.88[illegible]E+4	8.7[illegible]E+1
7.92[illegible]E+4	1.39[illegible]E+2
7.97[illegible]E+4	1.8[illegible]E+2
7.99[illegible]E+4	3.43[illegible]E+2
7.99[illegible]E+4	5.49[illegible]E+2
8.00[illegible]E+4	5.98[illegible]E+2



Figure 12. Absorption Coefficient of Sodium Fluoride (Temperature Dependence)

TABLE 15. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF SODIUM FLUORIDE (Temperature Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	79	Pohl, D.W. and Meier, P.F.	1974	T	943.2	31-390	Single crystal; made from Merck Suprapur NaF; grown in an argon atmosphere; specimen configurations and experimental details not given; absorption coefficient obtained; data extracted from a figure.
2	79	Pohl, D.W. and Meier, P.F.	1974	T	1.075×10^3	32-397	Same as above.
3	78	Harrington, J.A. and Hass, M.	1973	T	943.4	300-1110	Single crystal; specimen with surfaces mechanically and then chemically polished; absorption coefficients measured by transmission method with a laser and power meter; data extracted from a figure.
4	80	McNelly, T.F. and Pohl, D.W.	1974	T	700	108-843	Single crystals of extreme purity; specimens of 54.98 and 3.52 mm thick; no indication of any extrinsic absorption; absorption measured by means of infrared spectrophotometer; data extracted from a figure.
5	80	McNelly, T.F. and Pohl, D.W.	1974	T	900	105-849	Same as above.
6	80	McNelly, T.F. and Pohl, D.W.	1974	T	1100	200-861	Same as above.
7	80	McNelly, T.F. and Pohl, D.W.	1974	T	1300	207-881	Same as above.
8	80	McNelly, T.F. and Pohl, D.W.	1974	T	1400	221-899	Same as above.
9	81	Beck, H. and Pohl, D.W.	1975	T	800	103-845	Same as above and measured by McNelly and Pohl but reported in this reference.

TABLE 16. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF SODIUM FLUORIDE (Temperature Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

T	α
DATA SET 1	
ν = 9.434E+2	
31.4	2.7[illegible]E-1
36.8	2.821E-1
42.7	2.7[illegible]E-1
46.7	2.821E-1
54.3	2.563E-1
62.[illegible]	2.7[illegible]E-1
63.6	2.7[illegible]E-1
79.0	2.7[illegible]E-1
86.4	2.7[illegible]E-1
99.5	2.7[illegible]E-1
105.6	2.835E-1
109.3	2.738E-1
119.1	2.9[illegible]E-1
127.3	2.827E-1
143.2	2.95[illegible]E-1
146.2	3.1[illegible]E-1
164.[illegible]	3.245E-1
185.7	3.43[illegible]E-1
202.2	3.[illegible]E-1
22[illegible].0	4.12[illegible]E-1
243.7	4.[illegible]E-1
2[illegible].5	4.823E-1
2[illegible].[illegible]	5.277E-1
3[illegible].5	5.56[illegible]E-1
322.8	6.[illegible]72E-1
35[illegible].7	6.829E-1
349.9	7.733E-1
DATA SET 2	
ν = 1.375E+3	
32.8	1.242E-1
41.2	1.2[illegible]9E-1
49.6	1.2[illegible]5E-1
56.4	1.225E-1
61.2	1.259E-1
72.6	1.242E-1
85.5	1.236E-1
95.0	1.265E-1
106.0	1.228E-1
124.4	1.262E-1
139.9	1.3[illegible]E-1
150.6	1.39[illegible]E-1
176.5	1.514E-1
192.2	1.63[illegible]E-1
2[illegible].5	1.73[illegible]E-1
228.5	1.467E-1
246.5	1.395E-1
276.0	2.329E-1
29[illegible].3	2.013E-1
3[illegible].3	3.180E-1
390.2	3.777E-1
DATA SET 3	
ν = 9.434E+2	
3[illegible].9	6.682E-1
358.9	8.165E-1
4[illegible].5	9.79[illegible]E-1
443.6	1.132E+0
5[illegible].[illegible]	1.358E+0
595.0	1.760E+0
690.0	2.291E+0
8[illegible]3.5	2.965E+0
922.5	3.6[illegible]E+0
977.2	4.073E+0
1[illegible]4.1	4.529E+0
11[illegible].[illegible]	5.[illegible]12E+0
DATA SET 4	
ν = 7.[illegible]E+2	
1[illegible].0	3.69[illegible]E+0
1[illegible].[illegible]	3.91[illegible]E+0
133.0	4.03[illegible]E+0
145.[illegible]	4.15[illegible]E+0
155.0	4.28[illegible]E+0
172.0	4.07[illegible]E+0
187.0	4.96[illegible]E+0
211.0	5.06[illegible]E+0
213.0	5.42[illegible]E+0
226.0	5.83[illegible]E+0
240.0	6.100E+0
26[illegible].0	6.96[illegible]E+0
28[illegible].0	7.175E+0
292.0	6.9[illegible]E+0
3[illegible]5.0	7.830E+0
314.0	8.180E+0
332.0	8.550E+0
337.0	8.550E+0
362.0	9.480E+0
373.0	1.010E+1
383.0	1.0[illegible]E+1
394.0	1.070E+1
4[illegible]6.0	1.160E+1
430.0	1.160E+1
455.0	1.270E+1
462.0	1.370E+1
482.0	1.430E+1
510.0	1.50[illegible]E+1
525.0	1.56[illegible]E+1
546.0	1.650E+1
564.0	1.780E+1
589.0	1.890E+1
624.0	2.110E+1
639.0	2.360E+1
751.0	2.430E+1
819.0	2.9[illegible]E+1
843.0	2.940E+1
DATA SET 5	
ν = 9.[illegible]E+2	
1[illegible].0	3.860E-1
118.0	3.86[illegible]E-1
132.0	4.150E-1
144.0	4.30[illegible]E-1
152.0	4.540E-1
166.0	4.880E-1
184.0	4.960E-1
197.0	4.890E-1
209.0	5.260E-1
224.0	5.660E-1
241.0	6.090E-1
255.0	6.40[illegible]E-1
270.0	6.96[illegible]E-1
282.0	7.836E-1
303.0	8.060E-1
316.0	8.430E-1
330.0	9.[illegible]7E-1
345.0	9.340E-1
356.0	1.010E+0
376.0	1.050E+0
361.0	1.0[illegible]E+0
398.0	1.020E+0
4[illegible]4.0	1.130E+0
428.0	1.450E+0
447.0	1.080E+0
460.0	1.220E+0
488.0	1.270E+0
511.0	1.290E+0
522.0	1.560E+0
545.0	1.610E+0
561.0	1.780E+0
536.0	2.070E+0
620.0	2.300E+0
685.0	2.850E+0
736.0	3.310E+0
3[illegible].0	3.720E+0
849.0	4.440E+0
DATA SET 6	
ν = 1.100E+3	
199.8	3.590E-2
234.5	3.660E-2
256.6	4.130E-2
286.8	4.670E-2
307.2	4.710E-2
323.0	5.600E-2
342.9	6.310E-2
361.5	5.670E-2
386.7	8.470E-2
410.6	7.010E-2
462.9	9.130E-2
5[illegible]7.2	1.1[illegible]E-1
559.8	1.300E-1
625.5	1.750E-1
677.6	1.970E-1
725.3	2.220E-1
767.8	2.800E-1
831.8	2.990E-1
861.5	3.360E-1
DATA SET 7	
ν = 1.300E+3	
207.4	3.170E-3
2[illegible].0	4.0[illegible]E-3
271.7	4.830E-3
3[illegible].2	4.880E-3
325.3	6.690E-3
355.9	7.300E-3
381.7	8.300E-3
413.5	9.9[illegible]E-3
431.6	1.110E-2
466.2	1.330E-2
515.2	1.990E-2
563.7	2.390E-2
623.6	2.6[illegible]E-2
681.7	3.800E-2
710.2	4.270E-2
786.5	5.410E-2
822.7	6.810E-2
883.6	8.580E-2
DATA SET 8	
ν = 1.400E+3	
2[illegible].1	9.730E-4
2[illegible].8	1.3[illegible]E-3
267.4	1.450E-3
28[illegible].1	1.4[illegible]E-3
31[illegible].7	1.410E-3
32[illegible].3	1.99[illegible]E-3
357.4	1.8[illegible]E-3
375.7	2.670E-3
4[illegible].0	3.190E-3
4[illegible].8	4.530E-3
527.8	6.81[illegible]E-3
5[illegible].8	9.620E-3
625.6	1.1[illegible]E-2
6[illegible].5	1.6[illegible]E-2
71[illegible].6	1.830E-2
8[illegible].5	2.590E-2
8[illegible].6	3.090E-2
893.5	3.890E-2
DATA SET 9	
ν = 8.[illegible]E+2	
1[illegible].0	1.360E+0
107.0	1.460E+0
12[illegible].0	1.5[illegible]E+0
145.0	1.6[illegible]E+0
152.0	1.650E+0
17[illegible].0	1.8[illegible]E+0
185.0	1.7[illegible]E+0
195.0	1.8[illegible]E+0
227.0	1.970E+0
2[illegible].0	2.030E+0
2[illegible].0	2.1[illegible]E+0
273.0	2.320E+0
289.0	2.420E+0
297.0	2.610E+0
3[illegible].0	2.8[illegible]E+0
32[illegible].0	2.720E+0
34[illegible].0	2.950E+0

TABLE 16. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF SODIUM FLUORIDE (Temperature Dependence) (continued)

T	α
DATA SET 9(CONT.)	
348.0	2.980E+0
353.0	3.160E+0
359.0	3.250E+0
385.0	3.350E+0
391.0	3.600E+0
403.0	3.660E+0
432.0	3.770E+0
444.0	4.170E+0
471.0	4.110E+0
454.0	4.630E+0
465.0	4.910E+0
527.0	5.520E+0
543.0	5.590E+0
567.0	5.770E+0
593.0	6.990E+0
635.0	7.400E+0
692.0	8.370E+0
743.0	9.370E+0
787.0	1.110E+1
845.0	1.260E+1

AD-A118 601 CENTER FOR INFORMATION AND NUMERICAL DATA ANALYSIS AN--ETC F/G 7/2
ABSORPTION COEFFICIENT OF ALKALI HALIDES. PART I.(U)
MAR 79 H H LI F49620-76-C-0105
UNCLASSIFIED CINDAS-54 AFOSR-TR-82-0687 NL

2 of 3
AD
A118601



Figure 13. Reflectivity of Sodium Fluoride

TABLE 17. SUMMARY OF MEASUREMENTS ON THE REFLECTIVITY OF SODIUM FLUORIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	29	Hohls, H.W.	1936	R	19.8-54.1	293	Crystal; grown by the Kyropoulos method; specimen configuration and surface condition unspecified; normal reflectivity determined by using a freshly vacuum coated silver mirror as reference standard; data extracted from a figure; estimated uncertainty about ±10%; temperature was not given, 293 K assumed.
2	82	Roessler, D.M. and Walker, W.C.	1967	R	0.105-0.138	300	Bulk sodium fluoride; no information about the specimens given; reflection spectrum obtained; data extracted from a figure.
3	82	Roessler, D.M. and Walker, W.C.	1967	R	0.105-0.127	77	Same as above except at a lower temperature.
4	41	Klier, M.	1958	R	20.9-26.0	77	Crystal; specimen with top surface highly polished; reflection spectrum measured with a reference mirror made of German V_2A steel; data extracted from a figure.
5	41	Klier, M.	1958	R	20.5-26.0	293	Same as above.
6	41	Klier, M.	1958	R	21.4-26.0	573	*Same as above.*
7	83	Chang, I.F. and Mitra, S.S.	1972	R	19.5-58.2	132	Crystal; obtained from the Harshaw Chemical Co.; specimens with highly polished surface (with or without annealing) or freshly cleaved surface; reflection spectra measured and repeated several times and reproduced within 2% error in intensity and less than 1% error in band position; data extracted from a figure.
8	83	Chang, I.F. and Mitra, S.S.	1972	R	19.5-60.5	215	Same as above except at a higher temperature.
9	83	Chang, I.F. and Mitra, S.S.	1972	R	19.5-60.5	298	Same as above except at a higher temperature.
10	83	Chang, I.F. and Mitra, S.S.	1972	R	19.5-61.7	423	Same as above except at a higher temperature.
11	83	Chang, I.F. and Mitra, S.S.	1972	R	19.5-61.7	605	Same as above except at a higher temperature.
12	83	Chang, I.F. and Mitra, S.S.	1972	R	19.5-60.5	792	Same as above except at a higher temperature.
13	83	Chang, I.F. and Mitra, S.S.	1972	R	19.5-60.5	958	Same as above except at a higher temperature.
14	54	McCarthy, D.E.	1965	R	2.00-50.0	298	Synthetic crystal; 2.16 mm thick; polished to flatness of 10 fringes; 30° reflectivity measured with aluminum mirror as reference standard; data extracted from a curve.
15	84	Mitsuishi, A., Yamada, Y. and Yoshinaga, H.	1962	R	19.9-51.6	300	Single crystal; near normal reflectivity; measured in vacuum with aluminum mirrors as reference standard; data extracted from a curve.

TABLE 17. SUMMARY OF MEASUREMENTS ON THE REFLECTIVITY OF SODIUM FLUORIDE (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
16	57	Rao, K.K., Moravec, T.J., Rife, J.C., and Dexter, R.N.	1975	R	0.044-0.207	30	Single crystal; obtained from the Harshaw Chemical Co.; cleaved specimen of 1 cm diameter and 3 mm thick; specimen kept in vacuum during reflectivity measurements; near normal reflectivity obtained; data extracted from a curve.
17	71	Sano, R.	1969	R	0.108-0.128	78	Single crystal; obtained from the Harshaw Chemical Co.; cleaved specimens of 10 mm x 15 mm x 0.17-2.50 mm approximately; near normal reflectivity obtained; data extracted from a figure.
18	71	Sano, R.	1969	R	0.099-0.210	295	Same as above except at a higher temperature.
19	61	Nakagawa, I.	1971	R	21.5-74.7	293	Single crystal; near normal reflectivity measurements made in a vacuum; data extracted from a curve.
20	37	Tomiki, T. and Miyata, T.	1969	R	0.11-0.16	273	Single crystal; obtained from the Harshaw Chemical Co.; freshly cleaved; normal reflectivity measured in vacuum; data extracted from a curve.

TABLE 18. EXPERIMENTAL DATA ON THE REFLECTIVITY OF SODIUM FLUORIDE

[Wavelength, λ, μm; Temperature, T, K; Reflectivity, ρ]

λ	ρ	λ	ρ	λ	ρ	λ	ρ	λ	ρ	λ	ρ
DATA SET 1		DATA SET 1(CONT.)		DATA SET 2(CONT.)		DATA SET 3(CONT.)		DATA SET 3(CONT.)		DATA SET 3(CONT.)	
T = 293.0											
		54.07	0.307	0.1193	0.241	0.1079	0.008	0.1152	0.378	0.1262	0.066
19.81	0.0196			0.1193	0.239	0.1081	0.005	0.1152	0.382		
20.70	0.0359	DATA SET 2		0.1193	0.222	0.1084	0.005	0.1153	0.385	DATA SET 4	
21.42	0.0600	T = 300.0		0.1193	0.219	0.1086	0.003	0.1156	0.391	T = 77.0	
21.87	0.0829			0.1202	0.215	0.1089	0.003	0.1156	0.397		
22.64	0.127	0.1051	0.020	0.1203	0.210	0.1092	0.003	0.1156	0.399	20.98	0.032
22.54	0.231	0.1056	0.028	0.1205	0.188	0.1095	0.005	0.1161	0.401	22.96	0.084
22.85	0.274	0.1062	0.026	0.1211	0.177	0.1100	0.011	0.1165	0.399	22.97	0.193
23.32	0.439	0.1067	0.028	0.1212	0.173	0.1102	0.025	0.1168	0.390	23.96	0.445
23.93	0.497	0.1070	0.026	0.1219	0.133	0.1106	0.036	0.1166	0.392	24.94	0.509
24.21	0.515	0.1073	0.026	0.1220	0.133	0.1106	0.062	0.1168	0.353	26.00	0.487
24.54	0.515	0.1077	0.022	0.1230	0.108	0.1109	0.085	0.1172	0.384		
24.93	0.493	0.1082	0.019	0.1242	0.091	0.1113	0.133	0.1173	0.355	DATA SET 5	
25.00	0.490	0.1089	0.014	0.1247	0.084	0.1116	0.165	0.1173	0.354	T = 293.0	
25.23	0.491	0.1094	0.009	0.1251	0.080	0.1120	0.176	0.1173	0.349		
25.53	0.436	0.1096	0.007	0.1262	0.071	0.1117	0.192	0.1176	0.342	20.49	0.008
26.00	0.423	0.1101	0.005	0.1267	0.067	0.1120	0.267	0.1178	0.296	21.96	0.019
26.95	0.400	0.1112	0.012	0.1283	0.009	0.1119	0.215	0.1179	0.259	21.97	0.043
29.57	0.303	0.1116	0.021	0.1294	0.004	0.1121	0.224	0.1182	0.257	22.96	0.003
31.11	0.325	0.1119	0.031	0.1309	0.001	0.1123	0.227	0.1179	0.247	22.96	0.109
31.91	0.352	0.1120	0.037	0.1320	0.006	0.1123	0.246	0.1182	0.239	22.34	0.031
33.26	0.355	0.1122	0.046	0.1336	0.057	0.1123	0.253	0.1184	0.224	23.45	0.224
34.70	0.339	0.1124	0.060	0.1340	0.054	0.1125	0.266	0.1190	0.19[illegible]	23.90	0.370
35.83	0.333	0.1127	0.083	0.1355	0.054	0.1128	0.266	0.1191	0.267	24.00	0.516
35.29	0.333	0.1132	0.125	0.1365	0.053	0.1128	0.272	0.1193	0.26[illegible]	24.94	0.535
35.60	0.370	0.1135	0.138	0.1374	0.055	0.1131	0.292	0.1199	0.133	25.44	0.565
36.03	0.350	0.1137	0.193	0.1376	0.051	0.1133	0.298	0.1203	0.132	26.00	0.472
36.55	0.414	0.1140	0.261			0.1133	0.310	0.1206	0.122		
41.21	0.766	0.1146	0.286	DATA SET 3		0.1135	0.311	0.1210	0.115	DATA SET 6	
42.15	0.659	0.1147	0.193	T = 77.0		0.1137	0.314	0.1212	0.105	T = 573.0	
43.75	0.635	0.1149	0.212			0.1137	0.322	0.1221	0.137		
43.23	0.593	0.1152	0.208	0.1051	0.036	0.1137	0.327	0.1225	0.105	21.48	0.029
44.15	0.560	0.1155	0.212	0.1052	0.032	0.1141	0.326	0.1230	0.102	21.98	0.054
45.03	0.521	0.1158	0.221	0.1056	0.032	0.1139	0.328	0.1232	0.093	22.48	0.095
46.13	0.465	0.1160	0.233	0.1059	0.030	0.1141	0.348	0.1233	0.103	22.95	0.150
47.00	0.415	0.1165	0.243	0.1062	0.025	0.1148	0.352	0.1237	0.097	23.45	0.221
49.04	0.387	0.1168	0.248	0.1068	0.021	0.1145	0.359	0.1239	0.090	23.90	0.350
49.54	0.365	0.1170	0.259	0.1069	0.017	0.1148	0.365	0.1238	0.095	24.43	0.438
51.05	0.342	0.1176	0.257	0.1073	0.013	0.1150	0.367	0.1245	0.093	24.95	0.489
52.35	0.325	0.1191	0.248	0.1076	0.010	0.1156	0.378	0.1251	0.090	25.44	0.464

TABLE 19. EXPERIMENTAL DATA ON THE REFLECTIVITY OF SODIUM FLUORIDE (continued)

λ	ρ
DATA SET 6(CONT.)	
25.94	0.424
DATA SET 7	
T = 132.0	
19.50	0.021
20.[illegible]	0.021
20.72	0.027
21.67	0.037
21.44	0.344
21.74	0.[illegible]
22.03	0.171
22.32	0.206
22.69	0.171
23.02	0.255
23.29	0.344
23.51	0.416
23.72	0.474
23.97	0.537
24.19	0.549
24.39	0.549
24.71	0.542
25.[illegible]	0.532
25.54	0.516
25.79	0.521
26.19	0.532
26.69	0.657
27.11	0.722
27.74	0.824
28.15	0.848
28.66	0.891
29.25	0.913
29.94	0.935
30.65	0.953
31.39	0.951
32.21	0.974
32.84	0.979
33.44	1.982
34.11	0.984
35.60	0.982

λ	ρ
DATA SET 7(CONT.)	
35.73	0.973
36.36	0.961
37.36	0.935
38.[illegible]	0.910
38.59	0.876
39.43	0.699
40.29	0.571
41.22	0.479
42.47	0.457
43.87	0.436
44.75	0.395
43.78	0.359
44.44	0.332
45.45	0.305
46.25	0.291
47.41	0.273
48.[illegible]	0.264
49.26	0.231
50.42	0.238
52.21	0.225
53.53	0.216
54.79	0.212
56.40	0.205
58.24	0.199
DATA SET 8	
T = 215.0	
19.50	0.026
20.16	0.021
20.72	0.027
21.47	0.036
21.44	0.042
21.74	0.051
22.03	0.067
22.32	0.097
22.69	0.152
23.32	0.232
23.29	0.303
23.51	0.369

λ	ρ
DATA SET 8(CONT.)	
23.71	0.432
23.97	0.435
24.18	0.537
24.39	0.540
24.70	0.527
25.11	0.497
25.54	0.463
25.79	0.456
26.19	0.449
26.69	0.526
27.11	0.597
27.70	0.683
28.15	0.755
28.66	0.836
29.25	0.883
29.94	0.916
30.65	0.944
31.39	0.961
32.21	0.962
32.84	0.964
33.44	0.967
34.11	0.965
35.06	0.959
35.73	0.954
36.36	0.946
37.36	0.926
38.68	0.910
38.59	0.876
39.43	0.765
40.29	0.677
41.22	0.582
41.47	0.567
41.87	0.526
42.75	0.476
43.78	0.427
44.44	0.388
45.45	0.354
46.25	0.334
47.41	0.310
48.66	0.294

λ	ρ
DATA SET 8(CONT.)	
49.26	0.278
50.42	0.266
52.21	0.246
53.53	0.236
54.79	0.234
56.40	0.222
58.24	0.218
60.53	0.221
DATA SET 9	
T = 293.0	
19.50	0.026
20.16	0.021
20.72	0.027
21.47	0.035
21.44	0.038
21.74	0.054
22.03	0.064
22.32	0.090
22.69	0.147
23.02	0.206
23.29	0.272
23.51	0.341
23.71	0.416
23.97	0.467
24.18	0.498
24.39	0.526
24.70	0.527
25.11	0.512
25.54	0.487
25.79	0.469
26.19	0.449
26.69	0.436
27.11	0.465
27.70	0.533
28.15	0.596
28.66	0.667
29.25	0.766
29.94	0.836

λ	ρ
DATA SET 9(CONT.)	
30.65	0.875
31.39	0.900
32.21	0.919
32.84	0.925
33.44	0.938
34.11	0.934
35.06	0.947
35.73	0.948
36.36	0.946
37.36	0.945
38.30	0.934
38.59	0.929
39.43	0.898
40.29	0.853
41.22	0.689
41.47	0.640
41.87	0.603
42.75	0.521
43.78	0.459
44.44	0.422
45.45	0.383
46.25	0.350
47.41	0.333
48.36	0.314
49.26	0.291
50.42	0.270
52.21	0.254
53.53	0.245
54.79	0.235
56.40	0.220
58.24	0.222
60.53	0.221
DATA SET 10	
T = 423.0	
19.50	0.020
20.16	0.021
20.72	0.027
21.07	0.032

λ	ρ
DATA SET 10(CONT.)	
21.44	0.036
21.74	0.045
22.03	0.061
22.32	0.086
22.66	0.113
23.02	0.150
23.29	0.208
23.51	0.251
23.71	0.306
23.97	0.373
24.18	0.422
24.39	0.467
24.71	0.487
25.11	0.488
25.54	0.482
25.79	0.469
26.19	0.449
26.69	0.450
27.11	0.423
27.74	0.423
28.15	0.450
28.66	0.493
29.25	0.588
29.94	0.671
30.65	0.744
31.39	0.802
32.21	0.831
32.84	0.850
33.44	0.856
34.11	0.864
35.06	0.874
35.73	0.879
36.36	0.883
37.36	0.878
38.66	0.876
38.59	0.865
39.43	0.845
40.29	0.813
41.22	0.744
41.47	0.692

TABLE 18. EXPERIMENTAL DATA ON THE REFLECTIVITY OF SODIUM FLUORIDE (continued)

λ	ρ
DATA SET 10(CONT.)	
41.87	0.643
42.75	0.563
43.78	0.484
44.44	0.438
45.45	0.393
46.25	0.371
47.41	0.342
48.54	0.323
49.25	0.313
50.42	0.295
52.21	0.283
53.53	0.294
54.79	0.244
56.42	0.235
58.24	0.227
60.53	0.221
61.72	0.214
DATA SET 11	
T = 605.0	
19.53	0.824
20.25	0.821
20.72	0.837
21.07	0.832
21.44	0.838
21.74	0.843
22.03	0.844
22.32	0.853
22.69	0.813
23.02	0.815
23.29	0.778
23.51	0.813
23.71	0.753
23.97	0.739
24.13	0.353
24.39	0.379
24.74	0.408
25.11	0.433
25.54	0.453

λ	ρ
DATA SET 11(CONT.)	
25.79	0.457
26.19	0.449
26.69	0.439
27.11	0.436
27.74	0.416
28.15	0.413
28.66	0.414
29.25	0.400
29.94	0.514
31.05	0.587
31.39	0.627
32.21	0.686
32.84	0.722
33.44	0.749
34.11	0.773
[illegible]	0.798
35.73	0.819
36.36	0.821
37.36	0.822
38.00	0.847
38.53	0.854
39.43	0.788
40.29	0.772
41.22	0.741
41.87	0.731
42.87	0.717
42.75	0.675
43.78	0.644
44.44	0.627
45.45	0.467
46.25	0.432
47.41	0.398
48.00	0.378
49.26	0.348
50.42	0.324
52.21	0.301
53.53	0.286
54.79	0.278
56.42	0.266
58.24	0.258

λ	ρ
DATA SET 11(CONT.)	
60.53	0.245
61.72	0.249
DATA SET 12	
T = 792.0	
19.50	0.620
20.25	0.621
20.72	0.627
21.07	0.623
21.44	0.631
21.74	0.642
22.03	0.655
22.32	0.663
22.68	0.691
23.02	0.713
23.33	0.735
23.51	0.754
23.71	0.19
23.97	0.20[illegible]
24.18	0.274
24.39	0.2[illegible]9
24.73	0.343
25.11	0.353
25.54	0.394
25.79	0.414
26.19	0.423
26.69	0.419
27.11	0.430
27.74	0.424
28.15	0.415
28.66	0.409
29.25	0.400
29.94	0.402
30.65	0.419
31.39	0.468
32.21	0.525
32.84	0.563
33.44	0.599
34.11	0.625

λ	ρ
DATA SET 12(CONT.)	
35.36	0.663
35.73	0.676
36.36	0.688
37.36	0.762
38.00	0.764
38.59	0.763
39.43	0.699
40.29	0.692
41.22	0.680
41.87	0.673
41.87	0.662
42.75	0.645
43.78	0.626
44.44	0.588
45.45	0.547
46.25	0.514
47.41	0.474
48.00	0.439
49.26	0.395
50.42	0.358
52.21	0.327
53.53	0.306
54.79	0.294
56.42	0.278
58.24	0.266
60.53	0.255
DATA SET 13	
T = 958.0	
19.50	0.626
20.25	0.621
20.72	0.627
21.07	0.622
21.44	0.627
21.74	0.628
22.03	0.632
22.32	0.642
22.68	0.658
23.02	0.675

λ	ρ
DATA SET 13(CONT.)	
23.29	0.692
23.51	0.106
23.71	0.120
23.97	0.245
24.18	0.172
24.39	0.250
24.76	0.223
25.11	0.251
25.54	0.293
25.79	0.3[illegible]
26.19	0.330
26.69	0.363
27.11	0.389
27.74	0.393
28.15	0.397
28.66	0.395
29.25	0.393
29.94	0.373
31.65	0.3[illegible]
31.39	0.369
32.21	0.395
32.84	0.419
33.44	0.434
34.11	0.459
35.00	0.495
35.73	0.502
36.36	0.510
37.36	0.547
38.00	0.559
38.59	0.565
39.43	0.574
40.29	0.571
41.22	0.563
41.87	0.567
41.87	0.564
42.75	0.552
43.78	0.533
44.44	0.518
45.45	0.483
46.25	0.462

λ	ρ
DATA SET 13(CONT.)	
47.41	0.440
48.00	0.427
49.26	0.398
50.42	0.377
52.21	0.348
53.53	0.332
54.79	0.315
56.42	0.296
58.24	0.282
60.53	0.267
DATA SET 14	
T = 298.0	
2.00	0.023
8.30	0.023
21.44	0.04
22.1	0.16
23.4	0.472
24.5	0.551
26.3	0.430
27.4	0.456
30.0	0.016
34.0	0.516
37.5	0.561
40.1	0.542
41.3	0.767
41.9	0.576
43.3	0.437
50.0	0.376
44.0	0.286
50.0	0.249
DATA SET 15	
T = 300.0	
13.9	0.647
21.4	0.000
22.1	0.158
23.3	0.417

TABLE 18. EXPERIMENTAL DATA ON THE REFLECTIVITY OF SODIUM FLUORIDE (continued)

λ	ρ
DATA SET 15(CONT.)	
23.8	0.553
24.2	0.568
24.6	0.557
25.3	0.499
26.1	0.472
26.7	0.551
29.0	0.544
30.1	0.499
31.8	0.932
34.1	0.943
36.8	0.934
38.3	0.832
41.4	0.570
42.1	0.437
43.4	0.424
45.0	0.358
47.3	0.329
51.6	0.279
DATA SET 16	
T = 300	
0.0413	0.0334
0.0423	0.0334
0.0438	0.0343
0.0446	0.0352
0.0457	0.0353
0.0469	0.0350
0.0475	0.0354
0.0491	0.0337
0.0502	0.0392
0.0530	0.0305
0.0532	0.0243
0.0539	0.0245
0.0549	0.0277
0.0561	0.0331
0.0568	0.0333
0.0575	0.0321
0.0587	0.0298

λ	ρ
DATA SET 16(CONT.)	
0.0599	0.0485
0.0604	0.0433
0.0613	0.0503
0.0635	0.0306
0.0663	0.0159
0.0677	0.0129
0.0688	0.0130
0.0710	0.0346
0.0733	0.0472
0.0751	0.0509
0.0765	0.0491
0.0779	0.0460
0.0779	0.0475
0.0794	0.0476
0.0810	0.0472
0.0892	0.0316
0.0925	0.0272
0.0976	0.0242
0.1008	0.0234
0.1033	0.0243
0.1050	0.0245
0.1069	0.0225
0.1107	0.0222
0.1198	0.0458
0.1203	0.0414
0.1240	0.0424
0.1231	0.0598
0.1333	0.0471
0.1409	0.0413
0.1653	0.0329
0.1771	0.0297
0.2000	0.0288
DATA SET 17	
T = 70.0	
0.1142	0.010
0.1145	0.023
0.1138	0.058
0.1127	0.058

λ	ρ
DATA SET 17(CONT.)	
0.1120	0.189
0.1122	0.222
0.1124	0.232
0.1128	0.262
0.1134	0.315
0.1145	0.380
0.1147	0.391
0.1149	0.403
0.1152	0.443
0.1161	0.482
0.1162	0.462
0.1164	0.458
0.1166	0.453
0.1169	0.452
0.1173	0.418
0.1176	0.344
0.1179	0.280
0.1187	0.218
0.1191	0.200
0.1198	0.168
0.1205	0.144
0.1215	0.122
0.1230	0.100
0.1244	0.092
0.1252	0.086
0.1261	0.081
0.1277	0.081
0.1278	0.074
DATA SET 18	
T = 235.0	
0.0932	0.031
0.1003	0.034
0.1007	0.034
0.1017	0.035
0.1026	0.033
0.1031	0.033
0.1035	0.033
0.1041	0.035

λ	ρ
DATA SET 18(CONT.)	
0.1047	0.034
0.1052	0.034
0.1059	0.034
0.1066	0.032
0.1070	0.032
0.1078	0.029
0.1082	0.025
0.1085	0.023
0.1089	0.026
0.1095	0.031
0.1102	0.036
0.1104	0.036
0.1107	0.037
0.1110	0.040
0.1116	0.022
0.1119	0.038
0.1121	0.051
0.1124	0.071
0.1133	0.142
0.1147	0.223
0.1152	0.250
0.1161	0.286
0.1166	0.294
0.1172	0.310
0.1175	0.313
0.1181	0.315
0.1183	0.311
0.1188	0.311
0.1191	0.304
0.1193	0.298
0.1199	0.280
0.1201	0.273
0.1205	0.247
0.1210	0.205
0.1215	0.188
0.1219	0.175
0.1224	0.159
0.1230	0.136
0.1240	0.115
0.1246	0.105

λ	ρ
DATA SET 18(CONT.)	
0.1253	0.090
0.1267	0.093
0.1277	0.079
0.1294	0.072
0.1302	0.064
0.1313	0.062
0.1326	0.064
0.1336	0.057
0.1346	0.056
0.1359	0.055
0.1371	0.053
0.1380	0.053
0.1385	0.053
0.1394	0.051
0.1396	0.047
0.1831	0.030
0.1859	0.030
0.1881	0.029
0.1901	0.030
0.1947	0.031
0.1960	0.031
0.1931	0.033
0.1952	0.029
0.1971	0.027
0.1993	0.027
0.2010	0.026
0.2029	0.026
0.2046	0.026
0.2066	0.026
DATA SET 19	
T = 293.0	
21.5053	0.017
21.8919	0.010
21.9786	0.017
22.3214	0.041
22.7272	0.081
23.3414	0.124
23.9234	0.330
24.3349	0.400

λ	ρ
DATA SET 19(CONT.)	
24.5458	0.421
24.7524	0.421
25.0000	0.405
25.4452	0.360
25.7500	0.347
26.4550	0.351
26.9541	0.366
28.7350	0.574
29.3255	0.027
30.0000	0.081
30.9997	0.733
32.2580	0.772
33.6963	0.800
35.9712	0.824
37.0370	0.798
38.3242	0.768
39.2156	0.744
40.0000	0.742
40.8524	0.633
42.3003	0.571
42.1940	0.501
43.1234	0.497
43.5590	0.421
45.0000	0.394
46.7289	0.364
50.0000	0.334
52.3560	0.304
54.3478	0.293
56.1797	0.265
59.1716	0.241
63.2912	0.234
68.9655	0.228
74.0268	0.222
DATA SET 20	
T = 273.0	
0.1150	0.281
0.1166	0.294
0.1169	0.308

TABLE 18. EXPERIMENTAL DATA ON THE REFLECTIVITY OF SODIUM FLUORIDE (continued)

	ρ
DATA SET 20(CONT.)	
0.1170	0.313
0.1170	0.313
0.1133	0.337
0.1137	0.345
0.1137	0.343
0.1136	0.346
0.1193	0.297
0.1199	0.280
0.1201	0.272
0.1229	0.257
0.1240	0.247
0.1248	0.240
0.1215	0.196
0.1219	0.175
0.1224	0.157
0.1232	0.134
0.1233	0.116
0.1245	0.095
0.1253	0.080
0.1273	0.054
0.1277	0.079
0.1291	0.072
0.1302	0.065
0.1321	0.063
0.1334	0.058
0.1336	0.056
0.1343	0.055
0.1356	0.053
0.1371	0.052
0.1397	0.049
0.1394	0.049
0.1402	0.045
0.1425	0.045
0.1428	0.044
0.1455	0.041
0.1457	0.040
0.1490	0.039
0.1513	0.038
0.1527	0.036
0.1542	0.034



Figure 14. Transmission of Sodium Fluoride

TABLE 19. SUMMARY OF MEASUREMENTS ON THE TRANSMISSION OF SODIUM FLUORIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	54	McCarthy, D.E.	1965	T	2.20-16.8	298	Synthetic crystal; 2.16 mm thick; polished to flatness of 10 fringes of sodium D line; data extracted from a curve.
2	85	McCarthy, D.E.	1967	T	0.171-3.00	298	Single synthetic crystal; obtained from Harshaw Chemical Co.; thickness of 2.16 mm; the two surfaces of the specimen were parallel to within 0.001 mm/mm length; polished to flatness of 10 fringes of the mercury green line; data extracted from a curve.
3	37	Tomiki, T. and Miyata, T.	1969	T	0.13-0.19	298	Single crystal; obtained from Harshaw Chemical Co.; freshly cleaved specimen of 0.188 cm; transmittance measured in vacuum; data extracted from a curve.

TABLE 20. EXPERIMENTAL DATA ON THE TRANSMISSION OF SODIUM CHLORIDE

[Wavelength, λ, μm; Temperature, T, °C; Transmission, T]

λ	T
DATA SET 1	
T = 298.0	
2.20	0.952
8.40	0.952
9.50	0.926
10.9	0.920
12.1	0.603
[illegible]	[illegible]
14.6	0.143
15.5	0.054
16.8	0.019
DATA SET 2	
T = 298.0	
0.171	0.683
0.217	0.735
0.252	0.847
0.281	0.881
0.314	0.911
0.347	0.923
0.421	0.936
0.554	0.943
0.955	0.947
3.00	0.951
DATA SET 3	
T = 298.0	
0.130	0.001
0.131	0.006
0.133	0.009
0.134	0.008
0.134	0.008
0.135	0.013
0.137	0.016
0.138	0.019
0.138	0.023
0.139	0.023
0.140	0.023
0.142	0.045

λ	T
DATA SET 3(CONT.)	
0.143	0.066
0.144	0.081
0.144	0.098
0.145	0.133
0.147	0.185
0.149	0.285
0.150	0.4[illegible]
0.152	0.437
0.154	0.541
0.155	0.611
0.156	0.653
0.158	0.709
0.159	0.747
0.160	0.774
0.163	0.793
0.167	0.827
0.170	0.837
0.171	0.845
0.175	0.863
0.180	0.872
0.183	0.892
0.186	0.892
0.189	0.913

TABLE 21. PEAK POSITIONS (λ_{max}) IN μm AND HALF-WIDTHS (W) IN eV FOR THE F, R, M, AND N ABSORPTION BANDS IN SODIUM FLUORIDE*

Interionic dist., d (Å)	Temp.	F band		R_1 band	R_2 band	M band		N bands
		λ_{max}	W	λ_{max}	λ_{max}	λ_{max}	W	λ_{max}
2.31	RT	(0.328)†		(0.381)	(0.412)	(0.516)		
		0.335	0.70		0.415	0.505	0.16	
		0.340	0.51			0.507		
		0.341				0.510		
		0.342						
	NT	0.332	0.50			0.498		
	HT	0.336						

* Values were taken from Ref. [69].

† Values given in parentheses are calculated from the Ivey relations [70].

F band $\lambda_{max} = 703\ d^{1.84}$ for NaCl structure, $\lambda_{max} = 251\ d^{2.5}$ for CsCl structure.

R_1 band $\lambda_{max} = 816\ d^{1.84}$

R_2 band $\lambda_{max} = 884\ d^{1.84}$

M band $\lambda_{max} = 1400\ d^{1.56}$

TABLE 22. RECOMMENDED VALUES ON ABSORPTION COEFFICIENT OF SODIUM FLUORIDE IN IR REGION AT 300 K

ν, cm^{-1}	λ, μm	Absorption Coefficient, cm^{-1}	
		Intrinsic*	Observed† (Selected)
6.000E+02	16.7	3.2E+1	
7.000E+02	14.3	9.1E+0	7.4E+0
8.000E+02	12.5	2.6E+0	2.7E+0
9.000E+02	11.1	7.3E-1	8.0E-1
9.434E+02	10.6	4.2E-1	5.5E-1
1.000E+03	10.0	2.1E-1	
1.075E+03	9.30	8.1E-2	2.7E-1
1.100E+03	9.09	5.9E-2	4.6E-2
1.200E+03	8.33	1.6E-2	
1.300E+03	7.69	4.8E-3	4.8E-3
1.400E+03	7.14	1.3E-3	1.4E-3
1.500E+03	6.67	3.9E-4	
1.600E+03	6.25	1.1E-4	
1.700E+03	5.88	3.1E-5	
1.800E+03	5.56	8.9E-6	
1.887E+03	5.30	3.0E-6	
1.900E+03	5.26	2.5E-6	
2.000E+03	5.00	7.2E-7	
2.100E+03	4.76	2.0E-7	
2.200E+03	4.55	5.8E-8	
2.300E+03	4.35	1.6E-8	
2.400E+03	4.17	4.7E-9	
2.500E+03	4.00	1.3E-9	
2.600E+03	3.85	3.8E-10	
2.632E+03	3.80	2.5E-10	

*Intrinsic values were calculated according to Eq. (26) with uncertainties about ±10%.

†Values in this column are the total absorption coefficient which are either lowest reported or those used to define the constants in Eq. (26). Uncertainties of these values are about ±10%.

3.3. Sodium Chloride, NaCl

Pure rock salt is uniformly transparent from 0.2 μm in the ultraviolet to 12 μm in the infrared. In the region of 15 μm the absorption increases rapidly. Rock salt, in moderately thin pieces, may be expected to transmit several percent of the light up to wavelengths as long as 26.0 μm. However, a plate 1 cm in thickness is completely opaque to radiation of wavelengths greater than 20 μm.

Rock salt has long been a favorite material for infrared spectroscopy. It polishes easily and, although hygroscopic, it can be protected by evaporated plastic coatings on its surfaces. It shows excellent dispersion over its entire transmission range. It has been difficult, however, to obtain natural rock salt crystals of sufficient size and purity for making optical components. As crystal-growing techniques advanced, synthetic sodium chloride crystals have been grown commercially up to 30 inch diameter and half-ton in weight, making this material readily available for large optical parts and thus stimulating the design and construction of infrared instruments.

Measurement of the refractive index of sodium chloride dates back to 1871, when Stefan [86] determined the refractive indices of a rock salt prism for solar lines B, D, and F. Since then, a large amount of data in the transparent region has been contributed by a number of investigators, among them are Martens [87], Paschen [88], and Langley [89]. They used either the deviation method or interferometry in their experiments. It was not until 1929 that measurements were carried out beyond the transparent region in the infrared. Kellner [90] determined refractive indices of NaCl in the 23-35 μm region, based on information on transmission and reflection of thin specimens. In the vacuum ultraviolet region, Rossler and Walker [91] observed the region from 0.0476 to 0.2480 μm, and Miyata and Tomiki [92] studied from 0.10 to 0.25 μm. Data on the refractive index are now available from 0.0476 μm up to 300 μm and at 2000 μm. It was found that refractive index data in the transparent regions for colorless natural rock salt are in close agreement with those for synthetic sodium chloride crystal with discrepancies occurring in the third decimal place.

Li [33] reduced the then available experimental data on the refractive index to a common temperature of 293 K and after careful critical evaluation and analysis adopted a Sellmeier type dispersion equation to evaluate the refractive index at 293 K in the wavelength range 0.20-30.0 μm:

$$n^2 = 1.00055 + \frac{0.19800\ \lambda^2}{\lambda^2-(0.050)^2} + \frac{0.48398\ \lambda^2}{\lambda^2-(0.100)^2} + \frac{0.38696\ \lambda^2}{\lambda^2-(0.128)^2} + \frac{0.25998\ \lambda^2}{\lambda^2-(0.158)^2}$$

$$+ \frac{0.08796\ \lambda^2}{\lambda^2-(40.50)^2} + \frac{3.17064\ \lambda^2}{\lambda^2-(60.98)^2} + \frac{0.30038\ \lambda^2}{\lambda^2-(120.34)^2} \qquad (27)$$

where λ is in units of μm.

Investigations of absorption coefficient for practical applications are generally classified into three wavelength regions: the ultraviolet and the infrared limits of the transparent region and the transparent regions. In the ultraviolet side, the purposes of the studies were to investigate the exciton states in the crystal and to determine the Urbach-rule parameters. Roessler and Walker [91] determined the absorption index of NaCl in the spectral range from 0.047 to 0.248 μm by a Kramers-Kronig analysis of reflection spectrum. Evidenced by the strong temperature dependence of reflectivity in the exciton region and the appearance of spin-orbit split doublets, the surfaces of the specimen examined were believed to be near perfect. Kobayashi and Tomiki [93] studied the effects of impurities on the absorption coefficient and found significant differences between crystals in the spectral range from 0.171 to 0.231 μm. The main soruces of such discrepancies were the presence of hydroxyl ions and dislocations in the crystals. Miyata and Tomiki [94] and Tomiki et al. [77] studied the absorption of NaCl in the region 0.156 to 0.205 μm for the purpose of determining the Urbach-rule parameters and finding the features characteristic of the intrinsic tail. Through a systematic observation and analysis they found the following empirical relations among certain parameters:

$E_o = 8.025$ eV

$\alpha_o = 1.2 \times 10^{10}\ cm^{-1}$

$hf = 9.5$ meV

$\sigma_{so} = 0.741$

for the expression of absorption coefficient of the intrinsic tail

$$\alpha(E,T) = \alpha_o \exp\left[-\sigma_s(T)\ (E_o-E)/kT\right]$$

where

$$\sigma_s(T) = \sigma_{so} \frac{2kT}{hf} \tanh \frac{hf}{2kT} \qquad (28)$$

Measurements of absorption coefficient at the infrared side were made for the purpose of studying the optically active lattice vibrations. On the short wavelength side of the reststrahl band, where a photon is absorbed and two or more phonons are generated, multiphonon absorption can occur and lead to absorption coefficients that range from 10^{-3} cm^{-1} to 100 cm^{-1}, depending on the number of phonons generated.

Measurements of the absorption coefficient in the transparent region are relatively recent events as the development of high-power IR lasers has led to a need for better characterization of IR window materials. Among other things, the absorption coefficient plays a decisive role in determining whether a material is adequate for laser optical components. For this reason, absorption coefficients of a number of selected materials were investigated at wavelengths of laser interest. Sodium chloride is among the candidate laser window materials and its absorption coefficients at wavelengths 1.06, 2.7, 3.8, 5.3, and 10.6 μm were intensively studied in order to determine the influencing factors that contribute to the extrinsic absorption. These studies are very informative and provide clues and means for material preparation and parts fabrication in order to minimize the extrinsic components in the absorption. Califano and Czerny [95] examined the region, 11-14 μm, at room temperature. Barker [38] measured the region, 11-20 μm, at temperatures from 300 K up to 1105 K, 31 degrees beyond the melting temperature of NaCl. Harrigan and Rudko [96] obtained the 10.6 μm absorption coefficient, 1.3×10^{-3} cm^{-1}, for NaCl by a CO_2 laser calorimetric method. This value was believed intrinsic, as evidenced by the fact that no noticeable improvement could be obtained by improvements in purity and growth techniques.

Deutsch [12], using a differential technique with a dual beam spectrometer measured the absorption coefficient for the wavelength range from 11.7 to 20 μm, at room temperature. Together with data from earlier investigations, it was found that the absorption coefficient in the multiphonon absorption region can be represented by the expression

$$\alpha = \alpha_o \exp(-\nu/\nu_o) \tag{29}$$

where $\nu_o = 56.0$ cm^{-1}, and $\alpha_o = 2.4273 \times 10^4$ cm^{-1}. This relation covers the ranges of $\alpha = 0.001$ to 44 cm^{-1} and $\lambda = 10.6$ to 28.1 μm. It is not known if the exponential relations hold for the lower wavelength regions. If they do, the extrapolated values at 5.3 μm should be 6×10^{-10}.

Harrington and Hass [78] studied the temperature dependence of multiphonon absorption at a wavelength of 10.6 μm, from room temperature to near the melting point, by the calorimetric method. It was observed that the absorption coefficient increases monotonically with temperature as it would be anticipated for the near-intrinsic absorption of the crystal. Based on their high temperature (above 450 K) results, the extrapolated value at 300 K is in close agreement with that of Horrigan and Rudko [96]. However, their experimental values in the range below 450 K are considerably higher than the extrapolated values. Their value at 300 K is 2.8×10^{-3} cm^{-1}, apparently higher than 1.3×10^{-3} cm^{-1} reported by Horrigan and Rudko. This situation is quite similar to the case of KCl whose 10.6 μm absorption is complicated by the existence of a surface absorption band at 9.5 μm. The only difference between NaCl and KCl is that the intrinsic absorption of NaCl is about 2 to 3 orders of magnitude higher than that of KCl while the value of surface absorption observed in the case of KCl is about one order of magnitude higher. As a result, contribution from surface absorption dominates the 10.6 μm absorption of KCl, whereas the reverse is true in the case of NaCl for a surface absorption of similar magnitude and spectral location.

Hass et al. [97] used an improved laser calorimetric technique in the determination of the 1.06 μm absorption coefficient for NaCl. The observation of the temperature-time curve (thermal rise curve) indicated that the slope of the curve during the lasing duration is constant and corresponds to an absorption coefficient of 7×10^{-6} cm^{-1}, which is the lowest value of absorption coefficient reported so far for a crystalline material. In this technique, if the slope varies with time, the initial slope of the curve corresponds to the bulk absorption. With elapsed time, surface absorptions and other contributions are revealed as evidenced by an increase in the slope.

Allen and Harrington [98] measured the total absorption coefficients at infrared laser wavelengths of 2.8, 3.8, 5.3, 9.27, and 10.6 μm, using the calorimetric method. The samples, cut from a given boule, were reactive-atmosphere-processed single crystals. It was found that samples of higher purity exhibit lower absorption. Although all samples indicated essentially intrinsic absorption at 10.6 μm, absorption at other wavelengths were considerably higher than the intrinsics. Such excess absorption are mainly due to surface absorption and chemical impurities, which play an important role at low intrinsic levels.

At 3.8 μm, Rosenstock et al. [99] studied samples procured from a wide variety of sources and found that the bulk absorption coefficient was 9×10^{-4} cm^{-1} and the surface absorption 4×10^{-2} cm^{-1}. Rowe and Harrington [100] studied the temperature dependence of absorption coefficient at 10.6 μm, in the temperature range from 100 to 300 K. Combined with the results of Harrington and Hass [78], they found that the multiphonon theory of McGill and Winston [111] adequately fit the experimental data.

Figures 15 to 18 are plots of the available data. The pertinent information of each data set and the corresponding original values are given in Tables 23 to 26. In addition, available information and data on the reflectivity and transmission are also presented in the same manner (in Figures 19 and 20 and Tables 27 to 30) for completeness and comparison. For the visible and near visible regions, Table 31 gives the spectral positions of the well-known color centers. Noticeable absorptions are likely to occur at these centers when the crystal is exposed to ultraviolet, x-ray, or high energy radiation. However, these absorption bands may disappear at high temperature or by appropriate radiation exposure, resulting from the so-called "thermal and optical beaching."

Recommended room-temperature values given in Table 32 were calculated according to Eq. (29). In the range between 11 to 23 μm, these values are supported by measurements of Califano et al. [95] and Barker [38]. It appears that NaCl has high intrinsic absorption in this region. If Eq. (29) holds in the region <5 μm, the intrinsic absorptions in this region are lower than 10^{-4} cm. However, like most of optical crystals, one expects to observe an absorption band in the range between 2.6 to 2.8 μm due to the hydroxyl ions in the crystal. This absorption band can be reduced or eliminated through improved crystal growing techniques. It should be noted that the values in the "intrinsic" column are the lowest limits that one can obtain for ideal samples. In practice, the observed values are generally higher than the limiting values at low absorption levels. Unless values appear in the "observed" column, the limiting values are considered as guidelines for estimation and investigation.

Although it was not the intention of this study to compile and evaluate the absorption data in the vacuum ultraviolet region, in order to assist users to obtain a total picture of the available absorption data, a plot of available data in this region is given in the Appendix of this report.



Figure 15. Absorption Coefficient of Sodium Chloride (Wavenumber Dependence)



Figure 16. Absorption Coefficient of Sodium Chloride in the Urbach Tail Region



Figure 17. Absorption Coefficient of Sodium Chloride in the Multiphonon Region

TABLE 23. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF SODIUM CHLORIDE (Wavenumber Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	91	Roessler, D.M. and Walker, W.C.	1968	R	5.64×10^{4}-2.1×10^{5}	300	Single crystal; obtained from the Harshaw Chemical Co. or the Westinghouse Electric Corp.; absorption coefficients derived from a Kramers-Kronig analysis of the near normal reflection spectra; data extracted from a table.
2	101	Czerny, M.	1930	T	2.1×10^{2}-2.9×10^{2}	293	Crystal; plate specimens of thicknesses 8, 14, 19, 24 mm; transmittances measured; absorption coefficients deduce from the exponential decay relation; data extracted from a table; temperature not given, 293 K assumed.
3	101	Czerny, M.	1930	T	6.5×10^{1}-1.54×10^{2}	293	Similar to above except for specimens of various thicknesses from 20 to 385 mm.
4	102	Cartwright, C.H. and Czerny, M.	1934	Z	9.3×10^{1}-1.36×10^{2}	293	Crystal; thin plate specimen of 60 mm; absorption coefficients deduced from transmittance and thickness measurements; data extracted from a figure.
5	102	Cartwright, C.H. and Czerny, M.	1934	Z	55.7,69.3	293	Similar to above except for specimen of 97 mm thick.
6	102	Cartwright, C.H. Czerny, M.	1934	Z	4.53×10^{1}-1.37×10^{2}	293	Similar to above except for specimen of 147 mm thick.
7	102	Cartwright, C.H. and Czerny, M.	1934	Z	44.7-78.0	293	Similar to above except for specimen of 237 mm thick.
8	102	Cartwright, C.H. and Czerny, M.	1934	Z	42.8-52.5	293	Similar to above except for specimen of 380 mm thick.
9	95	Califano, S. and Czerny, M.	1958	T	7.14×10^{2}-9.1×10^{2}	293	Crystal; block specimens of 10.52 and 16.77 cm; extinction coefficients determined from transmittance measurements; data extracted from a figure.
10	38	Barker, A.J.	1972	R	4.4×10^{2}-7.0×10^{2}	300	Synthetic crystal; high purity; highly polished specimen of 1-2 mm thick; absorption coefficients deduced from measurements of reflectivity; absorption-coefficient data extracted from a figure.
11	38	Barker, A.J.	1972	R	5.1×10^{2}-7.4×10^{2}	615	Similar to above except at a higher temperature.
12	38	Barker, A.J.	1972	R	5.2×10^{2}-7.7×10^{2}	775	Similar to above except at a higher temperature.
13	38	Barker, A.J.	1972	R	5.4×10^{2}-8.1×10^{2}	935	Similar to above except at a higher temperature.
14	38	Barker, A.J.	1972	R	5.6×10^{2}-8.6×10^{2}	1105	Molten NaCl specimen of 1-2 mm thick; reflectivity measurements carried out in a largely inert gas atmosphere; absorption coefficients deduced from reflection spectra; absorption-coefficient data extracted from a figure; melting temperature of NaCl is 1074 K.

TABLE 23. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF SODIUM CHLORIDE (Wavenumber Dependence) (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
15	12	Deutsch, T.F.	1973	T	5.0×10^{2}~8.5×10^{2}	300	Single crystal; obtained from Optovac Co.; specimen of 2.54 cm diameter and 2.54 cm thick; absorption coefficient determined using a differential technique with a dual-beam spectrophotometer; data extracted from a figure.
16	77	Tomiki, T., Miyata, T., and Tsukamoto, H.	1974	R	6.37×10^{4}~6.50×10^{4}	10	Single crystal; obtained from the Harshaw Chemical Co.; absorption coefficients deduced from reflection spectra; data extracted from a figure.
17	103	Ikezawa, M. and	1973	R	9.3×10^{1}~1.6×10^{2}	1.8	Single crystal; grown from pure synthesized powders distilled in vacuum and zoned refined in a quartz tube in chlorine gas; cleaved; geometry not specified; data taken from a curve.
18	42	Owens, J.	1969	T	0.31~4.0	298	Single crystal; obtained from the Harshaw Chemical Co.; cylinder shaped specimen; filled resonant cavity method used for measuring dielectric constant and loss tangent; absorption coefficient then determined; data extracted from a figure.
19	93	Kobayashi, K. and Tomiki, T.	1960	R	4.3×10^{4}~5.83×10^{4}	285	Single crystal; grown by vacuum distillation; cleaved specimens of 0.06-1.0 mm thick; absorption coefficients measured with a vacuum ultraviolet spectrophotometer; data extracted from a figure.
20	97	Hass, M., Davison, J.W., Rosenstock, H.B. and Babiskin, J.	1975	C	9434	298	Single crystal; obtained from the Harshaw Chemical Co.; rectangular parallelepiped specimen of 1.2 cm x 1.3 cm x 10.3 cm; laser calorimetric method used and the thermal rise curve obtained; bulk absorption coefficient determined from the initial slope of the curve.
21	98	Allen, S.D. and Harrington, J.A.	1978	C	943.4,1079	298	Single crystal; produced by reactive-atmosphere-process; samples sectioned from a given boule; calorimetric method used and total absorption determined; data extracted from a table.
22	98	Allen, S.D. and Harrington, J.A.	1978	C	943.4-3571	298	Same as above but for a sample from other section of the boule.
23	98	Allen, S.D. and Harrington, J.A.	1978	C	943.4,1079	298	Same as above.
24	98	Allen, S.D. and Harrington, J.A.	1978	C	943.4-3571	298	Same as above.
25	104	Harrington, J.A., Buhler, C.J., Patten, F.W. and Hass, M.	1976	C	449-879	300	Single crystal; obtained from the Harshaw Chemical Co.; experimental details not given; data extracted from a figure.
26	104	Harrington, J.A. et al.	1976	C	411-713	80	Same as above.

TABLE 23. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF SODIUM CHLORIDE (Wavenumber Dependence) (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
27	94	Miyata, T. and Tomiki, T.	1967	Z	6.07×10^4-6.36×10^4	10	Single crystal; obtained from the Harshaw Chemical Co. and also prepared by a chemical reaction and purified by vacuum distillation and followed by zone melting in chlorine atmosphere; specimens cleaved from ingots zone refined many cycles; dimension of specimen 5 mm x 10 mm x 0.2-4 mm; thinner specimens of ~0.08 mm prepared by melting and pressing small pieces zone refined crystals between two parallel glassy carbon plates in vacuum; transmission and reflection measured with uv spectrophotometer; absorption coefficients then deduced; data extracted from a figure.
28	94	Miyata, T. and Tomiki, T.	1967	Z	5.10×10^4-6.36×10^4	18	Same as above.
29	94	Miyata, T. and Tomiki, T.	1967	Z	5.87×10^4-6.33×10^4	70	Same as above.
30	94	Miyata, T. and Tomiki, T.	1967	Z	4.96×10^4-6.12×10^4	95	Same as above.
31	94	Miyata, T. and Tomiki, T.	1967	Z	5.58×10^4-6.30×10^4	95	Same as above.
32	94	Miyata, T. and Tomiki, T.	1967	Z	5.99×10^4-6.13×10^4	195	Same as above.
33	94	Miyata, T. and Tomiki, T.	1967	Z	5.64×10^4-5.98×10^4	298	Same as above.
34	94	Miyata, T. and Tomiki, T.	1967	Z	4.95×10^4-5.99×10^4	298	Same as above.
35	94	Miyata, T. and Tomiki, T.	1967	Z	5.39×10^4-5.74×10^4	473	Same as above.
36	94	Miyata, T. and Tomiki, T.	1967	Z	4.84×10^4-5.74×10^4	473	Same as above.
37	94	Miyata, T. and Tomiki, T.	1967	Z	5.19×10^4-5.60×10^4	573	Same as above.
38	94	Miyata, T. and Tomiki, T.	1967	Z	4.83×10^4-5.60×10^4	573	Same as above.
39	23	Gensel, L., Happ, H., and Weber, R.	1959	T	3.2-33	298	Crystal; plane parallel plate specimens of 1.07, 2.10, 5.0, and 47.5 mm thick; transmission measured and absorption coefficient determined; data extracted from a figure.
40	105	Geick, R.	1962	Z	149-181	298	Evaporated NaCl film of 10 μm thick; samples put in desiccator for 4 weeks before use; absorption coefficient determined from reflectivity and transmission measurements; data extracted from a figure.

TABLE 23. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF SODIUM CHLORIDE (Wavenumber Dependence) (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
41	105	Geick, R.	1962	Z	60-143	298	Similar to above except for thin specimen shaved from the bulk.
42	106	Cartwright, C.H. and Czerny, M.	1933	Z	83-143	298	Natural NaCl crystal; thin plate specimens of 21.5 to 147 μm thick; absorption coefficients determined from the transmission measurement; data extracted from a table.
43	107	Dötsch, H. and Happ, H.	1964	T	3.2-11	300	Single crystal; plate specimen of 150 mm thick; absorption coefficient determined from transmission measurements; data extracted from a figure.
44	107	Dötsch, H. and Happ, H.	1964	T	3.3-8.2	360	Same as above.
45	107	Dötsch, H. and Happ, H.	1964	T	3.3-8.2	280	Same as above.
46	107	Dötsch, H. and Happ, H.	1964	T	3.3-8.2	200	Same as above.
47	107	Dötsch, H. and Happ, H.	1964	T	3.3-8.2	120	Same as above.
48	107	Dötsch, H. and Happ, H.	1964	T	3.3-8.2	80	Same as above.
49	108	Dianov, E.M. and Irisova, N.A.	1966	T	5	298	Natural crystal; plate specimens of 12 and 18 mm thick; absorption coefficient determined from transmission measurement; data extracted from a table.
50	99	Rosenstock, H.B., Gregory, D.A., and Harrington, J.A.	1976	C	2631.6	298	Single crystals; obtained from the Naval Research Lab., the Harshaw Chemical Co., and the Raytheon Corp.; mechanically polished and chemically cleaned with spectrograde CCl_4; laser calorimetric method used; data extracted from a table; it was found that the surface absorption was about 45 times higher than the bulk absorption.

TABLE 24. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF SODIUM CHLORIDE (Wavenumber Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

ν	α
DATA SET 1	
T = 293.0	
2.197E+5	3.352E+5
2.095E+5	4.411E+5
2.048E+5	4.376E+5
2.032E+5	4.937E+5
[illegible]	4.995E+5
[illegible]	4.944E+5
[illegible]	[illegible]
1.944E+5	5.373E+5
1.935E+5	5.614E+5
1.927E+5	5.571E+5
[illegible]	[illegible]
1.907E+5	5.971E+5
1.919E+5	5.739E+5
1.997E+5	5.464E+5
1.974E+5	5.119E+5
1.971E+5	4.937E+5
1.943E+5	[illegible]
1.917E+5	4.919E+5
1.831E+5	5.314E+5
1.815E+5	6.157E+5
1.861E+5	6.355E+5
1.740E+5	6.994E+5
1.731E+5	6.7[illegible]E+5
1.774E+5	6.512E+5
1.766E+5	7.1[illegible]E+5
1.739E+5	7.071E+5
1.734E+5	6.872E+5
1.702E+5	6.021E+5
1.695E+5	6.354E+5
1.677E+5	6.324E+5
1.651E+5	6.263E+5
1.633E+5	[illegible]
1.625E+5	6.7[illegible]E+5
1.621E+5	0.722E+5
1.613E+5	0.841E+5
1.605E+5	0.857E+5
1.597E+5	0.822E+5

ν	α
DATA SET 1(CONT.)	
1.581E+5	6.350E+5
1.573E+5	6.120E+5
1.565E+5	5.990E+5
1.556E+5	6.072E+5
1.548E+5	6.043E+5
1.540E+5	5.467E+5
1.532E+5	6.321E+5
1.524E+5	6.479E+5
1.516E+5	6.533E+5
1.508E+5	6.597E+5
1.492E+5	6.502E+5
1.476E+5	6.520E+5
1.460E+5	6.387E+5
1.452E+5	[illegible]
1.427E+5	5.919E+5
1.412E+5	5.552E+5
1.395E+5	5.902E+5
1.373E+5	6.239E+5
1.371E+5	6.374E+5
1.363E+5	6.563E+5
1.355E+5	6.471E+5
1.347E+5	6.432E+5
1.331E+5	6.394E+5
1.323E+5	6.482E+5
1.315E+5	6.617E+5
1.307E+5	6.598E+5
1.299E+5	7.1[illegible]E+5
1.291E+5	7.346E+5
1.283E+5	7.595E+5
1.266E+5	8.433E+5
1.259E+5	8.954E+5
1.242E+5	9.2[illegible]E+5
1.234E+5	9.313E+5
1.226E+5	9.[illegible]E+5
1.209E+5	1.012E+6
1.194E+5	1.055E+6
1.135E+5	1.117E+6
1.131E+5	1.143E+6
1.177E+5	1.154E+6
1.173E+5	1.165E+6

ν	α
DATA SET 1(CONT.)	
1.169E+5	1.176E+6
1.165E+5	1.186E+6
1.161E+5	1.197E+6
1.153E+5	1.217E+6
1.149E+5	1.223E+6
1.145E+5	1.235E+6
1.137E+5	1.257E+6
1.129E+5	1.263E+6
1.121E+5	1.269E+6
1.113E+5	1.259E+6
1.105E+5	1.235E+6
1.089E+5	1.163E+6
1.073E+5	1.192E+6
1.057E+5	9.824E+5
1.048E+5	9.354E+5
1.044E+5	9.137E+5
1.036E+5	9.151E+5
1.030E+5	9.246E+5
1.024E+5	9.211E+5
1.020E+5	9.053E+5
1.016E+5	1.034E+6
1.012E+5	1.069E+6
1.004E+5	1.064E+6
1.000E+5	1.083E+6
9.96E+4	1.064E+6
9.919E+4	1.060E+6
9.839E+4	1.026E+6
9.759E+4	9.687E+5
9.677E+4	9.672E+5
9.597E+4	9.527E+5
9.516E+4	9.567E+5
9.435E+4	1.020E+6
9.395E+4	1.051E+6
9.355E+4	1.109E+6
9.315E+4	1.241E+6
9.274E+4	1.329E+6
9.234E+4	1.381E+6
9.194E+4	1.398E+6
9.153E+4	1.415E+6
9.113E+4	1.397E+6

ν	α
DATA SET 1(CONT.)	
9.073E+4	1.357E+6
9.032E+4	1.365E+6
8.952E+4	1.170E+6
8.871E+4	1.037E+6
8.791E+4	8.610E+5
8.543E+4	6.116E+5
8.453E+4	5.842E+5
8.427E+4	5.719E+5
8.387E+4	5.962E+5
8.347E+4	6.186E+5
8.135E+4	7.201E+5
8.124E+4	7.207E+5
8.113E+4	7.236E+5
8.092E+4	7.195E+5
7.942E+4	6.910E+5
7.791E+4	6.192E+5
7.419E+4	5.874E+5
7.258E+4	5.472E+5
7.177E+4	5.321E+5
7.097E+4	5.351E+5
7.036E+4	5.232E+5
7.016E+4	5.262E+5
6.936E+4	5.055E+5
6.855E+4	4.990E+5
6.815E+4	4.967E+5
6.774E+4	4.937E+5
6.734E+4	4.925E+5
6.694E+4	4.879E+5
6.653E+4	4.849E+5
6.613E+4	4.956E+5
6.573E+4	5.309E+5
6.532E+4	6.074E+5
6.512E+4	6.591E+5
6.492E+4	7.261E+5
6.476E+4	8.056E+5
6.452E+4	8.916E+5
6.435E+4	9.543E+5
6.411E+4	1.039E+6
6.395E+4	1.093E+6

ν	α
DATA SET 1(CONT.)	
6.371E+4	1.145E+6
6.355E+4	1.166E+6
6.331E+4	1.195E+6
6.315E+4	1.182E+6
6.290E+4	1.118E+6
6.274E+4	1.112E+6
6.250E+4	1.045E+6
6.234E+4	9.871E+5
6.210E+4	8.193E+5
6.109E+4	4.574E+5
6.129E+4	2.098E+5
6.089E+4	2.000E+5
6.048E+4	1.672E+5
6.008E+4	1.359E+5
5.968E+4	1.125E+5
5.887E+4	6.658E+4
5.806E+4	3.048E+4
5.645E+4	7.094E+3
DATA SET 2	
T = 293.0	
2.857E+2	6.164E+2
2.773E+2	7.079E+2
2.743E+2	1.155E+3
2.632E+2	1.053E+3
2.564E+2	1.933E+3
2.534E+2	2.352E+3
2.439E+2	2.145E+3
2.326E+2	2.484E+3
2.174E+2	3.190E+3
DATA SET 3	
T = 293.0	
1.531E+2	5.966E+2
1.422E+2	4.469E+2
1.364E+2	1.337E+2
6.579E+1	5.291E+1

ν	α
DATA SET 4	
T = 293.0	
1.5[illegible]E+2	2.234E+2
1.292E+2	1.793E+2
1.[illegible]9E+2	1.499E+2
1.095E+2	1.275E+2
9.097E+1	1.[illegible]7E+2
9.333E+1	8.465E+1
DATA SET 5	
T = 293.0	
6.933E+1	5.713E+1
5.674E+1	4.354E+1
DATA SET 6	
T = 293.0	
1.366E+2	2.[illegible]1E+2
1.34[illegible]E+2	2.134E+2
1.3[illegible]E+2	2.[illegible]7E+2
1.257E+2	2.[illegible]1E+2
1.2[illegible]E+2	1.[illegible]7E+2
1.2[illegible]E+2	1.597E+2
1.2[illegible]E+2	1.5[illegible]E+2
1.[illegible]E+2	1.4[illegible]E+2
1.27[illegible]E+2	1.27[illegible]E+2
1.[illegible]7E+2	1.[illegible]7E+2
1.[illegible]E+2	1.237E+2
1.[illegible]E+2	1.23[illegible]E+2
1.[illegible]E+2	9.452E+1
5.591E+1	9.7[illegible]E+1
9.329E+1	9.19[illegible]E+1
8.[illegible]E+1	9.147E+1
8.313E+1	8.[illegible]E+1
7.91[illegible]E+1	7.[illegible]E+1
7.822E+1	6.27[illegible]E+1
6.177E+1	5.231E+1
5.97[illegible]E+1	4.[illegible]E+1
5.[illegible]0E+1	3.87E+1
4.[illegible]E+1	2.410E+1

TABLE 24. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF SODIUM CHLORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 7	
T = 293.0	
7.794E+1	7.355E+1
6.459E+1	6.025E+1
5.155E+1	5.002E+1
5.512E+1	7.693E+1
4.964E+1	3.391E+1
4.478E+1	2.715E+1
DATA SET 8	
T = 293.0	
5.244E+1	3.796E+1
4.793E+1	3.375E+1
4.286E+1	2.111E+1
DATA SET 9	
T = 293.0	
9.912E+2	1.771E-3
8.396E+2	8.935E-3
7.759E+2	2.605E-2
7.143E+2	8.908E-2
DATA SET 10	
T = 300.0	
6.970E+2	1.106E-1
6.650E+2	2.[illegible]E-1
6.366E+2	3.500E-1
6.030E+2	6.[illegible]E-1
5.840E+2	9.000E-1
5.440E+2	1.[illegible]E+0
5.[illegible]E+2	1.[illegible]E+0
5.432E+2	1.7[illegible]E+0
5.2[illegible]E+2	2.[illegible]E+0
5.190E+2	2.97E+0
5.[illegible]E+2	3.[illegible]E+0
4.5[illegible]E+2	4.[illegible]E+0
4.6[illegible]E+2	4.[illegible]E+0
4.750E+2	5.2[illegible]E+0
4.630E+2	6.21E+0

ν	α
DATA SET 10 (CONT.)	
4.550E+2	7.240E+0
4.440E+2	8.630E+0
DATA SET 11	
T = 625.0	
7.370E+2	1.500E-1
7.050E+2	2.860E-1
6.760E+2	5.130E-1
6.550E+2	7.610E-1
6.300E+2	1.[illegible]E+0
6.100E+2	1.500E+0
5.950E+2	2.190E+0
5.740E+2	2.360E+0
5.640E+2	3.560E+0
5.530E+2	4.200E+0
5.440E+2	4.940E+0
5.340E+2	5.790E+0
5.230E+2	6.890E+0
5.120E+2	8.390E+0
DATA SET 12	
T = 775.0	
7.050E+2	2.000E-1
7.300E+2	3.200E-1
7.000E+2	5.100E-1
6.700E+2	8.400E-1
6.500E+2	1.150E+0
6.350E+2	1.[illegible]E+0
6.270E+2	2.200E+0
5.940E+2	3.690E+0
5.440E+2	3.540E+0
5.750E+2	4.160E+0
5.040E+2	4.830E+0
5.550E+2	5.820E+0
5.450E+2	6.950E+0
5.330E+2	8.280E+0
5.250E+2	9.420E+0

ν	α
DATA SET 13	
T = 935.0	
8.070E+2	1.000E-1
7.700E+2	2.000E-1
7.400E+2	4.300E-1
7.160E+2	6.700E-1
6.800E+2	1.060E+0
6.670E+2	1.410E+0
6.470E+2	1.840E+0
6.260E+2	2.510E+0
6.000E+2	3.230E+0
5.990E+2	3.960E+0
5.840E+2	4.590E+0
5.740E+2	5.330E+0
5.640E+2	6.320E+0
5.550E+2	7.450E+0
5.430E+2	9.060E+0
DATA SET 14	
T = 1105.0	
8.570E+2	1.400E-1
8.260E+2	2.100E-1
7.970E+2	3.100E-1
7.650E+2	5.100E-1
7.370E+2	7.600E-1
7.000E+2	1.120E+0
6.870E+2	1.510E+0
6.670E+2	2.030E+0
6.470E+2	2.730E+0
6.260E+2	3.690E+0
6.050E+2	4.790E+0
5.950E+2	5.850E+0
5.860E+2	6.080E+0
5.740E+2	7.830E+0
5.640E+2	9.510E+0
DATA SET 15	
T = 300.0	
8.511E+2	4.600E-3

ν	α
DATA SET 15 (CONT.)	
8.700E+2	1.400E-2
7.500E+2	4.190E-2
6.930E+2	1.091E-1
6.510E+2	2.741E-1
6.120E+2	5.700E-1
5.510E+2	1.294E+0
5.010E+2	2.500E+0
DATA SET 16	
T = 1100.0	
6.432E+4	1.040E+6
6.409E+4	9.880E+5
6.459E+4	1.199E+6
6.447E+4	1.056E+6
6.435E+4	2.244E+6
6.425E+4	2.773E+6
6.411E+4	8.185E+5
6.400E+4	3.236E+5
6.398E+4	1.766E+5
6.384E+4	3.420E+4
6.378E+4	1.722E+4
DATA SET 17	
T = 1.8	
1.600E+2	1.001E+1
1.590E+2	6.067E+0
1.570E+2	5.463E+0
1.550E+2	5.035E+0
1.530E+2	3.396E+0
1.510E+2	2.838E+0
1.500E+2	2.754E+0
1.490E+2	2.773E+0
1.480E+2	2.651E+0
1.460E+2	3.192E+0
1.450E+2	3.214E+0
1.440E+2	3.090E+0
1.380E+2	1.429E+0
1.370E+2	1.327E+0

ν	α
DATA SET 17 (CONT.)	
1.300E+2	1.219E+0
1.350E+2	8.492E-1
1.340E+2	7.883E-1
1.330E+2	7.129E-1
1.320E+2	7.179E-1
1.290E+2	7.780E-1
1.270E+2	8.375E-1
1.250E+2	8.892E-1
1.240E+2	9.759E-1
1.230E+2	1.072E+0
1.220E+2	1.082E+0
1.200E+2	6.383E-1
1.190E+2	6.067E-1
1.180E+2	5.943E-1
1.170E+2	6.950E-1
1.160E+2	6.577E-1
1.150E+2	5.506E-1
1.145E+2	4.989E-1
1.100E+2	3.650E-1
1.090E+2	3.396E-1
1.080E+2	3.214E-1
1.070E+2	3.006E-1
1.030E+2	2.306E-1
1.000E+2	1.965E-1
9.300E+1	1.169E-1
DATA SET 18	
T = 298.0	
4.000E+0	2.138E-3
1.247E+0	5.916E-4
3.090E-1	1.432E-4
DATA SET 19	
T = 285.0	
5.331E+4	1.581E+1
5.819E+4	1.682E+1
5.798E+4	7.772E+0
5.782E+4	6.100E+0

ν	α
DATA SET 19 (CONT.)	
5.774E+4	4.812E+0
5.700E+4	3.034E+0
5.750E+4	3.520E+0
5.742E+4	3.050E+0
5.716E+4	2.630E+0
5.677E+4	2.000E+0
5.093E+4	2.000E+0
5.550E+4	1.490E+0
5.500E+4	1.090E+0
5.427E+4	1.500E+0
5.375E+4	1.200E+0
5.323E+4	1.200E+0
5.256E+4	1.030E+0
5.177E+4	1.130E+0
5.[illegible]E+4	9.000E-1
5.000E+4	7.000E-1
4.950E+4	6.700E-1
4.935E+4	6.700E-1
4.875E+4	4.900E-1
4.810E+4	4.500E-1
4.750E+4	4.000E-1
4.650E+4	4.100E-1
4.427E+4	3.100E-1
4.335E+4	1.300E-1
DATA SET 20	
T = 299.0	
9.430E+3	7.000E-6
DATA SET 21	
T = 298.0	
1.679E+3	2.000E-4
9.434E+2	1.000E-3
DATA SET 22	
T = 298.0	
3.572E+3	5.800E-5

TABLE 24. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF SODIUM CHLORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 22(CONT.)	
2.632E+3	5.300E-5
2.887E+3	5.100E-5
1.079E+3	3.000E-4
9.434E+2	1.000E-3
DATA SET 23	
T = 293.0	
1.079E+3	4.100E-4
9.434E+2	1.000E-3
DATA SET 24	
T = 293.0	
3.571E+3	6.900E-5
2.632E+3	6.500E-5
1.887E+3	3.400E-5
1.079E+3	8.000E-4
9.434E+2	1.400E-3
DATA SET 25	
T = 3.00	
4.490E+2	3.450E+0
4.790E+2	5.120E+0
4.990E+2	3.660E+0
5.190E+2	2.470E+0
5.490E+2	1.770E+0
5.570E+2	1.130E+0
5.790E+2	9.300E-1
5.990E+2	6.100E-1
6.150E+2	4.120E-1
6.390E+2	2.990E-1
6.590E+2	2.100E-1
6.790E+2	1.390E-1
6.990E+2	1.000E-1
7.190E+2	6.900E-2
7.370E+2	4.390E-2
7.570E+2	2.810E-2
7.760E+2	1.790E-2

ν	α
DATA SET 25(CONT.)	
7.960E+2	1.280E-2
8.150E+2	8.180E-3
8.350E+2	5.530E-3
8.590E+2	3.930E-3
8.790E+2	2.320E-3
DATA SET 26	
T = 3.0	
4.190E+2	3.250E+0
4.390E+2	2.330E+0
4.590E+2	1.760E+0
4.790E+2	1.260E+0
4.990E+2	1.010E+0
5.190E+2	7.600E-1
5.390E+2	6.080E-1
5.590E+2	4.850E-1
5.570E+2	3.470E-1
5.770E+2	2.930E-1
5.770E+2	2.220E-1
5.770E+2	1.770E-1
5.960E+2	1.590E-1
5.930E+2	1.010E-1
6.110E+2	1.070E-1
6.160E+2	8.110E-2
6.340E+2	6.470E-2
6.350E+2	4.130E-2
6.990E+2	4.020E-2
6.790E+2	3.700E-2
6.600E+2	2.360E-2
6.390E+2	2.230E-2
6.890E+2	1.080E-2
7.130E+2	1.210E-2
DATA SET 27	
T = 100	
6.073E+4	1.330E+0
6.137E+4	1.880E+0
6.145E+4	2.100E+0

ν	α
DATA SET 27(CONT.)	
6.161E+4	2.190E+0
6.169E+4	2.460E+0
6.202E+4	3.090E+0
6.218E+4	3.610E+0
6.234E+4	4.210E+0
6.242E+4	4.900E+0
6.258E+4	6.920E+0
6.282E+4	8.380E+0
6.282E+4	1.050E+1
6.298E+4	1.430E+1
6.315E+4	2.270E+1
6.323E+4	2.940E+1
6.331E+4	4.030E+1
6.347E+4	5.910E+1
6.355E+4	9.710E+1
DATA SET 28	
T = 18.	
5.145E+4	1.130E+0
5.129E+4	1.130E+0
5.185E+4	2.930E+0
5.331E+4	5.680E+0
5.387E+4	6.040E+0
5.597E+4	5.750E+0
5.045E+4	4.590E+0
5.743E+4	2.910E+0
5.758E+4	2.700E+0
5.806E+4	2.150E+0
5.855E+4	1.590E+0
5.879E+4	1.420E+0
6.000E+4	1.000E+0
6.081E+4	2.040E+0
6.092E+4	3.190E+0
6.121E+4	4.870E+0
6.177E+4	2.340E+0
6.218E+4	3.570E+0
6.200E+4	4.080E+0
5.337E+4	6.040E+0
5.589E+4	5.750E+0
5.645E+4	4.590E+0
6.234E+4	1.870E+1

ν	α
DATA SET 28(CONT.)	
6.266E+4	2.440E+1
6.292E+4	3.080E+1
6.319E+4	4.620E+1
6.339E+4	6.370E+1
6.355E+4	1.370E+2
DATA SET 29	
T = 70.0	
5.185E+4	3.740E+0
5.259E+4	3.000E+0
5.161E+4	3.090E+0
5.153E+4	3.330E+0
5.137E+4	2.860E+0
5.145E+4	2.050E+0
5.121E+4	2.450E+0
5.113E+4	2.450E+0
5.105E+4	2.100E+0
5.105E+4	1.990E+0
5.000E+4	9.620E-1
5.000E+4	9.020E-1
5.871E+4	5.250E-1
5.871E+4	3.450E-1
6.331E+4	1.720E+2
6.331E+4	1.270E+2
6.331E+4	1.090E+2
DATA SET 30	
T = 95.0	
4.900E+4	3.850E-1
4.900E+4	3.990E-1
5.073E+4	1.220E+0
5.129E+4	1.930E+0
5.177E+4	2.340E+0
5.218E+4	3.570E+0
5.200E+4	4.080E+0
5.337E+4	6.040E+0
5.589E+4	5.750E+0
5.645E+4	4.590E+0

ν	α
DATA SET 30(CONT.)	
5.742E+4	2.910E+0
5.758E+4	2.800E+0
5.798E+4	2.150E+0
5.855E+4	1.590E+0
5.479E+4	1.470E+0
6.000E+4	1.080E+0
6.073E+4	2.040E+0
6.081E+4	3.190E+0
6.121E+4	4.870E+0
DATA SET 31	
T = 95.0	
5.589E+4	5.750E+0
5.742E+4	3.990E+0
5.798E+4	3.270E+0
5.815E+4	3.150E+0
5.855E+4	2.930E+0
5.879E+4	2.720E+0
5.903E+4	2.430E+0
6.000E+4	2.260E+0
6.032E+4	2.260E+0
6.056E+4	2.440E+0
6.121E+4	5.900E+0
6.145E+4	7.720E+0
6.202E+4	1.000E+1
6.218E+4	1.370E+1
6.234E+4	2.530E+1
6.242E+4	2.840E+1
6.253E+4	3.310E+1
6.266E+4	4.020E+1
6.274E+4	5.050E+1
6.293E+4	8.970E+1
6.298E+4	9.090E+1
6.306E+4	1.650E+2
DATA SET 32	
T = 195.0	
5.992E+4	2.230E+0

ν	α
DATA SET 32(CONT.)	
6.000E+4	2.410E+0
6.000E+4	2.700E+0
6.010E+4	2.910E+0
6.032E+4	3.030E+0
6.040E+4	3.540E+0
6.040E+4	4.490E+0
6.060E+4	5.370E+0
6.052E+4	6.290E+0
6.073E+4	7.910E+0
6.081E+4	9.900E+0
6.093E+4	1.290E+1
6.097E+4	1.640E+1
6.113E+4	3.860E+1
6.133E+4	4.000E+1
6.121E+4	6.200E+1
6.129E+4	1.000E+2
DATA SET 33	
T = 295.0	
5.049E+4	1.330E-1
5.742E+4	3.030E-1
5.903E+4	1.000E+0
5.823E+4	1.500E+0
5.855E+4	5.350E+0
5.979E+4	1.690E+1
5.987E+4	1.900E+1
5.993E+4	2.300E+1
5.967E+4	4.540E+1
5.960E+4	1.490E+2
5.900E+4	1.070E+2
5.979E+4	2.270E+2
5.934E+4	2.850E+2
5.934E+4	3.330E+2
5.984E+4	4.290E+2

TABLE 24. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF SODIUM CHLORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 34	
T = 298.	
4.992E+4	1.21[illegible]E+0
4.952E+4	1.03[illegible]E+0
4.984E+4	1.3[illegible]E+0
5.012E+4	1.91[illegible]E+0
5.037E+4	2.42[illegible]E+0
5.145E+4	2.3[illegible]E+0
5.137E+4	3.42[illegible]E+0
5.194E+4	4.0[illegible]E+0
5.222E+4	4.5[illegible]E+0
5.252E+4	4.8[illegible]E+0
5.399E+4	5.74[illegible]E+0
5.444E+4	5.70[illegible]E+0
5.532E+4	5.37[illegible]E+0
5.556E+4	5.13[illegible]E+0
5.637E+4	4.8[illegible]E+0
5.653E+4	4.4[illegible]E+0
5.714E+4	3.70[illegible]E+0
5.742E+4	3.59[illegible]E+0
5.732E+4	3.47[illegible]E+0
5.739E+4	3.75[illegible]E+0
5.816E+4	4.72[illegible]E+0
5.855E+4	5.73[illegible]E+0
5.871E+4	1.2[illegible]E+1
5.879E+4	1.33[illegible]E+1
5.47[illegible]E+4	1.81[illegible]E+1
5.595E+4	2.65[illegible]E+1
5.927E+4	4.5[illegible]E+1
5.944E+4	7.47[illegible]E+1
5.9[illegible]E+4	1.49[illegible]E+2
5.960E+4	1.61[illegible]E+2
5.969E+4	2.13[illegible]E+2
5.954E+4	2.85[illegible]E+2
5.976E+4	3.59[illegible]E+2
5.992E+4	4.35[illegible]E+2
DATA SET 35	
T = 473.	
5.395E+4	2.06[illegible]E-1

ν	α
DATA SET 35(CONT.)	
5.444E+4	5.38[illegible]E-1
5.470E+4	1.10[illegible]E+0
5.532E+4	4.44[illegible]E+0
5.556E+4	7.0[illegible]E+0
5.597E+4	1.40[illegible]E+1
5.613E+4	1.91[illegible]E+1
5.621E+4	2.59[illegible]E+1
5.661E+4	5.38[illegible]E+1
5.653E+4	6.3[illegible]E+1
5.677E+4	8.20[illegible]E+1
5.694E+4	1.40[illegible]E+2
5.702E+4	1.51[illegible]E+2
5.742E+4	4.26[illegible]E+2
DATA SET 36	
T = 473.	
4.347E+4	9.46[illegible]E-1
4.47[illegible]E+4	9.46[illegible]E+0
4.927E+4	1.03[illegible]E+1
5.132E+4	3.42[illegible]E+0
5.137E+4	4.3[illegible]E+0
5.232E+4	5.69[illegible]E+0
5.395E+4	8.19[illegible]E+0
5.476E+4	8.[illegible]E+0
5.9[illegible]E+4	8.83[illegible]E+0
5.559E+4	1.16[illegible]E+1
5.583E+4	1.9[illegible]E+1
5.613E+4	2.8[illegible]E+1
5.653E+4	5.37[illegible]E+1
5.653E+4	8.[illegible]E+1
5.669E+4	8.19[illegible]E+1
5.685E+4	1.40[illegible]E+2
5.72[illegible]E+4	1.03[illegible]E+2
5.742E+4	4.1[illegible]E+2
DATA SET 37	
T = 573.	
5.194E+4	2.46[illegible]E-1

ν	α
DATA SET 37(CONT.)	
5.234E+4	3.61[illegible]E-1
5.274E+4	1.0[illegible]E+0
5.298E+4	1.28[illegible]E+0
5.339E+4	2.56[illegible]E+0
5.387E+4	8.4[illegible]E+0
5.444E+4	2.37[illegible]E+1
5.484E+4	4.38[illegible]E+1
5.532E+4	1.23[illegible]E+2
5.548E+4	1.68[illegible]E+2
5.597E+4	4.21[illegible]E+2
DATA SET 38	
T = 573.	
4.832E+4	1.24[illegible]E+0
4.847E+4	1.29[illegible]E+0
4.935E+4	2.65[illegible]E+0
5.032E+4	3.39[illegible]E+0
5.137E+4	4.47[illegible]E+0
5.252E+4	6.14[illegible]E+0
5.339E+4	8.65[illegible]E+0
5.387E+4	1.14[illegible]E+1
5.444E+4	2.56[illegible]E+1
5.4[illegible]E+4	4.38[illegible]E+1
5.484E+4	4.73[illegible]E+1
5.532E+4	1.23[illegible]E+2
5.55[illegible]E+4	1.68[illegible]E+2
5.597E+4	4.06[illegible]E+2
DATA SET 39	
T = 298.0	
3.311E+1	1.423E+1
2.401E+1	7.859E+0
2.242E+1	6.537E+0
2.012E+1	5.714E+0
1.821E+1	4.669E+0
1.661E+1	3.653E+0
1.437E+1	2.780E+0
1.337E+1	2.470E+0

ν	α
DATA SET 39(CONT.)	
1.253E+1	2.14[illegible]E+0
1.115E+1	1.5[illegible]E+0
1.0[illegible]8E+1	1.253E+0
9.[illegible]91E+0	1.[illegible]8E+0
8.4[illegible]3E+0	9.356E-1
7.143E+0	5.978E-1
6.329E+0	4.621E-1
5.587E+0	3.619E-1
4.695E+0	2.578E-1
3.9[illegible]4E+0	2.228E-1
3.155E+0	1.312E-1
DATA SET 40	
T = 298.0	
1.618E+2	9.391E+3
1.786E+2	1.055E+4
1.754E+2	1.164E+4
1.724E+2	1.349E+4
1.695E+2	1.431E+4
1.657E+2	1.573E+4
1.639E+2	1.337E+4
1.613E+2	7.216E+3
1.5[illegible]7E+2	4.029E+3
1.503E+2	2.631E+3
1.538E+2	1.682E+3
1.515E+2	1.219E+3
1.493E+2	9.613E+2
DATA SET 41	
T = 298.0	
1.429E+2	4.542E+2
1.389E+2	3.421E+2
1.351E+2	2.564E+2
1.316E+2	2.[illegible]83E+2
1.282E+2	1.8[illegible]4E+2
1.250E+2	1.571E+2
1.220E+2	1.416E+2
1.190E+2	1.287E+2

ν	α
DATA SET 41(CONT.)	
1.163E+2	1.213E+2
1.136E+2	1.142E+2
1.111E+2	1.075E+2
1.087E+2	1.02[illegible]E+2
1.064E+2	9.693E+1
1.044E+2	9.425E+1
1.02[illegible]E+2	9.114E+1
1.00[illegible]E+2	8.790E+1
9.9[illegible]4E+1	8.511E+1
9.615E+1	8.337E+1
9.434E+1	8.28[illegible]E+1
9.259E+1	8.629E+1
9.091E+1	7.997E+1
8.929E+1	7.854E+1
8.772E+1	7.826E+1
8.621E+1	7.692E+1
8.475E+1	7.668E+1
8.333E+1	7.645E+1
8.197E+1	7.519E+1
8.065E+1	7.499E+1
7.937E+1	7.48[illegible]E+1
7.813E+1	7.363E+1
7.692E+1	7.25[illegible]E+1
7.576E+1	7.14[illegible]E+1
7.463E+1	7.033E+1
7.353E+1	6.838E+1
7.246E+1	6.739E+1
7.143E+1	6.552E+1
7.042E+1	6.372E+1
6.944E+1	6.190E+1
6.849E+1	6.025E+1
6.757E+1	5.944E+1
6.667E+1	5.781E+1
6.579E+1	5.622E+1
6.494E+1	5.467E+1
6.411E+1	5.317E+1
6.329E+1	5.249E+1
6.250E+1	5.10[illegible]E+1
6.173E+1	4.965E+1
6.098E+1	4.827E+1

ν	α
DATA SET 41(CONT.)	
6.024E+1	4.709E+1
DATA SET 42	
T = 298.0	
1.429E+2	3.431E+2
1.379E+2	2.65[illegible]E+2
1.333E+2	2.22[illegible]E+2
1.291E+2	1.897E+2
1.25[illegible]E+2	1.60[illegible]E+2
1.218E+2	1.44[illegible]E+2
1.111E+2	1.243E+2
1.053E+2	1.124E+2
1.00[illegible]E+2	1.043E+2
9.54[illegible]E+1	9.65[illegible]E+1
9.[illegible]41E+1	9.139E+1
8.69[illegible]E+1	8.7[illegible]E+1
8.333E+1	8.378E+1
DATA SET 43	
T = 3[illegible].0	
3.236E+0	7.112E-2
4.31[illegible]E+0	1.34[illegible]E-1
5.376E+0	2.226E-1
6.52E+0	3.272E-1
7.519E+0	4.8[illegible]E-1
8.021E+0	6.483E-1
9.76[illegible]E+0	9.254E-1
1.067E+1	1.147E+0
DATA SET 44	
T = 360.0	
3.342E+0	8.458E-2
4.944E+0	2.015E-1
6.622E+0	3.929E-1
8.195E+0	6.351E-1

TABLE 24. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF SODIUM CHLORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 45	
T = 2[illegible]	
3.342E+0	6.459E-2
4.944E+0	1.552E-1
6.622E+0	3.155E-1
8.195E+0	5.27[illegible]E-1
DATA SET 46	
T = 2[illegible]	
3.342E+0	3.5[illegible]E-2
4.944E+0	9.8[illegible]1E-2
6.622E+0	2.[illegible]74E-1
8.195E+0	3.81[illegible]E-1
DATA SET 47	
T = [illegible]	
3.342E+0	[illegible]
4.944E+0	4.775E-2
6.622E+0	1.[illegible]77E-1
8.195E+0	1.935E-1
DATA SET 48	
T = [illegible]	
3.342E+0	1.175E-2
4.944E+0	2.9[illegible]E-2
6.622E+0	[illegible]
8.195E+0	[illegible]
DATA SET 49	
T = 2[illegible]	
5.[illegible]E+0	1.822E-1
DATA SET 50	
T = 2[illegible]	
2.63[illegible]E+3	9.[illegible]E-4



Figure 18. Absorption Coefficient of Sodium Chloride (Temperature Dependence)

TABLE 25. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF SODIUM CHLORIDE (Temperature Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	43	Stolen, R. and Dransfeld, K.	1965	T	31.25	96-402	High purity; single crystal; grown by the Bridgman method; plate specimens of thickness from 0.5 to 25.0 mm; absorption coefficients directly determined; data extracted from a figure.
2	43	Stolen, R. and Dransfeld, K.	1965	T	20	96-402	Same as above.
3	43	Stolen, R. and Dransfeld, K.	1965	T	9.804	96-402	Same as above.
4	72	Harrington, J.A. and Hass, M.	1973	C	943.4	304-1035	Single crystal; specimen with surfaces mechanically and then chemically polished; absorption coefficients measured by calorimetric method using a CO_2 laser source; data extracted from a figure.
5	107	Dötsch, H. and Happ, H.	1964	T	8.62	80-297	Single crystal; plate specimen of 150 mm thick; absorption coefficients determined from transmission measurements; data extracted from a figure.
6	107	Dötsch, H. and Happ, H.	1964	T	7.52	80-297	Same as above.
7	107	Dötsch, H. and Happ, H.	1964	T	6.45	80-297	Same as above.
8	107	Dötsch, H. and Happ, H.	1964	T	5.38	80-297	Same as above.
9	107	Dötsch, H. and Happ, H.	1964	T	4.21	80-297	Same as above.
10	107	Dötsch, H. and Happ, H.	1964	T	3.24	80-297	Same as above.
11	100	Rowe, J.M. and Harrington, J.A.	1976	C	943.4	100-300	Single crystals; grown by the reactive-atmosphere-process; obtained from the Naval Research Lab.; rod specimens of 2.5 cm diameter and of various lengths; chemically etched surface; bulk absorption determined; data extracted from a figure; data at low temperature carried large uncertainty of ±100%; uncertainty diminished toward higher temperatures.

TABLE 26. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF SODIUM CHLORIDE (Temperature Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

T	α
DATA SET 1	
ν = 3.125E+1	
95.0	8.254E+2
110.0	1.005E+3
125.0	1.245E+3
140.0	1.449E+3
155.0	1.591E+3
170.0	1.914E+3
195.0	2.197E+3
217.0	2.550E+3
237.0	2.825E+3
257.0	3.103E+3
279.0	3.405E+3
300.0	3.815E+3
332.0	4.315E+3
362.0	4.827E+3
402.0	5.499E+3
DATA SET 2	
ν = 2.000E+1	
95.0	3.954E+2
110.0	4.931E+2
125.0	5.931E+2
140.0	6.951E+2
155.0	8.115E+2
170.0	9.191E+2
195.0	1.055E+3
217.0	1.225E+3
237.0	1.335E+3
257.0	1.505E+3
279.0	1.654E+3
300.0	1.830E+3
332.0	2.074E+3
362.0	2.319E+3
402.0	2.641E+3
DATA SET 3	
ν = 9.804E+0	
73.0	2.073E+1

T	α
DATA SET 3 (CONT.)	
81.0	3.379E+1
94.0	4.583E+1
108.0	6.029E+1
121.0	7.491E+1
131.0	8.715E+1
142.0	1.009E+2
154.0	1.147E+2
168.0	1.331E+2
183.0	1.517E+2
198.0	1.713E+2
213.0	1.911E+2
232.0	2.151E+2
251.0	2.424E+2
273.0	2.719E+2
300.0	3.090E+2
DATA SET 4	
ν = 9.434E+2	
304.0	2.740E-3
370.0	3.530E-3
448.7	4.010E-3
548.2	6.450E-3
647.1	8.090E-3
734.5	1.207E-2
829.5	1.475E-2
910.2	2.050E-2
1035.1	2.360E-2
DATA SET 5	
ν = 8.621E+0	
80.0	1.344E-1
99.7	1.850E-1
150.3	3.007E-1
200.0	4.273E-1
296.5	6.772E-1

T	α
DATA SET 6	
ν = 7.519E+0	
80.0	8.879E-2
99.7	1.203E-1
150.3	2.076E-1
200.0	2.954E-1
296.5	4.924E-1
DATA SET 7	
ν = 6.452E+0	
80.0	5.860E-2
99.7	7.923E-2
150.3	1.373E-1
200.0	1.981E-1
296.5	3.426E-1
DATA SET 8	
ν = 5.376E+0	
80.0	3.703E-2
99.7	4.728E-2
150.3	7.951E-2
200.0	1.184E-1
296.5	2.201E-1
DATA SET 9	
ν = 4.310E+0	
80.0	2.166E-2
99.7	2.727E-2
150.3	4.536E-2
200.0	6.945E-2
296.5	1.333E-1
DATA SET 10	
ν = 3.236E+0	
80.0	1.143E-2
99.7	1.390E-2
150.3	2.235E-2

T	α
DATA SET 10 (CONT.)	
200.0	3.461E-2
296.5	7.281E-2
DATA SET 11	
ν = 9.434E+2	
100.0	1.420E-4
124.0	1.560E-4
149.0	1.800E-4
174.0	2.160E-4
199.0	2.710E-4
223.0	3.480E-4
248.0	4.610E-4
273.0	6.360E-4
299.0	8.910E-4



Figure 19. Reflectivity of Sodium Chloride

TABLE 27. SUMMARY OF MEASUREMENTS ON THE REFLECTIVITY OF SODIUM CHLORIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	109	Barnes, R.B. and Czerny, M.	1931	R	43-70.0	293	Crystal; plate specimen; normal spectral reflectivity obtained; silver mirror used as reference; data extracted from a figure; temperature not given, 293 K assumed.
2	101	Czerny, M.	1930	R	44.0-71.4	293	Crystal; plate specimen of about 30 x 40 mm^2; polished top surface; normal spectral reflectivity obtained with a silver mirror as reference; data extracted from a figure; temperature not given, 293 K assumed.
3	101	Czerny, M.	1930	R	35.0-47.0	293	Same as above.
4	102	Cartwright, C.H. and Czerny, M.	1934	R	126.0-231.0	293	Bulk NaCl; surface conditions unspecified; near normal reflectivities obtained; linearly averaged values of the tabulated data extracted.
5	110	Baldini, G. and Bosacchi, B.	1968	R	0.124-0.187	300	Single crystal; specimen with cleaved surface; back surface of the specimen treated with an emery cloth to reduce the reflection from the back; near normal reflectivity obtained with specimen in vacuum; data extracted from a figure.
6	110	Baldini, G. and Bosacchi, B.	1968	R	0.124-0.179	55	Same as above except at a low temperature.
7	94	Miyata, T. and Tomiki, T.	1967	R	0.157-0.212	78	Single crystal; obtained from the Harshaw Chemical Co. or grown by zone refined from melt; cleaved specimens of 8 mm x 10 mm x 0.2-4 mm; near normal reflectivity measured by an ultra violet spectrophotometer; data extracted from a curve.
8	54	McCarthy, D.E.	1963	T	2.1-50.4	298	Synthetic crystal; plate specimen of 5 cm thick; ground and polished to a flatness of seven fringes or better on both sides; incident angle 30°; data extracted from a figure.

TABLE 28. EXPERIMENTAL DATA ON THE REFLECTIVITY OF SODIUM CHLORIDE

[Wavelength, λ, μm; Temperature, T, K; Reflectivity, ρ]

λ	ρ
DATA SET 1	
T = 293.0	
43.0	0.644
44.0	0.633
45.4	0.724
49.7	0.734
49.8	0.757
49.0	0.792
[illegible]	0.775
[illegible]	0.599
[illegible]	0.590
[illegible]	0.[illegible]
57.7	0.[illegible]
59.9	0.[illegible]
59.9	0.[illegible]
[illegible]	0.[illegible]
57.2	0.[illegible]
[illegible]	0.[illegible]
59.5	0.[illegible]
60.7	0.792
61.9	0.652
63.6	0.657
63.6	0.644
64.1	0.641
64.2	0.634
66.3	0.492
66.5	0.491
66.0	0.455
67.0	0.349
68.5	0.381
70.0	0.339
DATA SET 2	
T = 293.0	
44.0	0.456
44.9	0.654
45.6	0.725
46.3	0.729
46.8	0.636
47.1	0.795

λ	ρ
DATA SET 2(CONT.)	
48.1	0.828
49.3	0.855
51.8	0.910
54.0	0.839
57.4	0.806
54.8	0.865
60.9	0.745
63.4	0.617
65.9	0.531
68.0	0.442
68.9	0.398
71.3	0.417
72.4	0.367
DATA SET 3	
T = 293.0	
35.2	0.079
36.0	0.133
36.1	0.137
36.1	0.160
36.9	0.2[illegible]
37.0	0.214
37.0	0.227
37.7	0.28[illegible]
37.9	0.256
37.9	0.265
37.9	0.261
38.0	0.201
38.6	0.288
38.7	0.240
39.7	0.253
39.5	0.257
39.5	0.269
39.6	0.231
40.4	0.262
40.4	0.286
40.5	0.244
41.2	0.288
41.3	0.311

λ	ρ
DATA SET 3(CONT.)	
42.1	0.300
42.2	0.369
43.0	0.374
43.1	0.377
43.8	0.427
43.9	0.457
44.7	0.549
44.8	0.588
45.7	0.659
46.6	0.718
DATA SET 4	
T = 293.0	
120.0	0.196
147.0	0.202
174.0	0.179
200.0	0.177
231.0	0.197
DATA SET 5	
T = 300.0	
0.124	0.1324
0.128	0.1273
0.130	0.1273
0.131	0.1297
0.132	0.1297
0.135	0.1233
0.137	0.1197
0.140	0.1197
0.141	0.1169
0.145	0.1169
0.149	0.1119
0.153	0.0983
0.151	0.1028
0.152	0.1145
0.153	0.1496
0.155	0.2114
0.155	0.2565

λ	ρ
DATA SET 5(CONT.)	
0.156	0.2945
0.157	0.3185
0.159	0.3573
0.162	0.3192
0.163	0.2612
0.165	0.2276
0.167	0.2028
0.169	0.1795
0.174	0.1588
0.178	0.1445
0.183	0.1330
0.187	0.1256
DATA SET 6	
T = 55.0	
0.124	0.1164
0.126	0.1114
0.128	0.1114
0.131	0.1167
0.132	0.1167
0.134	0.1119
0.136	0.1119
0.137	0.1148
0.139	0.1148
0.140	0.1137
0.142	0.1169
0.144	0.1169
0.145	0.1117
0.146	0.1176
0.147	0.0833
0.148	0.0662
0.148	0.0416
0.149	0.0283
0.151	0.1111
0.151	0.1754
0.152	0.2891
0.153	0.3973
0.154	0.2786
0.155	0.4530

λ	ρ
DATA SET 6(CONT.)	
0.156	0.3581
0.157	0.3069
0.158	0.2673
0.160	0.2334
0.164	0.2[illegible]
0.167	0.1791
0.171	0.1531
0.175	0.1410
0.179	0.1309
DATA SET 7	
T = 78.0	
0.1575	0.4[illegible]
0.1580	0.354
0.1585	0.315
0.1[illegible]	0.365
0.1614	0.24[illegible]
0.1619	0.237
0.1622	0.236
0.1630	0.239
0.1633	0.24[illegible]
0.1638	0.24[illegible]
0.164[illegible]	0.239
0.1648	0.236
0.1693	0.20[illegible]
0.1725	0.183
0.1770	0.160
0.1800	0.147
0.1836	0.133
0.1853	0.133
0.1807	0.131
0.1969	0.131
0.1927	0.133
0.1962	0.137
0.1981	0.14[illegible]
0.2100	0.141
0.2312	0.143
0.2028	0.144
0.2043	0.144

λ	ρ
DATA SET 7(CONT.)	
0.2063	0.142
0.2[illegible]	0.141
0.2101	2.098
0.2103	0.140
0.21.9	0.138
DATA SET 8	
T = 298.0	
2.1	0.[illegible]36
5.1	0.[illegible]23
7.5	0.[illegible]35
1[illegible]	0.031
12.7	0.[illegible]18
15.2	0.026
17.3	0.312
2[illegible]	0.[illegible]
3[illegible].7	0.[illegible]11
35.1	0.[illegible]12
36.1	0.071
37.[illegible]	0.[illegible]59
37.5	0.255
37.5	0.[illegible]42
38.4	0.[illegible]56
39.2	0.2[illegible]9
40.1	0.157
40.1	0.29[illegible]
42.2	0.375
42.5	0.375
42.9	0.[illegible]
43.3	0.34[illegible]
44.0	0.[illegible]27
45.2	0.560
45.5	0.085
46.2	0.759
46.4	0.6[illegible]3
46.9	0.603
47.8	0.796
48.9	0.760
50.3	0.710



Figure 20. Transmission of Sodium Chloride

TABLE 29. SUMMARY OF MEASUREMENTS ON THE TRANSMISSION OF SODIUM CHLORIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	109	Barnes, R.B. and Czerny, M.	1931	T	33.5-74.7	293	Vacuum evaporated thin film specimen of 0.17 mm thick on celluloid substrate; transmittance spectrum obtained; data extracted from a figure.
2	109	Barnes, R.B. and Czerny, M.	1931	T	32.3-75.0	293	Same as above except for specimen of 1.35 mm thick.
3	109	Barnes, R.B. and Czerny, M.	1931	T	32.3-75.0	293	Same as above except for specimen of 1.7 mm thick.
4	109	Barnes, R.B. and Czerny, M.	1931	T	34.6-75.0	293	Same as above except for specimen of 2.3 mm thick.
5	109	Barnes, R.B. and Czerny, M.	1931	T	33.5-75.0	293	Same as above except for specimen of 3.4 mm thick.
6	109	Barnes, R.B. and Czerny, M.	1931	T	33.5-75.0	293	Same as above except for specimen of 3.6 mm thick.
7	101	Czerny, M.	1930	T	35.8-46.3	293	Crystal; plate specimen of 8 mm thick; spectral transmittance obtained; data extracted from a figure; temperature not given; 293 K assumed.
8	101	Czerny, M.	1930	T	35.8-47.4	293	Same as above except for other specimen of some thickness.
9	101	Czerny, M.	1930	T	35.0-44.3	293	Same as above except for other specimen of 14 mm thick.
10	101	Czerny, M.	1930	T	33.4-40.8	293	Same as above except for other specimen of 19 mm thick.
11	101	Czerny, M.	1930	T	35.8-46.3	293	Same as above except for other specimen of 24 mm thick.
12	94	Miyata, T. and Tomiki, T.	1967	R	0.159-0.213	78	Single crystal; obtained from Harshaw Chemical Co. or grown by zone refined from melt; cleave specimens of 0.63 mm thick; transmission determined by an ultraviolet spectrophotometer; data extracted from a curve.
13	85	McCarthy, D.E.	1967	T	0.17-3.0	298	Synthetic crystal; plate specimen of 5.0 mm thick with surfaces parallel to within 0.001 mm/mm of length and flat to within 10 fringes or better of the mercury green line; measurements made on double-beam instruments with accuracy of ±2%; data extracted from a figure; temperature not given, 298 K assumed.
14	54	McCarthy, D.E.	1963	T	2.0-21.0	298	Synthetic crystal; plate specimen of 5 cm thick; ground and polished to a flatness of seven fringes or better on both sides; data extracted from a figure.

TABLE 30. EXPERIMENTAL DATA ON THE TRANSMISSION OF SODIUM CHLORIDE

(Wavelength, λ, μm; Temperature, T, K; Transmission, τ)

λ	τ	λ	τ	λ	τ	λ	τ	λ	τ	λ	τ
DATA SET 1		DATA SET 1(CONT.)		DATA SET 2(CONT.)		DATA SET 3(CONT.)		DATA SET 4(CONT.)		DATA SET 5(CONT.)	
T = 293.0											
		74.7	1.000	7[illegible].3	0.750	7[illegible].2	0.720	67.9	0.631	67.5	0.500
33.5	1.000			72.6	0.753	71.2	0.732	69.1	0.734	69.1	0.599
34.7	1.000	DATA SET 2		73.7	0.831	71.4	0.736	69.2	0.745	70.2	0.628
35.8	1.000	T = 293.0		75.0	0.918	72.5	0.780	71.3	0.715	71.4	0.657
36.9	1.000					73.7	0.842	72.5	0.768	72.5	0.675
39.0	1.000	32.3	0.979	DATA SET 3		75.0	0.854	73.0	0.879	73.7	0.724
39.2	1.000	33.5	0.973	T = 293.0						75.0	0.695
39.4	1.000	34.7	0.900			DATA SET 4		DATA SET 5			
[illegible]	1.000	35.9	0.957	32.3	0.970	T = 293.0		T = 293.0		DATA SET 6	
[illegible]	1.000	36.9	0.924	34.6	0.950					T = 293.0	
42.0	0.993	39.1	0.898	35.8	0.936	34.0	0.943	33.5	0.912		
43.0	1.000	39.2	0.877	36.9	0.949	34.6	0.923	34.7	0.891	33.5	0.886
45.0	0.993	40.3	0.858	38.1	0.934	35.8	0.913	35.8	0.875	34.7	0.904
46.1	0.990	41.0	0.851	39.2	0.860	36.9	0.886	36.9	0.817	35.8	0.925
47.3	0.994	42.7	0.840	40.4	0.833	38.1	0.844	38.1	0.753	36.9	0.779
48.4	0.979	43.7	0.829	41.5	0.823	39.2	0.800	39.2	0.710	38.0	0.721
49.0	0.995	45.0	0.815	42.6	0.818	40.3	0.774	39.2	0.694	39.1	0.681
51.7	0.975	46.2	0.789	43.6	0.808	41.6	0.756	40.3	0.633	40.4	0.626
52.0	0.990	47.3	0.757	44.9	0.784	42.6	0.745	41.5	0.674	41.5	0.607
53.0	0.990	48.3	0.760	46.0	0.766	43.8	0.733	42.6	0.637	42.6	0.563
54.2	0.954	49.7	0.699	47.3	0.701	43.8	0.722	43.8	0.613	43.8	0.583
55.3	0.962	50.3	0.650	48.4	0.672	44.9	0.714	44.9	0.535	44.9	0.524
56.3	0.[illegible]	51.9	0.633	49.6	0.646	46.1	0.657	46.1	0.564	46.1	0.474
[illegible]	0.990	53.0	0.604	50.7	0.618	47.2	0.590	47.3	0.485	47.3	0.[illegible]
57.6	0.993	54.2	0.589	51.8	0.591	48.4	0.557	48.4	0.412	48.5	0.297
57.6	0.994	55.2	0.552	53.0	0.567	49.5	0.505	49.6	0.379	49.6	0.325
58.9	0.737	55.4	0.538	54.1	0.544	50.7	0.491	50.7	0.323	50.6	0.300
60.0	0.644	56.6	0.474	55.3	0.510	51.9	0.493	52.0	0.310	51.9	0.296
62.2	0.571	57.0	0.407	56.5	0.443	53.0	0.471	53.0	0.294	53.1	0.285
63.4	0.715	58.3	0.322	57.0	0.378	54.2	0.471	55.4	0.265	54.2	0.274
64.5	0.935	59.4	0.261	58.0	0.291	55.3	0.462	56.5	0.275	54.6	0.261
64.6	0.913	60.1	0.171	59.9	0.196	55.3	0.451	57.7	0.268	55.3	0.227
65.7	0.9[illegible]	62.2	0.213	61.1	0.255	56.6	0.351	59.8	0.185	55.3	0.234
65.8	0.921	63.5	0.351	62.2	0.197	57.6	0.356	59.9	0.134	56.5	0.190
68.0	0.903	64.5	0.457	63.4	0.331	58.7	0.258	61.1	0.114	57.6	0.147
69.1	0.935	65.7	0.554	63.4	0.327	59.9	0.109	62.2	0.142	58.7	0.081
70.2	0.933	66.8	0.682	64.6	0.445	61.1	0.141	63.4	0.252	61.1	0.042
71.3	1.000	69.0	0.791	65.7	0.537	62.2	0.182	64.5	0.353	61.1	0.048
72.4	0.946	69.1	0.826	67.9	0.693	64.5	0.411	65.7	0.480	62.2	0.068
73.7	0.904	70.2	0.825	69.1	0.704	65.6	0.517	66.8	0.529	63.4	0.158

TABLE 30. EXPERIMENTAL DATA ON THE TRANSMISSION OF SODIUM CHLORIDE (continued)

DATA SET 6 (CONT.)

λ	τ
[illegible]	0.253
64.5	[illegible]
65.7	0.374
66.6	0.445
67.9	0.428
68.1	0.363
[illegible]	[illegible]
[illegible]	[illegible]
70.2	0.543
71.4	0.534
72.5	0.500
72.5	0.539
73.6	[illegible]
[illegible]	[illegible]
[illegible]	[illegible]
[illegible]	[illegible]
[illegible]	[illegible]

DATA SET 7
T = 293.0

λ	τ
[illegible]	[illegible]
[illegible]	[illegible]
[illegible]	0.374
39.3	[illegible]
40.4	[illegible]
41.0	0.310
42.4	[illegible]
46.3	0.227

DATA SET 8
T = 293.0

λ	τ
35.1	[illegible]
[illegible]	0.443
[illegible]	[illegible]
[illegible]	[illegible]
[illegible]	0.251
[illegible]	0.231
42.9	0.222

DATA SET 8 (CONT.)

λ	τ
44.0	0.222
45.2	0.184
46.4	0.156
47.4	0.124

DATA SET 9
T = 293.0

λ	τ
35.0	0.363
35.9	0.321
36.9	0.211
37.3	0.174
38.0	0.141
39.0	0.099
[illegible]	[illegible]
[illegible]	[illegible]
41.0	0.032
41.9	0.007
42.9	0.047
44.3	0.004

DATA SET 10
T = 293.0

λ	τ
33.4	0.370
33.7	0.370
34.0	0.295
[illegible]	0.258
35.3	0.229
[illegible]	[illegible]
35.9	0.213
37.3	0.158
38.1	0.067
38.5	0.042
39.6	0.036
[illegible]	0.022

DATA SET 11
T = 293.0

λ	τ
33.4	0.347
33.8	0.291
34.6	0.277
34.9	0.236
35.6	0.195
36.1	0.133
36.9	0.104
37.3	0.063
38.1	0.052
38.5	0.028
39.6	0.019
40.8	0.015

DATA SET 12
T = 73.0

λ	τ
0.1645	0.470
0.1654	0.507
0.1666	0.532
[illegible]	0.552
[illegible]	[illegible]
[illegible]	0.572
0.1722	0.569
0.1744	0.559
0.1756	0.546
[illegible]	0.510
0.1813	0.501
0.1831	[illegible]
0.1851	0.503
0.1871	0.515
[illegible]	0.554
0.1956	0.665
0.1971	0.675
[illegible]	0.726
[illegible]	0.739
0.2040	0.754
0.2055	0.762
[illegible]	0.773
0.2122	0.777

DATA SET 13
T = 300.0

λ	τ
0.191	0.05
0.199	0.17
0.203	0.29
0.203	0.56
0.208	0.66
0.214	0.77
0.227	0.82
0.269	0.86
0.327	0.89
0.428	0.91
0.552	0.91
0.696	0.91
0.876	0.91
1.15	0.91
1.46	0.91
1.96	0.91
2.50	0.91
2.90	0.91
[illegible]	0.91

DATA SET 14
T = 293.0

λ	τ
2.2	0.911
5.5	0.912
10.3	0.967
12.5	[illegible]
13.5	[illegible]
14.3	0.857
15.0	0.798
15.5	0.739
16.1	0.659
16.8	0.593
17.4	0.520
17.8	0.453
18.1	0.395
18.3	0.316
18.9	0.277
19.3	0.219

DATA SET 14 (CONT.)

λ	τ
19.6	0.157
20.0	0.107
20.2	0.043

TABLE 31. PEAK POSITIONS (λ_{max}) IN μm AND HALF-WIDTHS (W) IN eV FOR THE F, R, M, AND N ABSORPTION BANDS IN SODIUM CHLORIDE*

Interionic dist., d (Å)	Temp.	F band		R_1 band	R_2 band	M band		N bands
		λ_{max}	W	λ_{max}	λ_{max}	λ_{max}	W	λ_{max}
2.81	RT	(0.471)†		(0.547)	(0.592)	(0.701)		
		0.458	0.46			0.720		
		0.465	0.47			0.725		
		0.466	0.49					
		0.470	0.50					
	NT	0.448	0.28	0.545	0.596	0.706		0.823
		0.450	0.31			0.713		
		0.452	0.41					
	HT	0.450	0.25					
			0.28					
			0.29					

* Values were taken from Ref. [69].

† Values given in parentheses are calculated from the Ivey relations [70].

F band $\lambda_{max} = 703\ d^{1.84}$ for NaCl structure, $\lambda_{max} = 251\ d^{2.5}$ for CsCl structure.

R_1 band $\lambda_{max} = 816\ d^{1.84}$

R_2 band $\lambda_{max} = 884\ d^{1.84}$

M band $\lambda_{max} = 1400\ d^{1.56}$

TABLE 32. RECOMMENDED VALUES ON ABSORPTION COEFFICIENT OF SODIUM CHLORIDE IN IR REGION AT 300 K

ν, cm^{-1}	λ, μm	Absorption Coefficient, cm^{-1}	
		Intrinsic*	Observed† (Selected)
4.000E+02	25.0	1.9E+1	
5.000E+02	20.0	3.2E+0	
5.010E+02	20.0	3.1E+0	2.5E+0
5.510E+02	18.1	1.2E+0	1.2E+0
6.000E+02	16.7	5.3E-1	
6.020E+02	16.6	5.2E-1	5.7E-1
6.510E+02	15.4	2.1E-1	2.7E-1
6.998E+02	14.3	9.0E-2	1.0E-1
7.000E+02	14.3	9.0E-2	
7.508E+02	13.3	3.6E-2	4.1E-2
8.000E+02	12.5	1.5E-2	1.4E-2
8.511E+02	11.7	6.0E-3	4.6E-3
9.000E+02	11.1	2.5E-3	
9.434E+02	10.6	1.1E-3	1.0E-3
1.000E+03	10.0	4.2E-4	
1.079E+03	9.27	1.0E-4	2.6E-4
1.100E+03	9.09	7.1E-5	
1.200E+03	8.33	1.1E-5	
1.300E+03	7.69	2.0E-6	
1.400E+03	7.14	3.3E-7	
1.500E+03	6.67	5.6E-8	
1.600E+03	6.25	9.4E-9	
1.700E+03	5.88	1.5E-9	
1.800E+03	5.56	2.6E-10	
1.887E+03	5.30	5.6E-11	3.4E-5
2.632E+03	3.80	9.4E-17	5.3E-5

*Intrinsic values were calculated according to Eq. (29) with uncertainties about ±10%.

†Values in this column are the total absorption coefficient which are either lowest reported or those used to define the constants in Eq. (29). Uncertainties of these values are about ±10%. Values lower than 1.0E-3 carry higher uncertainties up to ±30%.

3.4. Potassium Chloride, KCl

Potassium chloride is widely used in spectroscopy, since its optical properties make it a convenient window and prism material over the spectrum from the ultraviolet to the infrared. The transmission range is about 0.21 to 30 μm. A plate 1 cm in thickness transmits radiation up to 24 μm. Since strong absorption occurs near the transmission limits, the transmission range of KCl is about 0.38 to 21 μm. Of all the substances which are otherwise suitable for optical parts, KCl is transparent over the widest range of the infrared spectrum.

KCl crystals are grown in the same way as NaCl, but sometimes multiple crystals instead of single-crystal ingots result. Therefore, large prisms are somewhat rare and expensive. As crystal growth techniques improved, crystals 30 cm in diameter are now available.

Measurement of the refractive index of potassium chloride dates back to 1871, when Stefan [86] determined the refractive index of a sylvite prism for the B, D, and F of Fraunhofer lines. Later work, represented by Rubens [112], Martens [87], Paschen [88], and Gyulai [27], provided a large amount of data in the transparent region. Measurements beyond the transparent region were not made until 1934 when Cartwright et al. [102] analyzed the reflection and transmission spectra of KCl thin films in the infrared region, 126 to 232 μm. In the low ultraviolet region, Tomiki [113] published values obtained by analyzing the reflection spectra. Refractive index data are now available for a wide wavelength range from 0.106 to 232 μm.

Li [33] reduced the then available experimental data on the refractive index to a common temperature of 293 K and after careful evaluation and analysis adopted a Sellmeier type dispersion equation to calculate the refractive index at 293 K in the wavelength range of 0.18-35.0 μm:

$$n^2 = 1.26486 + \frac{0.30523\,\lambda^2}{\lambda^2-(0.100)^2} + \frac{0.41620\,\lambda^2}{\lambda^2-(0.131)^2} + \frac{0.18870\,\lambda^2}{\lambda^2-(0.162)^2} + \frac{2.62[illegible]\,\lambda^2}{\lambda^2-(70.42)^2} \quad (30)$$

where λ is in units of μm.

Investigations of absorption coefficient for practical applications are generally classified into three wavelength regions: the ultraviolet and the

PRECEDING PAGE B[illegible]

far infrared limits of the transparent region, and the transparent regions. In the ultraviolet region, the main motivation for the study was to investigate and to determine the Urbach-rule parameters.

Roessler and Walker [91] determined the absorption index for KCl, in the spectral range from 0.047 to 0.248 μm, by a Kramers-Kronig analysis of the reflectance spectrum. Evidenced by the strong temperature dependence of reflectance in the exciton region and the appearance of spin-orbit split doublets, the surfaces of the KCl specimen examined were near perfect. Kobayashi and Tomiki [93] studied the effects of impurities on the absorption coefficient and found significant shifts in the position of the fundamental absorption edge and an absorption band at 0.204 μm. The latter is due to the presence of OH ion as an impurity in KCl grown in air. However, the shift of the position of the edge may not be caused by the OH ions; it may be due to the presence of bromine and/or dislocation in the crystals. Tomiki [114] and Tomiki et al. [77] studied the absorption of KCl in the wavelength region between 0.1 and 0.4 μm for the purpose of determining the Urbach-rule parameters and finding the features characteristic of the intrinsic tail. Through a systematic observation and analysis made at various temperatures they found the following empirical relations between some parameters

$E_o \approx 7.834$ eV

$\alpha_o \approx 1.26 \times 10^{10}$ cm^{-1}

$hf \approx 13.5$ meV

$\sigma_{so} \approx 0.745$

for the expression of absorption coefficient of the intrinsic tail

$$\alpha = \alpha_o \exp\left[-\sigma_s(T)\,(E_o - E)/kT\right] \tag{31}$$

where

$$\sigma_s(T) = \sigma_{so}\,\frac{2kT}{hf}\tanh\frac{hf}{2kT}$$

Measurements of the absorption coefficient for the infrared transparent region are just recent occurrences as the development of high-power IR lasers has led to a need for better characterization of IR window materials. Among other things, the absorption coefficient plays a decisive role in determining whether a material is adequate for laser optical components. For this reason, absorption coefficients of a number of selected materials were investigated at wavelengths of laser interest. Potassium chloride is among the best laser

window materials and its absorption coefficients at wavelengths 1.06, 2.7, 3.8, 5.3, and 10.6 μm were intensively studied in order to determine the influencing factors that contribute to the extrinsic absorption. These studies are very informative and provide clues and means for material preparation and parts fabrication in order to minimize the extrinsic components in the absorption.

To see whether or not certain intrinsic mechanical and optical properties at 10.6 μm could be achieved with the polycrystalline KCl, investigations were made on KCl specimens with various dopants. Shrader [115] observed that while the 10.6 μm absorption coefficients of the tested specimens were, in general, about the same magnitude as that of a pure KCl sample, 8.9×10^{-4} cm^{-1}, the absorption coefficients of doped KCl in the uv region are very much higher than the pure specimen.

Hass et al. [116] studied the infrared absorption in KCl single crystals near 10.6 μm using calorimetric techniques. They were able to separate the surface and bulk absorptions and a value of 8×10^{-5} cm^{-1} was assigned to the bulk part which is close to the estimated intrinsic limit of the crystal. They also found that an absorption band near 9.8 μm was present in all samples examined and appeared to be largely contributed by the surface absorption. The existence of this surface absorption band prevents observation of the intrinsic. They concluded that careful preparation and finishing of KCl crystals can give a near intrinsic absorption level at 10.6 μm.

Harrington and Hass [78] investigated the temperature dependence of multiphonon absorption at 10.6 μm for KCl samples. The absorption coefficient and its temperature dependence have been observed to vary markedly from sample to sample. In most cases, the absorption coefficient below 600 K is essentially independent of temperature. For purer samples the absorption coefficient increases more sharply at higher temperatures as would be expected for intrinsic behavior.

Boyer et al.[117] studied the temperature dependence of the absorption coefficients of pure KCl crystals at 10.6 μm from room temperature to within 50 K of the melting point, using laser calorimetric techniques. Crystals from a number of different sources were employed and the lowest absorption coefficient was observed with a crystal grown in a CCl_4 reactive atmosphere designed to minimize the introduction of oxygen-containing impurities. The temperature

dependence of the absorption is observed to be very sensitive to impurities, but for the best crystal with the lowest absorption, the dependence monotonically increases, which is anticipated for near-intrinsic absorption of the crystal. However, there always exists a surface absorption band at 9.5 μm whose wing contributes to the total absorption at 10.6 μm. When this surface component is subtracted, the bulk absorption coefficient is 8×10^{-5} cm^{-1}, which is in good agreement with other investigations. It has been experienced by many workers that the surface absorption can be considerably reduced by appropriate chemical polishing.

Deutsch [12], using a differential technique with a dual beam spectrometer, obtained absorption coefficients in the wavelength range from 13.3 to 32 μm for both single crystals and polycrystalline KCl provided by different suppliers. It was found that within the accuracy of the measurement, the long wavelength absorption coefficients of the polycrystalline KCl are the same as those of the single crystal. Furthermore, it was also found that the experimental data could be represented by an exponential relation of the form

$$\alpha = \alpha_o \exp(-\nu/\nu_o) \tag{32}$$

where

$$\alpha_o = 8696 \text{ cm}^{-1} \qquad \text{and} \qquad \nu_o = 50.8 \text{ cm}^{-1}$$

This relation was believed to represent the intrinsic absorption of KCl. The extrapolated absorption coefficient at 10.6 μm is approximately 8×10^{-5} cm^{-1}, which is somewhat lower than the measured values, 5×10^{-4} cm^{-1} and 3.5×10^{-4} cm^{-1}, for high purity samples. In a later study, Deutsch [118] reported the CO_2 laser calorimeter measurements on the 5.3 and 10.6 μm absorption coefficients of numerous KCl crystals with provisions made to eliminate the effect of surface absorption. One of the crystals showed a 10.6 μm absorption coefficient of $6.6 \pm 2 \times 10^{-5}$ cm^{-1} which corresponded to the predicted intrinsic value by the exponential relation, Eq. (32). It was then estimated the surface absorption to be $1.1 \pm 2 \times 10^{-4}$ per surface and, thus, the total absorption was dominated by surface loss. The lowest value of the 5.3 μm absorption coefficient he obtained was 1.5×10^{-5} cm^{-1}.

Hass et al. [119] measured absorption coefficients by calorimetric techniques at 1.06, 2.7, and 3.8 μm for a number of KCl samples. The results at 1.06 μm are generally in the 10^{-5} cm^{-1} range with the lowest reported at 7×10^{-6} cm^{-1}

which is very close to the limit of the method used. However, at wavelengths 2.7 and 3.8 μm, their best measurements were 3.7×10^{-4} cm^{-1} and 2.1×10^{-4} cm^{-1}, respectively. Compared with the absorption coefficients at 1.06 and 5.3 μm, the data imply excess absorption at 2.7 and 3.8 μm even in the purest available crystals. This has been observed not only in the KCl crystals but also in a number of low absorption alkali halide and alkaline earth fluoride crystals. The cause of such excessive absorption was not understood. They suggested the possibility of being attributable to the OH and CH impurities. If these were eliminated, the absorption level at these wavelengths could be reduced to 10^{-5} cm^{-1} range or lower.

Klein [120] investigated the origins of the extrinsic absorption at 2.7 and 3.8 μm. Correlation with vacuum-ultraviolet absorption measurements indicated that all of the excess 2.7 μm absorption can be accounted for by the OH^- content of the crystals. At 3.8 μm, the surplus absorption in the specimens are most likely contributed by the carbon-oxygen lineages, e.g., COF_2, CO_3^{-2}, HCO_3. Klein suggested that diminished residual absorption at these wavelengths can be achieved by substituting hydrogen chloride for carbon tetrachloride in purification procedures and treating the salt below its melting point.

Hass et al. [97] used an improved laser calorimetric technique in the determination of the 10.6 μm absorption coefficient of the material. As time elapses, the effect of surface absorptions and other contributions is reflected by the increase of slope at equilibrium. As a consequence, the surface and bulk absorptions can be separated by this technique. The bulk 10.6 μm absorption coefficient of KCl obtained by this method is 8×10^{-5} cm^{-1}.

The currently available lowest bulk absorption coefficients of KCl in the laser wavelength region were obtained by Allen and Harrington [98]. Since all of their calorimetric measurements were performed on one pure sample and at one laboratory, their results provided a more consistent and exact description of the dependence of the absorption on laser wavelength. All of their results are below 6×10^{-5} cm^{-1} level with the lowest value, observed at 5.3 μm, of 5×10^{-7} cm^{-1} which is at the limit of their instrument sensitivity. Earlier investigations of wavelength dependence of absorption by Rowe and Harrington [121] and others yielded considerably higher results than this data set.

It has been found that the following facts are common to all of the measurements in the laser wavelength region:

1. Surface absorption predominates at low bulk absorption levels. As a consequence, the observed total absorption is higher than the bulk. The surface absorption band at 9.6 μm is strong enough to mask the intrinsic behavior of the crystal in the wavelength region centered at 9.6 μm.

2. Absorption due to impurities contributes to bulk absorption as well as to surface absorption. At wavelengths 2.8 μm and 3.8 μm, absorptions due to hydroxyl ion and oxygen impurities are particularly outstanding.

3. It appears that the above mentioned extrinsic absorptions may render the crystal an unfavorable window material. It has been found, however, that the objectionable extrinsic absorption can be reduced through improved purification and polishing processes.

4. Low total and bulk absorptions, of the order of 10^{-6} cm^{-1} or less, were found, at wavelengths 1.03 and 5.3 μm. Although this value is still very much higher than the respective intrinsic limits, the results represent the limit of instrument sensitivity. Were the sensitivity of the instrument increased considerably, one might be able to observe very low absorption.

Figures 21 to 24 are plots of the available data. The pertinent information for each data source and the corresponding original values are given in Tables 33 to 36. In addition, available information and data on the reflectivity and transmission are also presented in the same manner (in Figures 25 and 26 and Tables 37 to 40), for completeness and comparison. For the visible and near visible regions, Table 41 gives the spectral positions of the well known color centers. Noticeable absorptions are likely to occur at these centers when the crystal is exposed to ultraviolet, x-ray, or high energy radiation. However, these absorption bands may disappear at high temperatures or by appropriate radiation, corresponding to the so-called "thermal and optical bleaching of color centers."

The recommended values given in Table 42 were calculated from Eq. (32). In the range between 10 to 32 μm, these values are supported by measurements

of Deutsch [12]. At other laser wavelengths, the observed values are generally higher than the calculated ones because of extrinsic contributions due to surface contamination and impurities. Current research has shown that the extrinsic absorptions can be reduced through improved techniques of sample preparation. Therefore, intrinsic values may serve useful purposes. It should be noted that the values in the "intrinsic" column are the lowest limits that we can obtain for ideal samples. In practice, the observed values are generally higher than the limiting values at low absorption levels. Unless values appear in the "observed" column, the limiting values are considered as guidelines for estimation and investigation.

Although it was not the intent of this study to evaluate the absorption data in the vacuum ultraviolet region, in order to provide the users a total picture of the available absorption data, plots of available data in this region are given in the Appendix of this report.



Figure 21. Absorption Coefficient of Potassium Chloride (Wavenumber Dependence)



Figure 22. Absorption Coefficient of Potassium Chloride in the Urbach Tail Region



Figure 23. Absorption Coefficient of Potassium Chloride in the Multiphonon Region

TABLE 33. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF POTASSIUM CHLORIDE (Wavenumber Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	91	Roessler, D.M. and Walker, W.C.	1968	R	5.80×10^{4}–2.1×10^{5}	300	Single crystal; obtained from the Harshaw Chemical Co. or the Westinghouse Electric Corp.; absorption coefficients derived from a Kramer-Kronig analysis of the near normal reflection spectra; data extracted from a table.
2	122	Antinori, M., Balzarotti, A., and Piacentini, M.	1973	R	1.04×10^{4}–1.66×10^{5}	293	Single crystal; obtained from the Harshaw Chemical Co.; specimen cleaved in air just before being mounted in the sample chamber to be vacuum pumped; reflection spectrum obtained with a monochromator of band width 1.5 Å; spectra obtained on the same specimen after 24 hours did not show significant changes and reproduced with uncertainty of about 5%; absorption coefficients derived by means of the Kramers-Kronig analysis of the reflection spectrum obtained in this paper from 13.5 to 20.5 eV, below 13.5 eV reflectivity data of Tomiki utilized while those of Blechschmidt et al. used beyond 20.5 eV; data extracted from a figure.
3	116	Hass, M., Davisson, J.W., Klein, P.H., and Boyer, L.L.	1974	C	9.2×10^{2}–1.08×10^{3}	300	Single crystal; grown by the Bridgman method in a carbon tetrachloride atmosphere; window specimens chemically polished in concentrated HCl; absorption coefficients measured with a tunable CO_2 laser by calorimetric method; the total absorption coefficient (bulk absorption + surface absorption) data extracted from a figure; the appearance of a surface absorption band near 9.8 μm prevents observation of bulk absorption.
4	102	Cartwright, C.H. and Czerny, M.	1934	T	49–92	293	Crystal; thin plate specimen of 123 μm thick; absorption coefficients deduced from transmittance and thickness measurements; data extracted from a figure.
5	102	Cartwright, C.H. and Czerny, M.	1934	T	43–91	293	Similar to above except for a specimen of 103 μm thick.
6	102	Cartwright, C.H. and Czerny, M.	1934	T	42–94	293	Similar to above except for a specimen of 258 μm thick.
7	102	Cartwright, C.H. and Czerny, M.	1934	T	42–70	293	Similar to above except for a specimen of 347 μm thick.
8	103	Blechschmidt, D., Klucker, R., and Swibowski, M.	1969	R	9.5×10^{4}–2.5×10^{5}	293	Single crystal; provided by Karl Korth, Kiel, Germany; freshly cleaved specimen; absorption coefficients derived with the reflectivity versus angle of incidence method; data extracted from a figure.
9	93	Kobayashi, K. and Tomiki, T.	1961	T	5.6×10^{4}–5.73×10^{4}	299	Crystal; specially purified; containing trace ions of 9×10^{-7} in mole fraction, divalent metallic ion impurities of 1×10^{15} per cc and hydroxyl ions of 2×10^{18} per cc; transmittances at the absorption tail measured with a vacuum ultraviolet spectrophotometer; data extracted from a figure.
10	93	Kobayashi, K. and Tomiki, T.	1961	T	5.5×10^{4}–5.7×10^{4}	327	Same as above.

TABLE 33. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF POTASSIUM CHLORIDE (*Wavenumber Dependence*) (*continued*)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
11	93	Kobayashi, K. and Tomiki, T.	1961	T	5.45×10^4-5.6×10^4	373	Similar to above except at a higher temperature.
12	93	Kobayashi, K. and Tomiki, T.	1961	T	5.35×10^4-5.53×10^4	420	Similar to above except at a higher temperature.
13	93	Kobayashi, K. and Tomiki, T.	1961	T	5.25×10^4-5.44×10^4	469	Similar to above except at a higher temperature.
14	124	Deutsch, T.F.	1974	T	8.0×10^2-1.25×10^3	298	Single crystal; bar specimens of 6.4 cm long; absorption coefficients determined from transmission measurements; data extracted from a figure.
15	12	Deutsch, T.F.	1973	T	5.0×10^2-7.5×10^2	300	Single crystal; obtained from the Harshaw Chemical Co.; specimen of 2.54 cm diameter and 2.54 cm thick; absorption coefficients determined using a differential technique with a dual-beam spectrophotometer; data extracted from a figure.
16	12	Deutsch, T.F.	1973	T	5.98×10^2-7.53×10^2	300	Similar to above except for an Optovac single crystal.
17	12	Deutsch, T.F.	1973	T	4.49×10^2-7.50×10^2	300	Similar to above except for a Harshaw polycrystalline.
18	125	Tomiki, T.	1966	Z	5.6×10^4-6.2×10^4	4.2	Single crystal; obtained by a zone refining in chlorine atmosphere following vacuum distillation; cleaved specimens of 0.0175 cm to 0.497 cm thick; absorption coefficients deduced from reflectivity and transmission; data extracted from a figure.
19	125	Tomiki, T.	1966	Z	5.6×10^4-6.2×10^4	81	Similar to above except at a higher temperature.
20	125	Tomiki, T.	1966	Z	5.6×10^4-5.8×10^4	295	Similar to above except at a higher temperature.
21	126	Philipp, H.R. and Ehrenreich, H.	1963	R	5.8×10^4-1.83×10^5	298	Single crystal; obtained from the Harshaw Chemical Co.; absorption coefficients deduced from reflection spectrum; data extracted from a figure.
22	127	Kobayashi, K. and Tomiki, T.	1960	R	5.3×10^4-5.52×10^4	285	Single crystal; grown by vacuum distillation; cleaved specimens of 0.6-1.0 mm thick; absorption coefficients measured with a vacuum ultraviolet spectrophotometer; data extracted from a figure.
23	128	Johnson, K. and Bell, E.	1966	R	5.89×10^2-2.86×10^3	300	Single crystal; well polished single surface; reflectivity and phase simultaneously measured by asymmetric Fourier-transform spectroscopy and absorption coefficients deduced from the measurements; data extracted from a figure.
24	105	Ikezawa, M. and Nasu, K.	1973	R	9.0×10^1-1.3×10^2	1.8	Single crystal; grown from pure synthesized powders distilled in vacuum and zoned refined in a quartz tube in chlorine gas; cleaved; geometry not specified; data taken from a curve.

TABLE 33. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF POTASSIUM CHLORIDE (Wavenumber Dependence) (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
25	115	Shrader, E.F.	1974	C	943.4	298	Pure crystal; polished disc specimens of 1 cm thick; absorption coefficient measured by calorimetric method; averaged value of the measurement 0.00089 cm^{-1}; absorption coefficients of doped KCl samples also measured with results of similar order of magnitude as that of pure crystal, temperature was not specified, 298 K discussed.
26	97	Hass, M., Davison, J.W., Rosenstock, H.B., and Babiskin, J.	1975	C	943.4	298	Single crystal; grown in reactive atmosphere; rectangular parallelepiped specimen of length 6.9 cm; all six sides chemically polished; laser calorimetric method used and the thermal rise curve obtained; bulk absorption coefficient determined based on the initial slope of the curve.
27	98	Allen, S.D. and Harrington, J.A.	1978	C	943.4-3571	298	Single crystal; grown by a reactive atmosphere process; rod specimen of 1 cm^2 x 13.97 cm; calorimetric method used; bulk absorption coefficient; data extracted from a figure.
28	119	Hass, M., Harrington, J.A., Gregory, D.A., and Davison, J.W.	1976	C	943.4,3571,2632	298	Single crystal; highly purified and polished rod specimens; measured with laser calorimetric techniques; data extracted from a table; origins of higher absorption at 2.7 μm and 3.8 μm due to impurities in bulk material and surface contamination.
29	118	Deutsch, T.F.	1975	C	1887	298	Single crystal; rod specimen; calorimetric method used; data extracted from a table.
30	129	Mentzel, A.	1934	T	222-455	298	Single crystals; thin film and plate specimens of thickness from 16 μm to 10 mm; absorption coefficients determined from transmission measurements; data extracted from a table.
31	129	Mentzel, A.	1934	Z	422-769	298	Single crystals; plate specimens of 10.7 mm to 1 cm; transmission measured by Ruben and Trowbridge [175] in 1897; incorporated with reflectivity obtained in this reference, the absorption coefficient determined; data extracted from a table.
32	23	Genzel, L., Happ, H., and Weber, R.	1959	T	3.1-33	298	Crystal; plate specimens of 2.5, 5.0, and 35.0 μm thick; transmission measured and absorption coefficient determined; data extracted from a figure.
33	114	Tomiki, T.	1967	Z	$6.1x10^4$-$6.8x10^4$	10	Single crystals; zone refined in the atmosphere of chlorine after the process of the vacuum distillation from the starting powder; specimens with cleaved surfaces; absorption coefficients determined from reflectivity and transmission measurements; data extracted from a figure.
34	114	Tomiki, T.	1967	Z	$5.6x10^4$-$6.7x10^4$	78	Same as above.
35	114	Tomiki, T.	1967	Z	$5.6x10^4$-$6.2x10^4$	85	Same as above.

TABLE 33. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF POTASSIUM CHLORIDE (Wavenumber Dependence) (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
36	114	Tomiki, T.	1967	Z	$5.5x10^4$-$6.2x10^4$	183	Same as above.
37	114	Tomiki, T.	1967	Z	$5.4x10^4$-$6.8x10^4$	295	Same as above.
38	114	Tomiki, T.	1967	Z	$5.3x10^4$-$5.7x10^4$	373	Same as above.
39	114	Tomiki, T.	1967	Z	$5.8x10^4$-$6.3x10^4$	387	Same as above.
40	114	Tomiki, T.	1967	Z	$5.0x10^4$-$6.3x10^4$	477	Same as above.
41	114	Tomiki, T.	1967	Z	$4.8x10^4$-$6.8x10^4$	573	Same as above.
42	99	Rosenstock, H.B., Gregory, D.A., and Harrington, J.A.	1976	C	943.4	298	Single crystals; obtained from the Naval Research Lab., the Harshaw Chemical Co., and the Raytheon Corp.; mechanically polished and chemically cleaned with spectrograde CCl_4; laser calorimetric method used; data taken from a table; it was found that the surface absorption was about 45 times higher than the bulk absorption.
43	121	Rowe, J.M. and Harrington, J.A.	1976	C	943.4-1048	300	Single crystal; grown by the early reactive-atmosphere-process; chemically etched surfaces; total absorption coefficient determined with laser calorimetric method; higher absorption near 9.6 μm due to extrinsic sources; data taken from a figure.
44	121	Rowe, J.M. and Harrington, J.A.	1976	C	943.4-1048	300	Similar to above except for samples grown by improved reactive-atmosphere-process and absorption near 9.6 μm decreased.
45	121	Rowe, J.M. and Harrington, J.A.	1976	C	943.4-1048	100	Same as above.
46	121	Rowe, J.M. and Harrington, J.A.	1976	C	943.4-1048	200	Same as above.

TABLE 34. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM CHLORIDE (Wavenumber Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

ν	α
DATA SET 1	
T = 300	
2.097E+5	2.035E+5
2.089E+5	3.150E+5
2.081E+5	3.661E+5
2.050E+5	4.052E+5
2.016E+5	5.374E+5
1.980E+5	5.910E+5
1.952E+5	6.131E+5
1.944E+5	6.105E+5
1.935E+5	6.[illegible]1E+5
1.927E+5	6.355E+5
1.927E+5	6.455E+5
1.857E+5	6.877E+5
1.871E+5	7.249E+5
1.863E+5	7.431E+5
1.853E+5	7.7[illegible]9E+5
1.859E+5	7.325E+5
1.847E+5	1.123E+5
1.795E+5	7.534E+5
1.782E+5	7.407E+5
1.774E+5	7.134E+5
1.766E+5	6.[illegible]E+5
1.758E+5	6.023E+5
1.751E+5	5.597E+5
1.734E+5	7.[illegible]E+5
1.726E+5	3.075E+5
1.719E+5	5.324E+5
1.714E+5	1.055E+6
1.714E+5	1.117E+6
1.7[illegible]E+5	1.[illegible]E+6
1.712E+5	1.197E+6
1.694E+5	1.[illegible]7E+6
1.685E+5	1.241E+6
1.669E+5	8.511E+5
1.661E+5	7.317E+5
1.657E+5	6.372E+5
1.653E+5	6.643E+5
1.649E+5	6.[illegible]25E+5
1.645E+5	6.522E+5
1.637E+5	6.583E+5

ν	α
DATA SET 1(CONT.)	
1.623E+5	6.9[illegible]E+5
1.625E+5	7.904E+5
1.621E+5	9.166E+5
1.617E+5	9.956E+5
1.613E+5	1.054E+6
1.609E+5	1.092E+6
1.6[illegible]5E+5	1.139E+6
1.597E+5	1.144E+6
1.581E+5	1.132E+6
1.565E+5	1.14[illegible]E+6
1.548E+5	1.113E+6
1.432E+5	8.[illegible]E+5
1.40[illegible]E+5	8.371E+5
1.[illegible]52E+5	6.749E+5
1.444E+5	6.712E+5
1.412E+5	6.917E+5
1.392E+5	7.013E+5
1.357E+5	6.972E+5
1.373E+5	6.932E+5
1.371E+5	6.891E+5
1.347E+5	5.923E+5
1.315E+5	4.295E+5
1.300E+5	4.269E+5
1.293E+5	4.179E+5
1.242E+5	4.526E+5
1.211E+5	4.744E+5
1.194E+5	5.339E+5
1.183E+5	5.874E+5
1.137E+5	7.[illegible]E+5
1.212E+5	7.745E+5
1.239E+5	8.491E+5
1.051E+5	9.234E+5
1.[illegible]05E+5	1.[illegible]3E+6
1.[illegible]06E+5	1.049E+6
1.[illegible]43E+5	1.123E+6
1.[illegible]44E+5	1.181E+6
1.[illegible]43E+5	1.242E+6
1.[illegible]36E+5	1.302E+6
1.332E+5	1.362E+6
1.328E+5	1.421E+6

ν	α
DATA SET 1(CONT.)	
1.[illegible]24E+5	1.467E+6
1.[illegible]2[illegible]E+5	1.513E+6
1.[illegible]1E+5	1.532E+6
1.[illegible]12E+5	1.526E+6
1.[illegible]0E+5	1.467E+6
9.919E+4	1.271E+6
9.[illegible]77E+4	1.049E+6
9.355E+4	7.641E+5
9.194E+4	6.932E+5
9.112E+4	6.413E+5
9.[illegible]32E+4	6.016E+5
8.952E+4	5.849E+5
8.911E+4	5.599E+5
8.871E+4	5.239E+5
8.794E+4	4.529E+5
8.710E+4	4.487E+5
8.5[illegible]E+4	4.297E+5
8.4[illegible]E+4	4.303E+5
8.337E+4	4.532E+5
8.347E+4	4.510E+5
8.3[illegible]E+4	4.175E+5
8.22[illegible]E+4	4.031E+5
8.145E+4	3.889E+5
8.[illegible]5E+4	3.75[illegible]E+5
8.[illegible]24E+4	3.63[illegible]E+5
8.[illegible]E+4	3.720E+5
7.908E+4	3.915E+5
7.935E+4	4.138E+5
7.903E+4	4.568E+5
7.803E+4	5.731E+5
7.923E+4	7.176E+5
7.774E+4	9.[illegible]5E+5
7.742E+4	1.[illegible]41E+6
7.72[illegible]E+4	1.107E+6
7.71[illegible]E+4	1.163E+6
7.694E+4	1.218E+6
7.685E+4	1.246E+6
7.677E+4	1.274E+6
7.609E+4	1.301E+6
7.661E+4	1.319E+6

ν	α
DATA SET 1(CONT.)	
7.653E+4	1.337E+6
7.645E+4	1.355E+6
7.613E+4	1.387E+6
7.581E+4	1.401E+6
7.540E+4	1.364E+6
7.501E+4	1.282E+6
7.419E+4	1.054E+6
7.255E+4	0.332E+5
7.177E+4	5.983E+5
7.116E+4	4.761E+5
6.935E+4	4.445E+5
6.895E+4	4.419E+5
6.855E+4	4.393E+5
6.815E+4	4.453E+5
6.734E+4	4.341E+5
6.774E+4	4.341E+5
6.755E+4	4.161E+5
6.734E+4	3.393E+5
6.694E+4	3.365E+5
0.613E+4	2.742E+5
6.573E+4	2.726E+5
6.532E+4	2.791E+5
6.51[illegible]E+4	2.948E+5
6.5[illegible]E+4	3.[illegible]26E+5
0.5[illegible]E+4	3.186E+5
6.484E+4	3.504E+5
6.4[illegible]E+4	3.826E+5
6.452E+4	4.378E+5
6.435E+4	4.771E+5
0.4[illegible]E+4	5.[illegible]E+5
6.371E+4	7.265E+5
6.331E+4	8.836E+5
6.291E+4	1.043E+6
6.274E+4	1.127E+6
6.258E+4	1.212E+6
6.255E+4	1.249E+6
6.242E+4	1.294E+6
6.234E+4	1.332E+6
6.226E+4	1.361E+6
6.218E+4	1.399E+6

ν	α
DATA SET 1(CONT.)	
6.210E+4	1.397E+6
6.202E+4	1.426E+6
0.194E+4	1.448E+6
6.185E+4	1.461E+6
6.177E+4	1.450E+6
6.169E+4	1.489E+6
6.161E+4	1.471E+6
6.153E+4	1.454E+6
0.145E+4	1.429E+6
0.137E+4	1.383E+6
0.129E+4	1.350E+6
0.113E+4	1.207E+6
6.089E+4	1.079E+6
6.348E+4	7.145E+5
6.[illegible]8E+4	3.779E+5
5.968E+4	1.500E+5
5.887E+4	1.483E+4
5.806E+4	7.297E+3
DATA SET 2	
T = 293.0	
1.654E+5	7.273E+5
1.648E+5	7.512E+5
1.643E+5	7.840E+5
1.638E+5	8.316E+5
1.635E+5	9.223E+5
1.631E+5	1.040E+6
1.624E+5	1.195E+6
1.622E+5	1.130E+6
1.620E+5	1.104E+6
1.618E+5	1.152E+6
1.615E+5	1.182E+6
1.613E+5	1.191E+6
1.603E+5	1.124E+6
1.594E+5	1.016E+6
1.587E+5	9.930E+5
1.573E+5	1.002E+5
1.569E+5	1.074E+5
1.561E+5	1.062E+5

ν	α
DATA SET 2(CONT.)	
1.5[illegible]E+5	9.430E+5
1.532E+5	9.256E+5
1.52[illegible]E+5	9.294E+5
1.5[illegible]E+5	8.22[illegible]E+5
1.493E+5	7.[illegible]0E+5
1.483E+5	6.770E+5
1.474E+5	6.526E+5
1.4[illegible]E+5	6.3[illegible]E+5
1.45[illegible]E+5	6.13[illegible]E+5
1.44[illegible]E+5	6.1[illegible]E+5
1.427E+5	6.37[illegible]E+5
1.417E+5	6.592E+5
1.4[illegible]E+5	6.86[illegible]E+5
1.4[illegible]5E+5	6.80[illegible]E+5
1.399E+5	6.802E+5
1.389E+5	6.5[illegible]E+5
1.371E+5	5.[illegible]E+5
1.35[illegible]E+5	5.44[illegible]E+5
1.337E+5	4.93[illegible]E+5
1.32[illegible]E+5	4.7[illegible]E+5
1.31[illegible]E+5	4.45[illegible]E+5
1.23[illegible]E+5	4.3[illegible]E+5
1.271E+5	4.3[illegible]E+5
1.244E+5	4.52[illegible]E+5
1.23[illegible]E+5	4.75[illegible]E+5
1.21[illegible]E+5	5.1[illegible]E+5
1.199E+5	5.613E+5
1.19[illegible]E+5	5.59[illegible]E+5
1.177E+5	6.150E+5
1.15[illegible]E+5	6.4[illegible]E+5
1.143E+5	6.65[illegible]E+5
1.143E+5	6.9[illegible]E+5
1.137E+5	7.31[illegible]E+5
1.13[illegible]E+5	7.82[illegible]E+5
1.123E+5	8.43[illegible]E+5
1.117E+5	8.92[illegible]E+5
1.109E+5	9.44[illegible]E+5
1.[illegible]E+5	9.8[illegible]E+5
1.[illegible]9[illegible]E+5	1.[illegible]E+6
1.078E+5	1.050E+6

TABLE 34. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM CHLORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 2(CONT.)	
1.072E+5	1.79[illegible]E+6
1.066E+5	1.111E+6
1.061E+5	1.154E+6
1.057E+5	1.231E+6
1.052E+5	1.261E+6
1.048E+5	1.4[illegible]E+6
DATA SET 3	
T = 300.0	
1.078E+3	5.759E-4
1.074E+3	5.371E-4
1.068E+3	5.37[illegible]E-4
1.059E+3	5.17[illegible]E-4
1.054E+3	5.51[illegible]E-4
1.039E+3	5.4[illegible]E-4
1.034E+3	5.91E-4
1.03[illegible]E+3	6.23E-4
1.027E+3	7.11E-4
9.814E+2	2.431E-4
9.760E+2	2.221E-4
9.7[illegible]E+2	2.47E-4
9.693E+2	2.25E-4
9.615E+2	2.07E-4
9.524E+2	1.79E-4
9.479E+2	1.43E-4
9.434E+2	1.03E-4
9.398E+2	2.03E-4
9.355E+2	1.99E-4
9.3[illegible]E+2	2.25E-4
9.289E+2	2.02E-4
9.244E+2	2.29E-4
9.2[illegible]E+2	2.40E-4
DATA SET 4	
T = 293.0	
9.219E+1	7.037E+1
8.340E+1	6.949E+1
7.782E+1	6.191E+1
DATA SET 4(CONT.)	
6.969E+1	5.797E+1
5.311E+1	3.919E+1
4.920E+1	2.891E+1
DATA SET 5	
T = 293.0	
9.591E+1	7.974E+1
8.344E+1	6.979E+1
7.274E+1	6.031E+1
6.472E+1	5.3[illegible]E+1
5.924E+1	4.541E+1
5.42[illegible]E+1	3.467E+1
5.025E+1	2.842E+1
4.307E+1	2.173E+1
DATA SET 6	
T = 293.0	
9.372E+1	7.879E+1
8.[illegible]34E+1	6.074E+1
7.2[illegible]9E+1	5.8[illegible]E+1
6.472E+1	5.124E+1
5.924E+1	4.161E+1
5.42[illegible]E+1	3.324E+1
4.974E+1	2.846E+1
4.04[illegible]E+1	2.47E+1
4.223E+1	2.03E+1
DATA SET 7	
T = 293.0	
7.21[illegible]E+1	5.947E+1
6.481E+1	4.895E+1
5.972E+1	3.971E+1
5.323E+1	3.177E+1
5.12[illegible]E+1	2.987E+1
4.577E+1	2.023E+1
4.[illegible]38E+1	2.226E+1
DATA SET 8	
T = 293.0	
2.485E+5	7.587E+5
2.420E+5	7.938E+5
2.379E+5	4.759E+5
2.35[illegible]E+5	9.853E+5
2.3[illegible]E+5	1.[illegible]E+6
2.283E+5	1.273E+6
2.258E+5	1.61[illegible]E+6
2.237E+5	8.627E+5
2.221E+5	8.345E+5
2.191E+5	8.646E+5
2.142E+5	1.011E+6
2.173E+5	1.270E+6
2.047E+5	1.159E+6
2.027E+5	1.093E+6
1.973E+5	1.012E+6
1.966E+5	9.689E+5
1.919E+5	9.451E+5
1.802E+5	9.650E+5
1.862E+5	1.120E+6
1.8[illegible]E+5	1.[illegible]45E+6
1.8[illegible]E+5	1.[illegible]3E+6
1.791E+5	9.809E+5
1.781E+5	9.514E+5
1.745E+5	9.157E+5
1.75[illegible]E+5	9.368E+5
1.731E+5	1.232E+6
1.711E+5	1.395E+6
1.677E+5	9.334E+5
1.645E+5	7.403E+5
1.623E+5	1.117E+6
1.0[illegible]E+5	1.195E+6
1.58[illegible]E+5	1.107E+6
1.551E+5	1.[illegible]4E+6
1.524E+5	9.979E+5
1.49[illegible]E+5	8.46[illegible]E+5
1.463E+5	7.392E+5
1.44[illegible]E+5	7.276E+5
1.416E+5	7.[illegible]56E+5
1.394E+5	7.793E+5
DATA SET 8(CONT.)	
1.345E+5	6.214E+5
1.3[illegible]9E+5	5.197E+5
1.294E+5	4.893E+5
1.255E+5	4.759E+5
1.225E+5	4.616E+5
1.193E+5	5.1[illegible]9E+5
1.178E+5	5.760E+5
1.139E+5	6.683E+5
1.13[illegible]E+5	7.9[illegible]6E+5
1.0[illegible]1E+5	1.356E+6
1.03[illegible]E+5	1.447E+6
1.021E+5	1.540E+6
9.831E+4	1.174E+6
9.712E+4	1.668E+6
9.53[illegible]E+4	9.751E+5
DATA SET 9	
T = 299.0	
5.727E+4	1.0[illegible]E+2
5.72[illegible]E+4	7.78[illegible]E+1
5.7[illegible]E+4	5.12E+1
5.68[illegible]E+4	1.828E+1
5.665E+4	1.0[illegible]E+1
5.653E+4	6.745E+0
5.645E+4	5.012E+0
5.627E+4	2.754E+0
5.6[illegible]E+4	1.0[illegible]E+0
DATA SET 10	
T = 329.0	
5.674E+4	1.000E+2
5.653E+4	7.78[illegible]E+1
5.656E+4	5.012E+1
5.627E+4	1.828E+1
5.61[illegible]E+4	1.0[illegible]E+1
5.60[illegible]E+4	6.745E+0
5.551E+4	5.112E+0
5.575E+4	2.754E+0
DATA SET 10(CONT.)	
5.546E+4	1.000E+0
DATA SET 11	
T = 373.0	
5.6[illegible]2E+4	1.0[illegible]E+2
5.593E+4	7.780E+1
5.560E+4	5.012E+1
5.548E+4	1.828E+1
5.529E+4	1.0[illegible]E+1
5.518E+4	6.745E+0
5.506E+4	5.012E+0
5.495E+4	2.754E+0
5.455E+4	1.000E+0
DATA SET 12	
T = 426.0	
5.524E+4	1.000E+2
5.515E+4	7.78[illegible]E+1
5.499E+4	5.012E+1
5.403E+4	1.828E+1
5.443E+4	1.000E+1
5.429E+4	6.745E+0
5.418E+4	5.012E+0
5.394E+4	2.754E+0
5.359E+4	1.000E+0
DATA SET 13	
T = 469.0	
5.437E+4	1.000E+2
5.428E+4	7.78[illegible]E+1
5.411E+4	5.012E+1
5.369E+4	1.828E+1
5.3[illegible]7E+4	1.0[illegible]E+1
5.331E+4	6.745E+0
5.319E+4	5.012E+0
5.294E+4	2.754E+0
5.258E+4	1.000E+0
DATA SET 14	
T = 298.0	
1.245E+3	6.300E-5
1.232E+3	1.320E-4
1.219E+3	3.[illegible]E-4
1.202E+3	4.3[illegible]E-4
1.18[illegible]E+3	7.[illegible]E-4
1.174E+3	9.4[illegible]E-4
1.16[illegible]E+3	1.3[illegible]E-3
1.147E+3	1.710E-3
1.135E+3	2.07[illegible]E-3
1.122E+3	2.620E-3
1.103E+3	3.60[illegible]E-3
1.0[illegible]3E+3	5.0[illegible]E-3
1.0[illegible]E+3	6.1[illegible]E-3
1.043E+3	6.420E-3
1.037E+3	6.54[illegible]E-3
1.024E+3	6.54[illegible]E-3
1.[illegible]2E+3	6.3[illegible]E-3
9.953E+2	5.380E-3
9.78[illegible]E+2	4.9[illegible]E-3
9.00[illegible]E+2	3.73[illegible]E-3
9.440E+2	2.470E-3
9.3[illegible]E+2	1.060E-3
9.[illegible]9E+2	4.1[illegible]E-4
9.[illegible]00E+2	1.0[illegible]E-4
8.640E+2	2.0[illegible]E-5
8.54[illegible]E+2	1.0[illegible]E-4
8.44[illegible]E+2	2.3[illegible]E-4
8.33[illegible]E+2	4.2[illegible]E-4
8.23[illegible]E+2	6.3[illegible]E-4
8.13[illegible]E+2	8.9[illegible]E-4
8.0[illegible]E+2	1.370E-3
DATA SET 15	
T = 3[illegible].0	
7.5[illegible]E+2	3.22[illegible]E-3
6.969E+2	6.9[illegible]E-3
6.439E+2	1.49[illegible]E-2
5.991E+2	6.22[illegible]E-2

TABLE 34. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM CHLORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 15(CONT.)	
5.531E+2	1.845E-1
5.640E+2	5.152E-1
DATA SET 16	
T = 3[illegible]	
7.5[illegible]E+2	[illegible]
6.993E+2	1.[illegible]E-2
5.301E+2	5.321E-2
DATA SET 17	
T = 3[illegible]	
7.5[illegible]E+2	[illegible]
7.[illegible]	[illegible]
5.91[illegible]E+2	1.0[illegible]
4.37[illegible]E+2	[illegible]77E-1
[illegible]E+2	1.153E+0
DATA SET 18	
T = [illegible]	
5.21[illegible]E+4	2.193E+1
5.2[illegible]E+4	1.337E+1
[illegible]E+4	5.321E+0
5.195E+4	3.311E+0
[illegible]E+4	2.367E+0
[illegible]	[illegible]
[illegible]E+4	1.122E+0
5.273E+4	[illegible]
5.104E+4	[illegible]E-1
5.159E+4	[illegible]E-1
5.145E+4	3.573E-1
5.125E+4	2.[illegible]E-1
[illegible]	1.73[illegible]E-1
[illegible]	1.2[illegible]E-1
5.23[illegible]E+4	5.354E-2
5.984E+4	5.306E-2
5.899E+4	[illegible]E-2
5.954E+4	3.[illegible]E-2

ν	α
DATA SET 18(CONT.)	
5.4[illegible]E+4	2.323E-2
5.794E+4	2.128E-2
5.645E+4	1.430E-2
DATA SET 19	
T = 4[illegible]	
[illegible]E+4	2.208E+1
[illegible]E+4	1.549E+1
[illegible]E+4	6.982E+0
[illegible]E+4	3.491E+0
[illegible]	[illegible]
[illegible]	[illegible]
[illegible]E+4	2.57[illegible]E+0
[illegible]E+4	2.32[illegible]E+0
[illegible]E+4	1.01[illegible]E+0
[illegible]E+4	1.351E+0
[illegible]E+4	1.05[illegible]E+0
[illegible]E+4	7.244E-1
[illegible]	[illegible]E-1
[illegible]E+4	2.143E-1
[illegible]E+4	1.722E-1
[illegible]E+4	7.621E-2
[illegible]	6.577E-2
5.937E+4	7.447E-2
[illegible]	[illegible]E-2
[illegible]	4.74[illegible]E-2
[illegible]	[illegible]
[illegible]E+4	3.459E-2
5.873E+4	3.219E-2
5.855E+4	2.854E-2
5.812E+4	2.338E-2
5.793E+4	2.[illegible]3E-2
5.757E+4	1.454E-2
5.6[illegible]E+4	1.044E-2
DATA SET 20	
T = 299.0	
5.8[illegible]E+4	1.528E+1

ν	α
DATA SET 20(CONT.)	
5.790E+4	9.511E+0
5.775E+4	4.656E+0
5.765E+4	2.924E+0
5.75[illegible]E+4	2.793E+0
5.735E+4	1.670E+0
5.726E+4	9.457E-1
5.719E+4	4.7[illegible]E-1
5.713E+4	3.819E-1
5.693E+4	2.099E-1
5.683E+4	1.380E-1
5.667E+4	8.356E-2
5.651E+4	5.593E-2
5.645E+4	4.285E-2
DATA SET 21	
T = 299.0	
1.631E+5	1.220E+6
1.732E+5	1.020E+6
1.77[illegible]E+5	9.760E+5
1.75[illegible]E+5	9.[illegible]0E+5
1.726E+5	1.[illegible]0E+6
1.718E+5	1.340E+6
1.7[illegible]2E+5	1.420E+6
1.695E+5	1.350E+6
1.037E+5	9.000E+5
1.021E+5	8.200E+5
1.0[illegible]5E+5	8.900E+5
1.[illegible]5E+5	1.420E+6
1.[illegible]08E+5	7.400E+5
1.452E+5	6.700E+5
1.4[illegible]3E+5	7.260E+5
1.363E+5	7.2[illegible]0E+5
1.347E+5	6.0[illegible]E+5
1.315E+5	5.300E+5
1.266E+5	4.500E+5
1.2[illegible]E+5	5.400E+5
1.153E+5	7.500E+5
1.121E+5	9.500E+5
1.081E+5	1.040E+6

ν	α
DATA SET 21(CONT.)	
1.037E+5	1.550E+6
9.839E+4	9.800E+5
9.516E+4	7.260E+5
9.113E+4	5.110E+5
8.629E+4	4.100E+5
8.287E+4	4.[illegible]E+5
8.145E+4	4.170E+5
7.934E+4	5.200E+5
7.742E+4	1.390E+6
7.177E+4	5.[illegible]0E+5
7.097E+4	3.900E+5
6.[illegible]5E+4	3.[illegible]E+5
6.694E+4	2.700E+5
6.632E+4	5.100E+5
6.296E+4	1.230E+6
6.048E+4	1.9[illegible]E+5
5.968E+4	9.00E+4
5.9[illegible]E+4	3.[illegible]E+4
DATA SET 22	
T = 285.0	
5.516E+4	1.342E+1
5.432E+4	9.700E+0
5.476E+4	6.910E+0
5.468E+4	4.958E+0
5.444E+4	2.826E+0
5.331E+4	1.310E-1
DATA SET 23	
T = 300.0	
2.850E+2	1.081E-2
2.4[illegible]3E+2	2.139E-2
2.734E+2	2.41[illegible]E-2
2.733E+2	2.594E-2
2.675E+2	2.9[illegible]5E-2
2.407E+2	1.426E-1
2.384E+2	1.578E-1
2.356E+2	1.637E-1

ν	α
DATA SET 23(CONT.)	
2.309E+2	1.667E-1
2.263E+2	1.811E-1
2.227E+2	2.061E-1
2.151E+2	5.224E-1
2.140E+2	5.5[illegible]E-1
2.118E+2	5.6[illegible]E-1
2.1[illegible]E+2	5.37[illegible]E-1
2.074E+2	5.105E-1
2.053E+2	5.105E-1
2.115E+2	5.152E-1
1.987E+2	5.297E-1
1.932E+2	6.577E-1
1.891E+2	7.834E-1
1.853E+2	9.71[illegible]E-1
1.731E+2	1.259E+0
1.626E+2	1.91[illegible]E+0
1.55[illegible]E+2	2.754E+0
1.491E+2	3.3[illegible]E+0
1.454E+2	5.346E+0
1.422E+2	5.754E+0
1.355E+2	2.642E+0
1.313E+2	3.963E-1
1.272E+2	2.613E-1
1.215E+2	2.023E-1
1.146E+2	1.629E-1
1.074E+2	1.361E-1
9.940E+1	1.112E-1
9.612E+1	8.954E-2
9.372E+1	6.942E-2
9.192E+1	6.457E-2
9.0[illegible]E+1	6.516E-2
8.84[illegible]E+1	6.855E-2
8.66[illegible]E+1	8.054E-2
8.55[illegible]E+1	9.247E-2
8.36[illegible]E+1	1.023E-1
7.962E+1	1.127E-1
7.59[illegible]E+1	1.1[illegible]E-1
7.341E+1	1.152E-1
7.110E+1	9.727E-2
5.830E+1	4.446E-2

ν	α
DATA SET 24	
T = 1.9	
1.30[illegible]E+2	3.631E+3
1.279E+2	2.911E+3
1.275E+2	2.692E+3
1.2[illegible]E+2	2.3[illegible]E+0
1.253E+2	1.993E+0
1.2[illegible]E+2	1.8[illegible]E+0
1.253E+2	1.826E+0
1.247E+2	1.920E+0
1.241E+2	1.7[illegible]E+0
1.239E+2	1.74[illegible]E+0
1.2[illegible]E+2	1.692E+0
1.22[illegible]E+2	1.[illegible]E+0
1.2[illegible]E+2	1.8[illegible]E+0
1.194E+2	1.[illegible]E+0
1.189E+2	1.[illegible]E+0
1.185E+2	1.5[illegible]E+0
1.1[illegible]E+2	1.941E+0
1.17[illegible]E+2	1.77[illegible]E+0
1.171E+2	1.931E+0
1.15[illegible]E+2	2.076E+0
1.1[illegible]E+2	1.[illegible]E+0
1.1[illegible]E+2	1.334E+0
1.1[illegible]E+2	9.376E-1
1.147[illegible]	8.453E-1
1.13[illegible]E+2	6.714E-1
1.123E+2	5.340E-1
1.1[illegible]E+2	4.[illegible]E-1
1.12[illegible]E+2	4.[illegible]7E-1
1.11[illegible]E+2	4.25[illegible]E-1
1.10[illegible]E+2	4.13[illegible]E-1
1.096E+2	4.13[illegible]E-1
1.093E+2	4.270E-1
1.092E+2	5.244E-1
1.07[illegible]E+2	5.3[illegible]E-1
1.076E+2	5.10[illegible]E-1
1.074E+2	5.0[illegible]E-1
1.0[illegible]E+2	4.457E-1
1.0[illegible]E+2	4.335E-1
1.043E+2	4.285E-1

TABLE 34. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM CHLORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 24(CONT.)	
1.[illegible]E+2 [illegible]E-1	
1.[illegible]E+2 [illegible]E-1	
1.[illegible]E+2 [illegible]E-1	
9.9[illegible]E+1 [illegible]E-1	
9.9[illegible]E+1 [illegible]E-1	
9.[illegible]E+1 [illegible]E-1	
9.[illegible]E+1 [illegible]E-1	
9.[illegible]E+1 [illegible]E-1	
DATA SET 25	
T = 298.0	
9.[illegible]E+2 [illegible]E+0	
DATA SET 26	
T = 295.0	
9.[illegible]E+2 [illegible]E+0	
DATA SET 27	
T = 295.0	
1.[illegible]E+3 [illegible]E+0	
[illegible]E+3 [illegible]E+0	
1.[illegible]E+3 [illegible]E-7	
[illegible]E+3 [illegible]E-5	
1.[illegible]E+3 [illegible]E+0	
[illegible]E+3 [illegible]E-5	
[illegible]E+3 [illegible]E+0	
DATA SET 28	
T = 293.0	
[illegible]E+3 [illegible]E+0	
3.7[illegible]E+3 3.7[illegible]E+0	
2.632E+3 2.1[illegible]E+0	

ν	α
DATA SET 29	
T = 298.0	
1.337E+3 2.5[illegible]E-5	
DATA SET 30	
T = 291.0	
4.9[illegible]E+2 1.257E+0	
[illegible]E+2 [illegible]E+0	
3.[illegible]E+2 4.[illegible]E+0	
3.57[illegible]E+2 0.73[illegible]E+0	
3.322E+2 1.257E+1	
3.1[illegible]E+2 2.[illegible]E+1	
2.9[illegible]E+2 3.[illegible]E+1	
2.77[illegible]E+1 0.981E+1	
2.[illegible]E+2 1.[illegible]E+2	
2.5[illegible]E+2 2.[illegible]E+2	
2.[illegible]E+1 3.19E+2	
2.273E+2 [illegible]E+2	
2.[illegible]E+2 8.93E+2	
DATA SET 31	
T = 294.0	
7.032E+2 8.[illegible]E-3	
7.1[illegible]E+2 [illegible]E-2	
6.[illegible]E+2 7.398E-2	
6.2[illegible]E+2 1.[illegible]E-1	
5.932E+2 1.361E-1	
5.5[illegible]E+2 2.[illegible]E-1	
5.[illegible]E+2 [illegible]E-1	
[illegible]E+2 [illegible]E-1	
[illegible]E+2 3.[illegible]E+0	
DATA SET 32	
T = 290.0	
3.3[illegible]E+1 1.373E+1	
2.8[illegible]E+1 9.[illegible]E+0	
2.5[illegible]E+1 7.440E+0	
2.[illegible]E+1 5.917E+1	

ν	α
DATA SET 32(CONT.)	
2.012E+1 4.880E+0	
1.82[illegible]E+1 3.891E+0	
1.601E+1 3.152E+0	
1.946E+1 2.758E+0	
1.437E+1 2.419E+0	
1.337E+1 2.05[illegible]E+1	
1.255E+1 1.861E+0	
1.178E+1 1.[illegible]E+0	
1.[illegible]E+1 1.293E+0	
1.[illegible]E+1 1.132E+0	
9.615E+0 1.032E+0	
8.929E+0 8.937E-1	
8.021E+0 7.562E-1	
7.822E+1 6.853E-1	
8.403E+0 6.727E-1	
7.2[illegible]E+0 5.537E-1	
7.1[illegible]E+0 4.892E-1	
6.329E+0 3.91[illegible]E-1	
5.567E+0 3.068E-1	
5.65[illegible]E+0 2.842E-1	
4.639E+0 1.870E-1	
3.953E+0 1.390E-1	
3.993E+0 1.286E-1	
3.125E+0 0.715E-2	
DATA SET 33	
T = 10.0	
6.8.6E+4 3.[illegible]E+5	
6.7[illegible]E+4 2.[illegible]E+5	
6.777E+4 1.093E+5	
6.765E+4 1.[illegible]E+5	
6.727E+4 5.5[illegible]E+4	
6.045E+4 5.53[illegible]E+4	
6.0[illegible]E+4 1.9[illegible]E+5	
6.019E+4 2.218E+5	
6.544E+4 3.715E+5	
6.565E+4 5.[illegible]E+5	
6.530E+4 6.664E+5	
6.51[illegible]E+4 9.162E+5	

ν	α
DATA SET 33(CONT.)	
6.472E+4 1.153E+6	
6.437E+4 1.458E+6	
6.402E+4 1.907E+6	
6.375E+4 2.619E+6	
6.355E+4 3.754E+6	
6.334E+4 1.[illegible]E+6	
6.329E+4 1.009E+6	
6.322E+4 6.91[illegible]E+5	
6.319E+4 8.091E+5	
6.296E+4 1.412E+6	
6.247E+4 2.123E+6	
6.273E+4 2.432E+6	
6.2[illegible]E+4 1.577E+6	
6.292E+4 3.361E+6	
6.2[illegible]E+4 1.2[illegible]E+6	
6.213E+4 3.133E+2	
6.190E+4 8.033E+1	
6.191E+4 3.09[illegible]E+1	
6.184E+4 1.907E+1	
6.177E+4 1.086E+1	
6.169E+4 9.375E+0	
6.162E+4 5.023E+0	
6.111E+4 2.606E+0	
DATA SET 34	
T = 79.3	
6.739E+4 7.620E+4	
6.713E+4 4.[illegible]87E+4	
6.683E+4 9.320E+4	
6.632E+4 1.2[illegible]E+5	
6.595E+4 3.095E+5	
6.5[illegible]E+4 7.244E+5	
6.45[illegible]E+4 1.[illegible]E+6	
6.4[illegible]E+4 1.5[illegible]E+6	
6.371E+4 1.977E+6	
6.357E+4 2.396E+6	
6.3[illegible]E+4 2.396E+6	
6.323E+4 1.836E+6	
6.300E+4 1.264E+6	

ν	α
DATA SET 34(CONT.)	
6.29[illegible]E+4 1.1[illegible]E+6	
6.264E+4 1.699E+6	
6.252E+4 1.699E+6	
6.244E+4 1.169E+6	
6.219E+4 2.355E+5	
6.2[illegible]E+4 1.047E+5	
6.156E+4 2.992E+2	
6.14[illegible]E+4 1.55[illegible]E+2	
6.1[illegible]E+4 9.397E+1	
6.1[illegible]E+4 1.379E+1	
6.115E+4 8.749E+0	
6.117E+4 5.152E+0	
6.12[illegible]E+4 3.162E+0	
6.1[illegible]E+4 2.582E+0	
6.[illegible]E+4 1.762E+0	
6.054E+4 1.282E+0	
6.117E+4 8.995E-1	
5.993E+4 6.31[illegible]E-1	
5.979E+4 5.702E-1	
5.941E+4 4.592E-1	
5.892E+4 4.1[illegible]E-1	
5.841E+4 3.[illegible]E-1	
5.787E+4 2.27[illegible]E-1	
5.644E+4 1.39[illegible]E-1	
DATA SET 35	
T = 85.3	
6.135E+4 1.570E+2	
6.12[illegible]E+4 5.75[illegible]E+1	
6.122E+4 4.1[illegible]E+1	
6.117E+4 1.723E+1	
6.1[illegible]E+4 1.[illegible]47E+1	
6.099E+4 4.264E+0	
6.09[illegible]E+4 2.582E+0	
6.082E+4 1.762E+0	
6.054E+4 1.282E+0	
6.117E+4 8.995E-1	
5.993E+4 6.31[illegible]E-1	
5.979E+4 5.702E-1	

ν	α
DATA SET 35(CONT.)	
5.[illegible]E+4 4.591E-1	
5.8[illegible]E+4 4.1[illegible]E-1	
5.8[illegible]E+4 3.[illegible]E-1	
5.737E+4 2.270E-1	
5.637E+4 1.3[illegible]E-1	
DATA SET 36	
T = 183.0	
6.21[illegible]E+4 1.23[illegible]E+6	
6.194E+4 1.155E+6	
6.169E+4 7.470E+5	
6.156E+4 7.[illegible]E+5	
6.121E+4 6.1[illegible]E+5	
6.095E+4 4.871E+4	
6.077E+4 1.541E+4	
6.597E+4 1.361E+2	
5.95[illegible]E+4 3.71[illegible]E+1	
5.937E+4 1.255E+1	
5.927E+4 6.836E+0	
5.912E+4 2.779E+0	
5.900E+4 1.745E+0	
5.830E+4 1.116E+0	
5.[illegible]E+4 0.194E-1	
5.692E+4 4.10[illegible]E-1	
5.830E+4 3.135E-1	
5.794E+4 2.818E-1	
5.730E+4 2.032E-1	
5.644E+4 1.563E-1	
5.935E+4 1.[illegible]E-1	
5.925E+4 1.066E-1	
DATA SET 37	
T = 295.0	
6.754E+4 2.837E+5	
6.7[illegible]E+4 2.35[illegible]E+5	
6.632E+4 2.2[illegible]E+5	
6.544E+4 2.[illegible]E+5	
6.540E+4 1.852E+6	

TABLE 34. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM CHLORIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 37(CONT.)	
6.564E+4	2.323E+5
6.542E+4	2.423E+5
6.522E+4	2.293E+5
6.499E+4	2.6[illegible]E+5
6.465E+4	2.047E+5
6.442E+4	4.697E+5
6.399E+4	9.[illegible]3E+5
6.370E+4	7.[illegible]9E+5
6.357E+4	7.702E+5
6.327E+4	8.922E+5
6.291E+4	1.[illegible]9E+6
[illegible]	[illegible]
6.179E+4	1.2[illegible]E+6
[illegible]	[illegible]
6.12[illegible]E+4	9.317E+5
6.193E+4	6.[illegible]E+5
6.173E+4	6.[illegible]E+5
6.147E+4	[illegible]
[illegible]	[illegible]
[illegible]	[illegible]
5.[illegible]11E+4	9.7[illegible]E+4
5.[illegible]E+4	2.7[illegible]E+4
5.3[illegible]E+4	5.3[illegible]E+3
5.313E+4	[illegible]
5.79[illegible]E+4	7.69[illegible]E+1
[illegible]	[illegible]
5.7[illegible]E+4	[illegible]
5.7[illegible]E+4	[illegible]
5.699E+4	[illegible]
5.665E+4	4.3[illegible]E-1
5.637E+4	9.572E-1
5.614E+4	6.911E-1
5.592E+4	1.3[illegible]E-1
5.550E+4	1.5[illegible]E-1
5.522E+4	1.219E-1
5.[illegible]07E+4	1.219E-1

ν	α
DATA SET 38	
T = 373.0	
5.67[illegible]E+4	7.178E+1
5.64[illegible]E+4	2.079E+1
5.607E+4	1.312E+1
5.592E+4	5.75[illegible]E+0
5.543E+4	1.977E+0
5.528E+4	1.071E+0
5.495E+4	4.556E-1
5.469E+4	3.230E-1
5.439E+4	2.158E-1
5.38[illegible]E+4	1.270E-1
5.36[illegible]E+4	1.091E-1
5.326E+4	8.030E-2
DATA SET 39	
T = 387.0	
6.283E+4	6.394E+5
6.254E+4	9.59[illegible]E+5
[illegible]	[illegible]
6.[illegible]E+4	1.153E+6
6.21[illegible]E+4	1.[illegible]27E+6
6.1[illegible]E+4	9.2[illegible]E+5
5.22[illegible]E+4	6.363E+5
5.913E+4	4.207E+5
5.47[illegible]E+4	3.[illegible]02E+5
5.9[illegible]E+4	2.370E+5
5.924E+4	[illegible]
5.477E+4	4.875E+4
5.435E+4	1.241E+4
DATA SET 40	
T = 477.0	
6.292E+4	6.729E+5
6.245E+4	6.241E+5
6.197E+4	9.082E+5
6.133E+4	1.[illegible]00E+6
6.[illegible]74E+4	1.[illegible]06E+6
6.030E+4	9.[illegible]76E+5

ν	α
DATA SET 40(CONT.)	
5.993E+4	7.691E+5
5.94[illegible]E+4	5.248E+5
5.91[illegible]E+4	3.564E+5
5.877E+4	2.498E+5
5.852E+4	1.472E+5
5.810E+4	6.637E+4
5.79[illegible]E+4	4.742E+4
5.73[illegible]E+4	1.5[illegible]6E+4
5.5[illegible]4E+4	1.3[illegible]6E+2
5.526E+4	7.762E+1
5.481E+4	3.235E+1
5.4[illegible]E+4	2.[illegible]1E+1
5.4[illegible]E+4	9.120E+0
5.378E+4	2.937E+0
5.323E+4	8.395E-1
5.267E+4	4.636E-1
5.268E+4	2.729E-1
5.212E+4	1.271E-1
5.18[illegible]E+4	1.265E-1
5.122E+4	6.983E-2
5.077E+4	6.246E-2
5.10[illegible]E+4	5.150E-2
DATA SET 41	
T = 573.0	
6.5[illegible]E+4	3.0[illegible]E+5
6.3[illegible]E+4	3.047E+5
6.725E+4	3.981E+5
6.692E+4	3.981E+5
6.643E+4	3.064E+5
6.523E+4	3.0[illegible]E+5
6.449E+4	3.9[illegible]E+5
6.43[illegible]E+4	4.[illegible]0E+5
6.371E+4	4.699E+5
6.293E+4	5.97[illegible]E+5
6.217E+4	6.982E+5
6.165E+4	7.906E+5
6.119E+4	8.669E+5
6.054E+4	9.289E+5

ν	α
DATA SET 41(CONT.)	
5.994E+4	8.591E+5
5.94[illegible]E+4	7.516E+5
5.911E+4	6.381E+5
5.870E+4	4.952E+5
5.848E+4	4.017E+5
5.79[illegible]E+4	2.218E+5
5.73[illegible]E+4	1.[illegible]6E+5
5.64[illegible]E+4	1.52[illegible]E+4
5.43[illegible]E+4	2.3[illegible]E+2
5.377E+4	8.128E+1
5.323E+4	2.642E+1
5.29[illegible]E+4	1.432E+1
5.268E+4	1.037E+1
5.268E+4	8.165E+1
5.239E+4	4.898E+0
5.239E+4	3.989E+0
5.213E+4	3.519E+0
5.2[illegible]E+4	2.766E+0
5.192E+4	1.621E+0
5.133E+4	5.649E-1
5.077E+4	2.489E-1
5.125E+4	1.294E-1
4.974E+4	8.24[illegible]E-2
4.943E+4	5.6[illegible]E-2
4.881E+4	5.89[illegible]E-2
4.843E+4	3.64[illegible]E-2
4.843E+4	3.52[illegible]E-2
4.834E+4	3.87[illegible]E-2
DATA SET 42	
T = 298.0	
9.434E+2	8.03[illegible]E-5
DATA SET 43	
T = 3[illegible].0	
9.434E+2	8.93[illegible]E-4
9.524E+2	7.954E-4
9.709E+2	8.02[illegible]E-4

ν	α
DATA SET 43(CONT.)	
9.901E+2	6.330E-4
1.036E+3	2.1[illegible]E-3
1.049E+3	2.383E-3
DATA SET 44	
T = 3[illegible].0	
9.434E+2	1.950E-4
1.0[illegible]E+3	1.93[illegible]E-4
1.034E+3	4.4[illegible]E-4
1.045E+3	4.12[illegible]E-4
DATA SET 45	
T = 16[illegible].0	
9.434E+2	8.280E-5
9.432E+2	1.132E-4
1.035E+3	4.219E-4
1.047E+3	2.961E-4
DATA SET 46	
T = 2[illegible].0	
9.434E+2	1.502E-4
9.832E+2	1.572E-4
1.035E+3	4.465E-4
1.047E+3	3.493E-4



Figure 24. Absorption Coefficient of Potassium Chloride (Temperature Dependence)

TABLE 35. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF POTASSIUM CHLORIDE (Temperature Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	78	Harrington, J.A. and Hass, M.	1973	C	943.4	297-1000	Single crystal; obtained from the Harshaw Chemical Co.; specimen with surfaces mechanically and then chemically polished; absorption coefficients measured by calorimetric method using a CO_2 laser source; data extracted from a figure.
2	78	Harrington, J.A. and Hass, M.	1973	C	943.4	299-944	Similar to above except for crystal obtained from Hughes Research Laboratories.
3	117	Boyer, L.L., Harrington, J.A., Hass, M., and Rosenstock, H.B.	1974	C	943.4	312-920	Crystal; obtained from the Harshaw Chemical Co.; absorption coefficients measured by calorimetric method with a laser source; data extracted from a figure.
4	117	Boyer, L.L., et al.	1974	C	943.4	312-960	Similar to above except for crystal obtained from the Hughes Co.
5	117	Boyer, L.L., et al.	1974	C	943.4	337-796	Similar to above except for crystals grown by the Naval Research Lab. under conditions designed to minimize the introduction of oxygen-containing impurities which can give rise to absorption bands in the mid-infrared region.
6	117	Boyer, L.L., et al.	1974	C	943.4	337.3	Similar to above except for crystals grown in a CCl_4 reactive atmosphere; it was observed that the crystal grown in this way has the least absorption among the crystals from various sources.
7	100	Rowe, J.M. and Harrington, J.A.	1976	C	943.4	100-300	Single crystals; grown by the reactive-atmosphere-process; obtained from the Naval Research Laboratory; rod specimens of 2.5 cm diameter and of various lengths; chemically etched surface; bulk absorption determined; data extracted from a figure; data at low temperature carried large uncertainty of ±100%; uncertainty diminished toward higher temperatures.

TABLE 36. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM CHLORIDE (Temperature Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, ν, cm^{-1}]

T	α
DATA SET 1	
ν = 9.434E+2	
297.1	3.570E-3
368.9	4.750E-3
479.7	4.360E-3
553.3	4.240E-3
659.1	3.550E-3
731.6	4.440E-3
833.6	3.000E-3
916.2	3.360E-3
1000.0	4.740E-3
DATA SET 2	
ν = 9.434E+2	
299.2	1.340E-3
371.5	1.430E-3
464.5	1.120E-3
553.8	1.650E-3
676.0	2.250E-3
816.5	2.070E-3
944.0	4.430E-3
DATA SET 3	
ν = 9.434E+2	
312.6	3.600E-3
380.2	4.350E-3
450.4	4.410E-3
575.4	4.440E-3
659.9	3.720E-3
767.4	4.570E-3
833.7	3.210E-3
920.4	4.110E-3
DATA SET 4	
ν = 9.434E+2	
312.6	1.870E-3
386.4	1.510E-3
476.4	1.140E-3
DATA SET 4(CONT.)	
578.1	1.670E-3
833.7	2.810E-3
959.4	4.540E-3
DATA SET 5	
ν = 9.434E+2	
337.3	3.200E-4
399.0	5.160E-4
430.4	8.430E-4
570.2	9.520E-4
660.7	1.320E-3
730.4	1.850E-3
750.2	2.550E-3
DATA SET 6	
ν = 9.434E+2	
337.3	1.900E-4
DATA SET 7	
ν = 9.434E+2	
100.0	3.070E-5
124.0	2.330E-5
150.0	2.330E-5
175.0	3.000E-5
198.0	3.630E-5
224.0	4.550E-5
248.0	5.870E-5
274.0	7.870E-5
299.0	1.070E-4



Figure 25. Reflectivity of Potassium Chloride

TABLE 37. SUMMARY OF MEASUREMENTS ON THE REFLECTIVITY OF POTASSIUM CHLORIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	122	Antinori, M., Balzarotti, A., and Piacentini, M.	1973	R	0.061-0.094	293	Single crystal; obtained from the Harshaw Chemical Co.; specimen cleaved in air just before being mounted in the sample chamber to be vacuum pumped; reflection spectrum obtained with a monochromator of band width of 1.5 A; measurement performed on the same specimen after 24 hrs did not show significant changes and reproduced with uncertainty of about 5%; data extracted from a figure.
2	101	Czerny, M.	1930	R	42.6-70.4	293	Synthetic crystal; plate specimen; polished surface; normal spectral reflectivity obtained with silver mirror as reference; data extracted from a figure; temperature not given, 293 K assumed.
3	102	Cartwright, C.M. and Czerny, M.	1934	R	126.0-231.0	293	Bulk KCl; surface conditions unspecified; near normal reflectivity obtained; linearly averaged values of tabulated data were extracted.
4	120	Blechschmidt, D., Klucker, R., and Skibowski, M.	1969	R	0.035-0.089	293	Single crystals provided by Karl Korth, Kiel, Germany; freshly cleaved specimen; near normal reflectivity measured in vacuum for polarized light with normal of the specimen lying on both sides of the incident beam for increased accuracy; data extracted from a figure.
5	110	Baldini, G. and Bosacchi, B.	1968	R	0.122-0.179	300	Single crystals; specimen with cleaved surface; back surface of the specimen treated with an emery cloth to reduce the reflection from the back; near normal reflectivity obtained with specimen in vacuum; data extracted from a figure.
6	110	Baldini, G. and Bosacchi, B.	1968	R	0.120-0.170	55	Same as above except at low temperature.
7	126	Philipp, H.R. and Ehrenreich, H.	1963	R	0.055-0.653	298	Single crystal; near normal reflection spectrum measured; data extracted from a curve.
8	114	Tomiki, T.	1967	R	0.147-0.171	10	Single crystal; grown by the Kyropoulos technique; specimen cleaved from the grown ingots; near normal reflectivity measured; data extracted from a figure.
9	114	Tomiki, T.	1967	R	0.147-0.173	78	Same as above.
10	114	Tomiki, T.	1967	R	0.106-0.148	295	Same as above.
11	123	Johnson, K. and Bell, E.	1969	R	27.2-229.2	300	Single crystal; well polished single surface; reflectivity measured by asymmetric Fourier-transform spectroscopy; data extracted from a figure.

TABLE 38. EXPERIMENTAL DATA ON THE REFLECTIVITY OF POTASSIUM CHLORIDE

[Wavelength, λ, μm; Temperature, T, K; Reflectivity, ρ]

λ	ρ
DATA SET 1	
T = 293.0	
0.0630	0.0347
0.0626	0.0354
0.0623	0.0412
0.0621	0.0482
0.0612	0.0511
0.0615	0.0502
0.0614	0.0629
0.0615	0.0739
0.0615	0.0376
0.0617	0.0424
0.0619	0.0797
0.0621	0.0516
0.0623	0.0744
0.0627	0.0918
0.0629	0.0931
0.0631	0.0570
0.0633	0.0502
0.0636	0.0548
0.0639	0.0602
0.0641	0.0648
0.0643	0.0592
0.0651	0.0537
0.0653	0.0519
0.0658	0.0523
0.0661	0.0510
0.0665	0.0432
0.0669	0.0348
0.0673	0.0353
0.0675	0.0345
0.0679	0.0349
0.0682	0.0293
0.0687	0.0279
0.0693	0.0279
0.0707	0.0324
0.0714	0.0351
0.0718	0.0351
0.0720	0.0319
0.0734	0.0230
0.0742	0.0249

λ	ρ
DATA SET 1(CONT.)	
0.0748	0.0214
0.0755	0.0194
0.0846	0.0183
0.0775	0.0193
0.0787	0.0193
0.0795	0.0213
0.0814	0.0237
0.0811	0.0287
0.0827	0.0365
0.0822	0.0343
0.0828	0.0395
0.0833	0.0455
0.0839	0.0547
0.0848	0.0575
0.0860	0.0638
0.0864	0.0673
0.0870	0.0675
0.0875	0.0774
0.0892	0.1249
0.0893	0.1289
0.0894	0.1325
0.0897	0.1387
0.0914	0.1443
0.0920	0.1496
0.0926	0.1543
0.0930	0.1642
0.0933	0.1687
0.0935	0.1746
0.0939	0.0[illegible]
DATA SET 2	
T = 293.0	
42.0	0.092
42.7	0.118
43.7	0.132
43.8	0.105
44.8	0.147
45.9	0.227

λ	ρ
DATA SET 2(CONT.)	
46.1	0.200
47.2	0.156
47.2	0.173
48.3	0.164
48.4	0.188
49.4	0.232
49.6	0.243
50.6	0.285
50.7	0.319
51.8	0.369
51.9	0.391
52.9	0.473
53.1	0.463
54.1	0.557
54.2	0.534
55.2	0.627
55.4	0.629
56.4	0.728
56.5	0.714
57.5	0.797
57.7	0.816
58.7	0.819
58.8	0.845
58.8	0.886
59.8	0.933
59.9	0.962
61.0	0.894
61.2	0.844
62.2	0.963
62.3	0.991
63.3	0.859
63.4	0.872
64.6	0.839
65.7	0.839
67.9	0.812
68.1	0.817
69.1	0.866
69.3	0.814
71.3	0.833
71.4	0.772

λ	ρ
DATA SET 3	
T = 293.0	
126.0	0.172
147.0	0.154
174.0	0.161
204.0	0.151
231.0	0.161
DATA SET 4	
T = 293.0	
0.0353	0.101
0.0357	0.093
0.0361	0.069
0.0365	0.069
0.0371	0.105
0.0375	0.133
0.0378	0.153
0.0383	0.166
0.0386	0.175
0.0398	0.178
0.0402	0.193
0.0408	0.219
0.0411	0.200
0.0421	0.362
0.0428	0.427
0.0430	0.451
0.0433	0.434
0.0438	0.362
0.0440	0.293
0.0444	0.272
0.0450	0.265
0.0455	0.313
0.0459	0.352
0.0466	0.436
0.0474	0.538
0.0476	0.572
0.0481	0.549
0.0494	0.430
0.0499	0.385
0.0503	0.371

λ	ρ
DATA SET 4(CONT.)	
0.0511	0.384
0.0527	0.484
0.0534	0.523
0.0544	0.547
0.0550	0.533
0.0555	0.509
0.0561	0.493
0.0566	0.507
0.0575	1.000
0.0580	0.689
0.0592	0.402
0.0596	0.330
0.0601	0.336
0.0605	0.321
0.0614	0.892
0.0622	0.635
0.0628	0.640
0.0635	0.662
0.0639	0.450
0.0666	0.334
0.0675	0.311
0.0685	0.294
0.0699	0.323
0.0709	0.343
0.0718	0.320
0.0724	0.260
0.0747	0.177
0.0761	0.154
0.0777	0.175
0.0790	0.221
0.0845	0.259
0.0851	0.559
0.0874	0.786
0.0887	0.973
DATA SET 5	
T = 300.0	
0.122	0.0729
0.124	0.0609

λ	ρ
DATA SET 5(CONT.)	
0.125	0.0552
0.125	0.0519
0.126	0.0559
0.127	0.1132
0.128	0.1887
0.129	0.2642
0.129	0.3019
0.130	0.3396
0.131	0.3962
0.132	0.2884
0.135	0.2013
0.137	0.1694
0.139	0.1453
0.141	0.1247
0.143	0.1174
0.145	0.1143
0.146	0.1044
0.149	0.0943
0.151	0.0863
0.152	0.0753
0.153	0.0707
0.154	0.0640
0.155	0.0732
0.156	0.1143
0.157	0.1815
0.158	0.2574
0.159	0.2831
0.160	0.3040
0.163	0.3341
0.165	0.3162
0.167	0.2952
0.169	0.2108
0.171	0.1374
0.175	0.1592
0.179	0.1399
DATA SET 6	
T = 55.0	
0.121	0.0682

TABLE 36. EXPERIMENTAL DATA ON THE REFLECTIVITY OF POTASSIUM CHLORIDE (continued)

λ	ρ	λ	ρ	λ	ρ	λ	ρ	λ	ρ	λ	ρ
DATA SET 6(CONT.)		DATA SET 6(CONT.)		DATA SET 8 T = 100.0		DATA SET 8(CONT.)		DATA SET 9(CONT.)		DATA SET 10(CONT.)	
0.121	0.3578	0.203	0.2419			0.164	0.196	0.161	0.255	0.126	0.3762
0.123	0.443	0.204	0.2032	0.147	0.094	0.165	0.172	0.162	0.271	0.126	0.2257
0.123	0.334	0.205	0.1729	0.147	0.078	0.166	0.153	0.162	0.257	0.127	0.2202
0.125	0.149	0.208	0.1573	0.148	0.152	0.170	0.129	0.162	0.246	0.163	0.2014
0.125	0.162	0.209	0.1469	0.149	0.028	0.170	0.123	0.163	0.236	0.129	0.3022
0.126	0.221			0.150	0.016			0.163	0.224	0.129	0.3093
0.126	0.386	DATA SET 7 T = 299.0		0.151	0.016	DATA SET 9 T = 78.0		0.164	0.209	0.129	0.3151
0.127	0.271			0.151	0.054			0.165	0.194	0.130	0.3303
0.127	0.343			0.152	0.095			0.165	0.187	0.130	0.3352
0.128	0.2147	0.055	0.096	0.153	0.209	0.147	0.102	0.160	0.165	0.131	0.2710
0.129	0.2735	0.055	0.058	0.153	0.229	0.147	0.087	0.170	0.132	0.132	0.2513
0.129	0.3140	0.053	0.131	0.153	0.325	0.148	0.061	0.170	0.131	0.133	0.2269
0.130	0.3475	0.061	0.042	0.154	0.398	0.149	0.036	0.170	0.129	0.133	0.2216
0.130	0.3286	0.063	0.132	0.154	0.454	0.150	0.016	0.172	0.124	0.134	0.2157
0.131	0.2741	0.069	0.034	0.155	0.461	0.151	0.013	0.172	0.121	0.134	0.1947
0.133	0.2177	0.072	0.041	0.155	0.508	0.151	0.021			0.135	0.1773
0.134	0.2770	0.073	0.041	0.156	0.588	0.152	0.055	DATA SET 10 T = 295.0		0.136	0.1603
0.135	0.4385	0.076	0.023	0.156	0.638	0.153	0.155			0.136	0.1573
0.138	0.257	0.078	0.120	0.156	0.638	0.153	0.252			0.137	0.1440
0.139	0.142	0.081	0.130	0.157	0.582	0.154	0.297	0.106	0.1333	0.137	0.1352
0.141	0.1134	0.089	0.129	0.157	0.553	0.154	0.385	0.106	0.1043	0.139	0.1192
0.143	0.1494	0.092	0.141	0.157	0.493	0.155	0.463	0.109	0.0831	0.140	0.1105
0.143	0.1144	0.096	0.201	0.157	0.420	0.156	0.557	0.110	0.0769	0.141	0.1050
0.145	0.114	0.100	0.243	0.157	0.370	0.156	0.571	0.111	0.0765	0.142	0.0934
0.146	0.1114	0.112	0.069	0.158	0.321	0.157	0.576	0.112	0.0673	0.143	0.0973
0.147	0.1109	0.115	0.046	0.158	0.268	0.157	0.559	0.114	0.0526	0.144	0.0950
0.147	0.1124	0.120	0.047	0.158	0.271	0.157	0.490	0.115	0.0493	0.145	0.0904
0.149	0.121	0.122	0.041	0.158	0.353	0.158	0.439	0.116	0.0478	0.146	0.0804
0.150	0.0895	0.129	0.030	0.159	0.457	0.158	0.377	0.116	0.0437	0.146	0.0850
0.151	0.112	0.140	0.103	0.159	0.527	0.158	0.354	0.117	0.0445	0.147	0.0843
0.152	0.324	0.147	0.076	0.159	0.501	0.158	0.324	0.118	0.0475	0.148	0.0865
0.153	0.974	0.153	0.041	0.159	0.414	0.159	0.342	0.119	0.0401	0.149	0.0732
0.154	0.2570	0.162	0.302	0.160	0.369	0.159	0.366	0.120	0.0439	0.150	0.0993
0.155	0.3435	0.167	0.157	0.160	0.340	0.159	0.417	0.121	0.0445	0.151	0.0435
0.156	0.3139	0.173	0.112	0.161	0.307	0.160	0.464	0.121	0.0345	0.152	0.0456
0.157	0.3395	0.193	0.071	0.161	0.293	0.160	0.453	0.123	0.0302	0.152	0.0420
0.157	0.4483	0.217	0.061	0.161	0.267	0.160	0.403	0.123	0.0362	0.152	0.0365
0.158	0.3228	0.275	0.049	0.162	0.236	0.160	0.358	0.124	0.0372	0.153	0.0325
0.161	0.4230	0.354	0.044	0.163	0.210	0.161	0.341	0.125	0.0449	0.153	0.0308
0.162	0.3140	0.652	0.046	0.163	0.201	0.161	0.314	0.125	0.0552	0.154	0.0365

TABLE 38. EXPERIMENTAL DATA ON THE REFLECTIVITY OF POTASSIUM CHLORIDE (continued)

λ	ρ
DATA SET 11(CONT.)	
0.154	0.0422
0.154	0.0491
0.155	0.0731
0.155	0.0908
0.156	0.1139
0.156	0.1420
0.157	0.1693
0.157	0.2041
0.158	0.2155
0.158	0.2300
0.159	0.2591
0.160	0.3042
0.160	0.3142
0.161	0.3261
0.161	0.3193
0.162	0.3169
0.162	0.3185
0.163	0.3001
DATA SET 11	
T = 300.0	
27.2	0.019
28.9	0.010
29.9	0.013
31.5	0.014
32.6	0.018
34.5	0.024
37.1	0.001
38.5	[illegible]
39.2	[illegible]
39.4	0.032
40.2	0.035
40.6	0.037
40.8	0.039
41.6	0.010
41.4	0.013
41.7	0.014
42.0	0.015
42.4	0.017

λ	ρ
DATA SET 11(CONT.)	
43.1	0.021
43.4	0.025
43.7	0.032
44.3	0.041
45.0	0.072
45.9	0.142
46.3	0.146
47.3	0.1[illegible]
47.7	0.091
48.4	0.121
49.5	0.131
51.1	0.252
52.9	0.363
54.7	0.494
56.2	0.675
57.3	0.797
59.5	[illegible]
61.6	0.877
6[illegible]	0.867
63.3	0.876
65.6	0.856
68.3	0.795
7[illegible].5	0.593
73.6	0.411
76.1	0.319
83.1	0.248
97.0	0.177
112.3	0.156
136.2	0.135
163.1	0.144
229.0	0.144



Figure 26. Transmission of Potassium Chloride

TABLE 39. SUMMARY OF MEASUREMENTS ON THE TRANSMISSION OF POTASSIUM CHLORIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	124	Deutsch, T.F.	1974	T	7.69-12.50	298	Single crystal; bar specimens of 6.4 cm long; transmission measured with 1% error; data extracted from a figure.
2	85	McCarthy, D.E.	1967	T	0.17-3.0	298	Synthetic crystal; plate specimen of 10.0 mm thick with surfaces parallel to within 0.001 mm/mm of length and flat to within 10 fringes or better of the mercury green line; measurements made on double-beam instruments with accuracy of ±2%; data extracted from a figure; temperature not given, 298 K assumed.
3	118	Deutsch, T.F.	1975	T	2.5-21.0	298	Single crystal; specimen of 6.4 cm thick; spectrophotometer used in the transmission measurements; a broad absorption band centered at 9.8 μm observed, the wings of which clearly extended to 10.6 μm; data extracted from a figure.
4	118	Deutsch, T.F.	1975	T	2.5-21.0	298	Same as above except for a specimen of 2.35 cm thick.

TABLE 40. EXPERIMENTAL DATA ON THE TRANSMISSION OF POTASSIUM CHLORIDE

(Wavelength, λ, μm; Temperature, T, K; Transmission, τ)

DATA SET 1
T = 298.0

λ	τ
7.09	0.920
9.11	0.920
8.41	0.916
8.71	0.910
9.05	0.900
9.35	0.889
9.61	0.882
9.63	0.881
9.82	0.891
9.98	0.893
10.13	0.889
10.52	0.902
10.73	0.912
11.11	0.916
11.27	0.920
11.83	0.921
11.97	0.917
12.50	0.912

DATA SET 2
T = 300.0

λ	τ
0.113	0.03
0.213	1.37
0.203	2.00
0.225	3.72
0.243	0.79
0.275	0.45
0.341	0.89
0.475	0.92
0.655	0.92
0.933	0.92
1.25	0.92
1.73	0.92
2.23	0.93
2.95	0.93

DATA SET 3
T = 300.0

λ	τ
2.51	0.80
2.53	0.88
2.63	0.88
2.76	0.89
2.86	0.89
2.96	0.89
3.09	0.88
3.20	0.89
3.28	0.89
3.35	0.89
3.61	0.89
3.83	0.89
4.13	0.89
4.26	0.89
4.37	0.90
4.49	0.88
4.93	0.88
5.07	0.89
5.07	0.90
5.22	0.89
5.27	0.91
5.42	0.91
5.54	0.91
5.64	0.91
5.79	0.91
6.10	0.91
6.58	0.92
6.93	0.91
7.22	0.92
7.82	0.92
8.36	0.92
8.93	0.90
9.45	0.88
10.02	0.90
10.51	0.91
11.22	0.93
12.44	0.93
13.61	0.91
14.42	0.86

DATA SET 3(CONT.)

λ	τ
15.55	0.70
16.36	0.67
16.85	0.55
18.11	0.32
18.72	0.18
19.38	0.09
20.09	0.04
20.86	0.01

DATA SET 4
T = 300.0

λ	τ
2.50	0.95
2.52	0.94
2.66	0.93
2.65	0.93
2.71	0.94
2.78	0.93
2.82	0.93
2.88	0.93
2.98	0.93
3.07	0.93
3.21	0.94
3.31	0.94
3.44	0.94
3.57	0.94
3.73	0.94
3.94	0.94
4.12	0.94
4.28	0.95
4.46	0.94
4.65	0.94
4.95	0.95
5.23	0.94
5.54	0.93
5.87	0.94
6.22	0.94
6.60	0.94
7.12	0.93
7.76	0.93

DATA SET 4(CONT.)

λ	τ
8.22	0.93
8.68	0.91
9.24	0.87
9.65	0.84
10.10	0.85
10.49	0.89
11.36	0.93
12.66	0.94
13.16	0.92
14.87	0.89
16.33	0.83
16.83	0.86
18.09	0.65
19.19	0.40
19.89	0.33
21.13	0.17
21.66	0.16
22.79	0.05
23.79	0.02

TABLE 41. PEAK POSITIONS (λ_{max}) IN μm AND HALF-WIDTHS (W) IN eV FOR THE F, R, M, AND N ABSORPTION BANDS IN POTASSIUM CHLORIDE *

Interionic dist., d (Å)	Temp.	F band		R_1 band	R_2 band	M band		N bands
		λ_{max}	W	λ_{max}	λ_{max}	λ_{max}	W	λ_{max}
3.14	RT	(0.576)†		(0.669)	(0.725)	(0.835)		
		0.556	0.31	0.680	0.740	0.820	0.12	
		0.557	0.34			0.822-0.825	0.13	
		0.560	0.35			0.825		
		0.562	0.36			0.830		
		0.563	0.39					
	NT	0.534	0.19	0.650	0.724	0.800-0.820	0.06-0.07	N_1: 0.955
		0.538	0.2	0.656	0.725	0.801-0.802	0.09	N_2: 1.080
		0.539	0.22	0.657	0.727	0.803		N_1: 0.966
		0.540	0.26	0.658	0.729	0.805		W = 0.08
		0.543	0.3	0.659	W = 0.08	0.808		N_2: 1.028
		0.546		W = 0.12				W = 0.09
	HT	0.536	0.16			0.798-0.799	0.05-0.06	
		0.537	0.17					
		0.539	0.18					

* Values were taken from Ref. [69].

† Values given in parentheses are calculated from the Ivey relations [70].

F band $\lambda_{max} = 703\ d^{1.84}$ for NaCl structure, $\lambda_{max} = 251\ d^{2.5}$ for CsCl structure.

R_1 band $\lambda_{max} = 816\ d^{1.84}$

R_2 band $\lambda_{max} = 884\ d^{1.84}$

M band $\lambda_{max} = 1400\ d^{1.56}$

TABLE 42. RECOMMENDED VALUES ON ABSORPTION COEFFICIENT OF POTASSIUM CHLORIDE IN IR REGION AT 300 K

ν, cm^{-1}	λ, μm	Absorption Coefficient, cm^{-1}	
		Intrinsic*	Observed† (Selected)
4.000E+02	25.0	3.3E+0	
4.490E+02	22.3	1.2E+0	1.1E+0
4.970E+02	20.1	4.9E-1	4.6E-1
5.000E+02	20.0	4.6E-1	
5.510E+02	18.1	1.6E-1	1.6E-1
5.992E+02	16.7	6.5E-2	6.2E-2
6.439E+02	15.5	2.7E-2	2.4E-2
6.969E+02	14.3	9.5E-3	8.8E-3
7.502E+02	13.3	3.3E-3	3.2E-3
8.000E+02	12.5	1.2E-3	1.3E-3
8.540E+02	11.7	4.3E-4	1.0E-4
9.000E+02	11.1	1.7E-4	1.0E-4
9.310E+02	10.7	9.5E-5	1.6E-3
9.434E+02	10.6	7.4E-5	6.0E-5(B), 1.2E-4(T)
9.756E+02	10.3	3.9E-5	3.3E-5(B), 1.0E-4(T)
9.780E+02	10.2	3.7E-5	4.5E-3
9.950E+02	10.1	2.7E-5	5.3E-3
1.028E+03	9.73	1.4E-5	6.5E-3
1.047E+03	9.55	9.7E-6	9.0E-6(B), 9.0E-5(T)
1.079E+03	9.27	5.1E-6	1.8E-5(B), 8.0E-5(T)
1.122E+03	8.91	2.2E-6	2.6E-3
1.174E+03	8.52	7.9E-7	9.8E-4
1.202E+03	8.32	4.6E-7	4.8E-4
1.232E+03	8.12	2.5E-7	1.3E-4
1.245E+03	8.03	1.9E-7	6.0E-5
1.300E+03	7.69	6.6E-8	
1.887E+03	5.30	6.4E-13	5.0E-7(B), 4.2E-6(T)
2.632E+03	3.80	2.7E-19	6.5E-6(B), 5.6E-5(T)
3.571E+03	2.80		5.5E-6(B), 5.9E-5(T)

*Intrinsic values were calculated according to Eq. (32) with uncertainties about ±10%.

†Values in this column are the total abosprtion coefficient which are either lowest reported or those used to define the constants in Eq. (32). Uncertainties of these values are about ±10%. Values lower than 1.0E-3 carry higher uncertainties up to ±30%. Letters in the parentheses have the following meaning: B - bulk absorption and T - total absorption.

3.5. Potassium Bromide, KBr

Potassium bromide has optical characteristics similar to those of rock salt, but, having a higher molecular weight, it transmits further into the infrared. Crystals up to 11 kg in size are available from the Harshaw Chemical Company. Very pure samples have been obtained and they can be cleaved easily. KBr is of interest to designers of optical instruments because of its transparency in the infrared region. Although KBr is transparent from 0.20 to 42 μm, the useful region is from 0.3 to 30 μm because strong absorption occurs near the transparency limits.

Measurements of the refractive index of KBr date back to 1874. For the transparent region experimental values were obtained mainly by the deviation method and reported by Spindler and Rodney [130], Stephens et al. [131], Forrest [132], Harting [30], and Gundelach [133]. For low ultraviolet and far infrared wavelengths, there were no measurements until 1967, when Vishnevskii et al. [134] reported their results for the region from 0.170 to 0.197 μm and Handi et al. [24] reported results for the range of 35 to 770 μm.

Li [33] reduced the then available experimental data on the refractive index to a common temperature of 293 K and after careful critical evaluation and analysis adopted a Sellmeier type dispersion equation to calculate refractive index at 293 K in the transparent wavelength region, 0.20 to 42.0 μm.

$$n^2 = 1.39408 + \frac{0.79221\,\lambda^4}{\lambda^2-(0.146)^2} + \frac{0.01981\,\lambda^2}{\lambda^2-(0.173)^2} + \frac{0.15587\,\lambda^2}{\lambda^2-(0.187)^2} + \frac{0.17673\,\lambda^2}{\lambda^2-(60.61)^2} + \frac{2.06217\,\lambda^2}{\lambda^2-(87.72)^2} \tag{33}$$

where λ is in units of μm.

Investigations of the absorption coefficient for practical applications are generally classified into three wavelength regions: the ultraviolet and the far infrared absorption edges and the transparent regions. In the ultraviolet region, Martienssen [135] investigated absorption coefficients of KBr in the range 0.18 to 0.30 μm and at 20 to 1000 K. He found that the expression

$$\alpha(f,T) = \alpha_o e^{-\sigma h(f_o-f)/kT}$$

can be used to describe the absorption behavior of KBr crystals. The constants in the equation were found to be $\alpha_o = 2.4 \times 10^6$ cm^{-1}, $\sigma = 0.79$, and $hf_o = 6.76$ eV. Tomiki et al. [71] studied the absorption of KBr in the wavelength range between 0.170 and 0.240 μm for the purpose of determining the Urbach-rule parameters and finding the features characteristic of the intrinsic tail. Through a systematic observation and analysis they found the empirical relations of the parameters:

$$E_o = 6.840 \text{ eV}$$
$$\alpha_o = 0.6 \times 10^{10} \text{ cm}^{-1}$$
$$hf = 10.5 \text{ meV}$$
$$\sigma_{so} = 0.774$$

for the expression of absorption coefficient of the intrinsic tail

$$\alpha = \alpha_o \exp[-\sigma_s(T)(E_o-E)/kT], \tag{34}$$

where

$$\sigma_s(T) = \sigma_{so} \frac{2kT}{hf} \tanh \frac{hf}{2kT}$$

Measurements of absorption coefficients in the infrared transparent region are recent occurrences as the development of high-power I.R. lasers has led to a need for better characterization of I.R. window materials. Among other factors, the absorption coefficient plays a decisive role in determining whether a material is adequate for laser optical components. For this reason, absorption coefficients of a number of selected materials were investigated at wavelengths of laser interest. Potassium bromide is among the best laser window materials and its absorption coefficients at wavelengths 1.06, 2.7, 3.8, 5.3, and 10.6 μm were intensively studied in order to determine the influencing factors that contribute to the extrinsic absorption. These studies are very informative and provide clues and means for material preparation and parts fabrication in order to minimize the extrinsic components in the absorption.

Deutsch [12], using a differential technique with a dual beam spectrometer, obtained abosrption coefficients for KBr samples in the wavelength range 16.7-33.3 μm. It was found that the observed absorption coefficient together with earlier literature data in the multiphonon absorption region could be represented by the expression

$$\alpha = \alpha_o \exp(-\nu/\nu_o) \tag{35}$$

where

$\alpha_o = 6{,}077\ cm^{-1}$, $\nu_o = 39.1\ cm^{-1}$

This expression, based on the available data that cover the regions $\alpha = 0.002$ to 12 cm^{-1} and $\nu = 250$ to 600 cm^{-1}, is believed to represent the intrinsic absorption of KBr. Extrapolations to the wavelengths 10.6 and 5.3 μm yield intrinsic absorption coefficients of $2.0 \times 10^{-7} cm^{-1}$ and $8 \times 10^{-18} cm^{-1}$, respectively. These values are considerably lower than the corresponding experimental results [118], of $4.2 \times 10^{-4} cm^{-1}$ and $2.1 \times 10^{-4} cm^{-1}$, respectively.

Hass et al. [119] measured absorption coefficients by calorimetric techniques at 1.06, 2.7, and 3.8 μm for a number of KBr samples. The results at 1.06 μm were usually in the $10^{-5} cm^{-1}$ region with the lowest reported value at $<3 \times 10^{-6} cm^{-1}$ which was very close to the limit of their instrument sensitivity. However, at wavelengths 2.7 and 3.8 μm, their best measurements yielded $1.2 \times 10^{-4} cm^{-1}$ and $2.2 \times 10^{-4} cm^{-1}$, respectively. From the observed similarities of a number of other quality crystals, they estimated the absorption coefficient of KBr at 5.3 μm should be in the region $10^{-5} cm^{-1}$ or lower. Compared with the absorption coefficients at these wavelengths, the data imply excess absorption at 2.7 and 3.8 μm even in the purest available crystals. This has been observed not only in the KBr crystals but also in a number of alkali halide and alkaline earth fluoride crystals. The origin of such excessive absorption was not clearly understood. The authors suggested the possibility that this was associated with the OH and CH impurities. If these were eliminated, the absorption level at 2.7 and 3.8 μm could be reduced to the level of $10^{-5} cm^{-1}$ or lower.

In a later study, Klein [120] investigated the origins of the excessive extrinsic absorption at 2.7 and 3.8 μm. Correlation with vacuum-ultraviolet absorption measurements indicated that all of the excess 2.7 μm absorption can be accounted for by the OH^- content of the crystals. At 3.8 μm, the surplus absorption are most likely contributed by the carbon-oxygen lineages, e.g., COF_2, CO_3^{-2}, HCO_3^-, in the specimens. He suggested that diminishing residual absorption at these wavelengths can be achieved by the substitution of hydrogen halides for carbon tetrachloride in the purification procedures and treating the salt below its melting point.

Rowe and Harrington [121] and Klein et al. [136] produced purified KBr crystals by reactive-halide purification processes with various reagents in an effort to minimize oxygen-containing impurities which are known to contribute significantly to extrinsic absorption in the 10.6 μm region. Among the reagents attempted, carbon tetrachloride processing yielded a KBr crystal that had one of the lowest bulk absorption coefficients at 10.6 μm. Among the samples measured, one sample had a bulk absorption coefficient of $7 \times 10^{-6} cm^{-1}$, the lowest for any solid, at 10.6 μm, that so far has been known; even lower than that for KCl crystal. Similar to KCl, for all the KBr samples measured, there exists a persistant absorption band at 9.6 μm. For the purest and best polished crystal, the absorption coefficient at 9.6 μm is greater than that at 10.6 μm by a factor of 2 to 3, yet the near-intrinsic behavior requires a lesser absorption at 9.6 μm. Unless this absorption band were eliminated, or reduced considerably, through purification and polishing process, the use of KBr in the 9.0-9.6 μm region would be limited. Since the method used in their investigation was able to identify the bulk and surface absorptions, an important finding was that the extrinsic absorption band near 9.6 μm is not due entirely to surface absorption, but is in fact due to impurity sources present in the bulk as well as on the surface of the sample.

Figures 27 to 30 are plots of the available data. The pertinent information of each data source and the corresponding original values are given in Tables 43 to 46. In addition, available information and data on the reflectivity and transmission are also presented in the same manner (in Figures 31 and 32 and Tables 47 to 50), for completeness and comparison. For the visible and near visible regions, Table 51 gives the spectral positions of the well known color centers. Noticeable absorptions are likely to occur at these centers when the crystal is exposed to ultraviolet, x-ray, or high energy radiations. However, these absorption bands may disappear at high temperatures or eliminated by appropriate irradiation, corresponding to the so-called "the thermal and optical bleaching of color centers."

Recommended values given in Table 52 were calculated from Eq. (35). In the range between 16.7 to 35 μm, these values are supported by measurements of Deutsch [12] and Barker [38]. In the laser wavelength region, the predicted values are lower than the existing data. It is not known if Eq. (35) holds for this region because the observation of very low absorption is handicapped

by the limit of the best available instrument sensitivity. However, like most of optical crystals, one expects to observe absorption bands in the range between 2.6 to 2.8 μm and at 3.8 μm due to the hydroxyl ions in the crystal and due to surface contamination. These absorption bands can be eliminated through improved crystal growing and polishing techniques. Therefore, it should be noted that the values in the "intrinsic" column are the lower limits that one can obtain for ideal samples. In practice, the observed values are higher than the limiting values at low absorption levels. Unless values appear in the "observed" column, the limiting values are considered as guidelines for estimation and investigation.

Although it was not the intent of this study to evaluate the absorption data in the vacuum ultraviolet region, in order to provide the users a total picture of the available absorption data, the plots of available data in this region are given in the Appendix to this report.



Figure 27. Absorption Coefficient of Potassium Bromide (Wavenumber Dependence)



Figure 28. Absorption Coefficient of Potassium Bromide in the Urbach Tail Region



Figure 29. Absorption Coefficient of Potassium Bromide in the Multiphonon Region

TABLE 43. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF POTASSIUM BROMIDE (Wavenumber Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	19	Hilsch, R. and Pohl, R.W.	1931	T	3.98×10^{4}-4.93×10^{4}	293	High purity; single crystal; grown from melt; absorption coefficients determined from transmission measurements; data extracted from a figure.
2	19	Hilsch, R. and Pohl, R.W.	1931	T	4.32×10^{4}-4.93×10^{4}	293	Similar to above except for a commercial crystal.
3	122	Antinori, M., Balzarotti, A., and Piacentini, M.	1973	R	1.04×10^{5}-1.65×10^{5}	293	Single crystal; obtained from the Harshaw Chemical Co.; specimen cleaved in air just before being mounted in the sample chamber to be vacuum pumped; reflection spectrum obtained with a monochromator of band width of 1.5 Å; spectra performed on the same specimen after 24 hours did not show significant changes and reproducible with uncertainty of about 5%; absorption coefficients derived by means of the Kramers-Kronig analysis on the reflection spectrum obtained from 13.5 to 20.5 eV, below 13.5 eV the reflection data of Robloff were utilized while those of Blechschmidt et al. were used beyond 20.5 eV; absorption-coefficient data extracted from a figure.
4	95	Califano, S. and Czerny, M.	1958	A	4.19×10^{2}-5.9×10^{2}	293	Crystal; block specimens of 15.15 and 16.90 cm; absorption coefficients determined from transmittance measurements; data extracted from a figure.
5	137	Bauer, C.	1934	T	5.26×10^{4}-5.4×10^{4}	293	Crystal; thin film specimens of various thicknesses; absorption coefficients of bulk crystal deduced from transmittance and specimen thickness measurements; data extracted from a table.
6	123	Blechschmidt, D., Klucker, R., and Skibowski, M.	1969	R	9.29×10^{4}-2.42×10^{5}	293	Single crystal; provided by Karl Korth, Kiel, Germany; freshly cleaved specimen; absorption coefficients derived with the reflectivity vs. angle of incidence method; data extracted from a figure.
7	38	Barker, A.J.	1972	R	2.58×10^{2}-4.38×10^{2}	300	Synthetic crystal; high purity; optically polished specimen of 1-2 mm thick; absorption coefficients deduced from reflectivity; data extracted from a figure.
8	38	Barker, A.J.	1972	R	2.98×10^{2}-4.67×10^{2}	500	Similar to above except at a higher temperature.
9	38	Barker, A.J.	1972	R	3.17×10^{2}-4.87×10^{2}	740	Similar to above except at a higher temperature.
10	38	Barker, A.J.	1972	R	3.28×10^{2}-5.08×10^{2}	885	Similar to above except at a higher temperature.
11	38	Barker, A.J.	1972	R	3.38×10^{2}-5.18×10^{2}	1035	Molten KBr specimen of 1-2 mm thick; reflectivity measurements carried out in a largely inert gas atmosphere; absorption coefficients deduced from reflection spectra; absorption-coefficient data extracted from a figure; melting temperature of KBr is 1003 K.

TABLE 42. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF POTASSIUM BROMIDE (Wavenumber Dependence) (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
12	12	Deutsch, T.F.	1973	T	2.99×10^{2}-6.0×10^{2}	300	Single crystal; obtained from Optovac Co.; specimen of 2.54 cm diameter and 2.54 cm thick; absorption coefficients determined using a differential technique with a dual-beam spectrophotometer; data extracted from a figure.
13	77	Tomiki, T., Miyata, T., and Tsukamato, H.	1974	R	4.88×10^{4}-5.37×10^{4}	84	Single crystal; obtained from Harshaw Chemical Co.; absorption coefficients deduced from reflection measurements; data extracted from a figure.
14	77	Tomiki, T., et al.	1974	R	4.83×10^{4}-5.19×10^{4}	194	Similar to above except at a higher temperature.
15	77	Tomiki, T., et al.	1974	R	4.76×10^{4}-5.04×10^{4}	300	Similar to above except at a higher temperature.
16	77	Tomiki, T., et al.	1974	R	4.69×10^{4}-4.94×10^{4}	373	Similar to above except at a higher temperature.
17	77	Tomiki, T., et al.	1974	R	4.54×10^{4}-4.80×10^{4}	473	Similar to above except at a higher temperature.
18	77	Tomiki, T., et al.	1974	R	4.42×10^{4}-4.68×10^{4}	536	Similar to above except at a higher temperature.
19	126	Philipp, H.R. and Ehrenreich, H.	1963	R	5.32×10^{3}-1.94×10^{5}	298	Single crystal; near normal reflection spectrum obtained; absorption coefficients deduced by the Kramers-Kronig relations; absorption-coefficient data extracted from a figure.
20	128	Johnson, K. and Bell, E.	1969	R	20.7-220	300	Single crystal; well polished single surface; reflectivity and phase simultaneously measured by asymmetric Fourier transform spectroscopy and absorption coefficient deduced from the measurements; data extracted from a figure.
21	42	Owens, J.	1968	T	0.25-3.5	298	Single crystals; obtained from the Harshaw Chemical Co.; cylinder shaped specimen; filled resonant cavity method used for measuring dielectric constant and loss tangent; absorption coefficient then determined; data extracted from a figure.
22	136	Klein, P.H., Davison, J.W., and Harrington, J.A.	1976	C	350,400,450	298	High purity crystal; purified with reagent IBr; bar specimens; water ground followed by polishing with HBr solution; measured with laser calorimetry; data extracted from a table.
23	136	Klein, P.H. et al.	1976	C	350,400,450	298	Similar to above except purified with C_2Br_6 in the halide process.
24	136	Klein, P.H. et al.	1976	C	350,400,450	298	Similar to above except purified with C_6Br_6 in the halide process.
25	136	Klein, P.H. et al.	1976	C	350,400,450	298	Similar to above except purified with reagent CCl_4 in the halide process.
26	136	Klein, P.H. et al.	1976	C	943,9434	298	Similar to above except purified with reagent IBr in the halide process and concentration of hydroxyl ion 0.005 per million anion (ppm A).

TABLE 43. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF POTASSIUM BROMIDE (Wavenumber Dependence) (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	*Temperature* Range, K	Specifications and Remarks
27	136	Klein, P.H., Davison, J.W., and Harrington, J.A.	1976	C	943,9434	298	Similar to above except purified with reagent C_2Br_6 in the halide process and concentration of hydroxyl ion 0.07 ppm A.
28	136	Klein, P.H. et al.	1976	C	943,2632,3704,9434	298	Similar to above except purified with reagent CCl_4 in the halide process and concentration of hydroxyl ion 0.05 ppm A.
29	136	Klein, P.H. et al.	1976	C	943,2632,3704,9434	298	Similar to above except concentration of hydroxyl ion <0.01 ppm A.
30	136	Klein, P.H. et al.	1976	C	926-1046	298	Above specimen; total absorption coefficients measured.
31	136	Klein, P.H. et al.	1976	C	926-1046	298	Above specimen; bulk absorption deduced from total absorption.
32	136	Klein, P.H. et al.	1976	C	926-1046	298	Similar to above specimen except concentration of hydroxyl ion 0.05 ppm A and total absorption measured.
33	119	Hass, M., Harrington, J.A., Gregory, D.A., and Davison, J.W.	1976	C	9434,3571,2632	298	Single crystal; highly purified and polished rod specimens; measured with laser calorimetric method; data extracted from a table; origins of higher absorption at 2.7 μm and 3.6 μm due to impurities in bulk material and surface contamination.
34	104	Harrington, J.A., Duchler, C.J., Patten, F.W., and Hass, M.	1976	C	272-576	300	Single crystal; obtained from the Harshaw Chemical Co.; experimental details not given; data extracted from a figure.
35	104	Harrington, J.A. et al.	1976	C	285-498	80	Same as above.
36	129	Mentzel, A.	1934	T	192-625	298	Single crystals; thin film and plate specimens of thickness from 43 μm to 13 mm; absorption coefficients determined from transmission measurements; data extracted from a table.
37	23	Genzel, L., Happ, H., and Weber, R.	1959	T	4.8-28	298	Crystal; plane parallel plate specimens of 2.5, 5.0, 38.5 mm thick; absorption coefficient determined based on transmission measurements; data extracted from a figure.
38	99	Rosenstock, H.B., Gregory, D.A., and Harrington, J.A.	1976	C	943.4,3703	298	Single crystals; obtained from the Naval Research Lab., the Harshaw Chemical Co., and the Raytheon Corp.; mechanically polished and chemically cleaned with spectrograde CCl_4; laser calorimetric method used; data extracted from a table; it was found that the surface absorption was about 45 times higher than the bulk absorption.
39	121	Rowe, J.M. and Harrington, J.A.	1976	C	926-1044	300	Single crystals; grown by the reactive-atmosphere-process; carefully polished surfaces; total absorption determined with laser calorimetric method; higher absorption occurred near 9.6 μm due to extrinsic contributions; data extracted from a figure.

TABLE 43. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF POTASSIUM BROMIDE (Wavenumber Dependence) (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
40	121	Rowe, J.M. and Harrington, J.A.	1976	C	926-1044	300	Same as above except the bulk absorption obtained.
41	121	Rowe, J.M. and Harrington, J.A.	1976	C	926-1044	300	Similar to above except for purer samples and bulk absorption obtained.

TABLE 44. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM BROMIDE (Wavenumber Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

ν	α
DATA SET 1	
T = 293.0	
4.926E+4	3.07[illegible]E+0
4.9[illegible]E+4	6.[illegible]E-1
4.894E+4	2.5[illegible]E-1
4.8[illegible]E+4	1.8[illegible]E-1
4.702E+4	1.0[illegible]E-1
4.734E+4	1.4[illegible]E-1
4.673E+4	1.2[illegible]E-1
4.566E+4	7.[illegible]E-2
4.4[illegible]E+4	0.[illegible]E-2
4.3[illegible]E+4	9.[illegible]E-2
3.984E+4	4.[illegible]E-2
DATA SET 2	
T = 293.0	
4.926E+4	3.91[illegible]E+0
4.9[illegible]E+4	2.7[illegible]E+0
4.874E+4	1.47E+0
4.474E+4	1.3[illegible]E+0
4.554E+4	1.27E+0
4.9[illegible]E+4	1.22[illegible]E+0
4.752E+4	1.12[illegible]E+0
4.734E+4	1.12[illegible]E+0
4.672E+4	1.07E+0
4.590E+4	8.3[illegible]E-1
4.5[illegible]E+4	7.5[illegible]E-1
4.40[illegible]E+4	0.[illegible]E-1
4.429E+4	5.4[illegible]E-1
4.329E+4	4.3[illegible]E-1
DATA SET 3	
T = 293.0	
1.649E+5	0.52[illegible]E+5
1.03[illegible]E+5	0.52[illegible]E+5
1.0[illegible]E+5	6.0[illegible]E+5
1.02[illegible]E+5	0.75[illegible]E+5
1.02[illegible]E+5	7.[illegible]E+5
1.6[illegible]E+5	7.0[illegible]E+5
DATA SET 3(CONT.)	
1.614E+5	8.51[illegible]E+5
1.61[illegible]E+5	9.29[illegible]E+5
1.61[illegible]E+5	9.55[illegible]E+5
1.601E+5	9.0[illegible]E+5
1.591E+5	9.34[illegible]E+5
1.588E+5	8.73[illegible]E+5
1.583E+5	8.[illegible]E+5
1.57[illegible]E+5	7.25[illegible]E+5
1.567E+5	6.54[illegible]E+5
1.55[illegible]E+5	6.28[illegible]E+5
1.552E+5	6.15[illegible]E+5
1.533E+5	6.32[illegible]E+5
1.519E+5	6.67[illegible]E+5
1.5[illegible]E+5	7.0[illegible]E+5
1.47[illegible]E+5	7.09[illegible]E+5
1.469E+5	6.06[illegible]E+5
1.40[illegible]E+5	8.46[illegible]E+5
1.449E+5	7.37[illegible]E+5
1.43[illegible]E+5	7.07[illegible]E+5
1.42[illegible]E+5	7.0[illegible]E+5
1.415E+5	7.3[illegible]E+5
1.393E+5	6.72[illegible]E+5
1.38[illegible]E+5	6.0[illegible]E+5
1.377E+5	6.43[illegible]E+5
1.367E+5	6.11[illegible]E+5
1.35[illegible]E+5	5.03[illegible]E+5
1.347E+5	5.54[illegible]E+5
1.3[illegible]E+5	5.44[illegible]E+5
1.327E+5	5.44[illegible]E+5
1.31[illegible]E+5	5.52[illegible]E+5
1.3[illegible]E+5	5.74[illegible]E+5
1.29[illegible]E+5	6.[illegible]E+5
1.281E+5	6.03[illegible]E+5
1.254E+5	5.37[illegible]E+5
1.24[illegible]E+5	5.37[illegible]E+5
1.223E+5	4.79[illegible]E+5
1.21[illegible]E+5	4.4[illegible]E+5
1.199E+5	4.21[illegible]E+5
1.18[illegible]E+5	4.0[illegible]E+5
1.164E+5	4.02[illegible]E+5
DATA SET 3(CONT.)	
1.15[illegible]E+5	4.12[illegible]E+5
1.14[illegible]E+5	4.26[illegible]E+5
1.133E+5	4.45[illegible]E+5
1.12[illegible]E+5	4.87[illegible]E+5
1.115E+5	5.23[illegible]E+5
1.1[illegible]E+5	5.37[illegible]E+5
1.094E+5	5.51[illegible]E+5
1.08[illegible]E+5	5.81[illegible]E+5
1.07[illegible]E+5	6.17[illegible]E+5
1.06[illegible]E+5	6.56[illegible]E+5
1.059E+5	7.66[illegible]E+5
1.048E+5	8.60[illegible]E+5
DATA SET 4	
T = 293.0	
5.9[illegible]E+2	3.452E-3
5.5[illegible]E+2	6.283E-3
5.269E+2	1.2[illegible]E-2
5.01[illegible]E+2	2.292E-2
4.778E+2	4.549E-2
4.548E+2	7.[illegible]66E-2
4.373E+2	1.171E-1
4.195E+2	1.629E-1
DATA SET 5	
T = 293.0	
5.382E+4	6.460E+5
5.35[illegible]E+4	8.7[illegible]E+5
5.312E+4	9.24[illegible]E+5
5.277E+4	8.90[illegible]E+5
5.261E+4	7.630E+5
DATA SET 6	
T = 293.0	
2.417E+5	6.287E+5
2.348E+5	7.139E+5
2.314E+5	7.967E+5
DATA SET 6(CONT.)	
2.293E+5	8.672E+5
2.272E+5	9.[illegible]43E+5
2.248E+5	8.928E+5
2.223E+5	8.407E+5
2.198E+5	8.[illegible]39E+5
2.156E+5	7.859E+5
2.123E+5	7.978E+5
2.114E+5	8.391E+5
2.033E+5	8.612E+5
2.047E+5	8.822E+5
1.994E+5	8.593E+5
1.926E+5	8.131E+5
1.895E+5	7.792E+5
1.838E+5	7.599E+5
1.778E+5	7.62[illegible]E+5
1.765E+5	8.8[illegible]E+5
1.717E+5	1.074E+6
1.71[illegible]E+5	1.117E+6
1.692E+5	1.[illegible]69E+6
1.66[illegible]E+5	7.426E+5
1.638E+5	6.936E+5
1.614E+5	7.016E+5
1.593E+5	8.66[illegible]E+5
1.571E+5	7.541E+5
1.56[illegible]E+5	6.942E+5
1.541E+5	6.567E+5
1.5[illegible]E+5	6.035E+5
1.49[illegible]E+5	7.52[illegible]E+5
1.463E+5	7.868E+5
1.423E+5	7.65[illegible]E+5
1.39[illegible]E+5	7.[illegible]89E+5
1.362E+5	6.316E+5
1.332E+5	5.592E+5
1.277E+5	5.46[illegible]E+5
1.254E+5	4.932E+5
1.231E+5	4.268E+5
1.212E+5	3.745E+5
1.1[illegible]7E+5	3.313E+5
1.111E+5	4.762E+5
1.025E+5	7.316E+5
DATA SET 6(CONT.)	
9.919E+4	8.401E+5
9.645E+4	9.879E+5
9.293E+4	1.401E+6
DATA SET 7	
T = 3[illegible].0	
4.380E+2	1.200E-1
4.17[illegible]E+2	2.4[illegible]E-1
3.970E+2	3.9[illegible]E-1
3.77[illegible]E+2	5.1[illegible]E-1
3.570E+2	6.8[illegible]E-1
3.380E+2	1.35[illegible]E+0
3.13[illegible]E+2	2.07[illegible]E+0
3.070E+2	2.48[illegible]E+0
2.970E+2	3.13[illegible]E+0
2.870E+2	3.99[illegible]E+0
2.780E+2	5.25[illegible]E+0
2.670E+2	7.56[illegible]E+0
2.580E+2	9.97[illegible]E+0
DATA SET 8	
T = 59[illegible].0	
4.670E+2	1.70[illegible]E-1
4.47[illegible]E+2	2.6[illegible]E-1
4.273E+2	4.70[illegible]E-1
4.080E+2	7.9[illegible]E-1
3.970E+2	1.21[illegible]E+0
3.680E+2	1.9[illegible]E+0
3.58[illegible]E+2	2.3[illegible]E+0
3.47[illegible]E+2	2.9[illegible]E+0
3.380E+2	3.73[illegible]E+0
3.28[illegible]E+2	4.76[illegible]E+0
3.180E+2	6.09[illegible]E+0
3.380E+2	7.61[illegible]E+0
2.98[illegible]E+2	9.32[illegible]E+0
DATA SET 9	
T = 74[illegible].0	
4.87[illegible]E+2	1.53[illegible]E-1
4.67[illegible]E+2	3.1[illegible]E-1
4.47[illegible]E+2	4.8[illegible]E-1
4.27[illegible]E+2	7.4[illegible]E-1
4.0[illegible]E+2	1.17[illegible]E+0
3.37[illegible]E+2	1.7[illegible]E+0
3.77[illegible]E+2	2.19[illegible]E+0
3.65[illegible]E+2	2.7[illegible]E+0
3.53[illegible]E+2	3.4[illegible]E+0
3.47[illegible]E+2	4.1[illegible]E+0
3.35[illegible]E+2	5.2[illegible]E+0
3.28[illegible]E+2	6.50[illegible]E+0
3.17[illegible]E+2	8.54[illegible]E+0
DATA SET 10	
T = 33[illegible].0	
5.0[illegible]E+2	2.1[illegible]E-1
4.87[illegible]E+2	2.8[illegible]E-1
4.67[illegible]E+2	4.3[illegible]E-1
4.47[illegible]E+2	6.7[illegible]E-1
4.27[illegible]E+2	9.8[illegible]E-1
4.0[illegible]E+2	1.4[illegible]E+0
3.97[illegible]E+2	1.8[illegible]E+0
3.87[illegible]E+2	2.2[illegible]E+0
3.77[illegible]E+2	2.7[illegible]E+0
3.0[illegible]E+2	3.45[illegible]E+0
3.53[illegible]E+2	4.37[illegible]E+0
3.47[illegible]E+2	5.4[illegible]E+0
3.38[illegible]E+2	6.67[illegible]E+0
3.28[illegible]E+2	8.5[illegible]E+0
DATA SET 11	
T = 2[illegible]3.0	
5.18[illegible]E+2	2.26[illegible]E-1
4.97[illegible]E+2	3.0[illegible]E-1
4.77[illegible]E+2	4.9[illegible]E-1
4.58[illegible]E+2	7.0[illegible]E-1

TABLE 44. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM BROMIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 11(CONT.)	
4.376E+2	1.192E+4
4.270E+2	1.522E+0
4.[illegible]E+2	1.355E+4
3.970E+2	2.321E+0
3.875E+2	2.[illegible]E+0
3.776E+2	3.5[illegible]E+0
3.681E+2	4.5[illegible]E+0
3.584E+2	5.63[illegible]E+0
3.470E+2	7.110E+0
3.38[illegible]E+2	8.65[illegible]E+0
DATA SET 12	
T = 3[illegible].0	
5.999E+2	1.5[illegible]E-3
5.492E+2	4.[illegible]E-3
5.310E+2	1.[illegible]E-2
4.5[illegible]E+2	1.8[illegible]E-2
4.[illegible]E+2	1.773E-2
2.99[illegible]E+2	2.[illegible]E+0
DATA SET 13	
T = 8[illegible].0	
5.365E+4	1.629E+1
5.300E+4	7.9[illegible]E+1
5.352E+4	6.101E+0
5.345E+4	5.123E+0
5.331E+4	2.754E+0
5.[illegible]12E+4	2.159E+0
[illegible]3E+4	1.432E+2
5.[illegible]1E+4	1.247E+0
5.277E+4	1.10[illegible]E+0
5.267E+4	1.1[illegible]E+0
5.25[illegible]E+4	1.29[illegible]E+0
5.234E+4	1.347E+0
5.22[illegible]E+4	1.637E+0
5.210E+4	1.935E+0
5.194E+4	2.051E+0
5.182E+4	2.301E+0

ν	α
DATA SET 13(CONT.)	
5.170E+4	2.188E+0
5.152E+4	2.188E+0
5.131E+4	2.118E+0
5.104E+4	1.563E+0
5.[illegible]75E+4	1.[illegible]23E+0
5.[illegible]51E+4	8.386E-1
5.[illegible]20E+4	3.098E-1
5.[illegible]02E+4	2.780E-1
4.977E+4	2.[illegible]3E-1
4.949E+4	2.128E-1
4.927E+4	2.198E-1
4.9[illegible]5E+4	2.024E-1
4.882E+4	1.778E-1
DATA SET 14	
T = 194.0	
5.194E+4	1.[illegible]9E-1
5.170E+4	5.754E+0
5.[illegible]71E+4	4.[illegible]4E+0
5.163E+4	3.767E+0
5.155E+4	2.871E+0
5.147E+4	2.679E+0
5.138E+4	2.574E+0
5.121E+4	2.276E+0
5.113E+4	2.234E+0
5.102E+4	1.959E+0
5.09[illegible]E+4	1.945E+0
5.[illegible]73E+4	1.770E+0
5.066E+4	1.637E+0
5.052E+4	1.445E+0
5.039E+4	1.380E+0
5.020E+4	1.3[illegible]E+0
5.017E+4	1.047E+0
5.0[illegible]4E+4	8.831E-1
4.9[illegible]5E+4	8.[illegible]54E-1
4.977E+4	7.[illegible]47E-1
4.951E+4	5.272E-1
4.927E+4	3.862E-1
4.9[illegible]5E+4	2.897E-1

ν	α
DATA SET 14(CONT.)	
4.879E+4	2.466E-1
4.856E+4	2.344E-1
4.833E+4	2.178E-1
DATA SET 15	
T = 30[illegible].0	
5.440E+4	1.770E+1
5.436E+4	1.374E+1
5.429E+4	1.476E+1
5.425E+4	9.462E+0
5.[illegible]12E+4	5.938E+0
5.[illegible]02E+4	4.074E+0
4.99[illegible]E+4	3.165E+0
4.976E+4	2.388E+0
4.965E+4	1.871E+0
4.952E+4	1.563E+0
4.937E+4	1.337E+0
4.927E+4	1.175E+0
4.915E+4	9.162E-1
4.9[illegible]5E+4	8.318E-1
4.891E+4	6.950E-1
4.879E+4	6.950E-1
4.865E+4	4.853E-1
4.856E+4	4.853E-1
4.844E+4	4.036E-1
4.832E+4	3.436E-1
4.823E+4	3.436E-1
4.814E+4	3.076E-1
4.797E+4	2.489E-1
4.785E+4	2.619E-1
4.776E+4	2.897E-1
4.763E+4	2.366E-1
DATA SET 16	
T = 373.0	
4.939E+4	1.514E+1
4.932E+4	1.208E+1
4.927E+4	9.683E+0

ν	α
DATA SET 16(CONT.)	
4.918E+4	7.586E+0
4.9[illegible]E+4	6.138E+0
4.902E+4	4.926E+0
4.89[illegible]E+4	3.664E+0
4.879E+4	2.742E+0
4.860E+4	2.[illegible]14E+0
4.850E+4	1.6[illegible]E+0
4.848E+4	1.272E+0
4.833E+4	9.772E-1
4.824E+4	8.279E-1
4.810E+4	6.792E-1
4.798E+4	5.916E-1
4.788E+4	4.943E-1
4.776E+4	4.266E-1
4.766E+4	3.926E-1
4.754E+4	4.130E-1
4.742E+4	3.[illegible]34E-1
4.718E+4	2.344E-1
4.696E+4	2.416E-1
DATA SET 17	
T = 473.0	
4.794E+4	1.472E+1
4.787E+4	1.247E+1
4.783E+4	1.067E+1
4.770E+4	9.162E+0
4.772E+4	7.379E+0
4.762E+4	6.194E+0
4.756E+4	5.495E+0
4.748E+4	4.926E+0
4.748E+4	4.508E+0
4.741E+4	3.981E+0
4.736E+4	3.236E+0
4.729E+4	3.034E+0
4.719E+4	2.301E+0
4.705E+4	1.837E+0
4.694E+4	1.459E+0
4.685E+4	1.148E+0
4.674E+4	9.550E-1

ν	α
DATA SET 17(CONT.)	
4.6[illegible]E+4	8.091E-1
4.65[illegible]E+4	6.516E-1
4.644E+4	5.321E-1
4.631E+4	3.837E-1
4.621E+4	3.837E-1
4.610E+4	3.236E-1
4.590E+4	2.911E-1
4.567E+4	2.489E-1
4.544E+4	2.280E-1
DATA SET 18	
T = 536.0	
4.672E+4	1.556E+1
4.607E+4	1.247E+1
4.659E+4	1.102E+1
4.651E+4	8.872E+0
4.640E+4	7.112E+0
4.629E+4	6.109E+0
4.619E+4	4.853E+0
4.611E+4	3.802E+0
4.606E+4	3.532E+0
4.599E+4	3.373E+0
4.593E+4	2.969E+0
4.585E+4	2.667E+0
4.581E+4	2.249E+0
4.567E+4	1.905E+0
4.558E+4	1.445E+0
4.548E+4	1.349E+0
4.531E+4	1.128E+0
4.525E+4	9.376E-1
4.519E+4	7.621E-1
4.508E+4	6.436E-1
4.499E+4	5.675E-1
4.485E+4	4.989E-1
4.463E+4	3.698E-1
4.444E+4	3.948E-1
4.423E+4	3.281E-1

ν	α
DATA SET 19	
T = 298.0	
1.939E+5	8.2[illegible]E+5
1.947E+5	9.2[illegible]E+5
1.753E+5	9.2[illegible]E+5
1.75[illegible]E+5	9.[illegible]E+5
1.720E+5	9.[illegible]3E+5
1.677E+5	1.15[illegible]E+6
1.653E+5	1.220E+6
1.637E+5	1.15[illegible]E+6
1.629E+5	1.02[illegible]E+6
1.6[illegible]5E+5	8.6[illegible]E+5
1.541E+5	8.2[illegible]E+5
1.5[illegible]E+5	7.8[illegible]E+5
1.532E+5	7.8[illegible]E+5
1.484E+5	9.0[illegible]E+5
1.4[illegible]E+5	9.6[illegible]E+5
1.439E+5	9.4[illegible]E+5
1.41[illegible]E+5	7.4[illegible]E+5
1.337E+5	6.7[illegible]E+5
1.331E+5	7.3[illegible]E+5
1.298E+5	8.4[illegible]E+5
1.282E+5	8.3[illegible]E+5
1.258E+5	7.2[illegible]E+5
1.234E+5	5.4[illegible]E+5
1.2[illegible]E+5	4.8[illegible]E+5
1.149E+5	5.5[illegible]E+5
1.1[illegible]5E+5	7.9[illegible]E+5
1.124E+5	8.6[illegible]E+5
9.919E+4	9.8[illegible]E+5
9.435E+4	1.3[illegible]E+6
8.79[illegible]E+4	8.4[illegible]E+5
8.[illegible]0E+4	7.4[illegible]E+5
8.[illegible]65E+4	6.6[illegible]E+5
7.823E+4	5.4[illegible]E+5
7.415E+4	5.[illegible]E+5
7.[illegible]97E+4	7.70[illegible]E+5
6.935E+4	1.130E+6
6.65[illegible]E+4	8.0[illegible]E+5
6.532E+4	5.1[illegible]E+5
6.210E+4	3.9[illegible]E+5

TABLE 44. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM BROMIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 19(CONT.)	
5.908E+4	4.203E+5
5.806E+4	7.950E+5
5.645E+4	3.000E+5
5.565E+4	3.100E+5
5.463E+4	8.900E+5
5.323E+4	1.600E+5
DATA SET 20	
T = 300.0	
2.197E+2	1.409E-2
2.109E+2	1.752E-2
2.143E+2	2.114E-2
2.101E+2	2.649E-2
2.009E+2	3.034E-2
2.039E+2	3.435E-2
2.013E+2	3.770E-2
1.951E+2	4.498E-2
1.976E+2	5.303E-2
1.974E+2	5.023E-2
1.996E+2	1.479E-1
1.875E+2	1.799E-1
1.848E+2	1.963E-1
1.848E+2	1.355E-2
1.771E+2	2.244E-1
1.750E+2	2.465E-1
1.741E+2	2.092E-1
1.727E+2	3.329E-1
1.717E+2	4.199E-1
1.695E+2	4.477E-1
1.654E+2	4.532E-1
1.621E+2	4.592E-1
1.622E+2	4.699E-1
1.579E+2	4.842E-1
1.403E+2	5.222E-1
1.291E+2	1.799E+0
1.175E+2	3.936E+0
1.141E+2	4.819E+0
1.130E+2	5.249E+0
1.114E+2	5.175E+0

ν	α
DATA SET 20(CONT.)	
1.108E+2	4.355E+0
1.103E+2	2.594E+0
1.078E+2	1.245E+0
1.043E+2	6.281E-1
8.960E+1	1.545E-1
8.770E+1	1.460E-1
8.540E+1	1.318E-1
8.040E+1	1.211E-1
7.480E+1	1.148E-1
7.020E+1	1.132E-1
6.100E+1	1.107E-1
5.510E+1	1.040E-1
5.130E+1	9.661E-2
4.350E+1	7.889E-2
3.600E+1	5.848E-2
2.070E+1	1.774E-2
DATA SET 21	
T = 298.0	
3.483E+0	2.716E-4
8.630E-1	5.058E-4
2.594E-1	1.175E-3
DATA SET 22	
T = 298.0	
4.500E+2	4.300E-2
4.000E+2	2.000E-1
3.500E+2	7.200E-1
DATA SET 23	
T = 298.0	
4.500E+2	9.600E-2
4.000E+2	7.000E-1
3.500E+2	8.800E-1

ν	α
DATA SET 24	
T = 298.0	
4.500E+2	1.200E-1
4.000E+2	2.800E-1
3.500E+2	7.000E-1
DATA SET 25	
T = 298.0	
4.500E+2	5.700E-2
4.000E+2	2.700E-1
3.500E+2	8.400E-1
DATA SET 26	
T = 298.0	
9.434E+3	2.000E-5
9.434E+2	2.000E-4
DATA SET 27	
T = 298.0	
9.434E+3	3.000E-5
9.434E+2	2.000E-4
DATA SET 28	
T = 298.0	
9.434E+3	5.000E-6
3.704E+3	1.200E-4
2.632E+3	1.700E-4
9.434E+2	6.000E-5
DATA SET 29	
T = 298.0	
9.434E+3	3.000E-6
3.704E+3	1.200E-4
2.632E+3	2.200E-4
9.434E+2	1.400E-5

ν	α
DATA SET 30	
T = 298.0	
1.046E+3	1.080E-4
1.035E+3	1.200E-4
1.035E+3	1.000E-4
9.834E+2	6.870E-5
9.709E+2	6.060E-5
9.524E+2	6.740E-5
9.524E+2	6.140E-5
9.434E+2	6.010E-5
9.434E+2	5.350E-5
9.259E+2	5.080E-5
DATA SET 31	
T = 298.0	
1.046E+3	3.390E-5
1.035E+3	2.700E-5
9.834E+2	2.200E-5
9.709E+2	1.510E-5
9.524E+2	2.870E-5
9.524E+2	2.620E-5
9.434E+2	2.010E-5
9.434E+2	1.880E-5
9.434E+2	1.280E-5
9.434E+2	6.590E-6
9.259E+2	1.840E-5
DATA SET 32	
T = 298.0	
1.046E+3	2.210E-4
1.035E+3	2.290E-4
9.834E+2	1.030E-4
9.709E+2	9.280E-5
9.524E+2	8.880E-5
9.434E+2	1.030E-4
9.434E+2	8.780E-5
9.259E+2	1.020E-4

ν	α
DATA SET 33	
T = 298.0	
9.434E+3	3.000E-6
3.704E+3	1.200E-4
2.632E+3	2.200E-4
DATA SET 34	
T = 300.0	
2.720E+2	8.950E+0
2.910E+2	5.080E+0
2.920E+2	3.010E+0
3.310E+2	2.720E+0
3.110E+2	2.890E+0
3.110E+2	2.170E+0
3.300E+2	1.840E+0
3.300E+2	1.550E+0
3.470E+2	1.310E+0
3.470E+2	9.850E-1
3.760E+2	7.030E-1
3.740E+2	5.290E-1
3.960E+2	4.220E-1
3.980E+2	3.360E-1
4.150E+2	2.540E-1
4.150E+2	2.270E-1
4.300E+2	1.610E-1
4.300E+2	1.440E-1
4.440E+2	1.090E-1
4.490E+2	9.760E-2
4.590E+2	7.730E-2
4.660E+2	6.170E-2
4.740E+2	5.510E-2
4.910E+2	3.930E-2
4.920E+2	3.130E-2
5.010E+2	2.790E-2
5.150E+2	1.630E-2
5.290E+2	1.010E-2
5.460E+2	6.060E-3
5.700E+2	3.860E-3

ν	α
DATA SET 35	
T = 600.0	
2.950E+2	1.300E+0
2.890E+2	6.950E-1
2.970E+2	8.730E-1
3.060E+2	6.580E-1
3.110E+2	4.190E-1
3.150E+2	4.050E-1
3.210E+2	2.970E-1
3.230E+2	3.990E-1
3.300E+2	2.000E-1
3.350E+2	3.900E-1
3.400E+2	2.000E-1
3.430E+2	3.950E-1
3.550E+2	3.100E-1
3.550E+2	2.290E-1
3.620E+2	2.920E-1
3.670E+2	1.390E-1
3.720E+2	1.790E-1
3.790E+2	9.010E-2
3.820E+2	1.350E-1
3.870E+2	5.450E-2
3.960E+2	1.020E-1
4.010E+2	2.920E-2
4.030E+2	8.230E-2
4.110E+2	2.030E-2
4.130E+2	6.120E-2
4.250E+2	4.890E-2
4.180E+2	8.870E-3
4.350E+2	3.630E-2
4.420E+2	2.770E-2
4.540E+2	2.340E-2
4.090E+2	1.950E-2
4.710E+2	1.590E-2
4.840E+2	1.490E-2
4.980E+2	1.060E-2
DATA SET 36	
T = 298.0	
6.250E+2	1.021E-2

TABLE 44. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM BROMIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 35(CONT.)	
5.000E+2	7.540E-2
4.167E+2	2.409E-1
3.571E+2	7.630E-1
3.125E+2	2.042E+0
2.778E+2	4.535E+0
2.500E+2	1.257E+1
2.273E+2	3.427E+1
2.083E+2	9.667E+1
1.923E+2	2.344E+2
DATA SET 37	
T = 298.0	
2.817E+1	1.083E+1
2.817E+1	1.083E+1
2.203E+1	5.453E+0
2.500E+1	7.791E+0
2.012E+1	4.273E+0
1.834E+1	3.395E+0
1.664E+1	2.844E+0
1.546E+1	2.292E+0
1.425E+1	1.852E+0
1.350E+1	1.531E+0
1.255E+1	1.253E+0
1.105E+1	8.913E-1
8.929E+0	3.550E-1
8.621E+0	3.402E-1
7.874E+0	2.444E-1
7.143E+0	2.199E-1
6.369E+0	1.561E-1
5.587E+0	1.109E-1
4.831E+0	8.499E-2
DATA SET 38	
T = 298.0	
9.434E+2	1.203E-4
3.703E+3	5.000E-5

ν	α
DATA SET 39	
T = 300.0	
9.259E+2	1.030E-4
9.434E+2	1.040E-4
9.434E+2	6.810E-5
9.524E+2	8.810E-5
9.709E+2	9.240E-5
9.804E+2	1.050E-4
1.033E+3	2.270E-4
1.044E+3	2.200E-4
DATA SET 40	
T = 300.0	
9.259E+2	5.710E-5
9.434E+2	5.460E-5
9.434E+2	5.990E-5
9.524E+2	6.270E-5
9.524E+2	6.730E-5
9.709E+2	6.050E-5
9.804E+2	6.890E-5
1.033E+3	1.000E-4
1.033E+3	1.220E-4
1.044E+3	1.100E-4
DATA SET 41	
T = 300.0	
9.259E+2	1.850E-5
9.434E+2	6.570E-5
9.434E+2	1.280E-5
9.434E+2	1.850E-5
9.434E+2	2.030E-5
9.524E+2	2.640E-5
9.524E+2	2.900E-5
9.709E+2	1.510E-5
9.804E+2	2.200E-5
1.033E+3	2.690E-5
1.044E+3	3.390E-5



Figure 30. Absorption Coefficient of Potassium Bromide (Temperature Dependence)

TABLE 45. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF POTASSIUM BROMIDE (Temperature Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	43	Stolen, R. and Dransfeld, K.	1965	T	31.25	41-300	High purity; single crystal; grown by the Bridgman Method; plate specimens of thickness 0.5 to 25.0 mm; absorption coefficients directly determined; data extracted from a figure.
2	43	Stolen, R. and Dransfeld, K.	1965	T	20.0	77-300	Same as above except for a longer wavelength.
3	43	Stolen, R. and Dransfeld, K.	1965	T	11.11	80-300	Same as above except for a longer wavelength.

TABLE 46. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM BROMIDE (Temperature Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

T	α
DATA SET 1	
ν = 3.125E+1	
41.0	2.419E+2
44.0	2.652E+2
50.0	3.584E+2
56.0	4.431E+2
65.0	5.628E+2
76.0	7.161E+2
93.0	9.[illegible]E+2
107.0	1.104E+3
129.0	1.5[illegible]E+3
146.0	1.815E+3
164.0	2.071E+3
189.0	2.475E+3
212.0	2.854E+3
241.0	3.345E+3
300.0	4.38[illegible]E+3
DATA SET 2	
ν = 2.000E+1	
77.0	1.369E+2
104.0	2.169E+2
134.0	3.213E+2
157.0	4.120E+2
173.0	4.783E+2
188.0	5.441E+2
209.0	6.373E+2
240.0	7.619E+2
267.0	9.151E+2
300.0	1.0[illegible]E+3
DATA SET 3	
ν = 1.111E+1	
81.0	1.014E+1
110.0	2.491E+1
139.0	4.323E+1
170.0	6.863E+1
203.0	9.869E+1
233.0	1.318E+2
DATA SET 3 (CONT.)	
270.0	1.785E+2
300.0	2.190E+2



Figure 31. Reflectivity of Potassium Bromide

TABLE 47. SUMMARY OF MEASUREMENTS ON THE REFLECTIVITY OF POTASSIUM BROMIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	122	Antinori, M., Balzarotti, A., and Piacentini, M.	1973	R	0.06-0.094	293	Single crystal; obtained from the Harshaw Chemical Co.; specimen cleaved in air just before being mounted in the sample chamber to be vacuum pumped; reflection spectrum obtained with a monochromator of band width of 1.5 A; spectra performed on the same specimen after 24 hrs did not show significant changes and reproduced with uncertainty of about 5%; data extracted from a figure.
2	123	Blechschmidt, D., Klucker, R., and Skibowski, M.	1969	R	0.034-0.094	293	Single crystal; provided by Karl Korth, Kiel, Germany; freshly cleaved specimen; near normal reflectivity measured in vacuum for polarized light with normal of the specimen lying on both sides of the incident beam for increased accuracy; data extracted from a figure.
3	110	Baldini, G. and Basacchi, B.	1968	R	0.136-0.222	300	Single crystals specimen with cleaved surface; back surface of the specimen treated with an emery cloth to reduce the reflection from the back; near normal reflectivity obtained with specimen in vacuum; data extracted from a figure.
4	110	Baldini, G. and Bosacchi, B.	1968	R	0.127-0.214	55	Same as above except at a low temperature.
5	138	Petroff, Y., Pinchaux, R., Chekroun, C., Balkanski, M., and Kamimura, H.	1971	R	0.155-0.188	1.8	Single crystal; specimen cleaved in liquid helium; near normal reflection spectrum obtained; data extracted from a curve.
6	24	Hadni, A., Claudel, J., Chanal, D., Strimer, P., and Vergnat, P.	1967	R	18.6-120	300	Single crystal; specimen of prism shape to avoid interference; near normal reflectivity obtained; data extracted from a curve.
7	24	Hadni, A. et al.	1967	R	18.6-120	72	Above specimen and conditions except at a lower temperature.
8	24	Hadni, A. et al.	1967	R	18.6-20	4.2	Above specimen and conditions except at a lower temperature.
9	126	Philipp, H.R. and Ehrenreich, H.	1963	R	0.049-0.62	298	Single crystal; near normal reflection spectrum obtained; data extracted from a curve.
10	128	Johnson, K. and Bell, E.	1969	R	27.4-278.5	300	Single crystal; well polished single surface; reflectivity measured by asymmetric Fourier-transform spectroscopy; data extracted from a figure.
11	54	McCarthy, D.E.	1963	R	1.9-40.0	298	Synthetic crystal; plate specimen of 5 cm thick; ground and polished to a flatness of seven fringes or better on both sides; incident angle 30°; data extracted from a figure.

TABLE 48. EXPERIMENTAL DATA ON THE REFLECTIVITY OF POTASSIUM BROMIDE

[Wavelength, λ, μm; Temperature, T, K; Reflectivity, ρ]

λ	ρ
DATA SET 1	
T = 293.0	
0.613	0.261
0.615	0.246
0.617	0.324
0.619	0.276
0.620	0.496
0.621	0.511
0.623	0.531
0.624	0.517
0.626	0.474
0.629	0.433
0.631	0.465
0.632	0.425
0.633	0.340
0.637	0.291
0.639	0.301
0.641	0.240
0.644	0.238
0.647	0.235
0.651	0.294
0.656	0.234
0.662	0.312
0.669	0.360
0.672	0.399
0.676	0.434
0.681	0.453
0.682	0.453
0.687	0.442
0.695	0.446
0.700	0.421
0.704	0.400
0.714	0.375
0.715	0.339
0.724	0.328
0.729	0.316
0.733	0.299
0.737	0.268
0.743	0.248
0.751	0.248
0.759	0.258

λ	ρ
DATA SET 1(CONT.)	
0.764	0.275
0.768	0.315
0.772	0.328
0.779	0.311
0.782	0.298
0.791	0.286
0.795	0.251
0.805	0.265
0.811	0.284
0.810	0.227
0.822	0.212
0.828	0.169
0.837	0.179
0.847	0.179
0.857	0.192
0.865	0.212
0.872	0.232
0.877	0.261
0.880	0.291
0.884	0.321
0.888	0.371
0.892	0.419
0.895	0.465
0.899	0.489
0.909	0.521
0.913	0.555
0.922	0.574
0.930	0.598
0.942	0.610
DATA SET 2	
T = 293.0	
0.346	0.154
0.345	0.169
0.349	0.181
0.353	0.181
0.359	0.176
0.363	0.164
0.373	0.164

λ	ρ
DATA SET 2(CONT.)	
0.384	0.137
0.392	0.219
0.402	0.284
0.409	0.250
0.414	0.275
0.420	0.339
0.430	0.453
0.433	0.467
0.436	0.453
0.446	0.322
0.453	0.313
0.459	0.314
0.474	0.433
0.479	0.453
0.487	0.434
0.516	0.321
0.523	0.296
0.535	0.301
0.554	0.372
0.562	0.405
0.572	0.455
0.575	0.684
0.573	0.750
0.590	0.258
0.603	0.235
0.609	0.260
0.615	0.428
0.619	0.496
0.623	0.432
0.633	0.239
0.637	0.214
0.643	0.225
0.658	0.337
0.668	0.464
0.675	0.485
0.684	0.469
0.727	0.240
0.737	0.223
0.752	0.237
0.757	0.255

λ	ρ
DATA SET 2(CONT.)	
0.768	0.274
0.781	0.260
0.799	0.243
0.823	0.178
0.831	0.196
0.856	0.267
0.894	0.553
0.936	0.871
DATA SET 3	
T = 300.0	
0.136	0.719
0.137	0.693
0.140	0.330
0.142	0.265
0.143	0.259
0.144	0.263
0.145	0.263
0.146	0.272
0.147	0.263
0.148	0.299
0.151	0.265
0.155	0.190
0.158	0.174
0.164	0.157
0.166	0.093
0.166	0.089
0.169	0.095
0.172	0.157
0.176	0.185
0.177	0.179
0.179	0.154
0.181	0.123
0.181	0.104
0.182	0.097
0.183	0.079

λ	ρ
DATA SET 3(CONT.)	
0.186	0.072
0.187	0.054
0.188	0.036
0.189	0.031
0.190	0.070
0.192	0.066
0.194	0.059
0.197	0.052
0.200	0.049
0.205	0.052
0.214	0.159
0.221	0.149
DATA SET 4	
T = 55.0	
0.127	0.034
0.128	0.045
0.129	0.013
0.130	0.031
0.131	0.039
0.131	0.039
0.132	0.026
0.133	0.027
0.134	0.051
0.135	0.038
0.137	0.035
0.138	0.079
0.139	0.087
0.140	0.049
0.140	0.092
0.142	0.052
0.142	0.035
0.143	0.079
0.144	0.056
0.1[illegible]4	0.092
0.140	0.136
0.147	0.187
0.147	0.148

λ	ρ
DATA SET 4(CONT.)	
0.148	0.212
0.150	0.214
0.152	0.207
0.156	0.201
0.158	0.112
0.159	0.096
0.162	0.034
0.164	0.091
0.165	0.066
0.166	0.126
0.168	0.087
0.168	0.073
0.170	0.031
0.171	0.326
0.172	0.265
0.175	0.273
0.176	0.003
0.177	0.061
0.178	0.210
0.180	0.217
0.181	0.462
0.182	0.467
0.183	0.593
0.183	0.584
0.185	0.624
0.185	0.265
0.187	0.295
0.189	0.335
0.193	0.178
0.197	0.531
0.202	0.361
0.208	0.227
0.214	0.119
DATA SET 5	
T = [illegible]	
0.155	0.163
0.155	0.161
0.156	0.157

AD-A118 601 CENTER FOR INFORMATION AND NUMERICAL DATA ANALYSIS AN--ETC F/G 7/2
ABSORPTION COEFFICIENT OF ALKALI HALIDES. PART I.(U)
MAR 79 H H LI F49620-76-C-0105
UNCLASSIFIED CINDAS-54 AFOSR-TR-82-0687 NL

3 of 3
AD
A118601

END
DATE
FILMED
9 82
DTIC

TABLE 48. EXPERIMENTAL DATA ON THE REFLECTIVITY OF POTASSIUM BROMIDE (continued)

λ	ρ
DATA SET 5(CONT.)	
0.165	0.161
0.157	0.174
0.157	0.180
0.155	0.177
0.158	0.232
0.159	0.165
0.160	0.132
0.161	0.121
0.161	0.235
0.162	0.110
0.162	0.111
0.163	0.120
0.164	0.115
0.165	0.120
0.165	0.114
0.165	0.125
0.167	0.130
0.167	0.133
0.168	0.249
0.168	0.373
0.169	0.378
0.169	0.370
0.170	0.354
0.170	0.346
0.171	0.351
0.171	0.344
0.171	0.275
0.172	0.249
0.172	0.190
0.175	0.165
0.175	0.197
0.177	0.177
0.177	0.146
0.178	0.122
0.179	0.134
0.179	0.237
0.180	0.227
0.181	0.292
0.181	0.265
0.181	0.054

λ	ρ
DATA SET 5(CONT.)	
0.183	0.462
0.183	0.336
0.184	0.251
0.184	0.255
0.185	0.234
0.180	0.242
0.187	0.175
DATA SET 6	
T = 300.0	
18.0	0.048
32.3	0.037
41.5	0.022
49.5	0.030
52.9	0.049
56.5	0.098
60.2	0.129
63.1	0.190
65.7	0.253
69.5	0.496
70.1	0.591
72.6	0.694
74.9	0.754
77.7	0.792
79.2	0.813
81.8	0.798
83.4	0.784
85.2	0.722
89.7	0.521
89.2	0.513
90.3	0.435
93.2	0.308
95.7	0.322
97.5	0.292
101.2	0.262
105.0	0.229
110.1	0.214
113.3	0.198
120.0	0.175

λ	ρ
DATA SET 7	
T = 72.0	
18.6	0.048
32.3	0.037
41.5	0.022
52.7	0.035
54.3	0.065
56.9	0.129
59.3	0.221
61.3	0.364
62.5	0.559
64.5	0.673
67.0	0.806
69.1	0.878
71.2	0.909
74.5	0.928
77.6	0.928
79.2	0.915
80.3	0.893
83.3	0.720
85.2	0.439
89.6	0.394
91.5	0.349
94.0	0.305
96.4	0.275
99.3	0.249
101.9	0.232
106.3	0.215
113.3	0.168
120.0	0.170
DATA SET 8	
T = 4.2	
18.6	0.048
32.3	0.037
41.5	0.022
51.1	0.030
53.1	0.063
54.8	0.097
56.9	0.156

λ	ρ
DATA SET 8(CONT.)	
59.3	0.212
60.2	0.350
61.5	0.525
63.1	0.640
65.2	0.767
67.1	0.851
68.3	0.896
70.2	0.919
72.5	0.939
74.6	0.959
78.0	0.925
79.6	0.900
80.7	0.830
85.1	0.558
86.3	0.487
87.2	0.428
89.8	0.352
92.1	0.321
95.2	0.273
98.4	0.247
101.9	0.225
105.0	0.212
110.1	0.204
113.3	0.186
120.0	0.170
DATA SET 9	
T = 293.0	
0.0496	0.066
0.0534	0.068
0.0553	0.062
0.0571	0.059
0.0584	0.069
0.0596	0.099
0.0601	0.093
0.0613	0.052
0.0629	0.043
0.0642	0.043
0.0659	0.047

λ	ρ
DATA SET 9(CONT.)	
0.0673	0.060
0.0688	0.073
0.0703	0.064
0.0747	0.051
0.0789	0.051
0.0863	0.024
0.0921	0.024
0.0949	0.032
0.0932	0.099
0.0961	0.119
0.1000	0.127
0.1042	0.120
0.1199	0.120
0.1227	0.093
0.1278	0.077
0.1323	0.093
0.1405	0.092
0.1494	0.184
0.1675	0.242
0.1746	0.262
0.1797	0.249
0.1878	0.283
0.1937	0.154
0.2066	0.133
0.2339	0.075
0.2952	0.059
0.3047	0.054
0.0200	0.049
DATA SET 10	
T = 300.0	
27.4	0.031
29.3	0.033
31.1	0.029
33.3	0.027
35.2	0.024
38.4	0.019
43.4	0.015
41.7	0.014

λ	ρ
DATA SET 10(CONT.)	
43.4	0.014
44.0	0.002
5.1	0.004
5.6	0.001
52.2	0.002
53.3	0.014
53.7	0.014
54.4	0.015
55.8	0.024
56.2	0.052
57.8	0.052
61.9	0.054
62.0	0.061
62.6	0.081
66.0	0.367
70.5	0.703
73.1	0.721
81.3	0.721
84.5	0.681
87.0	0.711
89.2	0.562
90.0	0.404
95.1	0.304
109.2	0.224
113.9	0.134
120.7	0.107
225.5	0.092
267.5	0.191
274.4	0.141
DATA SET 11	
T = 293.0	
1.9	0.035
4.8	0.051
10.0	0.075
15.2	0.070
20.0	0.070
25.3	0.063
29.9	0.057

TABLE 48. EXPERIMENTAL DATA ON THE REFLECTIVITY OF POTASSIUM BROMIDE (continued)

λ	ρ
DATA SET 11(CONT.)	
35.1	0.236
33.9	0.228



Figure 32. Transmission of Potassium Bromide

TABLE 49. SUMMARY OF MEASUREMENTS ON THE TRANSMISSION OF POTASSIUM BROMIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	24	Hadni, A., Claudel, J., Chanal, D., Strimer, P., and Vergnat, P.	1967	T	89.2-172.1	4.2	Single crystal; specimen of 2.5 mm thick; data extracted from a curve.
2	85	McCarthy, D.E.	1967	T	0.17-3.0	298	Synthetic crystal; plate specimen of 5.0 mm thick with surfaces parallel to within 0.001 mm/mm of length and flat to within 10 fringes or better of the mercury green line; measurements made on double-beam instruments with accuracy of ±2%; data extracted from a figure; temperature not given, 298 K assumed.
3	54	McCarthy, D.E.	1963	T	2.0-37.0	298	Synthetic crystal; plate specimen of 5 mm thick; ground and polished to a flatness of seven fringes or better on both sides; data taken from a figure.

TABLE 50. EXPERIMENTAL DATA ON THE TRANSMISSION OF POTASSIUM BROMIDE

[Wavelength, λ, μm; Temperature, T, K; Transmission, τ]

λ	τ
DATA SET 1	
T = [illegible]	
69.2	0.049
95.1	[illegible]
[illegible]	[illegible]
1[illegible].4	0.4[illegible]
1[illegible].5	0.4[illegible]
1[illegible].9	[illegible]
1[illegible].4	0.4[illegible]
1[illegible].4	0.3[illegible]
1[illegible].7	0.3[illegible]
1[illegible].4	[illegible]
1[illegible].9	[illegible]
1[illegible].9	[illegible]
1[illegible].5	[illegible]
1[illegible].4	0.572
1[illegible].5	[illegible]
1[illegible].4	0.603
152.9	0.632
[illegible]	[illegible]
[illegible]	[illegible]
[illegible]	0.637
DATA SET [illegible]	
T = 30[illegible]	
[illegible]	[illegible]
[illegible]	[illegible]
[illegible]	[illegible]
[illegible]	[illegible]
[illegible]	[illegible]
0.2[illegible]	0.72
0.3[illegible]	0.8[illegible]
[illegible]	[illegible]
0.5[illegible]	[illegible]
[illegible]	[illegible]
[illegible]	0.91
1.23	0.91
1.89	0.91
3.04	0.91

λ	τ
DATA SET 3	
T = 298.[illegible]	
2.1	0.933
5.2	0.934
10.2	0.928
15.[illegible]	0.921
20.1	0.915
21.3	0.906
23.7	0.865
25.3	0.791
26.6	0.711
28.[illegible]	0.5[illegible]
3[illegible].2	0.49[illegible]
32.3	0.4[illegible]
32.5	0.3[illegible]
33.3	0.205
35.1	0.112
35.3	0.059
36.7	0.029

TABLE 51. PEAK POSITIONS (λ_{max}) IN μm AND HALF-WIDTHS (W) IN eV FOR THE F, R, M, AND N ABSORPTION BANDS IN POTASSIUM BROMIDE*

Interionic dist., d (Å)	Temp.	F band		R_1 band	R_2 band	M band		N bands
		λ_{max}	W	λ_{max}	λ_{max}	λ_{max}	W	λ_{max}
3.29	RT	(0.630)†		(0.732)	(0.792)	(0.897)		
		0.625	0.35			0.917-0.918	0.12-0.13	1.080
		0.628	0.38					
		0.630	0.42					
		0.631						
	NT	0.599	0.19	0.735	0.790	0.887	0.06-0.07	
		0.601	0.20			0.892		
		0.603	0.22					
		0.607	0.30					
		0.608						
	HT	0.599	0.16			0.883-0.884	0.05	
		0.602	0.20					

* Values were taken from Ref. [69].

† Values given in parentheses are calculated from the Ivey relations [70].

F band $\lambda_{max} = 703\ d^{1.84}$ for NaCl structure, $\lambda_{max} = 251\ d^{2.5}$ for CsCl structure.

R_1 band $\lambda_{max} = 816\ d^{1.84}$

R_2 band $\lambda_{max} = 884\ d^{1.84}$

M band $\lambda_{max} = 1400\ d^{1.56}$

TABLE 52. RECOMMENDED VALUES ON ABSORPTION COEFFICIENT OF POTASSIUM BROMIDE IN IR REGION AT 300 K

ν, cm^{-1}	λ, μm	Absorption Coefficient, cm^{-1}	
		Intrinsic*	Observed† (Selected)
2.990E+02	33.4	2.9E+0	2.0E+0
3.000E+02	33.3	2.8E+0	
3.500E+02	28.6	7.8E-1	7.0E-1
4.000E+02	25.0	2.1E-1	2.0E-1
4.010E+02	24.9	2.1E-1	2.7E-1
4.500E+02	22.2	6.1E-2	1.8E-2
5.000E+02	20.0	1.6E-2	
5.010E+02	20.0	1.6E-2	1.3E-2
5.491E+02	18.2	4.8E-3	4.0E-3
6.000E+02	16.7	1.3E-3	1.5E-3
7.000E+02	14.3	1.0E-4	
8.000E+02	12.5	7.9E-6	
9.000E+02	11.1	6.1E-7	
9.259E+02	10.8	3.1E-7	1.8E-5(B), 5.6E-5(T)
9.434E+02	10.6	2.0E-7	1.4E-5(B), 5.6E-5(T)
9.524E+02	10.5	1.6E-7	2.7E-5(B), 6.4E-5(T)
9.709E+02	10.3	9.9E-8	1.5E-5(B), 6.0E-5(T)
9.804E+02	10.2	7.8E-8	2.2E-5(B), 6.8E-5(T)
1.000E+03	10.0	4.7E-8	
1.035E+03	9.66	1.9E-8	2.7E-5(B), 1.1E-4(T)
1.046E+03	9.56	1.4E-8	3.3E-5(B), 1.0E-4(T)
1.079E+03	9.27	6.2E-9	3.3E-5
2.632E+03	3.80	3.5E-26	1.7E-4
3.704E+03	2.70		1.2E-4
9.434E+03	1.06		3.0E-6

*Intrinsic values were calculated according to Eq. (35) with uncertainties about ±10%.

†Values in this column are the total absorption coefficient which are either lowest reported or those used to define the constants in Eq. (35). Uncertainties of these values are about ±10%. Values lower than 1.0E-3 carry higher uncertainties up to ±30%. Letters in the parentheses have the following meaning: B - bulk absorption and T - total absorption.

3.6. Potassium Iodide, KI

Potassium iodide is valuable as prism material, but it is too hygroscopic (being about twice as soluble in water as potassium bromide) and too soft for field use. It is also soluble in alcohol and in ammonia. Crystal ingots 19 cm in diameter are available. Although KI is one of the softest rock salt-structure alkali halides, thus not a suitable optical material, its wide transparency, 0.25 to 50 μm, draws considerable interest in research. Fundamental absorptions in the ultraviolet and infrared regions, as well as static and high-frequency dielectric constants have been measured by a number of investigators, and the results are reported in Table 2.

A reasonable quantity of data on the refractive index of KI are available in the open literature. By careful examination of the available data we find that for the transparent wavelength region the results of Gyulai [27] and Harting [30] are consistent (with temperature effects considered) to the fourth decimal place, in spite of the fact that Gyulai quoted an accuracy of one unit in the third decimal place. Korth's values [139], although being reported to the fourth decimal place, are good only to the third place. Data reported by Sprockhoff [140] and Topsöe and Christiansen [141] appear slightly too high at the assumed temperature; they either observed at a considerably lower temperature or used inadequate samples. In the infrared region, 40 μm and up, data were deduced by analyzing the information on reflection and transmission spectra. Data are available from the figures of Hadni et al. [24], Eldridge et al. [142], and Berg et al. [143].

Li [33] reduced the then available experimental data on the refractive index to a common temperature of 293 K and after careful critical evaluation and analysis adopted a Sellmeier type dispersion equation to evaluate the refractive index at 293 K in the transparent wavelength range 0.25-50 μm

$$n^2 = 1.47285 + \frac{0.16512\,\lambda^2}{\lambda^2-(0.129)^2} + \frac{0.41222\,\lambda^2}{\lambda^2-(0.175)^2} + \frac{0.44163\,\lambda^2}{\lambda^2-(0.187)^2} + \frac{0.16076\,\lambda^2}{\lambda^2-(0.219)^2}$$

$$+ \frac{0.33571\,\lambda^2}{\lambda^2-(69.44)^2} + \frac{1.92474\,\lambda^2}{\lambda^2-(98.04)^2} \qquad (36)$$

where λ is in units of μm.

PRECEDING PAGE B

Available data on the absorption coefficient, reflectivity, and transmission of KI compiled in the present work are given in Tables 53 and 60 and are plotted in Figures 33 to 38. Investigations of absorption coefficient for practical applications are generally classified into three wavelength regions: the ultraviolet and the infrared absorption edges and the transparent regions. In the case of KI, much of the absorption measurement was carried out in the vacuum uv region for the purposes of studying the band structure of the crystal. Many observations were performed in the far infrared region for study of the dielectric properties. Little information could be found in the transparent and absorption edge regions. In the uv absorption edge, early studies of the Urbach tail of KI were made by Martienssen [135] and Haupt [144]. Later, Tomiki et al. [77] studied the absorption of KI in the wavelength range between 0.200 and 0.280 μm for the purpose of determining the Urbach-rule parameters and finding the features characteristic of the intrinsic tail. Through a systematic observation and analysis, the following empirical relations of the parameters were found

$E_o = 5.890$ eV
$\alpha_o = 0.6 \times 10^{10}$ cm^{-1}
$hf = 4.5$ meV
$\sigma_{so} = 0.830$

for the expression of absorption coefficient of the intrinsic tail

$$\alpha = \alpha_o \exp\left[-\sigma_s(T)(E_o-E)/kT\right] \tag{37}$$

where

$$\sigma_s(T) = \sigma_{so} \frac{2kT}{hf} \tanh \frac{hf}{2kT}$$

This equation represents the intrinsic absorption coefficient for pure KI crystals.

In the multiphonon absorption region, absorption coefficients on the high frequency side of the reststrahlen band were measured by Berg and Bell [143] based on transmission and reflection measurements using the method of asymmetric Fourier spectroscopy. Eldridge and Kembry [142] investigated the optical properties in the vicinity of reststrahlen band at various temperatures using a Fourier spectrometer for specimens of a range of thicknesses. Their results

agreed with those of Berg and Bell at corresponding temperature as shown in Figure 34 where the exponential relation between the variables are clearly seen. We found that the room temperature data can be represented by the relation

$$\alpha = \alpha_o e^{-\nu/\nu_o} \tag{38}$$

with $\nu_o = 36\ cm^{-1}$ and $\alpha_o = 3458\ cm^{-1}$. Detailed discussion of this finding is given in the section entitled "Summary of Results and Recommendations".

We have seen that the intrinsic absorption coefficients of KI in the Urbach and multiphonon regions, respectively, obey the exponential law. It is not known if the two relations hold for the transparent region. If they did, absorption in the transparent region would be negligible. However, at the color centers (given in Table 61), possible absorptions should be considered. The intensity of absorption depends on the purity, thermal and irradiation history of the sample, and its physical environment. As the color centers may be bleached as well as created by appropriate thermal and/or radiation energy, absorption at these bands varies considerably. As a result, no definite values can be assigned other than the spectral positions of these bands.

Figures 33 to 36 are plots of the available data. The pertinent information of each data source and the corresponding original values are given in Tables 53 to 56. In addition, available information and data on the reflectivity and transmission are also presented in the same manner (in Figures 37 and 38 and Tables 57 and 60), for completeness and comparison. For the visible and near visible regions, Table 61 gives the spectral positions of the well known color centers.

Recommended values given in Table 62 were calculated from Eq. (38). It should be noted that the values in the "intrinsic" column are the lowest limits that one can obtain for ideal samples. In practice, the observed values are generally higher than the limiting values at low absorption levels. Unless values appear in the "observed" column, the limiting values are considered as guidelines for estimation and investigation.

Although it was not within the scope of this study to compile and evaluate the absorption data in the vacuum ultraviolet region, in order to provide the reader a total picture of the available absorption data of KI, a plot of selected data sets in the uv region is given in the Appendix to this report.



Figure 33. Absorption Coefficient of Potassium Iodide (Wavenumber Dependence)



Figure 34. Absorption Coefficient of Potassium Iodide in the Urbach Tail Region



Figure 35. Absorption Coefficient of Potassium Iodide in the Multiphonon Region

TABLE 53. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF POTASSIUM IODIDE (Wavenumber Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	143	Berg, J.I. and Bell, E.E.	1971	Z	2.2×10^{1}-2.28×10^{2}	300	Crystal; obtained from the Harshaw Chemical Co.; two kinds of specimens used, lapped and polished lamellar specimens as thin as 100 μm for transmittance measurements and plate specimens of about 1 cm thick with one surface lapped and polished for refractivity measurements; measurements made using a Michelson interferometer operated in the asymmetric mode; absorption coefficients deduced from transmittance and reflectance measurements; data extracted from a figure.
2	137	Bauer, G.	1934	T	4.41×10^{4}-5.4×10^{4}	293	Crystal; thin film specimens of various thicknesses; absorption coefficients of bulk crystal deduced from transmittance and specimen thickness measurements; data extracted from a table.
3	123	Blechschmidt, D., Klucker, R., and Skibowski, M.	1969	R	9.58×10^{4}-2.22×10^{5}	293	Single crystal; provided by Karl Korth, Kiel, Germany; freshly cleaved specimen; absorption coefficients derived with the reflectivity versus angle of incidence method; data extracted from a figure.
4	145	Delbecq, C.J. and Yuster, P.H.	1954	R	1.42×10^{4}-4.51×10^{4}	293	Single crystal; obtained from the Harshaw Chemical Co. or grown by the Kyropoulos method; geometry not specified; absorption-coefficient data extracted from a figure.
5	142	Eldridge, J.E. and Kembry, K.A.	1973	T	2.5×10^{1}-3.0×10^{2}	300	Single crystal from Harshaw Chemical Co.; sample cleaned in toluene, rinsed in alcohol, then dried and polished; sample thickness 0.01-1.0 cm (wedge shape); absorption coefficients deduced from transmission measurements; data extracted from a figure.
6	142	Eldridge, J.E. and Kembry, K.A.	1973	T	2.8×10^{1}-2.52×10^{2}	77	Above specimen and conditions except measured at a lower temperature.
7	142	Eldridge, J.E. and Kembry, K.A.	1973	T	6.9×10^{1}-2.4×10^{2}	12	Above specimen and conditions except measured at a lower temperature.
8	77	Tomiki, T., Miyata, T., and Tsukamato, H.	1974	R	4.54×10^{4}-4.65×10^{4}	65	Single crystal; obtained from the Harshaw Chemical Co.; absorption coefficients deduced from reflection spectrum; data extracted from a figure.
9	77	Tomiki, T., et al.	1974	R	4.25×10^{4}-4.5×10^{4}	185	Similar to above except at a higher temperature.
10	77	Tomiki, T., et al.	1974	R	4.03×10^{4}-4.32×10^{4}	295	Similar to above except at a higher temperature.
11	77	Tomiki, T., et al.	1974	R	3.93×10^{4}-4.22×10^{4}	367	Same as above except at a higher temperature.
12	77	Tomiki, T., et al.	1974	R	3.8×10^{4}-4.1×10^{4}	455	Same as above except at a higher temperature.
13	77	Tomiki, T., et al.	1974	R	3.64×10^{4}-3.95×10^{4}	595	Same as above except at a higher temperature.

TABLE 53. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF POTASSIUM IODIDE (Wavenumber Dependence) (Continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
14	126	Philipp, H.R. and Ehrenreich, H.	1963	R	4.35×10^{4}-1.86×10^{5}	298	Single crystal; near normal reflection spectrum obtained; absorption coefficients deduced by the Kramers-Kronig relations; absorption-coefficient data extracted from a figure.
15	104	Harrington, J.A., Duthler, C.J., Patten, F.W., and Hass, M.	1976	C	244-495	300	Single crystal; obtained from the Harshaw Chemical Co.; experimental detail not given; data extracted from a figure.
16	104	Harrington, J.A. et al.	1976	C	242-427	80	Same as above.

TABLE 54. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM IODIDE (Wavenumber Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

ν	α
DATA SET 1	
T = 300	
2.276E+2	3.432E+1
2.165E+2	8.434E+0
2.039E+2	1.493E+1
1.994E+2	2.335E+1
1.845E+2	6.279E+1
1.717E+2	1.232E+2
1.667E+2	1.095E+2
1.626E+2	2.339E+2
1.603E+2	2.703E+2
1.580E+2	3.352E+2
1.574E+2	4.478E+2
1.537E+2	5.711E+2
1.498E+2	7.511E+2
1.483E+2	8.519E+2
1.449E+2	9.512E+2
1.416E+2	9.779E+2
1.387E+2	9.311E+2
1.320E+2	9.529E+2
1.294E+2	1.445E+3
1.258E+2	1.185E+3
1.208E+2	1.433E+3
1.180E+2	3.537E+3
1.456E+2	5.083E+3
1.124E+2	6.935E+3
1.002E+2	6.297E+3
9.886E+1	3.759E+3
9.700E+1	2.578E+3
9.484E+1	1.361E+3
9.400E+1	9.499E+2
9.238E+1	7.218E+2
9.036E+1	6.019E+2
8.714E+1	3.76 E+2
8.441E+1	2.333E+2
8.138E+1	2.338E+2
7.734E+1	1.374E+2
8.531E+1	1.667E+2
8.478E+1	1.434E+2
8.054E+1	1.220E+2
8.254E+1	1.031E+2

ν	α
DATA SET 1(CONT.)	
4.452E+1	8.258E+1
4.414E+1	6.155E+1
4.120E+1	4.675E+1
3.992E+1	3.813E+1
3.530E+1	2.362E+1
3.193E+1	1.475E+1
2.85 E+1	8.560E+0
2.580E+1	5.252E+0
2.212E+1	2.472E+0
DATA SET 2	
T = 293.0	
9.382E+4	9.300E+5
9.036E+4	1.077E+6
8.202E+4	7.051E+5
9.105E+4	2.831E+5
9.024E+4	2.507E+5
4.930E+4	2.591E+5
4.847E+4	2.574E+5
4.702E+4	2.250E+5
4.654E+4	2.920E+5
4.556E+4	7.180E+5
4.415E+4	4.310E+4
DATA SET 3	
T = 293.0	
2.213E+5	6.896E+5
2.170E+5	6.720E+5
2.134E+5	6.596E+5
2.034E+5	6.347E+5
2.005E+5	6.07 E+5
2.044E+5	6.731E+5
2.019E+5	6.531E+5
1.985E+5	6.20 E+5
1.950E+5	6.074E+5
1.911E+5	5.932E+5
1.856E+5	5.853E+5
1.778E+5	5.698E+5

ν	α
DATA SET 3(CONT.)	
1.754E+5	5.731E+5
1.738E+5	5.639E+5
1.694E+5	5.539E+5
1.602E+5	5.579E+5
1.653E+5	5.672E+5
1.607E+5	8.604E+5
1.596E+5	8.022E+5
1.577E+5	6.185E+5
1.559E+5	5.485E+5
1.518E+5	4.943E+5
1.481E+5	4.689E+5
1.445E+5	4.576E+5
1.418E+5	4.543E+5
1.383E+5	4.598E+5
1.363E+5	4.847E+5
1.335E+5	5.035E+5
1.329E+5	5.745E+5
1.298E+5	5.740E+5
1.271E+5	5.734E+5
1.248E+5	5.830E+5
1.235E+5	6.708E+5
1.218E+5	6.106E+5
1.185E+5	5.140E+5
1.166E+5	4.902E+5
1.147E+5	4.309E+5
1.126E+5	4.188E+5
1.097E+5	4.090E+5
1.073E+5	4.030E+5
1.048E+5	4.084E+5
1.030E+5	4.271E+5
1.015E+5	4.364E+5
9.944E+4	4.423E+5
9.750E+4	4.961E+5
9.589E+4	5.422E+5
DATA SET 4	
T = 293.0	
4.505E+4	3.160E+1
4.464E+4	2.630E+1

ν	α
DATA SET 4(CONT.)	
4.425E+4	2.206E+1
4.386E+4	1.934E+1
4.348E+4	1.654E+1
4.310E+4	1.480E+1
4.274E+4	1.260E+1
4.237E+4	1.130E+1
4.202E+4	9.800E+0
4.167E+4	8.600E+0
4.132E+4	7.300E+0
4.115E+4	6.500E+0
4.105E+4	6.000E+0
4.080E+4	5.200E+0
3.845E+4	4.500E+0
2.000E+4	3.500E+0
1.815E+4	3.000E+0
1.687E+4	3.800E+0
1.538E+4	3.600E+0
1.427E+4	3.600E+0
DATA SET 5	
T = 300.0	
3.000E+2	6.607E-1
2.860E+2	6.316E-1
2.640E+2	1.349E+0
2.500E+2	2.396E+0
2.370E+2	3.982E+0
2.280E+2	6.007E+0
2.270E+2	2.042E+1
1.950E+2	4.169E+1
1.850E+2	6.457E+1
1.800E+2	7.702E+1
1.700E+2	8.711E+1
1.710E+2	1.122E+2
1.680E+2	1.413E+2
1.640E+2	1.778E+2
1.620E+2	2.235E+2
1.590E+2	2.834E+2
1.560E+2	4.677E+2
1.540E+2	3.981E+2

ν	α
DATA SET 5(CONT.)	
1.530E+2	4.265E+2
1.520E+2	5.248E+2
8.400E+1	3.631E+2
8.000E+1	2.754E+2
8.300E+1	2.188E+2
7.950E+1	1.738E+2
6.640E+1	1.738E+2
6.000E+1	1.479E+2
5.400E+1	1.172E+2
4.710E+1	7.244E+1
4.100E+1	4.074E+1
3.500E+1	2.089E+1
3.000E+1	9.120E+0
2.800E+1	5.612E+0
2.500E+1	1.000E-1
DATA SET 6	
T = 77.0	
2.500E+2	1.349E-1
2.400E+2	1.770E-1
2.420E+2	2.344E-1
2.290E+2	3.467E-1
2.320E+2	7.413E-1
2.270E+2	1.148E+0
2.190E+2	1.362E+0
2.120E+2	2.794E+0
2.050E+2	3.031E+0
2.000E+2	4.169E+0
1.970E+2	5.370E+0
1.950E+2	7.079E+0
1.900E+2	1.072E+1
1.850E+2	1.349E+1
1.870E+2	1.698E+1
1.830E+2	1.995E+1
1.740E+2	3.311E+1
1.700E+2	4.365E+1
1.630E+2	5.889E+1
1.660E+2	8.511E+1
1.640E+2	1.122E+2

ν	α
DATA SET 6(CONT.)	
1.630E+2	1.559E+2
1.620E+2	2.291E+2
1.602E+2	2.912E+2
1.600E+2	2.344E+2
1.590E+2	1.778E+2
1.570E+2	1.995E+2
1.590E+2	2.034E+2
1.520E+2	3.034E+2
1.500E+2	4.571E+2
1.490E+2	4.200E+2
1.480E+2	3.631E+2
1.410E+2	1.413E+2
9.400E+1	8.511E+1
8.300E+1	4.571E+1
8.200E+1	4.193E+1
7.800E+1	5.129E+1
7.000E+1	4.571E+1
6.300E+1	3.388E+1
5.000E+1	1.778E+1
4.800E+1	1.238E+1
4.200E+1	9.120E+0
3.900E+1	6.066E+0
3.400E+1	3.162E+0
3.300E+1	2.089E+0
2.900E+1	2.630E-1
2.000E+1	1.000E-1
DATA SET 7	
T = 12.0	
2.090E+2	1.000E-1
2.300E+2	1.413E-1
2.340E+2	2.754E-1
2.320E+2	3.981E-1
2.440E+2	4.730E-1
2.310E+2	7.244E-1
2.110E+2	1.148E+0
2.090E+2	1.349E+0
1.990E+2	1.555E+0

TABLE 54. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM IODIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 7(CONT.)	
1.966E+2	2.033E+0
1.014E+2	2.092E+1
9.301E+1	3.355E+0
9.7[illegible]E+1	1.423E+1
9.1[illegible]E+1	7.244E-1
7.7[illegible]E+1	5.439E-1
7.4[illegible]E+1	4.677E-1
6.9[illegible]E+1	4.074E-1
DATA SET 8	
T = 65.0	
4.642E+4	9.988E+0
4.630E+4	7.484E+0
4.635E+4	6.491E+0
4.631E+4	4.395E+0
4.627E+4	6.347E+0
4.623E+4	3.945E+0
4.615E+4	3.357E+0
4.606E+4	2.459E+0
4.617E+4	3.648E+0
4.616E+4	2.213E+0
4.614E+4	2.547E+0
4.613E+4	1.373E+0
4.613E+4	1.614E+0
4.598E+4	1.374E+0
4.598E+4	1.259E+0
4.594E+4	1.159E+0
4.587E+4	9.375E-1
4.583E+4	7.073E-1
4.545E+4	9.551E-1
4.545E+4	5.545E-1
DATA SET 9	
T = 135.0	
4.484E+4	1.617E+1
4.481E+4	1.271E+1
4.477E+4	9.817E+0
4.473E+4	7.447E+0

ν	α
DATA SET 9(CONT.)	
4.463E+4	4.365E+0
4.453E+4	2.079E+0
4.444E+4	1.075E+0
4.432E+4	1.087E+0
4.432E+4	6.372E-1
4.422E+4	7.345E-1
4.442E+4	6.135E-1
4.425E+4	6.138E-1
4.422E+4	4.066E-1
4.42[illegible]E+4	3.[illegible]E-1
4.390E+4	2.979E-1
4.388E+4	2.547E-1
4.376E+4	2.158E-1
4.366E+4	2.159E-1
4.354E+4	1.973E-1
4.340E+4	1.714E-1
4.335E+4	1.578E-1
4.327E+4	1.349E-1
4.303E+4	1.527E-1
4.287E+4	1.420E-1
4.273E+4	1.242E-1
4.252E+4	1.038E-1
DATA SET 10	
T = 245.0	
4.326E+4	2.032E+1
4.322E+4	1.535E+1
4.3[illegible]E+4	1.143E+1
4.3[illegible]E+4	8.472E+0
4.294E+4	7.244E+0
4.289E+4	4.853E+0
4.232E+4	3.373E+0
4.273E+4	2.523E+0
4.2[illegible]E+4	1.578E+0
4.250E+4	1.169E+0
4.245E+4	8.395E-1
4.243E+4	7.413E-1
4.237E+4	6.526E-1
4.237E+4	4.764E-1

ν	α
DATA SET 10(CONT.)	
4.227E+4	5.037E-1
4.225E+4	3.750E-1
4.220E+4	3.430E-1
4.232E+4	1.968E-1
4.192E+4	1.493E-1
4.165E+4	1.222E-1
4.149E+4	1.014E-1
4.129E+4	7.447E-2
4.109E+4	6.318E-2
4.094E+4	8.128E-2
4.070E+4	8.120E-2
4.06[illegible]E+4	9.333E-2
4.047E+4	6.982E-2
4.03[illegible]E+4	6.823E-2
DATA SET 11	
T = 367.0	
4.219E+4	1.914E+1
4.213E+4	2.593E+1
4.212E+4	1.714E+1
4.208E+4	1.556E+1
4.205E+4	1.219E+1
4.196E+4	1.175E+1
4.197E+4	1.457E+1
4.192E+4	8.710E+0
4.186E+4	6.223E+0
4.173E+4	5.612E+0
4.162E+4	4.618E+0
4.158E+4	2.793E+0
4.149E+4	2.623E+0
4.144E+4	1.706E+0
4.132E+4	1.459E+0
4.129E+4	1.549E+0
4.123E+4	1.138E+0
4.119E+4	9.638E-1
4.115E+4	8.720E-1
4.106E+4	7.345E-1
4.106E+4	6.792E-1
4.090E+4	5.888E-1

ν	α
DATA SET 11(CONT.)	
4.096E+4	5.421E-1
4.09[illegible]E+4	4.112E-1
4.087E+4	5.165E-1
4.079E+4	3.319E-1
4.063E+4	2.646E-1
4.048E+4	1.965E-1
4.032E+4	1.294E-1
4.015E+4	1.047E-1
3.999E+4	1.096E-1
3.981E+4	8.166E-2
3.965E+4	8.166E-2
3.944E+4	6.607E-2
3.933E+4	7.762E-2
DATA SET 12	
T = 455.0	
4.177E+4	1.862E+1
4.174E+4	1.778E+1
4.172E+4	1.346E+1
4.166E+4	1.318E+1
4.161E+4	1.191E+1
4.157E+4	9.291E+0
4.151E+4	8.356E+0
4.148E+4	7.211E+0
4.138E+4	5.808E+0
4.129E+4	4.786E+0
4.123E+4	4.385E+0
4.115E+4	3.632E+0
4.106E+4	2.858E+0
3.938E+4	2.377E+0
3.930E+4	1.863E+0
3.985E+4	1.563E+0
3.970E+4	1.343E+0
3.969E+4	1.143E+0
3.966E+4	1.065E+0
3.952E+4	7.447E-1
3.944E+4	6.109E-1
3.935E+4	5.371E-1
3.930E+4	4.466E-1

ν	α
DATA SET 12(CONT.)	
3.919E+4	3.388E-1
3.913E+4	3.129E-1
3.904E+4	2.918E-1
3.898E+4	2.692E-1
3.893E+4	2.249E-1
3.883E+4	2.061E-1
3.877E+4	1.480E-1
3.870E+4	1.466E-1
3.860E+4	1.542E-1
3.845E+4	1.614E-1
3.831E+4	1.180E-1
3.815E+4	8.954E-2
3.801E+4	9.247E-2
DATA SET 13	
T = 595.0	
3.844E+4	1.965E+1
3.94[illegible]E+4	1.5[illegible]E+1
3.927E+4	1.247E+1
3.922E+4	9.546E+0
3.910E+4	7.980E+0
3.905E+4	6.516E+0
3.900E+4	5.206E+0
3.893E+4	4.920E+0
3.885E+4	4.246E+0
3.877E+4	3.631E+0
3.867E+4	3.192E+0
3.860E+4	2.716E+0
3.855E+4	2.41[illegible]E+0
3.843E+4	1.883E+0
3.839E+4	1.622E+0
3.833E+4	1.460E+0
3.824E+4	1.094E+0
3.817E+4	9.772E-1
3.813E+4	8.264E-1
3.798E+4	6.081E-1
3.782E+4	4.831E-1
3.769E+4	3.784E-1
3.756E+4	3.483E-1

ν	α
3.747E+4	2.724E-1
3.730E+4	2.249E-1
3.710E+4	1.837E-1
3.644E+4	1.386E-1
DATA SET 14	
T = 295.0	
1.855E+5	9.1[illegible]E+5
1.8[illegible]E+5	7.9[illegible]E+5
1.774E+5	7.4[illegible]E+5
1.734E+5	8.2[illegible]E+5
1.71[illegible]E+5	8.950E+5
1.669E+5	8.9[illegible]E+5
1.645E+5	8.4[illegible]E+5
1.621E+5	7.4[illegible]E+5
1.597E+5	8.0[illegible]E+5
1.581E+5	1.6[illegible]E+6
1.5[illegible]E+5	8.4[illegible]E+5
1.932E+5	7.6[illegible]E+5
1.9[illegible]E+5	8.8[illegible]E+5
1.427E+5	8.4[illegible]E+5
1.379E+5	6.100E+5
1.347E+5	6.7[illegible]E+5
1.315E+5	7.4[illegible]E+5
1.27[illegible]E+5	7.420E+5
1.234E+5	6.5[illegible]E+5
1.21[illegible]E+5	6.7[illegible]E+5
1.194E+5	8.3[illegible]E+5
1.153E+5	4.680E+5
1.1[illegible]3E+5	5.180E+5
1.073E+5	5.1[illegible]E+5
1.032E+5	4.5[illegible]E+5
9.756E+4	3.[illegible]E+5
9.13E+4	5.3[illegible]E+5
8.366E+4	7.3[illegible]E+5
7.823E+4	9.4[illegible]E+5
7.581E+4	8.3[illegible]E+5
7.016E+4	5.0[illegible]E+5
6.694E+4	5.5[illegible]E+5

TABLE 54. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM IODIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 14(CONT.)	
6.290E+4	5.600E+5
6.129E+4	3.800E+5
5.887E+4	6.300E+5
5.726E+4	6.900E+5
5.565E+4	6.600E+5
5.323E+4	8.900E+5
5.081E+4	2.900E+5
5.000E+4	2.700E+5
4.919E+4	2.700E+5
4.758E+4	2.300E+5
4.597E+4	8.400E+5
4.516E+4	3.600E+5
4.435E+4	1.900E+5
4.355E+4	5.000E+4
DATA SET 15	
T = 3.0.0	
2.440E+2	3.610E+0
2.490E+2	2.710E+0
2.640E+2	2.430E+0
2.690E+2	1.830E+0
2.830E+2	1.230E+0
2.900E+2	9.530E-1
3.030E+2	7.840E-1
3.070E+2	6.250E-1
3.240E+2	4.990E-1
3.320E+2	3.550E-1
3.420E+2	2.670E-1
3.540E+2	2.260E-1
3.630E+2	1.610E-1
3.730E+2	1.210E-1
3.830E+2	7.690E-2
3.830E+2	5.790E-2
3.900E+2	5.470E-2
4.020E+2	4.370E-2
4.120E+2	2.940E-2
4.220E+2	2.210E-2
4.320E+2	1.570E-2
4.410E+2	1.330E-2

ν	α
DATA SET 15(CONT.)	
4.510E+2	1.000E-2
4.580E+2	7.540E-3
4.680E+2	6.740E-3
4.830E+2	6.030E-3
4.950E+2	4.540E-3
DATA SET 16	
T = 80.0	
2.420E+2	9.230E-1
2.540E+2	6.210E-1
2.590E+2	3.940E-1
2.670E+2	2.970E-1
2.710E+2	2.110E-1
2.740E+2	2.110E-1
2.840E+2	1.340E-1
2.840E+2	1.420E-1
2.910E+2	1.070E-1
2.890E+2	6.050E-2
2.930E+2	8.530E-2
3.010E+2	1.130E-1
3.010E+2	4.570E-2
3.050E+2	1.270E-1
3.100E+2	7.210E-2
3.150E+2	1.270E-1
3.180E+2	1.010E-1
3.200E+2	1.270E-1
3.250E+2	9.590E-2
3.300E+2	1.510E-1
3.350E+2	7.220E-2
3.420E+2	1.280E-1
3.440E+2	4.860E-2
3.510E+2	1.020E-1
3.540E+2	3.460E-2
3.590E+2	5.450E-2
3.600E+2	1.960E-2
3.710E+2	3.880E-2
3.760E+2	1.180E-2
3.810E+2	2.470E-2
3.860E+2	7.920E-2

ν	α
DATA SET 16(CONT.)	
3.910E+2	9.390E-2
3.960E+2	5.960E-3
4.050E+2	4.240E-3
4.200E+2	3.020E-3
4.270E+2	2.280E-3



Figure 36. Absorption Coefficient of Potassium Iodide (Temperature Dependence)

TABLE 55. SUMMARY OF MEASUREMENT ON THE ABSORPTION COEFFICIENT OF POTASSIUM IODIDE (Temperature Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	43	Stolen, R. and Dransfeld, K.	1965	T	31.25	83-300	High purity; single crystal; grown by the Bridgman method; plate specimens of thickness from 0.5 to 25.0 mm; absorption coefficients directly determined; data extracted from a figure.
2	43	Stolen, R. and Dransfeld, K.	1965	T	20	162-300	Same as above except for a longer wavelength.

TABLE 56. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF POTASSIUM IODIDE (Temperature Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

T	α
DATA SET 1	
ν = 3.125E+1	
93.0	3.319E+2
97.0	4.379E+2
120.0	6.824E+2
143.0	3.047E+2
163.0	1.093E+3
194.0	1.312E+3
206.0	1.551E+3
222.0	1.727E+3
244.0	1.939E+3
259.0	2.279E+3
300.0	2.671E+3
DATA SET 2	
ν = 2.000E+1	
162.0	1.344E+2
170.0	1.655E+2
194.0	2.134E+2
212.0	2.923E+2
231.0	3.159E+2
245.0	3.571E+2
257.0	3.479E+2
267.0	4.357E+2
274.0	4.724E+2
284.0	5.216E+2
292.0	5.045E+2
296.0	5.942E+2
300.0	6.302E+2



Figure 37. Reflectivity of Potassium Iodide

TABLE 57. SUMMARY OF MEASUREMENTS ON THE REFLECTIVITY OF POTASSIUM IODIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	143	Berg, J.I. and Bell, E.E.	1971	R	47.34-218.8	300	Crystal; obtained from the Harshaw Chemical Co.; lapped and polished plate specimens of about 1 cm thick; reflection spectrum obtained; data extracted from a figure.
2	123	Blechschmidt, D., Klucker, R., and Skibowski, M.	1969	R	0.035-0.099	293	Single crystal; provided by Karl Korth, Kiel, Germany; freshly cleaved specimen; near normal reflectivity measured in vacuum for polarized light with normal of the specimen lying on both sides of the incident beam for increased accuracy; data extracted from a figure.
3	110	Baldini, G. and Bosacchi, B.	1968	R	0.124-0.243	300	Single crystal; specimen with cleaved surface; back surface of the specimen treated with an emery cloth to reduce the reflection from the back; near normal reflectivity obtained with specimen in vacuum; data extracted from a figure.
4	110	Baldini, G. and Bosacchi, B.	1968	R	0.124-0.243	55	Same as above except at low temperature.
5	146	Baldini, G., Bosacchi, A., and Bosacchi, B.	1969	R	0.198-0.216	6	Cleaved crystal; sample geometry and origin not specified; near normal incidence; data extracted from a curve.
6	138	Petroff, Y., Pinchaux, R., Chekroun, C., Balkanski, M., and Kamimura, H.	1971	R	0.209-0.213	1.8	Single crystal; specimen cleaved in liquid helium to avoid surface contamination; near normal reflection spectrum obtained; data extracted from a curve.
7	147	Roessler, D.M.	1967	R	0.110-0.248	298	Crystal specimen cleaved in air; exposed to atmosphere for 2 minutes; near normal reflectivity measured in vacuum; data extracted from a curve.
8	147	Roessler, D.M.	1967	R	0.110-0.248	77	Same as above except at a low temperature.
9	148	Weeks, R.F.	1958	R	0.201-0.253	93	Single crystal; cleaved; near normal reflectivity measured in vacuum; data extracted from a curve.
10	149	Kato, R. and Watanabe, M.	1968	R	0.165-0.248	298	Single crystal; grown from the melt; 2 mm thick; freshly cleaved in air; near normal reflectivity measured in vacuum; data extracted from a curve.
11	84	Mitsuiski, A. and Yamada, Y.	1962	R	59.9-149	300	Single crystal; near normal reflectivity measured in vacuum with aluminum mirror reference standard; data extracted from a curve.
12	149	Kato, R. and Watanabe, M.	1968	R	0.165-0.248	298	Film specimen deposited on LiF substitute; near normal reflectivity measured in vacuum; data extracted from a curve.
13	150	Vishnevski, V.N., Stefanski, I.V., Kuzyk, M.P., Kulik, Z.S., and Kulik, L.N.	1973	R	0.154-0.239	298	Single crystal; grown by Kyropoulos method; near normal reflection spectrum obtained; data extracted from a figure.

TABLE 57. SUMMARY OF MEASUREMENTS ON THE REFLECTIVITY OF POTASSIUM IODIDE (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
14	142	Eidrige, J.E. and Kembry, K.A.	1973	R	62.5-333.4	300	Crystal specimen cleaved in air; exposed to atmosphere for 2 minutes; near normal reflectivity measured in vacuum; data extracted from a curve.
15	126	Philipp, H.R. and Ehrenreich, H.	1963	R	0.053-0.653	298	Single crystal; near normal reflection spectrum obtained; data extracted from a curve.
16	25	Hadni, A., Claudel, J., Morlot, G., and Strimer, P.	1968	R	42-196	290	Single crystal; high purity; reflectivity spectrum of 15° incident angle obtained; data extracted from a figure.
17	25	Hadni, A. et al.	1968	R	42-600	80	Same as above.
18	25	Hadni, A. et al.	1968	R	38-195	4.2	Same as above.

TABLE 58. EXPERIMENTAL DATA ON THE REFLECTIVITY OF POTASSIUM IODIDE

[Wavelength, λ, μm; Temperature, T, K; Reflectivity, R]

λ	R	λ	R	λ	R	λ	R	λ	R	λ	R
DATA SET 1		DATA SET 1(CONT.)		DATA SET 2(CONT.)		DATA SET 2(CONT.)		DATA SET 3(CONT.)		DATA SET 4(CONT.)	
T = 300.0											
		101.0	0.571	0.472	0.187	0.613	0.438	0.190	0.234	0.141	0.056
47.3	0.212	103.4	0.486	0.476	0.196	0.622	0.431	0.192	0.220	0.142	0.065
49.4	0.250	105.7	0.416	0.483	0.232	0.844	0.340	0.195	0.195	0.143	0.078
50.8	0.166	109.0	0.344	0.483	0.245	0.877	0.246	0.198	0.155	0.143	0.510
50.7	0.235	114.5	0.291	0.492	0.237	0.928	0.335	0.202	0.145	0.144	0.593
51.4	0.212	118.3	0.258	0.505	0.194	0.949	0.324	0.207	0.149	0.145	0.687
53.2	0.190	124.2	0.231	0.521	0.235	0.962	0.347	0.209	0.153	0.146	0.744
55.6	0.123	132.2	0.207	0.517	0.192	0.993	0.497	0.212	0.159	0.147	0.798
57.0	0.134	138.5	0.195	0.525	0.205			0.213	0.156	0.149	0.835
58.5	0.167	147.0	0.193	0.531	0.191	DATA SET 3		0.214	0.145	0.149	0.903
59.8	0.135	153.0	0.181	0.541	0.166	T = 300.0		0.217	0.2229	0.151	0.102
61.5	0.149	176.0	0.175	0.543	0.261			0.219	0.234	0.151	0.955
61.5	0.138	183.7	0.175	0.557	0.175	0.124	0.1482	0.221	0.3470	0.153	0.1102
61.3	0.1342	234.9	0.172	0.0563	0.198	0.126	0.1607	0.225	0.2449	0.154	0.910
61.6	0.2230	218.8	0.165	0.575	0.285	0.128	0.1824	0.227	0.1977	0.155	0.750
62.8	0.344			0.583	0.367	0.129	0.1919	0.234	0.1938	0.156	0.030
62.1	0.354	DATA SET 2		0.586	0.500	0.134	0.1977	0.234	0.1950	0.157	0.573
62.6	0.374	T = 293.0		0.595	0.372	0.132	0.1977	0.239	0.1459	0.157	0.343
63.3	0.150			0.601	0.218	0.135	0.1799	0.243	0.1357	0.158	0.563
64.2	0.337	0.356	0.130	0.605	0.201	0.138	0.1542			0.160	0.645
65.4	0.296	0.371	0.136	0.609	0.211	0.142	0.1327	DATA SET 4		0.162	0.679
65.6	0.350	0.376	0.143	0.612	0.489	0.143	0.1276	T = 55.0		0.165	0.524
68.3	0.35	0.381	0.136	0.620	0.396	0.140	0.1410			0.166	0.549
70.1	0.374	0.365	0.124	0.625	0.367	0.150	0.1520	0.124	0.0914	0.167	0.1033
72.2	0.374	0.359	0.214	0.633	0.145	0.151	0.1559	0.125	0.0927	0.169	0.3229
73.3	0.78	0.392	0.124	0.638	0.232	0.154	0.1559	0.126	0.1730	0.169	0.574
74.9	0.150	0.398	0.121	0.647	0.122	0.156	0.1545	0.239	0.1924	0.169	0.2958
75.8	0.113	0.4316	0.133	0.660	0.131	0.161	0.1545	0.127	0.1208	0.170	0.420
77.1	0.193	0.4142	0.144	0.672	0.142	0.163	0.1439	0.128	0.1349	0.170	0.534
78.6	0.216	0.4210	0.154	0.695	0.155	0.166	0.1324	0.129	0.1352	0.174	0.2344
80.1	0.351	0.421	0.149	0.706	0.175	0.168	0.1469	0.130	0.1324	0.177	0.1934
81.0	0.430	0.424	0.145	0.715	0.193	0.169	0.1742	0.132	0.1324	0.177	0.1994
84.1	0.391	0.430	0.154	0.726	0.237	0.170	0.2140	0.133	0.1349	0.180	0.3043
87.1	0.730	0.438	0.192	0.753	0.434	0.171	0.2275	0.133	0.1333	0.182	0.3542
88.0	0.757	0.445	0.273	0.763	0.444	0.172	0.2410	0.134	0.1343	0.182	0.3177
89.2	0.769	0.447	0.297	0.767	0.437	0.175	0.2466	0.135	0.1300	0.184	0.3351
91.7	0.781	0.450	0.316	0.775	0.396	0.177	0.2461	0.136	0.1343	0.185	0.3573
94.9	0.793	0.455	0.295	0.782	0.385	0.180	0.2393	0.136	0.1309	0.186	0.3776
95.7	0.776	0.406	0.262	0.793	0.393	0.186	0.3198	0.137	0.1080	0.188	0.2717
99.6	0.645	0.407	0.219	0.806	0.430	0.188	0.3342	0.140	0.0953	0.190	0.2244

TABLE 58. EXPERIMENTAL DATA ON THE REFLECTIVITY OF POTASSIUM IODIDE (continued)

λ	ρ
DATA SET 4(CONT.)	
0.192	0.1345
0.194	0.1754
0.196	0.1060
0.199	0.1511
0.200	0.1043
0.202	0.1349
0.204	0.1291
0.205	0.1770
0.208	0.1372
0.210	0.1517
0.211	0.9141
0.212	0.7764
0.215	0.4449
0.217	0.2799
0.219	0.2249
0.223	0.1932
0.225	0.1071
0.236	0.1459
0.243	0.1315
DATA SET 5	
T = 5.0	
0.198	0.34
0.199	0.229
0.199	0.132
0.199	0.130
0.199	0.132
0.199	0.132
0.199	0.130
0.199	0.145
0.200	0.135
0.200	0.149
0.201	0.107
0.202	0.107
0.203	0.136
0.204	0.147
0.206	0.174
0.208	0.179
0.210	0.170

λ	ρ
DATA SET 5(CONT.)	
0.201	0.154
0.202	0.142
0.203	0.114
0.204	0.079
0.205	0.061
0.207	0.028
0.207	0.023
0.208	0.023
0.208	0.129
0.208	0.046
0.208	0.101
0.208	0.231
0.209	0.426
0.209	0.542
0.210	0.639
0.211	0.667
0.211	0.727
0.212	0.779
0.212	0.841
0.212	0.827
0.211	0.846
0.211	0.878
0.212	0.907
0.212	0.914
0.212	0.912
0.212	0.873
0.212	0.833
0.212	0.708
0.212	0.629
0.213	0.565
0.213	0.507
0.213	0.404
0.213	0.425
0.214	0.397
0.214	0.366
0.214	0.339
0.215	0.313
0.215	0.292

λ	ρ
DATA SET 6	
T = 1.8	
0.209	0.516
0.209	0.538
0.210	0.566
0.210	0.580
0.210	0.600
0.210	0.615
0.210	0.633
0.210	0.650
0.210	0.665
0.210	0.677
0.210	0.687
0.210	0.693
0.210	0.700
0.210	0.708
0.210	0.719
0.211	0.740
0.210	0.750
0.210	0.766
0.210	0.730
0.211	0.791
0.211	0.802
0.211	0.814
0.211	0.826
0.211	0.843
0.211	0.866
0.211	0.879
0.211	0.893
0.211	0.899
0.211	0.899
0.211	0.895
0.211	0.867
0.211	0.876
0.211	0.872
0.211	0.869
0.211	0.869
0.211	0.864
0.211	0.859
0.211	0.845
0.211	0.826

λ	ρ
DATA SET 6(CONT.)	
0.211	0.848
0.211	0.794
0.211	0.754
0.211	0.760
0.211	0.735
0.212	0.711
0.212	0.689
0.212	0.673
0.212	0.643
0.212	0.649
0.212	0.588
0.212	0.549
0.212	0.516
DATA SET 7	
T = 303.0	
0.110	0.162
0.112	0.162
0.115	0.162
0.117	0.168
0.119	0.160
0.125	0.168
0.129	0.224
0.132	0.206
0.136	0.151
0.139	0.136
0.141	0.126
0.145	0.127
0.150	0.150
0.155	0.147
0.161	0.153
0.164	0.142
0.167	0.142
0.169	0.158
0.169	0.192
0.173	0.261
0.176	0.262
0.178	0.263
0.180	0.253

λ	ρ
DATA SET 7(CONT.)	
0.189	0.340
0.195	0.221
0.197	0.174
0.202	0.151
0.211	0.133
0.213	0.091
0.216	0.112
0.222	0.354
0.227	0.217
0.230	0.182
0.234	0.170
0.242	0.173
0.248	0.167
DATA SET 8	
T = 77.0	
0.110	0.197
0.114	0.180
0.115	0.190
0.117	0.217
0.118	0.251
0.120	0.250
0.122	0.240
0.124	0.230
0.127	0.213
0.128	0.310
0.131	0.272
0.134	0.243
0.136	0.214
0.138	0.182
0.139	0.163
0.142	0.111
0.142	0.111
0.144	0.113
0.146	0.173
0.149	0.193
0.155	0.192
0.160	0.192
0.161	0.173
0.164	0.125

λ	ρ
DATA SET 8(CONT.)	
0.106	0.120
0.108	0.252
0.171	0.395
0.175	0.310
0.177	0.284
0.179	0.334
0.184	0.424
0.193	0.370
0.196	0.442
0.198	0.299
0.199	0.249
0.199	0.200
0.203	0.195
0.203	0.265
0.209	0.052
0.210	0.098
0.213	0.798
0.216	0.362
0.219	0.232
[illegible]	[illegible]
0.227	0.178
[illegible]	0.083
0.242	0.174
0.248	0.207
DATA SET 9	
T = 93.0	
0.201	0.144
0.202	0.138
0.202	0.133
0.203	0.110
0.204	0.100
0.205	0.052
0.205	0.017
0.206	0.075
0.207	0.071
0.207	0.046
0.208	0.036
0.208	0.024

TABLE 58. EXPERIMENTAL DATA ON THE REFLECTIVITY OF POTASSIUM IODIDE (continued)

λ	ρ
DATA SET 9(CONT.)	
0.209	0.0232
0.209	0.0465
0.210	0.130
0.210	0.232
0.210	0.302
0.211	0.453
0.212	0.518
0.213	0.554
0.213	0.512
0.214	0.391
0.215	0.306
0.215	0.200
0.216	0.244
0.217	0.214
0.217	0.213
0.218	0.192
0.218	0.193
0.220	0.165
0.221	0.154
0.221	0.154
0.223	0.152
0.223	0.140
0.225	0.142
0.225	0.138
0.227	0.136
0.228	0.134
0.229	0.132
0.230	0.131
0.231	0.129
0.230	0.127
0.233	0.125
0.234	0.123
0.238	0.119
0.240	0.129
0.245	0.140
0.245	0.153
0.250	0.160
0.253	0.151

λ	ρ
DATA SET 10	
T = 298.0	
0.169	0.116
0.171	0.216
0.172	0.227
0.173	0.227
0.174	0.212
0.181	0.221
0.183	0.256
0.183	0.279
0.193	0.196
0.197	0.164
0.203	0.131
0.203	0.214
0.202	0.092
0.203	0.088
0.215	0.196
0.219	0.232
0.220	0.324
0.225	0.185
0.230	0.235
0.233	0.232
0.233	0.157
0.243	0.132
0.245	0.186
0.248	0.186
DATA SET 11	
T = 300.0	
63.3	0.024
67.4	0.072
72.0	0.091
75.3	0.119
77.2	0.185
80.1	0.650
80.2	0.732
89.7	0.768
92.2	0.768
95.0	0.746
96.8	0.711

λ	ρ
DATA SET 11(CONT.)	
102.	0.491
109.	0.399
107.	0.337
112.	0.285
117.	0.256
129.	0.225
136.	0.209
149.	0.203
DATA SET 12	
T = 298.0	
0.165	0.129
0.167	0.133
0.168	0.143
0.171	0.159
0.172	0.166
0.174	0.166
0.176	0.161
0.178	0.161
0.180	0.166
0.182	0.174
0.184	0.185
0.186	0.210
0.188	0.214
0.190	0.209
0.191	0.198
0.194	0.169
0.195	0.150
0.197	0.141
0.201	0.125
0.209	0.104
0.211	0.101
0.214	0.110
0.210	0.121
0.219	0.154
0.221	0.157
0.230	0.127
0.233	0.112
0.240	0.100

λ	ρ
DATA SET 12(CONT.)	
0.244	0.095
0.248	0.091
DATA SET 13	
T = 298.0	
0.154	0.099
0.156	0.095
0.160	0.089
0.164	0.094
0.166	0.093
0.167	0.087
0.169	0.115
0.171	0.131
0.173	0.139
0.175	0.150
0.177	0.146
0.180	0.148
0.183	0.138
0.184	0.144
0.186	0.169
0.187	0.174
0.188	0.184
0.189	0.187
0.190	0.183
0.191	0.169
0.193	0.162
0.196	0.113
0.198	0.101
0.201	0.095
0.202	0.086
0.204	0.081
0.207	0.084
0.209	0.084
0.210	0.080
0.211	0.074
0.212	0.070
0.215	0.073
0.216	0.080
0.218	0.057

λ	ρ
DATA SET 13(CONT.)	
0.219	0.062
0.220	0.093
0.224	0.153
0.225	0.161
0.226	0.156
0.230	0.213
0.231	0.215
0.233	0.695
0.235	0.691
0.238	0.689
DATA SET 14	
T = 300.0	
62.5	0.027
63.2	0.034
64.9	0.034
65.7	0.039
67.1	0.093
68.0	0.075
72.9	0.091
74.8	0.095
75.7	0.130
76.9	0.176
81.6	0.413
83.3	0.550
84.0	0.585
85.4	0.618
88.4	0.650
90.0	0.689
90.9	0.698
93.4	0.673
96.1	0.661
99.0	0.600
102.0	0.432
104.1	0.366
108.6	0.295
113.6	0.250
119.0	0.217
125.0	0.190

λ	ρ
DATA SET 14(CONT.)	
139.1	0.181
153.0	0.164
178.5	0.154
212.7	0.149
333.3	0.153
DATA SET 15	
T = 298.0	
0.054	0.037
0.055	0.029
0.056	0.028
0.058	0.037
0.059	0.042
0.061	0.041
0.061	0.034
0.062	0.032
0.065	0.039
0.067	0.032
0.069	0.026
0.072	0.028
0.073	0.032
0.075	0.045
0.079	0.049
0.082	0.044
0.083	0.045
0.080	0.031
0.083	0.023
0.091	0.033
0.094	0.035
0.098	0.031
0.102	0.015
0.107	0.046
0.113	0.073
0.120	0.067
0.133	0.133
0.141	0.081
0.155	0.114
0.160	0.066
0.169	0.098

TABLE 58. EXPERIMENTAL DATA ON THE REFLECTIVITY OF POTASSIUM IODIDE (continued)

λ	ρ
DATA SET 15(CONT.)	
0.179	0.167
0.185	0.257
0.197	0.137
0.207	0.113
0.213	0.077
0.215	0.291
0.225	0.149
0.245	0.112
0.275	0.093
0.319	0.079
0.429	0.067
0.653	0.062
DATA SET 16	
T = 290.0	
42.1	0.012
46.1	0.007
61.5	0.008
65.3	0.047
68.9	0.071
69.3	0.090
73.8	0.109
77.2	0.131
81.2	0.448
84.8	0.534
88.5	0.642
90.8	0.642
95.0	0.612
98.3	0.476
106.0	0.297
119.3	0.242
196.0	0.168
DATA SET 17	
T = 30.0	
41.8	0.010
50.3	0.008
54.3	0.032

λ	ρ
DATA SET 17(CONT.)	
58.5	0.001
62.5	0.005
64.5	0.035
68.1	0.089
70.1	0.123
72.2	0.188
74.6	0.392
76.1	0.640
79.3	0.764
84.1	0.799
88.5	0.793
95.4	0.509
100.3	0.300
114.4	0.219
130.0	0.184
210.1	0.162
600.9	0.140
DATA SET 18	
T = 4.2	
37.8	0.023
49.6	0.007
54.0	0.007
57.7	0.003
61.4	0.007
63.7	0.031
65.7	0.076
67.5	0.119
69.8	0.221
71.3	0.368
73.4	0.641
75.0	0.758
76.7	0.787
80.9	0.816
84.3	0.806
87.7	0.753
90.7	0.572
99.4	0.284
107.6	0.211

λ	ρ
DATA SET 18(CONT.)	
127.5	0.167
195.0	0.152



Figure 38. Transmission of Potassium Iodide

TABLE 59. SUMMARY OF MEASUREMENTS ON THE TRANSMISSION OF POTASSIUM IODIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	158	McCarthy, D.E.	1968	T	0.233-3.03	298	Single crystal; obtained from Harshaw Chemical Co.; 4.3 mm thick; transmission measured; data extracted from a figure.

TABLE 60. EXPERIMENTAL DATA ON THE TRANSMISSION OF POTASSIUM IODIDE

[Wavelength, λ, cm; Temperature, T, K; Transmission, τ]

λ	τ
DATA SET 1	
T = 298.0	
0.249	0.434
0.262	0.521
0.289	0.564
0.319	0.655
0.369	0.739
0.497	0.735
0.633	0.827
0.929	0.858
1.34	0.871
2.44	0.872
3.63	0.806

TABLE 61. PEAK POSITIONS (λ_{max}) IN μm AND HALF-WIDTHS (W) IN eV FOR THE F, R, M, AND N ABSORPTION BANDS IN POTASSIUM IODIDE*

Interionic dist., d (Å)	Temp.	F band		R_1 band	R_2 band	M band		N bands
		λ_{max}	W	λ_{max}	λ_{max}	λ_{max}	W	λ_{max}
3.53	RT	(0.718)†		(0.834)	(0.902)	(1.000)		
		0.685	0.34					
		0.689	0.35					
		0.692	0.41					
		0.695						
	NT	0.661	0.19					
		0.663	0.21					
		0.664	0.22					
		0.673	0.26					
		0.675						
		0.676						
	HT	0.659	0.14	0.810	0.905	1.010		
		0.666	0.18					
		0.674						

* Values were taken from Ref. [69].

† Values given in parentheses are calculated from the Ivey relations [70].

F band $\lambda_{max} = 703\ d^{1.84}$ for NaCl structure, $\lambda_{max} = 251\ d^{2.5}$ for CsCl structure.

R band $\lambda_{max} = 816\ d^{1.84}$

R band $\lambda_{max} = 884\ d^{1.84}$

M band $\lambda_{max} = 1400\ d^{1.56}$

TABLE 62. RECOMMENDED VALUES ON ABSORPTION COEFFICIENT OF POTASSIUM IODIDE IN IR REGION AT 300 K

ν, cm^{-1}	λ, μm	Absorption Coefficient, cm^{-1}	
		Intrinsic*	Observed† (Selected)
2.000E+02	50.0	1.4E+1	
2.440E+02	41.0	4.1E+0	3.6E+0
2.490E+02	40.2	3.5E+0	2.7E+0
2.640E+02	37.9	2.3E+0	2.4E+0
2.690E+02	37.2	2.0E+0	1.8E+0
2.830E+02	35.3	1.3E+0	1.2E+0
2.900E+02	34.5	1.1E+0	9.8E-1
3.030E+02	33.0	7.6E-1	7.8E-1
3.070E+02	32.6	6.8E-1	6.2E-1
3.240E+02	30.9	4.2E-1	4.9E-1
3.320E+02	30.1	3.3E-1	3.5E-1
3.420E+02	29.2	2.5E-1	2.6E-1
3.540E+02	28.2	1.7E-1	2.2E-1
3.630E+02	27.5	1.3E-1	1.6E-1
3.730E+02	26.8	1.0E-1	1.2E-1
3.830E+02	26.1	7.8E-2	5.7E-2
3.930E+02	25.4	5.8E-2	5.4E-2
4.020E+02	24.9	4.5E-2	4.3E-2
4.120E+02	24.3	3.4E-2	2.9E-2
4.220E+02	23.7	2.5E-2	2.2E-2
4.320E+02	23.1	1.9E-2	1.5E-2
4.410E+02	22.7	1.5E-2	1.3E-2
4.510E+02	22.2	1.1E-2	1.0E-2
4.580E+02	21.8	9.2E-3	7.5E-3
4.680E+02	21.4	6.9E-3	6.7E-3
4.830E+02	20.7	4.5E-3	6.0E-3
4.950E+02	20.2	3.2E-3	4.5E-3
5.000E+02	20.0	2.7E-3	
6.000E+02	16.7	1.6E-4	
7.000E+02	14.3	9.3E-6	
8.000E+02	12.5	5.4E-7	
9.000E+02	11.1	3.1E-8	
9.434E+02	10.6	9.1E-9	
1.000E+03	10.0	1.8E-9	

*Intrinsic values were calculated according to Eq. (38) with uncertainties about ±10%.

†Values in this column are the *total absorption coefficient* which are either lowest reported or those used to define the constants in Eq. (38). Uncertainties of these values are about ±10%. Values lower than 1.0E-3 carry higher uncertainties up to ±30%.

3.7. Cesium Iodide, CsI

Early measurements on the refractive index of CsI were made by Sprockhoff [140] in 1904, using a minimum deviation method for three visible spectral lines, 0.486, 0.589, and 0.656 μm. These three values were the only available data for about 50 years. The main reason for such a long period of inactivity was the difficulty in growing adequate CsI crystals. Large and good quality crystals, suitable for optical components, were not available; also, the need for infrared transparency was not generally felt.

It was not until 1955 that the refractive index for a wide range of transmission (0.129 to 53 μm) was measured by Rodney [151] on several cesium iodide samples grown by the Harshaw Chemical Company. The temperature coefficients of the refractive index were determined for each wavelength and all data were reduced to 297 K. Rodney adopted a dispersion equation of the Sellmeier type, simplified to five terms, to fit the reduced data.

In the ultraviolet region, 0.20-0.25 μm, Lamatsch et al. [152] derived the refractive indices from information on the transmission and reflection spectra. Since they used vacuum-evaporated thin film samples, the wavelengths of the two absorption bands obtained are higher than that of the bulk material. The large discrepancies between this set of data and that calculated from Rodney's work are to be expected.

Values of the refractive index beyond the transparent region, in the infrared, were obtained by Vergnat et al. [26] in 1969, by analyzing the reflection spectrum. They found that the wavelengths of infrared absorption bands are 117.65 and 161.29 μm at room temperature. One of the two is in close agreement with that of Rodney, which predominantly contributes to the absorption. Li [33] reduced the experimental data then available to a common temperature of 293 K and after careful analysis, generated a Sellmeier type formula representing the refractive index of CsI at 293 K in the spectral region between 0.25 and 67 μm,

$$n = 1.27587 + \frac{0.68689\,\lambda^2}{\lambda^2-(0.130)^2} + \frac{0.26090\,\lambda^2}{\lambda^2-(0.147)^2} + \frac{0.06256\,\lambda^2}{\lambda^2-(0.163)^2} + \frac{0.06527\,\lambda^2}{\lambda^2-(0.177)^2}$$

$$+ \frac{0.14991}{\lambda^2-(0.185)^2} + \frac{0.51818}{\lambda^2-(0.206)^2} + \frac{0.01918}{\lambda^2-(0.218)^2} + \frac{3.38229}{\lambda^2-(161.29)^2} \quad (39)$$

where λ is in units of μm.

Available data on the absorption coefficient, reflectivity, and transmission of CsI compiled in the present work are given in Tables 62 to 70 and are plotted in Figures 39 to 44. Investigations of absorption coefficient for practical applications are generally classified into three spectral regions: the ultraviolet and infrared absorption edges, and the transparent regions. In the case of CsI, available data in these regions are very limited. In the ultraviolet absorption edge region, Philipp and Taft [153] reported their absorption measurements for evaporated films of CsI. Their results were in reasonable agreement with earlier observation of Hilsch and Pohl [19] and Schneider and O'Bryan [20]. Lamatsch et al. [152] measured absorption coefficient for CsI film in the excitonic region, their results in the absorption edge were in concordance with those of Philipp and Taft [153].

In the multiphonon absorption region, Beairsto and Eldridge [154] determined absorption coefficient for CsI by measuring the transmission of samples of various thicknesses using a Fourier spectrophotometer. They found that the most reliable values of the absorption coefficient, α, were obtained when the thickness of the sample, d, was such that $\alpha d = 1.0$. As CsI does not cleave, the samples were cut with a wire saw and then carefully polished. With appropriate care, they found that the samples, stored over long periods, showed little deterioration.

As shown in Figures 39 to 44, the optical properties of CsI behave similarly as the other members of alkali ahlides. Although it is clearly suggested that in both of the absorption edges the exponential dependence of the absorption coefficient on frequency should hold, data at hand are insufficient to define unique solutions. As a result, it is not feasible to report recommended values, and only measurement information and original data are presented here in Tables 63 to 71.



Figure 39. Absorption Coefficient of Cesium Iodide (Wavenumber Dependence)



Figure 40. Absorption Coefficient of Cesium Iodide in the Urbach Tail Region



Figure 41. Absorption Coefficient of Cesium Iodide in the Multiphonon Region

TABLE 63. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF CESIUM IODIDE (Wavenumber Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	154	Beairsto, J.A.B. and Eldridge, J.E.	1973	T	3.79×10^{3}-1.49×10^{2}	12	Single crystal; plate specimens of different thickness; mechanically and chemically polished; transmittance spectra obtained and absorption coefficients deduced; absorption-coefficient data extracted from a figure.
2	154	Beairsto, J.A.B. and Eldridge, J.E.	1973	T	1.5×10^{1}-1.7×10^{2}	77	Same as above except at a higher temperature.
3	154	Beairsto, J.A.B. and Eldridge, J.E.	1973	T	1.5×10^{1}-2.0×10^{2}	300	Same as above except at a higher temperature.
4	155	Mitolidi, E.N., Neklyudov, I.M., and Panova, A.N.	1974	T	3.8×10^{1}-4.2×10^{1}	300	Single crystal; grown in evacuated quartz vials by the Stockbarger method from melt of pure salts; 2.5 x 3 x 8 mm specimen; mechanically ground and chemically polished; annealed for six hours at 773.15 K; absorption-coefficient data taken from a figure.
5	153	Philipp, H. and Taft, E.	1956	R	4.03×10^{4}-5.4×10^{4}	470	Pure CsI; obtained from the Fairmount Chemical Co.; thin film specimens evaporated onto a sapphire substrate; absorption coefficients measured; data extracted from a figure.
6	153	Philipp, H. and Taft, E.	1956	R	4.1×10^{4}-5.4×10^{4}	300	Similar to above except at a lower temperature.
7	153	Philipp, H. and Taft, E.	1956	R	4.3×10^{4}-5.4×10^{4}	180	Similar to above except at a lower temperature.
8	153	Philipp, H. and Taft, E.	1956	R	4.0×10^{4}-5.4×10^{4}	80	Similar to above except at a lower temperature.
9	156	Dianov, E.M.	1967	T	1.5×10^{1}-2.1×10^{1}	293	Single crystal; plane-parallel plate or disk specimens of 50-80 mm diameter and various thicknesses; average absorption coefficients determined from the measured values of transmission in the absence of internal interference; data extracted from a figure.
10	156	Dianov, E.M.	1967	R	7.27-20.8	293	Same as above.
11	156	Dianov, E.M.	1967	R	7.25-20.8	78	Similar to above except at a lower temperature.
12	152	Lautsch, H., Rossel, J., and Saurer, E.	1972	Z	4.0×10^{4}-5.0×10^{4}	300	Thin film specimen; evaporated on suprasil quartz substrate; absorption coefficients deduced from transmission and reflectivity measurements; data extracted from a figure.
13	152	Lautsch, H., et al.	1972	Z	4.0×10^{4}-5.0×10^{4}	77	Same as above except at a lower temperature.

TABLE 63. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF CESIUM IODIDE (Wavenumber Dependence) (continued)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
14	157	Said, K.I. and Green, G.W.	1977	R	$4.3x10^4$-$9.2x10^4$	300	Crystal; mechanically polished in mineral oil then rinsed and kept at 10^{-6} Torr; annealed at 400 K for several hours before measurement; reflection spectrum taken and analyzed by the Kramers-Kronig relation to obtain absorption coefficients; data extracted from a figure.
15	157	Said, K.I. and Green, G.W.	1977	R	$4.4x10^4$-$9.2x10^4$	25	Same as above.
16	108	Dianov, E.M. and Irisova, N.A.	1966	T	5	298	Natural crystal; plate specimen of 5.5 and 22 mm thick; absorption coefficient determined from transmission measurement; data extracted from a table.

TABLE 64. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF CESIUM IODIDE (Wavenumber Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

ν	α
DATA SET 1	
T = 1[illegible]	
1.492E+2	1.35[illegible]E-1
1.47[illegible]E+2	2.[illegible]2E-1
1.4[illegible]E+2	2.239E-1
1.[illegible]E+2	2.4[illegible]E-1
1.4[illegible]E+2	2.7[illegible]E-1
1.394E+2	3.312E-1
1.391E+2	3.890E-1
1.374E+2	4.467E-1
1.3[illegible]E+2	5.243E-1
1.3[illegible]E+2	6.126E-1
1.3[illegible]E+2	7.244E-1
1.334E+2	8.511E-1
1.31[illegible]E+2	1.251E+0
1.3[illegible]E+2	1.413E+0
1.297E+2	1.62[illegible]E+0
1.289E+2	1.9[illegible]E+0
1.282E+2	2.231E+0
1.273E+2	2.5[illegible]E+0
1.26[illegible]E+2	[illegible]
1.251E+2	4.333E+0
1.24[illegible]E+2	5.435E+0
1.24[illegible]E+2	6.3[illegible]E+0
1.236E+2	7.413E+0
1.217E+2	8.71[illegible]E+0
6.7[illegible]E+1	7.413E+0
6.31[illegible]E+1	7.413E+0
6.3[illegible]E+1	6.31[illegible]E+0
6.28[illegible]E+1	5.243E+0
6.24[illegible]E+1	4.467E+0
6.17[illegible]E+1	3.631E+0
6.17[illegible]E+1	3.[illegible]E+0
6.[illegible]E+1	2.6[illegible]E+0
6.[illegible]E+1	2.233E+0
5.63[illegible]E+1	1.8[illegible]E+0
5.91[illegible]E+1	1.473E+0
5.72[illegible]E+1	1.2[illegible]E+0
5.39[illegible]E+1	5.3[illegible]E-1
5.28[illegible]E+1	6.701E-1
5.19[illegible]E+1	5.0[illegible]E-1

ν	α
DATA SET 1(CONT.)	
5.[illegible]E+1	4.571E-1
4.8[illegible]E+1	3.715E-1
4.7[illegible]E+1	2.894E-1
4.5[illegible]E+1	2.291E-1
4.[illegible]E+1	1.662E-1
4.[illegible]E+1	1.549E-1
3.79[illegible]E+1	1.23[illegible]E-1
DATA SET 2	
T = 77.0	
1.09[illegible]E+2	3.389E-1
1.07[illegible]E+2	3.3[illegible]E-1
1.0[illegible]E+2	4.2[illegible]E-1
1.01[illegible]E+2	4.76[illegible]E-1
1.993E+2	5.246E-1
1.963E+2	5.754E-1
1.93[illegible]E+2	6.457E-1
1.9[illegible]E+2	6.31[illegible]E-1
1.8[illegible]E+2	7.702E-1
1.4[illegible]E+2	8.531E-1
1.417E+2	9.55[illegible]E-1
1.3[illegible]E+2	1.122E+0
1.30[illegible]E+2	1.33[illegible]E+0
1.337E+2	1.535E+0
1.31[illegible]E+2	2.042E+0
1.3[illegible]E+2	2.512E+0
1.293E+2	3.236E+0
1.27[illegible]E+2	4.169E+0
1.27[illegible]E+2	5.49[illegible]E+0
1.26[illegible]E+2	6.9[illegible]E+0
1.24[illegible]E+2	8.511E+0
1.2[illegible]E+2	1.0[illegible]E+1
1.233E+2	1.288E+1
1.223E+2	1.549E+1
1.21[illegible]E+2	1.99[illegible]E+1
1.23[illegible]E+2	2.399E+1
1.199E+2	2.938E+1
1.189E+2	3.467E+1
1.181E+2	4.169E+1

ν	α
DATA SET 2(CONT.)	
1.172E+2	5.[illegible]12E+1
1.159E+2	5.754E+1
1.134E+2	6.457E+1
1.119E+2	5.370E+1
1.[illegible]8E+2	4.786E+1
1.[illegible]9E+2	4.786E+1
1.032E+2	5.623E+1
1.011E+2	6.[illegible]7E+1
9.9[illegible]E+1	8.128E+1
9.8[illegible]E+1	9.772E+1
9.73[illegible]E+1	1.148E+2
9.62[illegible]E+1	1.38[illegible]E+2
9.56[illegible]E+1	1.698E+2
9.45[illegible]E+1	2.[illegible]42E+2
5.97[illegible]E+1	5.49[illegible]E+1
5.870E+1	4.365E+1
5.830E+1	3.631E+1
5.72[illegible]E+1	2.951E+1
5.62[illegible]E+1	2.45[illegible]E+1
5.4[illegible]E+1	1.995E+1
5.3[illegible]E+1	1.66[illegible]E+1
5.12[illegible]E+1	1.343E+1
4.94[illegible]E+1	1.122E+1
4.80[illegible]E+1	9.333E+0
4.42[illegible]E+1	8.128E+0
4.11[illegible]E+1	7.[illegible]79E+0
3.80[illegible]E+1	6.1[illegible]5E+0
3.63[illegible]E+1	5.023E+0
3.41[illegible]E+1	4.093E+0
3.07[illegible]E+1	4.266E+0
2.84[illegible]E+1	3.715E+0
2.63[illegible]E+1	3.162E+0
2.431E+1	2.692E+0
2.19[illegible]E+1	2.399E+0
2.62[illegible]E+1	2.[illegible]42E+0
1.80[illegible]E+1	1.738E+0
1.68[illegible]E+1	1.445E+0
1.50[illegible]E+1	1.2[illegible]2E+0

ν	α
DATA SET 3	
T = 30[illegible].0	
1.93[illegible]E+2	2.951E-1
1.961E+2	3.467E-1
1.943E+2	4.[illegible]74E-1
1.927E+2	4.398E-1
1.914E+2	5.754E-1
1.892E+2	6.[illegible]7E-1
1.882E+2	8.128E-1
1.86[illegible]E+2	9.333E-1
1.829E+2	1.148E+0
1.8[illegible]E+2	1.318E+0
1.782E+2	1.514E+0
1.755E+2	1.698E+0
1.732E+2	1.862E+0
1.71[illegible]E+2	2.[illegible]89E+0
1.688E+2	2.239E+0
1.665E+2	2.57[illegible]E+0
1.638E+2	2.884E+0
1.616E+2	3.236E+0
1.593E+2	3.715E+0
1.562E+2	4.169E+0
1.53[illegible]E+2	4.571E+0
1.517E+2	5.129E+0
1.485E+2	5.623E+0
1.465E+2	6.457E+0
1.439E+2	7.[illegible]79E+0
1.413E+2	7.[illegible]8E+0
1.337E+2	8.511E+0
1.305E+2	1.[illegible]1E+1
1.345E+2	1.122E+1
1.324E+2	1.259E+1
1.299E+2	1.445E+1
1.277E+2	1.698E+1
1.266E+2	2.042E+1
1.245E+2	2.399E+1
1.229E+2	2.884E+1
1.215E+2	3.548E+1
1.199E+2	4.169E+1
1.188E+2	5.012E+1
1.179E+2	5.888E+1

ν	α
DATA SET 3(CONT.)	
1.170E+2	6.761E+1
1.16[illegible]E+2	7.762E+1
1.148E+2	9.333E+1
1.1[illegible]E+2	1.09[illegible]E+2
1.123E+2	1.284E+2
1.111E+2	1.47[illegible]E+2
1.08[illegible]E+2	1.385E+2
1.057E+2	1.595E+2
1.024E+2	1.698E+2
1.012E+2	1.9[illegible]E+2
9.95[illegible]E+1	2.049E+2
9.65[illegible]E+1	2.57[illegible]E+2
9.49[illegible]E+1	3.09[illegible]E+2
5.51[illegible]E+1	2.042E+2
5.42[illegible]E+1	1.66[illegible]E+2
5.32[illegible]E+1	1.38[illegible]E+2
5.24[illegible]E+1	9.333E+1
4.98[illegible]E+1	7.762E+1
4.98[illegible]E+1	7.[illegible]7E+1
4.65[illegible]E+1	6.02[illegible]E+1
4.55[illegible]E+1	5.248E+1
4.31[illegible]E+1	4.571E+1
4.29[illegible]E+1	4.169E+1
4.[illegible]16E+1	3.84[illegible]E+1
3.35[illegible]E+1	3.162E+1
3.74[illegible]E+1	2.7[illegible]E+1
3.5[illegible]E+1	2.51[illegible]E+1
3.39[illegible]E+1	2.13[illegible]E+1
2.99[illegible]E+1	1.738E+1
2.8[illegible]E+1	1.51[illegible]E+1
2.64[illegible]E+1	1.445E+1
2.49[illegible]E+1	1.259E+1
2.35[illegible]E+1	1.072E+1
2.2[illegible]E+1	9.55[illegible]E+0
2.1[illegible]E+1	8.511E+0
1.9[illegible]E+1	7.079E+0
1.67[illegible]E+1	5.888E+0
1.53[illegible]E+1	4.78[illegible]E+0

ν	α
DATA SET 4	
T = 300.0	
4.161E+1	1.419E+1
4.159E+1	1.311E+1
4.153E+1	1.2[illegible]E+1
4.15[illegible]E+1	1.19[illegible]E+1
4.137E+1	1.[illegible]6E+1
4.127E+1	9.470E+0
4.114E+1	8.48[illegible]E+0
4.093E+1	7.62[illegible]E+0
4.08[illegible]E+1	6.72[illegible]E+0
4.065E+1	6.23[illegible]E+0
4.[illegible]43E+1	5.92[illegible]E+0
4.[illegible]E+1	5.5[illegible]E+0
3.960E+1	5.25[illegible]E+0
3.939E+1	4.97[illegible]E+0
3.909E+1	4.85[illegible]E+0
3.870E+1	4.[illegible]E+0
3.846E+1	4.47[illegible]E+0
DATA SET 5	
T = 47[illegible].0	
5.4[illegible]E+4	2.43[illegible]E+5
5.33[illegible]E+4	3.72[illegible]E+5
5.323E+4	3.77[illegible]E+5
5.3[illegible]E+4	3.73[illegible]E+5
5.23[illegible]E+4	3.7[illegible]E+5
5.25[illegible]E+4	3.57[illegible]E+5
5.6[illegible]E+4	2.87[illegible]E+5
5.1[illegible]E+4	2.5[illegible]E+5
5.[illegible]E+4	2.3[illegible]E+5
5.[illegible]24E+4	2.23[illegible]E+5
5.[illegible]E+4	2.23[illegible]E+5
4.97[illegible]E+4	2.3[illegible]E+5
4.887E+4	2.69[illegible]E+5
4.879E+4	2.73[illegible]E+5
4.863E+4	2.7[illegible]E+5
4.839E+4	2.72[illegible]E+5
4.823E+4	2.62[illegible]E+5
4.877E+4	2.35[illegible]E+5

TABLE 64. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF CESIUM IODIDE (Wavenumber Dependence) (continued)

ν	α
DATA SET 5(CONT.)	
4.645E+4	1.270E+5
4.556E+4	1.3[illegible]E+5
4.516E+4	1.370E+5
4.450E+4	1.5[illegible]E+5
4.435E+4	1.522E+5
4.412E+4	1.4[illegible]E+5
4.379E+4	1.2[illegible]E+5
4.3[illegible]E+4	1.0[illegible]E+5
4.33[illegible]E+4	9.1[illegible]E+4
4.315E+4	6.8[illegible]E+4
4.29[illegible]E+4	5.3[illegible]E+4
4.242E+4	3.3[illegible]E+4
4.195E+4	2.1[illegible]E+4
4.137E+4	1.2[illegible]E+4
4.03[illegible]E+4	5.0[illegible]E+3
DATA SET 6	
T = 3[illegible].0	
5.4[illegible]E+4	3.73[illegible]E+5
5.371E+4	3.8[illegible]E+5
5.35[illegible]E+4	3.8[illegible]E+5
5.3[illegible]E+4	3.8[illegible]E+5
5.2[illegible]E+4	3.[illegible]E+5
5.[illegible]E+4	2.1[illegible]E+5
5.1[illegible]E+4	2.0[illegible]E+5
5.0[illegible]E+4	2.0[illegible]E+5
4.97[illegible]E+4	2.0[illegible]E+5
4.95[illegible]E+4	2.1[illegible]E+5
4.9[illegible]E+4	2.2[illegible]E+5
4.8[illegible]E+4	2.4[illegible]E+5
4.871E+4	2.8[illegible]E+5
4.847E+4	3.12[illegible]E+5
4.831E+4	3.1[illegible]E+5
4.815E+4	3.1[illegible]E+5
4.79[illegible]E+4	2.9[illegible]E+5
4.758E+4	2.8[illegible]E+5
4.710E+4	2.5[illegible]E+5
4.665E+4	2.3[illegible]E+5
4.653E+4	1.32[illegible]E+5

ν	α
DATA SET 6(CONT.)	
4.637E+4	1.330E+5
4.621E+4	1.390E+5
4.540E+4	2.0[illegible]E+5
4.524E+4	2.080E+5
4.508E+4	2.15[illegible]E+5
4.5[illegible]E+4	2.15[illegible]E+5
4.4[illegible]E+4	2.12[illegible]E+5
4.47[illegible]E+4	2.0[illegible]E+5
4.452E+4	1.9[illegible]E+5
4.435E+4	1.[illegible]E+5
4.395E+4	6.3[illegible]E+4
4.371E+4	5.[illegible]E+4
4.339E+4	3.9[illegible]E+4
4.3[illegible]E+4	3.1[illegible]E+4
4.2[illegible]E+4	2.2[illegible]E+4
4.19[illegible]E+4	1.2[illegible]E+4
4.1[illegible]E+4	8.0[illegible]E+3
DATA SET 7	
T = 28[illegible]	
5.4[illegible]E+4	4.0[illegible]E+5
5.339E+4	4.[illegible]E+5
5.347[illegible]+4	3.970E+5
5.292E+4	3.[illegible]E+5
5.234E+4	2.78[illegible]E+5
5.161E+4	2.51[illegible]E+5
5.122E+4	2.35[illegible]E+5
5.065E+4	2.1[illegible]E+5
5.[illegible]E+4	1.84[illegible]E+5
4.97[illegible]E+4	1.4[illegible]E+5
4.964E+4	1.79[illegible]E+5
4.927E+4	1.940E+5
4.911E+4	2.09[illegible]E+5
4.895E+4	2.40[illegible]E+5
4.871E+4	2.91[illegible]E+5
4.859E+4	3.28[illegible]E+5
4.839E+4	3.63[illegible]E+5
4.831E+4	3.63[illegible]E+5
4.823E+4	3.62[illegible]E+5

ν	α
DATA SET 7(CONT.)	
4.8[illegible]E+4	3.350E+5
4.798E+4	2.860E+5
4.766E+4	2.61[illegible]E+5
4.734E+4	1.45[illegible]E+5
4.718E+4	1.31[illegible]E+5
4.71[illegible]E+4	1.27[illegible]E+5
4.69[illegible]E+4	1.24[illegible]E+5
4.6[illegible]E+4	1.37[illegible]E+5
4.637E+4	1.59[illegible]E+5
4.6[illegible]E+4	2.16[illegible]E+5
4.6[illegible]E+4	2.74[illegible]E+5
4.597E+4	3.320E+5
4.589E+4	3.510E+5
4.581E+4	3.54[illegible]E+5
4.573E+4	3.49[illegible]E+5
4.548E+4	2.890E+5
4.54[illegible]E+4	2.47[illegible]E+5
4.532E+4	1.95[illegible]E+5
4.516E+4	1.45[illegible]E+5
4.5[illegible]E+4	9.9[illegible]E+4
4.492E+4	7.0[illegible]E+4
4.4[illegible]E+4	6.[illegible]E+4
4.435E+4	4.2[illegible]E+4
4.387E+4	2.8[illegible]E+4
4.315E+4	1.860E+4
DATA SET 8	
T = 8[illegible].0	
5.4[illegible]E+4	3.78[illegible]E+5
5.323E+4	3.[illegible]E+5
5.25[illegible]E+4	2.57[illegible]E+5
5.16[illegible]E+4	2.24[illegible]E+5
5.121E+4	2.22[illegible]E+5
5.089E+4	2.19[illegible]E+5
5.073E+4	2.1[illegible]E+5
5.0[illegible]E+4	1.99[illegible]E+5
4.984E+4	1.59[illegible]E+5
4.908E+4	1.56[illegible]E+5
4.952E+4	1.540E+5

ν	α
DATA SET 8(CONT.)	
4.935E+4	1.56[illegible]E+5
4.919E+4	1.68[illegible]E+5
4.895E+4	2.0[illegible]E+5
4.847E+4	2.56[illegible]E+5
4.855E+4	3.3[illegible]E+5
4.847E+4	3.99[illegible]E+5
4.839E+4	4.36[illegible]E+5
4.831E+4	4.3[illegible]E+5
4.823E+4	3.05[illegible]E+5
4.798E+4	2.90[illegible]E+5
4.79[illegible]E+4	2.3[illegible]E+5
4.774E+4	2.00[illegible]E+5
4.76[illegible]E+4	1.47[illegible]E+5
4.753E+4	1.03[illegible]E+5
4.742E+4	9.9[illegible]E+4
4.726E+4	1.0[illegible]E+5
4.71[illegible]E+4	1.11[illegible]E+5
4.702E+4	1.52[illegible]E+5
4.677E+4	2.91[illegible]E+5
4.653E+4	3.36[illegible]E+5
4.645E+4	4.0[illegible]E+5
4.629E+4	4.85[illegible]E+5
4.62[illegible]E+4	4.40[illegible]E+5
4.621E+4	4.0[illegible]E+5
4.605E+4	3.13[illegible]E+5
4.597E+4	2.52[illegible]E+5
4.597E+4	2.1[illegible]E+5
4.589E+4	1.4[illegible]E+5
4.573E+4	1.04[illegible]E+5
4.556E+4	7.9[illegible]E+4
4.510E+4	5.3[illegible]E+4
4.408E+4	4.1[illegible]E+4
4.427E+4	3.10[illegible]E+4
4.359E+4	2.24[illegible]E+4
4.266E+4	1.44[illegible]E+4
4.194E+4	1.0[illegible]E+4
4.105E+4	7.0[illegible]E+3
4.032E+4	3.0[illegible]E+3

ν	α
DATA SET 9	
T = 293.0	
2.358E+1	9.748E+0
1.945E+1	8.248E+0
1.669E+1	6.965E+0
1.511E+1	5.752E+0
DATA SET 10	
T = 293.0	
2.375E+1	9.364E+0
1.984E+1	8.677E+0
1.862E+1	7.863E+0
1.715E+1	6.768E+0
1.59[illegible]E+1	6.013E+0
1.453E+1	4.9[illegible]E+0
1.350E+1	4.52[illegible]E+0
1.232E+1	3.994E+0
1.217E+1	3.837E+0
1.143E+1	3.695E+0
1.089E+1	2.998E+0
1.03[illegible]E+1	2.705E+0
9.862E+0	2.528E+0
9.515E+0	2.32[illegible]E+0
8.945E+0	2.181E+0
8.365E+0	1.672E+0
7.273E+0	1.545E+0
DATA SET 11	
T = 78.0	
2.375E+1	2.216E+0
1.835E+1	1.795E+0
1.689E+1	1.592E+0
1.565E+1	1.337E+0
1.433E+1	1.170E+0
1.3[illegible]E+1	1.0[illegible]E+0
1.265E+1	9.09[illegible]E-1
1.199E+1	8.739E-1
1.178E+1	7.177E-1
9.993E+0	6.4[illegible]E-1

ν	α
DATA SET 11(CONT.)	
8.096E+0	5.136E-1
7.257E+0	3.648E-1
DATA SET 12	
T = 3[illegible].0	
4.959E+4	5.289E+5
4.9[illegible]E+4	6.52[illegible]E+5
4.882E+4	7.520E+5
4.9[illegible]E+4	8.0[illegible]E+5
4.829E+4	7.793E+5
4.79[illegible]E+4	7.103E+5
4.77[illegible]E+4	4.9[illegible]E+5
4.74[illegible]E+4	3.8[illegible]E+5
4.72[illegible]E+4	3.197E+5
4.69[illegible]E+4	3.0[illegible]E+5
4.0[illegible]E+4	3.256E+5
4.599E+4	3.842E+5
4.5[illegible]E+4	5.427E+5
4.531E+4	5.80[illegible]E+5
4.515E+4	5.219E+5
4.4[illegible]E+4	4.6[illegible]E+5
4.478E+4	3.5[illegible]E+5
4.456E+4	2.615E+5
4.435E+4	1.657E+5
4.423E+4	1.1[illegible]E+5
4.4[illegible]E+4	0.256E+4
4.3[illegible]E+4	4.60[illegible]E+4
4.323E+4	3.097E+4
4.27[illegible]E+4	1.5[illegible]E+4
4.4[illegible]E+4	1.459E+4
4.1[illegible]E+4	7.0[illegible]E+3
DATA SET 13	
T = 77.3	
4.55[illegible]E+4	4.[illegible]6E+5
4.831E+4	4.387E+5
4.8[illegible]E+4	5.753E+5
4.97[illegible]E+4	5.241E+5

TABLE 64. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF CESIUM IODIDE (Wavenumber Dependence) (continued)

ν	α	ν	α	ν	α	ν	α	ν	α	ν	α
DATA SET 13(CONT.)		DATA SET 14(CONT.)		DATA SET 14(CONT.)		DATA SET 15(CONT.)		DATA SET 15(CONT.)		DATA SET 15(CONT.)	
4.861E+4	9.341E+5	8.981E+4	4.345E+5	5.564E+4	8.739E+5	8.037E+4	1.233E+6	6.134E+4	6.499E+5	4.756E+4	4.035E+5
4.854E+4	9.553E+5	8.794E+4	4.542E+5	5.527E+4	7.917E+5	7.919E+4	1.202E+6	6.134E+4	4.571E+5	4.722E+4	2.944E+5
4.840E+4	9.339E+5	8.531E+4	4.664E+5	5.490E+4	7.465E+5	7.863E+4	1.506E+6	6.078E+4	3.468E+5	4.720E+4	1.999E+5
4.826E+4	8.934E+5	8.344E+4	5.402E+5	5.415E+4	7.192E+5	7.806E+4	1.598E+6	6.060E+4	2.186E+5	4.731E+4	3.402E+5
4.806E+4	8.187E+5	8.159E+4	6.933E+5	5.363E+4	5.571E+5	7.705E+4	1.644E+6	5.948E+4	3.380E+5	4.702E+4	5.693E+5
4.812E+4	7.300E+5	7.900E+4	8.468E+5	5.304E+4	4.112E+5	7.732E+4	1.582E+6	5.873E+4	4.183E+5	4.681E+4	8.644E+5
4.792E+4	6.312E+5	7.835E+4	9.599E+5	5.231E+4	2.971E+5	7.640E+4	1.456E+6	5.817E+4	5.343E+5	4.651E+4	1.113E+6
4.765E+4	4.173E+5	7.685E+4	8.875E+5	5.156E+4	2.034E+5	7.505E+4	1.336E+6	5.760E+4	6.506E+5	4.600E+4	1.300E+6
4.776E+4	2.553E+5	7.612E+4	8.778E+5	5.099E+4	2.358E+5	7.473E+4	1.241E+6	5.741E+4	1.109E+6	4.697E+4	1.516E+6
4.778E+4	2.334E+5	7.572E+4	8.992E+5	5.006E+4	2.369E+5	7.384E+4	1.174E+6	5.722E+4	1.384E+6	4.666E+4	1.579E+6
4.771E+4	2.044E+5	7.384E+4	9.251E+5	4.931E+4	2.649E+5	7.305E+4	1.136E+6	5.665E+4	1.489E+6	4.661E+4	1.394E+6
4.753E+4	1.950E+5	7.196E+4	9.495E+5	4.892E+4	3.258E+5	7.231E+4	1.023E+6	5.623E+4	1.557E+6	4.642E+4	1.130E+6
4.746E+4	2.117E+5	7.033E+4	9.813E+5	4.836E+4	4.653E+5	7.194E+4	9.175E+5	5.573E+4	1.347E+6	4.642E+4	1.133E+6
4.719E+4	2.004E+5	6.970E+4	1.035E+6	4.816E+4	4.533E+5	7.138E+4	9.095E+5	5.559E+4	1.032E+6	4.643E+4	9.031E+5
4.700E+4	3.442E+5	6.870E+4	1.188E+6	4.779E+4	4.010E+5	7.064E+4	9.249E+5	5.556E+4	8.195E+5	4.644E+4	6.502E+5
4.652E+4	6.392E+5	6.813E+4	1.201E+6	4.724E+4	2.648E+5	6.971E+4	8.383E+5	5.511E+4	6.000E+5	4.627E+4	3.890E+5
4.643E+4	8.021E+5	6.731E+4	1.357E+6	4.706E+4	1.668E+5	6.859E+4	1.041E+6	5.482E+4	4.293E+5	4.627E+4	1.494E+5
4.639E+4	9.193E+5	6.752E+4	1.457E+6	4.669E+4	1.009E+5	6.821E+4	1.226E+6	5.446E+4	2.327E+5	4.639E+4	9.758E+4
4.613E+4	8.787E+5	6.631E+4	1.403E+6	4.632E+4	5.181E+4	6.783E+4	1.384E+6	5.449E+4	8.202E+4	4.692E+4	6.603E+4
4.613E+4	8.534E+5	6.559E+4	1.491E+6	4.594E+4	3.250E+4	6.727E+4	1.407E+6	5.339E+4	4.150E+4	4.693E+4	1.735E+4
4.613E+4	7.477E+5	6.535E+4	1.487E+6	4.556E+4	1.449E+5	6.653E+4	1.357E+6	5.293E+4	9.653E+4	4.653E+4	1.243E+3
4.608E+4	6.144E+5	6.441E+4	1.450E+6	4.518E+4	2.055E+5	6.618E+4	1.211E+6	5.200E+4	1.947E+5	4.495E+4	1.090E+4
4.593E+4	3.093E+5	6.406E+4	1.323E+6	4.482E+4	2.633E+5	6.598E+4	1.162E+6	5.185E+4	1.844E+5	4.462E+4	1.082E+4
4.593E+4	2.217E+5	6.343E+4	1.267E+6	4.444E+4	1.402E+5	6.564E+4	1.255E+6	5.222E+4	2.351E+5		
4.598E+4	1.814E+5	6.275E+4	1.209E+6	4.406E+4	7.838E+4	6.523E+4	1.035E+6	5.318E+4	3.009E+5	DATA SET 16	
4.569E+4	9.471E+4	6.234E+4	1.115E+6	4.369E+4	1.762E+4	6.468E+4	9.574E+5	4.329E+4	2.259E+5	T = 299.0	
4.555E+4	4.974E+4	6.212E+4	1.023E+6			6.449E+4	9.093E+5	4.946E+4	2.596E+5		
4.531E+4	3.359E+4	6.103E+4	8.467E+5	DATA SET 15		6.412E+4	9.492E+5	4.831E+4	4.577E+5	5.000E+0	6.472E-1
4.500E+4	1.795E+4	6.123E+4	6.939E+5	T = 25.0		6.374E+4	1.077E+6	4.830E+4	8.265E+5		
4.484E+4	2.530E+4	6.132E+4	5.423E+5			6.350E+4	1.141E+6	4.829E+4	1.098E+6		
4.444E+4	1.733E+4	6.054E+4	5.181E+5	9.186E+4	7.017E+5	6.319E+4	1.201E+6	4.810E+4	1.244E+6		
4.427E+4	2.653E+4	6.017E+4	4.317E+5	8.963E+4	7.456E+5	6.318E+4	1.221E+6	4.809E+4	1.379E+6		
4.320E+4	9.771E+3	6.012E+4	3.902E+5	8.777E+4	7.599E+5	6.281E+4	1.214E+6	4.810E+4	1.261E+6		
4.154E+4	9.929E+3	5.942E+4	4.256E+5	8.683E+4	7.507E+5	6.231E+4	1.134E+6	4.792E+4	1.022E+6		
4.116E+4	3.023E+3	5.823E+4	4.769E+5	8.553E+4	7.094E+5	6.203E+4	1.146E+6	4.793E+4	8.221E+5		
		5.814E+4	5.549E+5	8.442E+4	6.110E+5	6.226E+4	9.208E+5	4.794E+4	6.045E+5		
DATA SET 14		5.752E+4	6.679E+5	8.330E+4	5.069E+5	6.244E+4	9.236E+5	4.794E+4	5.373E+5		
T = 300.0		5.714E+4	8.207E+5	8.236E+4	8.823E+5	6.207E+4	9.611E+5	4.756E+4	5.994E+5		
		5.657E+4	9.285E+5	8.161E+4	1.102E+6	6.189E+4	1.023E+6	4.756E+4	6.657E+5		
9.188E+4	4.157E+5	5.619E+4	9.011E+5	8.106E+4	1.180E+6	6.170E+4	6.692E+5	4.756E+4	5.013E+5		



Figure 42. Absorption Coefficient of Cesium Iodide (Temperature Dependence)

TABLE 65. SUMMARY OF MEASUREMENTS ON THE ABSORPTION COEFFICIENT OF CESIUM IODIDE (Temperature Dependence)

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavenumber Range, cm^{-1}	Temperature Range, K	Specifications and Remarks
1	156	Dianov, E.M.	1967	T	20.41	78-292	Single crystal; plane-parallel plate or disk specimens of 50-80 m diameter and various thicknesses; absorption coefficients determined from the measured transmission in the absence of internal interference; data extracted from a figure.
2	156	Dianov, E.M.	1967	T	13.33	78-292	Same as above except for a longer wavelength.
3	156	Dianov, E.M.	1967	T	99	78-387	Same as above except for a longer wavelength.
4	156	Dianov, E.M.	1967	T	5	78-386	Same as above except for a longer wavelength.

TABLE 66. EXPERIMENTAL DATA ON THE ABSORPTION COEFFICIENT OF CESIUM IODIDE (Temperature Dependence)

[Wavenumber, ν, cm^{-1}; Temperature, T, K; Absorption Coefficient, α, cm^{-1}]

T	α
DATA SET 1	
ν = 2.041E+1	
77.7	2.057E+0
194.7	6.191E+0
292.4	9.745E+0
DATA SET 2	
ν = 1.333E+1	
78.2	1.012E+0
194.7	2.741E+0
292.4	4.399E+0
DATA SET 3	
ν = 9.931E+0	
77.7	9.512E-1
194.7	1.629E+0
292.4	2.534E+0
362.7	2.931E+0
347.3	3.155E+0
DATA SET 4	
ν = 5.000E+0	
77.7	1.349E-1
194.7	3.320E-1
292.4	6.523E-1
362.7	6.924E-1
385.8	8.099E-1



Figure 43. Reflectivity of Cesium Iodide

TABLE 67. SUMMARY OF MEASUREMENTS ON THE REFLECTIVITY OF CESIUM IODIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	154	Bealisto, J.A.B. and Eldridge, J.E.	1973	R	67.2-236.4	300	Single crystal; specimen with surface polished mechanically and then chemically; reflectivity measured; data extracted from a figure.
2	54	McCarthy, D.E.	1963	R	2.10-20.0	298	Synthetic crystal (1 cm thick); polished to flatness of seven fringes on both sides; 30° reflectivity measurements made with aluminum mirror reference standard; data extracted from a curve.
3	84	Mitsuishi, A., Yamada, Y., and Yoshinaga, H.	1962	R	49.7-223	298	Single crystal; near normal reflectivity measured in vacuum with aluminum reference standard; data extracted from a curve.
4	152	Lamatsch, H., Rosse, J., and Saurer, E.	1972	R	0.20-0.23	77	Single crystal; near normal reflectivity observed; data extracted from a curve.
5	26	Vergnat, P., Claudel, J., Hadni, A., and Strimer, P.	1969	R	66-297	290	CsI crystals; reflectivities at 15° incidence obtained; data extracted from a figure.
6	26	Vergnat, P. et al.	1969	R	82-246	80	Same as above.
7	26	Vergnat, P. et al.	1969	R	72-254	4.2	Same as above.

TABLE 68. IX EXPERIMENTAL DATA ON THE REFLECTIVITY OF CESIUM IODIDE

[Wavelength, λ, μm; Temperature, T, K; Reflectivity, ρ]

λ	ρ
DATA SET 1	
T = 300.0	
87.2	0.242
70.5	0.232
8[illegible].9	0.322
95.0	0.[illegible]
91.8	0.[illegible]
96.3	0.[illegible]
99.0	0.315
101.0	0.323
103.3	0.[illegible]
106.0	0.[illegible]
110.1	0.[illegible]
112.7	0.340
115.7	0.371
118.5	0.325
122.1	0.454
126.7	0.577
130.3	0.791
133.5	0.922
142.0	0.930
146.3	0.934
152.3	0.953
153.2	0.944
165.1	0.757
167.5	0.613
171.9	0.547
173.5	0.494
175.1	0.429
176.4	0.377
177.0	0.323
2[illegible].5	0.235
235.0	0.255
DATA SET 2	
T = 294.0	
2.16	0.[illegible]
4.0	0.[illegible]
2.1	0.[illegible]
30.0	0.[illegible]

λ	ρ
DATA SET 2 (CONT.)	
34.5	0.092
40.0	0.092
45.2	0.082
47.9	0.061
5[illegible].0	0.027
DATA SET 3	
T = 300.0	
49.7	0.178
96.4	0.126
103.	0.135
107.	0.183
110.0	0.146
115.	0.252
116.	0.293
120.	0.309
122.	0.308
125.	0.506
131.	0.637
134.	0.749
136.	0.793
138.	0.842
140.	0.851
143.	0.90[illegible]
150.	0.944
157.	0.916
160.	0.757
165.	0.676
170.	0.533
173.	0.488
174.	0.438
183.	0.373
200.	0.329
220.	0.297
223.	0.278

λ	ρ
DATA SET 4	
T = 77.0	
0.2009	0.168
0.2012	0.162
0.2021	0.158
0.2030	0.155
0.2137	0.155
0.2045	0.258
0.2049	0.273
0.2050	0.284
0.2052	0.198
0.2054	0.216
0.2056	0.246
0.2057	0.270
0.2059	0.293
0.2063	0.298
0.2060	0.289
0.2070	0.272
0.2074	0.246
0.2074	0.224
0.2076	0.211
0.2077	0.185
0.2079	0.161
0.2085	0.192
0.2085	0.199
0.2086	0.220
0.2088	0.235
0.2088	0.250
0.2094	0.259
0.2094	0.259
0.2090	0.190
0.2093	0.170
0.2103	0.151
0.2107	0.130
0.2120	0.119
0.2118	0.108
0.2121	0.112
0.2127	0.121
0.2130	0.130
0.2134	0.150
0.2136	0.198

λ	ρ
DATA SET 4 (CONT.)	
0.2137	0.245
0.2141	0.235
0.2141	0.265
0.2145	0.306
0.2148	0.321
0.2154	0.339
0.2153	0.321
0.2163	0.346
0.2160	0.276
0.2170	0.244
0.2174	0.2[illegible]
0.2177	0.246
0.2188	0.179
0.2194	0.159
0.2201	0.144
0.2205	0.138
0.2208	0.131
0.2214	0.125
0.2225	0.121
0.2234	0.122
0.2247	0.125
0.2261	0.131
0.2276	0.136
0.2297	0.138
DATA SET 5	
T = 290.0	
66.7	0.036
75.6	0.029
98.3	0.017
99.7	0.016
1[illegible]	0.017
107.5	0.07[illegible]
114.3	0.144
118.9	0.349
123.8	0.418
129.5	0.612
131.7	0.717
137.4	0.753

λ	ρ
DATA SET 5 (CONT.)	
148.0	0.774
157.4	0.721
162.2	0.642
164.4	0.533
173.5	0.417
176.4	0.312
222.4	0.243
297.1	0.211
DATA SET 6	
T = 0[illegible].0	
81.7	0.023
87.5	0.014
96.1	0.003
102.1	0.034
105.5	0.097
106.7	0.19[illegible]
108.1	0.327
110.2	0.420
117.5	0.593
120.7	0.835
127.1	0.929
137.9	0.954
146.0	0.948
150.4	0.924
157.1	0.835
162.6	0.915
179.3	0.347
246.4	0.231
DATA SET 7	
T = 0.2	
72.1	0.0[illegible]
78.3	0.032
85.6	0.023
91.5	0.014
96.6	0.014
101.7	0.030

λ	ρ
DATA SET 7 (CONT.)	
106.3	0.149
109.3	0.291
109.4	0.474
111.0	0.562
1[illegible].9	0.763
129.0	0.954
130.2	0.906
144.0	0.988
151.7	0.927
193.3	0.415
201.0	0.013
270.0	0.007
193.6	0.342
202.2	0.270
293.9	0.241
DATA SET 8	
T = 298.0	
1.0	0.077
4.9	0.084
10.6	0.085
14.5	0.078
20.3	0.079
25.2	0.073
30.1	0.073
33.2	0.060
34.9	0.0[illegible]
40.9	0.054
46.8	0.047
48.9	0.020



Figure 44. Transmission of Cesium Iodide

TABLE 69. SUMMARY OF MEASUREMENTS ON THE TRANSMISSION OF CESIUM IODIDE

Data Set No.	Ref. No.	Author(s)	Year	Method Used	Wavelength Range, μm	Temperature, K	Specifications and Remarks
1	54	McCarthy, D.E.	1963	T	2.00-50.00	298	Synthetic crystal; 1 cm thick; polished both sides; data extracted from a curve.
2	159	Plyler, E.K. and Blaine, L.R.	1960	T	17.2-55.5	298	High purity crystal; obtained from Harshaw Chemical Co.; 5 mm thick; data extracted from a curve.
3	85	McCarthy, D.E.	1967	T	0.203-3.00	298	Single synthetic crystal; 10 mm thick; polished; data extracted from a curve.
4	160	Viehmann, W., Arens, J.F., and Simon, M.	1974	T	0.33-0.67	298	Single crystal; plate specimen of 2.7 cm thick; not encapsulated; transmission measurements performed utilizing a HeNe laser of 1 mW output at 0.633 μm; data extracted from a figure.
5	160	Viehmann, W. et al.	1974	T	0.33-0.67	298	Similar to above except the specimen encapsulated in Si-oil and lucite.
6	160	Viehmann, W. et al.	1974	T	0.33-0.67	298	Similar to above except specimen of 5 cm thick and not encapsulated.
7	160	Viehmann, W. et al.	1974	T	0.33-0.67	298	Similar to above except specimen encapsulated.
8	160	Viehmann, W. et al.	1974	T	0.33-0.67	298	Similar to above except specimen of 2 cm thick and not encapsulated.
9	160	Viehmann, W. et al.	1974	T	0.33-0.67	298	Similar to above except specimen encapsulated.

TABLE 70. EXPERIMENTAL DATA ON THE TRANSMISSION OF CESIUM IODIDE

[Wavelength, λ, μm; Temperature, T, K: Transmission, τ]

λ	τ
DATA SET 1	
T = 298.0	
0.00	0.897
1.01	0.897
19.9	0.897
30.0	0.897
35.3	0.897
42.0	0.872
47.1	0.852
50.0	0.849
DATA SET 2	
T = 298.0	
17.2	0.9[illegible]
25.7	0.9[illegible]
32.9	0.9[illegible]
40.4	0.9[illegible]
41.8	0.8[illegible]
43.2	0.874
44.4	0.852
46.5	0.8[illegible]
48.0	0.770
50.7	0.693
55.5	0.542
DATA SET 3	
T = 298.0	
0.203	0.[illegible]
0.212	0.[illegible]
0.222	0.273
0.245	0.367
0.257	0.4[illegible]
0.325	0.562
0.369	0.624
0.380	0.650
0.425	0.7[illegible]
0.455	0.743
0.554	0.773
0.657	0.8[illegible]

λ	τ
DATA SET 3(CONT.)	
0.824	0.833
1.00	0.851
1.39	0.860
2.00	0.876
3.00	0.879
DATA SET 4	
T = 298.0	
0.335	0.1[illegible]6
0.340	0.3[illegible]8
0.354	0.384
0.369	0.437
0.390	0.477
0.420	0.520
0.433	0.554
0.5[illegible]	0.6[illegible]
0.57[illegible]	0.627
0.6[illegible]	0.649
0.6[illegible]	0.660
DATA SET 5	
T = 298.0	
0.340	0.0[illegible]6
0.353	0.188
0.355	0.362
0.357	0.495
0.35[illegible]	0.633
0.365	0.678
0.373	0.712
0.387	0.747
0.4[illegible]	0.766
0.452	0.787
0.4[illegible]	0.8[illegible]
0.525	0.809
0.559	0.826
0.602	0.828
0.654	0.834

λ	τ
DATA SET 6	
T = 298.0	
0.332	0.059
0.339	0.114
0.342	0.229
0.346	0.345
0.352	0.434
0.355	0.425
0.369	0.454
0.389	0.470
0.408	0.481
0.428	0.495
0.445	0.513
0.465	0.535
0.504	0.570
0.551	0.599
0.585	0.613
0.610	0.618
0.636	0.626
0.645	0.632
DATA SET 7	
T = 298.0	
0.364	0.051
0.367	0.170
0.372	0.298
0.375	0.433
0.379	0.523
0.383	0.574
0.393	0.603
0.409	0.624
0.434	0.648
0.462	0.678
0.483	0.710
0.531	0.737
0.565	0.748
0.602	0.756
0.629	0.762
0.643	0.765

λ	τ
DATA SET 8	
T = 298.0	
0.305	0.003
0.327	0.032
0.334	0.108
0.338	0.172
0.339	0.214
0.341	0.238
0.345	0.267
0.368	0.293
0.388	0.312
0.408	0.326
0.430	0.343
0.448	0.359
0.469	0.381
0.489	0.394
0.538	0.431
0.594	0.455
0.652	0.476
DATA SET 9	
T = 298.0	
0.340	0.003
0.338	0.303
0.350	0.016
0.361	0.127
0.360	0.257
0.372	0.404
0.373	0.491
0.380	0.529
0.391	0.576
0.418	0.597
0.462	0.626
0.503	0.645
0.536	0.660
0.577	0.676
0.612	0.687
0.633	0.695
0.651	0.703

TABLE 71. PEAK POSITIONS (λ_{max}) IN μm AND HALF-WIDTHS (W) IN eV FOR THE F, R, M, AND N ABSORPTION BANDS IN CESIUM IODIDE*

Interionic dist., d (Å)	Temp.	F band		R_1 band	R_2 band	M band		N bands
		λ_{max}	W	λ_{max}	λ_{max}	λ_{max}	W	λ_{max}
3.95	RT	(0.778)‡						
		0.785	0.36			1.220	0.1	
	NT	0.750	0.23			1.185	0.05	

* Values were taken from Ref. [69].

‡ Values given in parentheses are calculated from the Ivey relations [70].

F band $\lambda_{max} = 703\ d^{1.84}$ for NaCl structure, $\lambda_{max} = 251\ d^{2.5}$ for CsCl structure.

R_1 band $\lambda_{max} = 816\ d^{1.84}$

R_2 band $\lambda_{max} = 884\ d^{1.84}$

M band $\lambda_{max} = 1400\ d^{1.56}$

4. SUMMARY OF RESULTS AND RECOMMENDATIONS

The purpose of the present work is to survey and compile the available information on the absorption coefficient of alkali halides and to generate recommended values on the absorption coefficient in the infrared region. The results of this study are summarized below.

The Urbach rule appears to be generally applicable to the uv absorption edge of alkali halides. Measurements of absorption coefficients as a function of frequency at various temperatures, enable the establishment of the equations for the Urbach tails. These equations are useful in predicting the intrinsic absorption coefficients for these materials. Compared with the experimental results at the tails, this rule provides clues regarding the extent of impurity or defect in the samples. To ascertain if the Urbach rule can be extended into the transparent region requires experimental data on ultrapure samples. The current available data are less than adequate to provide such positive evidence.

In the highly transparent region, absorption coefficients are usually low. Since refractive indices in the transparent region can be measured accurately, the corresponding absorption coefficients can be calculated from the expressions

$$R = \frac{(n-1)^2 + k^2}{(n+1)^2 + k^2}$$

and

$$\alpha = 4\pi k\nu$$

It is clear that α can be determined provided that reliable reflectivity data are available. Such important data are currently missing as reflectivity measurements are concentrated in the fundamental uv absorption band and the reststrahlen region.

Available data in the multiphonon region indicate that the absorption coefficient can be expressed as an exponential function of frequency. Deutsch's results [12] supported the exponential dependence of the absorption coefficient on frequency for LiF, NaCl, KCl, and KBr; however, due to inadequate data, such a relation could not be developed for NaF and KI. However, we have found in this study that such an exponential relation can also be formulated for NaF and KI based on the following findings:

1. Listed below are the constant, ν_o, in Eqs. (23), (29), (32), and (35) for LiF, NaCl, KCl, and KBr, respectively, and their corresponding molecular weights, M, including those of NaF, KI, and CsI. In addition, the corresponding 1/M are also given.

	LiF	NaF	NaCl	KCl	KBr	KI	CsI
ν_o, cm^{-1}	153.2		56.0	50.8	39.1		
M, g $mole^{-1}$	26	42	58.5	74.5	120	166	260
1/M, $mole^{-1}g$	0.0385	0.0238	0.0171	0.0134	0.0083	0.0060	0.0038

A plot of log ν_o versus 1/M for LiF, NaCl, KCl, and KBr as shown in Figure 45 reveals that these four points can be approximated by a straight line. Based on this plot, the predicted values of ν_o for NaF, KI, and CsI are, respectively, 78.5 cm^{-1}, 35 cm^{-1}, and 32 cm^{-1}.

2. In the case of NaF, available data by Hohls [29] and Klier [41] (see Fig. 11) suggested a much higher value for ν_o. However, the data set obtained by McNelly and Pohl [80], read off from Figure 12, for a temperature of 300 K gave a value of 79.5 cm^{-1} for ν_o, closely in accordance with the predicted value 78.5 cm^{-1}. Careful review of their reports indicated that McNelly and Pohl used samples of extreme purity and they found no indications of any extrinsic absorption. Based on this evidence and the match of predicted ν_o value, we confidently adopted Eq. (26) to represent the absorption coefficient of pure NaF in the multiphonon region at room temperature.

3. In the case of KI, similar situations were encountered. Available data reported by Harrington et al. [104] were used to test the prediction. Indeed, a value of 35.1 cm^{-1} for ν_o was found and Eq. (38) was consequently adopted. In the case of CsI, unfortunately the current state of available data is inadequate either to substantiate the prediction or to define a unique value for ν_o.

With two additional points, those of NaF and KI, in Figure 45, there is little doubt to believe that log ν_o is proportional to 1/M in the form of equation

$$\nu_o = Ae^{B/M}$$

where A and B are constants. No attempt was made to assign numerical values to these constants until the physical meaning of this equation is understood.



Figure 45. Semi-log Plot of ν_0 of Alkali Halides as a Function of 1/M

A close examination of the absorption spectra in the multiphonon region for LiF, NaCl, KCl, and KBr (shown in Figs. 5, 17, 23, and 29), one will appreciate the strong possibilities that analytical expressions similar to those for the Urbach tail region can be formulated for the multiphonon region. Results toward these ends will be presented in the second report of this study on alkali halides.

In the wavelength region of laser interest, absorption coefficients were made available at a few selected wavelengths. Although it appeared that absorption coefficients at some wavelengths, 10.6 μm for example, could be predicted by Eqs. (29), (32), and (35) in the cases of NaCl, KCl, and KBr, experimental data showed considerable discrepancies due to impurities and surface contaminations. Furthermore, determination of extreme low absorption is hampered by the limit of instrument sensitivity, hence the inevitable discrepancies. Many investigators treated the bulk and surface absorption as two separate parts and efforts have been made to identify them separately. As a result, very low bulk absorption coefficients (close to the intrinsic) were reported with surface absorption generally many times higher. In practice, however, the total absorption actually accounts for the objectionable effects at high-power levels. Natural consequences of this are numerous investigations aimed at eliminating or reducing the extrinsic contributions. Growing of crystals with the reactive-atmosphere process and cleaning the surface with various chemical techniques are two popular means that have been employed. To date, only modest success has been achieved.

Assignment of the bulk and surface origins of extrinsic absorption at 9.5 and 3.8 μm has been controversial. Some workers believe that surface contamination is the main cause of excess absorption; others think bulk impurities are the reason. No clear line can be drawn between these two views based on currently available information.

Some materials have relatively high intrinsic absorption at certain laser wavelengths. However, it has been made clear by the advances of laser technology that laser wavelengths are no longer limited to the 2-6 μm region and to 10.6 μm, the so-called chemical and CO_2 laser wavelengths. New developments have shown that laser action can be produced at other wavelengths in the near infrared, visible, near ultraviolet, and ultraviolet regions. Optical materials that are not suitable at certain wavelengths may be found to be important

at other wavelengths. It is clear, therefore, that well planned and systematic experimental investigation of absorption should be carried out, covering wide spectral and temperature ranges for a wide variety of optical materials.

5. REFERENCES

1. National Materials Advisory Board, "High-Power Infrared Laser Windows," National Academy of Sciences-National Academy of Engineering, Washington, DC, Publication NMAB-292, 168 pp. (1972).

2. Gray, D.E. (Editor), American Institute of Physics Handbook, 3rd Ed., McGraw-Hill Book Co., New York, 2342 pp. (1972).

3. Trost, K.F., "Thermal Expansion of Alkali Halides of the Na-Cl Type at High and Low Temperatures," Z. Naturforsch., B18(8), 662-4 (1963).

4. Kirchner, H.P., Scheetz, H.A., Brown, W.R., and Smyth, H.T., "Investigation of Theoretical and Practical Aspects of the Thermal Expansion of Ceramic Materials," Cornell Aeronautical Lab. Rept., 101 pp. (1962). [AD 296 188]

5. Weast, R.C. (Editor), Handbook of Chemistry and Physics, The Chemical Rubber Co., Ohio (1969).

6. Stull, D.R. and Prophet, H., "JANAF Thermochemical Tables," National Standard Reference Data Series-National Bureau of Standards Rept. NSRDS-NBS 37, 1141 pp. (1971).

7. Strehlow, W.H. and Cook, E.L., "Compilation of Energy Band Gaps in Elemental and Binary Compound Semiconductors and Insulators," J. Phys. Chem. Ref. Data, 2(1), 163-99 (1973).

8. Wolfe, W.L., Handbook of Military Infrared Technology, U.S. Government Printing Office, Washington, DC, 906 pp. (1965).

9. Fowles, G.R., Introduction to Modern Optics, Holt, Rinehart and Winston, Inc., New York, 304 pp. (1968).

10. Hodgson, J.N., Optical Absorption and Dispersion in Solids, Chapman and Hall, Ltd., London, 138 pp. (1970).

11. Klein, C.A. and Rudko, R.L., "CO_2 Laser Radiation Absorption in Semi-Insulating Gallium Arsenide," Appl. Phys. Lett., 13, 129 (1968).

12. Deutsch, T.F., "Absorption Coefficient of Infrared Laser Window Materials," J. Phys. Chem. Solids, 34, 2091-104 (1973).

13. Lowndes, R.P. and Martin, D.H., "Dielectric Dispersion and the Structures of Ionic Lattices," Proc. Roy. Soc. London, A308, 473-96 (1969).

PRECEDING PAGE B

14. Lowndes, R.P., "The Temperature Dependence of the Static Dielectric Constant of Alkali, Silver, and Thallium Halides," Phys. Lett., 21(1), 26-7 (1966).

15. Andeen, C., Fontanella, J., and Donald, S., "Low-Frequency Dielectric Constant of LiF, NaF, NaCl, NaBr, KCl, and KBr by the Method of Substitution," Phys. Rev., B2(12), 5068-73 (1970).

16. Kartheuser, E., "Dielectric Properties of Polar Crystals," in Polarons in Ionic Crystals and Polar Semiconductors, (Devreese, J.T., Ed.), North-Holland/American Elsevier, 717-33 (1972).

17. Young, K.F. and Frederikse, H.P.R., "Compilation of the Static Dielectric Constant of Inorganic Solids," J. Phys. Chem. Ref. Data, 2(2), 313-409 (1973).

18. Hodby, J.W., Borders, J.A., and Brown, F.C., "Cyclotron Resonance of the Polaron in KCl, KBr, KI, RbCl, AgCl, AgBr, and TlCl," Phys. Rev. Lett., 19(17), 952-5 (1967).

19. Hilsch, R. and Pohl, R.W., "Dispersion Frequencies of Alkali Halides in the Schumann Region," Z. Phys., 59, 812-9 (1930).

20. Schneider, E.G. and O'Bryan, H.M., "The Absorption of Ionic Crystals in the Ultraviolet," Phys. Rev., 51(5), 293-8 (1937).

21. Ramachandran, G.N., "Thermo-optic Behavior of Solids, V. Alkali Halides," Proc. Indian Acad. Sci., 25A, 481-97 (1947).

22. Jasperse, J.R., Kahan, A., and Plendl, J.N., "Temperature Dependence of Infrared Dispersion in Ionic Crystals LiF and MgO," Phys. Rev., 146(2), 526-42 (1966).

23. Genzel, L., Happ, H., and Weber, R., "Dispersion Measurement on NaCl, KCl, and KBr Between 0.3 and 3 mm Wavelength," Z. Phys., 154, 13-8 (1959).

24. Handi, A., Claudel, J., Chanal, D., Strimer, P., and Vergnat, P., "Optical Constants of Potassium Bromide in the Far Infrared," Phys. Rev., 163(3), 836-43 (1967).

25. Handi, A., Claudel, J., Morlot, G., and Strimer, P., "Transmission and Reflection Spectra of Pure and Doped Potassium Iodide at Low Temperatures," Appl. Opt., 7(1), 161-5 (1968).

26. Vergnat, P., Claudel, J., Handi, A., Strimer, P., and Vermillard, F., "Far Infrared Optical Constants of Cesium Halides at Low Temperatures," J. Phys., 30(8-9), 723-35 (1969).

27. Gyulai, Z., "The Dispersion of Some Alkali Halides in Ultraviolet Region," Z. Phys., 46, 80-7 (1927).

28. Schneider, E.G., "Optical Properties of Lithium Fluoride in the Extreme Ultraviolet," Phys. Rev., 49(9), 341-5 (1936).

29. Hohls, H.W., "Dispersion and Absorption of Lithium Fluoride and Sodium Fluoride in the Infrared," Ann. Phys., 29, 433-48 (1937).

30. Harting, H., "The Optical Aspect of Some Crystals and Their Representation by the Hartmann Equation," Z. Instrum., 63, 125-31 (1943).

31. Durie, D.S.L., "The Refractive Indices of Lithium Fluoride," J. Opt. Soc. Amer., 40(12), 878-9 (1950).

32. Tilton, W.L. and Plyler, E.K., "Refractivity of Lithium Fluoride With Application to the Calibration of Infrared Spectrometers," J. Res. Natl. Bur. Stand., 47(1), 25-30 (1951).

33. Li, H.H., "Refractive Index of Alkali Halides and Its Wavelength and Temperature Derivatives," J. Phys. Chem. Ref. Data, 5(2), 329-528 (1976).

34. Kato, R., "Optical Properties of LiF in the Extreme Ultraviolet," J. Phys. Soc. Jpn., 16, 2525-33 (1961).

35. Roessler, D.M. and Walker, W.C., "Optical Constants of Magnesium Oxide and Lithium Fluoride in the Far Ultraviolet," J. Opt. Soc. Am., 57, 835-6 (1967).

36. Görlich, H., Karras, H., and Kötitz, G., "Studies on the Coloration of LiF Crystals," Phys. Status Solidi, 3, 1629-45 (1963).

37. Tomiki, T. and Miyata, T., "Optical Studies of Alkali Fluorides and Alkaline Earth Fluorides in VUV Region," J. Phys. Soc. Jpn., 27(3), 658-78 (1969).

38. Barker, A.J., "The Effect of Melting on the Multiphonon Infrared Absorption Spectra of KBr, NaCl and LiF," J. Phys. C: Solid State Phys., 5, 2276-82 (1972).

39. Mead, D.G., "Comparison of the Optical an Dielectric Properties of Crystalline and Molten Lithium Fluoride," J. Phys. C: Solid State Phys., 7, 445-53 (1974).

40. Kachare, A., Soriaga, M.P., and Andermann, G., "Kramers-Kronig Dispersion Analysis of LiF Reflectance Data Obtained at Ambient and Low Temperatures," J. Opt. Soc. Am., 64(11), 1450-5 (1974).

41. Klier, M., "The Temperature Coefficient of Optical Constants of Lithium Fluoride and Sodium Fluoride in Infrared," Z. Phys., 150, 49-63 (1958).

42. Owens, J.C., "Anharmonicity and Millimeter-wave Absorption in Alkali-Halide Crystals," Phys. Rev., 181(3), 1228-36 (1969).

43. Stolen, R. and Dransfeld, K., "Far-Infrared Lattice Absorption in Alkali Halide Crystals," Phys. Rev., 139(4A), A1295-303 (1965).

44. Eldridge, J.E., "Measurement and Analysis of the Isotope-Induced One-Phonon Infrared Absorption LiF," Phys. Rev. B, 6(8), 3128-34 (1972).

45. Eldridge, J.E., "Assignments of the Two-Phonon Infrared Absorption Spectrum of LiF," Phys. Rev. B, 6(4), 1510-9 (1972).

46. Heilmann, G., "The Temperature Dependence on the Optical Constants of LiF in the Region of Infrared Characteristic Frequencies," Z. Phys., 152, 368-83 (1958).

47. Genzel, L. and Klier, M., "Spectral Investigations in the Region Around 1 mm Wavelength. III. Dispersion Measurements on LiF," Z. Phys., 144, 25-30 (1956).

48. Fröhlich, D., "The Optical Constants of LiF in the Region of Infrared Characteristic Frequencies," Z. Phys., 169, 114-25 (1962).

49. Fröhlich, D., "Temperature Dependence of the Optical Constants of LiF in Region of Infrared Characteristic Frequencies," Z. Phys., 177, 126-37 (1964).

50. Seger, G. and Genzel, L., "Absorption Measurement on LiF Between Wavelength Region 0.3 and 0.9 mm," Z. Phys., 169, 66-71 (1962).

51. Gottlieb, M., "Optical Properties of Lithium Fluoride in the Infrared," J. Opt. Soc. Am., 50(4), 343-9 (1960).

52. Johnson, B.K., "Reflecting Power Measurements in the Spectral Region 2000 Å to 1300 Å," Proc. Phys. Soc. London, 53, 258-64 (1941).

53. Sulzbach, F. and Turner, A.F., "Infrared Coating Studies," Bausch and Lomb, Inc., Rochester, NY, 1-33 (1966). [AD 635 670]

54. McCarthy, D.E., "The Reflection and Transmission of Infrared Materials: I. Spectra from 2-50 Microns," Appl. Opt., 2(6), 591-603 (1963).

55. Stephan, G., Lemonnier, J.C., and Robin, S., "Optical Properties of Insulators in the Extreme Ultraviolet," J. Opt. Soc. Am., 57(4), 486-92 (1967).

56. Martin, T.P. and Turner, A.F., "Effect of Crystallite Size on the Infrared Dispersion of Lithium Fluoride Films," J. Appl. Phys., 37(4), 1749-54 (1966).

57. Rao, K.K., Moravec, T.J., Rife, J.C., and Dexter, R.N., "Vacuum Ultraviolet Reflectivities of LiF, NaF, and KF," Phys. Rev. B, 12(12), 5937-48 (1975).

58. Schaefer, J.C. and Hill, E.R., "Optical Coatings for CdS Photovoltaic Film Cells," NASA Rept. NASA CR 54965 (1965).

59. Gottlieb, M., "Reflectivity of Li-6F and Li-7F," J. Opt. Soc. Am., 50, 350-1 (1960).

60. Turner, A.F., Chang, L., and Martin, T.R., "Enhanced Reflectance of Reststrahlen Reflection Filters," Appl. Opt., 4(8), 927-33 (1965).

61. Nakagawa, I., "Far-Infrared Reflection Spectra, Optical and Dielectric Constants, and Lattice Vibrations of Some Fluoride Crystals," Bull. Chem. Soc. Jpn., 44, 3014-20 (1971).

62. Davis, R.J., "Factors Affecting the Transmittance of Lithium Fluoride and Barium Fluoride in the Vacuum Ultraviolet," J. Opt. Soc. Am., 56(6), 837-9 (1966).

63. Jones, D.A., Jones, R.V., and Stevenson, R.W., "Infrared Transmission Limits of Single Crystals of Some Fluorides," Proc. Phys. Soc. London, B65, 906-7 (1952).

64. Laufer, A.H., Pirog, J.A., and McNesby, J.R., "Effect of Temperature on the Vacuum Ultraviolet Transmittance of Lithium Fluoride, Calcium Fluoride, Barium Fluoride and Sapphire," J. Opt. Soc. Am., 55(1), 64-6 (1965).

65. Heath, D.F. and Sacher, P.A., "Effects of a Simulated High-Energy Space Environment on the Ultraviolet Transmittance of Optical Material Between 1050 A and 3000 A," Appl. Opt., 5(6), 937-43 (1966).

66. McCubbin, T.K. and Sinton, W.M., "Recent Investigations in the Far Infrared," J. Opt. Soc. Am., 40(8), 537-9 (1950).

67. Bolot, G., "Ultraviolet Windows and Filters for the Spectral Region Between 1000 A and 3000 A," NASA Rept. ESRO-SM-6, 14 pp., 1965.

68. Linsteadt, G., "Infrared Transmittance of Optical Materials at Low Temperatures," Appl. Opt., 3(12), 1453-6 (1964).

69. Compton, W.D. and Rabin, H., "F-Aggregate Centers in Alkali Halide Crystals," Solid State Phys., 16, 121-226 (1964).

70. Ivey, H.F., "Spectral Location of the Absorption Due to Color Centers in Alkali Halide Crystals," Phys. Rev., 72, 341-3 (1947).

71. Sano, R., "Optical Properties of NaF Single Crystals in VUV Region," J. Phys. Soc. Jpn., 27(3), 695-705 (1969).

72. Kublitzky, A., "Some Optical Constants of Alkali Halide Crystals," Ann. Phys., 5, 20, 793-808 (1934).

73. Spangenberg, K., "Density and Refraction of Alkali Halides," Z. Kristallogr., 57, 494-534 (1923).

74. Randall, C.M., "Interferometric Measurements of the Far-Infrared Refractive Index of NaF at Low Temperature," Aspen International Conference on Fourier Spectroscopy (1970), 371-6 (1971).

75. Zarzyski, J. and Naudin, F., "Index of Refraction and Refractivity of Molten Salts," C. R. Hebd. Seances Acad. Sci., 256, 1282-5 (1963).

76. Földvari, I., Veszka, R., and Raksanyi, K., "Optical Absorption of NaF Single Crystals in the VUV Region," Phys. Status Solidi, 26A, K83-5 (1974).

77. Tomiki, T., Miyata, T., and Tsukamoto, H., "The Urbach Rule for the Sodium- and Potassium-Halides," Z. Naturforsch., 29A, 145-57 (1974).

78. Harrington, J.A. and Hass, M., "Temperature Dependence of Multiphonon Absorption," Phys. Rev. Lett., 31(11), 710-4 (1973).

79. Pohl, D.W. and Meier, P.F., "Multiphonon Absorption in NaF," Phys. Rev. Lett., 32(2), 58-61 (1974).

80. McNelly, T.F. and Pohl, D.W., "Multiphonon Optical Spectrum of NaF," Phys. Rev. Lett., 32(23), 1305-8 (1974).

81. Beck, H. and Pohl, D.W., "Multiphonon Absorption in Alkali Halides," in Proceedings of the 2nd International Conference on Phonon Scattering Solids, 361-3 (1976).

82. Roessler, D.M. and Walker, W.C., "Electronic Spectrum of Crystalline Lithium Fluoride," J. Phys. Chem. Solids, 28, 1507-15 (1967).

83. Chang, I.F. and Miyata, S.S., "Temperature Dependence of Long-Wavelength Optic Phonons of NaF Single Crystals," Phys. Rev. B, 5(10), 4094-101 (1972).

84. Mitsuishi, A., Yamada, Y., and Yoshinaga, H., "Reflection Measurements on Reststrahlen Crystals in the Far-Infrared Region," J. Opt. Soc. Am., 52, 14-6 (1962).

85. McCarthy, D.E., "Transmittance of Optical Materials from 0.17 μm to 3.0 μm," Appl. Opt., 6(11), 1896-8 (1967).

86. Stefan, J.M., "The Influence of Heat on the Light Refraction of Solids," Sitzungsber. Akad. Wiss. Wien, 2, 63, 223-45 (1871).

87. Martens, F.F., "The Dispersion of Ultraviolet Radiation," Ann. Phys., 6, 603-40 (1901).

88. Paschen, F., "The Dispersion of Rocksalt and Sylvite in Infrared," Ann. Phys., 26, 120-38 (1908).

89. Langley, S.P., "The Dispersion of Rock Salt and Fluorite," Ann. Astrophys. Obs. Smithsonian Inst., 1, 219-37 (1900).

90. Kellner, L., "Investigations in the Spectral Region Between 20 and 40 Microns," Z. Phys., 56, 215-34 (1929).

91. Roessler, D.M. and Walker, W.C., "Optical Constants of Sodium Chloride and Potassium Chloride in the Far Ultraviolet," J. Opt. Soc. Am., 58, 279-81 (1968).

92. Miyata, T. and Tomiki, T., "Optical Studies of NaCl Single Crystals in 10 eV Region. II. The Spectra of Conductivity at Low Temperatures, Absorption Constant and Energy Loss," J. Phys. Soc. Jpn., 24(6), 1286-302 (1968).

93. Kobayashi, K. and Tomiki, T., "Temperature Dependences of the Fundamental Absorption Tail of KCl and the Absorption Due to Bromines in KCl," J. Phys. Soc. Jpn., 16(7), 1417 (1961).

94. Miyata, T. and Tomiki, T., "The Urbach Tails and Reflection Spectra of NaCl Single Crystals," J. Phys. Soc. Jpn., 22(1), 209-18 (1967).

95. Califano, S. and Czerny, M., "Absorption of NaCl and KBr in Short Infrared Wavelength Region," Z. Phys., 150, 1-3 (1958).

96. Horrigan, F.A. and Rudko, R., "Materials for High-Power CO_2 Lasers," Final Technical Report, Contract No. DAAH01-69-0038, Raytheon Research Division, Waltham, Mass. (Internal Number S-1170) (1969).

97. Hass, M., Davison, J.W., Rosenstock, H.B., and Babiskin, J., "Measurement of Very Low Absorption Coefficients by Laser Calorimetry," Appl. Opt., 14(5), 1128-30 (1975).

98. Allen, S.D. and Harrington, J.A., "Optical Absorption in KCl and NaCl at Infrared Laser Wavelengths," Appl. Opt., 17(11), 1679-80 (1978).

99. Rosenstock, H.B., Gregory, D.A., and Harrington, J.A., "Infrared Bulk and Surface Absorption by Nearly Transparent Crystals," Appl. Opt., 15(9), 2075-9 (1976).

100. Rowe, J.M. and Harrington, J.A., "Temperature Dependence of Surface and Bulk Absorption in NaCl and KCl at 10.6 μm," Phys. Rev. B, 14(12), 5442-50 (1976).

101. Czerny, M., "Measurements on the Refractive Index of NaCl in the Infrared to Prove the Dispersion Theory," Z. Phys., 65, 600-31 (1930).

102. Cartwright, C.H. and Czerny, M., "Dispersion Measurements on NaCl and KCl in the Far Infrared Region. II.," Z. Phys., 90, 457-67 (1934).

103. Ikezawa, M. and Nasu, K., "Isotope-Induced Far-Infrared Absorption in NaCl and KCl Crystals," J. Phys. Soc. Jpn., 34(6), 1563-6 (1973).

104. Harrington, J.A., Duthler, C.J., Patten, F.W., and Hass, M., "Multiphonon Absorption of Alkali Halides and Quasiselection Rules," Solid State Commun., 18, 1043-6 (1976).

105. Geick, R., "Dispersion of NaCl in the Region of Infrared Characteristic Frequencies," Z. Phys., 166, 122-47 (1962).

106. Cartwright, C.H. and Czerny, M., "Dispersion Measurements on NaCl in the Far Infrared," Z. Phys., 85, 269-77 (1933).

107. Dötsch, H. and Happ, H., "Temperature Dependence of Absorption of NaCl Between 1 and 3 mm Wavelength Range," Z. Phys., 177, 360-8 (1964).

108. Dianov, E.M. and Irisova, N.A., "Determination of the Absorption Coefficient of Solids in the Short-Wave Region of the Millimeter Band," J. Appl. Spectrosc., 5(2), 187-9 (1966).

109. Barnes, R.B. and Czerny, M., "Measurements on NaCl and KCl in the Spectral Region of Their Infrared Natural Frequencies," Z. Phys., 72, 447-61 (1931).

110. Baldini, G. and Bosacchi, B., "Optical Properties of Alkali-Halide Crystals," Phys. Rev., 166(3), 863-70 (1968).

111. McGill, T.C. and Winston, H.V., "Temperature Dependence of Multiphonon Absorption in Ionic Insulators," Solid State Commun., 13, 1459 (1973).

112. Rubens, H., "The Ketteler-Helmholtz Dispersion Formula," Wied. Ann., 54, 476-85 (1895).

113. Tomiki, T., "Optical Constants and Exciton States in KCl Single Crystals. I. The Low Temperature Properties," J. Phys. Soc. Jpn., 22(2), 463-87 (1967).

114. Tomiki, T., "Optical Constants and Exciton States in KCl Single Crystals. II. The Spectra of Reflectivity and Absorption Constant," J. Phys. Soc. Jpn., 23(6), 1280-96 (1967).

115. Shrader, E.F., "Chemically Strengthened Polycrystalline Potassium Chloride for High-Power, IR Laser Windows," U.S. Air Force Rept. AFML-TR-74-165, 79 pp. (1974).

116. Hass, M., Davison, J.W., Klein, P.H., and Boyer, L.L., "Infrared Absorption in Low-Loss KCl Single Crystals Near 10.6 μm," J. Appl. Phys., 45(9), 3959-63 (1974).

117. Boyer, L.L., Harrington, J.A., Hass, M., and Rosenstock, H.B., "Multiphonon Absorption in Ionic Crystals," Phys. Rev. B, 11(4), 1665-80 (1975).

118. Deutsch, T.F., "Laser Window Materials - An Overview," J. Elec. Materials, 4(4), 663-719 (1975).

119. Hass, M., Harrington, J.A., Gregory, D.A., and Davisson, J.W., "Infrared Absorption Limits of HF and DF Laser Windows," Appl. Phys. Lett., 28(10), 610-1 (1976).

120. Klein, P.H., "Compounds Containing Carbon-Oxygen and Hydroxyl Linkages as Limiting Contaminants in HF and DF Laser Window Materials," in Proceedings of the Infrared Laser Window Materials Meeting, 117-24 (1976).

121. Rowe, J.M. and Harrington, J.A., "Extrinsic Absorption in KCl and KBr at CO_2 Laser Frequencies," J. Appl. Phys., 47(11), 4926-8 (1976).

122. Antinori, M., Balzarotti, A., and Piacentini, M., "High-Resolution Reflection Spectra of Alkali Halides in the Far Ultraviolet," Phys. Rev. B, 7(4), 1541-9 (1973).

123. Blechschmidt, D., Klucker, R., and Skibowski, M., "Dielectric Properties of KCl, KBr, and KI Single Crystals in the Extreme Ultraviolet Up to 35 eV," Phys. Status Solidi, 36, 625-34 (1969).

124. Deutsch, T.F., "The 10.6 μm Absorption of KCl," Appl. Phys. Lett., 25(2), 109-12 (1974).

125. Tomiki, T., "Absorption Edges of KCl Single Crystals," J. Phys. Soc. Jpn., 21, 403-4 (1966).

126. Philipp, H.R. and Ehrenreich, H., "Intrinsic Optical Properties of Alkali Halides," Phys. Rev., 131(5), 2016-22 (1963).

127. Kobayashi, K. and Tomiki, T., "Studies on the Preparation of Pure Alkali Chlorides," J. Phys. Soc. Jpn., 15(11), 1982-90 (1960).

128. Johnson, K.W. and Bell, E.E., "Far-Infrared Optical Properties of KCl and KBr," Phys. Rev., 187(3), 1044-52 (1969).

129. Mentzel, A., "Investigation of Absorption of KCl and KBr on the Short Wavelength Side of Infrared Characteristic Vibration," Z. Phys., 88, 178-96 (1934).

130. Spindler, R.J. and Rodney, W.S., "Refractivity of Potassium Bromide for Visible Wavelengths," J. Res. Natl. Bur. Stand., 49(4), 253-62 (1952).

131. Stephens, R.E., Plyler, E.K., Rodney, W.S., and Spindler, R.J., "Refractive Index of Potassium Bromide for Infrared Radiant Energy," J. Opt. Soc. Am., 43(2), 110-2 (1953).

132. Forrest, J.W., "Refractive Index Values for Potassium Bromide," J. Opt. Soc. Am., 32, 382 (1942).

133. Gundelach, E., "The Dispersion of KBr Crystal in the Infrared," Z. Phys., 66, 775-83 (1930).

134. Vishnevskii, V.N., Kulik, L.N., and Romanyuk, N.A., "On the Refractive Properties of Alkali Halide Single Crystals in the Vacuum Ultraviolet Region," Opt. Spectros. (USSR), 22(4), 317-8 (1967).

135. Martienssen, W., "The Exciton Band of Alkali Halide Crystals," J. Phys. Chem. Solids, 2, 257-67 (1957).

136. Klein, P.H., Davison, J.W., and Harrington, J.A., "Potassium Bromide for Infrared Laser Windows: Crystal Growth, Chemical Polishing, and Optical Absorption," Mater. Res. Bull., 11, 1335-42 (1976).

137. Bauer, G., "Absolute Values of the Optical Absorption Constants of Alkali-Halide Crystals in the Region of Their Ultraviolet Characteristic Frequencies," Ann. Phys., 5, 19, 434-64 (1934).

138. Petroff, Y., Pinchaux, R., Chekroun, C., Balkanski, M., and Kamimura, H., "Excitonic Structure of Alkali Halides," Phys. Rev. Lett., 27(20), 1377-80 (1971).

139. Korth, K., "Dispersion Measurements on Potassium Bromide and Potassium Iodide in the Infrared Region," Z. Phys., 84, 677-85 (1933).

140. Sprockhoff, M., "Contributions to the Relationships Between the Crystal and Its Chemical Stability," Neues Jahrb. Mineral., Geol. Palaeont., Beilage, 18, 117-54 (1904).

141. Topsoe, H. and Christiansen, C., "Optical Researches on Some Series of Isomorphous Substances," Ann. Chem., Phys., 1, 5-99 (1874).

142. Eldridge, J.E. and Kembry, K.A., "Further Measurements and Calculations of the Far-Infrared Anharmonic Optical Properties of KI Between 12 and 300 K," Phys. Rev. B, 8(2), 746-55 (1973).

143. Berg, J.I. and Bell, E.E., "Far-Infrared Optical Constants of KI," Phys. Rev. B, 4(10), 3572-80 (1971).

144. Haupt, U., "Temperature Dependence and Shape of Long Wavelength Side of Exciton Band in KI Crystal," Z. Phys., 157, 232-46 (1959).

145. Delbecq, C.J. and Yuster, P.H., "Photon-Induced Diffusion in Thin Films and Single Crystals of Potassium Iodide," J. Chem. Phys., 22(5), 921-5 (1954).

146. Baldini, G., Bosacchi, A., and Bosacchi, B., "Exciton-Phonon Interaction in Alkali Halides," Phys. Rev. Lett., 23(15), 846-8 (1969).

147. Roessler, D.M. and Walker, W.C., "Exciton Structure in the Ultraviolet Spectra of KI and RbI," J. Opt. Soc. Am., 57(5), 677-82 (1967).

148. Weeks, R.F., "Simple Wide Range Specular Reflectometer," J. Opt. Soc. Am., 48(11), 775-7 (1958).

149. Kato, R. and Watanabe, M., "Optical Study on Alkali Halide Films in the Ultraviolet," J. Appl. Phys. Jpn., 7(1), 21-6 (1968).

150. Vishnevskii, V.N., Stefanskii, I.V., Kuzyk, M.P., Kulik, Z.S., and Kulik, L.N., "Influence of Uniaxial Mechanical Deformation on the Optical Properties of Alkali Halide Crystals," Sov. Phys.-Solid State, 15(1), 242-3 (1973).

151. Rodney, W.S., "Optical Properties of Cesium Iodide," J. Opt. Soc. Am., 45(11), 987-92 (1955).

152. Lamatsch, H., Rossel, J., and Saurer, E., "The Optical Constants of CsI in the Excitonic Region," Phys. Status Solidi, B49(1), 311-6 (1972).

153. Philipp, H.R. and Taft, E.A., "Photoelectric Emission from the Valence Band of Cesium Iodide," J. Chem. Phys. Solids, 1, 159-63 (1956).

154. Beairste, J.A.B. and Eldridge, J.E., "Far-Infrared Measurements of the Optical Properties of CsI Between 12 and 300 K, Compared with Calculations Based on Cubic Anharmonicity Only," Can. J. Phys., 51, 2550-63 (1973).

155. Metolidi, E.N., Neklyudov, I.M., and Panova, A.N., "Effect of Plastic Deformation on Optical Absorption of CsI Crystals," Sov. Phys.-Solid State, 16(5), 1008-9 (1974).

156. Dianov, E.M., "Experimental Investigation of the Absorption of CsI and CsBr Single Crystals in the Wavelength Range 0.38-2 mm," Sov. Phys.-Solid State, 9(2), 464-6 (1967).

157. Said, K.I. and Green, G.W., "Optical Properties of Cesium Iodide in the Vacuum Ultraviolet," J. Phys. C: Solid State Phys., 10, 479-88 (1977).

158. McCarthy, D.E., "Transmittance of Six Optical Materials from 0.2 Microns to 3.0 Microns," Appl. Opt., 7(6), 1243 (1968).

159. Plyler, E.K. and Blaine, L.R., "Transmittance of Materials in the Far Infrared," J. Res. Natl. Bur. Stand., C64(1), 55-6 (1960).

160. Viehmann, W., Arens, J.F., and Simon, M., "Optical Transmission Measurements on Monocrystalline and Polycrystalline Cesium Iodide," Nucl. Inst. Methods, 116, 283-95 (1974).

161. Milgram, A. and Givens, M.P., "Extreme Ultraviolet Absorption by Lithium Fluoride," Phys. Rev., 125, 1506 (1962).

162. Vinogradov, A.S., Zimkina, T.M., and Mal'tsev, Yu.F., "Fine Structure of Fluorine K Absorption Spectra in Alkali Halide Crystals," Sov. Phys.-Solid State, 11, 2721 (1970).

163. Brown, F.C., Gähwiller, C., Kunz, A.B., and Lipari, N.O., "Soft X-Ray Spectra of the Lithium Halides and Their Interpretation," Phys. Rev. Lett., 25, 927 (1970).

164. Haensel, R., Kunz, C., Sasaki, T., and Sonntag, B., "Measurement of Photoabsorption of the Sodium Halides Near the Sodium $L_{2,3}$ Edge," Phys. Rev. Lett., 20, 1436 (1968).

165. Watanabe, M., Ejiri, A., Yamashita, H., Saito, H., Sato, S., Shibaguchi, T., and Nishida, H., "Absorption Spectra of Rubidium Halides in the Extreme Ultraviolet," J. Phys. Soc. Jpn., 31, 1085 (1971).

166. Teegarden, K. and Baldini, G., "Optical Absorption Spectra of the Alkali Halides at 10 K," Phys. Rev., 155, 896 (1967).

167. Iguchi, Y., Sagawa, T., Sato, S., Watanabe, M., Yamashita, H., Ejiri, A., Sasanuma, M., Nakai, S., Nakamura, M., Yamaguchi, S., Nakai, Y., and Oshio, T., "Cl-L_{23} Absorption Spectra of Alkali Chlorides Obtained at 80°K With Synchrotron Radiation," Solid State Commun., 6, 575 (1968).

168. Saito, H., Saito, S., Onaka, R., and Ikeo, B., "Extreme Ultraviolet Absorption of Alkali Halides," J. Phys. Soc. Jpn., 24, 1095 (1968).

169. Le Comte, A., Savary, A., Morlais, M., and Robin, S., "Absorption of NaF and NaCl Thin Films in the Region Between 25 and 72 eV," Opt. Commun., 4, 296 (1971).

170. Saito, H., Watanabe, M., Ejiri, A., Sato, S., Yamashita, H., Shibaguchi, T., Nishida, H., and Yamaguchi, S., "Absorption Spectra of KCl and RbCl in the Extreme Ultraviolet Region," Solid State Commun., 8, 1861 (1970).

171. Lukirskii, A.P. and Zimkina, T.M., in Rontgenspectra and Chemical Bindings, Karl-Marx-Univ., Leipzig, 187-93 (1966).

172. Brown, F.C., Gähwiller, C., Fujita, H., Kunz, A.B., Scheifley, W., and Carrera, N., "Extreme-Ultraviolet Spectra of Ionic Crystals," Phys. Rev. B, 2, 2126 (1970).

173. Ejiri, A., Watanabe, M., Saito, H., Yamashita, H., Shibaguchi, T., Nishida, H., and Sato, S., "Absorption Spectra of Potassium and Rubidium Halides in the Extreme Ultraviolet," in Proceedings of the 3rd International Conference on Vacuum Ultraviolet Radiation Physics (Nakai, Y., Ed.) (1971).

174. Cardona, M., Haensel, R., Lynch, D.W., and Sonntag, B., "Optical Properties of the Rubidium and Cesium Halides in the Extreme Ultraviolet," Phys. Rev. B, 2, 1117 (1970).

175. Rubens, H. and Trowbridge, A., "Contribution to the Knowledge on the Refractive Index and Absorption of Infrared Radiation for Rocksalt and Sylvite," Ann. Phys. Chem., 60, 724-39 (1897).

APPENDIX

The figures included in the Appendix are vuv absorption spectra of the seven materials which are presented in this report. For each data set, the purposes of the investigations, where the curve was taken from, differences for different spectral regions are specified. Some researchers were interested in the absolute values of absorption coefficients, some simply wanted to show the spectral structure. As a result, many workers adopted arbitrary (arb) units for the absorption coefficient (α). Since the purpose of including these figures is to provide the readers the supplemental parts of the complete absorption spectra, selected, typical results are plotted in a single scale and the appropriate scaling magnitudes are given in the legend.



Figure A1. Absorption Coefficient of Lithium Fluoride in vuv Region



Figure A2. Absorption Coefficient of Sodium Fluoride in vuv Region



Figure A3. Absorption Coefficient of Sodium Chloride in vuv Region



Figure A4. Absorption Coefficient of Potassium Chloride in vuv Region



Figure A5. Absorption Coefficient of Potassium Bromide in vuv Region



Figure A6. Absorption Coefficient of Potassium Iodide in vuv Region



Figure A7. Absorption Coefficient of Cesium Iodide in vuv Region

END

DATE
FILMED

9 82

DTIC