AD-A140 650 EVALUATION OF MICA SUBSTITUTES FOR USE IN THERMAL BATTERIES(U) SAFT AMERICA INC COCKEYSVILLE MD ADVANCED BATTERY SYSTEMS DIV S DALLEK ET AL. 01 SEP 83 1/1

UNCLASSIFIED NSWC-TR-83-410 N60921-82-M-2277 F/G 10/3 NL





MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

NSWC TR 83-410

AD-A140 650

EVALUATION OF MICA SUBSTITUTES FOR USE IN THERMAL BATTERIES

BY S. DALLEK, B. F. LARRICK (NSWC)
D. BRISCOE, G. CHAGNON (SAFT AMERICA INC)

RESEARCH AND TECHNOLOGY DEPARTMENT

1 SEPTEMBER 1983

DTIC
ELECTE
S D

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER NSWC TR 83-410	2. GOVT ACCESSION NO. AD-A140 650	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) EVALUATION OF MICA SUBSTITUTES FOR USE IN THERMAL BATTERIES		5. TYPE OF REPORT & PERIOD COVERED FINAL 6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) S. Dallek, B. F. Larrick (NSWC) and G. Chagnon, D. Briscoe (SAFT INC.)		8. CONTRACT OR GRANT NUMBER(s) N60921-82-M-2277
9. PERFORMING ORGANIZATION NAME AND ADDRESS Naval Surface Weapons Center (Code R33) White Oak Silver Spring, Maryland 20910		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS 62761N; F61545; SF61-545-601; 3R32BH404
11. CONTROLLING OFFICE NAME AND ADDRESS		12. REPORT DATE 1 September 1983 13. NUMBER OF PAGES 38
14. MONITORING AGENCY NAME & ADDRESS(if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED 15a. DECLASSIFICATION/DOWNGRADING SCHEDULE

16. DISTRIBUTION STATEMENT (of this Report)

Approved for public release, distribution unlimited

17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)

18. SUPPLEMENTARY NOTES

19. KEY WORDS (Continue on reverse side if necessary and identify by block number)

Thermal batteries, mica, electrical insulators

20. ABSTRACT (Continue on reverse side if necessary and identify by block number)

The present work was undertaken to identify and support the development of a substitute for the critical and strategic material phlogopite mica used as electrical insulation in thermal batteries. Candidate materials were evaluated by thermogravimetry and by actual configurational tests in batteries.

DD FORM 1 JAN 73 1473 EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-LF-014-6601

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

FOREWORD

This work was undertaken in response to a general need within the thermal battery industry to find a substitute for the critical and strategic material phlogopite mica used as high temperature electrical insulation in thermal batteries. Possible substitute materials were studied by actual configurational tests in batteries and by thermogravimetry (TG).

The support of the Design Options for Substitute Materials Program of NAVSEA is gratefully acknowledged.

Approved by:

J. R. Dixon

JACK R. DIXON, Head
Materials Division

DTIC COPY INSPECTED 2

Accession For
NTIS GRA&I
DTIC TAB
Unannounced
Justification
By
Distribution/
Availability Codes
Dist | Avail and/or Special
A1

CONTENTS

Chapter		Page
1	INTRODUCTION	1
2	EXPERIMENTAL	3
	THERMOGRAVIMETRY (TG)	3
	BATTERY TESTS	3
3	RESULTS AND DISCUSSION	5
4	CONCLUSIONS	7

ILLUSTRATIONS

Figure		Page
1	CONSTRUCTION OF TEST BATTERIES SHOWING POSITION OF THERMOCOUPLES	9
2	TG CURVE OF PHLOGOPITE MICA, 80.31 MG, 100° C/MIN (20°-900°C), 5°C/MIN (900°-1150°C), ISOTHERMAL (1150°C), 50 CC/MIN Ar	10
3	TG CURVE OF MUSCOVITE MICA, 64.77 MG, 20°C/MIN, 50 CC/MIN Ar	10
4	TG CURVE OF KAPTON 300 H, 14.10 MG, 20°C/MIN, 50 CC/MIN Ar	11
5	TG CURVE OF PHLOGOPITE MICA, 80.70 MG, ISOTHERMAL (500°C), 50 CC/MIN He	11
6	TG CURVE OF MUSCOVITE MICA, 68.07 MG, ISOTHERMAL (500°C), 50 CC/MIN He	12
7	TG CURVE OF ESSEX P/N 11827, 77.15 MG, ISOTHERMAL (500°C), 50 CC/MIN He	12
8	TG CURVE OF ESSEX P/N 11054, 75.62 MG, ISOTHERMAL (500°C) 50 CC/MIN He	13
9	TG CURVE OF KAPTON 300 H, 19.98 MG, ISOTHERMAL (500°C) 50 CC/MIN He	13
10	TG CURVE OF KAPTON 500 H, 52.40 MG, ISOTHERMAL (500°C), 50 CC/MIN He	14
11	TG CURVE OF KAPTON 300 V, 33.33 MG, ISOTHERMAL (500°C), 50 CC/MIN He	14
12	TG CURVE OF QUINTERRA T3, 40.44 MG, ISOTHERMAL (500°C), 50 CC/MIN He	15
13	TG CURVE OF QUINORGO 5000, 25.68 MG, ISOTHERMAL (500°C), 50 CC/MIN He	15
14	TG CURVE OF CE QUIN 1, 23.01 MG, ISOTHERMAL (500°C), 50 CC/MIN He	16
15	TG CURVE OF QUIN-T, 8.61 MG, ISOTHERMAL (500°C), 50 CC/MIN He	16
16	TG CURVE OF FUEL CELL PAPER, 15.16 MG, ISOTHERMAL (500°C), 50 CC/MIN He	17
17	TG CURVE OF HAVEG SILTEMP TAPE, 12.23 MG, ISOTHERMAL (500°C), 50 CC/MIN He	17
18	TG CURVE OF SILICONE + VITON #1606, 44.16 MG, ISOTHERMAL (500°C), 50 CC/MIN He	18
19	TG CURVE OF ESSEX P/N 470005, 53.69 MG, ISOTHERMAL (500°C), 50 CC/MIN He	18

ILLUSTRATIONS (Cont.)

Figure		Page
20	TG CURVE OF NOMEX 410, 40.33 MG, ISOTHERMAL (500°C), 50 CC/MIN He	19
21	TG CURVE OF NOMEX 418, 45.24 MG, ISOTHERMAL (500°C), 50 CC/MIN He	19
22	TG CURVE OF ESSEX P/N 470005, 41.92 MG, ISOTHERMAL (500°C), 50 CC/MIN He	20
23	TG CURVE OF ESSEX P/N 11827, 43.92 MG, ISOTHERMAL (500°C), 50 CC/MIN He	20
24	TG CURVE OF ESSEX P/N 11054, 48.38 MG, ISOTHERMAL (500°C), 50 CC/MIN He	21
25	TG CURVE OF KAPTON 300 H 32.46 MG, ISOTHERMAL (500°C), 50 CC/MIN He	21
26	TG CURVE OF KAPTON 500 H, 45.35 MG, ISOTHERMAL (500°C), 50 CC/MIN He	22
27	TG CURVE OF KAPTON 300 V, 35.95 MG, ISOTHERMAL (500°C), 50 CC/MIN He	22
28	TG CURVE OF KAPTON 300 F, 30.30 MG, ISOTHERMAL (500°C), 50 CC/MIN He	23
29	POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH PHLOGOPITE MICA INSULATOR	23
30	POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH KAPTON 300 V INSULATOR	24
31	POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH KAPTON 500 H INSULATOR	24
32	POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH KAPTON 300 H INSULATOR	25
33	POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH MUSCOVITE MICA INSULATOR	25
34	POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH ESSEX P/N 11827 INSULATOR	26
35	POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH ESSEX P/N 470005 INSULATOR	26
36	POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH ESSEX P/N 11054 INSULATOR	27
37	POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH NOMEX 418 INSULATOR	27

TABLES

Table		Page
1	COMPOSITION OF TEST MATERIALS	28
2	THERMOGRAVIMETRY RESULTS	29
3	SUMMARY OF RESULTS AND RECOMMENDATIONS	30

CHAPTER 1

INTRODUCTION

Phlogopite mica is a complex naturally-occurring hydrous aluminum silicate mineral that is used as electrical insulation in thermal batteries. The idealized formula for phlogopite is $K_2Mg_6Al_2Si_6O_{20}(OH)_4$ but several other elements may be incorporated into the structure as isotopic replacements.[1] The United States is almost completely dependent on foreign sources for strategic sheet mica.[2] The Government has thus classified it as a critical and strategic material and must therefore maintain a stockpile for use in emergencies.

The objective of the present work was to perform an experimental evaluation to identify and support the development of a substitute material for phlogopite mica in thermal batteries. Candidate materials must be thin (0.003-0.010 in) and flexible to wrap around the cell stack and must maintain good electrical resistance and thermal stability at thermal battery operating temperatures (500°-$550^{o}C$). Chemically, the material must be resistant to molten salts, strong oxidizing and reducing agents, and should be non-hygroscopic.

Candidate materials were studied by thermogravimetry (TG) to determine the decomposition temperature and mass loss of each sample. The materials were also subjected to actual configurational tests in thermal batteries employing the $LiAl/LiCl\text{-}KCl,SiO_2/FeS_2$ molten salt electrochemical system.

---

[1]Skow, M. L., U. S. Bureau of Mines Information Circular 8125, "Mica, A Materials Survey," (1962).

[2]Petkof, B., U. S. Bureau of Mines Bulletin 630, "Mica" in Mineral Facts and Problems, 1965 edition, p. 583-94.

CHAPTER 2

EXPERIMENTAL

THERMOGRAVIMETRY (TG)

A DuPont 1090 Thermal Analysis System with a 951 Thermogravimetric Analyzer was employed in this study. In preliminary tests to study the decomposition behavior of phlogopite mica and various candidate replacement materials, samples were run in platinum boats at a heating rate of 20°C/min under a flowing atmosphere of dry argon to a maximum temperature of 1150°C. In all subsequent runs, the TG heating program was modified to simulate the actual temperature vs. time profile experienced by internal thermal battery components, i.e., a maximum average temperature of 500°C-550°C for periods up to 30 minutes. The sample was either heated at 100°C/min to about 500°C and then isothermally for about 30 minutes or was inserted into a preheated furnace at 500°C for 30 minutes. The candidate replacement materials for phlogopite mica evaluated in this study are listed in Table 1.

BATTERY TESTS

Batteries were constructed and discharged to compare the electrical properties of the various candidate insulating materials. The electrical noise level and life of the battery were used to evaluate the thermal stability and electrical insulating capability of the materials. In addition, post mortem analyses were performed to assess the degradation of the insulators. The details of construction of a typical battery are shown in Figure 1.

CHAPTER 3

RESULTS AND DISCUSSION

A TG curve of phlogopite mica is shown in Figure 2. The excellent high temperature stability of this material is seen up to about 1000°C, above which it slowly loses water. In Figure 3, a curve of muscovite mica is shown. Although it does not possess the same stability as phlogopite, muscovite does remain stable until about 800°C where it, too, begins to evolve water. A curve of a sample of KAPTON, a DuPont polyimide film, is shown in Figure 4. KAPTON starts decomposing at about 525°C, which is in the temperature range of thermal battery operation.

After these initial TG experiments on phlogopite and muscovite mica and on KAPTON and several other possible substitute materials, the TG heating programs were modified to simulate an actual thermal battery temperature vs. time profile as closely as possible. In Figures 5 through 21, the sample was heated at100°C/min to about 500°C and then isothermally for a total of about 30 minutes. At this high heating rate, the furnace would "overshoot" the 500°C limit, thus heating the sample to about 530°C-550°C. This overshoot could have been eliminated by a simple adjustment of the furnace proportional band control. However, the overshoot was considered a good simulation of a thermal battery temperature profile and was therefore retained as part of the heating program. Instead of programming the TGA to simulate the temperature decrease during an actual discharge as the battery slowly cools, the sample was held isothermally at about 500°C; thus, these samples remained at high temperatures longer than they would in an actual battery. In Figures 22 through 28, some samples were rerun by a slightly different method, whereby they were inserted for 30 minutes into a preheated 500°C furnace to achieve a faster rate of sample temperature increase. For samples run by both heating programs, the results were virtually identical although a slightly greater weight loss usually occurred in the program with the overshoot because of the higher temperature achieved and the slightly longer time at the 500°C temperature during isothermal operation. The solid curve is a plot of sample weight remaining vs. time; the dashed curve is a plot of sample temperature vs. time. The time to reach maximum temperature, the temperature during the isothermal heating mode, and the mass remaining after 30 minutes are printed on the curves. The TG results are summarized in Table 2. Discharge results of batteries constructed with several of the insulating materials are summarized in Figures 29 through 37 wherein battery potential and temperature (TC #1) are plotted versus discharge time. All of the batteries, except for the one with the NOMEX 418 insulator, performed comparably to the phlogopite mica battery, to a 24V cutoff, during this short discharge period.

CHAPTER 4

CONCLUSIONS

Of all the materials tested as possible replacements for phlogopite mica as electrical insulators in thermal batteries, only muscovite mica has comparable high temperature stability and electrical properties. Although its decomposition temperature is about 200°C below that of phlogopite mica (800°C vs 1000°C), this is still much higher than the average temperature inside a thermal battery during normal discharge. The discharge behavior of the batteries constructed with muscovite mica insulation was identical to that of the phlogopite mica batteries.

As seen in the TG curves, the other candidate insulators all begin decomposing at or below thermal battery operating temperatures. Post mortem analyses of these insulators from discharged batteries showed various stages of degradation. However, most of these batteries performed as well as the standard phlogopite mica batteries. Most of the degradation is a consequence of the insulators' contact with the high temperature cell stack for a long period after termination of the discharge as the battery slowly cools. Thus, it appears that several of the insulators could be used in short life thermal batteries (2-3 minutes). For longer life thermal batteries (10-30 minutes), actual configurational tests would be required to assess the insulators' capabilities. A summary of the results and recommendations for the eighteen high-temperature insulating materials included in this study is given in Table 3.

We are presently working on alternative methods to achieve electrical insulation of the cell stack in thermal batteries. One possible method is to use a high temperature inorganic polymer coating on the inside of the can; another is to use an anodized aluminum can, instead of mica, as electrical insulation.



NOTES:

1. FIRST THERMOCOUPLE PLACED BETWEEN THE ANODE AND THE TWO LAYER PELLET OF THE 9TH CELL (FROM TOP OF STACK).
2. SECOND THERMOCOUPLE IS BETWEEN THE MICA AND QUINARGO INSULATION OF THE INNER CASE.
3. THIRD THERMOCOUPLE IS BETWEEN THE FIBERFRAX INSULATION OF THE OUTER CASE AND THE OUTSIDE OF THE INNER CASE.
4. THE FOURTH THERMOCOUPLE IS ON THE OUTSIDE OF THE OUTER CASE.
5. ALL THERMOCOUPLES ARE APPROXIMATELY AT THE SAME LEVEL. (APPROX. MIDWAY DOWN THE STACK)

FIGURE 1. CONSTRUCTION OF TEST BATTERIES SHOWING POSITION OF THERMOCOUPLES



FIGURE 2. TG CURVE OF PHLOGOPITE MICA, 80.31 MG, 100° C/MIN (20°-900°C), 5° C/MIN (900°-1150°C), ISOTHERMAL (1150°C), 50 CC/MIN Ar



FIGURE 3. TG CURVE OF MUSCOVITE MICA, 64.77 MG, 20° C/MIN, 50 CC/MIN Ar



FIGURE 4. TG CURVE OF KAPTON 300 H, 14.10 MG, 20° C/MIN, 50 CC/MIN Ar



FIGURE 5. TG CURVE OF PHLOGOPITE MICA, 80.70 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 6. TG CURVE OF MUSCOVITE MICA, 68.07 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 7. TG CURVE OF ESSEX P/N 11827, 77.15 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 8. TG CURVE OF ESSEX P/N 11054, 75.62 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE [illegible] TG CURVE OF KAPTON 300 H, 19.98 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 10. TG CURVE OF KAPTON 500 H, 52.40 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 11. TG CURVE OF KAPTON 300 V, 33.33 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 12. TG CURVE OF QUINTERRA T3, 40.44 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 13. TG CURVE OF QUINORGO 5000, 25.88 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 14. TG CURVE OF CE QUIN 1, 23.01 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 15. TG CURVE OF QUINT-T, 8.61 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 16. TG CURVE OF FUEL CELL PAPER, 15.16 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 17. TG CURVE OF HAVEG SILTEMP TAPE, 12.23 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 18. TG CURVE OF SILICONE & VITON #1606, 44.16 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 19. TG CURVE OF ESSEX P/N 470005, 53.69 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 20. TG CURVE OF NOMEX 410, 40.33 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 21. TG CURVE OF NOMEX 418, 45.24 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 22. TG CURVE OF ESSEX P/N 470005, 41.92 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 23. TG CURVE OF ESSEX P/N 11827, 43.92 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 24. TG CURVE OF ESSEX P/N 11054, 48.38 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 25. TG CURVE OF KAPTON 300 H, 32.46 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 26. TG CURVE OF KAPTON 500 H, 45.35 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 27. TG CURVE OF KAPTON 300 V, 35.95 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 28. TG CURVE OF KAPTON 300 F, 30.30 MG, ISOTHERMAL (500°C), 50 CC/MIN He



FIGURE 29. POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH PHLOGOPITE MICA INSULATOR



FIGURE 30. POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH KAPTON 300V INSULATOR



FIGURE 31. POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH KAPTON 500H INSULATOR



FIGURE 32. POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH KAPTON 300H INSULATOR



FIGURE 33. POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH MUSCOVITE MICA INSULATOR



FIGURE 34. POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH ESSEX P/N 11827 INSULATOR



FIGURE 35. POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH ESSEX P/N 470005 INSULATOR



FIGURE 37. POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH NOMEX 418 INSULATOR



FIGURE 36. POTENTIAL AND TEMPERATURE DURING DISCHARGE OF BATTERY WITH ESSEX P/N 11054 INSULATOR

TABLE 1. COMPOSITION OF TEST MATERIALS

SAMPLE	COMPOSITION	COMPANY
PHLOGOPITE MICA	A COMPLEX HYDROUS ALUMINUM SILICATE	
MUSCOVITE MICA	A COMPLEX HYDROUS ALUMINUM SILICATE	
KAPTON 300H	POLYIMIDE FILM	DUPONT COMPANY
KAPTON 500H	POLYIMIDE FILM	DUPONT COMPANY
KAPTON 300V	POLYIMIDE FILM	DUPONT COMPANY
KAPTON 300F	POLYIMIDE FILM COATED WITH TEFLON	DUPONT COMPANY
ESSEX P/N 11827	KAPTON POLYIMIDE-MICA-GLASS CLOTH COMPOSITE	UNITED TECHNOLOGIES ESSEX GROUP
ESSEX P/N 11054	SILICONE-MICA-GLASS CLOTH	UNITED TECHNOLOGIES ESSEX GROUP
ESSEX P/N 470005	ARAMID POLYMER + PLATELET MICA	UNITED TECHNOLOGIES ESSEX GROUP
NOMEX 410	ARAMID POLYMER + PLATELET MICA	UNITED TECHNOLOGIES ESSEX GROUP
NOMEX 418	ARAMID POLYMER + PLATELET MICA	UNITED TECHNOLOGIES ESSEX GROUP
QUINTERRA T3	MAGNESIUM SILICATE FIBER (ASBESTOS FIBER PAPER)	QUIN-T CORPORATION
QUINORGO 5000	MAGNESIUM SILICATE FIBER (ASBESTOS FIBER + ELASTOMERIC BINDER)	QUIN-T CORPORATION
CE QUIN I	ALUMINUM SILICATE (NON-ASBESTOS)	QUIN-T CORPORATION
FUEL CELL PAPER	MAGNESIUM SILICATE FIBER (ASBESTOS FIBER)	QUIN-T CORPORATION
QUIN-T		QUIN-T CORPORATION
CHR SILICONE VITON 1601		CHR INDUSTRIES, INC.
SILTEMP TAPE		HAVEG CORPORATION

TABLE 2. THERMOGRAVIMETRY RESULTS

INSULATOR	THICKNESS (mils)	TG* WEIGHT LOSS	TG** % WEIGHT LOSS
PHLOGOPITE MICA	4	0.01	
MUSCOVITE MICA	4	0.15	
KAPTON 300 V	3	3.93	3.37
KAPTON 300 H	3	4.69	3.39
KAPTON 500 H	5	5.63	4.01
KAPTON 300 F	3		17.90
ESSEX P/N 11827	9	12.36	12.09
ESSEX P/N 11054	10	21.27	21.46
ESSEX 470005	5	2.55	2.30
NOMEX 410	5	22.56	
NOMEX 418	10	33.46	
CHR SILICONE VITON 1606	6	20.33	
SILTEMP TAPE	20	14.04	
QUINTERRA T3	4	11.91	
QUINORGO 5000	5	10.74	
Ce QUIN I	5	24.84	
QUIN-T		3.25	
FUEL CELL PAPER	10	3.30	

*Figures 5 through 21
**Figures 22 through 28

TABLE 3. SUMMARY OF RESULTS AND RECOMMENDATIONS

INSULATOR	THICKNESS (mils)	SUITABILITY FOR THERMAL BATTERY USE
PHLOGOPITE MICA MUSCOVITE MICA	4	EXCELLENT THERMAL STABILITY. SUITABLE FOR USE TO 1000°C. GOOD THERMAL STABILITY RECOMMENDED FOR USE TO 800°C
KAPTON 300 V KAPTON 300 H KAPTON 500 H	3 3 5	PARTIAL DECOMPOSITION AT 500°C. SOME SHRINKAGE AND DEFORMATION IN BATTERY TESTS. RECOMMENDED ONLY WHEN BATTERY DISCHARGE LIFE IS LESS THAN THREE MINUTES.
KAPTON 300 F	3	TEFLON COATING REACTS WITH LITHIUM ANODE. NOT RECOMMENDED.
ESSEX P/N 11827 ESSEX P/N 11054 ESSEX P/N 470005 NOMEX 410 NOMEX 418 CHR SILICONE VITON 1606 SILTEMP TAPE	9 10 5 10 6 20	EXCESSIVE THERMAL DECOMPOSITION AT 500°C RESULTING IN POOR ELECTRICAL INSULATION PROPERTIES. NOT RECOMMENDED.
QUINTERRA T3 QUINORGO 5000 Ce QUIN I QUINT-T FUEL CELL PAPER	4 5 5 10	WETTED BY MOLTEN SALT ELECTROLYTE RESULTING IN POOR ELECTRICAL INSULATION PROPERTIES. NOT RECOMMENDED.

DISTRIBUTION

	Copies
Naval Weapons Center Attn: L. Praccia/A. Fletcher China Lake, CA 93555	2
Naval Ocean Systems Center Attn: Leo Johnson/Dr. Szpak 2710 Catalina Blvd. San Diego, CA 92152	2
Naval Weapons Support Center Attn: M. Roberson/J. Gucinski Crane, IN 47522	2
AFWAL/MLTE Attn: J. Fenter/Glenn Buell WPAFB OH 45433	2
HQ AFLC/DLFP Attn: W. Supp Andrews AFB DC 20334	1
FTD/TQTA Attn: MAJ J. K. Erbacher WPAFB OH 45433	1
FJSRL/NC Attn: J. Wilkes USAF Academy Colorado Springs, CO 80840	1
AD/XRG (AFWAL) Attn: LTCOL Liberatori/ F. Harris Eglin AFB FL 32542	2
AFWAL/POOC Attn: Richard Marsh WPAFB OH 45433	1

	Copies
ERADCOM/DELET-P Attn: Dr. Berger Fort Monmouth, NJ 07703	1
Picatinny Arsenal, SARPA Attn: Gus Magistro/Burton Werbel Dover, NJ 07801	2
Army Materials & Mechanics Research Center Attn: AMXMR/Dr. James McCauley Watertown, MA 02172	1
HG ARMY DARCOM/AMCRP (Roy Arnold) Washington, DC 20334	2
Eagle-Picher Industries Inc. Attn: R. Cottingham P. O. Box 47 Joplin, MO 64801	1
SAFT America Inc. Attn: K. Press 107 Beaver Court Cockeysville, MD 21030	1
Catalyst Research Corporation Attn: F. Tepper/V. Klasons 1421 Clarkview Road Baltimore, MD 21209	2
Hughes Aircraft Company Attn: Dr. L. Fentnor, Bldg. 803-E Missile Systems Division P.O. Box 11337 Tucson, AZ 85734	1

DISTRIBUTION (Cont.)

	Copies
Harry Diamond Laboratory Attn: Dr. J. Nelson/W. Kuper 2800 Powder Mill Road Adelphi, MD 20783	2
Raytheon Company Attn: Paul Boudreau/AAMS Lowell, MA 01853	1
General Dynamics Attn: Dr. Frank Hess Mail Stop 4-66 P.O. Box 2507 Pomona, CA 91766	1
The Boeing Company Attn: Sid Gross Mail Stop 8W-08 P.O. Box 3999 Seattle, WA 98124	1
Sandia Laboratories Attn: J. T. Cutchens, Div. 2523 R. Wehrle, Div. 2522 P.O. Box 5800 Albuquerque, NM 87185	1 1
General Electric Company Attn: R. Walton/Ed Wegman GEND-Pinellas P.O. Box 11508 St. Petersburg, FL 33733	2
U. S. Department of Energy Attn: Ed Patenaude/Errol Davis Pinellas Area Office P.O. Box 11500 St. Petersburg, FL 33733	2
Defense Technical Information Center Cameron Station Alexandria, VA 22314	12
Library of Congress Attn: Gift and Exchange Div. Washington, DC 20540	4
Martin Marietta Company Attn: Paul H. Spear, Mail Stop 323 R. Higginbotham Mail Stop 511 P.O. Box 5837 Orlando, FL 32808	 1 1

DISTRIBUTION (Cont.)

	Copies
Internal Distribution:	
R33 (C. E. Mueller)	1
R33	40
R04	1
E431	9
E432	3

LMED

8