APPROVED FOR PUBLIC RELEASE
DISTRIBUTION UNLIMITED

MASSACHUSETTS INTITUTE OF TECHNOLOGY VLSI PUBLICATIONS

AD-A225 395

DTIC FILE COPY

VLSI Memo ~~No.~~ 89-575
October 1989

Mechanical Properties of Microelectronics Thin Films: Silicon DiOxide (SiO_2)

Fariborz Maseeh, Sean M. Gelston, and Stephen D. Senturia

Abstract

Mechanical design of microfabricated devices requires knowledge of mechanical material properties. Thin film material properties are sensitively process dependent, and should therefore be organized accordingly. A relational database of material properties is under development as part of a general micro-electro-mechanical CAD environment. A computerized literature search through the published values for Silicon DiOxide (SiO_2) properties under various processing conditions resulted in the following document.

DTIC
ELECTE
AUG 22 1990
S D
D

Microsystems Technology Laboratories
Massachusetts Institute of Technology
Cambridge Massachusetts 02139
Room 39-321
Telephone (617) 253-0292

90 08 21 053

Acknowledgements

This research was supported in part by the Defense Advanced Research Projects Agency under contract number MDA-972-88-K-0008.

Author Information

Maseeh and Gelston: Department of Electrical Engineering & Computer Science, Room 39-665, MIT, Cambridge, MA 02139. (617) 253-0725.

Senturia: Department of Electrical Engineering & Computer Science, Room 39-665, MIT, Cambridge, MA 02139. (617) 253-6869.

Copyright© 1989 MIT. Memos in this series are for use inside MIT and are not considered to be published merely by virtue of appearing in this series. This copy is for private circulation only and may not be further copied or distributed, except for government purposes, if the paper acknowledges U. S. Government sponsorship. References to this work should be either to the published version, if any, or in the form "private communication." For information about the ideas expressed herein, contact the author directly. For information about this series, contact Microsystems Technology Laboratories, Room 39-321, MIT, Cambridge, MA 02139; (617) 253-0192.

PROPERTIES OF MICROELECTRONIC SILICON DIOXIDE (SiO_2)

FARIBORZ MASEEH, SEAN M. GELSTON, STEPHEN D. SENTURIA

MICROSYSTEMS TECHNOLOGY LABORATORIES
MASSACHUSETTS INSTITUTE OF TECHNOLOGY
DEPARTMENT OF ELECTRICAL ENGINEERING & COMPUTER SCIENCE
CAMBRIDGE, MA, USA

OCTOBER 1989

Sponsored by
Defense Advanced Research Projects Agency
DARPA/ISTO
"Computer-Aided Fabrication of Integrated Circuits"
ARPA Order No. 6510, PCN 8E20
Program Code No. HR0011
Issued by Darpa/CMO under Contract No.
MDA-972-88-k-0008.

Accession For
NTIS CRA&I
DTIC TAB
Unannounced
Justification
By
Distribution /
Availability Codes
Dist | Avail and/or Special
A-1

QUALITY INSPECTED 4

Introduction

There is a growing need for the ability to perform mechanical analysis of microelectronic devices, both in assuring structural reliability against failure of thin film layers, and in evaluating the effects of various external loads including temperature and humidity effects. In addition, with the development of increasingly sophisticated micromechanical devices, including microsensors, pumps, valves, and micromotors, and with the increasing performance demands being placed on these devices, notably in the precision and accuracy of microsensors, there is a critical need for computer-aided-design (CAD) tools which will permit rational design of these devices. The present program is directed towards creation of a suitable CAD environment for micromechanical analysis of microfabricated deformable structures utilized for measuring the mechanical properties of thin films, and static analysis of which can be utilized for reliability investigations.

There are two fundamental problems that confront the designer [*,**]: (1) the need to construct a three- dimensional solid model from a description of the mask set and process sequence to be used in fabrication of a micromechanical device; and (2) the need to be able to predict the mechanical properties of each of the constituent materials in a device, including possible process dependences of these properties. With such a 3-D model in hand, with appropriate properties for each material, prediction of mechanical behavior could be done with existing finite-element modeling (FEM) programs. However, at the present time, there is no CAD system, either mechanical or microelectronic, which successfully addresses these problems in a coherent way. Koppelman [***] has developed a program called OYSTER which permits construction of a 3-D polyhedral-based solid model from a mask set and primitive process description, but as yet, there is no provision for linking to FEM tools or to standardly used layout and process modeling tools, and no database for prediction of mechanical properties from the process sequence.

An architecture for a micro-electro-mechanical CAD system in which these two critical problem areas can be the focus of simultaneous and parallel development work is presented in Fig. 1. The basic idea is to provide three different levels of user interaction: (1) at the conventional microelectronic level, with access to mask layout and process specification; (2) at the mechanical CAD level, for direct construction of 3-D solid models which can then be analyzed with FEM; and (3) at the mechanical-property database level, for entry of mechanical property data as it is acquired and documented. There are then two specific development tasks: (1) development of a 3-D solid modeling tool, which we call the "structure simulator", and which takes mask layout data and a realistic process description and builds a 3-D solid model in a format compatible with the mechanical CAD system (an extension of what OYSTER now does); and (2) the development of a mechanical property database using iterative measurements on deformable micromechanical structures (such as diaphragms, beams, and resonant structures) together with careful FEM studies of the dependence of their behavior on mechanical properties.

We have implemented this architecture in a Sun 4 host, drawing on existing codes wherever possible. The primary interface for mechanical modeling is through PATRAN, a mechanical CAD package which provides for manual construction of 3-D solid models, graphical display, and interfacing with FEM packages (we are using ABAQUS). The 3-D solid model resides in the PATRAN Neutral File, and we have elected to use the material-property format of the Neutral File as a first version of the Mechanical Property Database. Layout is provided through KIC, and process description through the process-flow representation (PFR) is created with a standard text editor. SUPREM III and SAMPLE are installed to provide depth and cross-sectional modeling capabilities. The structure simulator (under development) will accept KIC and PFR files as input, draw on SUPREM

III and SAMPLE as needed, and will output a 3-D solid model in the format of the PATRAN Neutral File. PATRAN will then be able to pick up the model, provide for FEM analysis and graphical display of behavior. The present status is that all of the commercially available codes (solid boxes in Fig. 1) are installed and operating. The first entries into the Mechanical Property Database have been made for silicon dioxide and silicon nitride as a result of the literature review enclosed.

This document is the result of a computerized literature search (done at MIT CLSS) to loacte published mechanical property data for silicon dioxide, SiO_2. Investigating some 120+ references, a group of 45 was selected and the mechanical properties of SiO_2 were extracted under both thermal growth and chemical vapor deposition (CVD). The cited values were arranged by different mechanical property headings, and then by the deposition methods as subheadings. The boldface values indicate results of experimental measurements (from references), and the italic values correspond to when a reference cites results from other references without measurements, or when no reference experiment was indicated to support the cited values. Most values were traced to their original measurement (experiment) when possible. Averages of the cited properties have been entered in our mechanical property database.

References

*. S. D. Senturia, "Microfabricated structures for the measurement of mechanical properties and adhesion of thin films", Transducers '87, Tokyo, 1987, pp. 11-16.

**. S. D. Senturia, "Can we design microrobotic devices without knowing the mechanical properties of materials?", IEEE MicroRobots and Teleoperators Workshop, Hyannis, 1987.

***. G. Koppelman, "OYSTER: a 3D structural simulator for microelectromechanical design," MEMS '89, Salt Lake City, 1989, pp. 88-93.



Fig. 1

CAD architecture for micro-electro-mechanical design

Table of Contents

1 Young's Modulus 1
- 1.1 Thermal Oxide 1
- 1.2 PECVD oxide 1

2 Poisson's Ratio 2
- 2.1 Thermal Oxide 2
- 2.2 PECVD Oxide 2
- 2.3 Bulk Oxide 2

3 Biaxial Modulus 3
- 3.1 Thermal Oxide 3
- 3.2 PECVD Oxide 3
- 3.3 Bulk Oxide 5

4 Density 6
- 4.1 Thermal Oxides 6
- 4.2 PECVD Oxide 7
- 4.3 Bulk Oxide 9

5 Coefficient of Thermal Expansion 10
- 5.1 Thermal Oxide 10
- 5.2 PECVD Oxide 11
- 5.3 Bulk Oxide 12

6 Thermal Conductivity 13
- 6.1 Thermal Oxide 13
- 6.2 PECVD Oxide 13
- 6.3 Bulk SiO_2 13

7 Stress 14
- 7.1 Thermal Oxide 14
- 7.2 PECVD Oxide 29

8 Stress Relaxation Time 37
- 8.1 Thermal Oxide 37
- 8.2 PECVD Oxide 38
- 8.3 Bulk Oxide 38

9 Viscosity 39
- 9.1 Thermal Oxide 39
- 9.2 PECVD Oxide 40
- 9.3 Bulk Oxide 40

10 Refractive Index 43
- 10.1 Thermal Oxide 43
- 10.2 PECVD Oxide 51
- 10.3 Bulk Oxide 56

11 Bibliography 57

1 Young's Modulus

1.1 Thermal Oxide

- *50* GPa, [3] oxide grown from 550° C to 1000° C.
- *100* GPa, [5].
- *70* GPa, [18].
- 66 GPa [27] for dry oxide grown between 875° C and 1200° C on (100) and (111) oriented Si.
- *76* GPa, [34].
- 57 GPa [36] for wet oxide grown at 960° C.
- 67 GPa [36] for dry oxide grown at 960° C.
- 110×10^5 psi [38].

1.2 PECVD Oxide

No values obtained for the Young's Modulus, E, of PECVD SiO_2

2 Poisson's Ratio

2.1 Thermal Oxide

- *0.15* [3], for oxide grown between 550° C and 1000°
- *0.20* [18], no conditions available.
- *0.17* [21], no conditions availabe.
- *0.164* [34], no conditions abailable.

2.2 PECVD Oxide

No data was retrieved for the Poisson's ratio of PECVD silicon oxide.

2.3 Bulk Oxide

- *0.18* [27].

3 Biaxial Modulus

3.1 Thermal Oxide

- *100* GPa [14]
- 63.3 GPa [30] for oxide grown at 1200° C
- 70 GPa [36] for steam oxide
- 82 GPa [36] for dry oxide

3.2 PECVD Oxide

- Biaxial modulus variant with precursor gas ratio.



This data reproduced from [23]

Conditions :
Substrates: Glass, Steel, and Quartz
Temperature : 250° C
Pressure : 500 mTorr

Rf Frequency : 13.56 MHz
Rf Power Density : 0.02W cm^{-2}

- 42 GPa [23] for the conditions immediately above , when gas ratio exceeds 5.

- Biaxial modulus variant with deposition temperature

Deposition Temperature, ° C	Biaxial Modulus, GPa
250	42
200	42
150	40
100	43

Data reproduced from [23]

Conditions :
N_2O flow : 165 sccm
N_2O/SiH_4 ratio : 12:1
Pressure : 500 mTorr
Temperature : variable
Rf frequency : 13.56 MHz
Power Density : 0.02 W cm^{-2}
Substrates : glass, steel, quartz

- 46.6 GPa and 51.5 GPa.

This data collected from [30].

Conditions:
Temperature : 250° C
Pressure : n/a
Rf frequency : n/a
Rf Power : n/a
SiH_4 (5 % in Ar) : 100 cc min^{-1}
O_2 : 10 cc min^{-1}
N_2 flow : 4000 cc min^{-1}
Substrates : Si and GaAs

- 75 GPa CVD-SiO_2 deposited at 490 A/min

100 GPa CVD SiO_2, deposited at 1900 A/min

Data collected from [37].

Conditions:
Temperature : 450° C
Substrate : (111) Si
Reagents : SiH_4 and O_2
Pressure : n/a:
Deposition rates : 490A/min & 1900A/min.

3.3 Bulk Oxide

- *88* GPa [15].

4 Density

4.1 Thermal Oxides

- Density versus oxidation temperature and pressure for several samples of dry oxide

Growth Temperature, °C	Pressure, atm	Density, g cm^{-3}
800	1	2.47
800	1	2.42
800	500	2.41
1000	500	2.35
1000	1	2.26

This data collected from [8].

Conditions :
Substrates : (111) and (100) Si
Ambient : pure dry O_2, for low pressure, ultradry for high pressure
Initial oxidation for high-pressure oxides : 1000° C, ultradry O_2, for a thickness of 1 nm

- 2.38 g cm^{-3} [10] for dry oxide grown at 500atm, 800° C

- 2.26 g cm^{-3} [10] for dry oxide grown at 1atm, 1000° C

- 2.208 g cm^{-3} [22] for dry oxide grown at 1150° C

- 2.268 g cm^{-3} [22] for dry oxide grown at 700° C

- Density varying with oxidation temperature, for dry oxide.

Temperature, °C	Density, g cm^{-3}
600*	2.286
700*	2.265
750	2.257
800	2.253
900	2.236
1000	2.224
1150	2.208

This data collected from [35].

- The results of anneals on higher density SiO_2 films.

Anneal	Density, g cm^{-3}
None	2.265
N_2 20 min, at 1000° C	2.209
N_2 16 hr, at 600° C	2.209
None	2.270
N_2 16 hr, at 700° C	2.260
N_2 H_2O, 20 hr, 700° C	2.220

This data collected from [35].

Conditions :
Oxidation Temperature : 700° C
Pressure : 5000 psi
Ambient : Dry O_2

- 2.2 g cm^{-3} for wet oxide grown at 960° C [36]

- 2.25 g cm^{-3} for dry oxide grown at 960° C [36]

4.2 PECVD Oxide

- Effects of gas flow rate and annealing on oxide density

Gas Flow Rate (sccm)	ρ (g cm^{-3})	ρ^* (g cm^{-3})
3	2.09	2.22
1	2.07	2.24
0.7	2.07	2.26
0.6	2.02	2.28
05.	1.98	2.30

* Films annealed at 1000° C for 30 min in N_2 ambient
These values collected from [20].

Conditions:
SiH_4 (1.5 % in Ar) flow rate : 0.3 sccm
O_2 flow rate : variable
Temperature : 350° C
Pressure : 1.5 Torr
Rf frequency: 13.562 MHz
Rf Power : 50W.

- Density varying with gas ratio



This data reproduced from [23].

Conditions :
Substrates: Glass, Steel, and Quartz
Temperature : 250° C
Pressure : 500 mTorr
Rf Frequency : 13.56 MHz
Rf Power Density : 0.02W cm^{-2}
N_2O Flow : 165 sccm
SiH_4 Flow : variable, to suit gas ratio (see above)

- Density varying with deposition temperature.



This data reproduced [29].

Conditions:
Temperature : variable
Pressure : 1 Torr
Gas Ratio, N_2O / SiH_4 : 65
Rf frequency : 13.56 MHz
Rf Power : 24W.

- **1.97 (+/- 0.02)** g cm^{-3} [32]

Conditions:
N_2O / SiH_4 ratio : 12:1
Temperature : variable

4.3 Bulk Oxide

2.2 g cm^{-3}, [33] at temperature = 300K

5 Coefficient of Thermal Expansion

5.1 Thermal Oxide

- 6×10^{-7} ° C^{-1} [14].
- 3.5×10^{-7} ° C^{-1} [22] dry grown from 950 - 1150° C.
- 5×10^{-7} ° C^{-1} [30] for oxide grown at 1200° C
- 6×10^{-7} ° C^{-1} [38] for dry oxide grown at 1200° C
- Thermal expansion coefficient vs. temperature



This data reproduced from [42].

Conditions :
Oxidation Temperature : 1050° C
Measurement Temperature : see above
Oxidation Pressure : n/a
Ambient : **Steam**
Substrate : (100) oriented Si
Film Thickness : 4000A

5.2 PECVD Oxide

- Coefficient of thermal expansion, α, variant with gas ratio.



Data reproduced from [23]

Conditions for PECVD:
Precursor gases : SiH_4 and N_2O
Substrates : quartz, steel, and glass
Temperature : 250° C
Pressure : 500 mTorr
Rf frequency : 13.56 MHz
Rf Power Density : 0.02 W cm^{-2}
Total Gas flow : 200 sccm.

- Measurements of thermal expansion coefficients for varying deposition temperatures.

Deposition Temperature, ° C	α, x 10^{-6} ° C^{-1}
250	2.3
200	2.6
150	2.2
100	2.2

This data reproduced from [24]

Conditions :
N_2O flow : 165 sccm
N_2O/SiH_4 ratio : 12:1
Pressure : 500 mTorr
Temperature : variable

Rf frequency : 13.56 MHz
Power Density : 0.02 W cm^{-2}
Substrates : glass, steel, quartz.

- **3.9 - 4.1 x 10^{-6} ° C^{-1}** [30]

Conditions :
Temperature : 250° C
SiH_4 (5 % in Ar) : 100 cc min^{-1}
O_2 flow: 10 cc min^{-1}
N_2 flow : 4000 cc min^{-1}

- **5.5 x 10^{-7} ° C^{-1}** [37]

Conditions:
Temperature : 450° C
Substrate : (111) Si
Reagents : SiH_4 and O_2
Pressure : n/a:
Deposition rates : 490A/min & 1900A/min.

5.3 Bulk Oxide

- *5.2 x 10^{-7}* ° C^{-1} [15].

6 Thermal Conductivity

6.1 Thermal Oxide

No values obtained for thermal oxide.

6.2 PECVD Oxide

No values obtained for PECVD oxide.

6.3 Bulk SiO_2

- Coefficient of thermal conductivity for bulk SiO_2, variant with temperature.



This data reproduced from [33].

7 Stress

7.1 Thermal Oxide

- 600 MPa, [3] oxide grown at 700° C.

- Schematic distribution of stress in the oxide film and its substrate.



This data reproduced from [6].

<u>Conditions :</u>
Oxidation Temperature : 1200° C
Growth Substrate : 2-6 Ω-cm p-type (111) Si
Anneal : 400° C. in N_2 and H_2 Annealing Duration : n/a

- Calculated stress in SiO_2 variant with oxidation temperature.



This data reproduced from [6].

Conditions :
Substrate : 2-6 Ω-cm p-type (111) Si
Anneal : 400° C. in N_2 and H_2. duration n/a

- Calculated variation of stress with oxide thickness



This data reproduced from [6].

Conditions :
Growth Temperature : 1200° C
Substrate : 2-6 Ω-cm p-type (111) Si
Anneal : 400° C. in N_2 and H_2. duration n/a

- Calculated variation of stress with substrate thickness



This data reproduced from [6].

Conditions :
Growth Temperature : 1200° C
Substrate : 2-6 Ω-cm p-type (111) Si
Anneal : 400° C, in N_2 and H_2, duration n/a

- Residual Stress Measurements for Pressure-Oxides, and Normal 1 atm Oxide.

Sample Type	Stress, MPa
Pressure Oxide,	
500 atm, 800° C	150
	400
	400
	230
	400
	280
Average:	310
Controls,	
1 atm, 1000° C	410
	420

This data collected from [8].

Conditions :
Sustrates : (100) and (111) Si
H_2O content : < 1ppm

- 350 MPa [9], average compressive sress at room temperature for dry oxides grown at 1000° C.

- 310 - 340 MPa [11], average compressive stress for dry oxide grwon at 500 atm, 800° C.

- Intrinsic stress variant with film thickness.



Oxidation Temperatures
700° C
800° C
1000° C

This data reproduced from [12]

Conditions :
Substrate : (100) p-type Si
Oxidation Ambient : dry O_2 with <5 ppm H_2O and <0.5 ppm hydrocarbons.

• Intrinsic stress variant with film thickness for etched oxide.



Oxidation Temperatures
700° C (□)
800° C (○)
1000° C (△)

This data reproduced from [12].

Conditions :
Substrate : (100) p-type Si
Oxidation Ambient : dry O_2 with <5 ppm H_2O and <0.5 ppm
Etching : in HF solution, (NH_4:HF = 50:1) hydrocarbons.

• 450 MPa, [12] maximum stress for a limit of a film with zero thickness.

• Total stress for dry oxides grown on two Si substrates at different temperatures.

Substrate	Temperature, ° C	Total Stress, MPa
p+ 10^{-2} Ωcm Si	850	150
p+ 10^{-2} Ωcm Si	1090	290
p 1 Ωcm Si	850	80
p 1 Ωcm Si	1090	260

This data collected from [13].

- Stress varying with oxidation temperature for <u>four Si orientations</u>.



This data reproduced from [15].

<u>Conditions</u> :

Ambient : dry O_2, with <5 ppm H_2O, and <0.5 ppm hydrocarbons

Pressure : 1 atm

• Stress varying with oxidation temperature for (100) Si.



This data reproduced from [15].

Conditions :
Ambient : dry O_2, with <5 ppm H_2O, and <0.5 ppm hydrocarbons
Pressure : 1 atm
Annealed : 1000° C. in N_2

• Stress varying with oxidation temperature for (111) Si.



This data reproduced from [15].

Conditions :
Ambient : dry O_2, with <5 ppm H_2O, and <0.5 ppm hydrocarbons
Pressure : 1 atm
Annealed : 1000° C. in N_2

- Stress varying with oxidation temperature for dry oxide.



2' Maximum Stress

1 Thermal Stress

2 Mininum Stress

This data reproduced from [21].

Conditions : n/a.

- Stress distribution over the thickness for dry oxide.



This data reproduced from [21].

Conditions : n/a.

- Intrinsic and thermal stresses varying with oxidation temperature for dry oxide.



This data reproduced from [21].

Conditions : n/a.

- Stress measurements from beam experiment.



This data reproduced from [27].

Conditions :
Substrates : (111) and (100) - oriented Si
Oxidation : Dry

- Stress measurements from balloon experiment.



This data reproduced from [27].

Substrates : (111) and (100) - oriented Si
Oxidation : Dry

- Stress vs. strain for typical oxide balloon



Substrates : (111) and (100) - oriented Si
Oxidation . Dry
This data reproduced from [27].

- 340 MPa [30] measured at room temp., grown at 700° C.

- 400 MPa compressive [35], grown at 700° C.

- 50 MPa tensile [35], grown at 1150° C.

- 220 - 360 MPa compressive, [37] measured at room temp., grown at 1100° C.

- Total film stress, measured at room temperature, vs. oxide thickness



This data reproduced from [41].

Conditions :
Oxidation Temperature : see above.
Oxidation Pressure : 1 atm
Ambient : Dry O_2
Substrate : *p*-type (100) oriented Si

Components of stress vs. oxidation temperature



This data reproduced from [41]

Intrinsic stress vs. oxidation temperature



Conditions For Both Graphs:

Oxidation Temperature : see above
Measurement Temperature : room temperature
Oxidation Pressure : 1 atm (unless otherwise specified)
Ambient : Dry O_2
Substrate : *p*-type (100) oriented Si

- Stress vs. temperature



This data reproduced from [42].

Conditions :
Oxidation Temperature : 1050° C
Measurement Temperature : see above
Oxidation Pressure : n/a
Ambient : Steam
Substrate : (100) oriented Si
Film Thickness : 4000A

- Change in curvature induced by stress, vs. oxide thickness



This data reproduced from [44].

Dashe line represents the expected curvature change for SiO_2 stress level of 700MPa.

Conditions :
Oxidation Temperature : see above
Measurement Temperature : ox. temp.
Oxidation Pressure : n/a
Ambient : wet O_2
Substrate : 1-Ω-cm P-doped (111) and (100) Si
Film Thickness : 4000A

- Interfacial stress at room temperature for various substrates.

P_2O_5 Diffusion	Direction of Stress Measurement	Si Orientation	Stress, MPa
No	(110)	(111)	47
No	(211)	(111)	450
Yes	(110)	(111)	250
No	(110)	(110)	390
No	(100)	(110)	390
Yes	(110)	(110)	260
No	(110)	(100)	400
No	(110)	(100)	380
Yes	(110)	(100)	240

This data reproduced from [45].

Conditions :
Oxidation Temperature : 1200° C
Measurement Temperature : room temperature>
Oxidation Pressure : n/a
Ambient : wet O_2 (dew point temperature 90° C)
Substrate : 5 Ω-cm (111), (110), and (100) Si
Film Thickness : 8400A
P_2O_5 Diffusion : in N_2 for 30 min. at 920° C

- Oxide stress at room temperature for quickly and slowly cooled films

Sample Type and Cooling	Film Stress, MPa
Dry Oxide	
Slowly Cooled	270
Quickly Cooled	370
Wet Oxide	
Slowly Cooled	160
Quickly Cooled	280

This data reproduced from [45].

Conditions :
Oxidation Temperature : 1200° C
Measurement Temperature : room temperature
Measurement Direction : (110) direction
Oxidation Pressure : n/a
Ambient : wet oxide, dew point temperature = 90° C
dry oxide, dew point temperature = -40° C
Substrate : (110) - oriented P-doped Si. Film Thickness : 8600-9200A
Cooling Duration : for quick cooling, immediate exposure to air

Cooling Duration : for quick cooling, immediate exposure to air
for slow cooling, duration = 5hr

- Oxide stress at room temperature for various doping levels of Si

Slice Resistivity, Ω-cm	Doping Level, cm^{-3}	Oxide Stress, MPa
1000	$4x10^{12}$	280
5-10	$8.5x10^{14}$ - $4x10^{14}$	270
0.37	$1.6x10^{16}$	200
0.035	$4.5x10^{17}$	260
0.0015	$5.5X10^{19}$	300

This data reproduced from [45].

Conditions :
Oxidation Temperature : 1200° C
Measurement Temperature : room temperature
Measurement Direction : (200) direction
Oxidation Pressure : n/a
Ambient : wet oxide, dew point temperature = 90° C
Substrate : (111) - oriented P-doped Si. Film Thickness : 9200A

7.2 PECVD Oxide

- Stress varying with temperature (not oxidation temperature).



This data reproduced from [14].

- Thermally induced stress in the oxide, as a function of the measured temperature.



This data reproduced from [23] and [24]

Conditions :
Temperature : 250° C
Pressure : 500 mTorr
N_2O / SiH_4 : 12:1
Total gas flow rate : 200 sccm
Rf frequency : 13.56 MHz
Rf Power Density : 0.02 W cm^{-2}
Substrates : quartz, steel, glass.

- Tension in the film as a function of film thickness.



This data reproduced from [24]

Conditions :
Temperature : 250° C
Pressure : 500 mTorr
Rf frequency : 13.56 MHz
Rf Power Density : 0.02 W cm^{-2}
N_2O / SiH_4 : 12:1
SiH_4 flow rate : 200 sccm
Substrates : glass, steel, quartz

- Stress in a CVD SiO_2 film as a function of temperature.

Air



Dry Air



This data reproduced from [30].

Conditions :
Deposition Temperature : 250° C
SiH_4 (5% in Ar) flow : 100 cc/min
O_2 flow : 10 cc/min
N_2 flow : 4000 cc/min
Deposition Thickness : 0.65 μm
Substrates : GaAs and Si

- Time variation of stress in CVD SiO_2

Kept in air, 49% rel. humid., exposure to a dry N_2 ambient at 22° C.



This data reproduced from [30].

Kept in dry N_2, upon exposure to air, 60% RH, at 22° C.



Conditions :

Deposition Temperature : 250° C

SiH_4 (5% in Ar) flow : 100 cc/min

O_2 flow : 10 cc/min

N_2 flow : 4000 cc/min

Depositoin Thickness : 0.65 μm

Substrates : GaAs and Si

- $\sigma(T) - \sigma(115^\circ C)$ as a function of temperature.

Solid curves represent calculated values. Measurements done in vacuum.



This data reproduced from [30].

Conditions :

Deposition Temperature : 250° C

SiH_4 (5% in Ar) flow : 100 cc/min

O_2 flow : 10 cc/min

N_2 flow : 4000 cc/min

Deposition Thickness : 0.47 μm

Substrates : GaAs and Si

- Time varying stress for a CVD SiO_2 film, previously kept in air, 48% RH, at 21° C, upon exposure to 40 μm Hg.



This data reproduced from [30].

Conditions :
Deposition Temperature : 250° C
SiH_4 (5% in Ar) flow : 100 cc/min
O_2 flow : 10 cc/min
N_2 flow : 4000 cc/min
Deposition Thickness : 0.47 μm
Substrates : GaAs

- Stress change in CVD SiO_2 after heat treatments.



This data reproduced from [37].

Conditions :
Deposition Temperature : 400° C - 450° C
Deposition Pressure : n/l
Reagent : SiH_4
Substrate : (111) Si, 200μm thick

Heat Treatment Temperature : see above

- Stress in CVD films vs. ambient temperature



This data reproduced from [37].

Conditions :
Deposition Temperature : 400° C - 450° C
Deposition Pressure : n/1
Reagent : SiH_4
Substrate : (111) Si, 200μm thick

- Stress in CVD SiO_2 films vs. deposition rate

Deposition Rate (A/min)	Stress after Deposition, MPa	Intrinsic Stress, MPa
1900 A/min	220	370
490 A/min	170	240

This data collected from [37].

Deposition Temperature : 400° C - 450° C
Deposition Pressure : n/1
Reagent : SiH_4
Substrate : (111) Si, 200μm thick

- Stress change of CVD SiO_2 film after various treatments.



This data collected from [37].

Conditions :
Deposition Temperature : 400° C - 450° C
Deposition Pressure : n/1
Reagent : SiH_4
Substrate : (111) Si, 200μm thick
Film Thickness : see above

- Temperature dependence of CVD SiO_2 stress on Si



This data reproduced from [42]

Conditions :
Deposition Temperature : 480° C
Deposition Pressure : n/a
Reagents : SiH_4 and O_2
Film Thickness : 6000A

8 Stress Relaxation Time

8.1 Thermal Oxide

- Stress relaxation time variant with temperature.

Temperature, ° C	Stress Relaxation Time, hrs
800	>1000
900	>1000
950	-
1000	~25-60
1050	~6-20
1100	~1-3
1180	<<0.3

This data collected from [5]

Condtions :
Oxidation Temperature : see above
Oxidation Pressure : n/a.
Ambient : dry oxide.

- Stress relaxation time variant with temperature.

Temperature, ° C	Stress Relaxation Time, hrs
700	5278
800	175
1000	0.2

This data collected from [12].

Conditions :
Substrate : (100) p-type Si
Oxidation Ambient : dry O_2 with <5 ppm H_2O and <0.5 ppm hydrocarbons.

- Stress relaxation time variant with temperature.

Temperature, ° C	Stress Relaxation Time, hrs
800	5100
900	21
1000	0.2
1100	(10 seconds)

This data collected from [35].

Conditions :
Oxidation Temperature : see above
Pressure : 1 atm
Substrate : (111) and (100) oriented Si crystals

8.2 PECVD Oxide

No information available for PECVD oxide films.

8.3 Bulk Oxide

- Stress Relaxation times for I. R. Vitreosil.

Temperature, ° C	τ, hrs.
900	>50,000
1000	>1000
1100	170
1200	24
1300	6
1400	2

This data collected from [39].

9 Viscosity

9.1 Thermal Oxide

- Viscosity variant with temperature.

Temperature, ° C	Stress Relaxation Time, hrs
800	$>>10^{18}$
900	$>10^{18}$
950	$\sim 10^{18}$
1000	7×10^{16}
1050	6×10^{15}
1100	5×10^{14}
1180	$\sim 10^{13}$

This data collected from [5]

Condtions :
Oxidation Temperature : see above
Oxidation Pressure : n/a.
Ambient : dry oxide.

- Viscosity (Poise), as a function of temperature.



This data reproduced from [40]

Conditions

Oxidation Tewmperature : 1100° C

Oxidation Ambient : steam

Substrate : standard *n*-type P-doped 1.0Ω-cm Si wafers of (100) orientation

9.2 PECVD Oxide

No information available for PECVD Oxides.

9.3 Bulk Oxide

- Equilibrium viscosities for different types of vitreous silica.



This data reproduced from [39].

- Variation of viscosity with temperature for Vitreosil.



Δ Fictive temperature 1000 C
Fictive temperature 1100 C
∇ Fictive temperature 1200 C
Fictive temperature 1300 C
◇ Fictive temperature 1400 C
Equilibrium viscosity curve—bold symbols

This data reproduced from [39].

- Variation of Viscosity with temperature for Spectrosil.



Fictive temperature 900° C
Δ Fictive temperature 1000 C
Fictive temperature 1100 C
∇ Fictive temperature 1200 C
Fictive temperature 1250 C
Fictive temperature 1400 C
Equilibrium viscosity curve—bold symbols

This data reproduced from [39].

10 Refractive Index

10.1 Thermal Oxide

- Refractive Index varying with oxidation temperature.



This data reproduced from [1].

Conditions :
H_2 / O_2 flow ratio : 1.8
Ambient : dry O_2
Pressure : 5.6 kg cm^{-2}.

- Refractive Index varying with oxidation pressure.



This data reproduced from [1]

Conditions :
H_2 / O_2 flow ratio : 1.8
Ambient : dry O_2
Pressure : 5.6 kg cm^{-2}.

- Effect of oxidation temperature and pressure on refractive index, for dry oxide.

Oxygen Pressure, atm	(Oxidation Temperature,) °C	Index of Refraction
1	700	1.486
1	800	1.474
1	850	1.478
1	900	1.466
1	1000	1.465
(high pressure)		
136	550	...
207	550	1.476
136	600	1.474
212	600	1.484
136	700	1.475
207	700	1.487
212	700	1.476
306	700	1.474
211	800	1.473

This data taken from [3]

- Index of refraction as a function of oxidation temperature.



This data reproduced from [3].

Conditions :
Pressure : 1 atm
Ambient : dry O_2.

- Refractive index versus anneal time for dry - oxide grown thermally on (111) Si at 800° C.



This data reproduced from [5].

Conditions :
Pressure : n/a.

- 1.460 for fully relaxed SiO_2 thin film. [5]

- 1.466 for an oxide, dry-grown at 1000° C. [5]

- Refractive Index values before and after relaxation.

Growth Temperature, ° C	Refractive Index	Relaxation Treatment	Ref. Index After Relaxation
800	1.472	none	
800	1.472	1000° C 1 hr N_2	1.467
800	1.472	1000° C 16 hr N_2	1.464
800	1.472	1180° C 40 min N_2	1.460
1180	1.460	none	
800	1.472	1204° C 5 min O_2	1.460
800	1.472	none	
800	1.472	1180° C 40 min Corona*	1.460
800	1.472	800° C 20 min O_2	1.460
1000	1.467	none	
1000	1.467	Corona*	1.460
1000	1.467	900° C 4 hr O_2	
		none	

* Stress relaxation performed by a Corona discharge device.

This data taken from [7].

- Refractive Index measurements for Pressure Oxide, Normal Oxide, and Low Temperature Oxide.

Sample Type	Film Thicness, nm	Refractive Index
Pressure Oxide, 500 atm, 800° C	947.6	1.476
	153.3	1.475
	983.0	1.473
	941.1	1.473
	685.7	1.475
	129.8	1.478
	960.0	1.475
	967.2	1.467
	684.6	1.477
Average:		
Controls, 1 atm, 1000° C	959.0	1.461
	951.4	1.461
	1293.0	1.462
Average :		1.461
Low Temperature Oxide, 1 atm, 800° C	...	1.468
	...	1.476

This data reproduced from [8]

Conditions :
Sustrates : (100) and (111) Si
H_2O content : < 1ppm

- **1.475** for oxide prepared at 500 atm. and 800° C. [10]

- **1.461** for oxide prepared at 1 atm. and 1000° C. [10]

- **1.462** for thermal oxide prepared at 1100° C. [11]

- The effect of oxidation time and annealing on refractive index and film thickness

Duration of Second Oxidation, hrs	Thickness of Unannealed Film, A	η of Unannealed Film	Thickness of Annealed Film, A	η of Annealed Film
1	9	**1.474**	23	**1.463**
2	15	**1.475**	44	**1.465**
4	30	**1.475**	83	**1.465**
9	78	**1.474**	163	**1.464**
19	178	**1.473**	267	**1.464**

Data taken from [17].

Both oxidations were conducted in pure dry O_2 at 800° C. The annealing was performed for 1 hour at 1000^0C in pure Ar.

- Refractive Index as it depends upon density.



Reproduced from [22].

- Refractive Index versus deposition temperature for thermal oxides grown on two different silicon substrates.

(111) Silicon



(100) Silicon



Reproduced from [34].

- Variation of refractive index with oxidation temperature for thermally grown SiO_2 films.

Temperature, ° C	Refractive Index
600*	1.480
700*	1.475
750	1.473
800	1.472
900	1.468
1000	1.465
1150	1.461

* These samples grown at 5000 psi O_2, all others at 1 atm O_2.

Reproduced from [35]

- Index of refraction vs. oxidation temperature



This data reproduced from [43]

Conditions :

Oxidation Temperature : see above

Ambient : 95° C saturated water vapor

Substrates : (111) and (100) lightly doped Si

10.2 PECVD Oxide

- Table of values of refractive index, and deposition parameters.

Deposition Temperature, ° C	Flow Rates N_2O:SiH_4:He, sccm	Deposition Rate, A/min.	Refractive Index
350	500:200:0	510	1.462
350	500:200:0	510	1.465
350	200:80:1000	150	1.469
350	100:40:2000	60	1.472
350	100:40:2000	60	1.464
350	100:40:2000	50	*1.471*
350	100:40:2000	80	*1.471*
350	100:40:2000	80	*1.471*
350	100:40:2000	60	*1.471*
275	100:40:2000	60	1.474

This data collected from [4].

Conditions :
Temperature : see above
Pressure : 1 Torr
Flow Rates : see above
Rf Power : 25 W (0.03 W cm^{-2})
Rf Freq. : 13.56 MHz

- Refractive Index dependent upon Deposition Temperature, Pressure, Rate, and Anealing.

Deposition Temperature, ° C	Deposition Pressure	Deposition Rate, A/min	Anneal Performed	Refractive Index
350	1 Torr	60	No	1.471 (+/- 0.001)
350	1 Torr	60	Yes	1.463 (+/- 0.002)
275	1 Torr	60	No	1.473 (+/- 0.002)
275	1 Torr	60	Yes	1.463 (+/- 0.002)
350	1 Torr	520	No	1.467 (+/- 0.004)
350	1 Torr	520	Yes	1.463 (+/- 0.003)
700	1 atm	50	No	1.444 (+/- 0.001)
700	1 atm	50	Yes	1.454 (+/- 0.001)

Data collected from reference N° 4.

Deposition Conditions
Temperature : see above
Pressure : see above
N_2O / SiH_4 ratio : 125 (for atmosphere pressure deposition only)

Rf frequency : 13.56 MHz.
Rf Power : 25W (0.03 W cm^{-2})

Annealing Conditions
Temperature : 1000° C
Ambient : N_2
Duration : 30 min.

- **1.461 - 1.465** for oxide prepared at 500° C, 10 mTorr, Rf frequency of 0.5-3.0 MHz, and Rf Power of 1 kW. Gas data : n/a. [16]

- Refractive index, before and after annealing for PECVD oxide.



This data reproduced from [20]

Deposition Conditions
Reagents: SiH_4, O_2, Ar
Rf frequency : 13.562 MHz
Rf Power : 50 W
Temperature : 350° C
Pressure : 1.5 Torr
SiH_4 flow : 0.3 sccm
O_2 flow rate : variable
Substrate : Al.

Annealing Conditions :
30 min. in N_2, at 1000° C

- Refractive index as it varies with reagent gas ratio, for PECVD oxide.



Graph reproduced from [25]

Conditions :
Temperature : n/a
Pressure : n/a
Rf frequency : 13.56 MHz
Rf Power : n/a
Substrate : Si wafer
Gas ratio : variable.

- Refractive index vs. gas ratio for photo-enhanced CVD SiO_2.



Graph reproduced from [26].

Conditions :
SiH_4 flow rate : 1 sccm
N_2O flow rate : 70 sccm
Pressure : 1 mbar
Temperature : 275° C
Power density : 0.1 mW cm^{-2}
N_2 flow rate : 30 sccm.

- Refractive index vs. gas ratio for glow-discharge deposited SiO_2.



Graph reproduced from [28].

Conditions :
Temperature : <40° C
Pressure : 45 mTorr
Rf frequency : 13.56 MHz
Power Density : 0.2-0.5 W cm^{-2}
Reagents : N_2O and SiH_4.

- Refractive index vs. deposition temperature for PECVD SiO_2.



Reproduced from [29]

Conditions:
Temperature : variable
Pressure : 1 Torr
Gas Ratio. N_2O / SiH_4 : 65
Rf frequency : 13.56 MHz
Rf Power : 24W

- Refractive index vs. gas ratio for PECVD SiO_2.



Reproduced from [31].

Conditions :
Temperature : 300° C
Pressure : 53 Pa
Rf frequency : 57 kHz
Rf Power Density : 0.05 W cm^{-2}.

- Refractive index vs. rf power, for PECVD SiO_2.



Reproduced from [31].

Conditions :
Temperature : 300° C
Pressure : 53 Pa
Rf frequency : 57 kHz
Gas Composition, N_2O : 98%, SiH_4 : 2%.

10.3 Bulk Oxide

1.46 for bulk SiO_2. [33]

11 Bibliography

1. Thin Oxide Films of Silicon by High Pressure Oxidation.
M. Hirayama, H. Miyoshi, N. Tsubouchi, and H. Abe, at *Computer Development Laboratories, Ltd.* and *LSI R&D Laboratory, Mitsubishi Electric Co., Mizuhara, Itami, Japan*
in J. Electron. Mater., 11 (5) May, **1982**, 919-929

2. Oxidation Induced Stresses and Some Effects on the Behavior of Oxide Films.
C. H. Hsueh and A. G. Evans, at *Materials and Molecular Research Division, Lawrence Berkeley Laboratory and Department of Materials Science and Mineral Engineering, University of California, Berkeley, California*
in J. Appl. Phys., 54 (11), Nov., **1983**, 6672-6686

3. Low-Temperature Growth of Silicon Dioxide Films: A Study of Chemical Bonding of Ellipsometry and Infrared Spectroscopy.
G. Lucovsky and M. J. Manitini, at *Department of Physics, North Carolina State University, Raleigh, North Carolina* and J. K. Srivastava and E. A. Irene, at *Department of Chemistry, University of North Carolina, Chapel Hill, North Carolina*
in J. Vac. Sci. Technol. B, 5 (2), Mar/Apr, **1987**, 530-537

4. Low-Temperature Deposition of High-Quality Silicon Dioxide by Plasma-Enhanced Chemical Vapor Deposition.
J. Batey and E. Tierney, at *IBM Thomas J. Watson Research Center, Yorktown Heights, New York*
in J. Appl. Phys., 60 (9), 1 Nov., **1986**, 3136-3145

5. Refractive Index, Relaxation Times and the Viscoelastic Model in Dry-Grown SiO_2 Films on Si.
L. M. Landsberger and W. A. Tiller, at *Stanford University, Stanford, California*
in Appl. Phys. Lett., 51 (18), 2 Nov. **1987**, 1416-1418

6. Surface Charge and Stress in the Si/SiO_2 System.
S. D. Brotherton, T. G. Read, D. R. Lamb, and A. F. W. Willoughby, at *Department of Electronics and Department of Mechanical Engineering, Southampton University, Southampton, England*
in Solid-State Electronics, 16, **1973**, 1367-1375

7. Stress Relaxation Technique for Thermally Grown SiO_2.
L. M. Landsberger, at *Department of Electrical Engineering, Stanford University, Stanford, California*, and W. A. Tiller, at *Department of Materials Science and Engineering, Stanford University, Stanford, California*
in Appl. Phys. Lett., 49 (3), 21 July **1986**, 143-145

8. Residual Stress, Chemical Etch Rate, Refractive Index and Density Measurements on SiO_2 Films Prepared Using High Pressure Oxygen.
E. A. Irene and D. W. Dong, at *IBM Thomas J. Watson Research Center, Yorktown Heights, New York*, and R. J. Zeto, at *U. S. Army Electronics Technology and Devices Laboratory (ERADCOM*, Fort Monmouth, New Jersey)
in J. Electrochem. Soc., 127 (2), Feb., **1980**, 396-399

9. Dislocation Generation at Si_3N_4 Film Edges on Silicon Substrates and Viscoelastic Behavior of SiO_2 Films.
S. Isomae, Y. Tamaki, A. Yajima, M. Nanba, and M. Maki, at *Central Research Laboratory, Hitachi Limited, Kokubunji, Tokyo, Japan*

in J. Electrochem. Soc., 126 (6), June **1979**, 1014-1019

10. Some Physical Properties of Dry High-Pressure Oxide Films on Silicon.
R. J. Zeto, at *U. S. Army Electronics Technology and Devices Laboratory (ERADCOM*, Fort Monmouth, New Jersey), andE. A. Irene and D. W. Dong, at *IBM Thomas J. Watson Research Center, Yorktown Heights, New York*
in IEEE Transactions on Electron Devices, 25 (11), **1978**, 1359

11. The Formation of SiO_2 in an RF Generated Oxygen Plasma.
A. K. Ray and A. Reisman, at *IBM Thomas J. Watson REsearch Center, Yorktown Heights, New York*
in J. Electrochem. Soc., 128 (11), Nov., **1981**, 2466-2472

12. SiO_2 Film Stress Distribution During Thermal Oxidation of Si.
E. Kobeda and E. A. Irene, at *Department of Chemistry, The University of North Carolina, Chapel Hill, North Carolina*
in J. Vac. Sci. Technol. B, 6 (2), Mar/Apr. **1988**, 574-578

13. Stress in Oxidized Porous Silicon Layers.
K. Barla, R. Herino, and G. Bomchil, at *Centre National d'Etudes des Telecommunications-CNS, Chemin du Vieux Chene, Cedex, France*
in J. Appl. Phys., 59 (2), 15 Jan. **1986**, 439-441

14. Stress in Chemical-Vapor-Deposited SiO_2 and Plasma-SiN_x Films on GaAs and Si.
C. Blaauw, at *Bell-Northern Research, Ottawa, Canada*
in J. Appl. Phys., 54 (9), Sept., **1983**, 5064-5068

15. Intrinsic SiO_2 Film Stress Measurements on Thermally Oxidized Si.
E. Kobeda and E. A. Irene, at *Department of Chemistry, The University of North Carolina, Chapel Hill, North Carolina*
in J. Vac. Sci. Technol. B, 5 (1), Jan/Feb. **1987**, 15-19

16. A Growth Model for the Variable Index of Refraction of Thermal Oxides on Silicon.
E. A. Taft, at *General Electric Corporation, Corporate Research and Development, Schenectady, New York*
in J. Electrochem. Soc., 134 (2), Feb. **1987**, 475-476

17. A Measurement poof the Effect of Intrinsic Films Stress on the Overall Rate of Thermal Oxidation of Silicon.
J. K. Srivastava and E. A. Irene, at *Department of Chemistry, University of North Carolina, Chapel Hill, North Carolina*
in J. Electrochem. Soc., 132 (11), Nov., **1985**, 2815-2816

18. Stress in Silicon at Si_3N_4 Film Edges and Viscoelastic Behavior of SiO_2 Films.
Seiichi Isomae, at *Central Research Laboratory, Hitachi, Ltd. Kokubunji, Tokyo, Japan*
in J. Appl. Phys., 57 (2), 15 Jan. **1985**, 216-223

19. Mechanical Properties of SiOx Thin Films.
J. Pivot, at *Department de Physique des Materiaux, Universite Claude Bernard Lyon I, Villeurbanne Cedex, France*
in Thin Solid Films, 89, **1982** 175-190

20. The Composition and Properties of PECVD Silicon Oxide Films.
P. Pan, L. A. Nesbit, R. W. Douse, and R. T. Gleason, at *IBM General Technology Division, Essex Junction,*

Vermont
in J. Electrochem. Soc. 132 (8), Aug. 1985, 2021-2019

21. Mechanical Stresses on the Si-SiO2 Interface.
V. I. Sokolov and N. A. Fedorovich, at *A. F. Ioffe Physico-Technical Institute, Academy of Sciences of the USSR, Leningrad*
in Phys. Status Solidi, A, 99 (1), 16. Jan. 1987, 151-158

22. Silicon Oxidation and Si-SiO Interface of Thin Oxides.
N. M. Ravindra and J. Narayan, at *Materials Science and Engineering Department, North Carolina State University, Raleigh, North Carolina*; Dariush Fathy, at *Solid State Division, Oak Ridge National Laboratory, Oak Ridge, Tennessee*; and J. K. Srivastava and E. A. Irene, at *Department of Chemistry, The University of North Carolina, Chapel Hill, North Carolina*
in J. Mater. Res. 2 (2), Mar/Apr 1987, 216-221

23. Thermal Expansion and Elastics Properties of Plasma-Deposited Amorphous Silicon and Silicon Oxide Films.
F. Jansen, M. A. Machonkin, N. Palmieri, and D. Kuhman, at *Xerox Webster Research Center, Webster, New York*
in Appl. Phys. Lett. 50 (16), 20 April 1987, 1059-1061

24. Thermomechanical Properties of Amorphous Silicon and Nonstoichiometric Silicon Oxide Films.
F. Jansen, M. A. Machonkin, N. Palmieri, and D. Kuhman, at *Xerox Webster Research Center, Webster, New York*
in J. Appl. Phys. 62 (12), 15 Dec. 1987, 4732-4736

25. Study and Characterization of PECVD Oxides.
S. Sen, S. Annamali, at *Indian Telephone Industries, Ltd., Bangalore, India*, and P. K. Acharya, at *Indian Institute of Technology, Delhi, India*
in Phys. Status Solidi, A 105 (1), 16 Jan. 1988, 171-176

26. Photoenhanced Deposition of Silicon Oxide Thin Films Using a Novel Windowless Internal Nitrogen Discharge Lamp.
S. D. Baker, W. I. Milne, and P. A. Robertson, at *Cambridge University Engineering Department, Cambridge, UK*
in Appl. Phys. A. Solids Surf., 46 (4), Aug. 1988, 243-248

27. Measurement of Strains at Si-SiO_2 Interface.
R. J. Jaccodine and W. A. Schlegel, at *Bell Telephone Laboratories, Inc., Allentown, Pennsylvania*
in J. Appl. Phys., 37 (6), May, 1966, 2429-2434

28. Room Temperature Glow Discharge Deposition of Silicon Oxide from SiH_4 and N_2O.
G. Kaganowicz, V. S. Ban, and J. W. Robinson, at *RCA Laboratories, Princeton, New Jersey*
in J. Vac. Sci. Technol. A, 2 (3), July-Sept. 1984, 1233-1237

29. Plasma-enhanced CVD: Oxides, Nitrides, Transition Metals, and Transition Metal Silicides.
D. W. Hess, at *Department of Chemical Engineering, University of California, and Materials and Molecular Research Division Lawrence Berkeley Laboratory, Berkeley, California*
in J. Vac. Sci. Technol. A 2 (2), Apr.-June 1984, 244-252

30. Effects of Humidity on Stress in Thin Silicon Dioxide Films.
I. Blech and U. Cohen, at *Department of Materials Engineering, Technion, Haifa, Israel*
in J. Appl. Phys. 53 (6), June 1982, 4202-4207

31. Plasma Deposition of Silicon Dioxide and Silicon Nitride Films.
E. P. G. T. van de Ven, at *Philips Research Laboratories, Sunnyvale, California*
in Solid State Technol., Apr. **1981**, 167-171

32. The Effects of Bond Strain on the Properties of Plasma-Deposited Silicon Oxide Films.
M. A. Machonkin and F. Jansen, at *Xerox Webster Research Center, Webster, New York*
in Thin Solid Films, 150 (2-3), 6 Jul. **1987**, L97-99

33. Physics of Semiconductor Devices 2nd Ed.,
S. Sze
1981, 42-43, 59, 852

34. The Optical Constants of Silicon and Dry Oxygen Oxides of Silicon at 5461A.
E. A. Taft, at *General Electric Corporate Research and Development, Schenectady, New York*
in Solid State Sci. and Technol., 125 (6), Jun. **1978**, 967-971

35. A Viscous Flow Model to Explain the Appearance of High Density Thermal SiO_2 at Low Oxidation Temperatures.
E. A Irene, E. Tierney, and J. Angilello, at *IBM Thomas J. Watson Research Center, Yorktown Heights, New York*
in J. Electrochem. Soc., 129 (11), Nov. **1982**, 2594-2597

36. Young's Modulus Measurements of Thin Films Using Micromechanics.
K. E. Petersen and C. R. Guarnieri, at *IBM Research Laboratory, San Jose, California*
in J. Appl. Phys. 50 (11), Nov. **1979**, 6761-6766

37. Stress and Thermal-Expansion Coefficient of Chemical-Vapor Deposited Glass Films.
H. Sunami, Y. Itoh, and K. Sato, at *Central Research Laboratory, Hitachi Ltd., Kokubunji, Tokyo, Japan in* J. Appl Phys. 41 (3), Dec. **1970**, 5115-5117

38. Stress at the Si-SiO_2 Interface and Its Relationship to Interface States.
C. H. Lane, at *Rome Air Development Center, Griffiss Air Force Base, Rome, NY in* IEEE Trans. on Electron. Devices, ED-15 (12), Dec. **1968**, 998-1003

39. The Viscosity of Vitreous Silica.
G. Hetherington, K. H. Jack, and J. C. Kennedy, at *Thermal Syndicate Ltd., Wallsend, England*
in Phys. Chem. Glasses, 5 (5), Oct. **1964**, 130-136

40. Viscous Flow of Thermal SiO_2,
E. P. EerNisse, at *Sandia Laboratories, Albuquerque, NM*
in Appl. Phys. Lett., 30 (6), 15 Mar. 1977, 290-293

41. A Measurement of Intrinsic SiO_2 Film Stress Resulting From Low Temperature Thermal Oxidation of Si.
E. Kobeda, E. A. Irene, at *Deparment of Chemistry, The University of North Carolina, Chapel Hill, North Carolina*
in J. Vac. Sci. Technol. B, 4 (3), May/June 1986, 720-722

42. Thermal Stresses and Cracking Resistance of Dielectric Films (SiN, Si_3N_4, and SiO_2 on Si Substrates).
A. K. Sinha, H. J. Levinstein, and T. E. Smith, at *Bell Laboratories, Murray Hill, NJ*
in J. Appl. Phys., 49 (4), 2423-2426, 1978

43. Index of Refraction of Steam Grown Oxides on Silicon.
E. A. Taft, at *General Electric Company, Corporate Research and Development, Schenectady, NY*
in J. Electrochem. Soc., 127 (4), Apr. 1980, 993-994

44. Stress in Thermal SiO_2 During Growth.
E. P. EerNisse, at *Sandia Laboratories, Albuquerque, NM*
in Appl. Phys. Lett., 35 (1), 1 July 1979, 8-10

45. Residual Stresses at an Oxide-Silicon Interface.
M. V. Whelan, A. H. Goemans, and L. M. C. Goossens, at *Philips Research Laboratories, N. V. Philips' Gloeilampenfabieken, Eindhoven, The Netherlands*
in Appl. Phys. Lett., 10 (10), 15 May 1967, 262-264