REPORT DOCUMENTATION PAGE					
Public reporting burden for this collection of information is estimated to average 1 hour per response, including			AFRL-SR-AR-TR-02-		
gathering and maintaining the data needed, an collection of information, including suggestions Davis Highway, Suite 1204, Arlington, VA 223	for reducing this burden, to Washington He 202-4302, and to the Office of Management	adquarters Services and Budget, Paperw	02	05	
1. AGENCY USE ONLY (Leave bla	nk) 2. REPORT DATE	3. REPOR	EINAL (15 AUC	5 98 - 31 AUG 01)	
4. TITLE AND SUBTITLE			5. FUNI	DING NUMBERS	
ASSERT STUDENT RESEARC	H ON IN-SITU TOUGHENE	D a'-SIALON	F49620	-98-1-0470	
6. AUTHOR(S) I-WEI CHEN					
7. PERFORMING ORGANIZATION	NAME(S) AND ADDRESS(ES)		8. PERF	ORMING ORGANIZATION	
UNIVERSITY OF PENNSYLVANIA					
PHILADELPHIA, PA 19104-32	246				
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) AIR FORCR OFFICE OF SCIENTIFIC RESEARCH 801 N. RANDOLPH STREET ARLINGTON, VA 22203				10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES		<u></u>	<u> </u>		
12a. DISTRIBUTION AVAILABILITY	STATEMENT				
Approved for p distribution	mblic release; unlimited,	•	20020	719 129	
13. ABSTRACT (Maximum 200 wo). The grant was initiated on May 1 in-situ toughened ct-SiAION can rare-earth ion-added composition kinetic data on phase transformat control of nucleation and growth in ci-SiAION prepared from com microstructure control must rely harvest seed crystals, of a control the ceramic to allow tailored gran observed experimentally. We have	<i>ds)</i> 5,1998 and was completed in be obtained. This essentially e is and alkali/alkali-earth ion-ad ion at different compositions, s , which dictate the microstructure amercial a-Si3N4 powders. The on nucleation treatment of exter lled composition, size and mor in growth. We have developed s from the oxynitride liquid. The re developed a wet chemical te	August 2001. W ncompasses the o ded compositions since this knowle are. We have dev ese materials hav ernal seeding. We phology, which o a theory for grain his model success chnique for etchi	e have explored entire single a-ph s. We have made edge is critically veloped methods e faster transform e have developed can be used to m in growth, based sfully predicted t ing the highly sta	the compositions at which hase region. It includes both e a systematic effort to obtain important for the precise for controlling microstructur mation rate and the I the method to grow and ucleate a'-SiAION grains in on the recent observations o he novel shape transition able a'-SiAION, which until	
now has proved difficult for cera exceed I CPa and the strength re- and show that they can reach a to	niographic preparation. We have the sention is good at least up to 13 bughness of 11-12 MPa m1t wh	ve shown that the 50 0C. We have ich compares fav	e mechanical stre obtained R-curv vorably with the	ength of ct-SIAION can es for a'SiAION ccramics, state-of-the-au j3 silicon	
nitride.					
14. SUBJECT TEKMS				16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT	18. SECURITY CLASSIFICATION OF THIS PAGE	19. SECURITY C OF ABSTRA	CLASSIFICATION	20. LIMITATION OF ABSTRAC	
UNCLASSIFIED	UNCLASSIFIED	UNCLA	SSIFIED		

k

N

## I. TITLE OF PROJECT

# AASERT STUDENT RESEARCH ON IN-SITU TOUGHENED $\alpha'$ -SIALON

# TECHNICAL AND FINAL REPORT

AUGUST 15, 1998-AUGUST 31, 2001

### U.S. AIR FORCE GRANT NO. F49620-98-1-0470

PRINCIPAL INVESTIGATOR

### **I-WEI CHEN**

### UNIVERSITY OF PENNSYLVANIA, PHILADELPHIA, PENNSYLVANIA

### II. OBJECTIVES

The objective of this research is to design experiments to expedite the development and understanding of the large family of in-situ toughened  $\alpha$ '-SiAlON that has been recently invented. The underlying premise is that the very large degree of freedom in alloy design for  $\alpha$ '-SiAlON, which encompasses a broad range of composition and processing conditions, can be advantageously focussed by utilizing principles of physical chemistry and statistical design that identify unbiased experimental conditions and facilitate the determination of the cause-effect relations. The subjects to be investigated include the role of interstitial cations (alkali-earth and rare earth), regions of phase field, processing temperature and time, and characteristics of starting powders in the densification, microstructure development and resulting strength and fracture toughness of these ceramics

### **III. STATUS OF EFFORT**

The grant was initiated on May 15, 1998 and was completed in August 2001. We have explored the compositions at which in-situ toughened  $\alpha$ '-SiAlON can be obtained. This essentially encompasses the entire single  $\alpha$ '-phase region. It includes both rare-earth ion-added compositions and alkali/alkali-earth ion-added compositions. We have made a systematic effort to obtain kinetic data on phase transformation at different compositions, since this knowledge is critically important for the precise control of nucleation and growth which dictate the microstructure. We have developed methods for controlling microstructure in  $\alpha$ '-SiAlON prepared from commercial  $\alpha$ -Si<sub>3</sub>N<sub>4</sub> powders. These materials have faster transformation rate and the microstructure control must rely on nucleation treatment of external seeding. We have developed the method to grow and harvest seed crystals, of a controlled composition, size and morphology, which can be used to nucleate  $\alpha$ '-SiAlON grains in the ceramic to allow tailored grain growth. We have developed a theory for grain growth, based on the recent observations of the morphology of isolated grains from the oxynitride liquid. This model successfully predicted the novel shape transition observed experimentally. We have developed a wet chemical technique for etching the highly stable  $\alpha$ '-SiAlON, which until now has proved difficult for ceramographic preparation. We have shown that the mechanical strength of  $\alpha$ '-SiAlON can exceed 1 GPa and the strength retention is good at least up to 1350 °C. We have obtained R-curves for  $\alpha$ '-SiAlON ceramics, and show that they can reach a toughness of 11-12 MPa m<sup>1/2</sup>, which compares favorably with the state-of-the-art  $\beta$  silicon nitride.

# IV. ACCOMPLISHMENTS/NEW FINDINGS

### Nucleation Control of Microstructure

The essence of microstructure control that enables the formation of in-situ toughened a'-SiAION is to control nucleation of  $\alpha'$  phase so that relatively few nuclei compete for growth. There are three general ways to achieve this goal. First, starting powders can be chosen to be energetically more stable or crystallographically less similar to the product phase. This implies that  $\beta$ - Si<sub>3</sub>N<sub>4</sub> powders are better as the starting powders. The second method is to choose a composition with less stability for

the  $\alpha'$  phase. This dictates the choice of larger cations or compositions near the phase boundary. An extension of the second approach is to take advantage the temperature dependence of the phase stability. This dictates the use of lower temperature for nucleation or use different heating rates to manipulate nucleation and growth. We have demonstrated that these three approaches, individually or in combination, with various conceivable variations, can be practiced to render any single phase  $\alpha'$ -SiAlON composition amenable to obtaining a fibrous microstructure.

We have found that for highly stable single phase  $\alpha$ '-SiAlON compositions the above approaches are more difficult to practice because the driving force is too large and nucleation rate too fast. In such a case, we have introduced seed crystals of single phase  $\alpha$ '-SiAlON composition to predetermine the nucleation statistics. This approach has proved successful. As a result, we are now able to obtain high toughness single phase  $\alpha$ '-SiAlON ceramics of any composition using either  $\alpha$  or  $\beta$ -Si<sub>3</sub>N<sub>4</sub> powders.

A parallel effort has been made to prepare  $\alpha$ '-SiAlON seeds of an appropriate size and shape. It is noted that, to be effective, seeds must have the same composition of the final phase, or have a composition that is thermodynamically more stable. This is a difficult task compared with the other seeding efforts reported in the literature, where the seeding can be provided simply by using compounds of an appropriate phase, e.g.  $\beta$ -Si<sub>3</sub>N<sub>4</sub> or  $\alpha$  SiC. In our case, such compounds invariably dissolve, so the seeds need to have a composition that is stable, i.e., it should be an  $\alpha$ -Si<sub>3</sub>N<sub>4</sub> solid solution itself. This task has been successful and a method for obtaining high-yield seed crystals of a variety size, shape and compositions have been developed. The physical chemistry of seed formation and growth has been investigated. In particular, the effect of different dopant cations has been determined.

Our research on  $\alpha'$ -SiAlON has also systematically explored the difference between compositions involving (a) rare earth cations of different sizes and (b) alkali and alkali earth cations, primarily Li and Ca. The stability of the single phase  $\alpha'$ -SiAlON varies significantly and this has a major impact on the phase nucleation and microstructural development of the ceramics. In addition, the kinetics are influenced by the different liquid viscosity due to the presence of different cations as well as the different interface characteristics due to the segregation of dopants. By controlling these factors separately, it is now possible to obtain the desired microstructure for all the rare-carth cation  $\alpha'$ -SiAlON and for Ca- $\alpha'$ -SiAlON.

### Mechanical Properties of *a*-SiAlON

We have investigated the mechanical properties of  $\alpha$ -SiAlON using three methods. Preliminary hardness and toughness data were obtained using the indentation method. Although toughness is usually underestimated by this method, the systematic trend between ceramics of different compositions and different microstructures is usually preserved. A more systematic investigation has been made using R-curve measurements. This was performed in-situ under a microscope in the four-point bending configuration. The R-curves show a very strong correlation with the microstructure and are sensitive to the compositions. The values at small crack

3

extension, approximately 50-100  $\mu$ m, appear to correspond well to the values of indentation toughness. Very high toughness of 11-12 MPa m<sup>1/2</sup> is seen in some microstructures, which compares favorably with the toughness of in-situ toughened  $\beta$ -silicon nitride. This method is particularly powerful in evaluating the influence of seeding and heat treatment on the mechanical properties. Finally, three-point bending has been performed to obtain strength data at room temperature and elevated temperatures, up to 1350 °C. Strength values exceeding 1 GPa have been obtained in some ceramics, which can be retained (up to 70%) at high temperatures. Optimization of the strength-toughness combination seems possible and has been attempted by using minor dopants and heat treatment. Further major progress in this area is anticipated in the next few years based on our preliminary findings.

#### Thermodynamics of Anisotropic Si<sub>3</sub>N<sub>4</sub> Crystals

The recent observation of Wang, Tien and Chen on  $\beta$ - Si<sub>3</sub>N<sub>4</sub> showed that an elongated rod grown from the liquid can have a concave end. Such morphology implies that material transport must come from the corner, and it in turns implies long range diffusion along the side surface or in a boundary layer near the side surface. Interface control is obviously an important factor in directing growth anisotropy. We have developed a thermodynamic theory for the chemical potential of surface atoms of an anisotropic crystal, with and without facet, under equilibrium and non-equilibrium conditions. The equilibrium shape has been obtained, and criterion for shape evolution has also been formulated. Using this theory, the evolution of the aspect ratio of grains during phase transformation and Ostwald ripening can now be understood. In addition, the case of interface control can also be rigorously treated with respect to the underlying equilibrium conditions to account for different growth scenarios. This theory has been extended to silicon carbide as well. Further experimental effort to determine the growth kinetics and the shape evolution has been made and the results have revealed the importance of compositional evolution during the precipitation and ripening process.

#### Microstructure Determination of $\alpha'$ -SiAlON

We have developed a new chemical etching technique that reveals the microstructure clearly under a light microscope. The new technique takes advantage of the bonding difference between nitride and oxide to differentially dissociate the Si-O-Si bond and the Si-N-Si bond. Alternatively, the nitrogen bond can be converted to oxygen bond resulting in a large change in refractive index. This technique makes it feasible to perform quantitative microscopy using image analysis softwares.

A new development in quantifying the microstructure of anisotropic grains has been made. Such microstructure must rely upon information on two-dimensional cross sections. Previous methods measured rectangular shapes on such cross sections; the statistics of such shapes are compared, using reverse transformation, with postulated three-dimensional shape statistics. We have shown that a linear intercept method works equally well for self-similar shapes. The advantage to the linear intercept method is that it is much faster for data collection, and it has much better sampling statistics.

4

- M. Zenotchkine, R. Shuba, J-S. Kim and I-Wei Chen, "R-Curve Behavior of Insitu Toughened a-SiAlON Ceramics," J. Am. Ceram. Soc., 84 [4] 884-86 (2001).
- (k) M. Zenotchkine, 'R. Shuba, J-S. Kim and I-Wei Chen, "Synthesis of α-SIALON Seed Crystals," J. Am. Ceram. Soc., 84 [7] 1651-53 (2001).
- I-W. Chen and R. Shuba, "Structure and Property of SiAlON Ceramics", to appear in Encyclopedia of Materials: Science and Technology, ed. K.H.J. Baschow, R.W. Cahn, M.C. Flemings, B. Ilschner, E.J. Kramer and S. Mahajan, Elsevier Science Ltd. Oxford, UK (2001).
- (m) A. Pechenik and I-W. Chen, "Advanced Silicon Nitride Ceramics", Advanced Materials and Processing, p. 37, March (2001).

### VII. INVITED TALKS BY PI

- (a) "Innovations in Processing of Structural Ceramics with High Aspect Ratio Features," International Symposium on Novel Synthesis and Processing of Ceramics, Kurume, Japan, October 1997.
- (b) "Paradigms of Innovations in Materials Research," plenary lecture, Annual Meeting of the Chinese Society for Materials Science, Tainan, Taiwan, November 1997.
- (c) "Phase Relations and Phase Stability in SiAION Systems," Annual Meeting of the American Ceramic Society, Cincinnati, OH, May 1998.
- (d) "Silicon Nitride at sub 1400 °C--Issues and Possible Solutions," Workshop on Ultra High Temperature Ceramics, May 1998, Boulder, CO, May 1998.
- (e) "Silicon Nitride -- A Matter of Kinetics," Conference on New Developments in High Temperature Ceramics, Istanbul, Turkey, August 1998.
- (f) "Silicon Nitride and SiAlON," plenary lecture at the First International Conference on Inorganic Materials, Versailles, France, September 1998.
- (g) "Innovations in Structural Ceramics and Composites," Brown University, Providence, April 1999.
- (h) "Using Silicon Nitride Based Ceramics at High Temperatures," ASME Meeting, Nashville, TN, November 1999.
- (i) "In Search of Ceramic Steel," Department of Materials Science and Engineering, University of California-Berkeley, January 2001.

### VIII. TRANSITIONS, PATENTS, AND HONORS

Samples of in-situ toughened  $\alpha$ '-SiAlON have been provided to a leading US cutting tool manufacturer and a leading German cutting tool manufacturer to evaluate their cutting performance. This evaluation process is on-going as the cutting applications are material specific, depending on the work piece as well as the tool. Thus, composition, microstructure and property optimization is required for each cutting application.

Two patents have been issued by the US Patent Office. (No. 5,908,798, "In-situ Toughened Alpha Prime Sialon Based Ceramics," by I-Wei Chen and Anatoly Rosenflanz; and No. 6,139,791, "Method of Making In-situ Toughened Alpha Prime Sialon Based Ceramics," by I-Wei Chen and Anatoly Rosenflanz.)

Collaborative research with Prof. R. Riedel of Damstadt Technical University of Germany has resulted in the discovery of a new structure of solid solution of Si-Al-O-N. A patent application has been filed with Prof. Chen as a co-inventor.