



Evaluation of a Foreign Silicon Nitride as a Potential Gun Barrel Liner

**by Jeffrey J. Swab, Dominic Danna, Charles Leveritt,
and Stephanie Piraino**

ARL-TR-5146

April 2010

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5069

ARL-TR-5146

April 2010

Evaluation of a Foreign Silicon Nitride as a Potential Gun Barrel Liner

Jeffrey J. Swab and Stephanie Piraino
Weapons and Materials Research Laboratory, ARL

Dominic Danna
Oak Ridge Institute for Science and Engineering
Oak Ridge, TN 37831

Charles Leveritt
Advocate Wood
Harford County, MD 21084

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188		
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY) April 2010		2. REPORT TYPE Final		3. DATES COVERED (From - To) June 2008–August 2009	
4. TITLE AND SUBTITLE Evaluation of a Foreign Silicon Nitride as a Potential Gun Barrel Liner			5a. CONTRACT NUMBER 622618AH80		
			5b. GRANT NUMBER		
			5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S) Jeffrey J. Swab, Dominic Danna, Charles Leveritt, and Stephanie Piraino			5d. PROJECT NUMBER		
			5e. TASK NUMBER		
			5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: RDRL-WMM-E Aberdeen Proving Ground, MD 21005-5069			8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-5146		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)			10. SPONSOR/MONITOR'S ACRONYM(S)		
			11. SPONSOR/MONITOR'S REPORT NUMBER(S)		
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT A silicon nitride (Si ₃ N ₄) ceramic manufactured by FCT Technologie GmbH, Rauenstein, Germany was subjected to a series of tests (mechanical, physical, thermal, and erosion) to determine if this material might have potential applications as gun barrel liners. The tests conducted were similar to earlier tests performed by the U.S. Army Research Laboratory (ARL) on a variety of ceramic materials, including silicon nitride, for the same application. The erosion behavior was comparable to the previously tested ceramics but the mechanical and thermal properties were inferior making it unlikely that it would survive the interior ballistic conditions of a gun barrel.					
15. SUBJECT TERMS Silicon nitride, gun barrel liner, strength, fracture toughness					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON Jeffrey J. Swab
a. REPORT UNCLASSIFIED	b. ABSTRACT UNCLASSIFIED	c. THIS PAGE UNCLASSIFIED			UU

Contents

List of Figures	iv
List of Tables	iv
1. Summary	1
1.1 Purpose/Scope	1
1.2 Key Findings	1
2. Introduction	1
3. Material	3
4. Test Methodology	3
4.1 Mechanical Properties	3
4.2 Thermal Properties	4
4.3 Erosion Testing.....	5
5. Results	6
6. Conclusions	9
7. References	10
Appendix. Mechanical Property Data	13
Distribution List	17

List of Figures

Figure 1. Material data sheet provided by the manufacturer with the material. The Si_3N_4 evaluated in this effort is the gas pressure sintered (GPS) labeled FSNI highlighted by red box.....	2
Figure 2. Gun used for blow-out tests.....	5
Figure 3. Nozzle assembly for the blow-out gun test. Dimensions are in inches.	6
Figure 4. Example of a pore as the strength-limiting flaw. White arrow shows that the pore is located just beneath the tensile surface of this c-ring specimen. Specimen strength was 565 MPa.....	7
Figure 5. Images of FCT nozzle #1 before and after erosion testing.....	8
Figure 6. Images of FCT nozzle #2 after erosion testing.....	9

List of Tables

Table 1. Mechanical and thermal properties summary.....	7
Table 2. Summary of the mass loss/shot for FCT Si_3N_4	8
Table A-1. Room temperature tensile strength data.	14
Table A-2. Room temperature c-ring strength data.	14
Table A-3. Room temperature o-ring strength data.	15
Table A-4. O-ring strength data at 700 °C.....	15
Table A-5. Chevron notch fracture toughness data.	16
Table A-6. Vickers hardness data at 300 g indention load.	16

1. Summary

1.1 Purpose/Scope

In this study a silicon nitride ceramic manufactured by a German company was subjected to a series of tests (mechanical, physical, thermal, and erosion) to determine if this material might have potential applications as gun barrel liners. The tests conducted were similar to earlier tests performed by the U.S. Army Research Laboratory (ARL) on a variety of ceramic materials, including silicon nitride, for the same application.

1.2 Key Findings

This silicon nitride performed quite well in the erosion testing. It exhibited a very low mass loss per test, which is in excellent agreement with other silicon nitrides previously subjected to the same erosion test procedure and parameters. However, when the mechanical and thermal properties of this Si_3N_4 are compared to the previously evaluated silicon nitrides and SiAlONs, it is inferior. The lower strength and toughness makes it unlikely that this Si_3N_4 would be able to handle the pressure and temperature profiles present during the interior ballistic event.

2. Introduction

The Army has a desire to develop lighter weight gun barrels with longer lifecycles that can handle the new high energy propellants currently available or under development. The steel barrels used in many systems have a short lifecycle and are susceptible to rapid and severe degradation when exposed to these new high-energy propellants. Ceramic materials have long been considered as a potential solution to these issues (1–5). It is anticipated that ceramic gun barrel liners will provide a 50% increase in barrel life with sustained accuracy for direct and indirect fire, enable a 20% increase in muzzle kinetic energy for direct fire, and provide a 5–25% weight reduction (per unit length of barrel) because of the combination of superior wear resistance, high temperature capability, and relatively low density that are inherent to ceramic materials. The development of a ceramic gun barrel will reduce maintenance costs while serving as an enabling technology for the use of higher energy propellants.

ARL completed a number of studies which have examined a variety of commercially-available ceramics for gun barrel applications (6–14). The ceramics examined included alumina (Al_2O_3), zirconia (ZrO_2), silicon carbide (SiC), silicon nitride (Si_3N_4) and silicon-aluminum oxynitride (SiAlON). These studies clearly identified the silicon nitride/SiAlON family of materials as the most promising for applications as gun barrel liners across a wide range of calibers.

In this study a Si₃N₄ ceramic manufactured by a company in Germany was subjected to tests similar to the ones used to evaluate the earlier silicon nitride ceramics (6) in order to determine if it also might be applicable for gun barrel applications. According to the manufacturer's property data sheet, figure 1, this Si₃N₄ has property values similar to the previously evaluated Si₃N₄ ceramics (6). The property values determined for this Si₃N₄ will be compared to the data already available on Si₃N₄.

FCT Ingenieurkeramik GmbH
FCT Group

Gewerbepark 11
96528 Rauenstein
Germany

Phone: +49 (0) 3 67 66 / 8 68 - 0
Fax: +49 (0) 3 67 66 / 8 68 - 68
ingenieurkeramik@fct-keramik.de



Material	HPSN		GFSN		GPSN	HPSN	NSIC	SSIC	LPSIC	
	HP	HP	ISO	SG	TiN	BN				
Sintering process			GPS	GPS	GPS	HP	RS	S	LPS	
FCT-grade	FHNM	FHNY	FSNI	FSNS	FSNT	FSNB	FSNC	FSC	FSCL	
Microstructure										
Bulk density	[g/cm ³]	3,22	3,23	3,26	3,21	4,35	2,4-3,0	2,8	3,15	3,25
Open porosity	[%]	0	0	0	0	0	2-12		<3	<1
Mechanical Properties										
Compressive strength	[MPa]	2.600	3.000	3.000	2.500	3.000	1.000	600	2.500	3.000
Bending strength σ RT	[MPa]	700	850	750	650	850	500	180	400	500
1.200 °C	[MPa]	450	500	450	400				400	450
Weibull modulus m		>18	>20	>20	>20	>20	>20	20	15	15
Fracture toughness K _{IC}	[MPa.m ^{1/2}]	7	8	8	7	8	9	4	3,5	5
Youngs modulus E	[GPa]	315	320	320	310	350	250	220	400	410
Poisson Ratio ν		0,29	0,28	0,28	0,28	0,20	0,25	0,20	0,20	0,20
Hardness (Vickers)	[GPa]	16	16	16	16	18			26	23
Thermal properties										
Max. working temp.										
- inert gas	[°C]	1.200	1.200	1.200	1.200	1.200	1.400	1.800	1.900	1.600
- air	[°C]	1.200	1.200	1.100	1.100	1.000	1.000	1.400	1.650	1.500
T melting/decomposition	[°C]	1.600	1.600	1.600	1.600	1.600	1.600	1.600	2.400	2.300
Thermal conductivity λ RT	[W/mK]	30	30	30	30	30	50	20	100	90
CTE α	[10 ⁻⁶ /K]	3,2	3,2	3,2	3,2	6,0	3,0	5,0	4,5	5,0
Thermal shock param. R ₁	[K]	495	598	527	472	324	500	110	177	195
Thermal shock param. R ₂	[W/m]	14.839	17.930	15.820	14.150	9.714	25.000	2.530	17.700	17.560
Electrical properties										
spec. resistance RT	[Ωcm]	10 ¹⁰	10 ¹⁰	10 ¹¹	10 ¹¹	10 ⁵	10 ¹⁰		10 ¹	10 ⁵
1.000 °C	[Ωcm]	10 ⁷	10 ⁷	10 ⁷	10 ⁷					

Production of components

We produce ceramic components by cold isostatic pressing or slip casting of preforms, then subsequent green machining by turning, milling, drilling cutting with conventional and CNC- equipment before firing.

FCT Ingenieurkeramik offers the economic production of components with large dimensions, high complexity and narrow tolerances as prototype and in series. Diameters up to 450 mm and lengths up to 1300 mm were already produced and are state of the art.

We help you with materials selection, design and implementation into a metallic, refractory or plastic aggregate.

We produce components corresponding to customers design from different gas pressure sintered and hot pressed silicon nitride, nitride bonded silicon carbide and sintered, recrystallized and C-fiber-reinforced silicon carbide composites.

For very specific applications we even develop tailor made materials according to your requirements.

Services

Additionally we offer services in sintering, hot pressing, cold isostatic pressing and ceramic processing.

Figure 1. Material data sheet provided by the manufacturer with the material. The Si₃N₄ evaluated in this effort is the gas pressure sintered (GPS) labeled FSNI highlighted by red box.

3. Material

The silicon nitride material to be evaluated was purchased from FCT Technologie GmbH, Rauenstein, Germany (FCT). It is fabricated using a GPS technique. Material was obtained from the manufacturer in three different geometries to facilitate the machining of the different test specimens required. Tubes 200-mm long with a nominal inner (Di) and outer (Do) diameters of 24 mm and 33 mm, respectively, as well as two different cylinders: one 80-mm long with a 30-mm diameter and the other 150-mm long with a 20-mm diameter, were purchased.

4. Test Methodology

4.1 Mechanical Properties

Three different specimens were prepared and used to determine the strength of each ceramic. Uniaxial tension tests were used in an attempt to promote the volume-distributed flaws in the material while c-ring and o-ring tests highlighted the surface-distributed flaws on the outer and inner diameter respectively.

Cylindrical button-head tensile specimens were machined from the 150-mm long cylinders to the gage section dimensions listed in figure 9 of ASTM C1273 (15) with an overall specimen length of 135 mm. The room temperature uniaxial strength was determined using 10 specimens following the guidelines and equations in ASTM C1273 (15). The uniaxial tensile strength was calculated using equation 1:

$$S_u = \frac{P_{\max}}{A}, \quad (1)$$

where S_u is the tensile strength, P_{\max} is the breaking load, and A is the cross sectional area of the specimen.

C-ring specimens having a width of 8 mm with longitudinal 45° chamfers to a distance of 0.15 mm on the Do, and a slot height of 5.7 mm were machined from the tubular components and tested at room temperature in accordance with ASTM C1323 (16). A displacement rate of 0.5 mm/min was used to compressively and diametrically load the specimens to failure. A thin (0.005-in) graphite sheet was placed between the upper and lower contact locations to minimize the likelihood of contact-induced fracture. The geometry and failure loads were used to calculate the hoop or Do tangential failure stress ($\sigma_{\theta\max}$) for each specimen according to the strength of materials solution in ASTM C1323:

$$\sigma_{\theta \max} = \frac{PR}{btr_o} \left[\frac{r_o - r_a}{r_a - R} \right], \quad (2)$$

where P is the failure load, $R = (r_o - r_i) / \ln(r_o / r_i)$, r_o is the outer c-ring radius, r_i is the inner c-ring radius, r_a is the average of r_o and r_i , b is width, and t is thickness or $r_o - r_i$.

The o-ring specimens were also machined from the tubular component to the same dimensions as the c-ring specimens but without a notch and with the chamfers on the Di of the specimen instead of the Do. These specimens were tested at room temperature and at 700 °C at a displacement rate of 0.5 mm/min. A 0.005-in thick graphite sheet was placed between the specimen and loading platens for testing at both temperatures. The specimens used in the high temperature testing were placed in the furnace and heated to temperature at a rate of 20 °C/min. Once at temperature each specimen was allowed to soak for 10 min to allow for thermal equilibrium to be achieved prior to the application of the load. The Di tangential failure stress ($\sigma_{\theta \max}$) at both temperatures was calculated using equation 3:

$$\sigma_{\theta \max} = \frac{P}{2} \left[0.637 \frac{r_a (r_a - r_i)}{bt^3 / 12} \right]. \quad (3)$$

The variables have been defined previously for the c-ring specimens.

Each set of raw strength data was subsequently analyzed using a two-parameter Weibull regression according to ASTM C1239 (17). This analysis yielded a biased Weibull modulus and characteristic strength.

Fracture toughness was determined using the procedures and equations in ASTM C1421 (18). Chevron notch specimens, nominally 3 mm×4 mm×50 mm in size with the D configuration notch ($a_o = 1.40 \pm 0.07$ mm), were machined and then were fractured in three- or four-point bending. The fracture toughness (K_{Ivb}) was calculated using:

$$K_{Ivb} = Y_{\min}^* \left[\frac{P_{\max} (S_o - S_i) 10^{-6}}{bw^{3/2}} \right], \quad (4)$$

where Y_{\min}^* is the minimum stress intensity factor, P_{\max} is the relevant maximum load that occurs during stable crack propagation, S_o and S_i are outer and inner support spans, respectively, b is the specimen width, and w the specimen height.

The Vickers hardness (H_v) was determined at room temperature using an indentation load of 300 g.

4.2 Thermal Properties

The thermal conductivity, heat capacity and coefficient of thermal expansion were determined between room temperature and 1000 °C. ASTM E1461 (19) and ASTM C714 (20) were used to

obtain thermal diffusivity and heat capacity values using the laser flash method. A thermal conductivity was calculated from these values. The linear coefficient of thermal expansion was obtained using a prismatic specimen nominally 3 mm×4 mm×25 mm in size. Tests were conducted in a dual-rod dilatometer using a heating rate of 1 °C/min following the procedure outlined in ASTM E228 (21). The data collection rate for this test was two datapoints/°C.

4.3 Erosion Testing

The test used to simulate the interior ballistic conditions was a blow-out gun, figure 2. In this test the ceramic was exposed to interior ballistic conditions (temperature, pressure, etc.) created using JA-2 propellant (flame temperature–3420 K, impetus–1144 J/g). A ceramic nozzle was machined and placed in a steel surround, figure 3, creating a test piece that could be inserted into the gun. The nozzle was exposed to one shot then cleaned and weighed. The mass loss was determined and compared to the mass loss experienced by typical gun steel and the previously tested Si₃N₄ exposed to the same conditions. Each nozzle tested was exposed to a total of six shots.



Figure 2. Gun used for blow-out tests.




Figure 3. Nozzle assembly for the blow-out gun test. Dimensions are in inches.

5. Results

The results of the mechanical and thermal property testing are summarized in table 1 with the individual data points listed in the appendix. While the FCT material possesses a hardness value and thermal properties very similar to the $\text{Si}_3\text{N}_4/\text{SiAlON}$ materials evaluated previously, it is inferior to these same materials when strength and fracture toughness are considered. Irrespective of the strength methodology employed there are two dominant flaw populations present in the material. One was a volume-distributed pore and the other was cracks or damage related to the surface finish. The pores, see figure 4, were essentially circular in shape with a diameter between 50 and 80 μm and were always located in the bulk of the specimen. The other flaw populations was always located at the specimen surface and due to either the machining process used to create the specimens for testing (for example, the chamfers machined on the c- or o-ring specimens) or the surface finish provided by the manufacturer. In the later instance the manufacturer was only provided the dimensional tolerances for the inner and outer diameter of tubes and not the procedure to achieve these dimensions or a requisite final surface finish. As a result, there were a number of specimens machined from these tubes that failed due to damage (cracks) imparted during the manufacturer's finishing process.

Table 1. Mechanical and thermal properties summary.

Density (g/cm³)	3.27
Ave. Tensile Strength (MPa)	455 ± 146
Weibull Modulus	4.1
Ave. C-ring Strength (MPa)	582 ± 60
Weibull Modulus	12.8
Ave. O-ring Strength @ RT (MPa)	583 ± 50
Weibull Modulus	16.4
Ave. O-ring Strength @ 700°C (MPa)	466 ± 57
Weibull Modulus	8.7
K_{Ic} (MPa*√m) (Chevron Notch)	5.7 ± 0.1
Hardness (Hv) – 300g (GPa)	13.3 ± 0.3
Thermal Conductivity (W/m-K) 25°C - 1000°C	25.2 - 14.2
Heat Capacity (J/g-K) 25°C - 1000°C	0.7 - 1.3
Ave. Coefficient of Thermal Expansion (25°C - 1000°C)	2.1 - 3.6




Figure 4. Example of a pore as the strength-limiting flaw. White arrow shows that the pore is located just beneath the tensile surface of this c-ring specimen. Specimen strength was 565 MPa.

The results from the erosion testing are summarized in table 2. The data shows that the Si₃N₄ nozzle experiences a small and consistent mass loss with each shot. Additionally, there was no

change in the diameter of the nozzle throat with each test shot but there was evidence of heat checking and discoloration of the front and back sides of both nozzles, see figures 5 and 6. The physical and structural integrity of both nozzles was maintained throughout the testing. These findings are in agreement with previous erosion testing results on other Si₃N₄/SiAlON materials (7).

Table 2. Summary of the mass loss/shot for FCT Si₃N₄.

Shot #	Nozzle #1 Mass Loss (mg)	Nozzle #2 Mass Loss (mg)
1	0.2	+2.1
2	2.6	2.8
3	3.4	2.2
4	2.8	3.0
5	3.3	4.5
6	4.3	3.4
Average	2.8	2.3




Figure 5. Images of FCT nozzle #1 before and after erosion testing.




Figure 6. Images of FCT nozzle #2 after erosion testing.

6. Conclusions

This Si_3N_4 performed quite well in the erosion testing. It exhibited a very low mass loss per test, which is in excellent agreement with other silicon nitrides previously subjected to the same erosion test procedure and parameters. However, when the mechanical and thermal properties of this Si_3N_4 are compared to the previously evaluated silicon nitrides and SiAlONs it is inferior. The lower strength and toughness makes it unlikely that this Si_3N_4 would be able to handle the pressure and temperature profiles present during an interior ballistic event.

7. References

1. Giles, R.; Bunning, E.; Claxton, D. *Feasibility of Ceramic Lined Gun Tube*; ARLCD-CR-80058; U. S. Army Armament Research and Development Command, prepared by Maremont Corporation: Saco, ME, 1981.
2. Katz, R. N. Ceramic Gun Barrel Liners: Retrospect and Prospect. *Proceedings of the Sagamore Workshop on Gun Barrel Wear and Erosion*, sponsored by the U.S. Army Research Laboratory: Wilmington, DE, 1996; pp. 69–84.
3. SACO Defense, *Advanced Materials Gun System Program–Phase I Final Technical Report*, Government Contract No. DAAA21-88-C-0037, U.S. Army Armament Research, Development and Engineering Center: Picatinny Arsenal, NJ, May 1988–August 1989.
4. SACO Defense, *Advanced Materials Gun System Program–Phase II Final Report*, Government Contract No. DAAA21-88-C-0037, U.S. Army Armament Research, Development and Engineering Center: Picatinny Arsenal, NJ, August 1992.
5. SACO Defense, *Advanced Materials Gun System Program–Phase III Final Report*, Government Contract No. DAAA21-88-C-0037, U.S. Army Armament Research, Development and Engineering Center: Picatinny Arsenal, NJ, February 1995.
6. Swab, J. J.; Wereszczak, A. A.; Tice, J.; Caspe, R.; Kraft, R. *Mechanical and Thermal Properties of Advanced Ceramics for Gun Barrel Applications*; ARL-TR-3417; U.S. Army Research Laboratory: Aberdeen Proving Ground, MD, February 2005.
7. Swab, J. J.; Szewcyk, S.; Leveritt, C.; Van Akin, D. A.; Mossey, C.; Hellmann, J.; Homan, B.; Conroy, P.; Vigilante, G. *Ceramic/Propellant Interactions in a Gun Barrel Environment*; ARL-TR-4349; U.S. Army Research Laboratory: Aberdeen Proving Ground, MD, January 2008.
8. Woodruff, A. K.; Hellmann, J. *Characterization of Long SiAlON Ceramic Tubes for Gun Barrel Applications*; ARL-CR-573; U.S. Army Research Laboratory: Aberdeen Proving Ground, MD, June 2006.
9. Burton, L.; Swab, J. J.; Emerson, R.; Carter, R. Ceramic Gun Barrel Technology; Flis, W.; Scott, B., Eds.; *22nd International Symposium on Ballistics*, Vol. 1; DEStech Publications Inc.: Lancaster, PA, 2005; pp. 251–258.
10. Carter, R. H.; Underwood, J. H.; Swab, J. J.; Emerson, R.; Wereszczak, A. A.; Leveritt, C. Material Selection for Ceramic Gun Tube Liner. *Materials and Manufacturing Processes–Special Issue on the 2005 Gun Barrel Materials & Manufacturing Symposium*, 21 (6); June 2006; pp. 584–590.

11. Carter, R. H.; Swab, J. J. Internal Pressure Testing of Structural Ceramic Tubes. *Ceram. Eng. Sci. Proc.* **2004**, 25 (4), 295–300.
12. Durrett, M.; Shin, Y. C.; Tian, Y. *Laser-Assisted Machining Applied to Rifling of Ceramic Barrels*; ARL-CR-571; U.S. Army Research Laboratory: Aberdeen Proving Ground, MD, March 2006.
13. Christou, K.; Hida, G. *SiAlON for Monolithic Ceramic Gun-Barrel Liners*; ARL-CR-572; U.S. Army Research Laboratory: Aberdeen Proving Ground, MD, June 2006.
14. Withers, J. C. *Silicon-Nitride-Based Ceramic Tubes for Gun Barrel Applications*; ARL-CR-618; U.S. Army Research Laboratory: Aberdeen Proving Ground, MD, December 2008.
15. ASTM C1273. Standard Test Method for Tensile Strength of Monolithic Advanced Ceramics at Ambient Temperatures. *Annu. Book ASTM Stand.* **2003**, Vol. 15.01.
16. ASTM C1323. Standard Test Method for Ultimate Strength of Advanced Ceramics with Diametrically Compressed C-Ring Specimens at Ambient Temperatures. *Annu. Book ASTM Stand.* **2002**, Vol. 15.01.
17. ASTM C1239. Standard Practice for Reporting Uniaxial Strength Data and Estimating Weibull Distribution Parameters for Advanced Ceramics. *Annu. Book ASTM Stand.* **2003**, Vol. 15.01.
18. ASTM C1421. Standard Test Methods for Determination of Fracture Toughness of Advanced Ceramics at Ambient Temperatures. *Annu. Book ASTM Stand.* **2003**, Vol. 15.01.
19. ASTM E1461. Standard Test Method for Thermal Diffusivity of Solids by the Flash Method. *Annu. Book ASTM Stand.* **2003**, 15.01.
20. ASTM C714. Standard Test Method for Thermal Diffusivity of Carbon and Graphite by a Thermal Pulse Method. *Annu. Book ASTM Stand.* **2003**, Vol. 05.05.
21. ASTM E228. Standard Test Method for Linear Thermal Expansion of Solid Materials with a Vitreous Silica Dilatometer. *Annu. Book ASTM Stand.* **2003**, Vol. 14.02.

INTENTIONALLY LEFT BLANK.

Appendix. Mechanical Property Data

Table A-1. Room temperature tensile strength data.

Specimen #	Length (mm)	Diameter (mm)	Radius (mm)	Area (mm ²)	Fracture Load (N)	σ_{MAX} (MPa)
FCT-1	150	6.283	3.142	31.00	7505.0	242.1
FCT-2	150	6.309	3.155	31.26	8575.0	274.3
FCT-3	150	6.314	3.157	31.31	15196.4	485.3
FCT-4	150	6.286	3.143	31.03	15064.3	485.4
FCT-5	150	6.286	3.143	31.03	17093.0	550.8
FCT-6	150	6.302	3.151	31.19	17940.2	575.1
FCT-7	150	6.309	3.155	31.26	18655.4	596.8
FCT-8	150	6.318	3.159	31.35	18605.6	593.5
FCT-9	150	6.355	3.178	31.72	9228.2	290.9
Average:						454.9
STD:						145.6

Table A-2. Room temperature c-ring strength data.

Specimen #	Do (mm)	Di (mm)	Slot (mm)	Thickness, b (mm)	Width, t (mm)	Load (N)	σ_{MAX} (MPa)
FCT-7-1	33.05	24.02	6.14	7.99	4.515	1263.51	564.7
FCT-7-2	33.04	24.04	6.14	7.98	4.500	1209.90	545.5
FCT-7-3	33.06	24.05	6.13	7.98	4.505	1351.79	608.3
FCT-7-4	33.05	24.04	6.15	7.97	4.505	1344.22	605.4
FCT-7-5	33.04	24.03	6.14	7.94	4.505	1288.23	582.2
FCT-7-6	33.04	24.05	6.13	7.98	4.495	1292.48	584.2
FCT-9-1	33.02	23.96	6.14	7.97	4.530	1178.98	523.5
FCT-9-2	33.06	23.96	6.11	7.97	4.550	1221.33	537.6
FCT-9-3	33.02	23.97	6.14	7.96	4.525	1156.77	515.6
FCT-9-4	33.02	23.96	6.14	7.97	4.530	946.39	420.2
FCT-9-5	33.02	23.95	6.11	7.96	4.535	1366.11	605.8
FCT-9-6	33.01	23.99	6.11	7.97	4.510	1424.10	638.7
FCT-9-7	33.01	23.97	6.12	7.96	4.520	1514.63	676.6
FCT-10-1	33.04	24.06	6.15	7.97	4.490	1394.57	632.8
FCT-10-2	33.04	24.02	6.13	7.97	4.510	1349.68	606.1
FCT-10-3	33.04	24.02	6.15	7.98	4.510	1428.29	640.6
FCT-10-4	33.03	24.04	6.13	7.98	4.495	1250.94	565.2
FCT-10-5	33.04	24.02	6.15	7.98	4.510	1391.73	624.2
Average:						582.1	
STD:						59.5	

Table A-3. Room temperature o-ring strength data.

Specimen #	Do (mm)	Di (mm)	B (mm)	Fracture Load (N)	σ_{MAX} (MPa)
FCT-3-1	33.10	24.04	7.96	3407.6	569.5
FCT-3-2	33.01	24.05	7.97	3577.2	609.6
FCT-3-3	33.01	24.03	7.96	3700.1	628.3
FCT-3-4	33.01	24.05	7.97	3625.6	617.9
FCT-3-5	33.01	24.05	7.97	3454.3	588.7
FCT-7-7	33.04	24.04	7.96	3213.8	543.7
FCT-7-8	33.05	24.04	7.97	2979.7	502.4
FCT-7-9	33.05	24.03	7.97	3023.9	508.7
FCT-7-10	33.04	24.04	7.96	3720.2	629.4
FCT-7-11	33.01	24.03	7.96	3727.1	632.9
Average:					583.1
STD:					49.9

Table A-4. O-ring strength data at 700 °C.

Specimen #	Do (mm)	Di (mm)	B (mm)	Fracture Load (N)	σ_{MAX} (MPa)
FCT-3-8	33.01	24.05	7.970	2900.8	494.3
FCT-3-9	33.01	24.05	7.950	2652.1	453.1
FCT-3-10	33.01	24.04	7.970	3081.3	523.9
FCT-3-11	33.01	24.05	7.960	2786.4	475.4
FCT-3-12	33.01	24.05	7.960	2452.0	418.4
FCT-7-12	33.05	24.04	7.950	2656.9	449.1
FCT-7-13	33.04	24.05	7.970	2568.4	435.0
FCT-7-14	33.05	24.04	7.970	2752.3	464.1
FCT-7-15	33.05	24.06	7.970	3418.8	579.3
FCT-7-16	33.05	24.04	7.950	2232.6	377.4
FCT-7-17	33.04	24.04	7.940	3222.5	546.6
FCT-10-6	33.03	23.97	7.970	2574.6	428.7
FCT-10-7	33.03	23.99	7.970	2499.2	418.1
Average:					466.42
STD:					56.84

Table A-5. Chevron notch fracture toughness data.

Specimen #	B (mm)	W (mm)	a ₀ (mm)	a ₁ (mm)	a ₁₁ (mm)	a ₁₂ (mm)	Fracture Load (N)	K _{IC} (MPa*m ^{1/2})
1	2.986	3.997	1.433	3.748	3.716	3.780	18.3	5.84
2	3.001	4.001	1.344	3.711	3.710	3.712	18.9	5.64
3	2.995	3.997	1.372	3.720	3.733	3.707	19.1	5.81
4	2.982	3.997	1.343	3.617	3.558	3.675	19.0	5.55
5	2.976	4.004	1.370	3.675	3.659	3.690	19.3	5.71
6	2.991	4.015	1.410	3.746	3.756	3.736	18.8	5.80
Average:								5.73
STD:								0.11

Table A-6. Vickers hardness data at 300 g indentation load.

Indent #	Ave d (um)	Ave d (mm)	HV (GPa)
1	20.3	0.0203	13.2
2	20.6	0.0206	12.9
3	20.3	0.0203	13.2
4	20.1	0.0201	13.5
5	20.0	0.0200	13.6
Average:	20.3	0.0203	13.3
STD:	0.2	0.0002	0.3

NO. OF
COPIES ORGANIZATION

1 DEFENSE TECHNICAL
(PDF INFORMATION CTR
only) DTIC OCA
8725 JOHN J KINGMAN RD
STE 0944
FORT BELVOIR VA 22060-6218

1 DIRECTOR
US ARMY RESEARCH LAB
IMNE ALC HRR
2800 POWDER MILL RD
ADELPHI MD 20783-1197

1 DIRECTOR
US ARMY RESEARCH LAB
RDRL CIM L
2800 POWDER MILL RD
ADELPHI MD 20783-1197

2 DIRECTOR
US ARMY RESEARCH LAB
RDRL CIM P
RDRL SES P
D DANNA
2800 POWDER MILL RD
ADELPHI MD 20783-1197

ABERDEEN PROVING GROUND

20 DIR USARL
RDRL CIM G (BLDG 4600)
RDRL WM
J MCCAULEY
RDRL WMM
J ZABINSKI
RDRL WMB B
S PIRAINO
RDRL WMB D
P CONROY
C LEVERITT
RDRL WMB E
T JESSEN
J LASALVIA
J SWAB (5)
J SYNOWCZYNSKI
RDRL WMB F
R CARTER
W DEROSSET
RDRL WML E
G OBERLIN
RDRL WMM A
J TZENG
RDRL WMM B
R KASTE
RDRL WMM G
J ANDZELM

INTENTIONALLY LEFT BLANK.